Ordered, Random, Monotonic, and
Non-monotonic Digital Nanodot Gradients

Grant Ongo, [1,2] *Sébastien G. Ricoult,* [2,3] *Timothy E. Kennedy,* [3] *and David Juncker* [1,2,3, *]

[1]Department of Biomedical Engineering, McGill University,
740 Dr. Penfield Avenue, Montreal, Quebec, Canada H3A 0G1
[2]McGill University & Genome Quebec Innovation Centre, McGill University, Montréal, Quebec,
Canada H3A 0G1
[3]McGill Program in Neuroengineering, Department of Neurology and Neurosurgery, Montreal
Neurological Institute, McGill University, 3801 University Ave,
Montreal, Quebec, Canada H3A 2B4

Corresponding Author
David Juncker
Dept. Biomedical Engineering
Micro and Nanobioengineering Laboratory
McGill University
740 Dr. Penfield, room 6206
Montreal, Quebec, Canada, H3A 0G1
Phone: (514) 398-7676, Fax: (514) 398 1790
Email: david.juncker@mcgill.ca

ABSTRACT

Cell navigation is directed by inhomogeneous distributions of extracellular cues. It is well

known that noise plays a key role in biology and is present in naturally occurring

gradients at the micro- and nanoscale, yet it has not been studied with gradients *in vitro*.

Here, we introduce novel algorithms to produce ordered and random gradients of

discrete nanodots – called digital nanodot gradients (DNGs) – according to monotonic

and non-monotonic density functions. The algorithms generate continuous DNGs, with

dot spacing changing in two dimensions along the gradient direction according to

arbitrary mathematical functions, with densities ranging from 0.02% to 44.44%. The

random gradient algorithm compensates for random nanodot overlap, and the

randomness and spatial homogeneity of the DNGs were confirmed with Ripley's K

function. An array of 100 DNGs, each 400 × 400 μm^2, comprising a total of 57 million

200 × 200 nm^2 dots was designed and patterned into silicon using electron-beam

lithography, then patterned as fluorescently labeled IgGs on glass using lift-off

nanocontact printing. DNGs will facilitate the study of the effects of noise and

randomness at the micro- and nanoscales on cell migration and growth.

Introduction

Gradients are fundamental to many phenomena of biology, from directing axonal

navigation during neural development to the differentiation of stem cells in response to

an injury [1,2]. Gradients may occur as either (i) free diffusion gradients, (ii) substrate-

bound gradients, or (iii) a combination of both [3]. Free diffusion gradients can be

generated by cell-excreted proteins that diffuse in the extracellular space. Substrate-

bound gradients arise when proteins are bound to the extracellular matrix or cell

membranes [4,5,6]. To better understand cellular haptotaxis – the directed movement of

a cell or axonal growth cone along a gradient of a substrate-bound guidance cue – many

techniques to generate surface-bound gradients *in vitro* have been developed [7]. Two

classes of concentration gradients exist, namely continuous and digital gradients.

Continuous gradients have protein concentration changing in a constant manner, and

are typically produced by adsorbing molecules from a diffusible gradient. Several

parameters of these gradients have been modulated, including the range and slope,

which was linear, exponential or non-monotonic [8]. For example, linear gradients of the

protein BDNF have been shown to modulate neuron polarization and growth [9] and

linear laminin gradients have been shown to orient rat hippocampal axon specification

based on slope [10]. Secondly, digital gradients which have been recently introduced,

are formed by patterning small dots of protein and varying the density of the dots by

changing their size [11], the spacing between them [12], or both [13]. The advantage of

digital gradients is that they are deterministic, and that the local concentration can be

precisely predicted and does not rely on fluorescence measurements which are prone to

error. Digital gradients have been used to study how retinal ganglion cells identify the

stop zone within graded distributions of repulsive EphrinA5 ligands [13]. However, digital

gradients rarely extend over 1-2 orders of magnitude (OM), whereas it is believed that

the dynamic range of gradients *in vivo* is between 3-4 OM. To overcome these

limitations, we previously developed digital nanodot gradients (DNGs), where the

spacing between nanodots (200 nm in diameter) was changed in two dimensions to

produce a dynamic range exceeding 3 OM. These designs were implemented using a

low-cost, lift-off nanocontact printing method to pattern substrate-bound gradients of

proteins and peptides. We employed these patterns for adhesion and migration studies

of C2C12 myoblasts on RGD peptide and netrin-1 gradients, respectively [14]. For these

experiments, gradients of 400×400 μm^2 were divided into 53 rectangular boxes of fixed

size and density. With this approach, gradients were non-continuous and had stepwise

changes in density. This is most pronounced in low-density regions where the spacing

between nanodots exceeded the dimensions of the box, requiring larger box sizes and

thus creating large "steps" at the bottom of the gradient. This may prove problematic as

cells may fail to sense a discontinuous gradient if they fall into a region of constant

density.

Noise is ubiquitous in biology [15], and modern patterning technologies can be exploited

to introduce defined amounts of noise and randomness into otherwise regular patterns.

The effect of randomness was evaluated in ordered arrays and repetitive patterns with a

constant average density. In one study, disorder was introduced in arrays of 120 nm

dots spaced 300 nm apart by randomly displacing the dot by up to 50% of the spacing to

avoid overlap [16]. While this approach introduced a controlled amount of noise by

restricting the maximum displacement, it was not random since dots were each

contained within the original grid. Nonetheless, cellular adhesion and stem cell

differentiation of osteoblasts were markedly altered as a result of increasing disorder. In

another study, whole proteome analysis of cells grown on the same disordered patterns

resulted in differential expression of certain proteins in the extracellular signal-regulated

kinase (ERK1/2) pathway [17]. Similarly, controlled amounts of topographical noise on

nanogratings of 500 nm ridges and grooves has shown to effect PC12 neuronal cell

alignment to the gratings, focal adhesion maturation and directionality [18].

Randomness and noise are also highly relevant to directed cell migration. The

stochasticity of chemo- and haptotaxis has been well studied, and is apparent from the

random-walk like traces of migrating cells [19]. It is well understood that biological

gradients, which appear continuous, are in fact quantized since they are comprised of

individual molecules adsorbed to a surface. The distribution of these molecules is not

deterministic, but stochastic at the nanoscale. The engagement of receptors from

migrating cells with these guidance cues has been modeled within a stochastic

framework [19,20]. Random variations in the gradient also occur at the microscale *in vivo*

from the local accumulation of chemo- and haptotactic molecules that form concentration

puncta [21]. Gradients formed by the expression of receptors from cells embedded in a

tissue a may become non-monotonic as particular cells over- and under- express a

receptor relative to their position in the gradient [22]. Cells navigating through such a

patchwork of microscale deviations must discriminate against local maxima and minima

to sense the overarching gradient slope. It has been suggested that cells alternate

between periods of sensitization and desensitization and are thereby capable of

maintaining an overall response to long-range gradients [23].

Random pattern generation is well established, however many patterns are not random

in the mathematical sense, and often implement only an approximation of randomness

to varying degrees depending on the needs of the application. Firstly, computers

typically generate 'pseudo-random' numbers that statistically approximate the properties

of true random numbers using an algorithm based on an initial 'random seed' – generally

a random bit. If this random seed is known, the set of pseudo-random numbers can be

replicated. However, for most applications, pseudo-random numbers are

indistinguishable from a true random number.

So-called random dot patterns are widely used in the reproduction of images and

patterns using displays or printers that impose digitization and pixilation. Pixilation

implies that pixels are positioned on a regular grid. Adjusting grayscale images to binary

(black and white pixels) through halftoning is achieved by adjusting the ratio of black and

white pixels in a local area, but if pixels are turned on and off according an ordered

pattern, rendering artifacts (such as Moiré patterns) arise. By locally randomizing the

pixels turned on or off while matching the overall desired grayscale, it is possible to

avoid such rendering artifacts. These 'random-grid' patterns can be generated using an

array of pseudo-random values and a threshold dictated by the local grey value used to

determine which pixels are black or white (Fig. S1) [24]. With this approach, the value of

each pixel is random, while the position of the pixels are fixed to an ordered grid. These

random-grids have found application in the halftoning of images for display or printing

[25] and the generation of random-dot stereograms for depth perception studies [26].

Random dot patterns also comprise dot patterns where the position of the dots is not

constrained to a grid as described previously, but is instead randomized within a given

space. However, pseudo-random distributions of the dots, when seen from afar, can

appear noisy and inhomogeneous to the eye. Therefore, algorithms involving so-called

quasi random numbers (also called low discrepancy sequences) are used to create

patterns with a more uniform distribution that appears visually smooth [27]. "Quasi-

random" is a broad term that encompasses numbers with a disordered distribution that

lie between a (pseudo-)random distribution and a regular distribution [28]; a quasi-

random distribution may closely resemble an ordered distribution than a random

distribution upon close examination. Many different algorithms have been developed to

produce quasi-random numbers. As an example, for liquid crystal displays, quasi-

random dot patterns without overlap are generated by mimicking molecular dynamics in

which two "molecules" cannot occupy the same space [29] or by iteratively repositioning

overlapping dots until overlap is minimized [27].

Both random-grid and quasi-random patterns have been optimized to produce a

pleasing (macroscopic) image to the eye by introducing a controlled amount of

microscale disorder, avoiding both the viewing artifacts of regular arrays and the

inhomogeneity of pseudo-random dot patterns. Cells however are microscopic and

sense their environment at the micro- and nanoscale. At these scales, random grid or

quasi-random distributions can be significantly different from a random one, and may not

adequately reproduce the effect of a random pattern on cells. It is therefore necessary to

establish an algorithm to produce random dot patterns that preserves randomness at the

micro- and nanoscale to study the effect of random *vs.* regular dot patterns on cell

navigation.

Here, we introduce continuous DNGs eliminating the stepwise density changes of the

previously reported "step" design [14] with (i) ordered and (ii) pseudo-random positioning

of nanodots, as well as (iii) non-monotonic DNGs that can be implemented using either

(i) or (ii). We discuss various strategies to create noisy DNGs and outline the challenges

in forming random DNGs with accurate slopes, and describe a novel algorithm with

pseudo-random positioning of the dots and compensating for random, but predictable,

dot overlap to achieve the desired coverage. The slope of random DNGs was measured

and compared to the programmed density function, and their randomness verified using

Ripley's K-function. We generated an array of 100 ordered and random $400 \times 400 \ \mu m^2$

large DNGs made of 200 × 200 nm^2 nanodots, including monotonic and non-monotonic

density curves, with a dynamic ranges spanning from 2.14 to 3.86 OM. Non-monotonic

gradients produced here aim to introduce in a quantitative and repeatable manner

"microscale noise" into surface-bound *in vitro* gradients. The entire array of 100 DNGs

covers a 35 mm^2 area and is comprised of more than 57 million nanodots. The DNG

array was patterned onto a silicon (Si) wafer by electron-beam (e-beam) lithography, and

was transferred onto glass slides by lift-off nanocontact printing of fluorescently labeled

IgGs [14]. The fidelity of the replication process was evaluated by overlaying the DNG

design with fluorescence microscopy images of the printed IgG proteins.

Materials and Methods

Software & Computers

Algorithms were developed in Matlab R2013a (Natick, MA, USA). Scripts of the ordered

and random gradient algorithms are available for download upon request. A spreadsheet

template (Microsoft Excel 2010) of gradient parameters was imported into Matlab for

processing. The output for each gradient was a text file of coordinates formatted as a

Caltech Intermediate Format (CIF) file. CIFs were imported into CleWin Version 4.1

(WieWeb, MESA Research Institute at the University of Twente and Deltamask,

Netherlands). Gradients were exported from CleWin as Bitmap (BMP) image files for

verification of density using ImageJ 1.47 64-bit (National Institutes of Health, USA) and

Matlab. The 100-gradient array was designed in L-edit (Tanner EDA, Monrovia, CA,

USA). All software was run on a 2013 iMac computer with a 3.4 GHz Intel Core i7

processor with 32 GB 1600 MHz DDR3 memory running Windows 7 through a bootcamp

partition.

Electron-Beam Lithography

A 4" Si wafer was coated with PMMA resist and the 100-gradient array was patterned by

e-beam lithography (VB6 UHR EWF, Vistec, Montreal, QC, Canada), followed by

reactive-ion etching (System100 ICP380, Plasmalab, Everett, WA, USA) 100 nm deep

into the Si wafer.

Stamp Fabrication

After cleaning, the Si wafer was coated with perfluorooctyltriethoxysilane (Sigma-Aldrich,

Oakville, ON, Canada) by vapor phase deposition. An accurate polymer copy of the

wafer was obtained after double replication using polydimethylsiloxane (PDMS) and a

UV-sensitive polyurethane as described in [14]. First, a 6 mm layer of 1:10 PDMS (Dow

Corning, Corning, NY, USA) was poured on the wafer inside a Petri dish, followed by

degassing under vacuum in a desiccator for 10 min. Next, the PDMS was cured in an

oven for 24 h at 60 ˚C (VWR, Montreal, QC, Canada), then peeled from the wafer. To

remove uncured monomers and other extractables, the PDMS replica was submersed in

70% ethanol for 24 h then baked at 60˚C for 4 h. Next, a drop of UV sensitive

polyurethane (Norland Optical Adhesive 63 (NOA 63), Norland Products, Cranbury, NJ)

was applied to the PDMS replica and cured by 600 W of UV light (Uvitron International,

Inc., West Springfield, MA) for 30 s. The PDMS was then removed yielding an NOA

replica of the original Si wafer pattern with 200 nm holes [14].

Nanocontact Printing

A flat PDMS stamp was cured against a perfluorooctyltriethoxysilane treated flat Si

wafer. Following removal of the extractables as mentioned above, the flat PDMS stamp

was inked with a 10 µL drop of phosphate buffered saline solution (PBS) containing 25

µg/mL of chicken immunoglobulin G (IgG) conjugated to Alexa Fluor 488 (Invitrogen,

Burlington, ON, Canada). A plasma activated hydrophilic coverslip was then placed on

the drop to spread the solution evenly across the surface of the hydrophobic PDMS

stamp during a 5 min incubation period. After rinsing with PBS and double distilled water

for 15 s each, the inked stamps were briefly dried under a stream of N_2 and immediately

brought into contact with a plasma activated (PlasmaEtch PE-50, PlasmaEtch, Carson

City, NV, USA) NOA master for 5 s. The PDMS and NOA were separated and proteins in

the contact regions were transferred to the NOA. The remaining proteins on the PDMS

were transferred to the final substrate by printing the PDMS stamp for 5 s onto a plasma

activated glass coverslip.

Imaging and Analysis

Images of the original Si master were collected using scanning electron microscopy

(SEM, JEOL, Japan). DNGs of fluorescent IgGs were imaged by fluorescence

microscopy (TE2000 microscope, Nikon, Canada and CoolSNAP HQ^2 camera,

Photometrics, USA). Images of the Si wafer were captured with a Panasonic Lumix GH3

DSLR equipped with an Olympus M. Zuiko Digital ED 60 mm macro lens. Dark field

images were captured with an inspection microscope (LV150A microscope and Digital

Sight DS-Fi1 camera, Nikon, Canada).

Results and Discussion

Ordered Gradient Algorithm

Ordered DNGs with continuously changing density were programmed by forming

columns of nanodots with equal vertical spacing while varying the spacing between

columns horizontally (Fig. 1A). The density of the gradient at any point along the length *l*

is dictated by an input density function *D*, and is realized by placing a single nanodot into

a virtual box to form a unit cell. The dimensions d_i of the unit cell at the i^{th} column of

nanodots are given by the square root of the nanodot area A_{dot} divided by the density

value at the given position (Eq. 1). In this algorithm, the size of the nanodot remains

constant while the dimensions of the unit cell vary for each column of nanodots along the

length.

$$d_i = \sqrt{\frac{A_{dot}}{D(l)}}$$ (1)

The unit cell is largest at low densities and decreases at higher densities, matching the

dimensions of the nanodot at a density equal to one. The unit cell dimensions for each

column are calculated using an iterative approach, starting from the first column of

nanodots at length zero. The position along the length for the next column of nanodots is

given by the cumulative sum of unit cell dimensions (Fig. 1B).

Figure 1: Ordered gradient algorithm for continuously changing density in Digital
Nanodot Gradients (DNGs) using a unit cell approach. *(A) Schematic of a linear*
DNG and unit cell parameters for the i^{th} column of nanodots. (B) Calculation of unit cell
dimensions at each position through an iterative process using the cumulative sum of
unit cell dimensions to determine position along the length.
227

The width of the gradient is divided by d_i to estimate the number of nanodots in the

column. The value of d_i is then recalculated to equally space the integer number of

nanodots along the width, ensuring that the distribution of nanodots is symmetrical. The

unit cells are concatenated to form a column of points in the y direction with constant

spacing as multiples of d_i. The x coordinate for each column is the position l at which the

unit cell dimensions are calculated. Thus, using this algorithm it is easy to form a

gradient with any slope as the size of the unit cell is directly derived from the value of the

density function at a specific position. Fig. 2 shows a linear density curve spanning from

a minimum density D_{min}=*0.01* to a maximum density D_{max}=*0.30* (Eq. 2) with

corresponding unit cell dimensions along the length of the gradient. Eq. 2 is normalized

to span the dynamic range over the total length L=*100 µm* of the gradient.

$$D(l) = (D_{max} - D_{min})\frac{l}{L} + D_{min} \qquad\qquad (2)$$

Figure 2: Programmed and measured density for an ordered linear DNG. *A 100 × 100 µm^2 linear DNG comprised of 0.04 µm^2 nanodots and spanning from 0.01 to 0.30 density. The measured density (left axis) precisely matches the programmed density (R^2=0.9998). The unit cell dimensions (right axis) change with the inverse square root of the density. Top insets show various spacing of nanodots at positions along the DNG.*

To verify that ordered gradients matched the programmed density functions, gradients were exported as bitmap images and the ratio of black to white pixels, averaged over several columns of nanodots, was used to measure density. The resulting gradients were found to match the programmed density functions with high fidelity (*R^2=0.9998*). Using this algorithm, a density of zero cannot be reached, as it would require an infinitely large unit cell. Consequently, when designing gradients of fixed length, the lowest density that is accessible may be limited since large unit cells are required at very low

density.

Random Gradient Algorithm

Naturally occurring gradients appear continuous at the microscale, but are in fact digital

at the scale of molecules and proteins. The diffusion of biomolecules is subject to

Brownian motion, and is therefore expected to be random. In an effort to mimic the

nanoscale noise present *in vivo*, we present an approach to produce DNGs with fully

randomized nanodot positions. Similar to ordered DNGs, random gradients have

increasing density along the length and constant density along the width.

Several strategies were considered to produce randomized DNGs. The first was akin to

the one proposed by Dalby, *et al.* [16] and consisted of starting with a regular distribution

of dots, and randomly displacing the nanodots within their "unit cell" so as to avoid

overlap with neighboring dots. However because this approach only produces a quasi-

random distribution, it was not pursued. A second approach that was considered was to

start with a pseudo-random dot pattern, and then compensate for the overlap by locally

moving dots. This parallels a strategy used in back-lit displays [29], however these

patterns are unsuitable for our application due to the dependence on or optimization for

quasi-random distributions. Whereas we don't see fundamental obstacles in developing

an algorithm to randomly redistribute overlapping dots, such algorithms tend to be

computationally intensive as the position of each dot needs to be tested against each

other dot, and require multiple iterations to achieve the final distribution [27]. We thus

devised a novel algorithm to create pseudo-random nanodot patterns for cell navigation

that could translate arbitrary density functions into random nanodot patterns, and that

was computationally economical.

The algorithm we developed compensates for the random overlap of dots by adding an

excess of dots to achieve the programmed density. The algorithm first defines equally

sized boxes to smoothly replicate the programmed density function without visible steps.

The number of nanodots within each box was calculated based on the density function

with predicted overlap at the box's position, and random *x* and *y* coordinates were

generated for each nanodot. Only the nanodot coordinates were stored. Noteworthy, the

shape of the nanodots can be defined subsequently as the exported CIF file allows

drawing shapes such as circles, polygons, etc. at the stored coordinates, thus making

this approach flexible while reducing the file size and computation time. A consequence

of the random nanodot position is that overlap between nanodots is possible. The

frequency of overlap increases with density, which in turn results in a lower density than

expected based on the surface area of all nanodots. However, because the distribution

of the nanodots is random and the density known, the overlap is predictable, and can be

compensated for, so that the designed DNG matches the density function with high

fidelity. For each box with area A_{box}, we first compute the probability P_{cov} that any given

point in the box is covered by a nanodot of area A_{dot} (Eq. 3).

299
$$P_{\text{cov}} = \frac{A_{dot}}{A_{box}} \qquad (3)$$

301   The probability $P_{not\ cov}$ that this point will *not* be covered by the nanodot is simply

302    $1 - P_{cov}$ (Eq. 4).

304
$$P_{\text{not cov}} = \left(1 - \frac{A_{dot}}{A_{box}}\right) = \frac{A_{box} - A_{dot}}{A_{box}} \qquad (4)$$

306 The probability that this point will not be covered by N nanodots simultaneously can then

307 be found (Eq. 5).

309
$$P_{\text{not cov}} = \left(\frac{A_{box} - A_{dot}}{A_{box}} \right)^{N}$$
(5)

311 To determine the total area of the box covered by nanodots (A_{cov}), the probability that a

312 point *will* be covered is integrated over the area of the box (Eq. 6).

314
$$A_{\text{cov}} = \int_{0}^{A_{box}} (1 - P_{\text{not cov}}) \, dA$$
(6)

316
$$A_{\text{cov}} = A_{box} - \frac{(A_{box} - A_{dot})^{N}}{A_{box}^{N-1}}$$
(7)

318 Eq. 7 can then be solved for N to determine the number of nanodots required for a given

319 A_{cov} in each box.

321
$$N = \frac{\log(1 - A_{\text{cov}} / A_{box})}{\log(1 - A_{dot} / A_{box})}$$
(8)

Using Eq. 8 it is possible to obtain the number of nanodots required for any given density

by substituting D for A_{cov}/A_{box}. As the area occupied approaches the area of the box, the

number of nanodots required increases rapidly, and is infinite for a density of 1. The

maximum density for a DNG was thus set to 0.9999. Without compensation, at density of

0.9999 would require 9,999 nanodots of $200 \times 200 \text{ nm}^2$ to be seeded into a $400 \times 1 \text{ μm}^2$

box to reach this density. When accounting for the overlap, 92,099 nanodots are

required, roughly a tenfold increase. Thus, producing a typical linear gradient, ranging in

density from 0.0002 to 0.4444 requires 1,061,307 nanodots and a computation time of

4.56 min. The ordered algorithm for the same linear gradient requires 885,737 nanodots

and a computation time of 3.88 min. Therefore, the random gradient algorithm overall

required a 19.8% increase in nanodots and a 17.5% increase in computation time using

our workstation. It is expected that the time will increase for random DNGs that reach a

higher density.

We compared the programmed density with the measured density of a monotonic

exponential curve with decay constant *k* (Eq. 9) using both the ordered and random

gradient generation approaches. Eq. 9 is normalized to span the dynamic range over the

length of the gradient. The random gradients produced with this algorithm were found to

follow the programmed curve with high fidelity (R^2 = *0.99986*), and accurately match the

measured density of ordered gradients produced with the same input function (Fig. 3).

$$D(l) = (D_{max} - D_{min}) \frac{e^{k\frac{l}{L}} - 1}{e^k - 1} + D_{min} \qquad (9)$$

345
Figure 3: Ordered and random DNGs superposed with their programmed
exponential density function and actual, measured density. *A 100 × 100 µm²*
exponential (k=3) DNG spanning from a density of 0.01 to 0.30 is shown in ordered (top
half) and random (bottom half) form. The random DNG was programmed by subdividing
it into 1 µm wide boxes with random seeding of nanodots and compensating for overlap.
The measured density follows the programmed exponential curve with high fidelity for
both ordered (R²=0.99996) and random (R²=0.99986) DNGs.

The distribution of neighboring nanodots can be parsed to verify whether it satisfies the

conditions of randomness. Since density changes along the length of the DNG,

randomness can only be assessed in the direction of constant density, perpendicular to

the gradient. The randomness along each box was verified using Ripley's K function

based on the number of nanodots N_{pi} within a distance *s* from the i^{th} point p_i taken over

the sum of all points *n* and normalized by the area *λ* (Eq. 10).

361
$$K(s) = \frac{1}{n} \sum_{i=1}^{n} N_{p_i}(s) / \lambda \qquad (10)$$

For a homogenous, random Poisson distribution, the expected value of Eq. 10 is πs^2.

Deviations from πs^2 indicate regions of clustering or dispersion [31]. Using the

coordinates of nanodots from the DNGs, *K(s)* was found to lie within a 95% confidence

interval obtained from 10 simulations of randomly distributed coordinates at the same

density. This suggests the nanodots are spatially homogenous and randomly distributed

compared to ordered gradients, which lie outside the confidence interval (Fig. 4).

Figure 4: Ripley's K analysis for randomness and spatial homogeneity of a sample
box produced with the ordered and random DNG algorithms. *K(s) for ordered and*
random gradients for a 10 × 400 µm^2 box at 0.20 density are shown. A 95% confidence
interval was calculated as 1.96 times the standard deviation of K(s) from 10 simulations
of randomly distributed points at 0.20 density. The inset shows a magnified portion of the
graph indicated by the box.

Non-monotonic gradients

We have shown that linear and exponential gradients can be produced using either the

ordered or random algorithms. These curves are monotonic, meaning they only ever

increase or decrease. Given the approaches outlined here, more complex gradients can

be easily generated from any input density function, specifically non-monotonous curves.

To study the ability of cells to recognize an average gradient in a non-monotonous

environment, we propose linear and exponential gradients that are superposed with

sinusoidal functions with either constant amplitude, or with linear or exponentially

changing amplitude. In the anticipation of future cell experiments, we also programmed a

series of sinusoids with varying frequency and amplitude, while having an average slope

of zero to act as negative controls.

Here, we demonstrate the flexibility of the algorithms with the production of non-

monotonic gradients. One such gradient produced is a sinusoid with exponentially

increasing amplitude superposed an exponential gradient. Eq. 11 gives the input density

function for such a curve, where A is the amplitude, B is the number of oscillations, and

k_1 and k_2 are the decay constants for the average gradient and amplitude of the sinusoid,

respectively.

397
$$D(l) = (D_{max} - D_{min})\frac{e^{k_1\frac{l}{L}} - 1}{e^{k_1} - 1} + A\sin\left(2\pi B\frac{l}{L}\right)\frac{e^{k_2\frac{l}{L}} - 1}{e^{k_2} - 1} + D_{min} \qquad (11)$$

Figure 5. Non-monotonic random DNG superposed with its density function and actual, measured density. *A 100 x 100 μm^2 non-monotonic DNG. The programmed density function (line) is a sinusoid (A=0.10, B=20) with an average exponential trend (k$_1$=3) and exponentially increasing amplitude (k$_2$=3). Measured density from bitmap (circles) accurately follows the programmed function (R^2=0.9988). Insets show close-up views of nanodots and reveal increasing overlap of nanodots at higher densities.*

One-Hundred-Gradient Array

The flexibility of the gradient algorithms and the fabrication method discussed below was leveraged by producing an array of 100 distinct gradients within a 35 mm^2 area (Fig. 6, Table. S1). The array is comprised of 20 ordered and 80 random gradients, with densities ranging from 0.0002 to 0.4444 for a maximum dynamic range of 3.85 OM. For ordered gradients, this corresponds to a maximum pitch of 14.8 μm at low density, and

100 nm at high density. The minimum density is limited by the size of the cell and its

capacity to sense the gradient, *i.e.* the cell will not sense the gradient if dot spacing

exceeds one third the size of the cell, which we previously assessed using the migratory

response of C2C12 myoblasts [14]. The maximum density is defined by the resolution of

e-beam lithography, which limits the minimum pitch to 100 nm. To address how

randomness affects cell navigation, 20 gradients (10 linear and 10 exponential) were

produced as both ordered (#1-20) and random (#81-100) gradients. This portion of the

array will serve to address gradient sensing mechanics for cell migration that may arise

from either (i) the absolute concentration of the gradient at a given location or (ii) the

concentration ratio between the cell's leading and trailing edges.

The other 60 gradients are non-monotonic and random. These consist of 14 sinusoids

with no average slope (#21-34) that serve as controls. These vary in frequency and

amplitude, and may have constant or increasing amplitude along their length. Controls

for ordered gradients were designed in our prior work. The remaining 46 gradients (#35-

80) have sinusoidal curves with various levels of complexity. These include sinusoids

with linearly (#41-60) and exponentially (#61-80) increasing average density, and non-

monotonic functions with linearly increasing amplitude and average density (#35-36) and

exponentially increasing amplitude and average density (#37-40) to demonstrate the

flexibility of this new approach in gradient generation. As discussed, the sinusoidal

curves with different amplitude and frequency may introduce obstacles for cells trying to

sense the overarching gradient, and replicate effects that may occur due to cell

"mosaicism" in a controlled manner.

Figure 6: Density functions of the array of 100 DNGs. *Each box shows the density function of one gradient. Functions 1-20 were*
produced with the ordered gradient algorithm (red), and functions 21-100 were produced with the random gradient algorithm (blue).
Functions 1-10 and 81-90 are linear. Functions 11-20 and 91-100 are exponential. Functions 21-34 are sinusoidal with no slope
(controls), where 21-30 have linearly increasing amplitude and 31-34 have constant amplitude. Functions 35-36 feature a linear slope
superposed with a sinusoid that has linearly increasing amplitude. Functions 37-40 feature an exponential slope superposed with a
sinusoid that has exponentially increasing amplitude. Functions 41-60 have a constant slope superposed with a sinusoid of constant
amplitude. Functions 61-80 are exponential slopes superposed with sinusoids of constant amplitude.

Gradient Array Fabrication

The hundred-gradient array was etched 100 nm deep into a Si wafer by e-beam

lithography (Fig. 7). The integrity of individual dots for ordered and random gradients

was confirmed by scanning electron microscopy (SEM) (Fig. 8).

Figure 7: Optical images of the 100-gradient-array. *The 100 DNGs were patterned*
into a Si wafer using e-beam lithography. (A) Image of all gradients; scale bar is 1 mm.
(B) Dark-field image of DNG 67 which is a random sinusoid with exponentially increasing
average density; scale bar is 100 μm.
10

11
Figure 8: Nanodot distribution in ordered and random DNGs. *SEMs of ordered (A-D)*
and random (E-H) exponential gradients at low (A,B,E,F) and high (C,D,G,H) densities.
(H) highlights the random overlap between nanodots that is compensated for by the
random DNG algorithm. Scale bars are 10 um (top row) and 500 nm (bottom row).

To translate the etched Si wafer into substrate-bound protein gradients, we employed

lift-off nanocontact printing [14]. First, a PDMS intermediate replica was produced,

followed by a second replication into low-cost Norland Optical Adhesive. A flat PDMS

stamp was inked with a protein solution, and through contact with the plasma-activated

NOA lift-off stamp, a monolayer of protein was selectively removed from the surface of

the flat stamp leaving behind the digital nanodot protein pattern. Next, the flat PDMS

stamp was brought into contact with a plasma-activated glass slide to transfer the DNG

pattern. To confirm the accuracy of the replication and printing process, images of the

design and the printed protein DNG were digitally overlapped and compared (Fig. 9),

revealing a high fidelity between the two patterns.

Figure 9: The printed nanodot pattern accurately replicates the design. *Bitmap*
image of the programmed design colored in red (A, D) compared with a fluorescent
image of nanocontact printed IgG by lift-off (B, E, green) and merged (C, F). In the inset
(E), out of ~1000 spots, 21 are missing, indicating that the replication works well. Scale
bars A-C are 10 µm, scale bars D-F are 2 µm.

The pattern overlay in Fig. 9 was characterized by thresholding the printed image with

boundaries of 31 and 255 in ImageJ and comparing it to the bitmap image (Fig. S3). The

total number of nanodots is difficult to determine owing to the random overlap, but we

estimate that there are ~1000 spots, and using the above threshold, 21 were not found

in the print. Overall, the transfer process is thus accurate to ~98% in this example. Dust

particles on the Si wafer or on the intermediate PDMS replica, or mechanical damage

due to the replication process could account for the absence of these protein dots.

Whereas the fidelity of the replication and printing process is thus high, it might be

improved further by employing more durable polymers during the replication process as

well as by working in a cleanroom environment throughout.

Conclusion

Patterned substrate-bound protein gradients are a valuable tool to study a number of

biological processes such as neuronal development or regeneration. The novel

algorithms presented here, providing pseudo-randomness at a scale commensurate to

the cellular level, can provide control over geometry and noise in DNGs. Combined with

high-throughput patterning, an array of one hundred DNGs with linear, exponential, and

non-monotonic slopes featuring 57 million spots over an area of 35 mm^2 can be

patterned at once in a matter of minutes. The diversity of DNGs shown here will help

study and quantify the mechanisms by which cells sense and navigate through

immobilized gradients. There are many opportunities for refining digital nanodot patterns.

Firstly, to mimic the self-repellent nature of proteins adsorbing to surfaces, it might be

useful to develop an algorithm that prevents, or limits, the overlap of nanodots.

Secondly, whereas here two sinusoidal curves were superposed in one direction, such

curves might be generated in two perpendicular directions and create two- dimensional

navigation landscape while better mimicking local accumulation of guidance cues as

puncta. Thirdly, it might be possible to program density functions that introduce clusters

of noise that more accurately replicate the noise and mosaicism imposed by individual

cells *in vivo* which can extend over tens of micrometers. Fourthly, it should be possible to

pattern overlapping DNGs of different proteins that run in the same, or different

directions, as well as produce any type of navigational landscapes that are found *in vivo*

simply by converting the recorded densities into digital nanodot patterns, following the

trend of rapid prototyping of replicas of living tissues [32]. Before expanding the nanodot

patterning, it will be important to test and validate the current DNGs and establish the

optimal conditions along with the suitable non-patterned reference surfaces for each

study [33].

Acknowledgments

We acknowledge Nabila Zaman for her help with gradient algorithms, and Marta

Garnelo-Abellanas and Veronique Laforte for proofreading this article.

References

1. McLaughlin T, O'Leary DDM (2005) Molecular gradients and development of retinotopic maps. Annu Rev Neurosci 28: 327-355.
2. Chung BG, Flanagan LA, Rhee SW, Schwartz PH, Lee AP, et al. (2005) Human neural stem cell growth and differentiation in a gradient-generating microfluidic device. Lab on a Chip 5: 401-406.
3. Goodman CS (1996) Mechanisms and molecules that control growth cone guidance. Annual Review of Neuroscience 19: 341-377.
4. Kim BK, Lee JW, Park PJ, Shin YS, Lee WY, et al. (2009) The multiplex bead array approach to identifying serum biomarkers associated with breast cancer. Breast Cancer Res 11: R22.
5. Lander AD, Nie Q, Wan FYM (2002) Do morphogen gradients arise by diffusion? Developmental Biology 247: 471-471.
6. Gurdon JB, Bourillot PY (2001) Morphogen gradient interpretation. Nature 413: 797-803.
7. Keenan TM, Folch A (2008) Biomolecular gradients in cell culture systems. Lab on a Chip 8: 34-57.
8. Joanne Wang C, Li X, Lin B, Shim S, Ming G-l, et al. (2008) A microfluidics-based turning assay reveals complex growth cone responses to integrated gradients of substrate-bound ECM molecules and diffusible guidance cues. Lab on a Chip 8: 227-237.
9. Mai J, Fok L, Gao HF, Zhang X, Poo MM (2009) Axon Initiation and Growth Cone Turning on Bound Protein Gradients. Journal of Neuroscience 29: 7450-7458.
10. Dertinger SKW, Jiang XY, Li ZY, Murthy VN, Whitesides GM (2002) Gradients of substrate-bound laminin orient axonal specification of neurons. Proceedings of the National Academy of Sciences of the United States of America 99: 12542-12547.
11. Von Philipsborn AC, Lang S, Bernard A, Loeschinger J, David C, et al. (2006) Microcontact printing of axon guidance molecules for generation of graded patterns. Nature Protocols 1: 1322-1328.
12. Coyer SR, García AJ, Delamarche E (2007) Facile Preparation of Complex Protein Architectures with Sub-100-nm Resolution on Surfaces. Angewandte Chemie International Edition 46: 6837-6840.
13. von Philipsborn AC, Lang S, Loeschinger J, Bernard A, David C, et al. (2006) Growth cone navigation in substrate-bound ephrin gradients. Development 133: 2487-2495.
14. Ricoult SG, Pla-Roca M, Safavieh R, Lopez-Ayon GM, Grütter P, et al. (2013) Large Dynamic Range Digital Nanodot Gradients of Biomolecules Made by Low-Cost Nanocontact Printing for Cell Haptotaxis. Small 9: 3308-3313.
15. Raser JM, O'Shea EK (2005) Noise in gene expression: Origins, consequences, and control. Science 309: 2010-2013.
16. Dalby MJ, Gadegaard N, Tare R, Andar A, Riehle MO, et al. (2007) The control of human mesenchymal cell differentiation using nanoscale symmetry and disorder. Nature Materials 6: 997-1003.
17. Kantawong F, Burgess KEV, Jayawardena K, Hart A, Burchmore RJ, et al. (2009) Whole proteome analysis of osteoprogenitor differentiation induced by disordered nanotopography and mediated by ERK signalling. Biomaterials 30: 4723-4731.
18. Tonazzini I, Meucci S, Faraci P, Beltram F, Cecchini M (2013) Neuronal differentiation on anisotropic substrates and the influence of nanotopographical noise on neurite contact guidance. Biomaterials 34: 6027-6036.

19. Dickinson R, Tranquillo R (1993) A stochastic model for adhesion-mediated cell random motility and haptotaxis. Journal of Mathematical Biology 31: 563-600.

20. Smith JT, Elkin JT, Reichert WM (2006) Directed cell migration on fibronectin gradients: Effect of gradient slope. Experimental Cell Research 312: 2424-2432.

21. Weber M, Hauschild R, Schwarz J, Moussion C, de Vries I, et al. (2013) Interstitial Dendritic Cell Guidance by Haptotactic Chemokine Gradients. Science 339: 328-332.

22. Sweetser DA, Birkenmeier EH, Hoppe PC, McKeel DW, Gordon JI (1988) Mechanisms underlying generation of gradients in gene expression within the intestine: an analysis using transgenic mice containing fatty acid binding protein-human growth hormone fusion genes. Genes & Development 2: 1318-1332.

23. Ming GL, Wong ST, Henley J, Yuan XB, Song HJ, et al. (2002) Adaptation in the chemotactic guidance of nerve growth cones. Nature 417: 411-418.

24. Pappas TN (1994) Digital Halftoning Techniques for Printing. Icps '94: The Physics and Chemistry of Imaging Systems - Is&T's 47th Annual Conference, Vols I and Ii: 468-471.

25. Ulichney R (1987) Digital halftoning: MIT press.

26. Dev P (1975) Perception of Depth Surfaces in Random-Dot Stereograms - Neural Model. International Journal of Man-Machine Studies 7: 511-528.

27. Imamichi T, Numata H, Mizuta H, Ide T (2011) Nonlinear Optimization to Generate Non-Overlapping Random Dot Patterns. Proceedings of the 2011 Winter Simulation Conference (Wsc): 2414-2425.

28. Dalal IL, Stefan D, Harwayne-Gidansky J (2008) Low Discrepancy Sequences for Monte Carlo Simulations on Reconfigurable Platforms. 2008 International Conference on Application-Specific Systems, Architectures and Processors: 108-113.

29. Chang JG, Su MH, Lee CT, Hwang CC (2005) Generating random and nonoverlapping dot patterns for liquid-crystal display backlight light guides using molecular-dynamics method. Journal of Applied Physics 98.

30. Thimbleby HT, Inglis S, Witten IH (1994) Displaying 3d Images - Algorithms for Single-Image Random-Dot Stereograms. Computer 27: 38-&.

31. Kiskowski MA, Hancock JF, Kenworthy AK (2009) On the Use of Ripley's K-Function and Its Derivatives to Analyze Domain Size. Biophysical journal 97: 1095-1103.

32. Derby B (2012) Printing and Prototyping of Tissues and Scaffolds. Science 338: 921-926.

33. Ricoult SG, Thompson-Steckel G, Correia JP, Kennedy TE, Juncker D (2014) Tuning cell–surface affinity to direct cell specific responses to patterned proteins. Biomaterials 35: 727-736.

1   **Supplementary Material**
2
3

4
Figure S1: Random gradients produced by a random matrix threshold approach. A
matrix of pseudo-random numbers is generated. Values greater than or equal to the
density threshold are set to 0 (white), while values less than the threshold are set to 1
(black). The binary array can then be exported directly as a bitmap image file. Each
nanodot is represented by one pixel. Thus, for a 400 × 400 µm^2 sized area with 200 ×
200 nm^2 nanodots, a 2000 × 2000 matrix with 4 million values is required. This approach
does not provide a fully random configuration since nanodots are aligned to a grid. While
these patterns appear random to the eye, the underlying grid might be sensed at the
cellular scale. Theoretically, it is possible to further randomize the position of dots by
subdividing the area, e.g. using a 50 nm grid to position and draw 200 × 200 nm^2 pixels,
but this would come at the cost of increased computational requirements and the
possibility   of   overlap   between   adjacent   dots.

18 *Figure S2: Ordered and random measured density matches programmed density*
19 *over full range.* *Linear gradients from densities of 0.01 to 0.99 were shown to match*
20 *(dots) the programed functions (line) with high fidelity for both ordered (R^2 = 0.9988) and*
21 *random (R^2 = 1.0000) gradients. Using either approach, a high dynamic range can be*
22 *achieved with near perfect match to the programmed function.*

25 *Figure S3: Image processing procedure to assess alignment of the DNG design*
26 *and print.* *The fluorescent image of nanocontact printed IgG was first thresholded in*
27 *ImageJ with boundary values of 31 and 255. The image was then transformed to binary*
28 *and the binary values inverted to facilitate visualization. The edited fluorescent image*
29 *(green) was then merged with the bitmap (red) and yellow dots, indicative of non-printed*
30 *dots, were counted to determine to what extent the print matched the design.*