Synthesis of extracellular stable gold nanoparticles by *Cupriavidus metallidurans* CH34 cells

(preprint)

Francisco Montero-Silva

Laboratorio de Microbiología Molecular y Biotecnología Ambiental, Departamento de Química,

Universidad Técnica Federico Santa María, Valparaíso, Chile.

Abstract

The biogenic synthesis of metallic nanoparticles is of increasing interest. In this report, the synthesis of

gold nanoparticles by the model heavy metal-resistant strain *Cupriavidus metallidurans* CH34 and

Escherichia coli strain MG1655 was studied. For the synthesis of AuNPs, bacterial cells and the

secretomes were incubated with Au(III) ions, revealing that only CH34 cells were capable of producing

dispersions of AuNPs. Comparative bioinformatic analysis of the proteomes from both strains showed

potential CH34 proteins that may be electron donors for the reduction of extracellular Au(III) ions and for

the biosynthesis of gold nuggets in nature. Powder X-ray diffraction demonstrated that biogenic AuNPs

are composed of face-centered cubic gold with a crystallinity biased towards {111} planes. Transmission

electron microscopy images showed that AuNPs morphology was dominated by triangular and decahedral

nanostructures. EDX and FT-IR spectra showed the presence of sulfur and vibrations associated to

proteins on the AuNPs surface. Based on these results, and analyses of previous genomic and proteomic

data, a mechanism for extracellular gold reduction and synthesis of AuNPs by strain CH34 is proposed.

Average AuNPs diameter was obtained by nanoparticle tracking analysis, dynamic light scattering and

analysis of electron microscopy images. DLS studies showed that biogenic AuNPs colloids are stable

after exposure to ultrasound, high ionic strength and extreme pH conditions, and revealed the presence of

basic groups associated to the AuNPs surface. Electrophoretic and dynamic light scattering indicated that

biogenic dispersions of AuNPs are stabilized by a steric mechanism. The AuNPs produced by *C.

metallidurans* CH34 are not cytotoxic towards bacterial cells, in contrast to biogenic AgNPs. These stable

non-toxic biogenic AuNPs have potential clinical applications including the development of topic

delivery formulations and optical biosensors.

Keywords

Cupriavidus metallidurans CH34, gold nanoparticles, biogenic AuNPs, extracellular nanoparticles.

1 Introduction

The need for cost-effective eco-friendly synthesis of metallic nanoparticles has established new methods to replace the chemical synthesis. The biogenic synthesis of nanoparticles is of increasing interest. Bacteria are versatile biocatalysts for the detoxification and biotransformation of heavy metals and aromatic compounds [1–8]. Microbial systems have been selected for the synthesis of nanoparticles due to their detoxification mechanisms of metallic ions through extracellular or intracellular reduction. The biogenic synthesis of metallic nanoparticles by diverse microorganisms has been described [9, 10]. The synthesis of gold nanoparticles by *Pseudomonas*, *Shewanella* and *Streptomyces* strains has been reported [11–15].

C. metallidurans is a model heavy metal-resistant bacterium that harbours gene clusters enabling detoxification of diverse heavy metal ions and complexes [1, 2, 16, 17]. Interestingly, *C. metallidurans* is also involved in the biogeochemical cycle of gold. The presence of *C. metallidurans* cells in biofilms that covered the surface of gold grains has been reported [18, 19]. Transcriptomic analysis suggested that oxidative stress and heavy metal resistances genes including an Au-specific operon were involved in Au reduction by *C. metallidurans* [19]. Recently, the formation of gold nanoparticle and microparticle aggregates onto the surface *C. metallidurans* biofilms has been reported [20].

The aim of this study was to obtain a stable dispersion of AuNPs by *C. metallidurans* CH34 cells. Bacterial cultures were fractionated and exposed to a gold aqueous solution. Using this procedure extracellular dispersions of NPs were obtained. The biogenic colloid of dispersed AuNPs was characterized by surface plasmon spectroscopy, dynamic and electrophoretic light scattering and nanoparticle tracking analysis. Solid state AuNPs were characterized by powder X-ray diffraction, Fourier transform infrared spectroscopy and TEM. The stability of the colloid was characterized by electrophoretic and dynamic light scattering. A synthesis mechanism is proposed. Finally, the cytotoxic effect of the biogenic gold NPs on bacterial growth was evaluated.

2 Experimental

2.1 Materials

Solid $HAuCl_4 \cdot 3 H_2O$ (99.9% purity) was obtained from Sigma Aldrich (Saint Louis, MO, USA). NaCl, NaOH and KCl were obtained from Merck (Darmstadt, Germany). Beef extract and yeast extract were acquired from Becton Dickinson (Cockeysville, MD, USA) and agar solid medium was obtained from Merck (Darmstadt, Germany). Biogenic AgNPs (40 nm average diameter) were recovered from fungal *Fusarium oxysporum* filtrates [13].

2.2 Biosynthesis of gold nanoparticles

C. metallidurans CH34 [21] and *E. coli* MG1655 [22] were grown in a low ionic strength medium with meat extract (20 g L^{-1}) and yeast extract (20 g L^{-1}) [23]. Biogenic synthesis of gold

nanoparticles was done according to methods A and B [13], with modifications (Fig. 1S). Method A evaluates the effect of bacterial biomass on the biogenic synthesis of AuNPs and method B evaluates the effect of the bacterial extracellular medium on the gold reduction process. In method A, the biomass (40 mL) was directly exposed to a gold solution achieving a final concentration of 2 mM. In method B, the bacterial biomass was used to obtain bacterial filtrates that were exposed to a gold solution (2 mM). In both methods, cell cultures grown until stationary phase were used as starting bacterial biomass. For the method A, cells were collected by centrifugation and washed 3 times with doubly deionized water. Cell pellet was suspended in doubly deionized water and diluted up to a concentration of 3.3×10^9 CFU mL^{-1}. The bacterial suspension was exposed to $AuCl_4^-$ (2 mM) and then incubated during 96 h in darkness without shaking at 30° C. The $HAuCl_4$ stock solution (40 mM) was previously adjusted to pH 7 with NaOH. To recover the biogenic AuNPs colloid, the bacterial suspension was centrifuged at $5,000 \times g$ during 10 min and the supernatant was filtered using a 0.45 μm pore size nitrocellulose membrane. The dispersion of biogenic AuNPs were recovered in the permeate fraction. For method B, cells from a stationary phase bacterial culture were collected by centrifugation and washed 3 times with doubly deionized water. The cell pellet was suspended in doubly deionized water and diluted up to a concentration of 6×10^9 CFU mL^{-1}. To obtain the bacterial secretome, the biomass was incubated during 3 days in flasks with shaking (150 rpm) at 30° C. Cells were centrifuged at $5,000 \times g$ during 10 min and the supernatant was recovered and filtered using a 0.2 μm pore size nitrocellulose membrane. The bacterial secretomes were recovered [24] and incubated with $AuCl_4^-$ (2 mM) during 96 h in darkness without shaking at 30° C.

2.3 Characterization of biogenic gold nanoparticles

The UV-visible absorbance spectra of gold nanoparticles were obtained at room temperature with an Agilent 8453 spectrophotometer equipped with a diode array (Palo Alto, CA, USA). The hydrodynamic diameter (Z-Ave) and dispersion index (PdI) of the biogenic dispersions were determined by dynamic light scattering (DLS) measurements, and zeta-potentials (ζ-potentials) were measured by electrophoretic light scattering using a ZetaSizer Nano ZS instrument (Malvern, Worcestershire, UK). Additional particles size distributions and concentration were determined by nanoparticle tracking analysis (NTA) technology using a NanoSight LM20 device (Amesbury, UK). In all cases, temperature was fixed at 25° C and 1 mM KCl solution was used as dissolvent. The morphology and size distribution of the biogenic AuNPs was observed by transmission electron microscopy. Images were obtained using a Carl Zeiss (Libra) transmission electron microscope (TEM) operating at 120 keV and analyzed using the software ImageJ 1.47v. To obtain the images, one drop of the biogenic AuNPs was deposited on a carbon-coated parlodion film supported in 300 mesh copper grids (Ted Pella, Redding, CA, USA). For the EDX measurements, biogenic AuNPs were extensively washed with MilliQ water, concentrated by centrifugation, and deposited on a carbon grid. Spectra were acquired with a Carl Zeiss, EVO MA-10 device. Solid state characterization was done to powder samples of the biogenic AuNPs. To obtain the powder samples, colloidal dispersions of biogenic AuNPs were centrifuged at $20,000 \times g$ during 20 min and then washed 3 times with MilliQ water. The sediment containing the biogenic AuNPs was lyophilized

and then analyzed by powder X-ray diffraction (XRD) and Fourier transform infrared (FT-IR)

spectrometry. Powder XRD spectra were obtained in a Shimadzu XRD 6000 diffractometer using Cu Kα

radiation (1.5406 Å) operating at 30 mA and 40 kV. The scan speed was 0.02 degree min^{-1} and the time

constant was 2 s. FT-IR spectra of powder samples were recorded using a Bomem MB spectrometer in the

4,000-400 cm^{-1} frequency range using an attenuated total reflectance mode. A total of 250 scans and a

resolution of 4 cm^{-1} were employed to obtain each spectrum. The concentrations of gold and silver in the

nanoparticles dispersions were determined by inductively coupled plasma (ICP) Perkin Elmer Optima

3000 DV spectrometry.

2.4   Cytotoxic activity assays

The cytotoxic effect of biogenic AuNPs and Ag nanoparticles on *E. coli* MG1655 cells was

evaluated by minimal inhibition concentration (MIC) measurements. The MIC of the nanoparticles was

determined by the microdilution method [25]. The liquid medium used in these assays contained meat

extract (5 g L^{-1}) and yeast extract (5 g L^{-1}) and was inoculated to a final bacterial concentration of 5×10^5

CFU mL^{-1}. Aliquots of the bacterial cultures were exposed to equivalent concentrations of gold and silver

NPs obtained by serial dilutions of the colloids. The initial concentration of both Au and Ag nanoparticles

was 14.5 μg mL^{-1}. The MIC was defined as the minimum concentration of nanoparticles that inhibit the

bacterial growth in liquid medium after an incubation period of 16 h at 37° C. The effect of gold and

silver nanoparticles on bacterial growth was visually analyzed on agar plates. The solid medium

contained meat extract (5 g L^{-1}), yeast extract (5 g L^{-1}) and agar (15 g L^{-1}). The agar plates (85 mm

diameter) were seeded with an aliquot (100 μL) of 1×10^8 CFU mL^{-1} of MG1655 cells and exposed to

AuNPs and AgNPs. The nanoparticle dispersions were serially diluted and drops containing 20 μL of each

dilution were poured onto the previously seeded solid medium. The agar plates were incubated during 16

h at 37° C.

3   Results

3.1   Biogenic synthesis of gold nanoparticles

Using CH34 cell suspension incubated with Au(III) ion (2 mM) during 96 h in darkness

supernatant of the CH34 culture developed a purple color indicating the production of an extracellular

dispersion of biogenic AuNPs (Fig. 1a). No viable cells were detectable after the biosynthesis process,

whilst cell viability of CH34 cultures without Au(III) ions remained constant.   In contrast to *C.*

metallidurans CH34, development of a purple color in the supernatant of *E. coli* MG1655 cells was not

detected and accumulation of a dark sediment was observed (Fig. 1a). Viable *E. coli* cells were not

detected after incubation with Au(III) ions , whereas cell viability of control cultures without Au(III) ions

remained constant.

The potential reduction of Au(III) ions and production of biogenic AuNPs by the secretomes of

strains CH34 and MG1655 was studied. Incubation of both bacterial secretomes with Au(III) ions did not

developed a purple color and appearance of an insoluble yellow gold complex was observed (not shown).

3.2   Characterization of biogenic AuNPs in colloidal state

The visible spectrum of the supernatants of CH34 cultures obtained after incubation with Au(III)

ions showed a maximum absorbance peak at a wavelength of 536 nm (Fig. 1b). No absorbance was

detected in the supernatants of *E. coli* MG1655 cells (Fig. 1b) and the secretomes of both strains. These

results indicate that under these conditions only CH34 cells are capable to produce extracellular

dispersions of biogenic AuNPs.

The biogenic colloid obtained with CH34 cells was characterized by light scattering

measurements. Dynamic and electrophoretic light scattering measurements indicated that the AuNPs

dispersion presents a Z-Ave of 126.4 nm (Fig. 2a) with an associated zeta-potential of -0.25±3 mV.

Additional measurements using NTA technology correlated well with previous DLS results. Mean

diameter of the biogenic colloid was 124 nm, with a mode of 78 nm and the presence of minor

populations of 302 nm and 405 nm (Fig. 2b, video in Supplemental information). The concentration of

biogenic AuNPs diluted 4 times with 1 mM KCl and reported by NTA was 4.19×10^9 particles mL^{-1}.

Therefore, the biogenic colloid has a concentration of 1.68×10^9 particles mL^{-1}.

The stability of the biogenic AuNPs colloid after exposure to ultrasound, extreme pH conditions

and elevated ionic strength was evaluated by DLS measurements (Table 1). Hydrodynamic diameter of

control samples was 126.4 nm with associated PdI of 0.284. Ultrasound treatment did not affect the size

distribution the colloid, with associated Z-Ave and PdI values of 124.9 nm and 0.279, respectively. The

stability of the colloid was also evaluated in the presence of highly acidic (pH 1) and alkaline (pH 10)

conditions. The presence of an acidic environment reduced Z-Ave from 126.4 nm to 114.6 nm, whilst an

alkaline environment increased Z-Ave to 135.3 nm. In both cases, PdI of the colloid increased to 0.33.

Finally, the presence of elevated ionic strength (500 mM NaCl) showed no-effect on the size distribution,

with associated Z-Ave and PdI values of 127.5 nm and 0.286, respectively.

3.3   Characterization of biogenic AuNPs in solid state

The degree of crystallinity of the biogenic gold nanoparticles was determined by powder X-ray

diffraction measurements. The XRD spectrum showed Bragg´s reflection peaks at positions $2\theta = 38.1°$,

44.3°, 64.6°, 77.5° and 81.7° (Fig. 3a). The position of the reflection peaks can be associated to the

diffraction planes (111), (200), (220), (311) and (222) of the crystalline unit cell of elemental gold as seen

in the 04-0784 file of the JCPDS database. The all odd or all even Miller index values of the diffraction

planes indicate that the biogenic gold nanoparticles have a face-centered cubic (*fcc*) crystalline structure.

The calculated lattice constant (a) using the distance value (d) associated to the {220} diffraction planes

was estimated to be 4.1 Å. This value is in agreement with the standard report value from JCPDS (a = 4.1

Å) confirming that the biogenic AuNPs synthetized by strain CH34 are composed of elemental gold. The

predominant diffraction plane present in the sample was determined. The ratio of the intensity peaks

(200), (220), (311) and (222) with respect to (111) are lower than the ratio intensity reported for the

standard JCPDS gold sample (0.25 versus 0.52, 0.18 versus 0.32, 0.14 versus 0.36, and 0.04 versus 0.12,

respectively). This analysis indicates that the crystallographic structure of the AuNPs synthetized by

strain CH34 is dominated by {111} diffraction planes.

The morphology and size distribution of the biogenic AuNPs were studied by transmission

electron microscopy. The morphology of the biogenic AuNPs was dominated by decahedral and triangular

nanostructures (Fig. 3b). The metallic core of the biogenic AuNPs showed diameters $\geq$ 10 nm, with 85%

of the particles showing a diameter between 20 and 60 nm. Few truncated triangular nanoplates with a

diameter $\geq$ 70 nm were also observed. The mean of the frequency distribution was 37.1 ± 15.5 nm. Further

analysis of TEM images showed that the perimeter of all nanoparticles was surrounded by a layer of non-

metallic material with a width of ~ 4.5 nm (Fig. 3b (Inset)). These structures could be organic capping

ligands adsorbed on the surface of the biogenic AuNPs.

Energy-dispersive X-ray analysis of biogenic AuNPs showed the presence of sulfur atoms

associated to AuNPs (Fig. 4a). Afterwards, the chemical nature of the biogenic AuNPs was characterized

by FT-IR spectroscopy (Fig. 4b). The absorbance spectrum of the biogenic AuNPs showed several peaks

that correlate with the molecular vibrations of functional groups from proteins; therefore, the biogenic

AuNPs spectrum was analyzed based on the FT-IR spectrum of bovine serum albumin [26]. The broad

band between 3700 and 3000 cm^{-1} corresponds to the vibrations of water molecules and protein functional

groups. The higher peak at 3450 cm^{-1} corresponds to the OH$\cdots$ stretching vibrations of residual H_2O (v_{O-}

$_H...$). The following absorption bands at lower energy correspond with the amide A group of vibrations.

These are the stretching vibrational modes of the N-H group of the peptide bonds ($v_{N-H}...$; 3290 cm^{-1} and

v_{N-H}; 3100 cm^{-1}). The absorption band between 3000 and 2800 cm^{-1} corresponds with the stretching

vibrations of the C-H groups. The broad band between 1600 and 1700 cm^{-1} corresponds with the

molecular vibrations of the amide I group. This group includes the stretching modes of the hydrogen bond

acceptor ($v_{C=O}...$; 1675, 1665 and 1630 cm^{-1}) and hydrogen bond non-acceptor ($v_{C=O}$; 1695 cm^{-1})

molecular vibrations associated to the C=O group of the peptide bonds. The absorption band between

1600 and 1500 cm^{-1} corresponds with the molecular vibrations of the amide II group. This group includes

the bending modes of the hydrogen bond acceptor ($\delta_{N-H}...$; 1550 and 1520 cm^{-1}) and hydrogen bond non

acceptor (δ_{N-H}; $\approx$ 1500 cm^{-1}) molecular vibrations associated to the N-H group of the peptide bonds. A

similar absorbance pattern has been described when albumin is adsorbed onto chemically synthetized

AuNPs [27, 28]. The absorption band between 1400 and 1360 cm^{-1} corresponds with the symmetric

stretch ($v^S_{COO^-}$) of the carboxylate groups of Asp and Glu residues. These global data suggests that

dispersion of biogenic AuNPs synthetized by the strain CH34 are covered by a layer of proteins.

3.4   Effect of biogenic AuNPs on bacterial growth

The effect of biogenic gold and silver NPs on bacterial cell growth was compared. The

microdilution method indicated that the biogenic AuNPs did not affect the growth of *E. coli* MG1655

cultures, while biogenic AgNPs showed a MIC of 0.45 μg mL^{-1} (Fig. 5). This value is in agreement with

previous reports [10, 29, 30]. Similar results were observed with the biogenic Au and Ag nanoparticles on

solid growth medium. These results indicate that biogenic AuNPs synthetized by *C. metallidurans* strain

CH34 do not affect the growth of *E. coli* MG1655. Therefore, these biogenic AuNPs are not cytotoxic for

E. coli cells.

4   Discussion

In this study, stable dispersions of AuNPs were produced after reduction of Au(III) ions by *C.*

metallidurans CH34 cells. The production of biogenic metallic nanoparticles occurred by redox agents

from the cellular biomass. Exposure of *C. metallidurans* CH34 and *E. coli* MG1655 secretomes to

Au(III) ions did not produce AuNPs dispersions. Therefore,under these experimental conditions both

strains do not secrete enzymes or compounds to the extracellular medium that allow reduction of Au(III)

ions with concomitant generation of biogenic AuNPs dispersion. Reduction of Au(III) ions by *E. coli* cells

has been reported, but the AuNPs aggregate onto the bacterial cells and do not generate extracellular

dispersions [31]. Production of extracellular AuNPs by cyanobacterium *Plectonema boryanum* UTEX485

cells has been described [32].

The results indicate that the mechanism of Au(III) reduction during the biogenic synthesis of

extracellular dispersions of AuNPs implies the oxidation of molecules that are produced by strain CH34

and are absent in strain MG1655. We propose that the reduction of Au(III) ions and production of

extracellular dispersions of AuNPs is mediated by oxidation of macromolecules that are located in the

cellular membranes or periplasm of CH34 cells and absent in MG1655 cells. A comparative bioinformatic

analysis of both genomes indicated that, in contrast to strain MG1655, *C. metallidurans* CH34 possess a

cop gene cluster that encodes periplasmic and outer membrane sulfur rich proteins that contain a

significant number of methionine and cysteine residues (CopA 36 Met/1 Cys, CopB 52 Met, CopC 7 Met,

CopK 9 Met, CopJ 4 Met/2 Cys) (Fig. 6). Proteomic studies of strain CH34 demonstrated the constitutive

expression of the periplasmic protein CopK and the outer membrane bound protein CopB [33]. The

presence of Cop sulfur rich proteins at the membranes and periplasm of the bacterial cell might allow the

direct interaction between the sulfur atoms of methionine and cysteine residues and the diffusive Au(III)

ions present in the extracellular space. It is proposed that extracellular Au(III) ions oxidize the sulfur atom

of the methionine residues into methionine-sulfoxide. This event has been described for methionine

residues from ribonuclease A and glycyl-D,L-methionine dipeptide, with concomitant production of Au(0)

[34–36]. In addition, Au(III) ions may oxidize cysteine to cystine, and subsequently to sulfonic acid [37,

38]. After interaction, the reduced gold atoms might return to the medium and generate nucleation centers

that finally evolve into extracellular AuNPs dispersions (Fig. 6). Moreover, redox cycling enzymes, like

methionine sulfoxide reductases, might reduce and recover the functionality of oxidized sulphur

containing residues. In this manner, this analysis suggests that redox cycling of the Met residues of CopA

and CopB are especially involved in the reduction of extracellular gold ions and the biosynthesis of gold

nuggets in nature.

Analysis of electron microscopy images showed that nanoparticles morphology was dominated

by decahedral and triangular structures. The origin of these structures may occur by interaction of ultra-

small tetrahedral nanoparticles [39-41]. The tetrahedral morphology becomes unstable when
nanoparticles reach diameters close to 10 nm. Then, the interaction of five tetrahedral units lowers down
the surface area allowing the formation of decahedral structures [39] (Fig. 3b and Fig. 6). On the other
hand, the presence of major triangular nanoplates has been attributed to a slow kinetic process during the
nanoparticles formation [42]. After long periods, the interaction of decahedra like structures serve as
nucleation centers that finally evolve into triangular and truncated triangular structures. We propose that
the synthesis mechanism of biogenic AuNPs involves an initial step where small tetrahedral nanoparticles
are generated. The interaction of small tetrahedral units evolves into decahedral structures. As observed
by TEM, one population of these decahedral structures may serve as nucleation centers for the subsequent
biosynthesis of triangular nanoplates and other population might evolve up to reach diameters close to 50
nm.

Analysis of XRD spectrum showed a bias towards {111} diffraction planes. This non-ideal
behavior may be attributed to morphological properties of the decahedral and triangular nanoparticles
observed by TEM. Decahedral structures are formed by the interaction of five tetrahedral particles
bounded by its lower energy {111} twin planes [39, 41]. Also the major faces of triangular and triangular
like nanoplates present a {111} crystallite structure [40, 43, 44]. As the surface area of these
nanostrucutres is dominated by {111} diffraction planes, we propose that morphology of the biogenic
AuNPs contains the information that enhanced the signal of the (111) diffraction plane, leading to a XRD
spectrum dominated by {111} diffraction planes as described above.

Comparison of the size distribution of biogenic AuNPs obtained by light scattering
measurements using two different technologies showed similar results. Dynamic light scattering
measurements indicated that the Z-Ave of the particles was 126.4 nm, whilst NTA indicated that the mean
diameter of the distribution was 124 nm. These results do not correlate with size distribution deduced
from TEM images (average diameter of 37.1 nm). The difference between diameters determined by TEM
and light scattering technologies can be explained by the characteristics of each technique. Size
distributions obtained from TEM images are proportional to the length of the nanoparticles and do not
include the width of capping ligands adsorbed onto the AuNPs surface. Also, size distributions obtained
from TEM images reflect the results from the analysis of AuNPs samples that are in a solid static state. In
contrast, size distributions obtained from DLS and NTA measurements are proportional to the volume of
the nanoparticles and represent the accumulation of multiple measurements obtained from a nanoparticles
population in dynamic state. Size distributions obtained by these light scattering technologies reveal
intermolecular interactions between AuNPs dispersions that leads to multiple equilibriums and are finally
detected as an average of major sized nanoparticles complexes [28, 45-47]. Therefore, size distributions
of colloids obtained by DLS and NTA contain information about interacting and non-interacting
nanoparticles, and detect small amounts of larger nanoparticles that are outside the normal distribution
and are not captured in TEM images [48].

The stability of the biogenic AuNPs colloid was determined by exposure to ultrasound, extreme
pH conditions and elevated ionic strength by DLS measurements. Ultrasound fuses non-functionalized
AuNPs into worm like units with concomitant increment in Z-Ave and PdI [49]. Exposure to prolonged
sonication periods did not change the Z-Ave nor PdI values, indicating that the biogenic colloid is not

sensitive to ultrasound perturbation by the protective effect of a layer of capping ligands that cover the

surface of the biogenic particles. Further Z-Ave determinations after exposure to extreme pH conditions

indicated that the biogenic colloid endures the chemical perturbance of acidic and alkaline environments

and reveals the presence of basic functional groups located at the surface of the nanoparticles. Exposure

to an acidic environment reduced the hydrodynamic diameter and increased the PdI of the colloid. We

propose that low pH conditions generate a re-distribution of the interacting nanoparticles population.

Protonation of basic groups of the capping ligands increase the electrostatic repulsion of at least one

fraction of the interacting nanoparticles. This process probably generate a novel group of non-interacting

nanoparticles that splits the population distribution and is detected as a reduction in Z-Ave and an

increment in the PdI of the colloid. On the other hand, alkaline environment increased both Z-Ave and

PdI of the colloid. Deprotonation of basic groups might reduce the electrostatic repulsion of at least one

fraction of the interacting nanoparticles. This process would generate a group of highly-interacting

nanoparticles that splits the former population distribution and is detected as an increment in both Z-Ave

and PdI of the biogenic colloid. The presence of high concentrations of NaCl did not alter the size

distribution of the colloid. This result demonstrates that biogenic AuNPs do not flocculate nor aggregate

in the presence elevated ionic strength conditions, and indicates that biogenic AuNPs colloids obtained

with *C. metallidurans* CH34 cells would remain stable even under physiological conditions (150 mM

NaCl).

The stability mechanism of the biogenic colloid was studied by electrophoretic and DLS

measurements in the presence and absence of ionic strength. Elevated absolute ζ-potential values ($\geq$ 30

mV) are indicative of electrostatic repulsion between nanoparticles and therefore to the stability of the

colloid mediated by an electrostatic repulsion mechanism [50]. In this case, the presence of ionic strength

shields the electrostatic repulsion between the particles, and induces flocculation and increment in the Z-

Ave of the colloid. The ζ-potential of biogenic AuNPs synthetized by strain CH34 was ~ 0 mV (-0.25±3

mV), and Z-Ave did not change in the presence of 500 mM NaCl (Table 1). These results indicate that the

biogenic colloid is not stabilized by electrostatic repulsion forces, and suggests that the stability

mechanism is based on the steric repulsion between the capping ligands of the nanoparticles. Stabilization

by steric repulsion mechanism indicates that elevated molecular weight ligands are adsorbed onto the

surface of the biogenic AuNPs [28, 51], and supports the FT-IR results that reveal the presence of

functional groups of proteins.

5   Conclusions

Stable colloidal dispersions of AuNPs were obtained after incubation of *C. metallidurans* CH34

cells with Au(III). Potential CH34 proteins that may act as electron donors for the reduction of Au(III)

ions during the biosynthesis process and a mechanism for the production of extracellular AuNPs by strain

CH34 were proposed.

Average diameter of the biogenic AuNPs in colloidal state obtained from light scattering

measurements (DLS and NTA) was four times higher than diameter of the biogenic AuNPs in solid state

obtained from analysis of TEM images. This comparison shows that the size distributions obtained from

analyses of nanoparticles in colloidal and solid state are not comparable.

The biogenic colloid is stable under chemical and physical perturbations, which is useful for

potential applications. Clinical applications include the topic delivery of bioactive compounds that may

interact with the protein layer of the nanoparticles and the development of colorimetric biosensors that

require colloidal probes with elevated stability and absorptivity.

Acknowledgements

The authors acknowledge CONICYT Ph.D, Mecesup CD FSM1204, RIABIN and UTFSM-PIIC (FMS)

fellowships, FAPESP (ND), MCTI/CNPq (ND) and IQ-UNICAMP (ND), NanoBioss (IQ-UNICAMP)

(ND), FONDECYT (1110992 & 1151174) (MS), USM (131562, 131342 & 131109) (MS), CN&SB (MS)

and Mecesup CD FSM1204 (MS, FSM) grants. The funders had no role in study design, data collection

and analyses, decision to publish, or preparation of the manuscript.

References

Monchy, S., Benotmane, M.A., Janssen, P., *et al.*: 'Plasmids pMOL28 and pMOL30 of *Cupriavidus metallidurans* are specialized in the maximal viable response to heavy metals', *J. Bacteriol.*, 2007, **189**, pp. 7417–7425.

Rojas, L.A., Yáñez, C., González, M., Lobos, S., Smalla, K., Seeger, M.: 'Characterization of the metabolically modified heavy metal-resistant *Cupriavidus metallidurans* strain MSR33 generated for mercury bioremediation', *PLoS One*, 2011, **6**, p. e17555.

Altimira, F., Yáñez, C., Bravo, G., González, M., Rojas, L.A., Seeger, M.: 'Characterization of copper-resistant bacteria and bacterial communities from copper-polluted agricultural soils of central Chile', *BMC Microbiol.*, 2012, **12**, p. 193.

Chirino, B., Strahsburger, E., Agulló, L., González, M., Seeger, M.: 'Genomic and functional analyses of the 2-aminophenol catabolic pathway and partial conversion of its substrate into picolinic acid in *Burkholderia xenovorans* LB400', *PLoS One*, 2013, **8**, p. e75746.

Ramanathan, R., Field, M.R., O'Mullane, A.P., Smooker, P.M., Bhargava, S.K., Bansal, V.: 'Aqueous phase synthesis of copper nanoparticles: a link between heavy metal resistance and nanoparticle synthesis ability in bacterial systems', *Nanoscale*, 2013, **5**, pp. 2300–2306.

Okamoto, A., Kalathil, S., Deng, X., Hashimoto, K., Nakamura, R., Nealson, K.H.: 'Cell-secreted flavins bound to membrane cytochromes dictate electron transfer reactions to surfaces with diverse charge and pH', *Sci. Rep.*, 2014, **4**, p. 5628.

Fuentes, S., Méndez, V., Aguila, P., Seeger, M.: 'Bioremediation of petroleum hydrocarbons: catabolic genes, microbial communities, and applications', *Appl. Microbiol. Biotechnol.*, 2014, **98**, pp. 4781–4794.

Fuentes, S., Barra, B., Caporaso, J.G., Seeger, M.: 'From rare to dominant: a fine-tuned soil bacterial bloom during petroleum hydrocarbon bioremediation', *Appl. Environ. Microbiol.*, 2016, **82**, pp. 888–896.

Durán, N., Marcato, P.D., Durán, M., Yadav, A., Gade, A., Rai, M.: 'Mechanistic aspects in the biogenic synthesis of extracellular metal nanoparticles by peptides, bacteria, fungi, and plants', *Appl. Microbiol. Biotechnol.*, 2011, **90**, pp. 1609–1624.

Rai, M., Birla, S., Ingle, A.P., *et al.*: 'Nanosilver: an inorganic nanoparticle with myriad potential applications', *Nanotechnol. Rev.*, 2014, **3**, pp. 281–309.

Kashefi, K., Tor, J.M., Nevin, K.P., Lovley, D.R.: 'Reductive precipitation of gold by dissimilatory Fe(III)-reducing Bacteria and Archaea', *Appl. Environ. Microbiol.*, 2001, **67**, pp. 3275–3279.

Karthikeyan, S., Beveridge, T.J.: '*Pseudomonas aeruginosa* biofilms react with and precipitate toxic soluble gold', *Environ. Microbiol.*, 2002, **4**, pp. 667–675.

Durán, N., Marcato, P.D., Alves, O.L., Souza, G.I.H. De, Esposito, E.: 'Mechanistic aspects of biosynthesis of silver nanoparticles by several *Fusarium oxysporum* strains', *J. Nanobiotechnol.*, 2005, **3**, p. 8.

Thakkar, K.N., Mhatre, S.S., Parikh, R.Y.: 'Biological synthesis of metallic nanoparticles',

Nanomedicine, 2010, **6**, pp. 257–262.

15 Derakhshan, F.K., Dehnad, A., Salouti, M.: 'Extracellular biosynthesis of gold nanoparticles by
metal resistance bacteria: *Streptomyces griseus*', *Synth React Inorg Met -Org Chem*, 2012, **42**, pp.
868–871.

16 Nies, D.H.: 'Efflux-mediated heavy metal resistance in prokaryotes', *FEMS Microbiol. Rev.*,
2003, **27**, pp. 313–339.

17 Taghavi, S., Lesaulnier, C., Monchy, S., Wattiez, R., Mergeay, M., van der Lelie, D.: 'Lead(II)
resistance in *Cupriavidus metallidurans* CH34: interplay between plasmid and chromosomally-
located functions', *Antonie Van Leeuwenhoek*, 2009, **96**, pp. 171–182.

18 Reith, F., Etschmann, B., Grosse, C., *et al.*: 'Mechanisms of gold biomineralization in the
bacterium *Cupriavidus metallidurans*', *Proc. Natl. Acad. Sci.*, 2009, **106**, pp. 17757–17762.

19 Reith, F., Rogers, S.L., McPhail, D., Webb, D.: 'Biomineralization of gold: biofilms on
bacterioform gold', *Science*, 2006, **313**, pp. 233–236.

20 Fairbrother, L., Etschmann, B., Brugger, J., Shapter, J., Southam, G., Reith, F.:
'Biomineralization of gold in biofilms of *Cupriavidus metallidurans*', *Environ. Sci. Technol.*,
2013, **47**, pp. 2628–2635.

21 Mergeay, M., Nies, D., Schlegel, H.G., Gerits, J., Charles, P., Van Gijsegem, F.: '*Alcaligenes
eutrophus* CH34 is a facultative chemolithotroph with plasmid-bound resistance to heavy metals',
J. Bacteriol., 1985, **162**, pp. 328–334.

22 Baba, T., Ara, T., Hasegawa, M., *et al.*: 'Construction of *Escherichia coli* K-12 in-frame, single-
gene knockout mutants: the Keio collection', *Mol. Syst. Biol.*, 2006, **2**, p. 2006.0008.

23 Parra, C., Montero-Silva, F., Henríquez, R., *et al.*: 'Suppressing bacterial interaction with copper
surfaces through graphene and hexagonal-boron nitride coatings', *ACS Appl. Mater. Interfaces*,
2015, **7**, pp. 6430–6437.

24 Song, C., Kumar, A., Saleh, M.: 'Bioinformatic comparison of bacterial secretomes', *Genomics
Proteomics Bioinformatics*, 2009, **7**, pp. 37–46.

25 Wiegand, I., Hilpert, K., Hancock, R.E.W.: 'Agar and broth dilution methods to determine the
minimal inhibitory concentration (MIC) of antimicrobial substances', *Nat. Protoc.*, 2008, **3**, pp.
163–175.

26 Grdadolnik, J., Maréchal, Y.: 'Bovine serum albumin observed by infrared spectrometry. I.
Methodology, structural investigation, and water uptake', *Biopolymers*, 2001, **62**, pp. 40–53.

27 Tsai, D.-H., Delrio, F.W., Keene, A.M., *et al.*: 'Adsorption and conformation of serum albumin
protein on gold nanoparticles investigated using dimensional measurements and *in situ*
spectroscopic methods', *Langmuir*, 2011, **27**, pp. 2464–2477.

28 Shi, X., Li, D., Xie, J., Wang, S., Wu, Z., Chen, H.: 'Spectroscopic investigation of the
interactions between gold nanoparticles and bovine serum albumin', *Chinese Sci. Bull.*, 2012, **57**,
pp. 1109–1115.

29 Marcato, P.D., Durán, M., Huber, S.C., *et al.*: 'Biogenic silver nanoparticles and its antifungal
activity as a new topical transungual drug', *J. Nano Res.*, 2012, **20**, pp. 99–107.

30 Huang, J., Zhan, G., Zheng, B., *et al.*: 'Biogenic silver nanoparticles by Cacumen Platycladi

extract: synthesis, formation mechanism, and antibacterial activity', *Ind. Eng. Chem. Res.*, 2011, **50**, pp. 9095–9106.

Du, L., Jiang, H., Liu, X., Wang, E.: 'Biosynthesis of gold nanoparticles assisted by *Escherichia coli* DH5α and its application on direct electrochemistry of hemoglobin', *Electrochem. commun.*, 2007, **9**, pp. 1165–1170.

Lengke, M.F., Ravel, B., Fleet, M.E., Wanger, G., Gordon, R.A., Southam, G.: 'Mechanisms of gold bioaccumulation by filamentous cyanobacteria from gold(III)-chloride complex', *Environ. Sci. Technol.*, 2006, **40**, pp. 6304–6309.

Monchy S, Benotmane M a., Wattiez R, van Aelst S, Auquier V, Borremans B, et al: 'Transcriptomic and proteomic analyses of the pMOL30-encoded copper resistance in *Cupriavidus metallidurans* strain CH34'. *Microbiology* 2006, **152**, pp. 1765–1776.

Isab, A., Sadler, P.: 'Reactions of gold(III) ions with ribonuclease A and methionine derivatives in aqueous solution', *Biochim. Biophys. Acta*, 1977, **492**, pp. 322–330.

Glišić, B.Đ., Rychlewska, U., Djuran, M.I.: 'Reactions and structural characterization of gold(III) complexes with amino acids, peptides and proteins', *Dalt. Trans.*, 2012, **41**, pp. 6887–6901.

Glišic, B.D., Rajkovic, S., Stanic, Z.D., Djuran, M.I.: 'A spectroscopic and electrochemical investigation of the oxidation pathway of glycyl-D,L-methionine and its N-acetyl derivative induced by gold(III)', *Gold Bull.*, 2011, **44**, pp. 91–98.

Shaw III, C.F., Cancro, M.P., Witkiewicz, P.L.: 'Gold (III) oxidation of disulfides in aqueous solution', *Inorg. Chem.*, 1980, **19**, pp. 3198–3201.

Witkiewicz, P.L., Shaw, C.F.: 'Oxidative cleavage of peptide and protein disulphide bonds by gold(III): a mechanism for gold toxicity', *J. Chem. Soc. Chem. Commun.*, 1981, pp. 1111–1114.

Johnson, C.L., Snoeck, E., Ezcurdia, M., *et al.*: 'Effects of elastic anisotropy on strain distributions in decahedral gold nanoparticles', *Nat. Mater.*, 2008, **7**, pp. 120–124.

Sun, J., Guan, M., Shang, T., Gao, C., Xu, Z.: 'Synthesis and optical properties of triangular gold nanoplates with controllable edge length', *Sci. China Chem.*, 2010, **53**, pp. 2033–2038.

Walsh, M.J., Yoshida, K., Kuwabara, A., Pay, M.L., Gai, P.L., Boyes, E.D.: 'On the structural origin of the catalytic properties of inherently strained ultrasmall decahedral gold nanoparticles', *Nano Lett.*, 2012, **12**, pp. 2027–2031.

Mukherjee, P., Roy, M., Mandal, B.P., *et al.*: 'Synthesis of uniform gold nanoparticles using non-pathogenic bio-control agent: evolution of morphology from nano-spheres to triangular nanoprisms', *J. Colloid Interface Sci.*, 2012, **367**, pp. 148–152.

Chen, S., Carroll, D.L.: 'Synthesis and characterization of truncated triangular silver nanoplates', *Nano Lett.*, 2002, **2**, pp. 1003–1007.

Montes, M.O., Mayoral, A., Deepak, F.L., *et al.*: 'Anisotropic gold nanoparticles and gold plates biosynthesis using alfalfa extracts', *J. Nanoparticle Res.*, 2011, **13**, pp. 3113–3121.

Filipe, V., Hawe, A., Jiskoot, W.: 'Critical evaluation of nanoparticle tracking analysis (NTA) by NanoSight for the measurement of nanoparticles and protein aggregates', *Pharm. Res.*, 2010, **27**, pp. 796–810.

Doane, T., Burda, C.: 'Nanoparticle mediated non-covalent drug delivery', *Adv. Drug Deliv. Rev.*,

490    2012, **65**, pp. 607–621.

491 47  Fu, C., Yang, H., Wang, M., Xiong, H., Yu, S.: 'Serum albumin adsorbed on Au nanoparticles:

492    structural changes over time induced by S–Au interaction', *Chem. Commun.*, 2015, **51**, pp. 3634–

493    3636.

494 48  Brar, S.K., Verma, M.: 'Measurement of nanoparticles by light-scattering techniques', *Trends*

495    *Anal. Chem.*, 2011, **30**, pp. 4–17.

496 49  Radziuk, D., Grigoriev, D., Zhang, W., Su, D., Möhwald, H., Shchukin, D.: 'Ultrasound-assisted

497    fusion of preformed gold nanoparticles', *J. Phys. Chem. C*, 2010, **114**, pp. 1835–1843.

498 50  Doane, T.L., Chuang, C.-H., Hill, R.J., Burda, C.: 'Nanoparticle ζ-potentials', *Acc. Chem. Res.*,

499    2012, **45**, pp. 317–326.

500 51  El Badawy, A.M., Luxton, T.P., Silva, R.G., Scheckel, K.G., Suidan, M.T., Tolaymat, T.M.:

501    'Impact of environmental conditions (pH, ionic strength, and electrolyte type) on the surface

502    charge and aggregation of silver nanoparticles suspensions', *Environ. Sci. Technol.*, 2010, **44**, pp.

503    1260–1266.

509　**Table 1 Dynamic light scattering measurements of biogenic AuNPs dispersions produced by *C.***

510　***metallidurans* CH34 after exposure to ultrasound, extreme pH and elevated ionic strength (average**

511　**of 3 measurements)**

Experimental condition	Z-Ave (d.nm)	PdI
Control	126.4	0.284
Ultrasound	124.9	0.279
pH 1	114.6	0.332
pH 10	135.3	0.334
NaCl (500 mM)	127.5	0.286

Fig. 1 Optical properties of gold nanoparticles synthetized by bacteria. (a) Reduction of $AuCl_4^-$ by *C.*

metallidurans CH34 (left) and *E. coli* MG1655 cells (right). (b) Visible spectra of the aqueous fractions

obtained from *C. metallidurans* CH34 and *E. coli* MG1655 supernatants.

Fig. 2 Comparison of size distributions of gold nanoparticles synthetized by *C. metallidurans* CH34

obtained by light scattering measurements. (a) Size distribution obtained by dynamic light scattering

(DLS) measurements. Reported Z-Ave of 126.4 nm and PdI of 0.284 (b) Size distribution and particles

concentration obtained by nanoparticle tracking analysis (NTA). Reported mean of 124 nm, mode of 78

nm and SD of 88 nm.

Fig. 3 Physical properties of biogenic gold nanoparticles synthetized by *C. metallidurans* CH34. (a)

Powder X-ray diffraction spectrum. (b) Size frequency distribution and morphology of the AuNPs

determined by analysis of TEM images (n=142). Mean of 37.1 with SD of 15.5 nm. Inset: representative

field of biogenic AuNPs.

Fig. 4 Chemical characterization of biogenic AuNPs synthetized by *C. metallidurans* CH34. (a) EDX

spectrum of biogenic AuNPs. (b) FT-IR spectrum of biogenic nanoparticles (straight line), and bovine

serum albumin adapted from [26] (dotted line).

Fig. 5 Minimal inhibitory concentration of AuNPs on planktonic cultures of *E. coli* MG1655. a,

AuNPs produced by *C. metallidurans* CH34 b, AgNPs produced by *Fusarium oxysporum.* nd: no growth

detected. Inset: growth of *E. coli* MG1655 cells on agar plates after exposure to an equivalent amount of

NPs.

Fig. 6 Proposed mechanism for the reduction of Au(III) ions by *C. metallidurans* CH34 cells and

subsequent formation of extracellular dispersions of AuNPs.

Fig. 1S Workflow of cell culture fractionation.

Interactive media S1. Video showing light dispersion and Brownian motion of biogenic AuNPs

synthetized by *C. metallidurans* CH34 cells.

EXTRACELLULAR

CYTOSOL