Scaffold pore geometry influences bone-like tissue formation in dynamic cell culture conditions

Marina Rubert*, Ph.D. [1*], Jolanda Rita Vetsch Ph.D. [1], Iina Lehtoviita [1], Marianne Sommer Ph.D.[2],

André R Studart, Ph.D. [2], Ralph Müller, Ph.D. [1], Sandra Hofmann, Ph.D. [1,3]

Affiliations:

[1] Institute for Biomechanics, ETH Zurich, Zurich, Switzerland.

[2] Complex Materials, Department of Materials, ETH Zurich, 8093 Zurich, Switzerland.

[3] Department of Biomedical Engineering, Eindhoven University of Technology and Institute for Complex Molecular Systems, Eindhoven, The Netherlands.

E-mail addresses:

Marina Rubert: marina.rubert@hest.ethz.ch. Phone: +41 (0) 44 633 91 93. Fax: +41 (0) 44 633 15 73

Jolanda Rita Vetsch: jvetsch@ethz.ch. Phone: +41 (0) 44 633 78 44. Fax: +41 (0) 44 633 15 73

Iina Lehtoviita: iina.lehtoviita@hest.ethz.ch. Phone: +41 44 633 71 16. Fax: +41 (0) 44 633 15 73Marianne Sommer: mariannewinksommer@gmail.com. Phone: +41 (0) 44 633 70 91. Fax: +41 (0) 44 633 15 45

André R. Studart: andre.studart@mat.ethz.ch. Phone: +41 (0) 44 633 70 50. Fax: +41 (0) 44 633 15 45

Ralph Müller: ram@ethz.ch. Phone: +41 (0) 44 633 6271. Fax: +41 (0) 44 633 15 73

Sandra Hofmann: S.Hofmann@tue.nl. Phone: +31 (0) 40 247 3494. Fax: +31 (0) 40247 3744

*Corresponding author

Abstract

Cells sense and respond to scaffold pore geometry and mechanical stimuli. Many fabrication methods used in bone tissue engineering render structures with poorly controlled pore geometries. Given that cell-scaffold interactions are complex, drawing a conclusion on how cells sense and respond to uncontrolled scaffold features under mechanical loading is difficult. Here, monodisperse templated scaffolds (MTSC) were fabricated and used as a well-defined porous scaffolds to study the effect of dynamic culture conditions on bone-like tissue formation. Human bone marrow derived stromal cells were cultured on MTSC or conventional salt-leached scaffolds (SLSC) for up to 7 weeks, either under static or dynamic conditions. Spinner flask bioreactors were used to provide dynamic culture conditions to apply mechanical loading on the seeded cells through wall shear stress. The influence of controlled spherical pore geometry of MTSC subjected to static or dynamic conditions on the cell response, specifically on bone-like tissue formation, structure and distribution was investigated. As revealed by collagen staining, mRNA expression levels and micro-computed tomography (micro-CT) images, dynamic conditions supported osteoblast cell differentiation and promoted a more regular extracellular matrix (ECM) formation and mineral distribution in both scaffold types compared to static conditions. The results showed that regulation of bone-related genes and the amount and the structure of mineralized ECM were dependent on scaffold pore geometry and the mechanical cues provided by the two different culture conditions. Under dynamic conditions, SLSC favored osteoblast cell differentiation and ECM formation, while MTSC enhanced ECM mineralization. The spherical pore shape in MTSC supported a more trabecular bone-like structure under dynamic conditions compared to MTSC statically cultured or to SLSC under either static or dynamic conditions. These results suggest that cell activity and bone-like tissue formation is driven not only by the pore geometry but also by the mechanical environment. This should be taken into account in the future design of complex scaffolds, which should favor cell differentiation while guiding the formation, structure and distribution of the engineered bone tissue. This could help to mimic the anatomical complexity of the bone tissue structure and to adapt to each bone defect needs.

Keywords: bone tissue engineering, silk fibroin, scaffolds, pore geometry, static and spinner flask bioreactors, osteogenic differentiation, micro-computed tomography.

1. Introduction

Restoring large bone defects remains a clinical challenge [1]. Although autologous bone grafts are the gold standard treatment, problems related to donor site morbidity and limited amount of available bone tissue remain a major drawback [2]. Implantation of biocompatible scaffolds that support the migration of the patients' own cells, their proliferation and new bone tissue formation (BTF) at the defect site could represent a cost- and time-effective alternative [3].

Numerous *in vitro* and *in vivo* studies have focused on the optimization of scaffold architectures to improve the biological response and to fulfill a variety of functional requirements [4-10]. Despite evidence that scaffold architecture affects its performance and cellular response, it is still not clear what the best pore size, shape and interconnectivity of the scaffold architecture should be. One reason is that the selection of an optimal bone graft varies from patient to patient and relies on, the defect size and shape, on the anatomical location and the specific biomechanical or functional requirements at that site [11]. Given that cell-scaffold interactions are complex and that the biological mechanism by which the scaffold mediates BTF is still missing [12], drawing a general conclusion on how cells sense and respond to a certain architectural scaffold feature is difficult [11]. This becomes even more challenging if one considers the poorly controlled structure of scaffolds typically used for bone tissue engineering. Many of the fabrication methods used in bone tissue engineering (e.g. salt leaching, gas foaming, lyophilization) often fail to allow an independent variation of individual geometric parameters [13]. To better understand cell-scaffold interactions and thus advance on the development of new strategies to enhance BTF, it is necessary to use methods that enable the fabrication of reproducible and geometrically controlled structures. Moreover, the use of fabrication methods that allow a systematic fabrication and evaluation of the influence of individual scaffold parameters on cell behavior and promoting BTF would simplify scaffold optimization to fulfill the requirements of the patient and the mechanical conditions at the defect site.

The next generation of three dimensional (3D) scaffolds to enhance *in vivo* BTF aims at supporting the amount of bone tissue formed but also at closely mimicking the anatomical organization of bone tissue and its extracellular matrix (ECM) at the defect site [14]. Attention has been given to the

stimulating and guiding role of the geometrical design of scaffolds [15-25]. *In vitro* and *in vivo* studies have suggested that the structure of engineered bone-like tissue can be modulated by controlling the scaffold pore diameter [21, 24, 26, 27], the channel orientation [16] and the porous scaffold architecture [17, 20]. *In vitro,* two-dimensional pore geometry and surface curvature have further shown to have a strong influence on cell viability [18], cell proliferation [15, 22, 25] and differentiation [19, 25] or overall tissue formation [15, 22, 25]. Cell-independent mineral nucleation was shown to be regulated by material surface curvature [19, 28]. It has been suggested that controlling the 3D scaffold pore geometry has a major impact on the bioactivity of a scaffold towards stem cell differentiation into bone tissue forming cells and subsequent ECM formation and mineralization [23]. In that study, silk fibroin (SF), a widely-used material for bone tissue engineering applications [29-31], was selected as material for scaffold fabrication. A new fabrication method for SF scaffolds with a highly controlled and monodisperse porous architecture was developed [23], which were referred to by the authors as inverse opal scaffolds. Here we name them, for consistency to the salt leached scaffolds based on the porogen, monodisperse template scaffolds (MTSC). A systematic evaluation of physical features and biological response of MTSC was performed relative to conventional salt-leached SF scaffolds (SLSC). The inverse opal method used poly(caprolactone) (PCL) as spherical monodisperse pore template. MTSC result in a close packed and regular spherical pore arrangement. While keeping comparable stiffness, roughness and mean pore diameter, MTSC showed a monodisperse pore diameter distribution, regular spherical shapes and lower overall porosity compared to SLSC [23]. While no differences were observed in cell proliferation, human bone marrow derived stromal cells (hBMSCs) cultured on MTSC under static conditions produced significantly more matrix mineralization compared to cells cultured on SLSC [23].

In addition to scaffold stiffness and topography (pore geometry), cells sense and respond to changes in their mechanical environment [32]. Spinner flask bioreactors have been used in tissue engineering to overcome nutrient constraints through large scaffolds but also to induce shear stresses *in vitro* through generation of increased fluid flow. Fluid-induced shear stress has been shown to alter the cytoskeletal composition of osteoblastic cells [33] and to induce osteoblast cell differentiation [34] and ECM mineralization [35-37]. Although substrate geometry and shear stresses have been shown to guide the

osteoblast cell differentiation, so far studies were limited to the investigation of these two components independently.

Here we investigated whether dynamic cell culture conditions, generated by culturing hBMSC in spinner flask bioreactors, play a role on the osteogenic cell fate and on the spatial organization of mineralized tissue within 3D SF scaffolds exhibiting either spherical and monodisperse (MTSC) or faceted and polydisperse (SLSC) porous architectures. Furthermore, we investigated whether scaffold type and shear stress could have a synergistic effect on increasing cell differentiation and mineralization.

2. Material and methods

2.1. Preparation of SF solution

SF solution was prepared as previously described [38]. Briefly, silk cocoons from *B. mori* (Trudel Inc.) were boiled twice in 0.02 M Na_2CO_3 solution for 1 hour and then washed with ultrapure water (UPW). Purified SF was solubilized in 9 M lithium bromide solution (ThermoScientific) and dialyzed (3.5K molecular weight cut-off, ThermoScientific) against UPW for 36 hours. After freezing at -80°C, the frozen SF solution was freeze-dried for 5 days. For SLSC, lyophilized SF was dissolved at 17% (w/v) in 1,1,1,3,3,3-hexafluoroisopropanol (HFIP) (FluoroChem Ltd.). For MTSC, lyophilized SF was dissolved at 12% (w/v) in HFIP.

2.2. Production of SLSC

Sodium chloride (NaCl) crystals with a granule diameter between 300-400 µm were used as a faceted polydisperse porogen. 1 ml of the 17% (w/v) SF-HFIP solution was added to 2.5 g of NaCl crystals. The HFIP was allowed to evaporate for 3 days. β-sheet conformation was induced by immersing the SF-salt blocks into 90% (v/v) methanol (Merck) in UPW for 30 minutes and blocks were subsequently dried overnight [39]. NaCl was leached by washing the SF-salt blocks in UPW for 2 days. SF blocks were cut and punched (Kai medical) into disks (3 mm height, 5 mm diameter). SLSC were

sterilized in phosphate buffered saline (PBS; Medicago AB) at 121°C, 1 bar for 20 minutes. The SLSC's fabrication process is depicted in figure 1A.

2.3. Production of MTSC

A 10% (w/w) PCL in dichloromethane solution (SIGMA) was emulsified in a 2% (w/w) poly(vinyl alcohol) (PVA; SIGMA) aqueous solution within a glass capillary microfluidic device to produce monodisperse droplets [23]. The inner and the outer flow rates were adjusted to 5 ml/hr and 8 ml/hr, respectively. The droplets were collected in an excess of PVA solution and left resting for approximately five weeks until dichloromethane was completely evaporated. The particles were washed 5 times in water and once in ethanol. Subsequently, particles were placed in moulds (7 mm diameter, 3 mm height) and slightly agitated to close pack and dry. The particles were then heated to 57°C at 25% relative humidity for 1 hour to form necks between the particles. 12% SF solution was infiltrated into each particle pack and let dry. β-sheet conformation was induced by immersing the SF-salt blocks into 90% (v/v) methanol in UPW for 1 hour [40]. Following 8 hours in dichloromethane to remove the porogen particles, samples were washed once in ethanol to remove any solvent residues and left to dry. Finally, MTSC were sterilized in PBS at 121°C, 1 bar for 20 min. Due to the scaffold fragility after autoclaving, scaffolds were not punched further out. The MTSC's fabrication process is depicted in figure 1B.

2.4.   Cell culture

hBMSCs were isolated and characterized from bone marrow (Lonza) as previously described [20]. hBMSCs (passage 3) were expanded at 37°C and 5% CO_2 in expansion medium (Dulbecco's modified Eagle's medium (DMEM; GIBCO) containing 10% fetal bovine serum (FBS; GIBCO), 1% Penicillin/Streptomycin/Fungizone (P/S/F; Invitrogen), 1% non-essential amino acids (Invitrogen) and 1 ng/ml basic fibroblast growth factor (Invitrogen)). After one week, $1*10^6$ cells dispersed in 20 µl medium were seeded on each scaffold. After cell incubation for 90 min under standard cell culture conditions (37°C, 5% CO_2), the scaffolds were transferred into static (static conditions) or spinner flask

bioreactors (dynamic conditions). Each bioreactor contained three scaffolds. Cells were cultured in 5 ml osteogenic media (DMEM, 10% FBS, 1% P/S/F, 50 µg/ml L-ascorbic acid (SIGMA), 100 nM dexamethasone (SIGMA), 10 mM beta-glycerolphosphate (SIGMA)) for 7 weeks either under static or dynamic culture conditions. The bioreactor caps were loosened to allow gas exchange. Culture media was changed every 2-3 days.

2.5. Dynamic culture conditions

Spinner flask bioreactors were chosen as a dynamic culture to induce fluid flow through and around the cell-scaffold construct. The culture medium was stirred through a magnet at approximately 70 rpm.

2.6. Histology

Constructs were fixed in 4 % formaldehyde overnight at room temperature. Samples were dehydrated, embedded in paraffin and cut into 10 µm thick sections. Weigert's hematoxylin and Sirius red were used to stain the cell nuclei and collagen simultaneously. Images were taken using a Slide Scanner Pannoramic 250 (3DHISTECH). Figures show representative images per group.

2.7. RNA isolation and Real-time PCR analysis

Total RNA was isolated using Trizol reagent (Invitrogen), according to the manufacturer's protocol. Each scaffold was disintegrated at 25'000 rpm for 10 seconds per cycle (6 cycles) using steel balls and a Minibead Beater (Biospec). Samples were placed on ice in between cycles. Total RNA (1 µg) was reverse transcribed to cDNA at 42°C for 60 min using the High Capacity RNA-to-cDNA kit (Applied Biosystems), according to the manufacture's protocol. 10 µl of cDNA was diluted into 10 µl of RNAse free water (SIGMA).

Real-time PCR (Biorad CFX96) was performed using TaqMan probe detection (Applied Biosystems). Real-time PCR was done for glyceraldehyde-3-phosphate dehydrogenase (GAPDH,

Hs02758991_g1), collagen type I (COL1A2-I, Hs01028956_m1), alkaline phosphatase (ALPL, Hs01029144_m1) and osteocalcin (BGLAP, Hs01587814_g1). A negative control without cDNA template was run for each assay. Values were normalized to GAPDH mRNA levels as an internal control and were presented as fold change compared to SLSC in static conditions. Data was analyzed using the comparative Cq method (2-ΔCCq) [41].

2.8. *Micro-computed tomography*

For quantification and visualization of the engineered mineralized bone-like tissue, scaffolds were analyzed using a micro-CT imaging system (μCT40, Scanco Medical AG). Samples were non-invasively scanned weekly for up to 7 weeks. All bioreactors were scanned at 36 µm resolution, 45 kVp and 177µA. An integration time of 200 ms and 2-fold data averaging was applied. Cylindrical volumes of interest were selected for the analysis. A constraint Gaussian filter of 1.2 and a filter support of 1 was used to suppress noise. Mineralized tissue was segmented from non-mineralized tissue using a global thresholding procedure [42]. All samples were thresholded at a grey value of 149 (corresponding to a density of 89.1 mg HA per cm^3). Quantitative histomorphometry was performed on all scaffolds to assess engineered bone-like tissue volume fraction (BV/TV), bone-like tissue surface-to-bone volume (BS/BV), trabecular thickness (Tb.Th.), trabecular separation (Tb.Sp.) and trabecular number (Tb.N.) [43, 44].

2.9. *Statistics*

Data (n=3) represent the mean ± standard deviation (SD). SPSS® 22.0 was used for statistical analysis. A one-way ANOVA with post-hoc Bonferroni correction was performed to compare differences among groups. P-values ≤ 0.05 were considered statistically significant. Figure 5 shows upper median samples based on the BV/TV values of the whole scaffold.

3. Results

3.1. Cell distribution, ECM formation

Hematoxylin staining revealed that, while cells could infiltrate and distribute regularly in SLSC both under static and dynamic conditions (figure 2A, B), homogenous cell distribution in MTSC was only observed in the dynamic culture (figure 2D). Sirius red staining showed the formation of a collagenous ECM that was more evenly distributed in SLSC compared to MTSC, both under static and dynamic conditions. Interestingly, a denser collagenous ECM formation was formed predominantly at the edge of SLSC cultured in the dynamic assay, as compared to all the other scaffolds and cell culture conditions (figure 3). Acellular SLSC and MTSC were stained in parallel to count for potential false positive staining (data not shown).

3.2. Bone-related mRNA expression levels

Dynamic conditions up-regulated the expression of osteoblastic differentiation markers in SLSC and MTSC compared to static conditions. This was evidenced by a significant increase of the ALPL mRNA levels by 3.1-fold (p = 0.00045, figure 4B) or of the BGLAP mRNA levels by 3.5-fold (p = 0.00500, figure 4C) in cells cultured on MTSC and on SLSC, respectively, compared to static conditions. The expression of these genes was also influenced by pore geometry. Under dynamic conditions, these genes were differentially expressed in both scaffolds. After 7 weeks of culture, ALPL mRNA levels were markedly up-regulated in MTSC compared to SLSC (8.4-fold, p = 0.00002) while BGLAP mRNA levels were significantly down-regulated (51-fold, p = 0.00043, figure 4B, 4C). Under static conditions, COL1A2 mRNA levels were up-regulated on SLSC compared to MTSC (p = 0.03, figure 4A).

3.3. ECM mineralization

Micro-CT was used to evaluate the influence of scaffold pore geometry and culture condition on mineralized bone-like tissue formation (figure 5). Both SLSC and MTSC supported mineralized tissue

formation under static and dynamic conditions. Dynamic conditions (figure 5 I-P) favored a more homogeneously distributed mineralized ECM deposition in both scaffold types, whereas under static conditions (figure 5 A-H) mineralized ECM was limited to the edges of the scaffold or the mid-bottom scaffold' region in SLSC and MTSC, respectively. The engineered mineralized bone-like tissue architecture was quantified by morphometrical parameters (figure 6). No differences in BV/TV were observed between SLSC and MTSC under static conditions (figure 6A). Nevertheless, the influence of dynamic conditions on BV/TV (figure 6A) and on engineered bone-like tissue distribution along the scaffold (figure 5 I-P) was affected by scaffold pore geometry. BV/TV was significantly higher for MTSC under dynamic conditions (12.27% ± 0.58%) compared to SLSC under dynamic conditions (6.17% ± 1.63%, p = 0.004). BS/BV was increased significantly in SLSC under dynamic conditions (24.05 ± 2.29 mm^{-1}) compared to SLSC under static conditions (18.46 ± 1.03 mm^{-1}, p = 0.016). Lower BS/BV values relate to more compact and plate-like bone structures. In line with the BS/BV data, SLSC under dynamic conditions were characterized by a more homogenous distribution of the mineralized tissue as compared to a compact and dense structure in SLSC under static conditions. Despite the more homogeneous distribution of mineralized tissue and the high BS/BV values (figure 6B), dynamically cultured SLSC scaffolds also showed a dense and compact bone-like surface density at the mid-bottom region of the scaffold (figure 5K). However, this local lower porosity was not as prominent as the overall homogenous distribution of the mineralized tissue throughout this scaffold. No differences were observed for BV/TV and BS/BV values between MTSC under static and dynamic conditions.

Similarly, the influence of dynamic culture conditions on the trabecular morphometric indices was dependent on scaffold pore geometry (figure 7). In accordance to the BS/BV data, Tb.Th. was significantly smaller in SLSC under dynamic conditions (0.08 ± 0.008 mm) compared to SLSC under static conditions (0.11 ± 0.006 mm, p = 0.054)(figure 7A). Similarly, Tb.Th showed a trend to be smaller in MTSC cultured in dynamic condition compared to MTSC static conditions, although this was not statistically different. Tb.N. (figure 7B) was higher in MTSC under dynamic conditions (1.26 ± 0.07 mm^{-1}) compared to MTSC under static conditions (0.9 ± 0.18 mm^{-1}, p = 0.087) and significantly higher than in SLSC under dynamic conditions (0.73 ± 0.15 mm^{-1}, p = 0.004). Conversely, the Tb.Sp. was

lower in MTSC under dynamic conditions compared to MTSC under static conditions and SLSC under dynamic conditions, although differences were not statistically significant (figure 7C).

4. Discussion

In this study, we used a new established method to systematically fabricate scaffolds with highly controlled monodisperse porous architecture. Our aim was to evaluate how scaffold pore geometry influences the response of cells to culture conditions, with regard to both osteogenic cell differentiation and the amount, structure and spatial distribution of the mineralized tissue formed. Dynamic culture conditions were used to overcome the nutrient flow limitations and to apply mechanical loading through wall shear stress. Cells (hBMSCs) differentiated towards the osteogenic lineage when cultured either under static or dynamic conditions for both scaffold pore geometries. Nevertheless, distinct responses to fluid flow in gene expression, the amount, structure and spatial distribution of the mineralized ECM formed were shown to be dependent on scaffold pore geometry.

The applied SLSC and MTSC specimens were produced following the same procedure described by Sommer *et al* 2016 [23]. Geometrical features reported by the authors were thus used here to aid the interpretation of the obtained results [23]. Despite their similar local stiffness and a comparable mean pore diameter of about 200 µm, SLSC and MTSC differed in the pore diameter distribution and pore geometry. This resulted in a lower porosity in the MTSC (84.7 ± 2.1 %) compared to SLSC (92.8 ± 0.6%) (figure S1) [23]. We used histology staining's to evaluate at the influence of these differences of scaffold porosities on cell proliferation capabilities. The histological results showed that cells could adhere well on both scaffold types but that the ability of cells to proliferate was reduced in the MTSC scaffolds under static conditions. Similarly, previous studies have shown that SF scaffolds with similar pore diameter and porosities were able to better support cell proliferation *in vitro* [9, 46, 47]. Assuming a similar MTSC porosity as described by Sommer *et al* [23], the lower porosity of the MTSC might have limited the initial cell distribution throughout the scaffold volume during the cell seeding. This restriction was lifted if the MTSC were cultured under dynamic conditions, indicating that the induced fluid flow could compensate for that.

Besides enhancing cell distribution, dynamic conditions also significantly increased mRNA levels of ALPL and BGLAP in MTSC and SLSC, respectively, compared to static conditions after 7 weeks of culture. These results indicate that cells cultured under dynamic conditions were at a more mature stage of the osteoblast cell differentiation compared to cells cultured under static conditions. Accordingly, previous reports have shown positive effects of turbulent flow created in spinner flask bioreactors on osteogenic cell differentiation *in vitro* [48, 49]. Although dynamic cultures supported a similar and homogenous distribution of cells for both scaffolds types, COL1A2 gene was stronger expressed in SLSC compared to MTSC under static conditions. The formation of a denser collagenous ECM was also observed in SLSC compared to MTSC under dynamic conditions. In line with this observation, SLSC enhanced osteogenic cell differentiation as shown by an increase in the BGLAP mRNA levels (the hallmark of mature osteoblasts) compared to MTSC under dynamic conditions. Differences in the up-regulation of mid (ALPL) or late (BGLAP) differentiation markers between MTSC and SLSC under dynamic conditions suggest that cells on SLSC were at a more matured differentiation stage. While the underlying mechanisms are not clear, we speculate that cells reacted distinctly to the different shear forces developed in the two types of scaffolds. In highly interconnected pores, the porosity and pore geometry affect the permeability of the scaffold and magnitude and distribution of the shear forces developed during induced flow [50]. The magnitudes of mechanical forces have been shown to influence gene expression in osteoblastic cells [51]. We hypothesize that the differences in scaffold pore geometry and in overall porosity between SLSC and MTSC [23] could have had an impact on the magnitude of the shear forces and on the nutrient flow velocity across the scaffolds, affecting cell proliferation, collagen formation in the ECM and consequently cell differentiation.

Osteoblast cell differentiation is characterized by the formation of a mineralized ECM. Although bone-like tissue was formed in all groups, the amount, the structure and distribution of the mineralized ECM was dependent on the pore geometry and whether the constructs were grown statically or dynamically. Interestingly and in contrast to the gene expression profile observed, MTSC under dynamic conditions had a significantly increased BV/TV compared to SLSC under dynamic conditions. This is in agreement with our observation that pore geometry can lead to differences in the bone-like structure along the scaffold under dynamic conditions. Based on the 3D images, MTSC under dynamic conditions

favored a more homogeneously distributed ECM mineralization characterized by a more trabecular bone-like structure including locally restricted areas of plate-like bone (larger surface of compact bone), compared to the rest of the groups. Compared to the spherical nature of PCL particles used for making the pores in MTSC, the rock-salt crystal structure of NaCl rendered more faceted pore surfaces in the SLSC scaffolds. It has been reported that surface concavities act as a strong template for *in vitro* surface mineralization, even in the absence of living cells [27, 28]. Surface mineralization is probably favored within pore concavities as compared to planar surfaces because nuclei are less exposed to shear and are thus able to grow larger in sites where the local fluid velocity is low [19, 28]. We hypothesize that MTSC with more regular and concave surfaces favor a more homogeneous deposition of mineral due to inhibited fluid motion close to regularly distributed pore walls. By contrast, the more planar features present in SLSC might result in an unevenly distributed mineral deposition with higher mineral formation at concave surfaces and lower mineral formation at planar surfaces of the pore. Differences in fluid flow next to concave and planar surfaces might then modulate the local ion concentration affecting the nucleation process and therefore mineral tissue formation. The decrease in BV/TV for SLSC under dynamic compared to static conditions could be due to the higher flow velocities at planar surfaces, which in turn could lead to more fluctuations in the local concentrations of Ca^{2+} and PO_4^{3}, as previously suggested by Bianchi *et al* 2014 [28]. This effect might be enhanced by the high porosity of the SLSC [23].

In conclusion, our results suggest that scaffold pore geometry and porosity generate different flow velocities within the scaffolds in the bioreactor, which in turn directly affect cell differentiation and bone-like tissue formation. While SLSC enhanced osteoblast cell differentiation, the spherical and more regular concave pore geometry in MTSC could probably favor nucleation of ions increasing the amount of bone-like tissue formation. These findings point out the role of pore geometry on the stimulation of cell differentiation and indirectly on guiding the mineral deposition process. This suggest the importance of 1) the fluid flow imposed by the scaffold's pore geometry on the cell response and the formation of an engineered bone-like tissue, 2) the need to control and tune the scaffold pore geometry to modulate the amount and structure of engineered bone-like tissue. Fabrication of complex scaffolds, by additive manufacturing methods, comprising regions with more concave pores with others with more planar pore

geometries might thus represent a promising direction towards the tunability of the BTF and to mimic the structural complexity of the bone tissue and its spatial distribution to each specific need.

6. Acknowledgements

The authors thanks to Trudel Inc. for the supply of the silk cocoons and ScopeM for providing access to their histology equipment. The research leading to these results has received funding from the European Union Seventh Framework Programme (FP7/2007-2013) under grant agreement n°. 329389, 262948 and 336043.

7. Author Disclosure Statement

The authors declare that no competing financial interests exist.

8. References

[1] S. Bose, M. Roy, A. Bandyopadhyay, Recent advances in bone tissue engineering scaffolds, Trends Biotechnol 30(10) (2012) 546-54.
[2] W.R. Moore, S.E. Graves, G.I. Bain, Synthetic bone graft substitutes, ANZ J Surg 71(6) (2001) 354-61.
[3] S.K. Nandi, S. Roy, P. Mukherjee, B. Kundu, D.K. De, D. Basu, Orthopaedic applications of bone graft & graft substitutes: a review, Indian J Med Res 132 (2010) 15-30.
[4] B. Amiri, M. Ghollasi, M. Shahrousvand, M. Kamali, A. Salimi, Osteoblast differentiation of mesenchymal stem cells on modified PES-PEG electrospun fibrous composites loaded with Zn2SiO4 bioceramic nanoparticles, Differentiation 92(4) (2016) 148-158.
[5] H.M. Aydin, A.J. El Haj, E. Piskin, Y. Yang, Improving pore interconnectivity in polymeric scaffolds for tissue engineering, J Tissue Eng Regen Med 3(6) (2009) 470-6.
[6] H.J. Haugen, M. Monjo, M. Rubert, A. Verket, S.P. Lyngstadaas, J.E. Ellingsen, H.J. Ronold, J.C. Wohlfahrt, Porous ceramic titanium dioxide scaffolds promote bone formation in rabbit peri-implant cortical defect model, Acta biomaterialia 9(2) (2013) 5390-9.
[7] J.H. Kuhne, R. Bartl, B. Frisch, C. Hammer, V. Jansson, M. Zimmer, Bone formation in coralline hydroxyapatite. Effects of pore size studied in rabbits, Acta Orthop Scand 65(3) (1994) 246-52.
[8] C.V.M. Rodrigues, P. Serricella, A.B.R. Linhares, R.M. Guerdes, R. Borojevic, M.A. Rossi, M.E.L. Duarte, M. Farina, Characterization of a bovine collagen–hydroxyapatite composite scaffold for bone tissue engineering, Biomaterials 24(27) (2003) 4987-4997.
[9] M. Rubert, H. Pullisaar, M. Gomez-Florit, J.M. Ramis, H. Tiainen, H.J. Haugen, S.P. Lyngstadaas, M. Monjo, Effect of TiO2 scaffolds coated with alginate hydrogel containing a proline-rich peptide on osteoblast growth and differentiation in vitro, Journal of biomedical materials research. Part A 101(6) (2013) 1768-77.

[10] M. Persson, P.P. Lehenkari, L. Berglin, S. Turunen, M.A.J. Finnila, J. Risteli, M. Skrifvars, J. Tuukkanen, Osteogenic Differentiation of Human Mesenchymal Stem cells in a 3D Woven Scaffold, Scientific reports 8(1) (2018) 10457.

[11] M. Bohner, Y. Loosli, G. Baroud, D. Lacroix, Commentary: Deciphering the link between architecture and biological response of a bone graft substitute, Acta biomaterialia 7(2) (2011) 478-84.

[12] A.M. Barradas, H. Yuan, C.A. van Blitterswijk, P. Habibovic, Osteoinductive biomaterials: current knowledge of properties, experimental models and biological mechanisms, European cells & materials 21 (2011) 407-29; discussion 429.

[13] M.I. Gariboldi, S.M. Best, Effect of Ceramic Scaffold Architectural Parameters on Biological Response, Front Bioeng Biotechnol 3 (2015) 151.

[14] N. Yuan, K.S. Rezzadeh, J.C. Lee, Biomimetic Scaffolds for Osteogenesis, Receptors Clin Investig 2(3) (2015).

[15] C.M. Bidan, K.P. Kommareddy, M. Rumpler, P. Kollmannsberger, P. Fratzl, J.W.C. Dunlop, Geometry as a Factor for Tissue Growth: Towards Shape Optimization of Tissue Engineering Scaffolds, Advanced healthcare materials 2(1) (2013) 186-194.

[16] T.M. Chu, D.G. Orton, S.J. Hollister, S.E. Feinberg, J.W. Halloran, Mechanical and in vivo performance of hydroxyapatite implants with controlled architectures, Biomaterials 23(5) (2002) 1283-93.

[17] A. Cipitria, C. Lange, H. Schell, W. Wagermaier, J.C. Reichert, D.W. Hutmacher, P. Fratzl, G.N. Duda, Porous scaffold architecture guides tissue formation, Journal of bone and mineral research : the official journal of the American Society for Bone and Mineral Research 27(6) (2012) 1275-88.

[18] M. Domingos, F. Intranuovo, T. Russo, R. De Santis, A. Gloria, L. Ambrosio, J. Ciurana, P. Bartolo, The first systematic analysis of 3D rapid prototyped poly(epsilon-caprolactone) scaffolds manufactured through BioCell printing: the effect of pore size and geometry on compressive mechanical behaviour and in vitro hMSC viability, Biofabrication 5(4) (2013) 045004.

[19] R.U.E. Eva, H. Astghik, G.C.W. Joop, J.E.C. Huib, K. Alexey, A.J. John, J.J.P.v.d.B. Jeroen, Effect of calcium phosphate ceramic substrate geometry on mesenchymal stromal cell organization and osteogenic differentiation, Biofabrication 8(2) (2016) 025006.

[20] S. Hofmann, H. Hagenmuller, A.M. Koch, R. Muller, G. Vunjak-Novakovic, D.L. Kaplan, H.P. Merkle, L. Meinel, Control of in vitro tissue-engineered bone-like structures using human mesenchymal stem cells and porous silk scaffolds, Biomaterials 28(6) (2007) 1152-62.

[21] S. Hofmann, M. Hilbe, R.J. Fajardo, H. Hagenmuller, K. Nuss, M. Arras, R. Muller, B. von Rechenberg, D.L. Kaplan, H.P. Merkle, L. Meinel, Remodeling of tissue-engineered bone structures in vivo, Eur J Pharm Biopharm 85(1) (2013) 119-29.

[22] M. Rumpler, A. Woesz, J.W. Dunlop, J.T. van Dongen, P. Fratzl, The effect of geometry on three-dimensional tissue growth, Journal of the Royal Society, Interface / the Royal Society 5(27) (2008) 1173-80.

[23] M.R. Sommer, J.R. Vetsch, J. Leemann, R. Muller, A.R. Studart, S. Hofmann, Silk fibroin scaffolds with inverse opal structure for bone tissue engineering, J Biomed Mater Res B Appl Biomater (2016).

[24] L. Uebersax, H. Hagenmuller, S. Hofmann, E. Gruenblatt, R. Muller, G. Vunjak-Novakovic, D.L. Kaplan, H.P. Merkle, L. Meinel, Effect of scaffold design on bone morphology in vitro, Tissue Eng 12(12) (2006) 3417-29.

[25] S. Van Bael, Y.C. Chai, S. Truscello, M. Moesen, G. Kerckhofs, H. Van Oosterwyck, J.P. Kruth, J. Schrooten, The effect of pore geometry on the in vitro biological behavior of human periosteum-derived cells seeded on selective laser-melted Ti6Al4V bone scaffolds, Acta biomaterialia 8(7) (2012) 2824-34.

[26] M.J. Gupte, W.B. Swanson, J. Hu, X. Jin, H. Ma, Z. Zhang, Z. Liu, K. Feng, G. Feng, G. Xiao, N. Hatch, Y. Mishina, P.X. Ma, Pore size directs bone marrow stromal cell fate and tissue regeneration in nanofibrous macroporous scaffolds by mediating vascularization, Acta biomaterialia 82 (2018) 1-11.

[27] J.R. Vetsch, R. Muller, S. Hofmann, The influence of curvature on three-dimensional mineralized matrix formation under static and perfused conditions: an in vitro bioreactor model, Journal of the Royal Society, Interface / the Royal Society 13(123) (2016).

[28] M. Bianchi, E.R. Urquia Edreira, J.G. Wolke, Z.T. Birgani, P. Habibovic, J.A. Jansen, A. Tampieri, M. Marcacci, S.C. Leeuwenburgh, J.J. van den Beucken, Substrate geometry directs the in vitro mineralization of calcium phosphate ceramics, Acta biomaterialia 10(2) (2014) 661-9.

[29] S. Sofia, M.B. McCarthy, G. Gronowicz, D.L. Kaplan, Functionalized silk-based biomaterials for bone formation, Journal of biomedical materials research 54(1) (2001) 139-48.

[30] B. Panilaitis, G.H. Altman, J. Chen, H.J. Jin, V. Karageorgiou, D.L. Kaplan, Macrophage responses to silk, Biomaterials 24(18) (2003) 3079-85.

[31] P.M. Cunniff, S.A. Fossey, M.A. Auerbach, J.W. Song, D.L. Kaplan, W.W. Adams, R.K. Eby, D. Mahoney, D.L. Vezie, Mechanical and thermal properties of dragline silk from the spider Nephila clavipes, Polymers for Advanced Technologies 5(8) (1994) 401-410.

[32] N.T. Collins, P.M. Cummins, O.C. Colgan, G. Ferguson, Y.A. Birney, R.P. Murphy, G. Meade, P.A. Cahill, Cyclic strain-mediated regulation of vascular endothelial occludin and ZO-1: influence on intercellular tight junction assembly and function, Arterioscler Thromb Vasc Biol 26(1) (2006) 62-8.

[33] W.M. Jackson, M.J. Jaasma, R.Y. Tang, T.M. Keaveny, Mechanical loading by fluid shear is sufficient to alter the cytoskeletal composition of osteoblastic cells, Am J Physiol Cell Physiol 295(4) (2008) C1007-15.

[34] L. Yu, X. Ma, J. Sun, J. Tong, L. Shi, L. Sun, J. Zhang, Fluid shear stress induces osteoblast differentiation and arrests the cell cycle at the G0 phase via the ERK1/2 pathway, Mol Med Rep 16(6) (2017) 8699-8708.

[35] G.N. Bancroft, V.I. Sikavitsas, A.G. Mikos, Design of a flow perfusion bioreactor system for bone tissue-engineering applications, Tissue Eng 9(3) (2003) 549-54.

[36] G.N. Bancroft, V.I. Sikavitsas, J. van den Dolder, T.L. Sheffield, C.G. Ambrose, J.A. Jansen, A.G. Mikos, Fluid flow increases mineralized matrix deposition in 3D perfusion culture of marrow stromal osteoblasts in a dose-dependent manner, Proc Natl Acad Sci U S A 99(20) (2002) 12600-5.

[37] K. Bilodeau, D. Mantovani, Bioreactors for tissue engineering: focus on mechanical constraints. A comparative review, Tissue Eng 12(8) (2006) 2367-83.

[38] R. Nazarov, H.-J. Jin, D.L. Kaplan, Porous 3-D Scaffolds from Regenerated Silk Fibroin, Biomacromolecules 5(3) (2004) 718-726.

[39] M. Tsukada, Y. Gotoh, M. Nagura, N. Minoura, N. Kasai, G. Freddi, Structural changes of silk fibroin membranes induced by immersion in methanol aqueous solutions, Journal of Polymer Science Part B: Polymer Physics 32(5) (1994) 961-968.

[40] E. Servoli, D. Maniglio, A. Motta, R. Predazzer, C. Migliaresi, Surface Properties of Silk Fibroin Films and Their Interaction with Fibroblasts, Macromolecular Bioscience 5(12) (2005) 1175-1183.

[41] K.J. Livak, T.D. Schmittgen, Analysis of relative gene expression data using real-time quantitative PCR and the 2(-Delta Delta C(T)) Method, Methods 25(4) (2001) 402-8.

[42] P. Ruegsegger, B. Koller, R. Muller, A microtomographic system for the nondestructive evaluation of bone architecture, Calcif Tissue Int 58(1) (1996) 24-9.

[43] T. Hildebrand, A. Laib, R. Muller, J. Dequeker, P. Ruegsegger, Direct three-dimensional morphometric analysis of human cancellous bone: microstructural data from spine, femur, iliac crest, and calcaneus, Journal of bone and mineral research : the official journal of the American Society for Bone and Mineral Research 14(7) (1999) 1167-74.

[44] B.D. Porter, A.S. Lin, A. Peister, D. Hutmacher, R.E. Guldberg, Noninvasive image analysis of 3D construct mineralization in a perfusion bioreactor, Biomaterials 28(15) (2007) 2525-33.

[45] G.S. Stein, J.B. Lian, J.L. Stein, A.J. Van Wijnen, M. Montecino, Transcriptional control of osteoblast growth and differentiation, Physiol Rev 76(2) (1996) 593-629.

[46] M. Gómez-Florit, M. Rubert, J.M. Ramis, H.J. Haugen, H. Tiainen, S.P. Lyngstadaas, M. Monjo, TiO2 Scaffolds Sustain Differentiation of MC3T3-E1 Cells, Journal of Biomaterials and Tissue Engineering 2(4) (2012) 336-344.

[47] L. Meinel, S. Hofmann, O. Betz, R. Fajardo, H.P. Merkle, R. Langer, C.H. Evans, G. Vunjak-Novakovic, D.L. Kaplan, Osteogenesis by human mesenchymal stem cells cultured on silk biomaterials: comparison of adenovirus mediated gene transfer and protein delivery of BMP-2, Biomaterials 27(28) (2006) 4993-5002.

[48] A. Woloszyk, S. Holsten Dircksen, N. Bostanci, R. Muller, S. Hofmann, T.A. Mitsiadis, Influence of the mechanical environment on the engineering of mineralised tissues using human dental pulp stem cells and silk fibroin scaffolds, PLoS One 9(10) (2014) e111010.

[49] V.I. Sikavitsas, G.N. Bancroft, A.G. Mikos, Formation of three-dimensional cell/polymer constructs for bone tissue engineering in a spinner flask and a rotating wall vessel bioreactor, Journal of biomedical materials research 62(1) (2002) 136-48.

[50] T.S. Karande, J.L. Ong, C.M. Agrawal, Diffusion in Musculoskeletal Tissue Engineering Scaffolds: Design Issues Related to Porosity, Permeability, Architecture, and Nutrient Mixing, Annals of Biomedical Engineering 32(12) (2004) 1728-1743.

[51] H.F. Lu, Z.H. Mai, Y. Xu, W. Wang, H. Ai, Mechanical loading induced expression of bone morphogenetic protein-2, alkaline phosphatase activity, and collagen synthesis in osteoblastic MC3T3-E1 cells, Chin Med J (Engl) 125(22) (2012) 4093-7.

Figures

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Figure legends

Fig. 1. Schematic illustration of the production process of salt-leached scaffolds (SLSC) (A) and inverse opal scaffolds (MTSC) (B).

Fig. 2. Overview of the cell distribution and formation of a collagenous ECM along the scaffold size. Weigert's haematoxylin staining (cell nuclei - dark purple spots) and Sirius red staining (collagenous ECM - pink) on hBMSCs cultured on SLSC (A, B) and MTSC (C, D) either under static (A, C) or dynamic conditions (B, D). Scaffolds are shown in orange color. Scale bar lengths are 1 mm.

Fig. 3. Magnified view of the formation of a collagenous ECM at the scaffold surface. Weigert's haematoxylin staining (cell nuclei - dark purple spots) and Sirius red staining (collagenous ECM - pink) on hBMSCs cultured on SLSC (A, B) and MTSC (C, D) either under static (A, C) or dynamic conditions (B, D). Scaffolds are shown in orange color. Image is taken from the top-middle region of the scaffold. Scale bar lengths are 200 µm.

Fig. 4. Relative mRNA expression levels of collagen type I (COL1A2) (A), alkaline phosphatase (ALPL) (B), and osteocalcin (BGLAP) (C) in hBMSCs cultured on SLSC or MTSC either under static (black bar) or dynamic (grey bar) culture conditions in osteogenic media for 7 weeks. Values were normalized to housekeeping gene (glyceraldehyde-3-phosphate dehydrogenase [GAPDH]) and expressed as fold change relative SLSC cultured under static conditions, which was set to 1. Values represent the mean ± SD (n = 3). Results were considered statistically significant with p≤ 0.05 between scaffold types (*) and culturing conditions (#), respectively.

Fig. 5. Morphology of engineered bone-like tissue from hBMSCs cultured on SLSC (A-D, I-L) and MTSC (E-H, I-L) under static (A-H) or dynamic (I-P) conditions for 7 weeks. Side view (A, E, I, M) top view (B, F, J, N) bottom view (C, G, K, O) and center-cross view (D, H, L, P). Scale bar lengths are 1 mm.

Fig. 6. Effect of pore geometry and culture conditions on engineered mineralized bone-like tissue volume fraction (BV/TV) (A) and bone-like tissue surface-to-bone volume (BS/BV) (B). (*) $p \leq 0.05$ versus SLSC for each culture condition (#) $p \leq 0.05$ versus static condition.

Fig. 7. Effect of pore geometry and culture conditions on trabecular structures. Trabecular thickness (Tb. Th) (A), trabecular number (Tb.N) (B) and trabecular separation (Tb.Sp) (C). hBMSCs were cultured on SLSC or MTSC under static or dynamic conditions for 7 weeks. (*) $p \leq 0.05$ versus SLSC for each culture condition (#) $p \leq 0.05$ versus static condition.