Title: Electronic blood vessel

Authors: Shiyu Cheng[1,2,4,5], Chen Hang[1,2,5], Li Ding[1,2,3,5], Liujun Jia[3], Lixue Tang[2],

Lei Mou[1,2], Jie Qi[1,2], Ruihua Dong[1,2], Wenfu Zheng[2], Yan Zhang[3]*, Xingyu Jiang[1,2,6]*

Affiliations:

[1]Department of Biomedical Engineering and Shenzhen Bay Laboratory, Southern

University of Science and Technology, Shenzhen, Guangdong 518055, China.

[2]National Center for NanoScience and Technology, University of Chinese Academy

of Sciences, Beijing 100190, China.

[3]State Key Laboratory of Cardiovascular Disease, Fuwai Hospital, National Center

for Cardiovascular Diseases, Chinese Academy of Medical Sciences and Peking

Union Medical College, Beijing 100037, China.

[4]Current address: Institute of Bioengineering, School of Engineering, Ecole

Polytechnique Federale de Lausanne, Lausanne 1015, Switzerland.

[5]These authors contributed equally.

[6]Lead Contact

*Correspondence: jiang@sustech.edu.cn; waikezhangyan@126.com

Summary

Advances in bioelectronics have great potential to address unsolvable biomedical

problems in the cardiovascular system. By using poly(L-lactide-co-ε-caprolactone)

(PLC) that encapsulates the liquid metal to make flexible and bio-degradable

electrical circuitry, we develop an electronic blood vessel that can integrate flexible

electronics with three layers of blood vessel cells, to mimic and go beyond the natural

blood vessel. It can improve the endothelization process through electrical stimulation

and can enable controlled gene delivery into specific part of the blood vessel via

electroporation. The electronic blood vessel has excellent biocompatibility in the

vascular system and shows great patency three months post-implantation in a rabbit

model. The electronic blood vessel would be an ideal platform to enable diagnostics

and treatments in the cardiovascular system and can greatly empower personalized

medicine by creating a direct link of vascular tissue-machine interface.

Keywords: Metal polymer conductor, blood vessel, electrical stimulation,

electroporation, bioelectronics, vascular interface.

Introduction

Cardiovascular diseases remain the number one cause of mortality worldwide[1]. In treating cardiovascular diseases via coronary artery bypass grafting (CABG) surgery, none existing small diameter (<6 mm) tissue engineered blood vessel (TEBV) has met clinical demands[2]. To fabricate the TEBV, a range of approaches, such as decellularized matrix[3–7], self-assembly cell sheets[8–11], bioactive and biomimetic materials[12–14], were developed and clinically investigated in recent years. However, most of these methods only serve as scaffolds to provide mechanical support and mainly rely on the remodeling process by the host tissue and present significant limitations in helping the regeneration of neo blood vessel. Thus far, none of them have achieved satisfactory clinical results. Specifically, a complex interplay between the blood flow and the TEBV can often cause inflammatory responses, resulting in thrombosis, neointimal hyperplasia or smooth muscle cell accumulation nearby the scaffold[2,15], in different pathological stages. To address these issues, next-generation TEBV should not only function as scaffolds to provide the mechanical support and facilitate host cell recruitments, but also have the capability to actively respond to and couple with the native remodeling process in order to provide adaptive treatments after implantation.

Combining living tissues with flexible electronics[16,17] could endow the conventional TEBV more functionalities and capabilities to overcome existing biomedical problems, such as precision diagnostics, by *in situ* sensing the blood flow and temperature, and treatments by therapeutic drug or gene delivery[18,19]. In previous

works, we have developed many approaches to fabricate structures that mimic natural

blood vessel with multiple types of blood vessel cells in different layers, including

stress-induced self-rolling membrane[13,20–22] and layer by layer technique[23]. Recently,

we have developed a printable metal-polymer conductor (MPC) which exhibited

excellent compatibility and high stretchability[24,25]. Here, we develop an electronic

blood vessel that integrates flexible electrodes into the bio-degradable scaffold by

combining the liquid metal with poly(L-lactide-co-ε-caprolactone) (PLC) into a

metal-polymer conductor. As a proof of concept, we used the electronic blood vessel

to carry out *in vitro* electrical stimulation and electroporation. By electrical

stimulation, the electronic blood vessel can effectively promote cell proliferation and

migration in a wound healing model. It can also *in situ* deliver the GFP DNA plasmid

into three kinds of blood vessel cells via electroporation. We evaluated the efficacy

and biosafety of the electronic blood vessel in the vascular system through a three-

month *in vivo* study by using a rabbit carotid artery replacement model and confirmed

its patency by using ultrasound imaging and arteriography. Our results pave the way

to integrating flexible, degradable bio-electronics into the vascular system, which can

serve as a platform to carry out further treatments, such as gene therapies, electrical

stimulation, electronically controlled drug releases.

Results

Fabrication of the electronic blood vessel.

We fabricated the electronic blood vessel (**Figure 1A**) by rolling up a PLC based

metal-polymer conductor (MPC-PLC) membrane (**Figure 1B**) with the assistance of a

polytetrafluoroethylene (PTFE) mandrel. The MPC circuit was well distributed in the

three dimensional (3D) multilayered tubular structure. The inner diameter of the

electronic blood vessel was around 2 mm **(Figure 2A)** and the minimum diameter

could be around 0.5 mm (**Figure S1A**). The MPC-PLC membrane is flexible and

degradable and the MPC circuit is conductive (**Figure 1B-D**). The conductivity of the

MPC circuit is about $8*10^3$ S cm^{-1} and the $\Delta R/R$ of the circuit remained constant after

around 1000 cycles of bending and rubbing (**Figure 1C**). The PLC is projected to be

entirely degraded around 1~2 years by the manufacturer. The MPC-PLC membrane

underwent a mass loss of around 10% during 8-week incubation in the phosphate-

buffered saline (PBS, 37 ^{o}C) (**Figure 1D**). We observed a relatively quick degradation

in the first week (**Figure S2**). To fabricate the MPC-PLC membrane, we screen-

printed the conductive ink on the polyethylene terephthalate (PET) membrane (**Figure

1E**). The electrode design was optimized for electroporation and electrical

stimulation. By preparing different electrode designs, we could either target individual

blood vessel layers (tunica intima/media/adventitia) with the electrodes distributed in

specific areas or target all three layers with the full electrode (**Figure S1B-C**). We

prepared the liquid metal conductive ink by sonicating the mixture of Gallium-Indium

alloy (EGAIn, ≥99.99%, Sigma, US) and the volatile solvent (1-decanol, Macklin,

Shanghai) (**Figure 1F, H**). The liquid metal particles (LMPs) exhibit a core-shell

structure, where the core is the Ga-In alloy and the shell is the Ga-In Oxide (**Figure**

1G). The diameter of the LMPs is around 2 μm (**Figure 1J**). We embedded the LMPs-

based circuit with the PLC solution (5 wt % in CH_2Cl_2) and peeled the MPC-PLC

membrane off the PET substrate after evaporation of the solvent in a chemical hood

(**Figure 1E**). The thickness of the MPC-PLC membrane is about 50 μm and it is

tunable by changing the volume of the PLC solution. The LMPs could be broken

during the process of peeling and release the Ga-In alloy to make the circuit

conductive[25]. We confirmed the structure of the conductive circuit via corrosion of the

Ga-In alloy by adding excessive hydrochloric acid (HCl, Beijing Chemical Works,

China). The LMPs were evenly distributed in the cellular PLC host (**Figure 1K, L**).

The liquid metal could form a coherent conductive pathway in the polymeric host.

***In vitro* characterization of the electronic blood vessel.**

To evaluate biocompatibility of the electronic blood vessel, we used the microfluidic

technology to realize accurate 3D pattern of three kinds of blood vessel cells in a

natural blood vessel mimicking fashion. By employing a multichannel microfluidic

chip, we delivered human umbilical vein endothelial cells (HUVECs, blue), human

aortic smooth muscle cells (SMCs, green), human aortic fibroblasts (HAFs, red)

sequentially on the MPC-PLC membrane (**Figure 2A-E**). We designed the width of

each channel to match the circumference of each layer of the tube based on thickness

of the MPC-PLC membrane and the diameter of the tube (**Figure 2B**). To distinguish

different cell types, we stained the HUVECs, SMCs, HAFs with different fluorescent

dyes (HUVECs: Cell Tracker Violet; SMCs: Cell Tracker Green; HAFs: Cell Tracker

Deep red) before seeding them into the microfluidic chip. After 1 d incubation in

culture medium (Dulbecco's modified eagle medium, DMEM, 10% FBS, 37 $^\circ$C, 5%

CO_2), cells attached on the MPC-PLC membrane (**Figure 2D, H**). We peeled the

microfluidic chip off the cell-laden MPC-PLC membrane and rolled it up with a

PTFE mandrel, forming a 3D multi-layered tubular structure (**Figure 2E-G**) with

HUVECs, SMCs, and HAFs evenly distributed in the inner layer, middle layer, and

outer layer, respectively (**Figure 2I, J**). This structure well mimics the structure of the

natural blood vessel. To better understand the blood vessel cells distributed in

different layers of the electronic blood vessel, we stained HUVECs, SMCs, HAFs,

and the MPC-PLC layer with CellTracker DiO, CellTracker DiI, CellTracker DiD,

and CellTracker Blue to show the relative distribution of different layers (**Figure S3**).

We used a biomedical fibrin glue to facilitate the combination of different layers[18]. We

incubated the cell-laden electronic blood vessel for 14 d and stained the cells with the

Calcein AM green. The evenly distributed green color on the MPC-PLC membrane

indicated that the cells exhibited high viability after a 14 d culture (**Figure 2K**). We

measured the transport of ions through the MPC-PLC membrane to further evaluate

and quantify the permeability of the electronic blood vessel **(Figure S4)**. Ca^{2+}, Fe^{3+},

Mg^{2+} could permeate the electronic blood vessel over time. We also conducted a

hemolysis test, which showed that the electronic blood vessel exhibited very good

blood biocompatibility (**Figure 2L**). The *in vitro* characterization demonstrated that

the electronic blood vessel exhibited excellent biocompatibility and we then

conducted further functional tests of the embedded MPC circuits, i.e. electrical

stimulation and electroporation.

***In vitro* electrical stimulation promotes HUVEC proliferation and migration**

To prove the functionality of the electronic blood vessel, we carried out *in vitro*

electrical stimulation to improve proliferation and migration of HUVECs. Direct

current (DC) electric field has been shown to effectively increase the angiogenesis *in*

vitro and *in vivo*[26]. We patterned HUVECs on the MPC-PLC membrane (DMEM,

10% FBS, 37 °C, 5% CO_2) by using a multi-chamber PDMS chip. The initial number

of cells in each chamber was the same (3×10^4). After 12 h incubation, we applied

different DC voltages to yield different electrical field strength: 25, 50, 75 100, 200,

and 400 mV mm^{-1}, respectively (**Figure 3A, B**). After 2 d incubation and electrical

stimulation, we randomly selected 6 different domains on each sample and analyzed

by using a laser scanning confocal microscopy (LSCM, LSM 710, Zeiss, Germany).

We stained nuclei (blue) with Hoechst 33342 (Invitrogen, USA) and stained the living

and dead cells with Calcein-AM (green) and PI (red), respectively. The green cells

occupied the whole domain, indicating that electrical stimulation did not hurt

proliferation of HUVECs (**Figure 3C**). We counted the number of nuclei by using

ImageJ. The cell number under 50 mV mm^{-1} was highest, about 2.4 times that of the

control (**Figure 3E**). We used the CCK-8 kit to confirm this conclusion (**Figure 3F**).

We speculated that the DC electric field had selectively regulated production of

certain growth factors and cytokines important for angiogenesis.

We explored the migration of HUVECs under different DC electric field strengths.

We made a scratch on a PDMS substrate by using a 10 μl tip. After application of an

electric field of 50 mV mm^{-1}, HUVECs migrated 750 μm and the wound completely

healed after 24 h (**Figure 3D**). Different strengths had enhanced migration differently

compared to the control group without electrical stimulation (**Figure 3G**). The *in vitro*

DC electrical stimulation thus proved to have effectively promoted the proliferation

and migration of HUVECs.

We further evaluated the effectiveness of electrical stimulation in a 3D model of

endothelization. We patterned the HUVECs on the MPC-PLC membrane and made a

scratch on the cell-laden membrane by using a 10 μl tip. We transformed the 2D cell-

laden membrane into 3D cell-laden structure and connected it to the electrochemical

station to test the proliferation and migration. We applied an electric field of 50 mV

mm^{-1} on multiple samples and we observed the proliferation and migration at different

time points. We stained the living and dead cells with Calcein-AM (green) and PI

(red). We counted the cell number and the cell density was higher than the control

group (Figure 3H). The HUVECs formed a complete endothelial layer after 24 h

(Figure 3I). To better evaluate the biocompatibility of the MPC circuit under electrical

stimulation, we extended the electrical stimulation time to 10 days and the live/dead

staining showed that cells exhibited excellent viability (Figure S5).

In vitro **electroporation**

To further prove the functionality of the electronic blood vessel, we designed multiple

circuit patterns for electroporation, being able to target different pathological issues in

different layers of blood vessel cells (**Figure S1B**). We conducted the electroporation

with a circuit pattern that could target all three layers. We seeded the cells onto the

MPC-PLC membrane and transformed it into 3D tubular structure for electroporation.

We immersed the 3D cell-laden electronic blood vessel in the GFP plasmid DNA

solution for 10 min before electroporation. The GFP plasmid DNA could also be

lyophilized onto the MPC-PLC membrane before seeding cells (**Figure S7A**) and

transforming to 3D structure for electroporation. We connected the 3D cell-laden

electronic blood vessel with an electroporator (BTX, CM630, US) to generate DC

pulses (**Figure 4A**) and achieved the delivery of the green fluorescent protein (GFP)

DNA plasmid in three kinds of blood vessel cells (**Figure 4B**). To optimize the

performance of the electronic blood vessel, we found two major parameters

determining the efficacy of electroporation, including voltage and pulse duration. We

conducted the electroporation with different voltages (40 V/60 V/80 V) and pulse

durations (100 μs/1 ms). If the voltage was too low, it would cause low efficacy or no

transfection; if the voltage was too high or if the pulse duration was too long, it would

cause low efficacy and cell death (**Figure S6**). To realize the optimal efficacy, we

exerted a square wave with the voltage of 60 V, pulse duration of 100 μs, and pulse

interval of 1 s for 5 times. We delivered GFP plasmid DNA into three kinds of blood

vessel cells and the GFP DNA realized expression with more than 95% of cells

showing green fluorescence (**Figure 4B**). We observed successful expression of GFP

among all three layers of the blood vessel cells and exhibited a uniform 3D

distribution in the electronic blood vessel **(Figure 4C)**. To evaluate the potential of

the electronic blood vessel for *in vivo* electroporation, we lyophilized the GFP

plasmids DNA on the MPC-PLC membrane to test its effectiveness **(Figure S7A)**. We

carried out electroporation by attaching the plasmids-laden MPC-PLC membrane to

an isolated rabbit vascular tissue with the voltage of 60 V, pulse duration of 100 μs,

and pulse interval of 1 s for 5 times. We observed successful expression of GFP in the

isolated rabbit vascular tissue **(Figure S7A)** after 2 d incubation. These promising *in*

vitro results encouraged us to carry out the *in vivo* tests of the electronic blood vessel.

Mechanical properties of the electronic blood vessel

To find out whether the electronic blood vessel is suitable for *in vivo* implantation, we

measured the mechanical properties, including stress-strain curve, compliance, and

burst pressure, of the electronic blood vessel with a diameter of 2 mm prior to

implantation (**Figure 5A-F and Figure S8**). The elastic modulus of the electronic

blood vessel is about 130 MPa, the value is much higher than the native carotid artery.

The ultimate tensile strength of the electronic blood vessel is about 27 MPa, the value

is also much higher than that of the native carotid artery. The initial compliance of the

electronic blood vessel (n= 5) is about 5% per 100 mmHg in the range of 80-120

mmHg, the value is apparently below that of the native carotid artery (n= 3). The

burst pressure of the electronic blood vessel (n= 5) is about 2800 mmHg, the value is

similar to that of the native carotid artery (n= 3). The elongation at break of the

electronic blood vessel is about 650% (n= 5), which is the twice as the value of native

carotid artery (n= 3). The mechanical property of electronic blood vessel was

considered robust enough for implantation.

***In vivo* implantation in rabbits and *in situ* monitoring**

To investigate the electronic blood vessel as a vascular implant, we chose the New

Zealand rabbit (age: 200-300 days, body weight: 3-4 kg) as the animal model and

replaced the native carotid artery with the electronic blood vessel (**Figure 6A-C**). To

avoid possible immunological response of the host tissue, we used the acellular

electronic blood vessel in the preliminary *in vivo* study. We *in situ* monitored the

implanted electronic blood vessel by doppler ultrasound imaging (**Figure 6D-I**) and

the arteriography (**Figure 6J, K**). Doppler ultrasound imaging showed that the

electronic blood vessel allowed for good blood flow 3 months post-implantation

(**Figure 6D-G and Video S1**). The asymmetric velocity curve synchronized with the

ultrasonic pulses indicated that the signal is from the carotid artery rather than the

vein (**Figure 6D**). The diameter of the electronic blood vessel remained at a relatively

constant value, about 2.3 mm, during the half month to three months post-

implantation (**Figure 6G, H**). The mean velocity of the blood flow in different

samples at different time point was about 0.47 m s^{-1}, which was in the range of the

normal value (**Figure 6I**). As the gold standard of the blood vessel patency,

arteriography showed that the electronic blood vessel matched with the native carotid

artery very well and allowed for excellent blood flow (**Figure 6J, K, Figure S9, and**

Video S2). There was no sign of narrowing. The electronic blood vessel allows

straightforward visualization under arteriography because the liquid metal-based

circuitry has sufficiently high contrast over host tissues (**Figure 6J**). The red frame

outlined the electronic blood vessel with an alternate strip structure from the MPC

circuit.

Ex vivo **study**

We dissected all the implanted electronic blood vessels three months post-

implantation for characterization. The lumen and the outer surfaces of the explanted

electronic blood vessel were smooth, covered by the remodeling tissues (**Figure 7A,**

B). The diameter of the native blood vessel significantly reduced due to the lack of the

blood pressure, whereas the electronic blood vessel remained the same as before

(**Figure 7C**). We observed the micro structure of the circuit by using the SEM after

explanting the electronic blood vessel from rabbit. The MPC-PLC membrane still

maintained interdigitated structure with the MPC circuit and PLC host (**Figure 7E**).

There was a layer of neo-tissue formed, which well covered the MPC-PLC membrane

(**Figure 7F-H**). We could also see some red blood cells on the top of the circuits,

which were similar in number to those on native blood vessels (**Figure 7D**). We tested

the conductivity of the circuit in the electronic blood vessel. The MPC circuit was still

conductive and the conductivity was around $7.2 *10^3$ S cm^{-1}.

To study the histological changes of the implanted electronic blood vessels, we

performed histological staining of the electronic blood vessels, setting native carotid

blood vessel as a positive control. Hematoxylin/eosin (H&E) staining (**Figure 7I**) of

the cross section of the electronic blood vessel is round-shaped, continuous, red,

which is similar as the native blood vessel. The three-layered MPC-PLC membrane

merged into one intact layer with secretion of substantial extracellular matrix between

the different layers of electronic blood vessel. We could clearly see dark blue nuclei

(red arrows in Figure 7I) in all the layers, which indicated successful migration and

infiltration of host cells into the electronic blood vessel. We compared the cell density

in the electronic blood vessel with the native carotid. The cell density of the electronic

blood vessel was around 400 cells mm^{-2} whereas that of the native carotid was around

535 cells mm^{-2}. More importantly, a dense layer of cells with curved structure were

formed in the lumen of the electronic blood vessel, which indicated the excellent

endothelization and thus ensured good blood flow. To further confirm the components

in the implanted electronic blood vessel, we performed Masson's trichrome (**Figure**

7J) and Verhoeff's staining (**Figure 7K**). Masson's trichrome staining can stain and

assess keratin and muscle fibers (red) or collagen (blue) and Verhoeff's staining can

stain and assess the presence of elastin fibers. Masson's trichrome and Verhoeff's

staining showed well-distributed collagen and elastin fibers both inside the layers and

between different layers, indicating appropriate remodeling. Compared to the

abundance level of extracellular matrix in the native blood vessel, the electronic blood

vessel still requires more time for material degradation and tissue remodeling. These

results indicated that the electronic blood vessel might still be functioning with the

presence of conductive materials and host remodeling 3 months post-implantation.

To investigate the influence of the electronic blood vessel on the host, we

performed the cross section and histological staining of the major organs, including

heart, liver, spleen, lung, and kidney, together with the dissection of the implanted

electronic blood vessel 3 months post-implantation. The H&E staining and Masson's

Chrome staining showed that there was no significant pathological changes or

inflammatory responses in these organs (**Figure S10**). To evaluate whether there were

chronic inflammation or infection, we conducted the ELISA assay of three important

proteins in the blood, including interleukin-6 (IL-6), procalcitonin (PCT), and C-

reactive protein (CRP) (**Figure S11**). The concentrations of IL-6 and PCT were not

higher than the normal value of healthy rabbits (red dotted lines). The concentration

of CRP was higher than the normal value of healthy rabbits (red dotted line). All three

indexes decreased over time, a tendency that was expected. The results showed that

most of the indexes were in the normal range and there were no significant

pathological changes or inflammatory responses. We also conducted the complete

blood count of the rabbit, including white blood cell count, absolute neutrophil count,

and absolute lymphocyte count, most of which were in the normal range over time

(**Figure S12**). These results confirmed that as an implant for vascular system, the

electronic blood vessel had no significant detriment to the host.

Discussion

None of the existing small-diameter TEBVs has met the demands in treating

cardiovascular diseases. Conventional TEBVs can be greatly improved to provide

next-generation treatment by integrating with flexible bioelectronics. In this work, we

report an electronic blood vessel with excellent biocompatibility, flexibility,

mechanical strength, and degradability by combining the MPC with a US FDA-

approved biodegradable polymer. As a proof of concept, we verified that the

electronic blood vessel can accelerate the HUVEC proliferation and migration by

electrical stimulation, thus facilitating the endothelization process, which is important

to an engineered vascular conduit in preventing early thrombosis. Because most

TEBVs occluded with 2 weeks post-implantation, our electronic blood vessel, with a

patency of at least 12 weeks, is of great promise for clinical application. We also

showcased that it could be used to perform *in situ* gene delivery via electroporation,

which laid a foundation for future design and optimization such that we can carry out

further gene therapies targeting different pathological problems after implantation.

The electronic blood vessel has a high level of safety. The liquid metal[16,27] has been

proven to be highly biocompatible and the PLC has been approved by the US FDA for

implants[28]. We validated its biosafety in the vascular system by a 3-month

implantation in a rabbit carotid artery model. Both the *in situ* monitoring, including

doppler ultrasound imaging and arteriography, and *ex vivo* study demonstrated that it

was safe as an electronic implant in the vascular system and at the body level. The

electronic blood vessel exhibited higher strength than the native blood vessel. The

potential harm of a rigid synthetic blood vessel is the mismatch with host tissue after

implantation. However, from the in vivo results, these discrepancies did not bring

about any major issues and the electronic blood vessel matched very well with the

host carotid artery during the time of *in situ* monitoring (Figure 6J, K, Video S2). The

reasons why we chose liquid metal in the electronic blood vessel are as following: i)

comparing with gold or platinum, the Ga-In liquid metal allows superior flexibility

and stretchability while maintains good conductivity, which is critical for an artificial

blood vessel to adapt to the deformation due to the rhythmic beating; ii) it exhibits

excellent cytocompatibility and blood compatibility according to our results; iii)

compared to other sophisticated microfabrication techniques, using the screen printing

technique is much more straightforward and could enable industrial-scale mass

production in a cost-effective manner.

As a vascular substitute, the electronic blood vessel breaks through the limitations

of the existing vascular scaffold by endowing the electrical function to conventional

biodegradable TEBV and provides us a new platform for tackling the problems

threatening the small-diameter blood vessel. By integrating with other electronic

devices, the electronic blood vessel can provide various treatments, such as electrical

stimulation, electroporation, electrically controlled drug release, and so forth. When

combining with emerging technologies such as artificial intelligence, it can greatly

boost future personalized medicine by bridging the vascular tissue-machine interface

and empowering the health data collection and storage, such as blood velocity, blood

pressure, and blood glucose level. In the future, optimizing its function and creating a

multifunctional electronic blood vessel can greatly benefit human cardiovascular

health.

Conclusions

In this work, by integrating the liquid metal-based conducting circuitry with a

biodegradable polymer, we develop an electronic blood vessel, with excellent

biocompatibility, flexibility, conductivity, mechanical strength, and degradability, that

enables *in situ* electrical stimulation to facilitate the endothelization process and

electroporation to deliver genes in specific layers of blood vessel cells. It exhibited

excellent patency and biosafety 3 months post-implantation in the vascular system of

a rabbit model. In the future, the electronic blood vessel can be integrated with other

electronic components and devices to enable diagnostic and therapeutic functions and

greatly empower personalized medicine by creating a direct link of vascular tissue-

machine interface.

Supplemental Information

Supplemental Information can be found online.

Acknowledgements

This study was supported by the National Key R&D Program of China

(2018YFA0902600, 2017YFA0205901), the National Natural Science Foundation of

China (21535001, 81730051, 21761142006, 51973045), the Chinese Academy of

Sciences (QYZDJ-SSW-SLH039, 121D11KYSB20170026, XDA16020902),

Shenzhen Bay Laboratory (SZBL2019062801004), the Tencent Foundation through

the XPLORER PRIZE, Beijing Science and Technology Plan Project

(Z191100007619053), Postgraduate Innovation Foundation of Peking Union Medical

College (2019-1002-28) and Teaching Reform Foundation of Postgraduate Education

in Peking Union Medical College (10023201900202). We thank Dr. Zewen Wei and

Dr. Deyao Zhao for discussions on the electroporation experiment. We thank Mrs.

Barbara Althaus at EPFL for her advice in writing the manuscript.

Author Contributions

X. J. and S. C. conceived the idea. S. C. designed the experiments, fabricated the

blood vessel, conducted the characterization, *in vitro* tests, mechanical tests, *in vivo*

tests and *ex vivo* tests, analyzed the data, and wrote the manuscript. C. H. fabricated

the blood vessel, performed *in vitro* tests, mechanical tests, and *in vivo* tests. L. D.

performed the *in vivo* and *ex vivo* tests. S. C., C. H., and L. D. contributed equally. L.

T. assisted with the preparation of the liquid metal particles, MPC-PLC membrane

and the electroporation experiments. L. J. and Y. Z. performed the implantation of the

electronic blood vessel, doppler ultrasound imaging and arteriography. L. M.

conducted the ELISA assay. J. Q. and R. D. assisted the TEM characterization. W. Z.

gave inputs on the *in vitro* tests and *ex vivo* tests. Y. Z. supervised the *in vivo* and *ex*

vivo study. X. J. supervised the project, and revised the manuscript. All the authors

took part in the discussion and writing.

Declaration of Interests

S. C. and X. J. declare financial interest in form of a patent application. Other authors

declare no competing financial interests.

Data Availability

All data are available from the corresponding authors upon reasonable request.

References and Notes

1. WHO | World Health Statistics 2019: Monitoring health for the SDGs. *World Heal. Organ.* (2019).

2. Seifu, D. G., Purnama, A., Mequanint, K. & Mantovani, D. (2013). Small-diameter vascular tissue engineering. *Nat. Rev. Cardiol.* **10**, 410–421.

3. Quint, C. *et al.* (2011). Decellularized tissue-engineered blood vessel as an arterial conduit. *Proc. Natl. Acad. Sci.* **108**, 9214–9219.

4. Dahl, S. L. M. *et al.* (2011). Readily available tissue-engineered vascular grafts. *Sci. Transl. Med.* **3**, 68ra9.

5. Lawson, J. H. *et al.* (2016). Bioengineered human acellular vessels for dialysis access in patients with end-stage renal disease: two phase 2 single-arm trials. *Lancet* **387**, 2026–2034.

6. Zhu, M. *et al.* (2019). In vivo engineered extracellular matrix scaffolds with instructive niches for oriented tissue regeneration. *Nat. Commun.* **10**, 4620.

7. Kirkton, R. D. *et al.* (2019). Bioengineered human acellular vessels recellularize and evolve into living blood vessels after human implantation. *Sci. Transl. Med.* **11**, 1–12.

8. L'Heureux, N. *et al.* (2006). Human tissue-engineered blood vessels for adult arterial revascularization. *Nat. Med.* **12**, 361–365.

9. L'Heureux, N., McAllister, T. N. & de la Fuente, L. M. (2007). Tissue-engineered blood vessel for adult arterial revascularization. *N. Engl. J. Med.* **357**, 1451–1453.

10.   L'Heureux, N. *et al.* (2007). Technology insight: the evolution of tissue-

engineered vascular grafts - from research to clinical practice. *Nat. Clin. Pract.*

Cardiovasc. Med. **4**, 389–395.

11.   Peck, M., Dusserre, N., McAllister, T. N. & L'Heureux, N. (2011). Tissue

engineering by self-assembly. *Mater. Today* **14**, 218–224.

12.   Wu, W., Allen, R. A. & Wang, Y. (2012). Fast-degrading elastomer enables

rapid remodeling of a cell-free synthetic graft into a neoartery. *Nat. Med.* **18**,

1148–1153.

13.   Cheng, S. *et al.* (2017). Self-Adjusting, polymeric multilayered roll that can

keep the shapes of the blood vessel scaffolds during biodegradation. *Adv.*

Mater. **29**, 1700171.

14.   Akentjew, T. L. *et al.* (2019). Rapid fabrication of reinforced and cell-laden

vascular grafts structurally inspired by human coronary arteries. *Nat. Commun.*

10, 1–15.

15.   Hoenig, M. R., Campbell, G. R., Rolfe, B. E. & Campbell, J. H. (2005). Tissue-

engineered blood vessels: alternative to autologous grafts? *Arterioscler.*

Thromb. Vasc. Biol. **25**, 1128–1134.

16.   Yan, J., Lu, Y., Chen, G., Yang, M. & Gu, Z. (2018). Advances in liquid

metals for biomedical applications. *Chem. Soc. Rev.* **47**, 2518–2533.

17.   Choi, S., Han, S. I., Kim, D., Hyeon, T. & Kim, D. H. (2019). High-

performance stretchable conductive nanocomposites: Materials, processes, and

device applications. *Chem. Soc. Rev.* **48**, 1566–1595.

18.   Son, D. *et al.* (2015). Bioresorbable electronic stent integrated with therapeutic

451   nanoparticles for endovascular diseases. *ACS Nano* **9**, 5937–5946.

452   19.   Du, Z. J., Bi, G. Q. & Cui, X. T. (2018). Electrically controlled neurochemical

453   release from dual-layer conducting polymer films for precise modulation of

454   neural network activity in rat barrel cortex. *Adv. Funct. Mater.* **28**, 1–12.

455   20.   Gong, P. *et al.* (2013). A strategy for the construction of controlled, three-

456   dimensional, multilayered, tissue-like structures. *Adv. Funct. Mater.* **23**, 42–46.

457   21.   Jin, Y. *et al.* (2013). Stress-induced self-assembly of complex three

458   dimensional structures by elastic membranes. *Small* **9**, 2410–2414.

459   22.   Yuan, B. *et al.* (2012). A strategy for depositing different types of cells in three

460   dimensions to mimic tubular structures in tissues. *Adv. Mater.* **24**, 890–896.

461   23.   Wang, N. *et al.* (2016). A strategy for rapid and facile fabrication of controlled,

462   layered blood vessel-like structures. *RSC Adv.* **6**, 55054–55063.

463   24.   Tang, L., Mou, L., Zhang, W. & Jiang, X. (2019). Large-scale fabrication of

464   highly elastic conductors on a broad range of surfaces. *ACS Appl. Mater.*

465   *Interfaces* **11**, 7138–7147.

466   25.   Tang, L. *et al.* (2018). Printable metal-polymer conductors for highly

467   stretchable bio-devices. *iScience* **4**, 302–311.

468   26.   Bai, H., McCaig, C. D., Forrester, J. V. & Zhao, M. (2004). DC electric fields

469   induce distinct preangiogenic responses in microvascular and macrovascular

470   cells. *Arterioscler. Thromb. Vasc. Biol.* **24**, 1234–1239.

27.   Lu, Y. *et al.* (2015). Transformable liquid-metal nanomedicine. *Nat. Commun.*

6, 10066.

28. Kenar, H. *et al.* (2019). Microfibrous scaffolds from poly(L-lactide-co-ε-

caprolactone) blended with xeno-free collagen/hyaluronic acid for

improvement of vascularization in tissue engineering applications. *Mater. Sci.*

Eng. C **97**, 31–44.

Figure 1. Fabrication and characterization of the electronic blood vessel. (A)

Snapshots of the electronic blood vessel. Scale bar, 4 mm. **(B)** Snapshots of the MPC-

PLC membrane. Scale bar, 1 mm. **(C)** ΔR/R changes with a bend of 180º for 1000

cycles (n=3). **(D)** Mass loss of the MPC-PLC membrane during 8-week incubation

(n=3 for each time point). **(E)** Schematic of fabrication of the MPC-PLC membrane.

(F) Schematic of fabrication of LMPs. **(G)** TEM image of the Ga-In particle. **(H)**

Photographs of mixture of the Ga-In alloy and the solvent, and the LMP ink after

sonication. **(I)** Representative SEM images of LMPs. Scale bar, 2 μm. **(J)** Diameter

distribution of LMPs (n =200). **(K)** SEM images of the MPC-PLC circuit. White

arrowheads indicate the PLC host and MPC-PLC membrane. Scale bar, 50 μm. Right

is the Zoom-in view. White arrowheads indicate the PLC and LMP ink. LMPs were

embedded by the PLC as the host polymer. Scale bar, 4 μm. **(L)** SEM images of the

MPC-PLC circuit after corrosion by excessive hydrochloric acid. Scale bar, 50 μm.

Right is the Zoom-in view. LMPs were fully removed by corrosion. The porous

structure only consisted of the PLC. Scale bar, 4 μm.

Figure 2. ***In vitro*** **biocompatibility of the electronic blood vessel. (A)** The MPC-

PLC membrane. **(B)** Attaching a multichannel microfluidic chip onto the MPC-PLC

membrane. **(C, D)** Patterning three kinds of blood vessel cells (blue: HUVECs, green:

SMCs, red: HAFs) onto the MPC-PLC membrane by using PDMS microfluidic chip.

(E, F) Rolling the cell-laden membrane into a multi-layered tubular structure with a

PTFE mandrel. **(G)** Cross-sectional view of natural blood vessel mimicking structure

with different cells distributed in different layers. **(H)** Fluorescent images of cells on

the MPC-PLC membrane, in corresponding to (D). Stained by CellTracker violet,

green, deep red, respectively. Scale bar, 20 μm. **(I)** Three kinds of blood vessel cells

distributed in different layers of the electronic blood vessel. Scale bar, 500 μm. **(J)** 3D

construction of (I). **(K)** Cell viability after 2-week incubation in the electronic blood

vessel. Stained by CellTracker green. The right column is the 3D reconstruction of the

left column in each image. The black area represents the MPC circuit and the

transparent area represents the PLC in bright-field images. **(L)** Hemolysis test. The

MPC circuit, PLC membrane, and liquid metal with different concentrations were

tested with the rabbit whole blood and exhibited good blood compatibility. Saline was

used as the positive control whereas water was used as the negative control.

Figure 3. *In vitro* electrical stimulation. (A-B) The electronic blood vessel was

connected to electrochemical station (A) to generate a direct current voltage (B). **(C)**

Confocal fluorescent images of HUVEC proliferation after 2 d incubation and

stimulation under different DC electric field: 25, 50, 75, 100, 200, 400 mV/mm,

respectively. Blue, DAPI; green, Calcein AM; red, PI. **(D)** Confocal fluorescent

images of HUVEC migration after 24 h incubation and stimulation under different

DC electric field: 25, 50, 75, 100, 200, 400 mV/mm, respectively. Stained by Calcein

AM. Scale bar, 400 μm. A 10 μl tip was used to scratch a line to create a model for

HUVECs migration. **(E)** The proliferation of HUVECs under different DC electrical

field, setting the control (without electric field) as 100%. (n=4). **(F)** The proliferation

of HUVECs under different DC electrical field tested with the CCK-8 kit. (n=4). **(G)**

The migration of HUVECs at different DC electrical field (n=4). **(H)** The

proliferation of HUVECs in a 3D model under DC electric field of 50 mV/mm.

Stained by Calcein AM. **(I)** The migration of HUVECs in a 3D model under DC

electric field of 50 mV/mm. Stained by Calcein AM. The HUVECs formed a

complete endothelial layer after 24 h electrical stimulation.

Figure 4. *In vitro* electroporation. (A) The electronic blood vessel was connected to

an electroporator to generate electrical pulses. **(B)** Confocal fluorescent images of

HUVECs, SMCs, and HAFs after electroporation under condition: voltage 60 V;

pulse duration 100 μs; 5 pulses; pulse interval 1 s. Upper: HUVECs; middle: HAFs;

lower: SMCs. Blue represents cell nucleus, stained by DAPI; red represents cell

skeleton, stained by Rhodamine Phalloidin; green represents GFP; black represents

that cells were on the top of non-transparent MPC-PLC circuit, bright field. Scale bar,

20 μm. **(C)** 3D distribution of HUVECs, SMCs, HAFs after electroporation under

condition: voltage 60 V; pulse duration 100 μs; 5 pulses; pulse interval 1 s. Blue

represents HUVECs, stained by CellTracker Blue; yellow represents SMCs, stained

by CellTracker DiI; red represents HAFs, stained by CellTracker DiD; green

represents green fluorescent protein. Scale bar, 200 μm.

Figure 5. Mechanical properties of the electronic blood vessel. (A) Stress-strain

curve. **(B)** Compliance test. **(C)** Burst pressure test. **(D)** Elongation at break. **(E)**

Modulus of elasticity. **(F)** Ultimate tensile strength. Electronic blood vessel (n= 5) and

native carotid artery (n= 3) were used in each test. All data are expressed as mean ±

SD.

Figure 6. *In situ* monitoring of the electronic blood vessel. (A) Schematic of the

electronic blood vessel in the carotid artery of the rabbit. **(B, C)** An end-to-end

anastomosis procedure of electronic blood vessel implantation on carotid arteries of

rabbits (n=6). The dotted frames outline the margin of the native carotid artery and the

implanted electronic blood vessel. The white arrows indicate two ends of the

electronic blood vessel. Scale bar, 1 cm. **(D-G)** *In situ* monitoring of the electronic

blood vessel by doppler ultrasound imaging 3 months post-implantation.

Representative images from at least three different animals. **(D, E)** The real-time

blood flow at the operational site and the synchronized ultrasound pulses. The

asymmetric velocity curve represents the signal is from carotid artery rather than vein.

(E) Zoom-in view of red box in (D). **(F)** The cross view of the blood flow. **(G)** The

suture site (red arrows) connecting the native carotid artery and the electronic blood

vessel. **(H)** The diameter changes of the electronic blood vessel in different time post-

implantation. **(I)** The velocity of blood flow at the operational site (n=18, from

different rabbits at different time points). **(J, K)** *In situ* monitoring by arteriography 3

months post-implantation. **(J)** Image before injecting the contrast media. Red box

indicates the position of the implanted electronic blood vessel. **(K)** Image after

injecting the contrast media. Red box indicates the position of the implanted blood

vessel. Red arrows indicate the suture sites connecting the native carotid artery and

the electronic blood vessel.

Figure 7. *Ex vivo* study of the electronic blood vessel after 3 months implantation

in the rabbit. (A-C) The cross-sectional (A) and lateral view (B, C) of the explanted

electronic blood vessel after 3-month host remodeling. Red arrows and the dotted line

indicate the suture site connecting the native carotid artery (right) and the electronic

blood vessel (left). Scale bar, 1 mm. **(D)** Representative SEM image of the lumen of

the native carotid. Scale bar, 10 μm. (**E**) Representative SEM image of the lumen of

the electronic blood vessel. Scale bar, 300 μm. **(F-H**) Zoom-in view of the MPC

circuit (F), PLC host (G) and the interconnection area of MPC circuit and PLC host

(H). Scale bar, 10 μm. **(I-K)** Hematoxylin/eosin (H&E) staining, Masson's trichrome

staining, and Verhoeff's staining of the implanted electronic blood vessel 3 months

586   post-implantation, setting native carotid artery as control. The right panel is the zoom-

587   in view of the left panel. Scale bar (left), 500 μm. Scale bar (right), 50 μm.