Title: Electronic blood vessel

Authors: Shiyu Cheng[1,2,4†], Chen Hang[1,2†], Li Ding[1,2,3†], Liujun Jia[3], Lixue Tang[2], Lei

Mou[1,2], Jie Qi[1,2], Ruihua Dong[1,2], Wenfu Zheng[2], Yan Zhang[3]*, Xingyu Jiang[1,2]*

Affiliations:

[1]Department of Biomedical Engineering and Shenzhen Bay Laboratory, Southern

University of Science and Technology, Shenzhen, Guangdong 518055, China.

[2]National Center for NanoScience and Technology, University of Chinese Academy

of Sciences, Beijing 100190, China.

[3]State Key Laboratory of Cardiovascular Disease, Fuwai Hospital, National Center

for Cardiovascular Diseases, Chinese Academy of Medical Sciences and Peking

Union Medical College, Beijing 100037, China.

[4]Current address: Institute of Bioengineering, School of Engineering, Ecole

Polytechnique Federale de Lausanne, Lausanne 1015, Switzerland.

*To whom correspondence should be addressed: jiang@sustech.edu.cn;

waikezhangyan@126.com

†These authors contributed equally to this work.

Abstract

Advances in bioelectronics have great potential to address unsolvable biomedical

problems in the cardiovascular system. By using poly(L-lactide-co-ε-caprolactone)

(PLC) that encapsulates the liquid metal to make flexible and bio-degradable

electrical circuitry, we develop an electronic blood vessel that can integrate flexible

electronics with three layers of blood vessel cells, to mimic and go beyond the natural

blood vessel. It can improve the endothelization process through electrical stimulation

and can enable controlled gene delivery into specific part of the blood vessel via

electroporation. The electronic blood vessel has excellent biocompatibility in the

vascular system and shows great patency three months post-implantation in a rabbit

model. The electronic blood vessel would be an ideal platform to enable diagnostics

and treatments in the cardiovascular system and can greatly empower personalized

medicine by creating a direct link of vascular tissue-machine interface.

Introduction

Cardiovascular diseases remain the number one cause of mortality worldwide[1]. In treating cardiovascular diseases via coronary artery bypass grafting (CABG) surgery, none existing small diameter (<6 mm) tissue engineered blood vessel (TEBV) has met clinical demands[2]. To fabricate the TEBV, a range of approaches, such as decellularized matrix[3–7], self-assembly cell sheets[8–11], bioactive and biomimetic materials[12–14], were developed and clinically investigated in recent years. However, most of these methods only serve as scaffolds to provide mechanical support and mainly rely on the remodeling process by the host tissue and present significant limitations in helping the regeneration of neo blood vessel. Thus far, none of them have achieved satisfactory clinical results. Specifically, a complex interplay between the blood flow and the TEBV can often cause inflammatory responses, resulting in thrombosis, neointimal hyperplasia or smooth muscle cell accumulation nearby the scaffold[2,15], in different pathological stages. To address these issues, next-generation TEBV should not only function as scaffolds to provide the mechanical support and facilitate host cell recruitments, but also have the capability to actively respond to and couple with the native remodeling process in order to provide adaptive treatments after implantation.

Combining living tissues with flexible electronics[16,17] could endow the conventional TEBV more functionalities and capabilities to overcome existing biomedical problems, such as precision diagnostics, by *in situ* sensing the blood flow and temperature, and treatments by therapeutic drug or gene delivery[18,19]. In previous

works, we have developed many approaches to fabricate structures that mimic natural

blood vessel with multiple types of blood vessel cells in different layers, including

stress-induced self-rolling membrane[13,20–22] and layer by layer technique[23]. Recently,

we have developed a printable metal-polymer conductor (MPC) which exhibited

excellent compatibility and high stretchability[24,25]. Here, we develop an electronic

blood vessel that integrates flexible electrodes into the bio-degradable scaffold by

combining the liquid metal with poly(L-lactide-co-ε-caprolactone) (PLC) into a

metal-polymer conductor. We evaluated the efficacy and biosafety of the electronic

blood vessel in the vascular system through a three-month *in vivo* study by using a

rabbit carotid artery replacement model and confirmed its patency by using ultrasound

imaging and arteriography. As a proof of principle, we used the electronic blood

vessel to carry out *in vitro* electrical stimulation and electroporation. By electrical

stimulation, the electronic blood vessel can effectively promote cell proliferation and

migration in a wound healing model. It can also *in situ* deliver the GFP DNA plasmid

into three kinds of blood vessel cells via electroporation. Our results pave the way to

integrating flexible, degradable bio-electronics into the vascular system, which can

serve as a platform to carry out further treatments, such as gene therapies, electrical

stimulation, electronically controlled drug releases.

Results

Fabrication of the electronic blood vessel.

We fabricated the electronic blood vessel (**Fig. 1a**) by rolling up a PLC based metal-polymer conductor (MPC-PLC) membrane (**Fig. 1b**) with the assistance of a polytetrafluoroethylene (PTFE) mandrel. The MPC circuit was well distributed in the three dimensional (3D) multilayered tubular structure. The inner diameter of the electronic blood vessel was about 2 mm. The MPC-PLC membrane is flexible, conductive, and degradable (**Fig. 1b-d**). The conductivity of the MPC circuit is about $8*10^3$ S cm^{-1} and the $\Delta R/R$ of the circuit remained constant after around 1000 cycles of bending and rubbing (**Fig. 1c**). The PLC is projected to be entirely degraded around 1~2 years by the manufacturer. The MPC-PLC membrane underwent a mass loss of around 10% during 8-week incubation in the phosphate-buffered saline (37 ^{o}C) (**Fig. 1d**). To fabricate the MPC-PLC membrane, we screen-printed the conductive ink on the polyethylene terephthalate (PET) membrane (**Fig. 1e**). The electrode design was optimized for electroporation and electrical stimulation (**Supplementary Fig. 1**). We prepared the liquid metal conductive ink by sonicating the mixture of Gallium-Indium alloy (EGAIn, ≥99.99%, Sigma, US) and the volatile solvent (1-decanol, Macklin, Shanghai) (**Fig. 1f, h**). The liquid metal particles (LMPs) exhibit a core-shell structure, where the core is the Ga-In alloy and the shell is the Ga-In Oxide (**Fig. 1g**). The diameter of the LMPs is around 2 μm (**Fig. 1j**). We embedded the LMPs-based circuit with the PLC solution (5 wt % in CH_2Cl_2) and peeled the MPC-PLC membrane off the PET substrate after evaporation of the solvent in a chemical hood

(**Fig. 1e**). The thickness of the MPC-PLC membrane is about 50 μm and it is tunable

by changing the volume of the PLC solution. The LMPs could be broken during the

process of peeling and release the Ga-In alloy to make the circuit conductive[25]. We

confirmed the structure of the conductive circuit via corrosion of the Ga-In alloy by

adding excessive hydrochloric acid (HCl, Beijing Chemical Works, China). The

LMPs were evenly distributed in the cellular PLC host (**Fig. 1k, l**). The liquid metal

could form a coherent conductive pathway in the polymeric host. We tested the

mechanical properties of the electronic blood vessel for the *in vivo* study (**Fig. 1m-r**).

Fig. 1. Fabrication and characterization of the electronic blood vessel. a,

Snapshots of the electronic blood vessel. Scale bar, 4 mm. **b**, Snapshots of the MPC-

PLC membrane. Scale bar, 1 mm. **c**, $\Delta R/R$ changes with a bend of 180° for 1000

cycles (n=3). **d**, Mass loss of the MPC-PLC membrane during 8-week incubation

(n=3 for each time point). **e**, Schematic of fabrication of the MPC-PLC membrane. **f**,

Schematic of fabrication of LMPs. **g**, TEM image of the Ga-In particle. **h**,

Photographs of mixture of the Ga-In alloy and the solvent, and the LMP ink after

sonication. **i**, Representative SEM images of LMPs. Scale bar, 2 μm. **j**, Diameter

distribution of LMPs (n =200). **k**, SEM images of the MPC-PLC circuit. White

arrowheads indicate the PLC host and MPC-PLC membrane. Scale bar, 50 μm. Right

is the Zoom-in view. White arrowheads indicate the PLC and LMP ink. LMPs were

embedded by the PLC as the host polymer. Scale bar, 4 μm. **l**, SEM images of the

MPC-PLC circuit after corrosion by excessive hydrochloric acid. Scale bar, 50 μm.

Right is the Zoom-in view. LMPs were fully removed by corrosion. The porous

structure only consisted of the PLC. Scale bar, 4 μm. **m-r**, Mechanical properties of

the electronic blood vessel. **m**, Stress-strain curve. **n**, Compliance test. **o**, Burst

pressure test. **p**, Elongation at break. **q**, Modulus of elasticity. **r**, Ultimate tensile

strength. Electronic blood vessel (n= 5) and native carotid artery (n= 3) were used in

each test. All data are expressed as mean ± SD.

***In vitro* characterization of the electronic blood vessel.**

To evaluate biocompatibility of the electronic blood vessel, we used the microfluidic

technology to realize accurate 3D pattern of three kinds of blood vessel cells in a

natural blood vessel mimicking fashion. By employing a multichannel microfluidic

chip, we delivered human umbilical vein endothelial cells (HUVECs, blue), human

aortic smooth muscle cells (SMCs, green), human aortic fibroblasts (HAFs, red)

sequentially on the MPC-PLC membrane (**Fig. 2a-e**). We designed the width of each

channel to match the circumference of each layer of the tube based on thickness of the

MPC-PLC membrane and the diameter of the tube (**Fig. 2b**). To distinguish different

cell types, we stained the HUVECs, SMCs, HAFs with different fluorescent dyes

(HUVECs: Cell Tracker violet; SMCs: Cell Tracker green; HAFs: Cell Tracker deep

red) before seeding them into the microfluidic chip. After 1 d incubation in culture

medium (Dulbecco's modified eagle medium, DMEM, 10% FBS, 37 $^{\circ}$C, 5% CO_2),

cells attached on the MPC-PLC membrane (**Fig. 2d, h**). We peeled the microfluidic

chip off the cell-laden MPC-PLC membrane and rolled it up with a PTFE mandrel,

forming a 3D multi-layered tubular structure (**Fig. 2e-g**) with HUVECs, SMCs, and

HAFs evenly distributed in inner layer, middle layer, and outer layers, respectively

(**Fig. 2i, j**). This structure well mimics the structure of the natural blood vessel. We

used a biomedical fibrin glue to facilitate the combination of different layers[18]. We

incubated the cell-laden electronic blood vessel for 14 d and stained the cells with the

Calcein AM green. The evenly distributed green color on the MPC-PLC membrane

indicated that the cells exhibited high viability after a 14 d culture (**Fig. 2k**).

Fig. 2. *In vitro* biocompatibility of the electronic blood vessel. **a**, The MPC-PLC

membrane. **b**, Attaching a multichannel microfluidic chip onto the MPC-PLC

membrane. **c, d**, Patterning three kinds of blood vessel cells (blue: HUVECs, green:

SMCs, red: HAFs) onto the MPC-PLC membrane by using PDMS microfluidic chip.

e, f, Rolling the cell-laden membrane into a multi-layered tubular structure with a

PTFE mandrel. **g**, Cross-sectional view of natural blood vessel mimicking structure

with different cells distributed in different layers. **h**, Fluorescent images of cells on

the MPC-PLC membrane, in corresponding to (**d**). Stained by CellTracker violet,

green, deep red, respectively. Scale bar, 20 μm. **i,** Three kinds of blood vessel cells

distributed in different layers of the electronic blood vessel. Scale bar, 500 μm. **j**, 3D

construction of (**i**). **k**, Cell viability after 2-week incubation in the electronic blood

vessel. Stained by CellTracker green. The right column is the 3D reconstruction of the

left column in each image. The black area represents the MPC circuit and the

transparent area represents the PLC in bright-field images.

***In vitro* electrical stimulation promotes HUVEC proliferation and migration**

To prove the functionality of the electronic blood vessel, we carried out *in vitro*

electrical stimulation to improve proliferation and migration of HUVECs as a proof of

concept. Direct current (DC) electric field has been proved to effectively increase the

angiogenesis *in vitro* and *in vivo*[26]. We patterned HUVECs on the MPC-PLC

membrane (DMEM, 10% FBS, 37 °C, 5% CO_2) by using a multi-chamber PDMS

chip. The initial number of cells in each chamber was the same (3×10^4). After 12 h

incubation, we applied different DC voltages to yield different electrical field

strength: 25, 50, 75 100, 200, and 400 mV mm^{-1}, respectively (**Fig. 3a, b**). After 2 d

incubation and electrical stimulation, we randomly selected 6 different domains on

each sample and analyzed by using a laser scanning confocal microscopy (LSCM,

LSM 710, Zeiss, Germany). We stained nuclei (blue) with Hoechst 33342 (Invitrogen,

USA) and stained the living and dead cells with Calcein-AM (green) and PI (red),

respectively. The green cells occupied the whole domain, indicating that electrical

stimulation did not hurt proliferation of HUVECs (**Supplementary Fig. 2a**). We

counted the number of nuclei by using ImageJ. The cell number under 50 mV mm^{-1}

was highest (**Fig. 3d**), about 2.4 times that of the control (**Fig. 3e**). We used the CCK-

8 kit to confirm this conclusion (**Fig. 3f**). We speculated that the DC electric field had

selectively regulated production of certain growth factors and cytokines important for

angiogenesis.

We used a wound healing model to explore the migration of HUVECs under

different DC electric field strengths. We made a scratch on a PDMS substrate by using

a 10 μl tip. After application of an electric field of 50 mV mm^{-1}, HUVECs migrated

750 μm and the wound completely healed after 24 h (**Fig. 3g, f**). Different strengths

had enhanced migration differently compared to the control group without electrical

stimulation (**Supplementary Fig. 2b**). The *in vitro* DC electrical stimulation thus

proved to have effectively promoted the proliferation and migration of HUVECs.

Fig. 3. *In vitro* electrical stimulation and electroporation. a-c, The electronic blood

vessel was connected to electrochemical station to generate a direct current voltage

(b) or an electroporator to generate electrical pulses (c). **d**, Confocal fluorescent

images of HUVECs after 2 d incubation and stimulation at a DC electric field of 50

mV mm^{-1}. Blue, DAPI; green, Calcein AM; red, PI. **e**, The proliferation of HUVECs

under different DC electrical field, setting the control (without electric field) as 100%.

(n=4). **f**, The proliferation of HUVECs under different DC electrical field tested with

the CCK-8 kit. (n=4). **g**, Confocal fluorescent images of HUVECs at a DC electrical

field of 50 mV mm^{-1} in a wound healing model. Scale bar, 400 μm. A 10 μl tip was

used to scratch a line for HUVECs migration. **h**, The migration of HUVECs at

different DC electrical field (n=4). **i**, Electroporation under condition: voltage 60 V;

pulse duration 100 μs; 5 pulses; pulse interval 1 s. Upper: HUVECs; middle: HAFs;

lower: SMCs. Blue represents cell nucleus, stained by DAPI; red represents cell

skeleton, stained by Rhodamine Phalloidin; green represents GFP; black represents

that cells were on the top of non-transparent MPC-PLC circuit, bright field. Scale bar,

20 μm.

***In vitro* electroporation**

To further prove the functionality of the electronic blood vessel, we designed a comb-

like circuit pattern for electroporation (**Supplementary Fig. 1**). We connected the

cell-laden electronic blood vessel with an electroporator (BTX, CM630, US) to

generate DC pulses (**Fig. 3c**) and achieved the delivery of the green fluorescent

protein (GFP) DNA plasmid. To optimize the performance of the electronic blood

vessel, we found two major parameters determining the efficacy of electroporation,

including voltage and pulse duration. To realize the optimal efficacy, we exerted a

square wave with the voltage of 60 V, pulse duration of 100 μs, and pulse interval of 1

s for 5 times. We delivered GFP DNA plasmid into three kinds of blood vessel cells

and the GFP DNA realized expression with more than 95% of cells showing green

fluorescence (**Fig. 3i**). These promising *in vitro* results encouraged us to carry out the

in vivo tests of the electronic blood vessel.

Mechanical properties of the electronic blood vessel

To find out whether the electronic blood vessel is suitable for *in vivo* implantation, we

measured the mechanical properties, including stress-strain curve, compliance, and

burst pressure, of the electronic blood vessel with a diameter of 2 mm prior to

implantation (**Fig. 1m-r and Supplementary Fig. 3**). The elastic modulus of the

electronic blood vessel is about 130 MPa, the value is much higher than the native

carotid artery. The ultimate tensile strength of the electronic blood vessel is about 27

MPa, the value is also much higher than that of the native carotid artery. The initial

compliance of the electronic blood vessel (n= 5) is about 5% per 100 mmHg in the

range of 80-120 mmHg, the value is apparently below that of the native carotid artery

(n= 3). The burst pressure of the electronic blood vessel (n= 5) is about 2800 mmHg,

the value is similar to that of the native carotid artery (n= 3). The elongation at break

of the electronic blood vessel is about 650% (n= 5), which is the twice as the value of

native carotid artery (n= 3). The mechanical property of electronic blood vessel was

considered robust enough for implantation.

In vivo implantation in rabbits and _in situ_ monitoring

To investigate the electronic blood vessel as a vascular implant, we chose the New

Zealand rabbit (age: 200-300 days, body weight: 3-4 kg) as the animal model and

replaced the native carotid artery with the electronic blood vessel (**Fig. 4a-c**). To

avoid possible immunological response of the host tissue, we used the acellular

electronic blood vessel in the preliminary _in vivo_ study. We _in situ_ monitored the

implanted electronic blood vessel by doppler ultrasound imaging (**Fig. 4d-i**) and the

arteriography (**Fig. 4j, k**). Doppler ultrasound imaging showed that the electronic

blood vessel allowed for good blood flow 3 months post-implantation (**Fig. 4d-g and**

Supplementary Video 1). The asymmetric velocity curve synchronized with the

ultrasonic pulses indicated that the signal is from the carotid artery rather than the

vein (**Fig. 4d**). The diameter of the electronic blood vessel remained at a relatively

constant value, about 2.3 mm, during the half month to three months post-

implantation (**Fig. 4g, h**). The mean velocity of the blood flow in different samples at

different time point was about 0.47 m s^{-1}, which was in the range of the normal value

(**Fig. 4i**). As the gold standard of the blood vessel patency, arteriography showed that

the electronic blood vessel matched with the native carotid artery very well and

allowed for excellent blood flow (**Fig. 4j, k, Supplementary Fig. 4, and**

Supplementary Video 2). There was no sign of narrowing. The electronic blood

vessel allows straightforward visualization under arteriography because the liquid

metal-based circuitry has sufficiently high contrast over host tissues (**Fig. 4j**). The red

frame outlined the electronic blood vessel with an alternate strip structure from the

MPC circuit. We explanted the electronic blood vessel three months post-implantation

for characterization. The lumen and the outer surfaces of the explanted electronic

blood vessel were smooth, covered by the remodeling tissues (**Fig. 4l, m**). The

diameter of the native blood vessel significantly reduced due to the lack of the blood

pressure, whereas the electronic blood vessel remained the same as before

(**Supplementary Fig. 5**).

Fig. 4. *In vivo and ex vivo* **study of the electronic blood vessel. a**, Schematic of the

electronic blood vessel in the carotid artery of the rabbit. **b, c**, An end-to-end

anastomosis procedure of electronic blood vessel implantation on carotid arteries of

rabbits (n=6). The dotted frames outline the margin of the native carotid artery and the

implanted electronic blood vessel. The white arrows indicate two ends of the

electronic blood vessel. Scale bar, 1 cm. **d-g**, *In situ* monitoring of the electronic

blood vessel by doppler ultrasound imaging 3 months post-implantation.

Representative images from at least three different animals. **d, e**, The real-time blood

flow at the operational site and the synchronized ultrasound pulses. The asymmetric

velocity curve represents the signal is from carotid artery rather than vein. **e**, Zoom-in

view of red box in (d). **f**, The cross view of the blood flow. **g**, The suture site (red

arrows) connecting the native carotid artery and the electronic blood vessel. **h**, The

diameter changes of the electronic blood vessel in different time post-implantation. **i**,

The velocity of blood flow at the operational site (n=18, from different rabbits at

different time points). **j, k**, *In situ* monitoring by arteriography 3 months post-

implantation. **j**, Image before injecting the contrast media. Red box indicates the

position of the implanted electronic blood vessel. **k**, Image after injecting the contrast

media. Red box indicates the position of the implanted blood vessel. Red arrows

indicate the suture sites connecting the native carotid artery and the electronic blood

vessel. **l, m**, The cross-sectional view of the explanted electronic blood vessel after 3-

month host remodeling. Scale bar, 1 mm. **n-p**, Hematoxylin/eosin (H&E) staining,

Masson's trichrome staining, and Verhoeff's staining of the implanted electronic

blood vessel 3 months post-implantation, setting native carotid artery as control. The

right panel is the zoom-in view of the left panel. Scale bar (left), 500 μm. Scale bar

(right), 50 μm.

Ex vivo **study**

To study the histological changes of the implanted electronic blood vessels, we

dissected all the implanted electronic blood vessels 3 months post-implantation and

performed histological staining of the electronic blood vessels, setting native carotid

blood vessel as a positive control. Hematoxylin/eosin (H&E) staining (**Fig. 4n**) of the

cross section of the electronic blood vessel is round-shaped, continuous, red, which is

similar to the native blood vessel. The three-layered MPC-PLC membrane merged

into one intact layer with secretion of substantial extracellular matrix between the

different layers of electronic blood vessel. We could clearly see dark blue nuclei in all

the layers, which indicated successful migration of host cells into the electronic blood

vessel. More importantly, a dense layer of cells with curved structure were formed in

the lumen of the electronic blood vessel which indicated the excellent endothelization

and thus ensured good blood flow. To further confirm the components in the

implanted electronic blood vessel, we performed Masson's trichrome (**Fig. 4o**) and

Verhoeff's staining (**Fig. 4p**). Masson's trichrome staining can stain and assess keratin

and muscle fibers (red) or collagen (blue) and Verhoeff's staining can stain and assess

the presence of elastin fibers. Masson's trichrome and Verhoeff's staining showed

well-distributed collagen and elastin fibers both inside the layers and between

different layers, indicating appropriate remodeling. Compared to the abundance level

of extracelluar matrix in the native blood vessel, the electronic blood vessel still

requires more time for material degradation and tissue remodeling. We also tested its

conductivity and the circuit in the electronic blood vessel was still conductive. These

results indicated that the electronic blood vessel was still functioning with the

presence of conductive materials and host remodeling 3 months post-implantation.

To investigate the influence of the electronic blood vessel on the host, we

performed the cross section and histological staining of the major organs, including

heart, liver, spleen, lung, and kidney, together with the dissection of the implanted

electronic blood vessel 3 months post-implantation. The H&E staining and Masson's

Chrome staining showed that there was no significant pathological changes or

inflammatory responses in these organs (**Supplementary Fig. 6**). To evaluate whether

there were chronic inflammation or infection, we conducted the ELISA assay of three

important proteins in the blood, including the interleukin-6 (IL-6), procalcitonin

(PCT), and C-reactive protein (CRP) (**Supplementary Fig. 7**). The concentrations of

IL-6 and PCT were not higher than the normal value of healthy rabbits (red dotted

lines). The concentration of CRP was higher than the normal value of healthy rabbits

(red dotted line). All three indexes decreased over time, a tendency that was expected.

The results showed that most of the indexes were in the normal range and there were

no significant pathological changes or inflammatory responses. These results

confirmed that as an implant for vascular system, the electronic blood vessel had no

significant detriment to the host.

Discussion

None of the existing small-diameter TEBVs has met the demands in treating

cardiovascular diseases. Conventional TEBVs can be greatly improved to provide

next-generation treatment by integrating with flexible bioelectronics. In this work, we

report an electronic blood vessel with excellent biocompatibility, flexibility,

mechanical strength, and degradability by combining the MPC with a US FDA-

approved biodegradable polymer. As a proof of concept, we verified that the

electronic blood vessel can accelerate the HUVEC proliferation and migration by

electrical stimulation, thus facilitating the endothelization process, which is important

to an engineered vascular conduit in preventing early thrombosis. Because most

TEBVs occluded with 2 weeks post-implantation, our electronic blood vessel, with a

patency of at least 12 weeks, is of great promise for clinical application. We also

showcased that it could be used to perform *in situ* gene delivery via electroporation,

which laid a foundation for future design and optimization such that we can carry out

further gene therapies targeting different pathological problems after implantation.

The electronic blood vessel has a high level of safety. The liquid metal[16,27] has been

proven to be highly biocompatible and the PLC has been approved by the US FDA for

implants[28]. We validated its biosafety in the vascular system by a 3-month

implantation in a rabbit carotid artery model. Both the *in situ* monitoring, including

doppler ultrasound imaging and arteriography, and *ex vivo* study demonstrated that it

was safe as an electronic implant in the vascular system and at the body level.

As a vascular substitute, it breaks through the limitations of the existing vascular

scaffold by endowing the electrical function to conventional biodegradable TEBV and

provides us a new platform for tackling the problems threatening the small-diameter

blood vessel. By integrating with other electronic devices, the electronic blood vessel

can provide various treatments, such as electrical stimulation, electroporation,

electrically controlled drug release, and so forth. When combining with emerging

technologies such as artificial intelligence, it can greatly boost future personalized

medicine by bridging the vascular tissue-machine interface and empowering the

health data collection and storage, such as blood velocity, blood pressure, and blood

glucose level. In the future, optimizing its function and creating a multifunctional

electronic blood vessel can greatly benefit human cardiovascular health.

References

References

1.   WHO | World Health Statistics 2019: Monitoring health for the SDGs. *World*

Heal. Organ. (2019).

2.   Seifu, D. G., Purnama, A., Mequanint, K. & Mantovani, D. Small-diameter

vascular tissue engineering. *Nat. Rev. Cardiol.* **10**, 410–421 (2013).

3.   Quint, C. *et al.* Decellularized tissue-engineered blood vessel as an arterial

conduit. *Proc. Natl. Acad. Sci.* **108**, 9214–9219 (2011).

4.   Dahl, S. L. M. *et al.* Readily available tissue-engineered vascular grafts. *Sci.*

Transl. Med. **3**, 68ra9 (2011).

5.   Lawson, J. H. *et al.* Bioengineered human acellular vessels for dialysis access

in patients with end-stage renal disease: two phase 2 single-arm trials. *Lancet*

387, 2026–2034 (2016).

6.   Zhu, M. *et al.* In vivo engineered extracellular matrix scaffolds with instructive

niches for oriented tissue regeneration. *Nat. Commun.* **10**, 4620 (2019).

7.   Kirkton, R. D. *et al.* Bioengineered human acellular vessels recellularize and

evolve into living blood vessels after human implantation. *Sci. Transl. Med.* **11**,

1–12 (2019).

8.   L'Heureux, N. *et al.* Human tissue-engineered blood vessels for adult arterial

revascularization. *Nat. Med.* **12**, 361–5 (2006).

9.   L'Heureux, N., McAllister, T. N. & de la Fuente, L. M. Tissue-engineered

blood vessel for adult arterial revascularization. *N. Engl. J. Med.* **357**, 1451–

1453 (2007).

10. L'Heureux, N. *et al.* Technology insight: the evolution of tissue-engineered

vascular grafts - from research to clinical practice. *Nat. Clin. Pract.*

Cardiovasc. Med. **4**, 389–395 (2007).

11. Peck, M., Dusserre, N., McAllister, T. N. & L'Heureux, N. Tissue engineering

by self-assembly. *Mater. Today* **14**, 218–224 (2011).

12. Wu, W., Allen, R. A. & Wang, Y. Fast-degrading elastomer enables rapid

remodeling of a cell-free synthetic graft into a neoartery. *Nat. Med.* **18**, 1148–

1153 (2012).

13. Cheng, S. *et al.* Self-Adjusting, polymeric multilayered roll that can keep the

shapes of the blood vessel scaffolds during biodegradation. *Adv. Mater.* **29**,

(2017).

14. Akentjew, T. L. *et al.* Rapid fabrication of reinforced and cell-laden vascular

grafts structurally inspired by human coronary arteries. *Nat. Commun.* **10**, 1–15

(2019).

15. Hoenig, M. R., Campbell, G. R., Rolfe, B. E. & Campbell, J. H. Tissue-

engineered blood vessels: alternative to autologous grafts? *Arterioscler.*

Thromb. Vasc. Biol. **25**, 1128–1134 (2005).

16. Yan, J., Lu, Y., Chen, G., Yang, M. & Gu, Z. Advances in liquid metals for

biomedical applications. *Chem. Soc. Rev.* **47**, 2518–2533 (2018).

17. Choi, S., Han, S. I., Kim, D., Hyeon, T. & Kim, D. H. High-performance

stretchable conductive nanocomposites: Materials, processes, and device

applications. *Chem. Soc. Rev.* **48**, 1566–1595 (2019).

18.   Son, D. *et al.* Bioresorbable electronic stent integrated with therapeutic

nanoparticles for endovascular diseases. *ACS Nano* **9**, 5937–5946 (2015).

19.   Du, Z. J., Bi, G. Q. & Cui, X. T. Electrically controlled neurochemical release

from dual-layer conducting polymer films for precise modulation of neural

network activity in rat barrel cortex. *Adv. Funct. Mater.* **28**, 1–12 (2018).

20.   Gong, P. *et al.* A strategy for the construction of controlled, three-dimensional,

multilayered, tissue-like structures. *Adv. Funct. Mater.* **23**, 42–46 (2013).

21.   Jin, Y. *et al.* Stress-induced self-assembly of complex three dimensional

structures by elastic membranes. *Small* **9**, 2410–4 (2013).

22.   Yuan, B. *et al.* A strategy for depositing different types of cells in three

dimensions to mimic tubular structures in tissues. *Adv. Mater.* **24**, 890–896

(2012).

23.   Wang, N. *et al.* A strategy for rapid and facile fabrication of controlled, layered

blood vessel-like structures. *RSC Adv.* **6**, 55054–55063 (2016).

24.   Tang, L., Mou, L., Zhang, W. & Jiang, X. Large-scale fabrication of highly

elastic conductors on a broad range of surfaces. *ACS Appl. Mater. Interfaces*

11, 7138–7147 (2019).

25.   Tang, L. *et al.* Printable metal-polymer conductors for highly stretchable bio-

devices. *iScience* **4**, 302–311 (2018).

26.   Bai, H., McCaig, C. D., Forrester, J. V. & Zhao, M. DC electric fields induce

distinct preangiogenic responses in microvascular and macrovascular cells.

Arterioscler. Thromb. Vasc. Biol. **24**, 1234–1239 (2004).

27. Lu, Y. *et al.* Transformable liquid-metal nanomedicine. *Nat. Commun.* **6**, 10066 (2015).

28. Kenar, H. *et al.* Microfibrous scaffolds from poly(L-lactide-co-ε-caprolactone) blended with xeno-free collagen/hyaluronic acid for improvement of vascularization in tissue engineering applications. *Mater. Sci. Eng. C* **97**, 31–44 (2019).

Data availability

All data are available from the corresponding authors upon reasonable request.

Acknowledgement

This study was supported by the National Key R&D Program of China (2018YFA0902600, 2017YFA0205901), the National Natural Science Foundation of China (21535001, 81730051, 21761142006, 51973045), the Chinese Academy of Sciences (QYZDJ-SSW-SLH039, 121D11KYSB20170026, XDA16020902), Shenzhen Bay Laboratory (SZBL2019062801004), the Tencent Foundation through the XPLORER PRIZE, Beijing Science and Technology Plan Project (Z191100007619053), Postgraduate Innovation Foundation of Peking Union Medical College (2019-1002-28) and Teaching Reform Foundation of Postgraduate Education in Peking Union Medical College (10023201900202). We thank Dr. Zewen Wei and Dr. Deyao Zhao for discussions on the electroporation experiment. We thank Mrs. Barbara Althaus at EPFL for her advice in writing the manuscript.

Author Contributions

X. J. and S. C. conceived the idea. S. C. designed the experiments, fabricated the blood vessel, conducted the characterization, *in vitro* tests, mechanical tests, *in vivo* tests and *ex vivo* tests, analyzed the data, and wrote the manuscript. C. H. prepared the liquid metal particles and fabricated the blood vessel, performed *in vitro* tests, electrical stimulation study, mechanical tests, and *in vivo* tests. L. D. performed the *in vivo* and *ex vivo* tests. S. C., C. H., and L. D. contributed equally to this work. L. T. assisted with the preparation of the liquid metal particles, MPC-PLC membrane and the electroporation experiments. L. J. and Y. Z. performed the implantation of the electronic blood vessel, doppler ultrasound imaging and arteriography. L. M. conducted the ELISA assay. J. Q. and R. D. assisted the TEM characterization. W. Z. gave inputs on the *in vitro* tests and *ex vivo* tests. Y. Z. supervised the *in vivo* and *ex vivo* study. X. J. supervised the project, and revised the manuscript. All the authors took part in the discussion and writing.

Competing financial interests

S. C. and X. J. declare financial interest in form of a patent application. Other authors declare no competing financial interests.

Additional Information

Supplementary Information is available for this paper.

Correspondence and requests for materials should be addressed to: S. C. or X. J.