An In situ Collagen-HA Hydrogel System Promotes Survival and Preserves the Proangiogenic Secretion of hiPSC-derived Vascular Smooth Muscle Cells

Biraja C. Dash[1]*#, Kaiti Duan[1]#, Themis R. Kyriakides [2,3,4], and Henry C. Hsia[1, 2]*

[1]Section of Plastic Surgery, Department of Surgery, Yale School of Medicine, Yale University, New Haven, CT 06510, USA

[2] Department of Biomedical Engineering, Yale University, New Haven, CT 06510, USA

[3]Department of Pathology, Yale University, New Haven, CT, 06510, USA

[4]Vascular Biology and Therapeutics Program, Yale University, New Haven, CT, 06510, USA

Running Title: In situ collagen-HA hydrogel for hiPSC-VSMCs

*Corresponding authors email: henry.hsia@yale.edu; biraja.dash@yale.edu

# Authors contributed equally

Address: Yale University School of Medicine, 330 Cedar St., BB 3rd Floor, PO Box 208041, New Haven, Connecticut 06510, Telephone: 203 737-2049, Fax: 203 785-5714

Abstract:

Human induced pluripotent stem cell-derived vascular smooth muscle cells (hiPSC-VSMCs) with proangiogenic properties have huge therapeutic potential. While hiPSC-VSMCs have already been utilized for wound healing using a biomimetic collagen scaffold, an in situ forming hydrogel mimicking the native environment of skin offers the promise of hiPSC-VSMC mediated repair and regeneration. Herein, the impact of a collagen type-I-hyaluronic acid (HA) in situ hydrogel cross-linked using a PEG based cross-linker on hiPSC-VSMCs viability and proangiogenic paracrine secretion was investigated. Our study demonstrated increases in cell viability and maintenance of proangiogenic growth factor secretion. The optimally cross-linked and functionalized collagen type-I/HA hydrogel system developed in this study shows promise as an in situ hiPSC-VSMC carrier system for wound regeneration.

Keywords: induced pluripotent stem cell, in situ hydrogel, vascular smooth muscle cells, paracrine secretion, angiogenesis, wound regeneration

Introduction:

Human-induced pluripotent stem cells (hiPSCs) have shown enormous potential for applications in regenerative therapy and disease modeling (Shi, Inoue, Wu, & Yamanaka, 2017; Soldner & Jaenisch, 2012; Takagi et al., 2019; Takahashi & Yamanaka, 2006). Human iPSCs with properties similar to embryonic stem cells can be differentiated into various specialized cells such as endothelial (hiPSC-ECs) and vascular smooth muscle cells (hiPSC-VSMCs) (Ayoubi, Sheikh, & Eskildsen, 2017; B. C. Dash, Z. X. Jiang, C. Suh, & Y. B. Qyang, 2015b; Klein, 2018; Maguire, Xiao, & Xu, 2017). The latter in pure population have been generated in abundance (Cheung, Bernardo, Trotter, Pedersen, & Sinha, 2012; Dash et al., 2015b; Dash et al., 2016; Patsch et al., 2015) and their ability to carry the disease mutations and to secrete collagen has been used to develop robust disease models (Atchison et al., 2020; Atchison, Zhang, Cao, & Truskey, 2017; Dash et al., 2016; Ge et al., 2012; Liu et al., 2011; Zhang et al., 2011) and vascular grafts (Gui et al., 2016; Karamariti et al., 2013; Luo et al., 2020) , respectively. In addition, we recently reported the secretion of various growth factors and cytokines from these cells (Dash et al., 2020; Gorecka et al., 2020). Specifically, hiPSC-VSMCs, when embedded in a dense collagen scaffold, experienced a microenvironment attributable to a combination of mechanical forces and hypoxia that induced secretion of growth factors and cytokines vascular endothelial growth factor (VEGF), basic fibroblast growth factor (bFGF), angiopoietin-1 (ANG-1), transforming growth factor (TGF)-β, platelet-derived growth factor (PDGF), matrix metalloproteinase (MMP)-2, stromal cell-derived factor (SDF)-1α, interleukin (IL)-10 and IL-8 (Dash et al., 2020). Moreover, hiPSC-VSMCs in vivo exhibited proangiogenic and anti-inflammatory activities and were shown to promote regenerative healing in both acute and diabetic wound models in nude mice (Dash et al.,

2020; Gorecka et al., 2020). These initial studies have shown future translation potentials of hiPSC-VSMCs in wound healing and ischemic diseases.

Extracellular matrix (ECM)-based biomaterials such as collagen have been designed for the delivery of stem cells' beneficial properties (Dash et al., 2018; Hinderer, Layland, & Schenke-Layland, 2016). While collagen and its biophysical properties have been shown to have significant impact on stem cells' therapeutic function, cross-linked in situ collagen-based hydrogels have been developed to enhance their stability and ease of application (Ahmed & Ffrench-Constant, 2016; Dash et al., 2020; Hou, Coller, Natu, Hastie, & Huang, 2016; Watt & Huck, 2013). Widely used chemical cross-linking methods have impact on collagen matrix architecture, stability, porosity, morphology, and function of stem cells (Depalle, Qin, Shefelbine, & Buehler, 2015; Gu, Shan, Ma, Tay, & Niu, 2019). Polyethylene glycol (PEG)-based cross-linker has been used to develop mechanically robust and enzyme resistant biomaterials without compromising their biocompatibility (Lee, Tong, & Yang, 2016; Taguchi et al., 2005). Previously, 4arm PEG Succinimidyl Glutarate (4S-StarPEG) has been used to crosslink collagen type-I and II to fabricate various forms of cell and drug delivery systems (Browne et al., 2015; Collin et al., 2011; Fontana et al., 2015; Fontana, Thomas, Collin, & Pandit, 2014; Monaghan, Browne, Schenke-Layland, & Pandit, 2014; Thomas et al., 2014). 4S-StarPEG-based carrier systems with enhanced mechanical strength have been used to provide a niche for survival and regenerative function of mesenchymal stem cells (MSCs), adipose-derived stem cells (ADSCs), nucleus pulposus cells (NPCs) (Collin et al., 2011; Fontana et al., 2015; Fontana et al., 2014; Thomas et al., 2014).

Hyaluronic acid (HA), a non-sulfated glycosaminoglycan, is abundantly present in the ECM of the skin and many other major organs and has tissue-specific functions (Papakonstantinou, Roth, & Karakiulakis, 2012). HA has been shown to promote cellular proliferation and migration, and blood vessel formation during tissue injury (Gerecht et al., 2007; Hanjaya-Putra et al., 2012; Kwon et al., 2019; Shen et al., 2014). HA contains cell-binding motifs and has been widely used for surface modification of biomaterials to support cell survival and proliferation (Highley, Prestwich, & Burdick, 2016; Khetan & Corey, 2019; Solis et al., 2012). Several earlier studies have reported the use of HA-based hydrogels to maintain stem cells such as NPCs, ADSCs, and hiPSC-derived vascular cells (Collin et al., 2011; Fontana et al., 2014; Shen et al., 2016). In particular, one of the studies that used acrylated HA-based hydrogel for hiPSC-derived early vascular cells, demonstrated enhanced angiogenic potentials that translated to improved wound healing capacities in diabetic mice (Shen et al., 2016).

In this study, we characterized an in situ cell-carrier system for hiPSC-VSMCs. The biomaterial system was comprised of type I collagen hydrogel optimally stabilized with 4S-StarPEG and enriched with HA. In addition, we investigated how collagen density is a crucial factor impacting chemical and biophysical behavior of the in situ hydrogels, and ultimately cellular viability and paracrine function. It is our hypothesis that a system mimicking skin composition would be a suitable carrier for hiPSC-VSMCs for wound healing. Specifically, an in situ hydrogel will allow encapsulation and delivery of hiPSC-VSMCs, and provide a better conducive environment for the maintenance of their cell viability and paracrine functions.

Methods:

Cell culture:

Human primary cells: Human umbilical vascular endothelial cells (HUVECs) and human dermal fibroblasts of passage number below 7 were used in the experiments. Both the primary cells were cultured on 1% gelatin-coated plates. The medium for HUVECs was endothelial cell growth medium (EGM)-2 and for fibroblasts, it was DMEM high Glucose with 10% FBS. The respective medium was replenished with a fresh one every other day and cultured until 80% confluency before using them on hydrogels.

hiPSC-VSMCs: hiPSC-VSMCs were differentiated using a previously described protocol (Dash et al., 2016). Briefly, hiPSCs were initially cultured under feeder-free conditions until reaching 80% confluency in a 6-well culture plate (4 days). Then clumps of uniform sizes were harvested after treating with dispase for 15 minutes at 37^{o}C. The resulting hiPSC clumps were then seeded in a 6-well low attachment plate with mTESR medium. Next day, the medium was replaced with mixture of mTeSR and EB differentiation medium (DMEM high glucose + 10% FBS + 1% non-essential amino acid (v/v) + 2mM L-glutamine and 0.012 mM 2-mercaptoethanol) at a 1 to 3 ratio. On day 3, the medium was replaced with just the EB differentiation medium. On day 5, the resulting EB were collected and seeded on a gelatin-coated 6-well plate and cultured in EB differentiation medium for 5 days or until 80% confluency (around 7 days). After reaching the targeted density, the smooth muscle cell growth medium (SmGM)-2 medium was used for culturing and was replaced every other day. The resulting differentiated cells were validated with immunofluorescence staining. (calponin and SM-22α). Human iPSC-VSMCs were cultured until at least 80% confluence, then they were seeded into collagen-based hydrogels for subsequent experiments.

In situ collagen-HA hydrogel fabrication:

The in situ hydrogels were fabricated using a rat tail collagen type-I, HA and 4S-StarPEG (Figure 1). Briefly, the in situ collagen-HA hydrogels were generated by properly mixing collagen type-I of initial concentration of 5mg/ml, 10xMEM, and 1M NaOH followed by the addition of final concentration of 1mg/ml of HA and cross-linker 4S-StarPEG. Various molar ratios (1:0.5, 1:1 and 1:2) of collagen to the 4S-StarPEG cross-linker were tested. The entire hydrogel generation process was done on ice. The mixture ratios of varying collagen densities to 10x modified essential medium (MEM), 1M NaOH, HA, and 4S-StarPEG has been listed in the tables in the supplementary information. The resultant mixture was mixed quickly and gently to avoid bubble formation and quick gelation. The collagen mixture was then distributed as 100μL aliquots into 96 well cell culture plate and incubated for 30 minutes at 37°C for the gelation. The final in situ collagen-HA hydrogel contained 4mg/ml and 1mg/ml final concentration of collagen and HA respectively and 1:1 molar ratio collagen to 4S-StarPEG cross-linker. The controls were cross-linked collagen hydrogels and uncross-linked collagen and collagen-HA hydrogels. Please refer to the tables (Table S1-S3) in the supplementary information for a detailed composition of each of these hydrogels.

Cell seeding:

HUVECs and dermal fibroblasts: HUVECs and dermal fibroblasts from primary sources were seeded on top of the hydrogels at a concentration of 1×10^5/ml of cells. The primary cells were cultured for 3 days supplemented with 100μl of the respective medium on the top of the hydrogels. The hydrogels were tested on days 1 and 3 for cell viability.

hiPSC-VSMCs: hiPSC-VSMCs of 4 x 10^5/ml concentration were embedded while forming the collagen-HA in situ hydrogels. The cells were added after HA and before the cross-linker during the process. The hiPSC-VSMCs were cultured for 3 days supplemented with 200µl of SmGM-2 medium on the top of the hydrogels. After day 3, the hydrogels were tested for cell viability while the 200µl of conditioned medium (CM) was collected to analyze paracrine secretion.

2,4,6-trinitrobenzene sulfonic acid assay:

2,4,6-Trinitrobenzene Sulfonic Acid (TNBSA) assay was performed to determine the degree of crosslinking of collagen type I as per the previously method (Collin et al., 2011). The efficacy of 4S-StarPEG of crosslinking collagen type-I was tested in varies collagen densities (1.25mg/ml, 2.5mg/ml, and 4mg/ml). The degree of PEG cross-linking in varying Collagen to PEG ratios (control, 1:0.5, 1:1, and 1:2) was also evaluated. Glycine titration in sodium bicarbonate (0.1M) pH 8.5 standard curve was established at: 300uM, 250uM, 200uM, 150uM, 100uM, 75uM, 50uM, 25uM, and 0uM. 250uL of 0.01% TNBSA was added into 500uL of each sample. A 0.2% glutaraldehyde solution was used as a positive control. The resultant mixtures were incubated at 37^{o}C for 2 hours. After incubation, 250µL of 10% sodium dodecyl sulfate was added. Then, 125µL of 1M HCI was added to and mixed to stop the reaction. 100µL of the final solution was used to test for the degree of amine group cross-linkage. Plate reader absorbance was set at 335nm.

Results:

Cross-linking and cell viability of in situ collagen hydrogel is collagen density dependent:

4S-StarPEG was used to fabricate in situ collagen hydrogels as reported earlier. We used rat tail Type-I collagen of 5mg/ml initial concentration to develop hydrogels of the final

concentration of 1.25, 2.5 and 4mg/ml. TNBSA assay was used to evaluate cross-linking by determining the amine content of the hydrogels (Figure 2). The initial amount of amine was determined for un-crosslinked hydrogels to determine the collagen to 4S-StarPEG ratios of 1:0.5, 1:1 and 1:2. TNBSA data showed a decrease in the free amine groups in the cases of cross-linked hydrogels and was dependent on their final collagen concentration. For 1.25mg/ml of hydrogels only 1:2 ratio had a significant reduction in the level of the amine group and was reduced compared to control 1:0.5 and 1:1, while no difference was seen between control, 1:0.5 and 1:1 (Figure 2A). However, in the case of 2.5mg/ml 1:2 there was higher degree of cross-linking than 1:0.5 and control groups, and 1:1 ratio showed higher cross-linking compared to the control group. There were no significant differences between 1:2 and 1:1, 1:1 and 1:0.5, and 1.05 and control (Figure 2B). For the 4mg/ml group 1:2, 1:1 and 1:05 were all more cross-linked than control, and 1:2 was higher than 1:0.5. But there were no differences between 1:1 and 1:0.5, and 1.2 and 1:1 (Figure 2C). The percentage of cross-linking was found to be higher in the case of 4mg/ml hydrogels with a 40-70% reduced amine group compared to 20-50% in 2.5mg/ml and 7-20% in 1.25mg/ml hydrogels (Figure 2D). Collagen cross-linked with glutaraldehyde was used as a positive control and TNBSA assay showed reduced free amines (Figure S1).

AlamarBlue assay was performed to determine the biocompatibility of the 4S-StarPEG cross-linked collagen hydrogels using HUVECs and dermal fibroblast cells (Figure 3). On day 1 an increase in the cell viability of fibroblasts was seen with increasing collagen concentration irrespective of cross-linker ratios except for 1:2 where 2.5mg/ml was similar to 1.25mg/ml (Figure 3A). On day 3, an overall increase in the cell viability of fibroblasts compared to day 1 was observed (Figure 3B). 4mg/ml was found to be significantly higher compared to 2.5mg/ml and

1.25mg/ml across different cross-linker ratios. On both days 1 and 3, there was no difference in the cell viability of fibroblasts in relation to cross-linker ratios except control 4mg/ml day 3 was found to be higher than the 4mg/ml cross-linked groups (Figure 3B). Similarly, Day 1 HUVECs showed an increase in cell viability in 4mg/ml hydrogel groups irrespective of cross-linking ratios compared to other concentrations. However, unlike fibroblasts, on day 1 there was no difference between 2.5mg/ml and 1.25mg/ml across all the cross-linking ratios. Most importantly, on day 1 HUVECs on 4S-StarPEG cross-linked collagen hydrogels displayed an increase in viability with increasing cross-linking ratios except 1:2 (Figure 3C). Like dermal fibroblasts, we saw an overall increase in viability of HUVECs on day 3 compared to day 1 and an increase in viability in 4mg/ml hydrogel compared to all other groups. (Figure 3D).

hiPSC-VSMCs derived utilizing an EB method generated a pure population of synthetic VSMCs in abundance within 21 days. The hiPSC-VSMCs when characterized using synthetic VSMC markers calponin and SM-22α were found to be highly positive. These synthetic hiPSC-VSMCs were then embedded within the in situ hydrogels (Figure 4). Cells embedded in different concentrations of hydrogel were tested for viability using AlamarBlue. The data suggest no changes in the cell viability with increasing ratios of 4S-StarPEG in the case of 1.25mg/ml groups and 4mg/ml hydrogels (Figure 5A and 5C). However, in the case of 2.5mg/ml group, the viability of hiPSC-VSMCs increased with an increase in the cross-linking to 1:1 and 1:2., whereas 1:0.5 ratio was similar to control (Figure 5B). Overall, the cell viability was higher in the case of 4mg/ml hydrogels compared to 1.25 and 2.5mg/ml.

In situ Collagen-HA hydrogel promotes cell viability and maintains the paracrine function:

HA of 1mg/ml final concentration was added while fabricating collagen hydrogels. The effect of HA on the viability of hiPSC-VSMCs embedded was evaluated using the alamarBlue assay. We observed an increase in the viability of hiPSC-VSMCs in 1.25mg/ml and 4mg/ml scaffolds (Figure 6A and C). However, we did not see any difference in the case of 2.5mg/ml group (Figure 6B). The difference in the increase in the viability was bigger in the case of 1.25mg/ml than 2.5mg/ml and 4mg/ml hydrogels (Figure 6D). 4mg/ml scaffold with 4S-StarPEG of 1:1 ratio and HA of 1mg/ml was chosen as the final hydrogel component (Figure 7). Gross images of the hydrogel showed an increase in transparency with 4S-StarPEG cross-linker (Figure 7A). This was further validated by quantifying % transmittance at 450 nm (Figure 7B). The hiPSC-VSMCs embedded in the hydrogel showed a significant increase in cell viability compared to cross-linked and uncross-linked control and collagen hydrogels (Figure 7C). Furthermore, the in situ hydrogel resisted hiPSC-VSMC mediated contraction.

ELISA-based analysis of CM demonstrated secretion of proangiogenic growth factors VEGF, bFGF, SDF-1α and PDGF-AA (Figure 8A-D). There was no significant difference between any of the groups. Figure S2A shows no difference in VEGF expression between control and various crosslinking ratios and also no difference was found between control collagen only and collagen/HA hydrogels (Figure S2B).

Discussion:

Vascular smooth muscle cells derived from integration-free human iPSCs are transforming the field of vascular tissue engineering and regenerative healing with enormous translational potential (B. C. Dash, Z. Jiang, C. Suh, & Y. Qyang, 2015a; Gorecka et al., 2019). Most recently,

our studies revealed the proangiogenic and anti-inflammatory potential of these cells and their use in the treatment of acute and chronic wounds (Dash et al., 2020; Gorecka et al., 2020). While these reports further confirm the future translational implications of hiPSC-VSMCs, we see an unmet need for a suitable delivery system for hiPSC-VSMCs. Our previous findings extensively studied the applicability of plastic compressed collagen scaffolds as a topical delivery system (Dash et al., 2020; Gorecka et al., 2020). However, the degradation, mechanical strength, and ease of delivery are key concerns. Here, we attempted to develop collagen and HA-based in situ hydrogels that can alleviate these issues. Furthermore, these in situ hydrogels would be appealing for wound healing applications because of their non-invasive nature. In addition, they can be considered as potent bioadhesive materials, sealant, or hemostatic agents while facilitating rapid healing.

In this study, we developed an in situ hydrogel using a combination of rat tail collagen type-I and HA for the delivery of hiPSC-VSMCs. To increase the stability of the hydrogel, collagen was cross-linked with 4S-StarPEG without compromising cell viability. The 4S-StarPEG with four NHS groups can cross-link with four amine groups on type-I collagen at 37°C and promote in situ gel formation. We determined the effectiveness of this in situ crosslinking via TNBSA quantification, which indicated a decrease in free amine groups with an increase in collagen to the 4S-StarPEG ratio. However, the effectiveness and efficiency of 4S-StarPEG cross-linking is collagen concentration-dependent. The highest degree of cross-linking was achieved in 4mg/ml of collagen hydrogels and was around 70% compared to 2.5mg/ml (~50%) and 1.25mg/ml (~20%). While an inefficient cross-linking found in the case of 1.25mg/ml can be attributed to less availability of amine molecules, there was no difference in cross-linking between 1:1 and 1:2 in the case of 4mg/ml hydrogels, which can be attributed to a steric hindrance caused by a saturation of 4S-StarPEG. Previous studies with both collagen I and II have demonstrated an increase in

mechanical strength, viscosity, and resistance to collagenase degradation (Collin et al., 2011; Lotz et al., 2017). One such study demonstrated the use of 4S-StarPEG cross-linked collagen scaffold as a skin substitute (Lotz et al., 2017). The report showed the development of a mechanically stronger collagen scaffold with increased resistance to collagenase degradation. Subsequent addition of HA to this collagen hydrogel system made it more skin mimetic with regards to ECM content and strength. The cross-linker visibly increased the transparency of collagen/HA hydrogel as reported earlier in the case of collagen (Lotz et al., 2017). The transparent hydrogel system would help better visualization of cell morphology and wound regeneration.

After the initial cross-linking characterization of the collagen hydrogels, the cellular response to the cross-linking was assessed. We used two different primary cell types, HUVECs and dermal fibroblasts from a human source, and plated them on the top of the hydrogels to assess the viability. We saw an increase in cell viability over time for both cell types. The amount of cross-linking did not have much impact on the viability of either cell type. However, collagen concentration had a greater impact on cell viability. This is consistent with our earlier report and can be attributed to the collagen fibrillar density (CFD) (Dash et al., 2020). The CFD increases with increasing concentration of collagen and impacts cell viability and proliferation. In addition, we observed a greater amount of proliferation in the case of HUVECs compared to dermal fibroblasts. This along with the reduced proliferation of fibroblasts in the cross-linked 4mg/ml hydrogels suggest that HUVECs and dermal fibroblasts respond differently to biomechanical cues. Overall, higher concentrations of 4S-StarPEG did not compromise cell viability of primary cell types such as HUVECs and human dermal fibroblasts.

Next, we determined the effect of 4S-StarPEG on the hiPSC-VSMCs when the cross-linking reaction is conducted with the presence of embedded hiPSC-VSMCs. Similar to HUVECs and dermal fibroblasts, embedded hiPSC-VSMCs showed an increase in cell viability with increasing concentration of collagen. The viability and proliferation of embedded hiPSC-VSMCs were not affected by the cross-linker unlike earlier reports (Lotz et al., 2017). Instead, in the case of 2.5mg/ml, an increase in cell viability can be seen with an increase in amount of cross-linker. These data indicate the importance of cell-matrix interactions in cell viability and proliferation, and suggest that CFD influences viability. We believe at a lower concentration, the cell-binding motifs are less available while at 2.5mg/ml their availability is enhanced due to increased cross-linking. With regards to 4mg/ml, there are more than enough binding motifs and hence the oversaturation with cross-linking did not have an effect. This is further suggested by the observations after addition of HA to the system. Most possibly HA brings a new cellular binding motif and further increases the viscosity irrespective of the cross-linking. That may explain why an increase in cell proliferation across the various concentrations of cross-linked collagen can be seen with the addition of HA. However, the stiff increase in proliferation in the case of 1.25mg/ml can be attributed to both an increase in viscosity and additional cellular motifs.

After careful evaluation of the effects of 4S-StarPEG and HA with various combinations of collagen concentration, we chose 4mg/ml of collagen scaffold with 1:1 collagen to 4S-StarPEG cross-linker ratio and HA for the generation of robust in situ collagen/HA hydrogels. This combination not only has a higher amount of cross-linking to provide a robust skin equivalent but was associated with significant cell viability for all the cell lines tested including hiPSC-VSMCs. We saw a further increase in cell proliferation in the in situ hydrogels of 4mg/ml with the addition

of HA. Furthermore, unlike the scaffolds with a lower concentration of collagen, these scaffolds do not contract when cultured with hiPSC-VSMCs over the culture period.

Although the capability of hiPSC-VSMCs to promote angiogenesis in a collagen scaffold has been illustrated (Dash et al., 2020; Gorecka et al., 2020), the effect of 4S-StarPEG cross-linking and HA is not known. In addition, most of the cell delivery or cell-responsive platforms investigated the ability of the scaffolds to maintain cell viability and not their effect on their ability to secrete paracrine factors. This study investigated both viability and the proangiogenic response of cells in the in situ scaffolds.   Here, we investigated whether cross-linking and HA will affect the secretion. Our data suggested cross-linking and HA did not promote or adversely affected the secretion of VEGF, bFGF, SDF-1α, and PDGF-AA. This might be due to a cross-linker mediated disruption in the collagen fibril formation. This phenomenon has already been described in published studies (Lotz et al., 2017; Yunoki & Matsuda, 2008). This maintenance of growth factor production is critical as cell-mediated regenerative healing is mediated, in part, by cellular paracrine functions. This experimental inquiry demonstrated the usefulness of this delivery system as protection not only at the cell viability level and but also at the secretory level. Together, these results support the utility of a cell-laden in situ hydrogel that could be used for regenerative wound healing without any adverse effect on cell viability or production of angiogenic factors, suggesting such cellular constructs may be exploited to deliver hiPSC-VSMCs locally for wound repair applications.

Conclusion:

In summary, our initial characterization showed that 4S-starPEG cross-linked in situ collagen type I /hyaluronan hydrogel promoted cell viability and maintained the proangiogenic

paracrine secretion of hiPSC-VSMCs. A potential correlation between collagen density and cross-linking and cell viability can be drawn and is key to maintaining the cell viability in addition to the presence of HA. Future in-depth studies should be performed to further analyze cell viability, phenotype, and secretory function of hiPSC-VSMCs in the hydrogel. Also, the skin mimetic property, in addition to in situ properties, make this hydrogel a promising candidate as a carrier of hiPSC-VSMCs for future wound healing applications.

Author Contributions: B.C.D. conceived the study. B.C.D. and H.C.H., procured the funding. B.C.D. and K.D. designed the experiments. K.D. and B.C.D. performed the experiments. B.C.D. and K.D. wrote the manuscript. All the authors participated in data analysis, discussed the results and reviewed the manuscript.

Funding: This work was funded by Plastic Surgery Foundation Grant 18-003032 (H.C.H and B.C.D) and Yale Department of Surgery (H.C.H).

Acknowledgement: The authors would like to thank the core research facilities at Yale Department of Surgery.

Conflicts of Interest: The authors declare no conflict of interest.

References:

Ahmed, M., & Ffrench-Constant, C. (2016). Extracellular Matrix Regulation of Stem Cell Behavior. *Curr Stem Cell Rep, 2*, 197-206. doi: 10.1007/s40778-016-0056-2

Atchison, L., Abutaleb, N. O., Snyder-Mounts, E., Gete, Y., Ladha, A., Ribar, T., . . . Truskey, G. A. (2020). iPSC-Derived Endothelial Cells Affect Vascular Function in a Tissue-Engineered Blood Vessel Model of Hutchinson-Gilford Progeria Syndrome. *Stem Cell Reports, 14*(2), 325-337. doi: 10.1016/j.stemcr.2020.01.005

Atchison, L., Zhang, H., Cao, K., & Truskey, G. A. (2017). A Tissue Engineered Blood Vessel Model of Hutchinson-Gilford Progeria Syndrome Using Human iPSC-derived Smooth Muscle Cells. *Sci Rep, 7*(1), 8168. doi: 10.1038/s41598-017-08632-4

Ayoubi, S., Sheikh, S. P., & Eskildsen, T. V. (2017). Human induced pluripotent stem cell-derived vascular smooth muscle cells: differentiation and therapeutic potential. *Cardiovasc Res, 113*(11), 1282-1293. doi: 10.1093/cvr/cvx125

Browne, S., Monaghan, M. G., Brauchle, E., Berrio, D. C., Chantepie, S., Papy-Garcia, D., . . . Pandit, A. (2015). Modulation of inflammation and angiogenesis and changes in ECM GAG-activity via dual delivery of nucleic acids. *Biomaterials, 69*, 133-147. doi: 10.1016/j.biomaterials.2015.08.012

Cheung, C., Bernardo, A. S., Trotter, M. W., Pedersen, R. A., & Sinha, S. (2012). Generation of human vascular smooth muscle subtypes provides insight into embryological origin-dependent disease susceptibility. *Nat Biotechnol, 30*(2), 165-173. doi: 10.1038/nbt.2107

Collin, E. C., Grad, S., Zeugolis, D. I., Vinatier, C. S., Clouet, J. R., Guicheux, J. J., . . . Pandit, A. S. (2011). An injectable vehicle for nucleus pulposus cell-based therapy. *Biomaterials, 32*(11), 2862-2870. doi: 10.1016/j.biomaterials.2011.01.018

Dash, B. C., Jiang, Z., Suh, C., & Qyang, Y. (2015a). Induced pluripotent stem cell-derived vascular smooth muscle cells: methods and application. *Biochem J, 465*(2), 185-194. doi: 10.1042/BJ20141078

Dash, B. C., Jiang, Z. X., Suh, C., & Qyang, Y. B. (2015b). Induced pluripotent stem cell-derived vascular smooth muscle cells: methods and application. *Biochemical Journal, 465*, 185-194. doi: 10.1042/Bj20141078

Dash, B. C., Levi, K., Schwan, J., Luo, J., Bartulos, O., Wu, H., . . . Qyang, Y. (2016). Tissue-Engineered Vascular Rings from Human iPSC-Derived Smooth Muscle Cells. *Stem Cell Reports, 7*(1), 19-28. doi: 10.1016/j.stemcr.2016.05.004

Dash, B. C., Setia, O., Gorecka, J., Peyvandi, H., Duan, K., Lopes, L., . . . Hsia, H. C. (2020). A Dense Fibrillar Collagen Scaffold Differentially Modulates Secretory Function of iPSC-Derived Vascular Smooth Muscle Cells to Promote Wound Healing. *Cells, 9*(4). doi: 10.3390/cells9040966

Dash, B. C., Xu, Z., Lin, L., Koo, A., Ndon, S., Berthiaume, F., . . . Hsia, H. (2018). Stem Cells and Engineered Scaffolds for Regenerative Wound Healing. *Bioengineering (Basel), 5*(1). doi: 10.3390/bioengineering5010023

Depalle, B., Qin, Z., Shefelbine, S. J., & Buehler, M. J. (2015). Influence of cross-link structure, density and mechanical properties in the mesoscale deformation mechanisms of collagen fibrils. *J Mech Behav Biomed Mater, 52*, 1-13. doi: 10.1016/j.jmbbm.2014.07.008

Fontana, G., Srivastava, A., Thomas, D., Lalor, P., Dockery, P., & Pandit, A. (2015). Three-Dimensional Microgel Platform for the Production of Cell Factories Tailored for the Nucleus Pulposus. *Bioconjug Chem, 26*(7), 1297-1306. doi: 10.1021/bc5004247

Fontana, G., Thomas, D., Collin, E., & Pandit, A. (2014). Microgel microenvironment primes adipose-derived stem cells towards an NP cells-like phenotype. *Adv Healthc Mater, 3*(12), 2012-2022. doi: 10.1002/adhm.201400175

Ge, X., Ren, Y., Bartulos, O., Lee, M. Y., Yue, Z., Kim, K. Y., . . . Qyang, Y. (2012). Modeling supravalvular aortic stenosis syndrome with human induced pluripotent stem cells. *Circulation, 126*(14), 1695-1704. doi: 10.1161/CIRCULATIONAHA.112.116996

Gerecht, S., Burdick, J. A., Ferreira, L. S., Townsend, S. A., Langer, R., & Vunjak-Novakovic, G. (2007). Hyaluronic acid hydrogel for controlled self-renewal and differentiation of human embryonic stem cells. *Proc Natl Acad Sci U S A, 104*(27), 11298-11303. doi: 10.1073/pnas.0703723104

Gorecka, J., Gao, X., Fereydooni, A., Dash, B. C., Luo, J., Lee, S. R., . . . Dardik, A. (2020). Induced pluripotent stem cell-derived smooth muscle cells increase angiogenesis and accelerate diabetic wound healing. *Regen Med, 15*(2), 1277-1293. doi: 10.2217/rme-2019-0086

Gorecka, J., Kostiuk, V., Fereydooni, A., Gonzalez, L., Luo, J., Dash, B., . . . Dardik, A. (2019). The potential and limitations of induced pluripotent stem cells to achieve wound healing. *Stem Cell Res Ther, 10*(1), 87. doi: 10.1186/s13287-019-1185-1

Gu, L., Shan, T., Ma, Y. X., Tay, F. R., & Niu, L. (2019). Novel Biomedical Applications of Crosslinked Collagen. *Trends Biotechnol, 37*(5), 464-491. doi: 10.1016/j.tibtech.2018.10.007

Gui, L. Q., Dash, B. C., Luo, J. S., Qin, L. F., Zhao, L. P., Yamamoto, K., . . . Qyang, Y. B. (2016). Implantable tissue-engineered blood vessels from human induced pluripotent stem cells. *Biomaterials, 102*, 120-129. doi: 10.1016/j.biomaterials.2016.06.010

Hanjaya-Putra, D., Wong, K. T., Hirotsu, K., Khetan, S., Burdick, J. A., & Gerecht, S. (2012). Spatial control of cell-mediated degradation to regulate vasculogenesis and angiogenesis in hyaluronan hydrogels. *Biomaterials, 33*(26), 6123-6131. doi: 10.1016/j.biomaterials.2012.05.027

Highley, C. B., Prestwich, G. D., & Burdick, J. A. (2016). Recent advances in hyaluronic acid hydrogels for biomedical applications. *Curr Opin Biotechnol, 40*, 35-40. doi: 10.1016/j.copbio.2016.02.008

Hinderer, S., Layland, S. L., & Schenke-Layland, K. (2016). ECM and ECM-like materials - Biomaterials for applications in regenerative medicine and cancer therapy. *Adv Drug Deliv Rev, 97*, 260-269. doi: 10.1016/j.addr.2015.11.019

Hou, L., Coller, J., Natu, V., Hastie, T. J., & Huang, N. F. (2016). Combinatorial extracellular matrix microenvironments promote survival and phenotype of human induced pluripotent stem cell-derived endothelial cells in hypoxia. *Acta Biomater, 44*, 188-199. doi: 10.1016/j.actbio.2016.08.003

Karamariti, E., Margariti, A., Winkler, B., Wang, X., Hong, X., Baban, D., . . . Xu, Q. (2013). Smooth muscle cells differentiated from reprogrammed embryonic lung fibroblasts through DKK3 signaling are potent for tissue engineering of vascular grafts. *Circ Res, 112*(11), 1433-1443. doi: 10.1161/CIRCRESAHA.111.300415

Khetan, S., & Corey, O. (2019). Maintenance of stem cell viability and differentiation potential following cryopreservation within 3-dimensional hyaluronic acid hydrogels. *Cryobiology, 90*, 83-88. doi: 10.1016/j.cryobiol.2019.08.001

Klein, D. (2018). iPSCs-based generation of vascular cells: reprogramming approaches and applications. *Cell Mol Life Sci, 75*(8), 1411-1433. doi: 10.1007/s00018-017-2730-7

Kwon, M. Y., Wang, C., Galarraga, J. H., Pure, E., Han, L., & Burdick, J. A. (2019). Influence of hyaluronic acid modification on CD44 binding towards the design of hydrogel biomaterials. *Biomaterials, 222*, 119451. doi: 10.1016/j.biomaterials.2019.119451

Lee, S., Tong, X., & Yang, F. (2016). Effects of the poly(ethylene glycol) hydrogel crosslinking mechanism on protein release. *Biomater Sci, 4*(3), 405-411. doi: 10.1039/c5bm00256g

Liu, G. H., Barkho, B. Z., Ruiz, S., Diep, D., Qu, J., Yang, S. L., . . . Izpisua Belmonte, J. C. (2011). Recapitulation of premature ageing with iPSCs from Hutchinson-Gilford progeria syndrome. *Nature, 472*(7342), 221-225. doi: 10.1038/nature09879

Lotz, C., Schmid, F. F., Oechsle, E., Monaghan, M. G., Walles, H., & Groeber-Becker, F. (2017). Cross-linked Collagen Hydrogel Matrix Resisting Contraction To Facilitate Full-Thickness Skin Equivalents. *ACS Appl Mater Interfaces, 9*(24), 20417-20425. doi: 10.1021/acsami.7b04017

Luo, J., Qin, L., Zhao, L., Gui, L., Ellis, M. W., Huang, Y., . . . Qyang, Y. (2020). Tissue-Engineered Vascular Grafts with Advanced Mechanical Strength from Human iPSCs. *Cell Stem Cell, 26*(2), 251-261 e258. doi: 10.1016/j.stem.2019.12.012

Maguire, E. M., Xiao, Q., & Xu, Q. (2017). Differentiation and Application of Induced Pluripotent Stem Cell-Derived Vascular Smooth Muscle Cells. *Arterioscler Thromb Vasc Biol, 37*(11), 2026-2037. doi: 10.1161/ATVBAHA.117.309196

Monaghan, M., Browne, S., Schenke-Layland, K., & Pandit, A. (2014). A collagen-based scaffold delivering exogenous microrna-29B to modulate extracellular matrix remodeling. *Mol Ther, 22*(4), 786-796. doi: 10.1038/mt.2013.288

Papakonstantinou, E., Roth, M., & Karakiulakis, G. (2012). Hyaluronic acid: A key molecule in skin aging. *Dermatoendocrinol, 4*(3), 253-258. doi: 10.4161/derm.21923

Patsch, C., Challet-Meylan, L., Thoma, E. C., Urich, E., Heckel, T., O'Sullivan, J. F., . . . Cowan, C. A. (2015). Generation of vascular endothelial and smooth muscle cells from human pluripotent stem cells. *Nat Cell Biol, 17*(8), 994-1003. doi: 10.1038/ncb3205

Shen, Y. I., Abaci, H. E., Krupsi, Y., Weng, L. C., Burdick, J. A., & Gerecht, S. (2014). Hyaluronic acid hydrogel stiffness and oxygen tension affect cancer cell fate and endothelial sprouting. *Biomater Sci, 2*(5), 655-665. doi: 10.1039/C3BM60274E

Shen, Y. I., Cho, H., Papa, A. E., Burke, J. A., Chan, X. Y., Duh, E. J., & Gerecht, S. (2016). Engineered human vascularized constructs accelerate diabetic wound healing. *Biomaterials, 102*, 107-119. doi: 10.1016/j.biomaterials.2016.06.009

Shi, Y., Inoue, H., Wu, J. C., & Yamanaka, S. (2017). Induced pluripotent stem cell technology: a decade of progress. *Nat Rev Drug Discov, 16*(2), 115-130. doi: 10.1038/nrd.2016.245

Soldner, F., & Jaenisch, R. (2012). Medicine. iPSC disease modeling. *Science, 338*(6111), 1155-1156. doi: 10.1126/science.1227682

Solis, M. A., Chen, Y. H., Wong, T. Y., Bittencourt, V. Z., Lin, Y. C., & Huang, L. L. (2012). Hyaluronan regulates cell behavior: a potential niche matrix for stem cells. *Biochem Res Int, 2012*, 346972. doi: 10.1155/2012/346972

Taguchi, T., Xu, L., Kobayashi, H., Taniguchi, A., Kataoka, K., & Tanaka, J. (2005). Encapsulation of chondrocytes in injectable alkali-treated collagen gels prepared using poly(ethylene glycol)-based 4-armed star polymer. *Biomaterials, 26*(11), 1247-1252. doi: 10.1016/j.biomaterials.2004.04.029

Takagi, S., Mandai, M., Gocho, K., Hirami, Y., Yamamoto, M., Fujihara, M., . . . Takahashi, M. (2019). Evaluation of Transplanted Autologous Induced Pluripotent Stem Cell-Derived Retinal

Pigment Epithelium in Exudative Age-Related Macular Degeneration. *Ophthalmol Retina, 3*(10), 850-859. doi: 10.1016/j.oret.2019.04.021

Takahashi, K., & Yamanaka, S. (2006). Induction of pluripotent stem cells from mouse embryonic and adult fibroblast cultures by defined factors. *Cell, 126*(4), 663-676. doi: 10.1016/j.cell.2006.07.024

Thomas, D., Fontana, G., Chen, X., Sanz-Nogues, C., Zeugolis, D. I., Dockery, P., . . . Pandit, A. (2014). A shape-controlled tuneable microgel platform to modulate angiogenic paracrine responses in stem cells. *Biomaterials, 35*(31), 8757-8766. doi: 10.1016/j.biomaterials.2014.06.053

Watt, F. M., & Huck, W. T. (2013). Role of the extracellular matrix in regulating stem cell fate. *Nat Rev Mol Cell Biol, 14*(8), 467-473. doi: 10.1038/nrm3620

Yunoki, S., & Matsuda, T. (2008). Simultaneous processing of fibril formation and cross-linking improves mechanical properties of collagen. *Biomacromolecules, 9*(3), 879-885. doi: 10.1021/bm7012058

Zhang, J., Lian, Q., Zhu, G., Zhou, F., Sui, L., Tan, C., . . . Colman, A. (2011). A human iPSC model of Hutchinson Gilford Progeria reveals vascular smooth muscle and mesenchymal stem cell defects. *Cell Stem Cell, 8*(1), 31-45. doi: 10.1016/j.stem.2010.12.002

Figures:

Figure 1: Schematic showing the fabrication of an in situ Collagen/HA hydrogel for the delivery of hiPSC-VSMCs.

Figure 2: Characterization of 4S-starPEG cross-linking of collagen type-I hydrogels. TNBSA showing qualitative analysis of free amine groups in in situ collagen hydrogels of (A) 1.25mg/ml, (B) 2.5mg/ml and (C) 4mg/ml of collagen concentration with various molar ratios (1:0.5, 1:1, and 1:2) of collagen to 4S-starPEG. (D) The cumulative data presenting percent cross-linking of various hydrogels. * denotes statistical significance differences between the different groups (n=4, one-way ANOVA, *p < 0.05, **p<0.005, ***p<0.001, and ****p<0.0001). Control (CTRL) is Uncross-linked collagen hydrogel.

Figure 3: Characterization of biocompatibility of in situ collagen hydrogels. AlamarBlue assay showing proliferation of fibroblasts on (A) day 1 and (B) day 3 and HUVECs on (C) day 1 and (D) day 3 of culture on top of 1.25mg/ml, 2.5mg/ml and 4mg/ml of collagen concentration and different collagen to 4S-starPEG ratios. * and # denote statistical significance differences between the different groups (n=5, two-way ANOVA, *p<0.05, **p<0.005, ***p<0.001, ****p<0.0001, #p<0.05, and ###p<0.001). Control (CTRL) is Uncross-linked collagen hydrogel.

Figure 4: Phenotype assessment of hiPSC-VSMCs. Immunofluorescence images showing (A) Calponin (Green) and (B) SM-22α (Green) stained hiPSC-VSMCs. Dapi (Blue) was used to stain nuclei. Scale bar measures 43 µm.

Figure 5: Characterization of hiPSC-VSMC viability in the in situ Collagen hydrogels. AlamarBlue assay showing cell proliferation of hiPSC-VSMCs embedded in the in situ collagen hydrogels of (A) 1.25mg/ml, (B) 2.5mg/ml and (C) 4mg/ml of collagen concentration and various collagen to PEG ratios on day 3. * denotes statistical significance differences between the different groups (n=4, one-way ANOVA, $*p < 0.05$ and $****p < 0.0001$).

Figure 6: Characterization of hiPSC-VSMC viability in the Collagen-HA hydrogels. AlamarBlue assay showing cell proliferation of hiPSC-VSMCs embedded in the in situ Collagen hydrogels of (A) 1.25mg/ml, (B) 2.5mg/ml and (C) 4mg/ml of collagen concentration and HA of 1mg/ml final concentration on day 3. (D) Relative fluorescence intensity comparing hiPSC-VSMC viability in 1.25mg/ml, 2.5mg/ml and 4mg/ml collagen concentration of scaffolds with HA. * denotes statistical significance differences between the different groups (n=4, t-test and one-way ANOVA, **$p < 0.005$ and ****$p < 0.0001$).

Figure 7: Characterization of optical properties of in situ hydrogel and the hiPSC-VSMC viability. (A) Macroscopic images of Uncross-linked collagen hydrogels (Col-I) and cross-linked collagen hydrogels with 1:1 ratio of collagen to 4S-StarPEG (Col-I + PEG) and cross-linked hydrogel with HA (Col-I + PEG + HA). (B) Transmission of different collagen hydrogels and collagen solution (Col-I Solution) were compared in an absorption at 450 nm. (C) AlamarBlue cell viability assay showing the viability of hiPSC-VSMCs embedded in the in situ Collagen-HA hydrogels of 4mg/ml of collagen concentration, 1:1 ratio of collagen to PEG cross-linker and HA of 1mg/ml final concentration on day 3. Collagen scaffold with and without cross-linking was kept as controls. * denotes statistical significance differences between the different groups (n=3-6, one-way ANOVA, *p<0.05).

Figure 8: Characterization of pro-angiogenic growth factor secretion in the in situ Collagen-HA hydrogels. Qualitative ELISA showing secretion of growth factors (A) VEGF, (B) bFGF, (C) SDF-1α and (D) PDGF-AA from in situ Collagen-HA hydrogels. Collagen scaffold with and without cross-linking was kept as controls. * denotes statistical significance differences between the different groups (n=3-6, one-way ANOVA, *p<0.05).