Mineral density differences between femoral cortical bone and trabecular bone are not explained by turnover rate alone

Chloé Lerebours[a,] , Richard Weinkamer[b], Andreas Roschger[c], Pascal R. Buenzli[d*]

[a]School of Mathematical Sciences, Monash University, Clayton, Australia
[b]Max Planck Institute of Colloids and Interfaces, Department of Biomaterials, Potsdam, Germany
[c]Department of the Chemistry and Physics of Materials, Paris–Lodron University of Salzburg, Salzburg, Austria
[d]School of Mathematical Sciences, Queensland University of Technology (QUT), Brisbane, Australia

June 9, 2020

Abstract – We report on measurements of the bone mineral density distribution (BMDD) from human femoral cortical bone samples, which show that femoral cortical bone possesses a higher bone mineral density, but a similar mineral heterogeneity around the mean as trabecular bone. To understand why cortical and trabecular BMDDs differ, we propose a rigorous hypothesis-testing approach based on quantitative modelling, and test whether the difference in BMDD can be explained by (i) differences in turnover rate; (ii) differences in osteoclast resorption behaviour; and (iii) differences in mineralisation kinetics between the two bone types. We find that accounting only for differences in turnover rate is inconsistent with the fact that both BMDDs have a similar spread around the mean, and that accounting for differences in osteoclast resorption behaviour leads to biologically inconsistent bone remodelling patterns. We conclude that the kinetics of mineral accumulation in bone matrix must therefore be different in femoral cortical bone and trabecular bone. Although both cortical and trabecular bone are made up of lamellar bone, the different mineralisation kinetics in the two types of bone point towards more profound structural differences than usually assumed.

Key words: Bone mineral heterogeneity, Turnover rate, Mineralisation kinetics, Bone Remodelling, Femoral cortical bone, Trabecular bone.

1 Introduction

Bone remodelling periodically replaces old bone with an unmineralised collagen-rich matrix, which is subsequently infiltrated with a mineral phase. The growth of mineral crystals in this phase gradually confers to bone its stiffness and strength [44, 16]. Regions of bone formed at different times achieve various degrees of mineralisation and are visualised as different grey-level intensities in bone scans obtained by X-ray absorption or quantitative backscattered electron imaging (qBEI) [49, 6, 13, 43, 46, 56, 17]. The heterogeneity of mineral density in a bone scan gives an indication of bone's renewal history and provides an indirect measure of remodelling and mineralisation processes. Bone mineral density distributions (BMDDs) quantify this mineral heterogeneity experimentally as frequency distributions of calcium content constructed from qBEI scans [50, 53].

In adult trabecular bone, the BMDD is independent of age, ethnicity, sex, and skeletal site (transiliac bone, vertebrae, femoral neck, femoral head, and patella) [50, 53], and the relatively low inter-individual variation has enabled the definition of a reference trabecular BMDD of healthy adults [50]. In several diseases, the BMDD deviates from this reference because of differences in remodelling and/or mineralisation processes [53]. In cortical bone, the mean mineral content depends on skeletal site [29], so that cortical BMDDs may differ from the reference trabecular BMDD in health too.

In this paper, we report on novel measurements of cortical BMDDs from human femur midshafts collected post mortem in healthy adults. These measurements reveal a higher degree of mineralisation than the reference trabecular BMDD, but

a similar spread of mineral heterogeneity around the most frequently occurring calcium content (position of the peak of the BMDD). To understand the reason for the difference in mineral distribution between trabecular bone and femoral cortical bone in healthy adults, we use an established theoretical framework that allows us to quantify BMDD signatures in terms of descriptive parameters of remodelling and mineralisation processes [54, 55].

Shifts of BMDDs and of average bone mineral densities towards higher and lower mineral densities have previously been attributed to lower and higher birth rates of basic multicellular units (BMUs), respectively [5, 39], and acceleration and deceleration of mineral accumulation in specific bone diseases [42]. Mineralisation kinetics, i.e. the accumulation of mineral density with time in a small volume of newly formed bone, has been reported to be similar in cortical and trabecular bones in healthy dogs [34], and in the iliac crest of healthy ewes [2]. Since turnover rates are normally lower in femoral cortical bone than in trabecular bone [33, 45], this difference could explain the shift in BMDD towards higher mineral densities seen in human femoral cortical bone. A lower turnover rate provides more time for secondary mineralisation to take place, which increases the average bone mineral density [5].

Using the theoretical modelling framework to compare quantitatively the femoral cortical BMDD and the reference trabecular BMDD, we show that their difference cannot be accounted for by a difference in turnover rate only. We thus explore systematically further hypotheses related to differences in resorption patterns of remodelling, and in mineralisation kinetics. The novelty of the mathematical analysis is to investigate whether resorption behaviour of osteoclasts targeting

---

specific calcium content could explain the differences between the BMDDs. Resorption patterns are likely to be different in cortical bone, where resorption may reach any mineral density by tunnelling of new Haversian canals, and in trabecular bone, where resorption predominantly reaches weakly mineralised bone at the trabeculae's surfaces [36, 20]. Our analysis shows that any hypothesis that does not account for a difference in mineralisation kinetics is inconsistent with the experimental data. We are led to conclude that mineralisation kinetics has to be different between these bone types. A possible interpretation of this difference is that the rate of mineralisation kinetics is coupled with the rate of turnover in such a way that mineral accumulation is faster in bone turned over quickly than in bone turned over slowly.

2 Materials and Methods

2.1 Backscattered electron imaging and experimental BMDD

Midshaft femur cross-sections were extracted post mortem at the Department of Forensic Medicine of the Medical University of Vienna from four adult women (48, 50, 55 and 56 years old) and three young adults (female 25, male 18, 22 years old), who died unexpectedly with no known bone pathologies. The study was performed in accordance with the ethic commission board of the institution (EK#: 1757/2013). The samples were frozen at $-20°C$ immediately after extraction. Prior to measurements, the samples were unfrozen, dehydrated and embedded in polymethylmethacrylate (PMMA) as described elsewhere [49]. Using the scanning electron microscope (Zeiss supra 40, Oberkochen, Germany) in backscattered mode, qBEI scans of in average of $40\,mm^2$ bone area per sample covering medial and or lateral cortical bone were acquired with a pixel resolution of $1.73\,\mu m$. The imaging experimental setup was calibrated and checked for measurement reliability to convert grey intensity values into calcium weight percent (wt% Ca), and further to extract BMDDs following standard procedures [49, 31]. The evaluation was done twice, first by considering the whole cortex and then, by excluding the endosteal and periosteal regions. Obtained differences were minor and, therefore, only results from a whole cortex evaluation are presented. A mean femoral cortical BMDD (Fm.BMDD) was constructed from the very similar individual BMDDs of the adult and the young adult age group by calculating the mean values for each histogram bin.

The reference trabecular BMDD (Tb.BMDD) used in this paper corresponds to the average of 52 BMDDs coming from different individuals, and different skeletal sites from a previous study [50]. Although the number of individuals investigated here to define (Fm.BMDD) is lower than the cohort used to establish the reference trabecular BMDD, the cortical BMDD statistics is substantially improved by the large areas measured. In the femur, the degree of mineralisation is known to depend slightly on the region of interest along the periosteal-endosteal axis [56]. However, the variation in BMDD within the cross-sections was small enough to justify the consideration of whole cross-section BMDDs.

The Tb.BMDD and Fm.BMDD were smoothed by the 'loess'

Figure 1 – Experimental BMDDs: Reference trabecular BMDD (Tb.BMDD, thick black line) with the ± SD interval (grey lines); adult femoral cortical mean BMDD (Fm.BMDD: thick orange line, with corresponding individual BMDDs as thin orange lines). The BMDDs are normalised to the evaluated bone area (100%).

Matlab procedure [37] with a span of 1.05 wt% Ca. This smoothing enabled better numerical evaluations in the mathematical analyses by alleviating the poor signal-to-noise ratio of the BMDD at very low and very high calcium content [31].

The trabecular and femoral cortical BMDDs exhibit an overall bell-shaped curve (Figure 1). To quantify this shape, we calculated the following shape parameters introduced in Refs [50, 53]: Ca_{PEAK}, the calcium content at the peak of the BMDD; Ca_{MEAN}, the mean of the BMDD, which corresponds to the average calcium content of the bone sample; and Ca_{WIDTH}, the full width at half maximum of the BMDD, which characterises the heterogeneity in mineral density of the sample around the distribution peak [50, 53]. We also calculated the skewness Ca_{SKEW} and the kurtosis Ca_{KURT} of the distribution, which characterise the asymmetry and the peakedness of the distribution, respectively. Skewness and kurtosis are calculated on a restricted interval where the BMDD is larger than 1% of the peak height.

The strength of the BMDD analysis presented in this study, is to address rather late stages of mineralisation, which are difficult to investigate with labelling techniques.

2.2 Mathematical model of the BMDD

To evaluate the influence of turnover rate and mineralisation kinetics on BMDDs, we use the mathematical model developed in Refs [54, 55]. We summarise the main features of this mathematical model below and refer the reader to A for further details. In the mathematical equations, the BMDD is denoted by $\rho(c)$, where c is the calcium content. The quantity $\rho(c)dc$ represents the volume of bone within the sample that possesses a calcium content in the histogram bin $[c, c + dc]$. The remodelling and mineralisation processes are fully characterised in the model by three elements: the mineralisation rate, the resorption rate, and the formation rate, as described below.

The mineralisation rate, denoted by $q(c)$ (in wt% Ca per unit time), describes how fast calcium accumulates in a microscopic region of bone of calcium content c. This function is defined such that during a small time increment Δt, calcium content increases by $\Delta c = q(c)\Delta t$. The

mineralisation rate $q(c)$ entirely determines the kinetics of mineralisation $c(t)$, i.e. how the calcium content of this region accumulates with time. Conversely, the mineralisation kinetics $c(t)$ entirely determines the mineralisation rate $q(c)$, see Eq. (10) [54]. The effect of mineralisation, which occurs at different speeds $q(c)$ within a sample because of the heterogeneity of mineral density, is to push the BMDD towards higher calcium content, as illustrated in Figure 2(e).

The resorption rate $r(c)$ is the probability per unit time that bone matrix with calcium content c is resorbed by osteoclasts. Different osteoclast resorption patterns can be captured by modifying this function. The effect of this function in the mathematical model is to lower the height of the BMDD with different propensities depending on c, as illustrated in Fig. 2(f). A calcium-independent resorption rate represents random resorption, i.e. each region of bone is as likely to be resorbed, irrespective of its calcium content. The quantity $r(c)\rho(c)\mathrm{d}c$ is the volume of bone with calcium content in $[c, c + \mathrm{d}c]$ resorbed per unit time. Summing $r(c)\rho(c)\mathrm{d}c$ over all the histogram bins gives the total volume of bone resorbed per unit time in the sample, see Eq. (6).

Finally, the formation rate is the total volume of bone formed per unit time by the osteoblasts. Since osteoblasts form unmineralised matrix, the calcium content deposited by the osteoblasts is taken to be 0 wt% Ca.

Because we investigate differences in BMDDs in healthy adults, we assume that bone resorption and bone formation are balanced. The bone volume formed per unit time and the bone volume resorbed per unit time are taken to be identical, and we express these quantities by the turnover rate χ, defined as the fraction of bone volume (BV) renewed per unit time (Eq. (6)) [19]. In humans, turnover rate depends on bone type and skeletal site. In this study, we take the turnover rate in trabecular bone to be $\chi_{\mathrm{Tb}} = 20\%$/year, and the turnover rate in femoral cortical bone to be $\chi_{\mathrm{Fm}} = 5\%$/year [21, 44, 45]. The functions and parameters used in this model are listed in Table 1.

The conservation of bone volume leads to a steady state of the BMDD, due to an equilibrium between (i) the continuous generation of new unmineralised bone due to formation; (ii) the continuous drift of bone towards higher calcium content due to mineralisation; and (iii) the continuous lowering of the BMDD due to resorption (Fig. 2). In steady state, the mathematical model expresses a relationship between the BMDD $\rho(c)$, the mineralisation rate $q(c)$, the resorption rate $r(c)$ and the turnover rate χ [54]. Both mineralisation rate and resorption rate combine to make up a BMDD signature (see Eq. (7)). To extract the mineralisation rate $q(c)$ from measurements of the BMDD (Eq. (8)), assumptions need to be made on the resorption rate $r(c)$. Equivalently, to extract the resorption rate $r(c)$ from measurements of the BMDD (Eq. (9)), assumptions need to be made on the mineralisation rate $q(c)$. To explain the differences observed between Fm.BMDD and Tb.BMDD, we thus test a series of assumptions on differences that may exist in turnover rate, resorption rate, and mineralisation rate between these two bone types.

3 Results

The qBEI measurements show that the mean femoral cortical BMDD (Fm.BMDD) is of similar shape as the reference trabecular BMDD of healthy adults (Tb.BMDD), but it is shifted towards higher calcium contents (Fig. 1). This observation is described quantitatively by our measurements of peak shape and location. Table 2 shows that the full width at half maximum $\mathrm{Ca_{WIDTH}}$, skewness $\mathrm{Ca_{SKEW}}$, and kurtosis $\mathrm{Ca_{KURT}}$ are nearly identical for Fm.BMDD and Tb.BMDD. The difference in value of these parameters is well within the standard deviations of the measurements. However, the peak location $\mathrm{Ca_{PEAK}}$ of Fm.BMDD is shifted by about 3wt% Ca, well beyond the standard deviations of $\mathrm{Ca_{PEAK}}$.

In the following, we explore computationally a series of hypotheses on the intrinsic remodelling and mineralisation processes of femoral cortical and trabecular bone with the aim to understand how the mineral heterogeneity in these bone types can be distributed similarly, but around different peak positions.

Hypothesis 1: *The difference between femoral cortical and reference trabecular BMDDs is only due to the difference in turnover rate between these two bone types.*

The motivation for this hypothesis is the well-known difference in turnover between bone types [45], and the suspected influence that turnover exerts on the BMDD [5, 55]. As a first step, we therefore assume that

(1) Resorption rate is slower in cortical bone than in trabecular bone due to the difference in turnover rate, i.e., the total volume fraction resorbed per unit time is lower in cortical bone;

(2) Resorption rate is unbiased in the two bone types, i.e., osteoclasts resorb bone independently of calcium content (random resorption);

(3) Mineralisation rate is identical in the two bone types.

To test Hypothesis 1, we check whether Fm.BMDD and Tb.BMDD measured experimentally are compatible with BMDDs calculated from Eq. (7) with the three assumptions above. When resorption is random, the resorption rate functions $r(c)$ are constant and equal to the turnover rates χ_{Fm} or χ_{Tb}, respectively (see Eqs (5)–(6)). Two possible choices can then be made to determine the common mineralisation rate $q(c)$ from the experimental data. The first choice corresponds to the mineralisation rate determined from Tb.BMDD and χ_{Tb} using Eq. (8), as was done in Ref. [54]. The second choice corresponds to the mineralisation rate determined from Fm.BMDD and χ_{Fm} using Eq. (8). Hypothesis 1 then allows us to estimate computationally Fm.BMDD from the experimental Tb.BMDD, and to estimate computationally Tb.BMDD from the experimental Fm.BMDD by means of Eq. (7). Figure 3 shows that the BMDDs computed using either of these choices of mineralisation rates differ significantly from the BMDDs measured experimentally.

The mathematical model, therefore, shows that turnover rate influences $\mathrm{Ca_{PEAK}}$ as expected, i.e., $\mathrm{Ca_{PEAK}}$ is low at high turnover rate and $\mathrm{Ca_{PEAK}}$ is high at low turnover rate.

Figure 2 – (a) qBEI image of iliac crest trabecular bone. Distinct bone packets within trabeculae are seen as regions of distinct grey colours. (b) Schematic representation of the zoomed qBEI image, where the different degree of mineralisation between the bone packets are highlighted. The influence of mineralisation without remodelling, and of remodelling without mineralisation on the calcium distribution in this region of bone is schematised in (c) and (d), respectively. The corresponding changes in BMDD due to these processes are shown in (e)–(f): (e) mineralisation pushes the BMDD towards higher calcium content; and (f) bone resorption lowers the BMDD while bone formation introduces unmineralised bone.

But turnover rate has also a strong influence on peak width Ca_{WIDTH}. Both experimental BMDDs have a similar Ca_{WIDTH} (Table 2), so that no value of turnover rate difference between femoral cortical bone and trabecular bone is able to match jointly Ca_{PEAK} and Ca_{WIDTH} of the computed BMDDs with those of the measured BMDDs [54, 9]. Thus, the difference in mineral distribution between the two bone types cannot be attributed to a change in turnover rate alone.

Hypothesis 2: *The difference between femoral cortical and trabecular BMDDs is due to a difference in turnover rate, and to an osteoclastic bone resorption biased towards specific calcium contents in* one *of the two bone types.*

The motivation for this hypothesis is the likely difference in resorption pattern between femoral cortical bone and trabecular bone. As a second step in our computational hypothesis testing, we still assume random resorption in trabecular bone, but explore whether there are biased resorption patterns in femoral cortical bone such that the BMDD computed from

Eq. (7) matches the measured femoral cortical BMDD. The unique resorption function $r(c)$ that satisfies this requirement is computed using Eq. (9), and shown in Figure 4. This function is negative at some values of calcium content, which means Hypothesis 2 only holds if there is formation by osteoblasts of readily mineralised bone, which clearly contradicts what is known about osteoblast action and bone mineralisation. Conversely, assuming random resorption in cortical bone, the unique trabecular bone resorption function such that the BMDD computed from Eq. (7) matches the measured reference trabecular BMDD is also negative at some values of calcium content (Fig. 4). Hypothesis 2 is thereby falsified.

Hypothesis 3: *The difference between femoral cortical and trabecular BMDDs is due to a difference in turnover rate, and to osteoclastic bone resorption biased towards specific calcium content differently in* both *bone types.*

As a third step, we now relax the assumption that random

Table 1 – Nomenclature

Symbol	Description	Value/Unit
c	Calcium content	wt% Ca
$\rho(c)$	Bone Mineral Density Distribution (Tb.BMDD; Fm.BMDD)	mm^3/wt% Ca
$q(c)$	Mineralisation rate	wt% Ca/year
$r(c)$	Resorption function	year^{-1}
$c(t)$	Mineralisation kinetics	wt% Ca
χ_{Tb}	Turnover rate in trabecular bone	20%/year
χ_{Fm}	Turnover rate in femoral cortical bone	5%/year

Table 2 – Shape parameters of the femoral cortical BMDD from adults, the reference trabecular BMDD, and their difference. The trabecular values are taken from Ref. [53].

BMDD-Parameter	Cortical Mean Values ± StD	Trabecular Mean Values ± StD	Difference (Cortical − Trabecular)
Ca$_{\text{PEAK}}$[wt% Ca]	25.95 ± 0.22	22.94 ± 0.39	+3.01
Ca$_{\text{MEAN}}$[wt% Ca]	25.05 ± 0.28	22.20 ± 0.45	+2.85
Ca$_{\text{WIDTH}}$[wt% Ca]	3.20 ± 0.10	3.35 ± 0.34	−0.15
Ca$_{\text{SKEW}}$[−]	−0.91± 0.21	−0.90± 0.41	−0.01
Ca$_{\text{KURT}}$[−]	5.16 ± 0.68	5.17 ± 1.31	−0.01

Figure 3 – Comparison between experimental BMDDs (thick lines) and BMDDs computed with Hypothesis 1 (thin lines). There is a large discrepancy between the measured femoral cortical BMDD (thick orange) and the BMDD computed with cortical turnover rate and mineralisation rate extracted from the reference trabecular BMDD (thin orange). There is also a large discrepancy between the reference trabecular BMDD (thick black) and the BMDD computed with trabecular turnover rate and mineralisation rate extracted from the femoral corticalBMDD (thin black).

Figure 4 – Distribution of volume of bone resorbed per unit time under Hypothesis 2 with random resorption assumed in trabecular bone (orange), and random resorption assumed in femoral cortical bone (black). The unique resorption rate functions $r(c)$ for which Hypothesis 2 holds are negative in a region of calcium content, which means Hypothesis 2 would only hold if there is formation by osteoblasts of readily mineralised bone.

resorption occurs in one of the bone types and we attempt to determine whether there are two resorption rate functions $r_{\text{Fm}}(c)$ and $r_{\text{Tb}}(c)$, such that the BMDDs computed from Eq. (7) match the experimental BMDDs. Mineralisation kinetics is still assumed to be identical in both bone types as in Hypotheses 1 and 2, i.e., we still consider Assumption (3) to hold. The analysis is now complicated by the fact that mineralisation rates are determined from the experimental BMDDs under a choice of resorption functions by Eq. (8). The procedure employed to test Hypothesis 3, is therefore (i) to first choose a resorption function $r_{\text{Tb}}(c)$; (ii) to deduce the mineralisation rate from Eq. (8) using the femoral cortical BMDD and the choice of resorption function $r_{\text{Tb}}(c)$; and (iii) to then determine $r_{\text{Fm}}(c)$ from Eq. (9) using the reference trabecular BMDD. We can also proceed conversely by choosing first $r_{\text{Fm}}(c)$, and calculate how this choice determines $r_{\text{Tb}}(c)$. This procedure is repeated to explore the set of all possible choices of positive resorption functions $r_{\text{Tb}}(c)$ that lead to positive resorption functions $r_{\text{Fm}}(c)$, and vice versa. Such a pair of resorption functions $r_{\text{Tb}}(c)$, $r_{\text{Fm}}(c)$ represents targeted osteoclast resorption behaviours that lead to the experimental BMDDs while having identical mineralisation kinetics in femoral cortical bone and trabecular bone. Below, we show that this set is strongly restricted by the requirement that both resorption functions must be positive. We find that only cortical resorption

functions that strongly target very lowly mineralised bone are possible.

The detailed mathematical analysis is more involved than in the previous cases, since it requires the exploration of a large space of possible resorption functions. The reader is referred to B for the mathematical details. To help us enforce the positivity of $r_{\mathrm{Fm}}(c)$ given a choice of $r_{\mathrm{Tb}}(c)$, we introduce an auxiliary function $G_{\mathrm{Tb}}(c)$ defined in Eq. (14). Choosing an initial resorption function $r_{\mathrm{Tb}}(c)$ is equivalent to choosing an auxiliary function $G_{\mathrm{Tb}}(c)$. The advantage is that to explore the set of all resorption functions $r_{\mathrm{Tb}}(c)$ that give rise to positive resorption functions $r_{\mathrm{Fm}}(c)$, it is sufficient to explore the set of all auxiliary functions $G_{\mathrm{Tb}}(c)$ below an explicit upper limit determined by the experimental BMDDs (Eq. (17)). Conversely, to explore the set of all resorption functions $r_{\mathrm{Fm}}(c)$ that give rise to positive resorption functions $r_{\mathrm{Tb}}(c)$, it is sufficient to explore the set of all auxiliary functions $G_{\mathrm{Fm}}(c)$ below an explicit upper bound.

To illustrate the difficulty of enforcing the positivity of the resorption functions, Figures 5a,c show a number of different initial choices of $r_{\mathrm{Fm}}(c)$ that correspond to osteoclasts resorbing cortical bone that is preferentially (i) lowly mineralised (exponentials with negative exponents, $\gamma = -10, -30$; (ii) highly mineralised (exponentials with positive exponents, $\gamma = 5, 20$); and (iii) of calcium content restricted to Gaussians of different centres M and widths σ. Since the resorption functions must satisfy the turnover condition (13), they only depend on one independent parameter. Figures 5b,d show that choosing functions $r_{\mathrm{Fm}}(c)$ that correspond to preferential resorption targeting intermediate or highly mineralised cortical bone ($\gamma = 5, 20$, and $M = 25, 28$) do not lead to trabecular resorption rate functions $r_{\mathrm{Tb}}(c)$ that are positive. The auxiliary functions $G_{\mathrm{Fm}}(c)$ corresponding to these choices of $r_{\mathrm{Fm}}(c)$ lie in part above the upper limit (Fig. 5b,d). The same holds for a mild resorption preference towards low calcium content ($\gamma = -10$). The only resorption functions $r_{\mathrm{Fm}}(c)$ that lead to positive trabecular resorption functions $r_{\mathrm{Tb}}(c)$ are the Gaussian centred around lowly mineralised bone ($M = 15$), and the exponential resorbing only lowly mineralised bone ($\gamma = -30$).

The procedure to check Hypothesis 3 thoroughly is to explore the full set of initial choices $G_{\mathrm{Tb}}(c)$ below the upper limit and inspect the cortical resorption functions $r_{\mathrm{Fm}}(c)$ determined by these choices (see B). For illustrative purposes, we show in Fig. 6 the distribution of cortical bone volume resorbed per unit time $r_{\mathrm{Fm}}(c)\rho_{\mathrm{Fm}}(c)$ when $G_{\mathrm{Tb}}(c)$ is set as the upper limit (borderline case, Eq. (17)). In this case too, cortical bone would be preferentially resorbed at extremely low calcium content ($< 22\mathrm{wt\%\,Ca}$).

In B.1, we show rigorously that under Hypothesis 3, for any choice of auxiliary function, at least 25% of the femoral cortical bone resorbed per unit time would have a calcium content less than $21\mathrm{wt\%\,Ca}$, and at least 15% would have a calcium content less than $20\,\mathrm{wt\%\,Ca}$ (see Eq. (21) and Fig. 10). In other words, more than a quarter of all the cortical bone renewed would be targeting new, poorly mineralised bone, to the extent that more than 15% of all cortical bone would be resorbed before undergoing secondary mineralisation. These predictions clearly conflict with the concept that bone remodelling is a repair mechanism that enables bones to maintain structural integrity despite fatigue

loading [35, 11, 4], especially in mechanically stimulated bone such as the femoral cortex. For all the above reasons, we therefore deem Hypothesis 3 to be falsified.

Hypothesis 4: *The difference between femoral cortical and trabecular BMDDs is due to a difference in turnover rate, and a difference in mineralisation kinetics between the two bone types.*

Having exhausted all the possibilities in which mineralisation kinetics was assumed identical between trabecular and femoral cortical bone, we now hypothesise that mineralisation kinetics may be different in trabecular bone and femoral cortical bone, i.e., we no longer consider our assumption (3) to hold. To explore this hypothesis computationally, we revert to the assumption of random resorption in both bone types for simplicity. In this case, the mineralisation rates $q(c)$ and mineralisation kinetic laws $c(t)$ can be determined in each bone types independently by Eqs. (8) and (10) from the experimental BMDDs, Tb.BMDD and Fm.BMDD. The mineralisation rates and kinetic laws determined in this way are shown in Figure 7. Both mineralisation kinetics display a fast initial increase in calcium content, followed by a slower increase in calcium content with time. However, the overall rate of mineralisation in femoral cortical bone is slower than the overall rate of mineralisation in trabecular bone. The timescale of mineralisation kinetics in either bone type depends on the assumed turnover rate in Eq. (8). To factor out the influence of the choice of turnover rate and compare qualitatively the mineralisation kinetics in femoral cortical bone and trabecular bone, we perform a scaling in time of the mineralisation kinetics of cortical bone by the ratio of turnover rates $\frac{\chi_{\mathrm{Tb}}}{\chi_{\mathrm{Fm}}}$. Remarkably, Figure 7 shows that the time-scaled cortical mineralisation rate and time-scaled cortical mineralisation kinetic laws have similar shape as the trabecular mineralisation rate and mineralisation kinetic law, respectively, but are shifted along the calcium content axis. Accounting for this shift additionally by including an offset κ results in a nearly perfect superposition of the transformed cortical mineralisation functions and the trabecular mineralisation functions, i.e.,

$$q_{\mathrm{Tb}}(c) \approx \frac{\chi_{\mathrm{Tb}}}{\chi_{\mathrm{Fm}}}\, q_{\mathrm{Fm}}(c + \kappa) \tag{1}$$

$$C_{\mathrm{Tb}}(t) \approx C_{\mathrm{Fm}}(t)\left(\frac{\chi_{\mathrm{Tb}}}{\chi_{\mathrm{Fm}}}\, t\right) + \kappa \tag{2}$$

The goodness of match between the mineralisation kinetics of trabecular and femoral cortical bone after a scaling in time and a shift in calcium content in Eqs (1)–(2) is remarkable because it holds in the full range of experimentally accurate measurements of calcium densities (Fig. 7). It is important to note that this match does not rely on the choice of ratio of turnover rates. The same match holds for other assumed values of turnover rates, so long as these values are used consistently in the other quantities that depend on them. It can be shown mathematically from Eq. (7) that the reason for this goodness of match is the similarities of the *shapes* of the two BMDDs (Fig. 1 and Table 2). By translating the femoral cortical BMDD towards lower calcium contents, such that both peak locations coincide, the two BMDDs superimpose almost perfectly. The

Figure 5 – Resorption functions used to test Hypothesis 3; (a) exponential resorption functions; and (c) Gaussian resorption functions. The inset in (c) shows a broader view of the Gaussian centred at 15wt% Ca. The auxiliary functions $G_{Fm}(c)$ corresponding to these exponential and Gaussian resorption functions are shown in (b) and (d), respectively. Auxiliary functions $G_{Fm}(c)$ must sit below the shaded area to ensure that resorption functions are positive, i.e., that no bone is formed readily mineralised. Only resorption functions strongly targeting lowly mineralised bone satisfy this constraint.

Figure 6 – Distribution of volume of bone resorbed per unit time in cortical bone, $r_{Fm}(c)\rho_{Fm}(c)$, obtained for certain choices of trabecular auxiliary functions $G_{Tb}(c)$. The measured femoral cortical BMDD (rescaled by χ_{Fm}) is also shown to emphasise that the cortical resorption behaviours obtained in these cases renew a very small volume of lowly mineralised cortical bone at an extremely high rate.

translated femoral cortical BMDD is within the 95% confidence interval of the trabecular measurements. A sensitivity analysis of the link between BMDD shape and mineralisation kinetics is provided in C.

4 Discussion

Turnover rate is well-known to vary across skeletal sites and bone types. In particular, regions of femoral cortical bone of low porosity may be turned over roughly 4 times slower than trabecular bone [21, 44, 45]. This has been proposed to explain the high degree of mineralisation of cortical bone compared to trabecular bone [5]. However, our analysis clearly excludes that the difference in mineral density distribution between femoral cortical bone and trabecular bone captured in the BMDDs is an effect of turnover only (Hypothesis 1, Fig. 3). By testing rigorously general hypotheses on resorption rates, we were able to exclude other possible ways by which one may explain the difference between the two BMDDs. In particular, the concept that different resorption behaviours of osteoclasts may take place in cortical versus trabecular bone, was found to be an insufficient explanation (Hypotheses 2 and 3, Fig. 4–6). The assumption that osteoclasts may resorb preferentially bone with specific calcium content can be understood as (i) a cellular preference to target microcracks, generally situated in old, highly mineralised bone [11, 35]; (ii) geometrical constraints related to the fact that resorption occurs first at existing surfaces in trabecular bone, but that resorption surfaces in cortical bone have first to be created by tunnelling of osteoclasts, which results in bone of different calcium content to be available for resorption [32]; and (iii) mechanical regulation of remodelling, which may recruit osteoclasts at different rates depending on the mechanical properties of the bone site, which are clearly different in femoral cortical bone, and trabecular bone [10]. Our completely general choice of possible resorption functions $r(c)$ takes into consideration all of these influencing factors on osteoclastic behaviour.

The fact that the mineralisation kinetic laws in Figure 7 only match after rescaling in time suggests that mineralisation kinetics is different in trabecular and femoral cortical bone. Eqs (1)–(2) indicate that the time scale of mineralisation is coupled with the time scale of bone turnover independently of bone type (see D). Our conclusion that mineralisation may proceed at a different rate in trabecular and femoral cortical bone focuses on mid/late stages of mineralisation. In a previous study, Marotti et al. studied the mineralisation kinetics by fluorescence labelling over 47 days in the dog humerus, radius, ulna, femur, tibia diaphysis, and radius metaphysis, and found no statistical differences [34]. However, by investigating only the first 47 days, this study focused on the early stage of secondary mineralisation. At this early stage of mineralisation, our computational model predicts a mineralisation kinetics which is very similar for the two bone types (Fig. 7). In a more recent study, Bala et al. investigated the mineralisation kinetics in iliac crest of ewes over 30 months [2], also finding no statistical differences of mineralisation kinetics between trabecular and cortical bone. However, the iliac crest follows an intricate development during growth [24] and its cortical and trabecular compartments may be regulated similarly [38].

The experimental basis of our study is that the peak position of Tb.BMDD and Fm.BMDD is different, but the mineral heterogeneity is similar, as quantified by Ca_{WIDTH} (Table 2). One major intent of the current work is to emphasise that this similar heterogeneity is unexpected from our current understanding of the processes of remodelling and mineralisation. If mineralisation kinetics were identical in trabecular and femoral cortical bone, our model predicts that the lower turnover rate in cortical bone would result in a broadening of the BMDD. This broadening is analogous to the broadening of the age distribution of humans when life expectancy increases: the human population becomes simply redistributed on a larger variety of possible ages. Our experimental observation that peak width in Fm.BMDD and Tb.BMDD is not significantly different seems to be observed in other situations of changed bone turnover analysed in terms of the BMDD:

(i) The effect of different bisphosphonates on bone turnover [18] and the BMDD [52] have been extensively studied over the last twenty years. Depending on their potency bisphosphonates can reduce the rate of bone remodelling substantially [25, 41]. After 10 years of alendronate treatment the mineral heterogeneity was not significantly different from the trabecular reference BMDD [51]. In a separate study, 5 years of risedronate treatment resulted in a Ca_{WIDTH} not significantly different from its baseline value [58].

(ii) Hypoparathyroidism is a condition of known low bone turnover. In vitamin-D treated hypoparathyroid patients the activation frequency in trabecular bone of iliac crest biopsies was reduced by a factor 4.5 in these patients compared to healthy individuals [30]. While the BMDD in the hypoparathyroid patients was significantly shifted towards higher values, the heterogeneity of mineralisation around the peak was not changed compared to the reference trabecular BMDD [40].

(iii) Our study also provides a new perspective on the

Figure 7 – (a) Mineralisation rates $q_{Tb}(c)$, $q_{Fm}(c)$; and (b) Mineralisation kinetic laws $c_{Tb}(t)$, $c_{Fm}(c)$ obtained from the experimental trabecular BMDD and femoral cortical BMDD under Hypothesis 4. The mineralisation rates $q(c)$ and kinetic laws $c(t)$ obtained by rescaling the timescale of femoral cortical mineralisation by the ratio of turnover rate $\frac{\chi_{Tb}}{\chi_{Fm}}$, and by shifting the calcium axis by $\kappa \approx 2.83\,\text{wt\% Ca}$ are also shown. The time-rescaled and calcium-shifted femoral cortical mineralisation functions $q(c)$ and $c(t)$ fit the trabecular mineralisation functions $q_{Tb}(c)$ and $c_{Tb}(t)$ remarkably well both at low calcium densities ($\lesssim 20\,\text{wt\% Ca}$, as seen more obviously in (a)), and at high calcium densities ($\gtrsim 20\,\text{wt\% Ca}$, as seen more obviously in (b)).

definition of the trabecular reference BMDD of healthy adults [50]. The reference BMDD is defined based on the average of 52 individual BMDDs, since it was found that in healthy adults the trabecular BMDD does not depend on age, gender, ethnicity and skeletal site. The reference value for Ca_{WIDTH} was reported to be 3.35 wt% Ca with a standard deviation of ±0.34 wt% Ca (Table 2). Translating this standard deviation in a variability of turnover using Fig. 6 in Ref. [54] shows that the corresponding variability in turnover would range from −40% to +10% of the average value, a remarkably narrow range having in mind the natural variability of turnover across bone sites and individuals, which is expected to be much larger [45]. The fact that the trabecular BMDD is so consistent despite large variability of turnover rate suggests that another mechanism compensates the influence of turnover rate on mineral heterogeneity in trabecular bone.

(iv) The BMDD of cortical bone measured in transiliac bone samples was found to have a much lower Ca_{PEAK} value [38] compared to the Ca_{PEAK} value of cortical bone at the midshaft femur (Fig. 1). Consequently, a reference cortical BMDD (independent of skeletal site) of healthy adults cannot be defined, in contrast with the reference trabecular BMDD. The similarity of Ca_{WIDTH} in Tb.BMDD and Ca_{WIDTH} in Fm.BMDD is inconsistent with what one would expect if differences in mineral density distributions would result from differences in turnover rate alone. If only turnover rate would differ, our model shows that Fm.BMDD would have a broader peak than Tb.BMDD, which is not what is observed.

(iv) Data from the control group of the risedronate study in Ref. [58] shows that three years of treatment with calcium and vitamin D supplementation (with unknown consequences on the turnover rate) only resulted in a statistically significant shift of the BMDD peak by 0.73wt% Ca [8, 58, 22]. This shift in peak location,

presumably due to the extra calcium intake of the patients, was not associated with a change in BMDD peak width compared to baseline values.

A possible interpretation of our observations that the heterogeneity of mineral content around the mean seems rather uniform, is that the processes of remodelling and mineralisation are interlinked (see Eqs (22)–(23)). Indeed, our model shows that if mineralisation rate scales with turnover rate, then the degree of heterogeneity of mineral density around the mean, measured in particular by Ca_{WIDTH}, is independent of turnover rate.

A turnover-limited mineralisation kinetics suggests a limitation imposed by the transport and recycling of minerals. If mineral transport is spatially restricted, minerals that are embedded into bone matrix during bone mineralisation may come mostly from the recycling of minerals freed from the bone matrix during bone resorption [48]. The abundance of these recycled minerals depends on turnover rate.

In the studies (i)-(iv) mentioned above the width of the BMDD peak was virtually unchanged, but the peak position typically shifted significantly. In our study an additional shift along the calcium content axis was needed to match the mineralisation kinetics of trabecular and femoral cortical bone. These shifts in the BMDD peak location suggest the existence of an additional calcium reservoir in bone that may be filled to different levels in trabecular and cortical bone during early stages of mineralisation. Indeed, the shift in calcium density between the mineralisation kinetic laws $c(t)$ of trabecular bone and of femoral cortical bone is generated during the first 1–2 years of mineralisation, see Fig. 7. Recent works have proposed the existence of mineral reservoirs in association with the lacuno-canalicular network of the osteocytes [14, 12]. In the context of a revived discussion about osteocytic osteolysis [57, 7], the osteocytes are thought to play an active role in the mineralisation process by modifying the perilacunar and pericanalicular matrix [28, 26]. In a recent study on human osteons, the local Ca content measured by qBEI was spatially correlated with the density of the lacuno-

canalicular network measured by confocal microscopy. In line with the hypothesis of a mineral reservoir associated with the canalicular network, regions with a dense network were found to have a higher mineral content [47].

Two alternative explanations for the difference between Tb.BMDD and Fm.BMDD should be mentioned. The first relies on the idea that the amount of Ca that can be incorporated into the bone matrix is limited and that this limitation may reduce Ca_{WIDTH} in low turnover scenarios [39, 38]. Our previous computational analysis [9] exploring how a reduced capacity of mineral uptake influences the BMDD in late stages of mineralisation showed indeed that peak broadening is suppressed in low turnover rate scenarios. However, this computational analysis also predicted an increase in the BMDD's skewness which is not observed experimentally [9]. The second possible explanation is based on the lack of reliable data about turnover rates depending on different skeletal sites and, in particular, different bone types (i.e., cortical vs. trabecular) [45]. If femoral cortical bone and trabecular bone are turned over with more similar rates than what is usually assumed, then the similarity in the shape of the BMDDs of these different bones is also less surprising.

A strength of the quantitative hypothesis-testing approach used in this work is to be able to investigate the influence of various biological processes in isolation. The mathematical model we based our analysis on uses very general principles of mass conservation laws in which bone is created, matures, and is resorbed. The manner in which these processes occur was subject only to recovering the experimentally measured BMDDs. Nevertheless, the model makes two fundamental assumptions most important for the interpretation of our results. First, it is assumed that the temporal incorporation of minerals in bone matrix follows the same kinetics for bone formed at different location and different times in the same qBEI image. This assumption allows the definition of a mineralisation rate $q(c)$, which can be different depending on bone type, but is otherwise the same for each newly formed bone packet in this bone type. While osteocytes may interfere with the time course of mineral accumulation during the mineralisation of bone matrix [57, 1, 3, 47], most measurements of mineralisation kinetics so far suggest that mineral accumulation remains a good proxy of tissue age within a same qBEI scan. Second, our analysis of adult BMDDs assumes that these mineral distributions are in steady state, i.e. they would not evolve in time under the given conditions of remodelling. This assumption seems justified considering that the age of the individuals is between 48 and 56 years old. However, this steady-state assumption may have to be revisited when interpreting BMDD data of individuals afflicted recently by certain bone disorders, or data from children due to their growth [24].

In summary, our findings suggest that trabecular and (femoral) cortical bone are more different than usually assumed. The common view is that both bone types are made up of bone lamellae, but that there is a difference in the spatial arrangement of the lamellae, and a difference in the rate at which the bone is turned over. Our conclusion, drawn from quantitative hypothesis testing, that the mineralisation kinetics is different in these bone types suggests that this common view needs to be supplemented by the notion that minerals are incorporated in the two bone types differently. This conclusion is further corroborated by qBEI measurements of very low turnover rate trabecular bone, which exhibits a distinctively lower value of Ca_{PEAK} than that of femoral cortical bone despite having a similar low turnover rate [40, 39]. A possible reason for why trabecular bone and femoral cortical bone may exhibit differences in mineralisation kinetics is that these bone types have different mechanical requirements [15, 23].

Acknowledgments

We thank Paul Roschger for stimulating discussions. PRB and RW acknowledge support by Universities Australia (UA) and German Academic Exchange Service (DAAD) for the Australia–Germany Joint Research Cooperation Award (Project "The cellular control of mineral heterogeneity in bone").

Conflicts of interests: none.

A Mathematical model

Ruffoni et al. developed a phenomenological model of the time evolution of the BMDD $\rho(c, t)$ at the tissue scale [54, 55]. This model includes: (i) bone formation; (ii) bone resorption; and (iii) bone mineralisation. The time evolution of the BMDD is governed by the reaction–advection equation

$$\frac{\partial}{\partial t}\rho(c,t) = -\frac{\partial}{\partial c}\big(q(c)\rho(c,t)\big) - r(c,t)\rho(c,t) \qquad (3)$$

with the boundary condition

$$\rho(0,t) = \frac{\dot{V}_f(t)}{q(0)}, \qquad (4)$$

where $\dot{V}_f$ is the total volume of new bone formed per unit time in the sample. In steady state, the total volume of bone formed per unit time equals the total volume of bone resorbed per unit time, and is related to the turnover rate χ. Since $\rho(c)\mathrm{d}c$ represents the volume of bone with calcium content within $[c, c + \mathrm{d}c]$ and $r(c)\rho(c)\mathrm{d}c$ the volume of bone with calcium content within $[c, c + \mathrm{d}c]$ resorbed per unit time, one has in steady state:

$$\mathrm{BV} = \int_0^{c_{\max}} \rho(c)\mathrm{d}c, \qquad (5)$$

$$\dot{V}_f = \dot{V}_r = \int_0^{c_{\max}} r(c)\rho(c)\mathrm{d}c = \chi\ \mathrm{BV}, \qquad (6)$$

where $c_{\max}$ is an upper bound for the maximum amount of calcium that can be stored in bone. In a previous study we explored the influence of lower values of the maximum calcium capacity of bone $c_{\max}$ on the BMDD with the result that in low turnover scenarios, the BMDD peak becomes strongly asymmetric if $c_{\max}$ is assumed to be smaller than $30\,\mathrm{wt\%}$ Ca [9]. Here we therefore choose $c_{\max} = 35\,\mathrm{wt\%}$ Ca.

From Eq. (3), the BMDD in steady state is [54]:

$$\rho(c) = \mathrm{BV}\,\frac{\chi}{q(c)}\exp\left(-\int_0^c \frac{r(c')}{q(c')}\mathrm{d}c'\right). \qquad (7)$$

Equation (7) is the central equation used to check whether BMDDs measured experimentally are consistent with the resorption rate functions $r(c)$ and the mineralisation rate functions $q(c)$ assumed in Hypotheses 1–4. From Equation (3), we can also obtain the mineralisation rate, $q(c)$, or the resorption function, $r(c)$, as a function of the BMDD:

$$q(c) = \frac{1}{\rho(c)} \int_c^{c_{\max}} r(c')\rho(c')\,dc'$$

$$= \frac{1}{\rho(c)} \left(\chi \, BV - \int_0^c r(c')\rho(c')\,dc' \right) \qquad (8)$$

$$r(c) = -\frac{1}{\rho(c)} \frac{d}{dc}\big(q(c)\rho(c)\big). \qquad (9)$$

Note that the mineralisation kinetic law $c(t)$ and the mineralisation rate $q(c)$ are related by the differential equation

$$\frac{dc(t)}{dt} = q(c(t)). \qquad (10)$$

B Conditions for positive resorption functions in Hypothesis 3

Hypothesis 3 allows both trabecular and cortical resorption functions to depend on calcium content. In this Appendix, we derive necessary and sufficient conditions to ensure that these two resorption functions are positive for all values of calcium content c. Since Hypothesis 3 assumes that mineralisation rate is identical in femoral cortical and trabecular bone, i.e. $q_{Fm}(c) = q_{Tb}(c)$, we can express one resorption function as function of the other. Indeed, substituting $q_{Fm}(c)$ occurring in $r_{Fm}(c)$ (Eq. (9)) with $q_{Tb}(c)$ determined from r_{Tb} and ρ_{Tb} in Eq. (8) gives:

$$r_{Fm}(c) = \frac{-1}{\rho_{Fm}(c)} \frac{d}{dc}\left(\frac{\rho_{Fm}(c)}{\rho_{Tb}(c)} \int_c^{c_{\max}} r_{Tb}(c^*)\rho_{Tb}(c^*)\,dc^* \right). \qquad (11)$$

Conversely:

$$r_{Tb}(c) = \frac{-1}{\rho_{Tb}(c)} \frac{d}{dc}\left(\frac{\rho_{Tb}(c)}{\rho_{Fm}(c)} \int_c^{c_{\max}} r_{Fm}(c^*)\rho_{Fm}(c^*)\,dc^* \right). \qquad (12)$$

Not all choices of positive resorption functions $r_{Tb}(c)$ in Eq. (11) will lead to a positive resorption function $r_{Fm}(c)$. To ensure that $r_{Fm}(c)$ is positive, $r_{Tb}(c)$ must be such that

$$\frac{d}{dc}\left(\frac{\rho_{Fm}(c)}{\rho_{Tb}(c)} \int_c^{c_{\max}} r_{Tb}(c^*)\rho_{Tb}(c^*)\,dc^* \right) \leqslant 0. \qquad (13)$$

To determine the sign of this derivative, let $I_{Tb}(c) = \int_c^{c_{\max}} r_{Tb}(c^*)\rho_{Tb}(c^*)\,dc^*$ and $f(c) = \frac{\rho_{Fm}(c)}{\rho_{Tb}(c)}$. We can rewrite the derivative in Eq. (13) as: $\frac{d}{dc}\big(f(c)I_{Tb}(c)\big)$. Since both $f(c)$ and $I_{Tb}(c)$ are positive, we have:

$$\mathrm{sign}\left[\frac{d}{dc}\big(f(c)I_{Tb}(c)\big) \right] = \mathrm{sign}\left[\frac{\frac{d}{dc}\big(f(c)I_{Tb}(c)\big)}{f(c)I_{Tb}(c)} \right]$$

$$= \mathrm{sign}\left[\frac{I'_{Tb}(c)}{I_{Tb}(c)} + \frac{f'(c)}{f(c)} \right].$$

Introducing the auxiliary function:

$$G_{Tb}(c) = \frac{I'_{Tb}(c)}{I_{Tb}(c)} = \frac{-r_{Tb}(c)\rho_{Tb}(c)}{\int_c^{c_{\max}} r_{Tb}(c^*)\rho(c^*)\,dc^*}, \qquad (14)$$

it is clear that the resorption function $r_{Fm}(c)$ is positive if and only if

$$G_{Tb}(c) \leqslant -\frac{f'(c)}{f(c)}. \qquad (15)$$

Equation (14) expresses $G_{Tb}(c)$ as a function of $r_{Tb}(c)$. This relationship can be inverted, so that choosing a resorption function $r_{Tb}(c)$ is entirely equivalent to choosing an auxiliary function $G_{Tb}(c)$. Indeed, integrating Eq. (14) over $[0,c]$ gives $I_{Tb}(c) = \chi_{Tb} \, BV_{Tb} \exp\big(\int_0^c G_{Tb}(c^*)\,dc^*\big)$. Plugging this expression back into Eq. (14) now expresses $r_{Tb}(c)$ as a function of $G_{Tb}(c)$:

$$r_{Tb}(c) = -\chi_{Tb} \, BV_{Tb} \frac{G_{Tb}(c)}{\rho_{Tb}(c)} \exp\left(\int_0^c G_{Tb}(c^*)\,dc^* \right). \qquad (16)$$

The advantage of introducing the auxiliary function $G_{Tb}(c)$ is that Condition (15) represents a direct restriction on choices of $G_{Tb}(c)$. By definition, $I_{Tb}(c) > 0$, and $I'_{Tb}(c) = -r_{Tb}(c)\rho_{Tb}(c) < 0$, so that $G_{Tb}(c)$ must also be negative. However, the right hand side of Ineq. (15) is not always negative, so that the restriction on the auxiliary function can be rewritten $G_{Tb}(c) \leqslant \min\{0, -f'/f\}$. Similar constraints on allowable resorption functions $r_{Fm}(c)$ can be developed to ensure that $r_{Tb}(c) > 0$. Taken together, these conditions give:

$$\begin{cases} r_{Fm}(c) \geqslant 0 \\ r_{Tb}(c) \geqslant 0 \end{cases} \iff \begin{cases} G_{Tb}(c) \leqslant \min\left[0; \frac{\rho_{Fm}}{\rho_{Tb}} \frac{d}{dc}\left(\frac{\rho_{Tb}}{\rho_{Fm}}\right)\right] \\ G_{Fm}(c) \leqslant \min\left[0; \frac{\rho_{Tb}}{\rho_{Fm}} \frac{d}{dc}\left(\frac{\rho_{Fm}}{\rho_{Tb}}\right)\right] \end{cases} \qquad (17)$$

Note that the right-hand sides of these inequalities are only functions of the experimental BMDDs and as such are fully known.

In Figure 5, we build resorption functions r_{Fm} and check that the auxiliary function G_{Fm} fulfills Eq. (17). In Figure 6, we build an auxiliary function G_{Tb} that fulfils Eq. (17), and we determine the corresponding resorption function by Eq. (16). The cortical resorption function $r_{Fm}(c)$ is then found using Eq. (11).

The further away the auxiliary function $G_{Tb}(c)$ is from the upper bound, the further away the minimum resorption rate $r_{Fm}(c)$ is from zero (Ineq. (17)). But also the closer to zero is the corresponding resorption rate $r_{Tb}(c)$ (Eq. (16)). It is clear from this trade-off that the set of physiologically realistic functions $G_{Tb}(c)$ is also bounded from below.

The strict restrictions that exist on the possible choices of the auxiliary functions $G_{Tb}(c)$ imply that the probability to renew interstitial cortical bone would always be very low under Hypothesis 3. This is exemplified in Figure 8a,b, where a region of the qBEI image of one of the femoral cortical samples has been coloured by its corresponding hypothetical tissue age. In this figure, tissue age was calculated from the mineralisation kinetics $c(t)$ corresponding to the choice of the upper limit of the auxiliary function $G_{Tb}(c)$. Other choices lead to similar tissue age distributions. In all cases, interstitial bone would have to be interpreted as being over 100 years old.

Figure 8 – (a) qBEI image, and (b) hypothetical age map resulting from Hypothesis 3, with the cortical resorption function obtained by assuming the auxiliary function $G_{\mathrm{Tb}}(c)$ to be the upper bound Condition.

B.1 Resorption of unmineralised bone

As stated in the Results section, the volume of bone resorbed per unit time comes mainly from the unmineralised bone packets. Here, we give the mathematical steps to reach this statement.

Let $R(c^*)$ be the volume of femoral cortical bone with calcium content less than c^* resorbed per unit time:

$$R(c^*) = \int_0^{c^*} r_{\mathrm{Fm}}(c)\rho_{\mathrm{Fm}}(c)\mathrm{d}c. \tag{18}$$

It is clear from Eq. (18) that $R(c_{\max}) = \dot{V}_r = \chi_{\mathrm{Fm}}\mathrm{BV}_{\mathrm{Fm}}$. The aim here is to show that under Hypothesis 3, any choice of r_{Fm} leads to $B(c^*)$ being unreasonably close to $B(c_{\max})$ already at very small values of c^*. Let α be the fraction of the total volume of bone resorbed per unit time that has a calcium content below c^*:

$$\alpha(c^*) = \frac{R(c^*)}{R(c_{\max})} = \frac{R(c^*)}{\dot{V}_r}. \tag{19}$$

In the following, we provide a lower bound for $\alpha(c^*)$ which we will use to show that under Hypothesis 3 and given the experimental measurements of trabecular and cortical BMDDs, $\alpha(21\,\mathrm{wt\%\,Ca}) \geqslant 25\%$ and $\alpha(20\,\mathrm{wt\%\,Ca}) \geqslant 15\%$. Hypothesis 3 would thus mean that (i) at least 25% of the femoral cortical bone resorbed per unit time would corresponds to bone of calcium content below $21\,\mathrm{wt\%\,Ca}$, which represent the 5% lowest mineralised bone in the femoral cortex; (ii) at least 15% of the femoral cortical bone resorbed per unit time would be resorbed before this bone starts secondary mineralisation, estimated to start at around $20\,\mathrm{wt\%\,Ca}$. These two highly unlikely predictions go against the idea of bone self-repair.

To bound $\alpha(c^*)$ from below, we first note that $r_{\mathrm{Fm}}(c)\rho_{\mathrm{Fm}}(c) = -I'_{\mathrm{Fm}}(c)$ and from Eq. (17),

$$\frac{I'_{\mathrm{Fm}}(c)}{I_{\mathrm{Fm}}(c)} \leqslant \min\left[0; \frac{f'(c)}{f(c)}\right] \leqslant \frac{f'(c)}{f(c)}.$$

Thus $I'_{\mathrm{Fm}}(c) \leqslant I_{\mathrm{Fm}}(c)\frac{f'(c)}{f(c)}$, so that

$$r_{\mathrm{Fm}}(c)\rho_{\mathrm{Fm}}(c) \geqslant -I_{\mathrm{Fm}}(c)\frac{f'(c)}{f(c)}.$$

By integrating both sides of the inequality up to c^*, and using the definition of $R(c^*)$ in Eq. (18), we have:

$$R(c^*) \geqslant A(c^*), \text{where } A(c^*) = -\int_0^{c^*} I_{\mathrm{Fm}}(c)\frac{f'(c)}{f(c)}\mathrm{d}c.$$

To bound $R(c^*)$ further, we first integrate $A(c^*)$ by parts:

$$
\begin{aligned}
A(c^*) &= \left[-I_{\mathrm{Fm}}(c)\ln\left(\frac{\rho_{\mathrm{Fm}}(c)}{\rho_{\mathrm{Tb}}(c)}\right)\right]_0^{c^*} \\
&\quad + \int_0^{c^*} I'_{\mathrm{Fm}}(c)\ln\left(\frac{\rho_{\mathrm{Fm}}(c)}{\rho_{\mathrm{Tb}}(c)}\right)\mathrm{d}c \\
&= \dot{V}_r \ln\left(\frac{\rho_{\mathrm{Fm}}(0)}{\rho_{\mathrm{Tb}}(0)}\right) - I_{\mathrm{Fm}}(c^*)\ln\left(\frac{\rho_{\mathrm{Fm}}(c^*)}{\rho_{\mathrm{Tb}}(c^*)}\right) \\
&\quad - \int_0^{c^*} r_{\mathrm{Fm}}(c)\rho_{\mathrm{Fm}}(c)\ln\left(\frac{\rho_{\mathrm{Fm}}(c)}{\rho_{\mathrm{Tb}}(c)}\right)\mathrm{d}c.
\end{aligned}
$$

Because the femoral cortical BMDD's peak is shifted along the calcium axis compared to the trabecular BMDD's peak, $\rho_{\mathrm{Tb}}(c) > \rho_{\mathrm{Fm}}(c)$ up until $c \simeq 24\,\mathrm{wt\%\,Ca}$. Accordingly, the function $\ln\left(\frac{\rho_{\mathrm{Fm}}(c)}{\rho_{\mathrm{Tb}}(c)}\right)$ is negative for all $c \leqslant 24\,\mathrm{wt\%\,Ca}$ (see Figure 9). Hence, for $c^* < 24\,\mathrm{wt\%\,Ca}$,

$$-\int_0^{c^*} r_{\mathrm{Fm}}(c)\rho_{\mathrm{Fm}}(c)\ln\left(\frac{\rho_{\mathrm{Fm}}(c)}{\rho_{\mathrm{Tb}}(c)}\right)\mathrm{d}c \geqslant 0.$$

This leads to:

$$R(c^*) \geqslant A(c^*) \geqslant \dot{V}_r \ln\left(\frac{\chi_{\mathrm{Fm}}}{\chi_{\mathrm{Tb}}}\right) - I_{\mathrm{Fm}}(c^*)\ln\left(\frac{\rho_{\mathrm{Fm}}(c^*)}{\rho_{\mathrm{Tb}}(c^*)}\right).$$

With Eq. (19), this inequality becomes:

$$\alpha\dot{V}_r \geqslant \dot{V}_r\left(\ln\left(\frac{\rho_{\mathrm{Fm}}(c_f)}{\rho_{\mathrm{Tb}}(c_f)}\right) - (1-\alpha)\ln\left(\frac{\rho_{\mathrm{Fm}}(c^*)}{\rho_{\mathrm{Tb}}(c^*)}\right)\right) \tag{20}$$

Figure 9 – Plot of the function $\ln\left(\frac{\rho_{\mathrm{Fm}}(c)}{\rho_{\mathrm{Tb}}(c)}\right)$, which shows that this function is negative for all $c \leqslant 24\,\mathrm{wt\%\,Ca}$.

Figure 10 – Under Hypothesis 3, the fraction $\alpha(c^*)$ of total volume of bone resorbed per unit time that has a calcium content less than c^* must be greater than the lower bound in Eq. (21) plotted in this figure. This shows that $\alpha(21\,\mathrm{wt\%\,Ca}) \geqslant 25\%$ and $\alpha(20\,\mathrm{wt\%\,Ca}) \geqslant 20\%$.

where we used the fact that from the definitions of I_{Fm} and α, $I_{\mathrm{Fm}}(c^*) = (1 - \alpha(c^*))\,\dot{V}_r$. The inequality (20) can be reorganised into

$$\alpha \geqslant 1 - \frac{1 - \ln\left(\frac{\chi_{\mathrm{Fm}}}{\chi_{\mathrm{Tb}}}\right)}{1 - \ln\left(\frac{\rho_{\mathrm{Fm}}(c^*)}{\rho_{\mathrm{Tb}}(c^*)}\right)}, \quad c^* \leqslant 24\ \mathrm{wt\%\,Ca} \qquad (21)$$

All the quantities in the right hand side of Ineq. (21) are known. Evaluating them at $c^* = 21\,\mathrm{wt\%\,Ca}$ and $c^* = 20\,\mathrm{wt\%\,Ca}$ shows that $\alpha(21\,\mathrm{wt\%\,Ca}) \geqslant 25\%$ and $\alpha(20\,\mathrm{wt\%\,Ca}) \geqslant 15\%$ (Figure 10). In other words, under Hypothesis 3, at least 25% of the total amount of femoral cortical bone resorbed per unit time would have a calcium content less than $c^* = 21\,\mathrm{wt\%\,Ca}$, and at least 15% would have a calcium content less than $c^* = 20\,\mathrm{wt\%\,Ca}$.

C Goodness of fit of the mineralisation kinetics

To understand the sensitivity of mineralisation kinetic laws to measured BMDDs, we quantify in this appendix how similar two BMDDs have to be in order for their mineralisation kinetics $c(t)$ to be within the same error as that between the trabecular and the transformed cortical mineralisation kinetics. To weigh the discrepancy between mineralisation kinetic laws by the frequency of occurrence of calcium density, we define the following measure of discrepancy of a mineralisation kinetic law $c(t)$ compared to that of trabecular bone: $E[c(\cdot)] \stackrel{\mathrm{def}}{=} \int_{15\,\mathrm{wt\%}}^{30\,\mathrm{wt\%}} (t_{\mathrm{Tb}}(c) - t(c))^2 \rho_{\mathrm{Tb}}(c)\,\mathrm{d}c$, where $t_{\mathrm{Tb}}(c)$ and $t(c)$ are the inverse functions of $c_{\mathrm{Tb}}(t)$ and $c(t)$, respectively. The discrepancy between the scaled cortical mineralisation kinetics and the reference trabecular mineralisation kinetics gives a value $E_{\mathrm{Fm}} = E[c_{\mathrm{Fm}}(\cdot)] = 0.017\,\mathrm{year}^2$. We then vary systematically the reference trabecular BMDD width ($\mathrm{Ca}_{\mathrm{WIDTH}}$), skewness ($\mathrm{Ca}_{\mathrm{SKEW}}$), and kurtosis ($\mathrm{Ca}_{\mathrm{KURT}}$) by applying a parametric transformation following the approach by Jones and Pewsey [27]. For each of these modified trabecular BMDDs, we calculate the corresponding mineralisation kinetics and estimate the error E with respect to the reference trabecular mineralisation kinetics. We find that to maintain these errors E below E_{Fm}, $\mathrm{Ca}_{\mathrm{WIDTH}}$ has to deviate less than 5% from the trabecular value, while skewness and kurtosis may deviate by up to 35%. This shows that the spread of mineral heterogeneity around the mean captured by $\mathrm{Ca}_{\mathrm{WIDTH}}$ is an important signature of mineralisation kinetics, whereas skewness and kurtosis are less closely related to it.

D Universal coupling laws between mineralisation kinetics and turnover rate

The very good match between the mineralisation kinetics of trabecular bone and the mineralisation kinetics of femoral cortical bone after a scaling in time and a shift in calcium content in Eqs (1)–(2) suggests that we may define a universal, bone-type-independent mineralisation rate $\hat{q}(c)$ by

$$\hat{q}(c) \stackrel{\mathrm{def}}{=} \frac{q_{\mathrm{Tb}}(c)}{\chi_{\mathrm{Tb}}} \approx \frac{q_{\mathrm{Fm}}(c + \kappa_{\mathrm{Fm}})}{\chi_{\mathrm{Fm}}} \qquad (22)$$

and a universal, bone-type-independent mineralisation kinetic law $\hat{c}(t)$ by

$$\hat{c}(\hat{t}) \stackrel{\mathrm{def}}{=} c_{\mathrm{Tb}}\left(\frac{\hat{t}}{\chi_{\mathrm{Tb}}}\right) \approx c_{\mathrm{Fm}}\left(\frac{\hat{t}}{\chi_{\mathrm{Fm}}}\right) - \kappa_{\mathrm{Fm}} \qquad (23)$$

where $\hat{t}$ is a dimensionless time variable corresponding to turnover time. The approximations in Eqs (22)–(23) are a direct consequence of the matches observed in Fig. 7, summarised mathematically in Eqs (1)–(2). The functions $\hat{q}(c)$ and $\hat{c}(t)$ that these matches define in Eqs (22)–(23) are free of bone-type specific time scales, and in that sense, universal. The mineralisation rates and mineralisation kinetic laws in trabecular bone and in femoral cortical bone are retrieved by a simple rescaling in time and shift in mineral density of these scale-free mineralisation laws:

$$q_{\mathrm{Tb}}(c) = \chi_{\mathrm{Tb}}\,\hat{q}(c), \qquad c_{\mathrm{Tb}}(t) = \hat{c}\left(\chi_{\mathrm{Tb}}\,t\right) \qquad (24)$$

$$q_{\mathrm{Fm}}(c) = \chi_{\mathrm{Fm}}\,\hat{q}(c - \kappa_{\mathrm{Fm}}), \quad c_{\mathrm{Fm}}(t) = \hat{c}\left(\chi_{\mathrm{Fm}}\,t\right) + \kappa_{\mathrm{Fm}} \qquad (25)$$

In other words, the time scale of mineralisation in each of these bone types is determined by the time scale of bone

turnover only. Equations (24)–(25) summarise the concept that mineralisation is coupled to turnover rate. Equations (22)–(23) are proposed as an explicit experimental test for the validity of this hypothesis. Hypothesis 4 would be further corroborated if measurements of BMDDs in other skeletal sites would fulfil Eqs (22)–(23) for suitable (site-dependent) calcium shifts.

It is important to note here that the scaling laws we observed in Eqs (22)–(23) are completely independent of the values of turnover rate χ_{Tb} and χ_{Fm} that we have assumed. The division by turnover rate in Eq. (22) cancels the turnover rate dependence of mineralisation rate in Eq. (8). The values assumed in this paper for the trabecular and femoral cortical turnover rate were used in Fig. (7) only to transform the time variable from the dimensionless 'turnover time' into absolute units of time (years).

References

[1] Atkins, G. J .and Findlay, D. M., 2012. Osteocyte regulation of bone mineral: a little give and take. Osteoporosis international 23 (8), 2067–79.

[2] Bala, Y., Farlay, D., Delmas, P. D., Meunier, P. J., Boivin, G., Apr. 2010. Time sequence of secondary mineralization and microhardness in cortical and cancellous bone from ewes. Bone 46 (4), 1204–12.

[3] Belanger, L. F., Belanger, C., Semba, T., 1967. Technical approaches leading to the concept of Osteocytic Osteolysis. Clinical orthopaedics and related research 54 (Sept-Oct), 187–196.

[4] Bentolila, V., Boyce, T. M., Fyhrie, D. P., Drumb, R., Skerry, T. M., Schaffler, M. B., 1998. Intracortical remodeling in adult rat long bones after fatigue loading. Bone 23 (3), 275–281.

[5] Boivin, G., Meunier, P. J., 2002. Changes in Bone Remodeling Rate Influence the Degree of Mineralization of Bone. Connective Tissue Research 43, 535–537.

[6] Boivin, G., Meunier, P. J., 2002. The degree of mineralization of bone tissue measured by computerized quantitative contact microradiography. Calcified Tissue International 70 (6), 503–511.

[7] Bonewald, L. F., Feb. 2011. The amazing osteocyte. Journal of Bone and Mineral Research 26 (2), 229–38.

[8] Borah, B., Dufresne, T. E., Chmielewski, P. A., Johnson, T. D., Chines, A., Manhart, M. D., 2004. Risedronate preserves bone architecture in postmenopausal women with osteoporosis as measured by three-dimensional microcomputed tomography. Bone 34 (4), 736–746.

[9] Buenzli, P., Lerebours, C., Roschger, A., Roschger, P., Weinkamer, R., 2017. Late stages of mineralisation and their signature on the bone mineral density distribution. Connective Tissue Research - under review -.

[10] Burger, E. H., Klein-Nulend, J., Smit, T. H., 2003. Strain-derived canalicular fluid flow regulates osteoclast activity in a remodelling osteon - A proposal. Journal of Biomechanics 36, 1453–1459.

[11] Burr, D. B., 2002. Targeted and Nontargeted Remodeling. Bone 30 (1), 2–4.

[12] Busse, B., Djonic, D., Milovanovic, P., Hahn, M., Puschel, K., Ritchie, R. O., Djuric, M., Amling, M., 2010. Decrease in the osteocyte lacunar density accompanied by hypermineralized lacunar occlusion reveals failure and delay of remodeling in aged human bone. Aging Cell 9 (6), 1065–1075.

[13] Busse, B., Hahn, M., Soltau, M., Zustin, J., Püschel, K., Duda, G. N., Amling, M., 2009. Increased calcium content and inhomogeneity of mineralization render bone toughness in

osteoporosis: Mineralization, morphology and biomechanics of human single trabeculae. Bone 45 (6), 1034–1043.
URL http://dx.doi.org/10.1016/j.bone.2009.08.002

[14] Canè, V., Marotti, G., Volpi, G., Zaffe, D., Palazzini, S., Remaggi, F., Muglia, M. A., 1982. Size and density of osteocyte lacunae in different regions of long bones. Calcified Tissue International 34 (1), 558–563.

[15] Currey, J. C., 2006. Bones: Structure and mechanics. Princeton University Press.

[16] Currey, J. D., 1999. What determines the bending strength of compact bone? The Journal of experimental biology 202 (Pt 18), 2495–2503.
URL http://www.scopus.com/inward/record.url?eid=2-s2.0-0033198818{&}partnerID=tZOtx3y1

[17] Dierolf, M., Menzel, A., Thibault, P., Schneider, P., Kewish, C. M., Wepf, R., Bunk, O., Pfeiffer, F., 2010. Ptychographic X-ray computed tomography at the nanoscale. Nature 467 (7314), 436–439.

[18] Ebetino, F. H., Hogan, A. M. L., Sun, S., Tsoumpra, M. K., Duan, X., Triffitt, J. T., Kwaasi, A. A., Dunford, J. E., Barnett, B. L., Oppermann, U., Lundy, M. W., Boyde, A., Kashemirov, B. A., McKenna, C. E., Russell, R. G. G., 2011. The relationship between the chemistry and biological activity of the bisphosphonates. Bone 49 (1), 20–33.

[19] Eriksen, E. F., 1986. Normal and Pathological Remodeling of Human Trabecular Bone : Three Dimensional Reconstruction of the Remodeling Sequence in Normals and in Metabolic. Endocrine Reviews 7 (4), 379–408.

[20] Eriksen, E. F., 2010. Cellular mechanisms of bone remodeling. Reviews in Endocrine and Metabolic Disorders 11 (4), 219–227.

[21] Eriksen, E. F., Melsen, F., Sod, E., Barton, I., Chines, A., 2002. Effects of long-term risedronate on bone quality and bone turnover in women with postmenopausal osteoporosis. Bone 31 (5), 620–625.

[22] Fratzl, P., Roschger, P., Fratzl-Zelman, N., Paschalis, E. P., Phipps, R., Klaushofer, K., 2007. Evidence that treatment with risedronate in women with postmenopausal osteoporosis affects bone mineralization and bone volume. Calcified Tissue International 81 (2), 73–80.

[23] Fratzl-Zelman, N., Roschger, P., Gourrier, A., Weber, M., Misof, B. M., Loveridge, N., Reeve, J., Klaushofer, K., Fratzl, P., 2009. Calcified Tissue International 85, 335–343.

[24] Fratzl-Zelman, N., Roschger, P., Misof, B. M., Pfeffer, S., Glorieux, F. H., Klaushofer, K., Rauch, F., 2009. Normative data on mineralization density distribution in iliac bone biopsies of children, adolescents and young adults. Bone 44 (6), 1043–1048.
URL http://dx.doi.org/10.1016/j.bone.2009.02.021

[25] Fuchs, R. K., Faillace, M. E., Allen, M. R., Phipps, R. J., Miller, L. M., Burr, D. B., 2011. Bisphosphonates do not alter the rate of secondary mineralization. Bone 49 (4), 701–705.

[26] Hesse, B., Varga, P., Langer, M., Pacureanu, A., Schrof, S., Mannicke, N., Suhonen, H., Maurer, P., Cloetens, P., Peyrin, F., Raum, K., 2015. Canalicular network morphology is the major determinant of the spatial distribution of mass density in human bone tissue: Evidence by means of synchrotron radiation phase-contrast nano-CT. Journal of Bone and Mineral Research 30 (2), 346–356.

[27] Jones, M. C., Pewsey, A., 2009. Sinh-arcsinh distributions. Biometrika 96 (4), 761–780.

[28] Kerschnitzki, M., Kollmannsberger, P., Burghammer, M., Duda, G. N., Weinkamer, R., Wagermaier, W., Fratzl, P., 2013. Architecture of the osteocyte network correlates with bone material quality. Journal of Bone and Mineral Research 28 (8),

1837–1845.

[29] Kingsmill, V. J., Gray, C. M., Moles, D. R., Boyde, A., 2007. Cortical vascular canals in human mandible and other bones. Journal of Dental Research 86 (4), 368–372.

[30] Langdahl, B. L., Mortensen, L., Vesterby, A., Eriksen, E. F., Charles, P., 1996. Bone histomorphometry in hypoparathyroid patients treated with vitamin D. Bone 18 (2), 103–108.

[31] Lukas, C., Kollmannsberger, P., Ruffoni, D., Roschger, P., Fratzl, P., Weinkamer, R., 2011. The heterogeneous mineral content of bone—using stochastic arguments and simulations to overcome experimental limitations. Journal of Statistical Physics 144 (2), 316–331.

[32] Lukas, C., Ruffoni, D., Lambers, F. M., Schulte, F. A., Kuhn, G., Kollmannsberger, P., Weinkamer, R., Müller, R., 2013. Mineralization kinetics in murine trabecular bone quantified by time-lapsed in vivo micro-computed tomography. Bone 56 (1), 55–60.
URL http://dx.doi.org/10.1016/j.bone.2013.05.005

[33] Manolagas, S., 2000. Birth and death of bone cells: basic regulatory mechanisms and implications for the pathogenesis and treatment of osteoporosis. Endocr. Rev. 21 (July), 115–137.

[34] Marotti, G., Favia, A., Zamlone, A. Z., 1972. Quantitative Analysis on the Rate of Secondary Bone Mineralization. Calcified tissue research 10, 67–81.

[35] Martin, R., Jan. 2002. Is all cortical bone remodeling initiated by microdamage? Bone 30 (1), 8–13.

[36] Martin, R. B., Burr, D. B., Sharkey, N. A., 1998. Skeletal Tissue Mechanics. Springer.

[37] MATLAB, 2017. MATLAB version 9.2 (R2017a). The Mathworks, Inc., Natick, Massachusetts.

[38] Misof, B. M., Dempster, D. W., Zhou, H., Roschger, P., Fratzl-Zelman, N., Fratzl, P., Silverberg, S. J., Shane, E., Cohen, A., Stein, E., Nickolas, T. L., Recker, R. R., Lappe, J., Bilezikian, J. P., Klaushofer, K., 2014. Relationship of Bone Mineralization Density Distribution (BMDD) in Cortical and Cancellous Bone Within the Iliac Crest of Healthy Premenopausal Women. Calcified Tissue International, 332–339.

[39] Misof, B. M., Gamsjaeger, S., Cohen, A., Hofstetter, B., Roschger, P., Stein, E., Nickolas, T. L., Rogers, H. F., Dempster, D., Zhou, H., Recker, R., Lappe, J., McMahon, D., Paschalis, E. P., Fratzl, P., Shane, E., Klaushofer, K., 2012. Bone material properties in premenopausal women with idiopathic osteoporosis. Journal of Bone and Mineral Research 27 (12), 2551–2561.

[40] Misof, B. M., Roschger, P., Dempster, D. W., Zhou, H., Bilezikian, J. P., Klaushofer, K., Rubin, M. R., 2016. PTH(1-84) Administration in Hypoparathyroidism Transiently Reduces Bone Matrix Mineralization. Journal of Bone and Mineral Research 31 (1), 180–189.

[41] Misof, B. M., Roschger, P., Gabriel, D., Paschalis, E. P., Eriksen, E. F., Recker, R. R., Gasser, J. A., Klaushofer, K., 2013. Annual intravenous zoledronic acid for three years increased cancellous bone matrix mineralization beyond normal values in the HORIZON biopsy cohort. Journal of Bone and Mineral Research 28 (3), 442–448.

[42] Nawrot-Wawrzyniak, K., Varga, F., Nader, A., Roschger, P., Sieghart, S., Zwettler, E., Roetzer, K. M., Lang, S., Weinkamer, R., Klaushofer, K., Fratzl-Zelman, N., 2009. Effects of tumor-induced osteomalacia on the bone mineralization process. Calcified Tissue International 84 (4), 313–323.

[43] Nuzzo, S., Lafage-Proust, M. H., Martin-Badosa, E., Boivin, G., Thomas, T., Alexandre, C., Peyrin, F., 2002. Synchrotron Radiation Microtomography Allows the Analysis of Three-Dimensional Microarchitecture and Degree of Mineralization of Human Iliac Crest Biopsy Specimens: Effects of Etidronate Treatment. Journal of Bone and Mineral Research 17 (8), 1372–1382.
URL http://doi.wiley.com/10.1359/jbmr.2002.17.8.1372

[44] Parfitt, A., 1983. The Physiologic and Clinical significance of Bone Histomorphometric Data. In: Recker, R. (Ed.), Bone histomorphometry: Techniques and Interpretation. CRC Press, Boca Raton, Ch. 9, pp. 143–224.

[45] Parfitt, A. M., 2002. Misconceptions (2): Turnover is always higher in cancellous than in cortical bone. Bone 30 (6), 807–809.

[46] Rohrbach, D., Lakshmanan, S., Peyrin, F., Langer, M., Gerisch, A., Grimal, Q., Laugier, P., Raum, K., Aug. 2012. Spatial distribution of tissue level properties in a human femoral cortical bone. Journal of Biomechanics 45 (13), 2264–70.

[47] Roschger, A., Roschger, P., Wagermaier, W., Chen, J., van Tol, A. F., Repp, F., Blouin, S., Berzlanovich, A., Gruber, G. M., Klaushofer, K., Fratzl, P., Weinkamer, R., 2019. The contribution of the pericanalicular matrix to mineral content in human osteonal bone. Bone 123, 76–85.

[48] Roschger, A., Wagermaier, W., Gamsjaeger, S., Hassler, N., Schmidt, I., Blouin, S., Berzlanovich, A., Gruber, G. M., Weinkamer, R., Roschger, P., Paschalis, E. P., Klaushofer, K., Fratzl, P., 2020. Newly formed and remodeled human bone exhibits differences in the mineralization process. Acta Biomaterialia 104, 221 – 230.
URL http://www.sciencedirect.com/science/article/pii/S1742706120300052

[49] Roschger, P., Fratzl, P., Eschberger, J., Klaushofer, K., 1998. Validation of quantitative backscattered electron imaging for the measurement of mineral density distribution in human bone biopsies. Bone 23 (4), 319–326.

[50] Roschger, P., Gupta, H. S., Berzlanovich, A., Ittner, G., Dempster, D. W., Fratzl, P., Cosman, F., Parisien, M., Lindsay, R., Nieves, J. W., Klaushofer, K., 2003. Constant mineralization density distribution in cancellous human bone. Bone 32 (3), 316–323.

[51] Roschger, P., Lombardi, A., Misof, B. M., Maier, G., Fratzl-Zelman, N., Fratzl, P., Klaushofer, K., 2010. Mineralization density distribution of postmenopausal osteoporotic bone is restored to normal after long-term alendronate treatment: qBEI and sSAXS data from the fracture intervention trial long-term extension (FLEX). Journal of Bone and Mineral Research 25 (1), 48–55.

[52] Roschger, P., Misof, B., Paschalis, E., Fratzl, P., Klaushofer, K., 2014. Changes in the degree of mineralization with osteoporosis and its treatment. Current Osteoporosis Reports 12 (3), 338–350.

[53] Roschger, P., Paschalis, E. P., Fratzl, P., Klaushofer, K., 2008. Bone mineralization density distribution in health and disease. Bone 42 (3), 456–466.

[54] Ruffoni, D., Fratzl, P., Roschger, P., Klaushofer, K., Weinkamer, R., 2007. The bone mineralization density distribution as a fingerprint of the mineralization process. Bone 40 (5), 1308–1319.

[55] Ruffoni, D., Fratzl, P., Roschger, P., Phipps, R., Klaushofer, K., Weinkamer, R., 2008. Effect of temporal changes in bone turnover on the bone mineralization density distribution: a computer simulation study. Journal of Bone and Mineral Research 23 (12), 1905–1914.

[56] Sansalone, V., Naili, S., Bousson, V., Bergot, C., Peyrin, F., Zarka, J., Laredo, J. D., Haïat, G., Jul. 2010. Determination of the heterogeneous anisotropic elastic properties of human femoral bone: from nanoscopic to organ scale. Journal of Biomechanics 43 (10), 1857–63.

[57] Teti, A., Zallone, A., 2009. Do osteocytes contribute to bone

mineral homeostasis? Osteocytic osteolysis revisited. Bone 44 (1), 11–16.
URL http://dx.doi.org/10.1016/j.bone.2008.09.017

[58] Zoehrer, R., Roschger, P., Paschalis, E. P., Hofstaetter, J. G., Durchschlag, E., Fratzl, P., Phipps, R., Klaushofer, K., 2006. Effects of 3- and 5-year treatment with risedronate on bone mineralization density distribution in triple biopsies of the iliac crest in postmenopausal women. Journal of Bone and Mineral Research 21 (7), 1106–12.
URL http://www.ncbi.nlm.nih.gov/pubmed/16813531