An Organoid for Woven Bone

Anat Akiva^[1,3,4,5]*, Johanna Melke^[2,3], Sana Ansari[2,3,5], Nalan Liv[6], Robin van der Meijden[5,7], Merijn van Erp,[1,4] Feihu Zhao[2,3,8], Merula Stout[5], Wouter H. Nijhuis[9], Cilia de Heus[6], Claudia Muñiz Ortera[5], Job Fermie[6], Judith Klumperman[6], Keita ito[2,3], Nico Sommerdijk[3,4,5,7]*, Sandra Hofmann[2,3]*

Affiliations:

1. Department of Cell Biology, Radboud Institute of Molecular Life Sciences, Radboud University Medical Center, Geert Grooteplein 6525 GA Nijmegen, The Netherlands

2. Orthopaedic Biomechanics, Department of Biomedical Engineering, Eindhoven University of Technology, PO Box 513, 5600 MB, Eindhoven, the Netherlands

3. Institute for Complex Molecular Systems (ICMS), Eindhoven University of Technology, PO Box 513, 5600 MB, Eindhoven, the Netherlands

4. Electron Microscopy Center, Radboud Institute of Molecular Life Sciences, Radboud University Medical Center, Geert Grooteplein 6525 GA Nijmegen, The Netherlands

5. Department of Chemical Engineering and Chemistry, Laboratory of Materials and Interface Chemistry PO Box 513, 5600 MB, Eindhoven, the Netherlands

6. Section Cell Biology, Center for Molecular Medicine, University Medical Center Utrecht, Utrecht, The Netherlands

7. Department of Biochemistry, Radboud Institute of Molecular Life Sciences, Radboud University Medical Center, Geert Grooteplein 6525 GA Nijmegen, The Netherlands

8. Zienkiewicz Centre for Computational Engineering, College of Engineering, Swansea

University, Swansea, SA1 8EN, United Kingdom.

9. Department of Orthopaedic Surgery, University Medical Centre Utrecht, Wilhelmina

Children's Hospital, The Netherlands.

^equal contribution

Corresponding authors: anat.akiva@radboudumc.nl ; nico.sommerdijk@radboudumc.nl;

s.hofmann@tue.nl

Stem cell-based organoids are promising as functional, self-organizing 3D *in vitro* models for

studying the physiology and pathology of various tissues[1]. Bone formation (osteogenesis) is a

complex process in which i) cellular differentiation and ii) the generation of a mineralized organic

matrix are synchronized to produce a hybrid hierarchical architecture. To study the molecular

mechanisms of osteogenesis in health and disease there is great need for organoids that capture

both processes in parallel[2], however, for human bone no such functional model system is yet

available[3].

Here, we report the *in vitro* differentiation of human bone marrow stromal cells into a functional

3D self-organizing co-culture of osteoblasts and osteocytes, creating an organoid for early stage

bone (woven bone) formation. We demonstrate that the osteocytes form a network showing cell-

cell communication via the expression of sclerostin, embedded within the collagen matrix that is

formed by the osteoblasts and mineralized under biological control.

Organoids have been defined as "in vitro 3D cellular clusters derived exclusively from embryonic

stem cells, induced pluripotent stem cells or primary tissue, capable of self-renewal and self-

organization, and exhibiting similar organ functionality as the tissue of origin", where they may "rely

on artificial extracellular matrices (ECM) to facilitate their self-organization into structures that

resemble native tissue architecture"[1]. In the case of bone, such a model system where mechanical

and (bio)chemical signals can be applied in a dynamic environment, would be an important tool in

the development of treatments for bone related human diseases such as osteoporosis and skeletal

dysplasia such as osteogenesis imperfecta, and aid in the development of strategies for personalized

bone regenerative medicine.

Realizing a 3D model with different interacting bone cell types is, however, still an enormous

challenge. In particular the differentiation of *human* bone marrow-derived mesenchymal stromal

cells (BMSCs) into osteocytes, which form 90-95% of the cellular fraction of bone tissue[4], has not yet

been achieved *in vitro* and currently remains a critical step in the engineering of *in vitro* human bone

models.

In vivo, osteocytes form through the differentiation of osteoblasts, after these become embedded in

the extracellular matrix they produce[4,5]. Osteocytes are responsible for sensing the biophysical

demands placed on the tissue and orchestrating the concomitant actions of osteoblasts and

osteoclasts in the remodeling of bone[2], as well as for maintaining calcium and phosphate

homeostasis. During the differentiation from osteoblasts to osteocytes, the cells grow long

extensions called processes, by which they form a sensory network that translates mechanical cues

into biochemical signals and through which they interact with other cells[2].

In vitro, osteoblast-based cell lines developed as models of osteocytes or osteocyte differentiation

have not yet been shown to produce a fully developed mineralized collagen matrix[6], and hence are

limited as 3D models for bone formation. So far, the full differentiation from MSCs to functional

osteocytes has been demonstrated for mouse cells[7,8] but not yet for human cells. Recently, pre-

osteocyte-like cells have been achieved from human primary cells[9,10], and co-cultures were

generated from pre-prepared populations of osteoblasts and osteocytes[11], but the *in vitro* production

of a bone-like mineralized matrix formed under biological control was not yet demonstrated. Also

missing is a demonstration of the production of sclerostin by osteocytes at the protein level, where

sclerostin is a key anti-anabolic molecule that interacts with osteoblasts to down-regulate ECM

formation. Hence, the creation of an organoid, as a model for developing bone, through the full

differentiation of human primary cells into a functional osteocyte network within a bone-like

mineralized matrix is still an outstanding challenge.

In the present work, primary human bone marrow stromal cells (hBMSC) were seeded on porous 3D

silk fibroin scaffolds[12] and subsequently cultured in osteogenic differentiation medium. The cells

were exposed to mechanical stimulation through fluid flow derived shear stress, by applying

continuous stirring in a specifically designed spinner-flask bioreactor (Supplementary Fig. 1)[13], while a

static system was used as control. Cells subjected to mechanical loading showed the production of a

mineralized extracellular matrix (ECM) - as assessed by micro-computed tomography (μCT) and

histological staining for collagen, glycosaminoglycans and minerals (Supplementary Fig. 2). Fourier-

Transformed Infrared (FTIR) spectroscopy indicated a matrix composition similar to that of

embryonic chicken bones (Supplementary Fig. 3)[14]. In contrast, no significant ECM production was

observed in the static system.

The differentiation from primary cells to osteoblasts and osteocytes was followed using

immunohistochemistry, visualizing the expression of specific biomarkers at the protein level for the

subsequent development to pre-osteoblasts, osteoblasts and osteocytes[2] (Fig. 1, Supplementary Fig.

4). The pre-osteoblastic stage was identified by the expression of transcription factors RUNX2 (CBFA-

1) and osterix (OSX, SP7) (Fig. 1 a-b, Supplementary Fig. 4). The next stage in the differentiation, the

formation of osteoblasts, was heralded by the detection of osteoblast-specific markers, where

alkaline phosphatase (ALP) was detected at the cell surfaces, and osteocalcin (BGLAP), osteopontin

(BSP1) and osteonectin (SPARC) localized in the cellular environment (Fig. 1 c-f, Supplementary Fig.

4). Finally, the differentiation into osteocytes was indicated by the expression of dentin matrix

protein1 (DMP1), podoplanin (E11) and sclerostin (Fig. 1 g-i, Supplementary Fig. 4). DMP1 is a marker

for the early stages of osteocyte formation, coinciding with the embedding of the osteoblasts in the

collagenous matrix. Podoplanin marks the osteocyte embedded in the non-mineralized matrix stage

and has been suggested to regulate process formation[4]. Sclerostin indicates the maturation of the

osteocytes and their ability to perform their signaling function in the bone regulatory process[2,15]. We

note that the rate of osteocyte differentiation depended on the glucose concentration in the

medium, as indicated by the detection of sclerostin after ~4 weeks for 5.55 mM glucose (Fig. 1 i) and

~ 8 weeks for 25 mM glucose (Fig. 1 k).

Fluorescence microscopy using calcein staining showed the co-localization of sclerostin and mineral

in large domains with dimensions of hundreds of micrometers, indicating the embedding of the

osteocytes in a mineralized organic matrix (Fig. 1 k). Indeed, combined staining with calcein (mineral)

and CNA35 (collagen) revealed the presence of sub-millimeter sized mineralized collagen domains

(Fig. 1 l) throughout the entire scaffold, co-existing with non-mineralized domains osteoblast markers

were also still observed (Supplementary Fig. 5). This implies that this co-culture presents different

stages of osteogenic cell differentiation and maturation in which osteocytes had formed that

organized themselves with the mineralized matrix also produced by the system.

Fluorescence microscopy further confirmed osteocyte formation showing the development of cell

processes, and the formation of an interconnected network (Fig. 2 a). Additionally, three dimensional

focused ion beam/scanning electron microscopy (3D FIB/SEM) showed that the cells form a relatively

dense 3D network with significant variation in their morphologies, as well as in the number, lengths

and connectivity of their processes (Fig. 2 b-e, Supplementary table 1 and 2). We note that our

osteocytes most often show flattened morphologies, which differ from those in text books with

generally spherical or oblate bodies and long homogeneous protrusions but are similar to osteocyte

morphologies observed in different bone types, including rat tibia,[16] human femur[17] and mouse

woven bone[18].

Cells showed both connected and unconnected processes, with connections to 1-7 neighboring cells

(Fig 2 f, Supplementary Fig. 7 and table 2). The network had a density of 750,000 cells.mm^{-3}, which is

higher than observed for mature osteocytes in cortical bone (20,000-80,000 cells.mm^{-3})[5], but in line

with numbers found for woven bone such as in embryonic chicken tibia (500,000-700,000 cells.mm^{-3}

)[19]. Image analysis (Supplementary Fig. 11) showed that for the different cells the number of

processes per unit surface area ranged between 0.05 - 0.23 µm^{-2} (Supplementary Table 3), in line

with reported for mouse osteocytes (0.08 – 0.09 µm^{-2})[20]. The functionality of the processes was

indicated not only by their connection to neighboring cells (Fig. 2 g-h), but also by their co-

localization with connexin43, a protein essential for gap junction communication (Fig. 2 i)[2]. The

observed variation in osteocyte morphology, together with the variation in the number of cell

processes per surface area reflects the different stages of development and maturation, as expected

in a differentiating osteogenic co-culture.

To evaluate the physiological relevance of our co-culture model system, we also analyzed its

capability to reproduce the bone extracellular matrix. FIB/SEM volume imaging with 3D

reconstruction showed that the osteocytes were fully embedded in their ECM (Fig. 3 a; Video 1). The

produced collagen matrix enveloped the cells, but showed a low degree of long range order (Fig. 3 b),

as known for woven bone[18,21], and in line with what was described for collagen layers containing

osteocytes.[22] The extracellular deposition of non-collagenous proteins (NCPs) was evidenced by

immunohistochemical analysis, showing the presence of osteocalcin, osteopontin, and DMP1 and

their co-localization with collagen (Fig. 3 c-d, Supplementary Fig. 8).

Whereas µCT (Supplementary Fig. 2), FTIR (Supplementary Fig. 3), histochemistry (Supplementary

Fig. 2), and fluorescence microscopy (Fig. 1 k) all indicated the mineralization of the organic matrix,

none of these methods can provide the spatial resolution to demonstrate whether the mineral

crystals are indeed, as in bone, co-assembled with the collagen fibrils[23], and not just the result of

uncontrolled precipitation[24]. We therefore applied a multiscale imaging approach to verify that

matrix mineralization indeed occurred under biological control. Raman micro-spectroscopy of the

extracellular matrix showed the spectral signature of developing bone (Fig. 3 f) and confirmed the co-

localization of the mineral with the collagen (Supplementary Fig. 9). Spectral analysis further

confirmed that the mineral/matrix ratio (a key parameter for bone development, determined from

the PO_4 ν_4 / Amide III vibrations intensity ratio [25]) in the co-culture was indeed in the range found for

developing bone (Fig. 3 g)[26].

At higher resolution (voxel size 10x10x20 nm^3), 3D FIB/SEM with back scatter detection revealed thin

collagen fibrils (diameters 50-80 nm) with varying degrees of mineralization as also commonly

observed in the early stages of bone development[27] (Fig. 3 i, video-2, supplementary Fig. 10).

Applying a heat map presentation showed the coexistence of non-mineralized fibrils (blue) alongside

a mineralized population (green-red range). Additionally, transmission electron microscopy (TEM)

showed mineralized single fibrils,[7] indicating that the collagen matrix was indeed mineralized under

biological control (Fig. 3 j)[28]. Nevertheless, in some areas also larger mineral precipitates were

observed (Supplementary Fig. 10 c, orange) (Video-2), possibly due to local non-biologically

controlled precipitation of calcium phosphate.

Woven bone is the first form of mammalian bone deposited during embryonic development and

fracture, before being replaced by other bone types.[21] Hence, in situations in which rapid formation

is a prime concern, and where osteoclasts and bone remodeling do not yet play a role. Our results

show the formation of a bone organoid consisting of a self-organized co-culture of osteoblasts and

osteocytes representing a functional model for woven bone. We demonstrate the functionality of the

organoid by showing that the ECM formed by the osteoblasts is mineralized under biological control,

and that the mature osteocytes self-organize into a network within the mineralized matrix where

they express sclerostin and connexin43 at the protein level.

Interestingly, the production of sclerostin did not prohibit ECM formation throughout the organoid,

suggesting that the down regulation of this process is a local effect. This may be explained by

assuming the most mature osteocytes are in the center of the osteocyte domains, which would lead

to a gradient of sclerostin decreasing towards the periphery of the network, only affecting the

activity of the osteoblasts closest to the osteocyte domain.

The use of silk fibroin as a scaffold material rather than the frequently used collagen scaffolds,

permits to differentiate between the supplied and the newly formed matrix material, and study the

quality of the collagen matrix as function of external stimuli (mechanical load, therapeutics) or

genetic diseases (e.g. osteogenesis imperfecta). The application of mechanical stimulation during the

development of our stem cell based co-culture proved crucial for the osteogenic differentiation, and

underlines the importance of the integration of self-organizing stem cell based strategies with

environmental control in microfluidic systems in the recent organoid-on-a-chip approaches.[29]

Acknowledgments: We would like to thank like Lia Addadi and Steve Weiner for providing the

zebrafish and embryonic chicken data, and Carlijn Bouten for providing CNA35 collagen probe. We

also thank Deniz Daviran for her help in preparing the figures. AA was supported by the Marie Curie

Individual Fellowship (H2020-MSCA-IF-2017-794296-SUPERMIN), by the Netherlands Organization

for Scientific Research (NWO) through an ECHO grant to NS, and by the National Postdoctoral Award

Program for Advancing Women in Science - the Weizmann Institute of Science, Israel. NS, RvdM and

MvE were supported by the European Research Council (ERC) Advanced Investigator grant (H2020-

ERC-2017-ADV-788982-COLMIN) to NS, SA was supported by the Ministry of Education, Culture and

Science (Gravitation Program 024.003.013). NL was supported by the Netherlands Organization for

Scientific Research (NWO) through a ZonMW-TOP grant to JK. JM, FZ and SH were supported by the

ERC Starting grant (FP7-ERC-2013-StG-336043-REMOTE) to SH.

Author Contributions: AA, KI, NS, SH designed the project and wrote the paper. AA, JM, SA were

responsible for 3D cell culture, light and fluorescent imaging and analyzed the data. NL, JF, CdeH and

JK prepared samples for EM and took EM images. RvdM, AA and NS acquired and analyzed the

spectroscopic data. MS, CMO and AA performed the FIB/SEM reconstruction and segmentation.

CMO, FZ, RvdM, AA, NS, MvE and SH analyzed the connectivity map of the osteocyte network. WHN

provided the bone reference sample. All authors read the paper and gave their comments.

Competing Interests statement:

The authors declare no competing interests

Data availability statements:

The datasets generated during and/or analysed during the current study are available from the

corresponding author on reasonable request

Code availability:

Computer codes are available at: https://filesender.surf.nl/?s=download&token=e5f72e20-

2240-4f58-abeb-3ecbeaab54f2

Materials and methods:

Materials:

Dulbecco's modified Eagle medium (DMEM high glucose Cat. No. 41966 and low glucose Cat. No. 31885) and antibiotic/antimycotic (Anti-Anti) were from Life Technologies (Bleiswijk, The Netherlands). Citrate buffer was from Thermo Fisher Scientific (Breda, The Netherlands). Methanol was from Merck (Schiphol-Rijk, The Netherlands). Trypsin-EDTA (0.25%) was from Lonza (Breda, The Netherlands). Fetal bovine serum (FBS) was from PAA Laboratories (Cat. No A15-151, Cölbe, Germany). 10-nm Au particles conjugated to Protein-A were from CMC, UMC Utrecht (Utrecht, The Netherlands). BSA-c was from Aurion (Wageningen, The Netherlands). Silkworm cocoons from Bombyx mori L. were purchased from Tajima Shoji Co., LTD. (Yokohama, Japan). All other substances were of analytical or pharmaceutical grade and obtained from Sigma Aldrich (Zwijndrecht, The Netherlands). The reference human bone sample used for Raman micro-spectrometry was waste material from a surgical procedure on a fractured left tibia of a 10-year-old female. According to the Central Committee on Research involving Human Subjects (CCMO), this type of study does not require approval from an ethics committee in the Netherlands (see https://english.ccmo.nl/investigators/legal-framework-for-medical-scientific-research/your-research-is-it-subject-to-the-wmo-or-not). For information on the embryonic chicken bone and zebrafish bone we refer to references 14 (Kerschnitzky et al.) and 26 (Akiva et al.), respectively.

Scaffold fabrication:

Silk fibroin scaffolds were produced as previously described[30]. Briefly, Bombyx mori L. silkworm cocoons were degummed by boiling in 0.2M Na_2CO_3 twice for 1 h. The dried silk was dissolved in 9 M LiBr and dialyzed against ultra-pure water (UPW) for 36 h using SnakeSkin Dialysis Tubing (molecular weight cutoff: 3.5 K; Thermo Fisher Scientific, Breda, The Netherlands). Dialyzed silk fibroin solution was frozen at -80°C and lyophilized (Freezone 2.5, Labconco, Kansas City, MO, USA) for 4 days, then dissolved in hexafluoro-2-propanol, resulting in a 17% (w/v) solution. 1 ml of dissolved silk fibroin

was added to 2.5 g NaCl with a granule diameter of 250–300 µm and was allowed to air dry for 3

days. Silk-salt blocks were immersed in 90% MeOH for 30 min to induce β-sheet formation[31]. NaCl

was extracted from dried blocks in UPW for 2 days. Scaffolds were cut into disks of 5 mm in diameter

and 3 mm in height and autoclaved in PBS at 121°C for 20 min.

Cell culture:

Cells were isolated from unprocessed, fresh, human bone marrow (Lonza, Walkersville, MD, USA, cat.

No #1M-125) of one male donor (healthy, non-smoker). hBMSC isolation and characterization was

performed as previously described and passaged up to passage 4[30]. Pre-wetted scaffolds were

seeded with 1 million cells each in 20 µL control medium (DMEM, 10% FBS, 1% Anti-Anti) and

incubated for 90 min at 37° C. The cell-loaded scaffolds were transferred to custom-made spinner

flask bioreactors (n = 4 per bioreactor, Supplementary Fig. 1). Each bioreactor contained a magnetic

stir bar and was placed on a magnetic stirrer (RTv5, IKA, Germany) in an incubator (37° C, 5% CO_2).

Each bioreactor was filled with 5 mL osteogenic medium (control medium, 50 µg/mL ascorbic-acid-2-

phosphate, 100 nM dexamethasone, 10 mM β-glycerophosphate) and medium was changed 3 times

a week.

Micro-computed tomography imaging (µCT):

µCT measurements and analysis were performed on a µCT100 imaging system (Scanco Medical,

Brüttisellen, Switzerland). Scanning of the co-culture samples within the bioreactor was performed at

an isotropic nominal resolution of 17.2 µm, energy level was set to 45 kVp, intensity to 200 µA, 300

ms integration time and two-fold frame averaging. A constrained Gaussian filter was applied to

reduce part of the noise. Filter support was set to 1.0 and filter width sigma to 0.8 voxel. Filtered

grayscale images were segmented at a global threshold of 23% of the maximal grayscale value to

separate the mineralized tissue from the background and binarize the image. Unconnected objects

smaller than 50 voxels were removed and neglected for further analysis. Quantitative

morphometrical analysis was performed to assess mineralized ECM volume within the entire scaffold

volume using direct microstructural bone analysis as previously described for human bone

biopsies[32,33].

Histological sections:

Co-cultures were fixed in 10% neutral buffered formalin (24 h at 4° C), dehydrated in serial ethanol

solutions (50%, 70%, 90%, 96%, 100%, 100%, 100%), embedded in paraffin, cut into 6 µm thick

sections and mounted on Poly-L-Lysine coated microscope slides. Paraffin sections were dewaxed

with xylene and rehydrated to water through graded ethanol solutions.

Brightfield imaging:

Sections were stained with Alizarin Red to identify mineralization (2%, Sigma-Aldrich), Picrosirius Red

(0.1%, Sigma-Aldrich) to identify collagen, Alcian blue (1%, Sigma-Aldrich) to identify

Glycosaminoglycan (GAGs). Sections were imaged using Zeiss Axio Observer Z1 microscope.

Immunohistochemistry:

Antigen retrieval in pH 6 citrate buffer at 95° C was performed for 20 min. Sections were washed

three times in PBS. Non-specific antibody binding was blocked with 5% serum (v/v) from the host of

the secondary AB and 1% bovine serum albumin (w/v) in PBS (blocking buffer) for 1 h. Sections were

then incubated overnight at 4° C with primary antibodies in blocking buffer. The sections were rinsed

with PBS four times for 5 min and incubated for 1 h with secondary antibodies in blocking buffer and

at times with calcein solution (1 µg/mL, C0875 Sigma-Aldrich). All used antibodies and dyes are listed

in Table 1. Nuclei were stained with DAPI for 5 min, after which sections were again washed three

times with PBS and mounted on microscope glass slides with Mowiol. Cytoplasm was stained with

FM 4-64 (Molecular Probes cat#T3166) for 1 minute and followed by washing the sections three

times with PBS. Except for primary antibody incubation, all incubation steps were performed at room

temperature. Sections were imaged either by Zeiss Axiovert 200M microscope (large field of view) or

by Leica TCS SP5X (x63, high magnification images). Images were post processed (brightness,

contrast, channel merging and crop) using Fiji software.

Table 1. List of all antibodies and dyes used.

Antigen	Source	Cat. No	Label	Species	Dilution/concentration
ALP	ThermoFisher	MA5-17030	-	Mouse	1:200
Calcein Green	Sigma	C0875	-	-	1 µg/ml
CNA35-mCherry	Homemade[34]	-	mCherry	-	1 µM
Collagen1	Abcam	ab34710	-	Rabbit	1:250
Connexin 43	Sigma	C6219	-	Rabbit	1:500
DAPI	Sigma	D9542	-	-	0.1 µg/ml
DMP1	biorbyt	orb247330	-	Rabbit	1:400
FM 4-64	Molecular Probes	T3166	-	-	5 µg/ml
Osteocalcin	Abcam	Ab93876	-	Rabbit	1:200
Osteonectin	ThermoFisher	MA1-43027	-	Mouse	1:500
Osteopontin	ThermoFisher	14-9096-82	-	Mouse	1:200
OSX	Abcam	ab22552	-	Rabbit	1:200
Podoplanin	Abcam	ab128994	-	Rabbit	1:200
RUNX2	Abcam	Ab23981	-	Rabbit	1:500
Sclerostin	ThermoFisher	PA5-37943	-	Goat	1:200
Goat IgG (H+L)	Jackson Immuno	A11055	Alexa 488	Donkey	1:200

Mouse IgG (H+L)	Molecular Probes	A21236	Alexa 647	Goat	1:200
Mouse IgG (H+L)	Jackson Immuno	715-545-150	Alexa 488	Donkey	1:200
Rabbit IgG (H+L)	Invitrogen	A21206	Alexa 488	Donkey	1:200
Rabbit IgG (H+L)	Molecular Probes	A21244	Alexa 647	Goat	1:200
Alizarin Red	Sigma-Aldrich	A5533	-	-	2%
Picrosirius Red	Sigma-Aldrich	365548	-	-	0.1%
Alcian blue	Sigma-Aldrich	A5268	-	-	1%

Sample preparation for electron microscopy:

Samples were processed for electron microscopy as previously described[35]. In short, co-culture

samples were fixed in 2.5% glutaraldehyde and 2% paraformaldehyde in 0.1 M sodium cacodylate

buffer (CB) for 72 h and washed 5 times in 0.1 M CB and 5 times in double-distilled water (ddH$_2$O).

Co-cultures were then post fixed using 1% OsO$_4$ with 0.8% K$_3$Fe(CN)$_6$ in 0.1 M CB for 1 hour on ice.

After rinsing in 0.1 M CB, the co-cultures were treated with 1% Tannic acid followed by 1% uranyl

acetate in ddH$_2$O for 1 hour. Finally, the samples were rinsed using ddH$_2$O, dehydrated with ethanol

(50%, 70%, 90%, 96%, 100%), and embedded in Epon resin.

Focused Ion Beam Scanning Electron Microscopy (FIB/SEM) imaging:

Epon embedded samples were imaged with a Scios FIB/SEM (Thermo Fisher Scientific, Breda, The

Netherlands) under high vacuum conditions. Using the gas injection system (GIS) in the FIB/SEM

microscope, a 500 nm thick layer of Pt was deposited over the ROI, at an acceleration voltage of 30

kV and a current of 1 nA. Trenches flanking the ROI were milled at an acceleration voltage of 30 kV,

using a high FIB beam current (5-7 nA), followed by a staircase pattern in front of the ROI to expose

the imaging surface. Fine polishing was performed with the ion beam set to 30 kV with a FIB beam

current of 0.5 nA, resulting in a smooth imaging surface. Serial imaging was then performed using the

in-column backscattered electron detector, and the following settings: Acceleration voltage 2 kV,

Beam current 0.2 nA, Pixel dwell time 10 µs, voxel size: 30x30x30 nm (stack in video 1) and 10x10x20

nm (stack in Video 2).

Sample preparation for Transmission Electron Microscopy (TEM):

Epon embedded samples: 70 nm sections from resin embedded blocks were made using an ultra-

microtome (Leica), and collected on carbon coated copper TEM grids. Post staining with uranyl

acetate and led citrate was performed using the Leica EM AC20 automatic contrasting instrument.

Preparation and Immunogold labelling of Tokuyasu Sections:

Thin sections were prepared following the Tokuyasu protocol[36,37]. Briefly, co-cultures were fixed as

described above and infiltrated overnight in 2.3 M sucrose for cryo-protection. Small blocks of the

co-cultures were mounted on aluminum pins and plunge frozen in liquid nitrogen. 70 nm thick

cryosections were sectioned with a cryo-ultramicrotome and picked up with a mixture of 2%

methylcellulose/2.3 M sucrose on copper support grids coated with formvar and carbon. After rinsing

away the pick-up solution in PBS at 37° C for 30 minutes, the sections were treated with PBS

containing 0.15% glycine, followed by blocking for 10 minutes with 0.5% cold fish skin gelatin and

0.1% BSA-c in PBS. The TEM grids were incubated for 1 hour with a collagen type 1 antibody in

blocking solution (Abcam, AB34710). The grids were then rinsed with 0.1% BSA in PBS and incubated

with 10-nm Au particles conjugated to Protein-A in blocking solution.[38] The sections were then

thoroughly washed in ddH$_2$O, stained with uranyl acetate and embedded in methylcellulose.[38]

TEM imaging:

The sections were imaged using a Tecnai T12 TEM (80kV) (Thermo Fisher Scientific, Breda, The Netherlands), equipped with Veleta (EMSIS GmbH, Münster, Germany).

Raman spectroscopy:

Raman measurements were conducted using a WiTec Alpha 300R confocal Raman microscope. Co-culture samples were fixed in 10% neutral buffered formalin (24 h at 4° C), incubated for 2 hours in 5% sucrose at 4° C, embedded in Tissue-Tek (Sakura Finetek 4609024), cut into 10 µm thick sections and mounted on Poly-L-Lysine coated microscope slides. Raman imaging was conducted using 532 nm excitation lasers with a laser power of 10 mW, using 50x 0.8 objective (0.8 NA) with a grating of 600 gr/mm. The maps were obtained with a spatial resolution of 3 spectra/µm. Data analysis was performed using Project V plus software (Witec , Ulm) and Origin 8.

FTIR spectroscopy:

Prior to the FTIR measurement, the co-culture samples were freeze dried overnight. After drying, 1.5 mg of the samples was crushed using mortar and pestle until a fine powder was achieved. After this, 148.5 mg of KBr was added to the mortar and pestle and the materials were mixed and further crushed to a fine homogeneous mixture. The mixture was added to a pellet press holder, the transparent and homogeneous pellets were then inserted into the FTIR spectrometer (Perking Elmer one 1600). The FTIR spectra were obtained in transmission mode. Spectra were obtained over the range form 200 cm^{-1} to 6000 cm^{-1} with a spectral resolution of 0.5 cm^{-1}.

Image Analysis:

3D FIB/SEM Image processing was performed using Matlab and Avizo 3D software (FEI VSG, www.avizo3d.com). 3D image reconstruction, alignment, denoising and brightness and contrast adjustments were done usign Matlab. 3D segmentation was done using Avizo. Segmentation was

performed using manual thresholding, and cell processes were counted manually. As all cells were

only partially captured in the available FIB/SEM volume, cell process density was determined per unit

surface area of the cell body. The surface areas of cell parts captured in the FIB/SEM volume were

calculated from the segmented 3D image mask using Matlab and Fiji. Further details are given in

Supplementary Fig. 11.

Cell density was determined from the number of cells in the imaged FIB/SEM volume (20 μm x 20 μm

x 40 μm) and compared to literature data from histological sections[19] (volume 5 μm x 1000 μm x

1000 μm).

References

Fatehullah, A., Tan, S. H. & Barker, N. Organoids as an in vitro model of human development and disease. *Nat Cell Biol* **18**, 246-254, doi:10.1038/ncb3312 (2016).

in *Principles of Bone Biology (Fourth Edition)* (eds John P. Bilezikian, T. John Martin, Thomas L. Clemens, & Clifford J. Rosen) 1943-1986 (Academic Press, 2020).

Owen, R. & Reilly, G. C. In vitro Models of Bone Remodelling and Associated Disorders. *Front Bioeng Biotechnol* **6**, 134, doi:10.3389/fbioe.2018.00134 (2018).

Bonewald, L. F. The amazing osteocyte. *J Bone Miner Res* **26**, 229-238, doi:10.1002/jbmr.320 (2011).

Franz-Odendaal, T. A., Hall, B. K. & Witten, P. E. Buried alive: How osteoblasts become osteocytes. *Dev Dynam* **235**, 176-190 (2006).

Zhang, C., Bakker, A. D., Klein-Nulend, J. & Bravenboer, N. Studies on Osteocytes in Their 3D Native Matrix Versus 2D In Vitro Models. *Curr Osteoporos Rep* **17**, 207-216, doi:10.1007/s11914-019-00521-1 (2019).

Wang, K. *et al.* A Novel Osteogenic Cell Line That Differentiates Into GFP-Tagged Osteocytes and Forms Mineral With a Bone-Like Lacunocanalicular Structure. *J Bone Miner Res* **34**, 979-995, doi:10.1002/jbmr.3720 (2019).

Iordachescu, A. *et al.* An In Vitro Model for the Development of Mature Bone Containing an Osteocyte Network. *Advanced Biosystems* **2**, doi:10.1002/adbi.201700156 (2018).

Thrivikraman, G. *et al.* Rapid fabrication of vascularized and innervated cell-laden bone models with biomimetic intrafibrillar collagen mineralization. *Nat Commun* **10**, 3520, doi:10.1038/s41467-019-11455-8 (2019).

Nasello, G. *et al.* Primary Human Osteoblasts Cultured in a 3D Microenvironment Create a Unique Representative Model of Their Differentiation Into Osteocytes. *Frontiers in Bioengineering and Biotechnology* **8**, doi:10.3389/fbioe.2020.00336 (2020).

Skottke, J., Gelinsky, M. & Bernhardt, A. In Vitro Co-culture Model of Primary Human Osteoblasts and Osteocytes in Collagen Gels. *Int J Mol Sci* **20**, doi:10.3390/ijms20081998 (2019).

Vetsch, J. R., Paulsen, S. J., Muller, R. & Hofmann, S. Effect of fetal bovine serum on mineralization in silk fibroin scaffolds. *Acta Biomater* **13**, 277-285, doi:10.1016/j.actbio.2014.11.025 (2015).

Melke, J., Zhao, F., van Rietbergen, B., Ito, K. & Hofmann, S. Localisation of mineralised tissue in a complex spinner flask environment correlates with predicted wall shear stress level localisation. *Eur Cell Mater* **36**, 57-68, doi:10.22203/eCM.v036a05 (2018).

Kerschnitzki, M. *et al.* Bone mineralization pathways during the rapid growth of embryonic chicken long bones. *J Struct Biol* **195**, 82-92, doi:10.1016/j.jsb.2016.04.011 (2016).

Kenneth E. S. Poole, R. L. v. B., Nigel Loveridge, Herman Hamersma, & Socrates E. Papapoulos, C. W. L., and Jonathan Reeve. Sclerostin is a delayed secreted product of osteocytes that inhibits bone formation. *The FASEB Journal* **19**, 1842-1844 (2005).

Verbruggen, S. W., Vaughan, T. J. & McNamara, L. M. Strain amplification in bone mechanobiology: a computational investigation of the in vivo mechanics of osteocytes. *J R Soc Interface* **9**, 2735-2744, doi:10.1098/rsif.2012.0286 (2012).

Varga, P. *et al.* Synchrotron X-ray phase nano-tomography-based analysis of the lacunar-canalicular network morphology and its relation to the strains experienced by osteocytes in situ as predicted by case-specific finite element analysis. *Biomech Model Mechanobiol* **14**, 267-282, doi:10.1007/s10237-014-0601-9 (2015).

Kerschnitzki, M. *et al.* The organization of the osteocyte network mirrors the extracellular matrix orientation in bone. *J Struct Biol* **173**, 303-311, doi:10.1016/j.jsb.2010.11.014 (2011).

Yair, R., Cahaner, A., Uni, Z. & Shahar, R. Maternal and genetic effects on broiler bone properties during incubation period. *Poult Sci* **96**, 2301-2311, doi:10.3382/ps/pex021 (2017).

Tokarz, D. *et al.* Intravital imaging of osteocytes in mouse calvaria using third harmonic generation microscopy. *PLoS One* **12**, e0186846, doi:10.1371/journal.pone.0186846 (2017).

and, S. W. & Wagner, H. D. THE MATERIAL BONE: Structure-Mechanical Function Relations. *Annual Review of Materials Science* **28**, 271-298, doi:10.1146/annurev.matsci.28.1.271 (1998).

Reznikov, N., Shahar, R. & Weiner, S. Three-dimensional structure of human lamellar bone: The presence of two different materials and new insights into the hierarchical organization. *Bone* **59**, 93-104, doi:https://doi.org/10.1016/j.bone.2013.10.023 (2014).

Reznikov, N., Shahar, R. & Weiner, S. Bone hierarchical structure in three dimensions. *Acta Biomaterialia* **10**, 3815-3826 (2014).

de Wildt, B. W. M. *et al.* From bone regeneration to three-dimensional in vitro models: tissue engineering of organized bone extracellular matrix. *Current Opinion in Biomedical Engineering* **10**, 107-115, doi:https://doi.org/10.1016/j.cobme.2019.05.005 (2019).

Kazanci, M., Roschger, P., Paschalis, E. P., Klaushofer, K. & Fratzl, P. Bone osteonal tissues by Raman spectral mapping: Orientation–composition. *Journal of Structural Biology* **156**, 489-496, doi:https://doi.org/10.1016/j.jsb.2006.06.011 (2006).

Akiva, A. *et al.* Mineral Formation in the Larval Zebrafish Tail Bone Occurs via an Acidic Disordered Calcium Phosphate Phase. *J Am Chem Soc* **138**, 14481-14487, doi:10.1021/jacs.6b09442 (2016).

McKee, M. D. & Nanci, A. Postembedding colloidal-gold immunocytochemistry of noncollagenous extracellular matrix proteins in mineralized tissues. *Microscopy Research and Technique* **31**, 44-62, doi:10.1002/jemt.1070310105 (1995).

Weiner, S. & Traub, W. Organization of hydroxyapatite crystals within collagen fibrils. *FEBS letters* **206**, 262-266 (1986).

Park, S. E., Georgescu, A. & Huh, D. Organoids-on-a-chip. *Science* **364**, 960-965, doi:10.1126/science.aaw7894 (2019).

Hofmann, S. *et al.* Control of in vitro tissue-engineered bone-like structures using human mesenchymal stem cells and porous silk scaffolds. *Biomaterials* **28**, 1152-1162, doi:10.1016/j.biomaterials.2006.10.019 (2007).

Nazarov, R., Jin, H.-J. & Kaplan, D. L. Porous 3-D Scaffolds from Regenerated Silk Fibroin. *Biomacromolecules* **5**, 718-726, doi:10.1021/bm034327e (2004).

Hildebrand T, L. A., Muller R, Dequeker J, Ruegsegger P. Direct three-dimensional morphometric analysis of human cancellous bone: microstructural data from spine, femur, iliac crest, and calcaneus. *J. Bone Miner. Res.* **14** (1999).

van Lenthe, G. H. *et al.* Nondestructive micro-computed tomography for biological imaging and quantification of scaffold-bone interaction in vivo. *Biomaterials* **28**, 2479-2490, doi:10.1016/j.biomaterials.2007.01.017 (2007).

Krahn, K. N., Bouten, C. V. C., van Tuijl, S., van Zandvoort, M. A. M. J. & Merkx, M. Fluorescently labeled collagen binding proteins allow specific visualization of collagen in tissues and live cell culture. *Analytical Biochemistry* **350**, 177-185, doi:https://doi.org/10.1016/j.ab.2006.01.013 (2006).

Fermie, J. *et al.* Single organelle dynamics linked to 3D structure by correlative live-cell imaging and 3D electron microscopy. *Traffic* **19**, 354-369, doi:10.1111/tra.12557 (2018).

Oorschot VMJ, S. T., Bryson-Richardson RJ, Ramm G. . in *Correl. Light Electron Microsc. II* 241-258 (Academic Press, 2014).

van Meel, E. *et al.* Disruption of the Man-6-P targeting pathway in mice impairs osteoclast secretory lysosome biogenesis. *Traffic* **12**, 912-924, doi:10.1111/j.1600-0854.2011.01203.x (2011).

Slot, J., Geuze, H. Cryosectioning and immunolabeling. *Nat protoc* **2**, 2480-2491, doi:https://doi.org/10.1038/nprot.2007.365 (2007).

Nyman, J. S. *et al.* Measuring Differences in Compositional Properties of Bone Tissue by Confocal Raman Spectroscopy. *Calcified Tissue International* **89**, 111-122, doi:10.1007/s00223-011-9497-x (2011).

Figure 1: Differentiation of hBMSCs into osteoblasts and osteocytes: a-i) Fluorescence

immunohistochemistry imaging showing markers for a-c) early stages of osteoblast formation, d-f)

mature osteoblasts, and g-i) osteocyte development (5.6 mM glucose). Color code: red - cell

cytoplasm, blue - cell nuclei, green: a) RUNX2 (day 7) , b) OSX (day 7), c) ALP (day 26), d) osteocalcin

(day 26), e) osteopontin (day 26), f) osteonectin (day 21), g) DMP1 (day 28), h) podoplanin (day 28), i)

sclerostin (day 28). Scale bars: 10 μm. See Supplementary Fig.4 for separate channels. j) Schematic

illustration of MSC differentiation into osteoblasts and osteocytes, indicating at which state which

protein expression is expected in a-i. k,l) Fluorescent images indicating self-organized domains of

osteocytes embedded in a mineralized matrix after 8 weeks (25 mM glucose), k) co-localization of

osteocytes (sclerostin, red) and mineral (calcein, green) and l) collagen (CNA35, red) and mineral

(calcein, green) * Indicates the silk fibroin scaffold.

Figure 2: Osteocyte development and network formation. a) Fluorescent cytoplasm staining

showing the development of long (> 5µm, arrows) cell processes connecting cells, and the formation

of an interconnected network. The long processes were enhanced using a gamma value of -1.5. (see

original image in supplementary fig. 6). b) 3D FIB/SEM reconstruction showing cell morphology and

network formation in the whole volume. c-e) Details from the 3D reconstruction in (b) showing

individual osteocytes in different stages of morphological development (cell numbers refer to

identification in supplementary Fig. 7). c) Cell #7, d) cell #9, e) cell #14. f-i) Cell connectivity: f)

Connectivity map of the cells in the 3D FIB/SEM stack (see also Supplementary Tables 1 and 2). Sizes

of the circles reflect the number of processes of that respective cell. Thickness of the lines reflects

the number of connections between individual cells (cell numbers refer to identification in

supplementary Fig. 7). g) single slice from the 3D FIB/SEM stack showing long processes (arrow),

creating a cellular network. h) TEM image shows a gap junction between processes of two

connecting cells. i) fluorescent immunohistochemistry showing the presence of gap junctions on the

surface of the different cells. Color code: red - cell cytoplasm, blue - cell nuclei, green - connexin43.

Figure 3: Extracellular matrix development: a) 3D FIB/SEM reconstruction shows the embedding of

the cells in the collagen matrix (cyan). Discrete cells are represented with different colors. b) TEM

image of a 70 nm section showing the random distribution of collagen fibrils. Collagen type I was

identified by immunolabelling. c-e) Fluorescent immunohistochemistry identifying key non-

collagenous proteins in the collagenous matrix: c) Co-localization of osteocalcin (green) and collagen

(red). d) Osteopontin (green) distribution in the collagen matrix (red). * Indicates the silk fibroin

scaffold. e) Co-localization of DMP1 (green) with the collagen structure (see supplementary Fig. 5 for

collagen image). f-g) Raman microspectrometry of mineralized matrices. f) Localized Raman spectra

of mineralized collagen of developing zebrafish bone (red), the 3D osteogenic co-culture (blue) and

human bone of a 10 year old female (grey g) Raman derived mineral/matrix ratios of 4 mineralized

tissues of zebrafish (N=6, red), Osteogenic 3D culture (N=7, green), 10 year old human female (N=1,

grey), and 48+ years old human male (N=7, black, taken from reference[39]). Bars indicate sample

standard deviations. h) Heat map presentation of a 3D FIB/SEM cross section showing collagen fibrils

with different degrees of mineralization (see Supplementary Fig. 10). Arrowheads indicate non-

mineralized collagen fibrils (light blue), arrow indicates mineralized collagen fibril (orange) i) TEM

image showing individual mineralized collagen fibrils.