Controlling protein nanocage assembly with hydrostatic pressure

Kristian Le Vay[1,2], Ben M. Carter[3], Daniel W. Watkins[1], T-Y. Dora Tang[1], Valeska P. Ting[4], Helmut Cölfen[5], Robert P. Rambo[6], Andrew J. Smith[6], J. L. Ross Anderson[*,1,7], Adam W. Perriman[*,3]

[1]School of Biochemistry, University of Bristol, University Walk, Bristol, BS8 1TD, UK.

[2]Bristol Centre for Functional Nanomaterials, HH Wills Physics Laboratory, University of Bristol, Tyndall Avenue, Bristol, BS8 1TL, UK.

[3]School of Cellular and Molecular Medicine, University of Bristol, University Walk, Bristol, BS8 1TD, UK.

[4]Bristol Composites Institute (ACCIS), University of Bristol, Queen's Building BS8 1TR, UK

[5]Department of Chemistry, University of Konstanz, Universitätsstraße 10, 78457 Konstanz, Germany

[6]Diamond Light Source Ltd., Diamond House, Harwell Science and Innovation Campus, Fermi Ave, Didcot OX11 0DE, UK

[7]BrisSynBio Synthetic Biology Research Centre, Life Sciences Building, University of Bristol, Tyndall Avenue, Bristol, BS8 1TQ, UK.

*Email: ross.anderson@bristol.ac.uk, chawp@bristol.ac.uk

Controlling the assembly and disassembly of nanoscale protein cages is fundamental to the internalisation of protein and non-proteinaceous components for diverse bionanotechnological applications. To this end, here we study the reversible, pressure-induced dissociation of a natural protein nanocage, *E. coli* bacterioferritin (Bfr), principally using synchrotron radiation small angle X-ray scattering and circular dichroism. We demonstrate that hydrostatic pressures of 450 MPa are sufficient to completely dissociate the Bfr icositetramer into protein dimers, and the reversibility and kinetics of the reassembly process can be controlled by selecting appropriate buffer conditions. We also demonstrate that the heme B prosthetic group present at the subunit dimer interface influences the stability and pressure lability of the cage, despite its location being discrete from the inter-dimer interface that is key to cage assembly. This indicates a major cage-stabilising role for heme within this family of ferritins.

Nanoscale protein cages are exceptionally attractive scaffolds for bionanotechnology and materials science, where they can be exploited as platforms for constructing robust and configurable therapeutic delivery vectors[1], vaccines[2], nanoreactors[3,4] and templates for the synthesis of diverse nanomaterials[5–8]. These multifunctional containers, both natural[9–13] and designed[14,15], offer unparalleled control over size, shape, microenvironment, surface functionalisation and stability when constructing novel bionanomaterials.

The ability to control the assembly of such nanocages is an invaluable tool in the synthesis of complex materials, and can be instrumental in facilitating the

encapsulation of non-native nanomaterials. While this can be achieved by exploiting

natural[16–18] or engineered[19–21] cage metastability, the use of such nanocages could

ultimately compromise the robustness of the final assembled material. For nanocages

with higher relative stability, harsher environmental conditions[22,23] are required that

can adversely affect the protein cage, its functional modifications or the intended

payload for encapsulation. New methods are therefore required to circumvent the

necessity for harsh chemical conditions or specific interfacial engineering to promote

cage instability, and to realise the full potential of these cages in bionanotechnology.

Here we report on how hydrostatic pressure can be employed to control the

disassembly and reassembly of the protein nanocage bacterioferritin from *E. coli* (Bfr).

While hydrostatic pressure has been previously employed to dissociate the weakly

stable cage-like assemblyHSP26[24], the structure is not truly hollow[25]. There are

currently no reports of complete, reversible hydrostatic pressure-induced dissociation

in a highly robust nanocage such as ferritin[26,27]. While hydrostatic pressure has been

applied to human ferritin to facilitate the loading of doxorubicin and increase protein

recovery[27], the assembly/disassembly of the cage under pressure was not

investigated. Specifically, we use synchrotron radiation small angle X-ray scattering[28]

to show that the Bfr nanocage dissociates reversibly under pressure, and that the

reassembly can be controlled by altering solution conditions. Hydrostatic pressures of

450 MPa were sufficient to induce reversible dissociation of the Bfr icositetramer into

subunit dimers, and the reversibility of the pressure-induced dissociation was found to

be highly dependent on ionic strength and temperature, allowing for control of

oligomerisation state through pressurisation and selection of buffer conditions.

Furthermore, we demonstrate that the pressure lability of the nanocage can be

modulated by removal of the native heme B prosthetic group. Our study exploits the

ability of SAXS to probe the quaternary, tertiary and secondary structure of proteins,

and will provide not only the means for studying the supramolecular assembly of these

highly valuable nanocages, but will also inform future methodologies for controlling

protein nanocage assembly for efficient payload encapsulation.

Results & Discussion

We initially probed the pressure-induced dissociation of the core-free, or apo-,

bacterioferritin icositetramer (ABfr) by gradually raising the applied hydrostatic

pressure in a diamond-windowed SAXS pressure cell to 450 MPa in 25 MPa

increments, equilibrating for 40 seconds prior to data collection at each pressure. An

oscillating scattering pattern was observed at low pressures (Figure 1a), characteristic

of the hollow nanocage structure. With increasing pressure, fringes corresponding to

the hollow sphere form factor broaden and then disappear, indicating increasing

polydispersity and decreasing concentration of icositetramer due to dissociation into

lower order oligomeric species. The presence of isosbestic points in the reciprocal

space and Kratky data (Figure 1a and 1b), indicate that two species contribute to I(q)

with proportional stoichiometry. At higher pressures (> 300 MPa), a slight drift in the q

value of the isosbestic points is observed, suggesting additional species likely

contribute to the dissociation process.

From the pair distance distribution factor ($P(r)$), we determined $I(0)$ and the radius of

gyration, R_g (Figure 1c), finding that the latter decreases non-linearly from 50 Å to 32

Å over the pressures applied here (Figure 1d). This non-linear change in R_g with

pressure is due to the power law dependence of R_g upon particle size, rather than

suggesting a cooperative dissociation mechanism. The data therefore indicate gradual

icositetramer dissociation with multiple intermediates, and a final state in which the

majority of species are small subunit oligomers. The $P(r)$ distribution is characteristic

of a hollow sphere until 250 MPa. The maximum of this distribution, $P(r)_{max}$, occurs at

$r = 84$ Å, corresponds to the distance between the cage center and the protein shell

and decreases steadily with pressure, indicating gradual loss of the icositetramer. At

high pressures, the magnitude at $r = 84$ Å tends to zero and a new $P(r)_{max}$, emerges

at $r = 32$ Å, corresponding to a subunit oligomer of ABfr, previously masked by that of

the fully assembled cage.

Using a linear combination of theoretical SAXS data from various oligomeric

components, we were able to identify possible dissociation pathways[29,30]. Our

prediction of possible stable oligomers using the PISA (Proteins, Interfaces, Surfaces

and Assemblies)[31] tool returned only the subunit dimer and icositetramer as stable

states (Table S1). We then used single value decomposition to determine the number

of required components (Figure S1 and S2) from the pressure dissociation SAXS, and

constructed various models using oligomer structures derived from crystal structures

of the ABfr icositetramer (Table S2, Figure S3 and S4). Two component models

consisting of the icositetramer and a subunit oligomer provided the worst fits of the

dataset (Table S3), though of these, the model consisting of the icositetramer and

dimer best represented the data. Three component models generally provided better

representations of the dissociation dataset, and all models in which the dimer was the

lowest oligomeric state gave the best fit quality. Thus, in this pressure range, we

assigned the initial and final state as icositetramer and dimer. Ultimately, we found

that the data were best represented by models comprised of icositetramer, dimer and

an intermediate hexamer, octamer or dodecamer (Figure 1e). We acknowledge that

there is no justification for selecting a specific intermediate state based on these data

alone, and therefore refrain from doing so; the equivalence of the models and lack of

cooperativity suggests that a range of intermediate states are present during

dissociation. Although little work has been carried out on pressure-induced ferritin

dissociation, there are many studies detailing pH and denaturant-induced dissociation

and reassembly of mammalian ferritin[32–37]. The dissociation products and

mechanisms of reassociation observed are consistent with the results obtained here,

with dissociation to subunit dimer and reassociation *via* intermediate species including

tetramers, hexamers and octamers most commonly reported.

To assess the effect of pressure on the internal structure, secondary structure and

folding of ABfr, we used a combination of Kratky plot analysis and high pressure

synchrotron radiation circular dichroism (CD). At low pressure, the Kratky plots for ABfr

exhibit multiple bell shaped peaks at low q and converge to the baseline at high q,

indicating a globular, spherical structure (Figure 1b). At high pressure, low q peaks

decrease in intensity and become less distinct, whilst the high q region diverges from

the baseline, indicating a partially folded internal structure above 375 MPa. This may

alter tertiary structure and interfacial interactions, destabilising the icositetramer

structure. We observed no significant change in the circular dichroism spectra

between 0.1 MPa and experimental limit of this technique, 200 MPa (Figure 1f), and

predicted structural composition *via* basis spectra remained constant (alpha helix =

0.99, beta sheet, 0.01)[38]. The CD data support the SAXS data in this pressure range,

and it is therefore likely that the observed changes in quaternary structure up to 375

MPa are due to the system shifting towards a lower volume state, rather than

significant perturbation of the ABfr secondary structure[39].

We then explored the reversibility of the pressure dissociation process. Initially, ABfr

in 45 mM sodium phosphate (NaPi) buffer was pressurised to 450 MPa and held for 5

minutes before pressure release (Figure 2a). An immediate depression in R_g was

observed, and the hollow spherical structure was lost after 30 seconds. Fitting the

change in icositetramer volume fraction against time with a single exponential function

(Figure S5), the observed rate constant (k_{diss}) of dissociation was determined to be

0.114 ± 0.002 s^{-1}. Almost complete reassembly occurred over 30 minutes following

depressurisation, as apparent from the recovery of the radius of gyration over time

(Figure 2a) and the hollow cage form of the P(r) function (Figure 2b). Again, fitting the

change in icositetramer volume fraction against time with a single exponential function

(Figure S7), the observed rate constant of reassociation (k_{ass}), was determined to be

0.006 ± 0.001 s^{-1} (Figure S5). Following reassociation, we noted that the final R_g and

I(0) values were slightly lower than initial values (Figure 2a, b). To quantify the degree

of reassociation and to control for possible radiation damage or background mismatch,

a sample of ABfr was pressurised under identical conditions without SAXS

measurement. Analytical ultracentrifugation (AUC) before pressurisation (Figure 2c,

Table S4) demonstrated that ABfr is almost fully assembled as the icositetramer ($S_{20,}$

$_w$ = 15.76, MW = 424 kDa). Following pressurisation (t = 60 minutes), 94.3% of ABfr

was assembled in the icositetramer state ($S_{20, w}$ = 16.1, MW = 426 kDa), with the

remaining material present as the subunit dimer ($S_{20, w}$ = 3.53, MW = 44.5 kDa). TEM

imaging confirmed the presence of assembled ABfr cages before and after

pressurisation, with no apparent change in morphology (Figure 2d, e).

The rate of reassociation under these conditions appears slow, and is significantly

slower than the calculated dimer collisional frequency[40] ($f_{25°C}$ = 6.79 x10^5 S^{-1} at 25°C)

demonstrating unequivocally that reassembly is not diffusion limited. We then sought

to determine whether recovery from pressure induced conformational drift influenced

the kinetics of reassociation[41,42]. We assessed the degree of protein denaturation by

inspection of a normalised Kratky plot (Figure 2f), in which globular protein exhibits a

maximum value of 1.104 for $qR_g=\sqrt{3}$, whilst unfolded protein has a maximum value of

1.5-2[43]. This plot confirmed that the protein recovers almost immediately from the

denatured state after pressure release, so the process is unlikely to be refolding-

mediated.

The relatively slow rate of association may also be due to a kinetic barrier in the

association process which could arise from repulsive interactions between subunit

dimers. To determine the types of interaction dominant in this process, we explored

the effect of ionic strength and temperature on the nanocage reassembly, finding

strong correlation between these parameters and the rate and completeness of

nanocage reassembly (Figure 3, Table S5). We observed the most efficient

reassembly in high ionic strength sodium phosphate buffer (45 mM, 250 mM NaCl, pH

7; I = 373 mM)), with higher initial R_g than the low ionic strength buffers and almost

complete reassembly at both 5 and 25 °C. In contrast, the assembly was notably

slower and less complete in lower ionic strength sodium phosphate buffer (pH 7, 45

mM; I = 123 mM) at both temperatures, with only gradual recovery of R_g over the 1500

seconds of measurement. Most notably, the reassembly process in water was

significantly impaired at 25 °C, and was effectively arrested at 5 °C, with no

discernable increase in R_g observed over 1500 seconds, indicating the presence of

only discrete subunit dimers within this timeframe. Given these data, we propose that

the reassembly of ABfr nanocages is likely driven by hydrophobic dispersion forces

while opposed by coulombic repulsion.

Similar ionic strength dependencies on nanocage reassembly were observed for the

naturally heme-free *E. coli* ferritin FtnA[44] following low pH-induced dissociation, and it

is likely that the origin of this effect lies at the interface between ferritin subunit dimers,

which associate to form the highly charged, carboxylate-rich ion channels at the C3

and C4 interfaces[45–47]. The increased degree and rate of reassembly with temperature

is a strong indication that assembly is entropically driven by the formation of weak

protein-protein interactions[48]. For oligomeric assemblies, the enthalpic contribution

(ΔH) is generally small, because the strength of protein-water and water-water

interactions are similar. As such, increasing temperature decreases the Gibb's free

energy of association (ΔG^{ass}) and favours assembly.

We also observed a greater degree of dissociation following pressurization at 5°C (5

minutes at 450 MPa) at all ionic strengths tested here; previous studies of pressure-

induced viral capsid dissociation have reported similar effects, and were attributed to

a strong entropic contribution to the free energy of association[49]. In these cases,

higher temperatures lower ΔG^{ass}, promoting association in systems where entropic

contributions to the free energy dominate. Once the interfacial protein-protein

interactions (principally salt bridges and dispersion interactions) are broken and the

oligomers dissociate, dipole-dipole protein-water interactions are formed in their

place[49,50]. At high pressure, inherently shorter dipole interactions are favoured over

dispersion interactions due to the differential effect of compression on bond strength,

and dissociation occurs due to the increasing formation of protein-water interactions.

In addition, the hydration of hydrophobic surfaces is more favourable at high pressure,

as the ordered solvation shell is denser than the bulk solvent. Both similar and

contrasting behaviours have been reported for viral capsids under pressure. Silva *et*

al.[51,52] demonstrated that the 86-subunit bromegrass mosaic virus capsid undergoes

a reversible partial dissociation into dimers upon application of pressure (10%

dissociation at 200 MPa). In contrast, the turnip yellow mosaic virus irreversibly

decapsidates rather than dissociates under pressure, resulting loss of RNA and

formation of a holed capsid, as the subunit interface contains few pressure sensitive

salt bridge and is rich in pressure insensitive hydrogen bonding interactions[53].

We subsequently investigated the ability of the native heme B prosthetic group to

modulate cage stability. Using a well-established procedure for tetrapyrrole extraction,

we removed heme B from an acidified water:2-butanone mixture and confirmed the

successful removal by UV/visible spectroscopy (Figure 4a)[54]. We next explored the

composition of oligomeric species in this apo-apo-Bfr (AABfr) by sedimentation

velocity analytical ultracentrifugation (SV-AUC, Figure 4b). In contrast to the heme

containing ABfr, the SV-AUC distribution reveals a mixture of assembled icositetramer

($S_{(20, w)}$ = 15.85, MW = 427.1 kDa, 62.1%) and subunit dimer ($S_{(20, w)}$ = 2.97, MW =

34.7 kDa, 37.9%). The icositetramer peak is broadened, indicating greater

polydispersity and potentially incomplete assembly. We further characterized this

mixture of species by high-performance liquid chromatography-SAXS (HPLC-SAXS)

(Figure 4c), and observed scattering patterns consistent with both the assembled

icositetrameric nanocage (R_g = 49.88 Å), and a smaller ellipsoidal or parallelepipedal

particle[55]. The extrapolated R_g (22.21 Å) of the smaller particle is in good agreement

with that calculated for the subunit dimer (PDBID: 2VXI, R_g = 21.16 Å)[56], and the Kratky

plot (Figure 4d) indicates a folded structure, although with a greater degree of disorder

than the AABfr icositetramer. We used bead modelling to analyse the SAXS data for

both the ABfr and AABfr icositetramers and found excellent agreement between the

hollow spherical models and the published Bfr crystal structure (Figure 4e)[56]. Similarly,

the bead model of the AABfr subunit dimer closely overlays with the crystal structure

of the AABfr dimer (PDBID: 4CVP)[57]. To further probe the effects of removing heme B

from the nanocages, we used circular dichroism spectroscopy to determine the

thermal stabilities of the Bfr samples. We found the denaturation midpoints of ABfr (T_m

= 68°C) and AABfr (T_m = 58°C) in agreement with previously reported values[58,59],

confirming that removal of heme B has an overall destabilizing effect on the protein.

Comparison of the ABfr and AAbfr subunit dimer crystal structures reveals slight

secondary and tertiary structure differences that may impact the ability of the dimer to

assemble into the icositetramer (Figure S6). In particular, the position of the E helix is

shifted in the heme free protein; this helix lies at the tetramerization interface and is

essential for cage assembly (Figure S7)[60].

These data indicate that the binding of heme B not only leads to an increase in thermal

stability of the bulk Bfr protein, but it specifically stabilises the nanocage assembly.

While such increases in thermal stability induced through cofactor binding in heme-

proteins are widely reported, the bound cofactor's impact on cage stability and

assembly is unknown[61]. To determine the effect of heme B on the pressure stability of

Bfr, we pressurised AABfr to 450 MPa in 25 MPa increments, allowing time at each

step for equilibration before SAXS measurement (Figure 5a). We found the real space

distribution for ABfr at ambient pressure is representative of a mixture of assembled

icositetramers and smaller subunit oligomers, in good agreement with the SV-AUC

data described above (Figure 5b). The icositetramer nanocage structure visible in the

real space distribution is rapidly lost with applied pressure, whilst the final state

resembles a mixture of the subunit dimer and other lower order oligomers. The Kratky

plots demonstrate a less globular structure than ABfr at similar pressures, and do not

reveal any further unfolding over the pressure range (Figure 5c). The initial R_g for

AABfr (42 Å) Is notably lower than that of ABfr (50 Å) due to the mixture of icositetramer

and dimer at ambient pressure. The R_g remains constant until 175 MPa, then

deceases, reaching a plateau at 350 MPa, demonstrating that AABfr is significantly

less pressure stable than ABfr (Figure 5d). The final R_g of 35 Å, was higher than that

of ABfr (32 Å), suggesting a dissociation endpoint with a different oligomeric state.

Conclusions

We have demonstrated here that hydrostatic pressure is a valuable method to control and modulate the assembly, disassembly and oligomeric composition of the bacterioferritin nanocage. It is highly likely that this methodology can be extended to other protein nanocages, especially those stabilized primarily by hydrophobic interactions. Since the method we report here is also gentle, tunable and not limited to intrinsically metastable or mutationally compromised cages, more robust hybrid materials tolerant of harsh environmental conditions are potentially accessible. Full cage dissociation might also provide a route to higher loading ratios of therapeutic molecules or larger payloads unable to traverse the protein cage, leading, for example, to significantly improved synthetic routes to nanocage-based drug delivery vehicles.

Furthermore, we have also demonstrated that the heme B prosthetic groups significantly enhance the Bfr nanocage stability. While it has been previously reported that heme B facilitates electron transfer and iron release from the Bfr core, this can occur in the absence of the prosthetic group and it is notable that heme B is absent in many/most of the known ferritins. It therefore seems plausible that an additional major role of heme B in Bfr is to stabilise the protein nanocage, thus enabling the retention of the protein superstructure for iron mineralisation.

Methods

Protein expression and purification

Bacterioferritin expression was carried out in T7 express *E. coli* BL21 (DE3) cells using a modified pUC119 plasmid, PGS281 as described in Andrews *et al*[62]. Cultures were grown aerobically at 37 °C in LB media containing 34 μg mL^{-1} carbenicillin. Flasks were shaken for 24 hours at 200 rpm, before cultures were harvested by centrifugation (10 minutes, 7277 ×g rcf). The pellets were washed then re-suspended in lysis buffer (1.5 mM KH_2PO_4, 8 mM Na_2HPO_4, 150 mM NaCl, 3 mM KCl, pH 7). Phenylmethylsulfonyl fluoride (PMSF) (1 mM) was added, and then cells were lysed using a probe sonicator (3 × 20s, maximum amplitude). The crude extract was then centrifuged (47808 ×g, 60 minutes). The supernatant was decanted, heated to 70 °C for 15 minutes, then cooled and centrifuged (47808 ×g, 30 minutes). The supernatant was concentrated using a centrifugal concentrator (MWCO = 50 kDa) to half the original volume. The extract was purified by size exclusion chromatography using a Sephadex S200 26/600 column equilibrated with lysis buffer at a flow rate of 2.3 mL *per* minute. Bfr containing fractions were pooled, concentrated, and then further purified by anion exchange chromatography using a Q-Sepharose FF column. The target protein was eluted with a linear gradient of 0-0.3 M NaCl in histidine buffer (20 mM histidine.HCl, pH 5.5). The purified protein was dialysed in a solution of EDTA (10 mM) and DTT (5 mM) to remove the native core, forming ABfr.

High pressure SAXS measurement

Data collection was carried out at the I22 beamline, Diamond Light Source (DLS, Harwell, UK), using a hydrostatic pressure cell with a maximum operation pressure of 500 MPa[28]. Samples were loaded into thin-wall polycarbonate capillaries (θ=2 mm),

which were then sealed with a rubber bung and two-part adhesive. The beam energy

was 18 keV (λ = 0.69 Å) to reduce absorption from the diamond windows and water in

the beam path. ABfr samples were prepared at a concentration of 5 mg mL^{-1} in a range

of buffers and centrifuged (10 minutes, 16000 ×g) prior to measurement. The collection

time for individual measurements was between 6 and 60 s. Hydrostatic pressure

experiments were performed under both equilibrium and dynamic, time resolved

conditions. In the former, the pressure was raised in incremental steps allowing time

for equilibrium before measurement. The beam was blocked during equilibration to

prevent radiation damage. In dynamic experiments the sample was pressurised, held

at pressure, then returned to ambient pressure whilst measuring the time resolved

scattering pattern. Pressure jump experiments were conducted in which pressure was

increased rapidly to 450 MPa whilst measuring the time resolved scattering.

The data were collected using a Pilatus P3-2M detector. The sample to detector

distance was 6 m, providing a q-range of 0.008-0.52 Å^{-1}. The two-dimensional data

sets were reduced using DAWN[63]. Briefly, the q-axis was calibrated using with a silver

behenate standard data, then detector images were masked, radially averaged from

the beam centre and normalised to absolute intensity using a glassy carbon standard.

Background subtraction was carried out using a user-written python script (Figure S8

and S9) to account for background mismatch in the high-q data region. This mismatch

resulted from the necessity of using different capillaries for sample and background,

and slight changes in cell and capillary position when changing samples. Whilst this

mismatch was generally low, systemic under-subtraction at low pressure and over-

subtraction at high pressure was present across data sets. The background

measurement was multiplied by a constant to align the high-q region with that of the

sample. The median I(q) of the region q = 0.3-0.4 Å^{-1} was determined for both sample

and background data. The background was then multiplied by a constant, k, such that

the corrected median I(q) of the background was equal to the median I(q) of the sample

minus a small constant, A. The scaling constant was therefore:

$$k = \frac{I(q)_{sample} - A}{I(q)_{background}} \qquad q = 0.3 - 0.4 \, \text{Å}^{-1}$$

This method was effective in background matching the high-q data region and

preventing over and under subtraction with k = 1 x 10^{-5}. Example data corrections for

ABfr at 0.1 MPa and 200 MPa are shown in Figure S8. The background adjustment

results in lower overall I(q) relative to the unprocessed data, but the shape of the

scattering curve is preserved. Artefacts resulting from Kossel lines are visible in the

data at 200 MPa at q = 0.016 and 0.7 Å^{-1} despite background subtraction. The effect

is most visible in the 2D detector image, shown in Figure S9. Kossel lines are observed

between 100-300 MPa in both background and sample images. The intensity of the

effect is pressure dependent, and line position is dependent on the orientation of the

diamond windows. Care was taken to repeat background measurements following

window changes. However, mismatched line intensity between sample and

background resulted in artefacts in the reduced data. The mismatch occurs due to the

pressure dependence of line intensity: whilst pressure control is accurate to 0.1 MPa

in this apparatus, slight pressure loss often occurs during measurement due to

leakage. Consequently, pressure differences between samples and background

measurements of up to 0.3 MPa are observed. Although visible in the data, the

artefacts are small and not expected to affect subsequent fitting and data analysis.

Parasitic scattering is present in some data sets, particularly where Kossel lines

intersect with the beam-stop (Figure S9 (200 MPa)). This effect is not effectively

removed by background subtraction, and manifests as aggregation-like scattering at

$q < 0.04$ Å^{-1}, which precludes the use of Guinier methods for the approximation of I(0)

and R_g, but does not affect the determination of these parameters from the indirect

Fourier transform of the data.

Circular Dichroism

Circular dichroism (CD) spectroscopy was used to determine the relative thermal

stabilities of ABfr and AABfr and to investigate the secondary structure of both

proteins. Solutions of ABfr or AABfr (0.5 g L^{-1}) were prepared in 45 mM sodium

phosphate buffer (pH 7). The far UV spectrum (190-260 nm) was measured at 25 °C,

then the temperature was increased in 3 degree increments allowing for equilibration

(300s) at each step. The helical content was measured by monitoring mean residue

ellipticity at λ= 222 nm. The thermal denaturation midpoint temperature was

determined using sigmoidal fits of the raw the [$\theta_{222\ nm}$] data and from the maxima in

first differential of the [$\theta_{222\ nm}$] data (Figure 4f). Secondary structure composition was

determined by linear combination of basis spectra using CAPITO[38].

High pressure circular dichroism

High pressure circular dichroism measurements were carried out at the B23 beamline,

Diamond Light Source (DLS, Harwell, UK), using a hydrostatic pressure cell with a

maximum operation pressure of 200 MPa[64]. Results obtained were processed using

CDApps and OriginLab. Secondary structure estimation from CD spectra was carried

out using the CAPITO CD analysis and plotting tool[38].

Sedimentation velocity analytical ultracentrifugation

Sedimentation velocity was measured in sodium phosphate buffer (45 mM NaPi, 250 mM NaCl, pH 7) using a Beckmann ProteomeLab XL-I at 20 °C and 24000 rpm. Data were collected at a wavelength of 418 nm. Date file time stamps were corrected using REDATE, and continuous sedimentation velocity coefficient (c(S)) distributions were produced using SEDFIT. Buffer density and viscosity were measured using an Anton-Paar rolling ball viscometer. The protein partial specific volume was calculated from the primary sequence ($\tilde{v}$ = 0.736 cm^3 g^{-1}).

PISA analysis of ABfr

A bioinformatics approach was adopted in order to identify potential dissociation states of ABfr under pressure. The Proteins, Interfaces, Structures and Assemblies (PISA) tool was used to calculate overall solvent accessible surface areas, solvation free energies (ΔG^{int}) and dissociation free energies (ΔG^{diss}) for stable subunit oligomers of ABfr[31,65,66]. The PISA analysis identifies thermodynamically stable assemblies of subunits based on interfacial interactions. For ABfr, only the fully assembled icositetramer and dimer were identified as stable quaternary structures in solution. The surface areas and free energies of these species are shown in Table S1. The free energy of dissociation, ΔG^{diss}, corresponds to the free energy difference between associated and dissociated states. A positive value indicates that the assembled state is stable under standard conditions.

SVD reconstruction of ABfr equilibrium pressure dissociation.

SVDPLOT and Ultrascan II were used to produce a set of basis eigenvectors and eigenvalues for the ABfr dataset (Figure S1)[67]. A non-parameterised runs test was

used to identify non-random curves in the eigenvector set[68]. Eigenvectors with $p <$

0.05 were deemed to be non-random, yielding 12 significant eigenvectors. Inspection

of the ABfr eigenvectors revealed that those with the highest two eigenvalues are

smooth curves reminiscent of scattering form factors, and so are likely to contain

structural information corresponding to the initial icositetramer and oligomeric

dissociation products. The subsequent curves are structured but contain significant

noise, and may contain contributions from minor species as well as background

components due to imperfect background subtraction. The data were then

reconstructed incrementally by adding eigenvectors to the model in order of

decreasing significance. The root mean squared deviation between the reconstructed

datasets and the experimental curves was calculated at each stage (Figure S2).

Acknowledgements

This work was supported at the University of Bristol by the Bristol Centre for Functional

Nanomaterials (EPSRC Doctoral Training Centre Grant EP/G036780/1) through a

studentship for K.L.V. We acknowledge Diamond Light Source for time on I22 under

proposals SM8237, SM9367, and SM11615, for time on B21 under proposals

SM10054, SM1318 and SM16020, and for time on B23 under proposal SM14069.

Author Contributions

J.L.R.A and A.W.P conceived the project; K.L.V., D.W., B.C., D.T., V.T., and

A.J.S. performed the experiments; K.L.V., B.C., R.R., A.J.S., J.L.R.A. and

A.W.P. discussed the results; K.L.V. and J.L.R.A. wrote the manuscript.

Supporting Information

PISA analysis, detailed AUC data, structural models and additional SAXS data including single value decomposition, calculated P(r) distributions, OLIGOMER models, ABfr dissociation data and background subtraction examples are provided in the supporting information.

References

1. Bhaskar, S. & Lim, S. Engineering protein nanocages as carriers for biomedical applications. *NPG Asia Materials* **9**, e371–e371 (2017).

2. Kanekiyo, M. *et al.* Self-assembling influenza nanoparticle vaccines elicit broadly neutralizing H1N1 antibodies. *Nature* **499**, 102–106 (2013).

3. Ren, H., Zhu, S. & Zheng, G. Nanoreactor design based on self-assembling protein nanocages. *Int. J. Mol. Sci.* **20**, (2019).

4. Maity, B., Fujita, K. & Ueno, T. Use of the confined spaces of apo-ferritin and virus capsids as nanoreactors for catalytic reactions. *Curr. Opin. Chem. Biol.* **25**, 88–97 (2015).

5. Douglas, T. & Stark, V. T. Nanophase cobalt oxyhydroxide mineral synthesized within the protein cage of ferritin. *Inorg. Chem.* **39**, 1828–1830 (2000).

6. Yamashita, I., Hayashi, J. & Hara, M. Bio-template Synthesis of Uniform CdSe Nanoparticles Using Cage-shaped Protein, Apoferritin. *Chem. Lett.* **33**, 1158–1159 (2004).

7. Ueno, T. *et al.* Size-selective olefin hydrogenation by a Pd nanocluster provided in an apo-ferritin cage. *Angew. Chemie - Int. Ed.* **43**, 2527–2530 (2004).

8. Douglas, T. *et al.* Protein engineering of a viral cage for constrained nanomaterials synthesis. *Adv. Mater.* **14**, 415–418 (2002).

9. He, D. & Marles-Wright, J. Ferritin family proteins and their use in bionanotechnology. *N. Biotechnol.* **32**, 651–657 (2015).

10. Jutz, G., Van Rijn, P., Santos Miranda, B. & Böker, A. Ferritin: A versatile building block for bionanotechnology. *Chem. Rev.* **115**, 1653–1701 (2015).

11. Putri, R. M. *et al.* Structural Characterization of Native and Modified Encapsulins as Nanoplatforms for in Vitro Catalysis and Cellular Uptake. *ACS Nano* **11**,

484   12796–12804 (2017).

485   12.   Choi, S. H., Kwon, I. C., Hwang, K. Y., Kim, I. S. & Ahn, H. J. Small heat shock

486   protein as a multifunctional scaffold: Integrated tumor targeting and caspase

487   imaging within a single cage. *Biomacromolecules* **12**, 3099–3106 (2011).

488   13.   Azuma, Y., Edwardson, T. G. W. & Hilvert, D. Tailoring lumazine synthase

489   assemblies for bionanotechnology. *Chemical Society Reviews* **47**, 3543–3557

490   (2018).

491   14.   Butterfield, G. L. *et al.* Evolution of a designed protein assembly encapsulating

492   its own RNA genome. *Nature* **552**, 415–420 (2017).

493   15.   Malay, A. D. *et al.* An ultra-stable gold-coordinated protein cage displaying

494   reversible assembly. *Nature* **569**, 438–442 (2019).

495   16.   Swift, J., Butts, C. A., Cheung-Lau, J., Yerubandi, V. & Dmochowski, I. J.

496   Efficient Self-Assembly of Archaeoglobus fulgidus ferritin around metallic cores.

497   *Langmuir* **25**, 5219–5225 (2009).

498   17.   Sana, B., Johnson, E. & Lim, S. The unique self-assembly/disassembly property

499   of Archaeoglobus fulgidus ferritin and its implications on molecular release from

500   the protein cage. *Biochim. Biophys. Acta - Gen. Subj.* **1850**, 2544–2551 (2015).

501   18.   Nasrollahi, F. *et al.* Incorporation of Graphene Quantum Dots, Iron, and

502   Doxorubicin in/on Ferritin Nanocages for Bimodal Imaging and Drug Delivery.

503   *Adv. Ther.* **3**, 1900183 (2020).

504   19.   Fletcher, J. M. *et al.* Self-assembling cages from coiled-coil peptide modules.

505   *Science (80-.).* **340**, 595–599 (2013).

506   20.   Peng, T. & Lim, S. Trimer-based design of pH-responsive protein cage results

507   in soluble disassembled structures. *Biomacromolecules* **12**, 3131–3138 (2011).

21.   Dalmau, M., Lim, S. & Wang, S. W. Design of a pH-dependent molecular switch

in a caged protein platform. *Nano Lett.* **9**, 160–166 (2009).

22.   Pontillo, N., Pane, F., Messori, L., Amoresano, A. & Merlino, A. Cisplatin

encapsulation within a ferritin nanocage: A high-resolution crystallographic

study. *Chem. Commun.* **52**, 4136–4139 (2016).

23.   Liu, X. *et al.* Apoferritin-CeO2nano-truffle that has excellent artificial redox

enzyme activity. *Chem. Commun.* **48**, 3155–3157 (2012).

24.   Skouri-Panet, F., Quevillon-Cheruel, S., Michiel, M., Tardieu, A. & Finet, S.

sHSPs under temperature and pressure: The opposite behaviour of lens alpha-

crystallins and yeast HSP26. *Biochim. Biophys. Acta - Proteins Proteomics*

1764, 372–383 (2006).

25.   White, H. E. *et al.* Multiple Distinct Assemblies Reveal Conformational Flexibility

in the Small Heat Shock Protein Hsp26. *Structure* **14**, 1197–1204 (2006).

26.   Zhang, T. *et al.* Effect of high hydrostatic pressure (HHP) on structure and

activity of phytoferritin. *Food Chem.* **130**, 273–278 (2012).

27.   Wang, Q. *et al.* High hydrostatic pressure encapsulation of doxorubicin in ferritin

nanocages with enhanced efficiency. *J. Biotechnol.* **254**, 34–42 (2017).

28.   Brooks, N. J. *et al.* Automated high pressure cell for pressure jump x-ray

diffraction. *Rev. Sci. Instrum.* **81**, 064103 (2010).

29.   Svergun, D., Barberato, C. & Koch, M. H. CRYSOL - A program to evaluate X-

ray solution scattering of biological macromolecules from atomic coordinates. *J.*

Appl. Crystallogr. **28**, 768–773 (1995).

30.   Konarev, P. V., Volkov, V. V., Sokolova, A. V., Koch, M. H. J. & Svergun, D. I.

PRIMUS: A Windows PC-based system for small-angle scattering data analysis.

J. Appl. Crystallogr. **36**, 1277–1282 (2003).

31.   Krissinel, E. & Henrick, K. Inference of Macromolecular Assemblies from

Crystalline State. *J. Mol. Biol.* **372**, 774–797 (2007).

32. Stefanini, S., Vecchini, P. & Chiancone, E. On the Mechanism of Horse Spleen Apoferritin Assembly: A Sedimentation Velocity and Circular Dichroism Study. *Biochemistry* **26**, 1831–1837 (1987).

33. Gerl, M. & Jaenicke, R. Mechanism of the self-assembly of apoferritin from horse spleen - Cross-linking and spectroscopic analysis. *Eur. Biophys. J.* **15**, 103–109 (1987).

34. Banyard, S. H., Stammers, D. K. & Harrison, P. M. Electron density map of apoferritin at 2.8-Å resolution. *Nature* **271**, 282–284 (1978).

35. Sato, D. *et al.* Ferritin Assembly Revisited: A Time-Resolved Small-Angle X-ray Scattering Study. *Biochemistry* **55**, 287–293 (2016).

36. Kilic, M. a, Spiro, S. & Moore, G. R. Stability of a 24-meric homopolymer: comparative studies of assembly-defective mutants of Rhodobacter capsulatus bacterioferritin and the native protein. *Protein Sci.* **12**, 1663–1674 (2003).

37. Andrews, S. C. *et al.* Physical, chemical and immunological properties of the bacterioferritins of Escherichia coli, Pseudomonas aeruginosa and Azotobacter vinelandii. *Biochim. Biophys. Acta - Protein Struct. Mol. Enzymol.* **1078**, 111–116 (1991).

38. Wiedemann, C., Bellstedt, P. & Görlach, M. CAPITO - A web server-based analysis and plotting tool for circular dichroism data. *Bioinformatics* **29**, 1750–1757 (2013).

39. Weber, G. Thermodynamics of the association and the pressure dissociation of oligomeric proteins. *J. Phys. Chem.* **97**, 7108–7115 (1993).

40. Atkins, P. & de, P. J. Atkins' Physical Chemistry, 7th Edition. *Oxford Univ. Press* (2002).

41.   Ward, A. B., Sali, A. & Wilson, I. A. Integrative Structural Biology. *Science (80-.*

). **339**, 913–915 (2013).

42.   Brooks-Bartlett, J. C. *et al.* Development of tools to automate quantitative

analysis of radiation damage in SAXS experiments. *J. Synchrotron Radiat.* **24**,

63–72 (2017).

43.   Kikhney, A. G. & Svergun, D. I. A practical guide to small angle X-ray scattering

(SAXS) of flexible and intrinsically disordered proteins. *FEBS Lett.* **589**, 2570–

2577 (2015).

44.   Sato, D. *et al.* Electrostatic Repulsion during Ferritin Assembly and Its Screening

by Ions. *Biochemistry* **55**, 482–488 (2016).

45.   Watt, R. K., Hilton, R. J. & Graff, D. M. Oxido-reduction is not the only

mechanism allowing ions to traverse the ferritin protein shell. *Biochimica et*

Biophysica Acta - General Subjects **1800**, 745–759 (2010).

46.   Bakker, G. R. & Boyer, R. F. Iron incorporation into apoferritin. The role of

apoferritin as a ferroxidase. *J. Biol. Chem.* **261**, 13182–13185 (1986).

47.   Rui, H., Rivera, M. & Im, W. Protein dynamics and ion traffic in bacterioferritin.

Biochemistry **51**, 9900–9910 (2012).

48.   Kegel, W. K. & van der Schoot, P. Competing Hydrophobic and Screened-

Coulomb Interactions in Hepatitis B Virus Capsid Assembly. *Biophys. J.* **86**,

3905–3913 (2004).

49.   Silva, J. Pressure Stability of Proteins. *Annu. Rev. Phys. Chem.* **44**, 89–113

(1993).

50.   Silva, J. L., Foguel, D. & Royer, C. A. Pressure provides new insights into protein

folding, dynamics and structure. *Trends Biochem. Sci.* **26**, 612–618 (2001).

51.   Silva, J. L. & Weber, G. Pressure-induced dissociation of brome mosaic virus.

J. Mol. Biol. **199**, 149–159 (1988).

52. Leimkühler, M., Goldbeck, A., Lechner, M. D. & Witz, J. Conformational changes

preceding decapsidation of bromegrass mosaic virus under hydrostatic

pressure: A small-angle neutron scattering study. *J. Mol. Biol.* **296**, 1295–1305

(2000).

53. Leimkühler, M. *et al.* The formation of empty shells upon pressure induced

decapsidation of turnip yellow mosaic virus. *Arch. Virol.* **146**, 653–667 (2001).

54. Teale, F. W. J. Cleavage of the haem-protein link by acid methylethylketone.

BBA - Biochim. Biophys. Acta **35**, 543 (1959).

55. Nayuk, R. & Klaus, H. Formfactors of Hollow and Massive Rectangular

Parallelepipeds at Variable Degree of Anisometry. *Zeitschrift für Physikalische*

Chemie **226**, 837 (2012).

56. Willies, S. C., Isupov, M. N., Garman, E. F. & Littlechild, J. A. The binding of

haem and zinc in the 1.9 Å X-ray structure of Escherichia coli bacterioferritin. *J.*

Biol. Inorg. Chem. **14**, 201–207 (2009).

57. Hingorani, K. *et al.* Photo-oxidation of tyrosine in a bio-engineered

bacterioferritin 'reaction centre' - A protein model for artificial photosynthesis.

Biochim. Biophys. Acta - Bioenerg. **1837**, 1821–1834 (2014).

58. Ardejani, M. S., Li, N. X. & Orner, B. P. Stabilization of a protein nanocage

through the plugging of a protein-protein interfacial water pocket. *Biochemistry*

50, 4029–4037 (2011).

59. Wong, S. G. *et al.* Structural and mechanistic studies of a stabilized subunit

dimer variant of Escherichia coli bacterioferritin identify residues required for

core formation. *J. Biol. Chem.* **284**, 18873–18881 (2009).

60. Fan, R., Boyle, A. L., Vee, V. C., See, L. N. & Orner, B. P. A helix swapping

study of two protein cages. *Biochemistry* **48**, 5623–5630 (2009).

61.   Hargrove, M. S. *et al.* Stability of Myoglobin: A Model for the Folding of Heme
Proteins. *Biochemistry* **33**, 11767–11775 (1994).

62.   Andrews, S. C. *et al.* Overproduction, purification and characterization of the
bacterioferritin of Escherichia coli and a C-terminally extended variant. *Eur. J.*
Biochem. **213**, 329–338 (1993).

63.   Basham, M. *et al.* Data Analysis WorkbeNch (DAWN). *J. Synchrotron Radiat.*
22, 853–858 (2015).

64.   Hussain, R., Jávorfi, T. & Siligardi, G. Circular dichroism beamline B23 at the
Diamond Light Source. *J. Synchrotron Radiat.* **19**, 132–135 (2012).

65.   De Val, N., Declercq, J. P., Lim, C. K. & Crichton, R. R. Structural analysis of
haemin demetallation by L-chain apoferritins. *J. Inorg. Biochem.* **112**, 77–84
(2012).

66.   Chen, C. R. & Makhatadze, G. I. ProteinVolume: calculating molecular van der
Waals and void volumes in proteins. *BMC Bioinformatics* **16**, 101 (2015).

67.   Demeler, B. *et al.* Characterization of size, anisotropy, and density heterogeneity
of nanoparticles by sedimentation velocity. *Anal. Chem.* **86**, 7688–7695 (2014).

68.   Wald, A. & Wolfowitz, J. On a Test Whether Two Samples are from the Same
Population. *Ann. Math. Stat.* **11**, 147–162 (1940).

69.   Hansen, S. BayesApp: A web site for indirect transformation of small-angle
scattering data. *J. Appl. Crystallogr.* **45**, 566–567 (2012).

632
Figure 1. Pressure dissociation of ABfr under equilibrium conditions between 0.1 and 450 MPa
measured using high pressure synchrotron radiation SAXS and circular dichroism. (A)
Reciprocal space SAXS profiles, **(B)** Kratky plots, **(C)** pair distance distribution (P(r)) functions, **(D)**
change in radius of gyration, R_g, with pressure, **(E)** change in solution oligomer composition with
pressure and **(F)** circular dichroism spectra. SAXS data were collected between 0.1 MP (red) and 450
MPa (blue) at a protein concentration of 5 mg mL^{-1} in 45 mM sodium phosphate buffer (pH 7). Real
space transformations were performed using BAYESAPP, which uses Bayesian analysis to select
parameters such as D_{max} and data noise level.[69] I(0) and R_g were calculated from real space data. I(0)
was normalised to a maximum value of 1. Component volume fraction versus pressure generated from
OLIGOMER models of ABfr dissociation. The volume fractions of the icositetramer, *n*-mer and dimer
are shown in black, blue and red respectively. The intermediate oligomer states are hexamer (solid
line), octamer (dashed line) and dodecamer (dotted line). High-pressure circular dichroism data was
collected between 0.1 (red) and 200 MPa (yellow) at a protein concentration of 0.03 mg mL^{-1}, 45 mM
sodium phosphate, pH 7.

662
Figure 2. Reassociation of ABfr following pressure induced dissociation measured by SAXS,
AUC and TEM. (A) Changes in ABfr R_g pre, during and post- pressurization measured by SAXS.
Pressure cycle was performed at 25°C NaPi (45 mM, pH 7, I = 123 mM). **(B)** Pair distance distribution
(P(r)) functions for ABfr pre- (black), during (red) and post- pressurisation (blue). **(C)** Sedimentation
velocity c(S) distribution for ABfr pre-pressurisation (black) and post-pressurisation (red). Sedimentation
velocity was measured at a protein concentration of approximately 50 μM in sodium phosphate buffer
(45 mM NaPi, 250 mM NaCl, pH 7) using a Beckmann ProteomeLab XL-I at 20°C and 24000 rpm. Data
was collected at a wavelength of 418 nm. Data file time stamps were corrected using REDATE, and
continuous sedimentation coefficient (c(S)) distributions were fitted using SEDFIT. Buffer density (ρ =
1.003 g cm-3) and viscosity (η = 1.0107 mPa s-1) were measured using an Anton-Paar rolling ball
viscometer. **(D)** Negative stain (phosphotungstic acid) TEM images of ABfr pre-pressurisation and **(E)**
and post-pressurisation (scale bars = 100 nm). **(F)** Change in normalised Kratky intensity
($I_{(q=1.1)}/I_{(0)}$x(q^*R_g)^2) with pre, during and post- pressurization. Dotted black trace shows pre-
pressurisation data, yellow – red traces show pressurised data at 0, 120 and 300s, light blue – dark
blue traces show post pressurisation data with increasing time.
678

679
680 **Figure 3. Changes in ABfr R_g pre, during and post- pressurisation.** Pressure cycles were performed
681 at 5 ˚C **(A)** and 25˚C **(B)** in H_2O (I = 0 mM, black), NaPi (45 mM, pH 7, I = 123 mM, blue) and in NaPi
682 (45 mM, pH 7) + NaCl (250 mM) (I = 373 mM, red). Pressure level depicted as hashed region.
683

685
Figure 4. Physicochemical characterization of ABfr and AABfr under ambient pressure. (A)
UV/visible spectra of ABfr (black) and AABfr (blue). UV-visible spectra were recorded measured at a
protein concentration of approximately 50 μM in sodium phosphate buffer (45 mM NaPi, 250 mM NaCl,
pH 7). Curves are normalised to A280 = 1 to highlight differences in heme absorbance. **(B)** SV-AUC
c(s) distributions for ABfr (black) and AABR (blue). Sedimentation velocity was measured at a protein
concentration of approximately 50 μM in potassium phosphate buffer (45 mM KPi, 250 mM NaCl, pH
7) using a Beckmann ProteomeLab XL-I at 20˚C and 24000 rpm. Data was collected at a wavelength
of 280 nm. Data file time stamps were corrected using REDATE, and continuous sedimentation
coefficient (c(S)) distributions were fitted using SEDFIT. Buffer density (ρ = 1.003 g cm^{-3}) and viscosity
(η = 1.0107 mPa 865-) were measured using an Anton-Paar rolling ball viscometer. The protein partial
specific volume was calculated from the primary sequence ($\tilde{v}$ = 0.736 cm^3 g^{-1}). **(C)** HPLC-SAXS profiles
and **(D)** Kratky plots for ABfr icositetramer (black) and AABfr icositetramer (blue) and dimer (red). **(E)**
Ab initio bead model of ABfr (icositetramer, orange) and AABfr (icositetramer and dimer, blue), overlaid
with corresponding crystal structures (2VXI and 4CVP)[56,57]. Real space transformations were performed
using ScÅtter. The maximum diameter was determined by selecting values that resulted in high
reciprocal fit quality, and produced smooth, oscillation-free, real-space functions that decreased
smoothly to zero at high radius. A constant background was applied in the transformation, and real
space distributions were refined using the L1 norm of the Moore coefficients as a regularisation
target.The *ab initio* models were produced from refined pair distance distribution functions using
DAMMIF, and are DAMAVER averages of 23 runs. The models and crystal structures were visualized
using PyMOL. **(F)** Thermal denaturation far-UV circular dichroism spectra and fits for ABfr (open circles)
and AABfr (black circles). Data were collected at B23, Diamond Light Source, UK. Measurements were
performed in potassium phosphate buffer (45 mM, pH 7) at a protein concetnration of 0.5 g L^{-1}. Raw
data was converted to mean residue elipticity and secondary structure analysis was performed using
CAPITO.

Figure 5. Pressure dissociation of AABfr under equilibrium conditions between 0.1 and 450 MPa.
(A) reciprocal space SAXS profiles, **(B)** Pair distance distribution (P(r)) functions, **(C)** Kratky plots and
(D) Radius of gyration, R_g. SAXS data was collected between 0.1 MP (red) and 450 MPa (blue) at a
protein concentration of 5 mg mL^{-1} in 45 mM sodium phosphate buffer (pH 7). Real space
transformations were performed using BAYESAPP, which uses Bayesian analysis to select parameters
such as D_{max} and data noise level.[69] I(0) and R_g were calculated from real space data. I(0) was
normalised to a maximum value of 1.

723