APPLICATION OF DIGITAL COLORIMETER FOR PRELIMINARY CHARACTERIZATION OF GOLD NANOPARTICLE SWARMS PRODUCED BY *Termitomyces heimii* USING A NOVEL BIOINSPIRED MICROFLUIDICS ASSAY

Sujata Dabolkar and Nandkumar M. Kamat*

Mycological Laboratory, Department of Botany, Goa University, Taleigao Goa-403206, India

*Corresponding author E-mail address: nandkamat@gmail.com

ABSTRACT

In our laboratory work extending over several years we have successfully studied the biogeochemical role of termite mounds and their occupants the termites and the exosymbiont fungus-*Termitomyces*. Fungi appear to be promising for large scale production of nanoparticles (NPs) as these are simpler to grow both in laboratory and at industrial scale. This paper reports a novel microfluidics based assay system to detect Gold bioreduction capacity of different tissues in tissue based and cell free environment. Using sterile microtest well, different tissues such as umbo, pileus, lamellae, stipe context, stipe epicutis, pseudorrhiza context, pseudorrhiza epicutis of *Termitomyces heimii* mature fruitbodies were tested with 200μl chloroauric acid (one mM) and after an interval of 5,10, 15, 30, 45, 60, 120 min and 12, 24 and 48 hours. The results in terms production of distinct nanoparticles were directly visualized microscopically and using mobile based digital colorimeter. Membrane filtered sterile water soluble extracts (SWSE) from the same tissues were similarly screened. The results manifested by mono and polydisperse GNPs and

22   microparticles of mixed size groups demonstrated that cell free system can be potentially useful

23   for bioinspired fabrication of GNPs. Further work in this direction is in progress using several

24   *termitomyces* cultures.

25   Keywords: Microfluidic assay, Gold, Bio reduction, Termitophilic mushrooms

Introduction

In poor and under developed countries like India and resource starved universities find it difficult to have easy excess to expensive instrumentation for characterization of Gold nanoparticles (GNPs). However now the new Apps such as digital colorimeter from laboratory tools make it possible to rapidly detect GNP formation and perform quick and simple analysis. Having seen the chemical creativity of termitophilic mushrooms in our laboratory we aimed to use microfluidic assay for rapid screening of gold bioreduction system in this species. *Termitomyces heimii* being the most dominant species and state mushroom of Goa we used this for our study. However, it was not easy to rapidly detect and characterize swarms of gold micro and nanoparticles. It was at this point that we came across a mobile based digital colorimeter which was found useful in analysis of the GNP swarms and obtain spectra in visible band. Swarm are formed by the collective behavior of GNPs. Inspired by animal interactions, the autonomous movement and collective behavior of synthetic nanomaterials are of considerable interest as they have implications for the future in nanomachinery, nanomedicine, and chemical sensing (Kagan et al., 2011). Values such as CIE LAB, Chroma, Hue°, RGB, color names, real time visible spectra (400 nm to 700 nm) can be recorded using this digital tool. The CIELAB color space (also known as CIE L*a*b* or sometimes abbreviated as simply "Lab" color space) is a color space defined by the International Commission on Illumination (CIE) in 1976. It expresses color as three values where L* stands for the lightness from black to white, a* from green to red, and b* from blue to yellow. Chroma (Saturation) may be defined as the strength or dominance of the hue, the quality of a color's purity, intensity or saturation (Solomon & Breckon 2011). Hue is common distinction between colors positioned around a color wheel. On the outer edge of the hue wheel are the intensely saturated hues whereas towards the center of the color wheel no hue dominates and

becomes less and less saturated. The RGB color model is an additive color model in which red,

green and blue light are added in various ways to reproduce a broad array of colors (Meruga et al.,

2014). Finally, it has been shown that absorbance peaks of GNPs are correlated to their size and

we aimed to test the ability of digital colorimeter to get an idea of size distribution of GNPs in the

swarms. Statistical importance of the data was obtained using jvenn, a new JavaScript library

(http://bioinfo.genotoul.fr/jvenn/example.html) which processes lists and produces Venn

diagrams. Venn diagrams with more than four lists, are much harder to interpret. To solve this

problem, the classical or Edwards-Venn representation introduces new shapes providing a clearer

view (Philippe Bardou et al., 2014). Jvenn enables to compare up to six lists and updates the

diagram automatically when modifying the lists content.

Methodology

Sample collection

Termitomyces heimii being the most dominant species in Goa and state mushroom of Goa we use

this it for our study. Fresh, healthy specimens of *Termitomyces heimii* Natarajan (1979) were

collected from fields of Taleigao, Goa during monsoon season, 2019 and taxonomically identified

using standard published *Termitomyces* keys (Heim R. 1942,1977; Natarajan,1979) (**Fig.1**). Dried

herbarium is deposited in Goa university fungal herbarium collection.

Processing of the specimens

T. heimii specimens were cleaned with 95% ethanol (v/v) upto 30 seconds and photographed. Specific processing of each part of the fruitbody ie umbonal tissue, pileus context, lamellae, stipe context, stipe epicutis, pseudorrhiza context, pseudorrhiza epicutis was carried out. Using a sterile forceps small pieces of the tissues were transferred into a microtest plate (Tarson, Mumbai) with 96 wells having volumetric capacity of 420µl under a laminar air flow bench. Care was taken to use tissue identical fragments appropriate equivalent to 200 µm. Tissues were tested with 200µl chloroauric acid (one mM) (**Fig. 2**) and after an interval of 5,10, 15, 30, 45, 60, 120 minutes and 12, 24 and 48 hours. Nine replicates of each tissue was performed.

Preparation of extracts

Sterile water soluble extracts (SWSE) (**Fig. 3**) were prepared by grinding in sterile mortar and pestle, centrifuged and membrane filtered (0.22µm pore size, 30mm diameter-HIMedia laboratories). The SWSE were stored at refrigerated temperature in sterile test tubes. The extracts (210 µl) and chloroauric acid (210 µl) were mixed in a equal proportion in a well of microwell test plate and checked after interval of 5,10,15,25,30,45,60,120 minutes and after 12, 24, 48 hours. The assay design was similar to fig.3.

Stereomicroscopic visualization of swarms

The microtest plate with the GNP swarms was visualized under stereomicroscope (Olympus SZ51, model SZ2-ILST, olympus corporation, Tokyo, Japan) (**Fig.4**). Care was taken to bring the swarm view under uniform illumination in bright light.

Use of Digital Colorimeter App

Scanning of the swarms with 12 MP plus dual rear (F 1.5/ F 2.4) camera on Samsung Galaxy Note

9 with colorimeter software (http://researchlabtools.blogspot.com/) (Ravindranath et al, 2018)

version 3.5.2, developed by Research Lab Tools, São Paulo, Brazil; purchased from Google Play)

was installed on an android smartphone.

Digital color analysis and colorimetric data

The color terminology is used according to color data based of the App. Colorimeter software was

used to record values such as CIE LAB, Chroma, Hue°, RGB, color names, real time visible spectra

(400 nm to 700 nm). The App allows online and offline analysis of samples.

Use of Venn diagram

Venn diagrams are commonly used to display list comparison. However, when the number of input

lists exceeds four, the diagram becomes difficult to read. Alternative layouts and dynamic display

features can improve its use and its readability. The jvenn library accepts three different input

formats "Lists", "Intersection counts" and "Count lists". For "Intersection counts", the lists are

given a label ("A" or "B") which is used to make the correspondence between the list and its count.

Finally, "Count lists" provide a count number for each element of a list. Hence, with "Count lists"

the figures presented in the diagram correspond to the sums of counts of all elements shared

between lists For "Lists" and "Count lists", jvenn computes the intersection counts and displays

the chart (http://bioinformatics.psb.ugent.be/). Vein diagrams were plotted using tissues and

lambda max values.

Results

Fresh, healthy *Termitomyces heimii* which is dominant species in Goa were successfully obtained

and were taxonomically identified using standard published *Termitomyces* keys (Heim R. 1942,

1977; Natarajan,1979; DeSouza & Kamat, 2018, 2019). GNP swarms were detected in all

treatments and could be visualized easily under stereomicroscope (**Fig.5 & Fig 6**). Umbonal tissue

produced grey GNP swarms and color values as shown in table 1. Overall the color range is from

grey to juniper green. The chromaticity values showed a difference and chroma values ranged from

4 to 47 whereas Hue differed from 40 to 199. The R value varied from 131 to 177, G from 102 to

187 whereas B from 27 to 191. Detail treatment of absorbance value is given in table 3. Similarly

the colors and color analysis and absorbance values of other tissues and SWSE are shown in **Table**

1 and **Table 2**.

Table 3 shows 30 different peaks obtained using each tissue and extract. Absorbance value ranged

from 455 nm to 644 nm. Stipe exhibited most promising results with peaks at 455, 510, 642 nm.

Table 4 gives approximate GNP size range diameter which ranged from 5 nm to 100 nm. It was

noticed that only extract system was producing GNP swarms at wavelength of 455, whereas only

umbonal tissue produced maximum absorption at 461 nm similar results were obtained in

remaining reaction as shown in table 3. The fractal correlation are shown in venn diagram analysis

are shown (**Fig7a-7f**).

Discussion

This paper reports a novel microfluidics based assay system to detect Gold bioreduction capacity

of different tissues in Termitophilic mushrooms (Kalia & Kaur, 2018; DeSouza & Kamat, 2017;

de Souza & Kamat, 2018, 2019) in tissue based and cell free environment. Umbonal tissue, pileus

context, lamellae, stipe context, stipe epicutis, pseudorrhiza context, pseudorrhiza epicutis of

Termitomyces heimii mature fruitbodies successfully produced GNPs for the first time. We were

successful in producing membrane filtered SWSE from same tissues and also successful in

producing GNPs from the same extracts. Our assay can be useful to carry out large number of

replicates, under sterile forms, microtest plates can be directly visualized due to its transparent

makeup and swarms can be directly characterized under stereomicroscope. Small amounts of gold

solutions and small amount of SWSE can be tested this microfluidic assay. This is useful in rapid

screening of large number of biological or microbiological gold bioreduction systems.

In case of tissues the colour varied from grey, rock blue, ship cove blue, juniper green to

saddle brown where as in case of SWSE it was willow grove, drim grey dark grey, charcoal grey

to brown gramble. For small (~30nm) monodisperse gold nanoparticles, the surface plasmon

resonance phenomenon causes an absorption of light in the blue-green portion of the spectrum

(~450 nm) while red light (~700 nm) is reflected, yielding a rich red color. As particle size

increases, the wavelength of surface plasmon resonance related absorption shifts to longer, redder

wavelengths (https://www.sigmaaldrich.com/). Larger the size, darker is the color and may also

shift to blue in case of colloidal particles (Jana et al., 2001; Haiss et al., 2007; Martinez et al.,

2012). Absorbance reading tells the composition and size of NPs (Doak et al., 2010). SWSE

prepared from same tissue do not produce GNPs of same size or with same concentration. The

GNP swarm population is represented by 18 different size groups ranging from less than 5 nm to

100 nm. The concentration of nanoparticles as function of optical absorbance ranges from 0.12 to

0.8 indicating that some bioreduction systems are much more efficient in production of GNPs this

includes GNPs of the size of less than 5 to 15 nm.

It was found that stipe was showing most promising results in case of both tissue and

SWSE. CIE chromaticity values ranged from L (16-75), a (3-33) and b (1-46) thus indicating the

lightness from black to white, green to red and blue to yellow (Cheng et al.,2014). Choma values

ranged from 4 to 47 and hue values from 40 to 199 indicating the strength or dominance of the

hue, the quality of a color's purity, intensity or saturation.

GNPs produced using tissue showed low absorbance from min 0.10 to max 0.5 whereas

SWSE produced GNP with absorbance ranging from 0.1 to 0.8 thereby indicating a more efficient

system in cell free environment. Low absorbance 0.19 for intact tissue indicating low concentration

of GNP swarms. Mean absorbance produced by treatment with extract 0.40 indicating almost

double the bioreduction efficiency of intact tissue incase of GNP production. Thus, cell free

environment is much better system to produce polydisperse GNP swarms in higher concentration.

In all 30 different peaks ranging from 455 to to 644 nm were obtained using in each tissue

and extract thus indicating the presence of nanoparticle of size 5 nm to 100 nm

(https://www.sigmaaldrich.com). Mushrooms are rich in proteins and have high availability of the

amino acids lysine, tryptophan, glutamic acid and aspartic acid (Hsu et al., 2002). It is also reported

that certain mushroom extract contain polysaccharide/oligosaccharide complex (Cho et al., 2003).

FTIR studies have also shown the possible biomolecules responsible for capping and efficient

stabilization of the metal nanoparticles synthesized using mushroom extract (Philip, 2009). It was

noticed certain SWSE and tissues produced specific wavelength for example umbonal, pileaus

context, pseudorrhizal context extract system was producing GNP swarms at wavelength of 455,

whereas only umbonal tissue produced at 461 λmax. Similar results were obtained in remaining

reaction as shown in table 3. It was noticed that there is relationship between solubility and swarm

formation and it could be a different molecule based bioreduction system. Jvenn's statistics charts

give a simple and quick overview of the sizes of the different lists and of their overlaps. It permits

to compare different Venn diagrams. For biologists using different techniques in their experiment

or in their statistical analysis, jvenn enables to quickly extract the shared identifiers. numerous

features, dynamic behavior and graphical layout quality, jvenn can be efficiently used in many

cases to compare different sets of results and easily extract shared elements. Being a simple

JavaScript plug-in allows developers to embed it in any web environment.

Preliminary characterization of GNP swarms is important as in high throughput screening

system one cannot differentiate the most promising system and thus can be time consuming. Once

you carry out the preliminary results you zero down to the specific system to obtain the promising

system and then can go for final characterization of the GNPs. Preliminary results can also help in

standardization of the procedure and also there is no waste of resources.   In poor and under

developed countries like India and resource starve universities researchers find it difficult to have

easy excess to expensive instrumentation for characterization of GNPs. However now the new

Apps such as digital colorimeter from developers Laboratory tools make it possible to rapidly

detect GNP formation and perform quick analysis.

Conclusions

Our work clearly demonstrates that that simple and easy to use mobile digital Colorimeter Apps

can be used for primary optical characterization of swarms of Gold nanoparticles. This is useful in

rapid screening of large number of microbiological gold bioreduction systems. The spectral

absorbance profile detected in visible range also helps in understanding the presumptive size of

GNPs in swarms. For high throughput screening systems we recommend development of more

such mobile based apps. Our present approach has helped us to a fabricate to a very sensitive

Gold biosensor.

Acknowledgements

The authors would like to thank RNSB project for the support. This work was also supported by UGC SAP Phase III Biodiversity, Bioprospecting programme and Goa University Fungus Culture Collection GUFCC). First author also acknowledges UGC, NF OBC Junior Research fellowship. Thanks for guidance from Dr. Absar Ahmad director, interdisciplinary center for Nanotechnology AMU regarding potential of GNPs.

References

Bardou, P., Mariette, J., Escudié, F. et al. jvenn: an interactive Venn diagram viewer. BMC Bioinformatics. 15: 293 (2014). https://doi.org/10.1186/1471-2105-15-293

Cheng, X., Dai, D., Yuan, Z., Peng, L., He, Y. and Yeung, E.S., 2014. Color difference amplification between gold nanoparticles in colorimetric analysis with actively controlled multiband illumination. Analytical chemistry. 86(15): 7584-7592.

Cho, J., Kang, J.S., Long, P.H., Jing, J., Back, Y. and Chung, K.S., 2003. Antioxidant and memory enhancing effects of purple sweet potato anthocyanin and cordyceps mushroom extract. Archives of pharmacal research. 26(10): 821-825.

de Souza, R.A. and Kamat, N.M., 2018. Evaluation and characterization of pellet morphology of genus *Termitomyces heim* of a wild tropical edible mushroom. Journal of Pharmaceutical, Chemical and Biological Sciences. 6(4): 320-328.

de Souza, R.A. and Kamat, N.M., 2019. *Termitomyces* holomorph benefits from anomalous

Sulphur content in teleomorph. International Journal of Life scinces Research. 1 (186-192).

De Souza, R.A., Kamat, N.M. and Nadkarni, V.S., 2018. Purification and characterisation of a

sulphur rich melanin from edible mushroom *Termitomyces albuminosus Heim*. Mycology. 9(4):

296-306.

Doak, J., Gupta, R.K., Manivannan, K., Ghosh, K. and Kahol, P.K., 2010. Effect of particle size

distributions on absorbance spectra of gold nanoparticles. Physica E: Low-dimensional Systems

and Nanostructures. 42(5): 1605-1609.

D'Souza, R.A. and Kamat, N.M., 2017. Potential of FTIR spectroscopy in chemical

characterization of *Termitomyces* Pellets. Journal of Applied Biology & Biotechnology. 5(04):

080-084.

Haiss, W., Thanh, N.T., Aveyard, J. and Fernig, D.G., 2007. Determination of size and

concentration of gold nanoparticles from UV− Vis spectra. Analytical chemistry.79(11): 4215-

4221.

Heim, R., 1942. Nouvelles études descriptives sur les agarics termitophiles d'Afrique tropicale.

Arch. Mus. Natl. Hist. Nat. Paris. 6: 1-133.

Heim, R., 1977. Termites et champignons; les champignons termitophiles d'Afrique noire et d'Asie

meridionale.

Hsu, T.H., Shiao, L.H., Hsieh, C. and Chang, D.M., 2002. A comparison of the chemical

composition and bioactive ingredients of the Chinese medicinal mushroom DongChongXiaCao,

its counterfeit and mimic, and fermented mycelium of Cordyceps sinensis. Food chemistry. 78(4):

463-469.

http://bioinfo.genotoul.fr/jvenn/example.html

http://bioinformatics.psb.ugent.be/

http://researchlabtools.blogspot.com

https://www.sigmaaldrich.com

https://www.tedpella.com

Jana, N. R., Gearheart, L., & Murphy, C. J. (2001). Seeding growth for size control of 5− 40 nm

diameter gold nanoparticles. Langmuir. 17(22): 6782-6786.

Kagan, D., Balasubramanian, S., and Wang, J. (2011). Chemically triggered swarming of gold

microparticles. Angewandte Chemie International Edition, 50(2): 503-506.

Kalia, A. and Kaur, G., 2018. Biosynthesis of Nanoparticles Using Mushrooms. In Biology of

Macrofungi. 351-360. Springer, Cham.

Meruga, Jeevan Manikyarao, Aravind Baride, William Cross, Jon J. Kellar, and P. Stanley May.

"Red-green-blue printing using luminescence-upconversion inks." *Journal of Materials Chemistry*

C 2, no. 12 (2014): 2221-2227.

Natarajan, K., 1979. South Indian Agaricales V: *Termitomyces heimii*. Mycologia. 71(4): 853-855.

Philip, D., 2009. Biosynthesis of Au, Ag and Au–Ag nanoparticles using edible mushroom extract.

Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy. 73(2): 374-381.

Sen, I.K., Maity, K. and Islam, S.S., 2013. Green synthesis of gold nanoparticles using a glucan of

an edible mushroom and study of catalytic activity. Carbohydrate polymers. 91(2): 518-528.

Solomon, C. and Breckon, T., 2011. *Fundamentals of Digital Image Processing: A practical*

approach with examples in Matlab. John Wiley & Sons.

Figures and Tables

Fig.1. Scheme for specific processing of different fruitbody parts

Fig.2. Design of Microfluidics based assay using Microtest plate

Fig.3. Homogenized aquous extracts from different tissues

Fig.4: Direct Acquisition of images for stereomicroscopic characterization

Fig.5. Positive bioreduction obtained with homogenized tissues as indicated by color changes

Fig.6. Positive bioreduction with cell free membrane filtered SWSE indicated by change in colour,

yellow is control

Fig.7 (a-f). 7(a-c)- The shape corresponding to the lists involved in the intersection are highlighted

in case of tissue, (a-455-463, b-510-540, c-632-644 λmax). 7(d-f)- The shape corresponding to the

lists involved in the intersection are highlighted in case of extracts, (a-455-463 λmax, b-510-540,

c-632-644 λmax).

Tables

Table 1 & 2: Colour analysis and Colorimetric absorption characterization of presumptive GNP

swarms

Table 3: Visible spectral characteristics of GNP swarms using *T. heimii* tissue sample and SWSE

Table 4: Approximate GNP size range diameter

317   Fig.1. Scheme for specific processing of different fruitbody parts

319   Fig.2. Design of Microfluidics based assay using Microtest plate

321   Fig.3. Homogenized aquous extracts from different *T.heimii* fruit body tissue

326   Fig.4. Direct Acquisition of images for stereomicroscopic characterization

329   **Fig.5.** Positive bioreduction obtained with homogenized tissues as indicated by color changes

331   **Fig.6.** Positive bioreduction with cell free membrane filtered SWSE indicated by change in

332   colour, yellow is control

Fig.7 (a-f): 7(a-c)- The shape corresponding to the lists involved in the intersection are highlighted in case of tissue,(a-455-463 λmax,b-510-540,c-632-644). 7(d-f)- The shape corresponding to the lists involved in the intersection are highlighted in case of extracts,(a-455-463 λmax,b-510-540,c-632-644).

Table 1: Colour analysis and Colorimetric absorption characterization of presumptive GNP swarms

Mushroom Tissues	GNPs swarms (X 6000)	Colour	CIE Chromaticity values	Chroma	Hue	R, G, B value	Absorbance (nm)	Absorbance values
		Grey	L=75 a=4 b=1	4	174	177, 187, 186		463 (0.18), 520 (0.18), 641 (0.22)
		Rock Blue	L=73 a=9 b=6	11	190	156, 185, 191		462 (0.19), 522 (0.18), 642 (0.19)
		Ship Cove Blue	L=66 a=10 b=9	13	193	131, 165, 174		462 (0.17), 520 (0.16), 641 (0.15)

Mushroom Tissues	GNPs swarms	Color	CIE Chromaticity values	Chroma	Hue	R, G,	Absorbance (nm)	Absorbance values
		Saddle Brown	L=46 a=9 b=46	47	40	141, 102, 27		460(0.5), 520(0.10), 643(0.18)
		Juniper Green	L=61 a=3 b=5	6	199	137, 150, 156		540 (0.15), 519 (0.14), 642 (0.17)

Table 2: Colour analysis and Colorimetric absorption characterization of presumptive GNP swarms

Mushroom Tissues	GNPs swarms (X 6000)	Color	CIE Chromaticity values	Chroma	Hue	R, G,	Absorbance (nm)	Absorbance values

						B value		
		Willow Grove	L=45, b=12	12	42	114, 106, 87		461(0.8), 519 (0.11), 640 (0.15)
		Dark Grey	L=16, b=2	4	140	35, 41, 37		455(0.2), 512(0.3), 632 (0.4)
		Charcoal grey	L=33 a=8 b=7	11	111	67, 79, 65		455(0.8), 511(0.11), 632(0.15)

		Brown Bramble	L=24 a=8 b=16	18	27	74, 51, 33		460(0.6), 522(0.8), 644(0.7)
		Dim grey	L=42 a=5 b=5	7	96	94, 100, 90		455 (0.2), 510(0.5), 642(0.10)

Table 3: Visible spectral characteristics of GNP swarms using *T. heimii* tissue sample and SWSE

Absorbance wavelength (nm)	Tissue					SWSE				
	I Umbonal tissue	II Pileus context	III Lamellae	IV Stipe context	V Pseudorrhiza context	VI Umbonal context	VII Pileus context	VIII Lamellae	IX Stipe context	X Pseudorrhiza context
455	-	-	-	-	-	-	+	+	-	+
460	-	-	-	+	-	-	-	-	+	-
461	+	-	-	-	-	-	-	-	-	-
462	+	+	-	-	-	-	-	-	-	-
463	+	-	-	-	-	-	-	-	-	-
510	-	-	-	-	-	-	-	-	-	+
511	-	-	-	-	-	-	-	+	-	-
512	-	-	-	-	-	-	+	-	-	-
519	-	-	-	-	+	+	-	-	-	-

520	+	-	+	+	-	-	-	-	-	-
522	-	+	-	-	-	-	-	-	+	-
540	-	-	-	-	+	-	-	-	-	-
632	-	-	-	-	-	-	+	+	-	-
640	-	-	-	-	-	+	-	-	-	-
641	+	-	+	-	-	-	-	-	-	-
642	-	+	-	-	+	-	-	-	-	+
643	-	-	-	+	-	-	-	-	-	-
644	-	-	-	-	-	-	-	-	+	-

Table 4: Approximate GNP size range

Wavelength reported in present assay (nm)	Approximate GNP size range (nm)	Reference
455, 460, 461, 462, 463	< 5	Ted Pella Inc.
510, 511	5	Ted Pella Inc.
512, 519	10	Sigma-Aldrich
520, 522	15	Sigma-Aldrich, Ted Pella Inc.
540	10-30	Radtsig et al., 2016
632	50-80	Ted Pella Inc.
640	80-100	Sigma-Aldrich
641	100	Sigma-Aldrich
642, 643, 644	100	Sigma-Aldrich, Ted Pella Inc.