Severe corrosion of carbon steel in oil field produced water can be linked to methanogenic

archaea containing a special type of [NiFe] hydrogenase.

Sven Lahme,[a]# Jaspreet Mand,[a] John Longwell,[a] Ramsey Smith,[a] and Dennis Enning[a]#

[a]ExxonMobil Upstream Research Company, Spring, Texas, USA

Running Head: Methanogenic MIC mechanism

#Address correspondence to Sven Lahme, sven.a.lahme@exxonmobil.com and Dennis Enning,

dennis.r.enning@exxonmobil.com

ABSTRACT

Methanogenic archaea have long been implicated in microbially influenced corrosion (MIC) of oil

and gas infrastructure, yet a first understanding of the underlying molecular mechanisms has only

recently emerged. We surveyed pipeline-associated microbiomes from geographically distinct oil

field facilities and found methanogens to account for $0.2 - 9.3\%$ of the sequenced communities.

Neither the type nor the abundance of the detected methanogens correlated to the perceived

severity of MIC in these pipelines. Using fluids from one pipeline, MIC was reproduced in the

laboratory, both under stagnant conditions and in customized corrosion reactors simulating

pipeline flow. High corrosion rates (up to 2.43 mm Fe^0 yr^{-1}) with macroscopic, localized corrosion

features were attributed to lithotrophic, mesophilic microbial activity. Other laboratory tests with

the same waters yielded negligible corrosion rates (< 0.08 mm Fe^0 yr^{-1}). Recently a novel [NiFe]

hydrogenase, from *Methanococcus maripaludis* strain OS7, was demonstrated to accelerate

corrosion. We developed a specific qPCR assay and detected the gene encoding the large subunit

of this hydrogenase (labelled *micH*) in corrosive (> 0.15 mm Fe^0 yr^{-1}) biofilms. The *micH* gene on

the other hand was absent in non-corrosive biofilms despite an abundance of methanogens.

Reconstruction of a nearly complete *Methanococcus maripaludis* genome from a highly corrosive

mixed biofilm revealed *micH* and associated genes in near-identical genetic configuration as strain

OS7, thereby supporting our hypothesis that the encoded molecular mechanism contributed to

corrosion. Lastly, the proposed MIC biomarker was detected in multiple oil fields, indicating a

geographically widespread involvement of this [NiFe] hydrogenase in MIC.

IMPORTANCE

Microorganisms can deteriorate built environments, which is particularly problematic in

the case of pipelines transporting hydrocarbons to industrial end users. MIC is notoriously difficult

to detect and monitor and as a consequence, is a particularly difficult corrosion mechanism to

manage. Despite the advent of molecular tools and improved microbial monitoring strategies for

oil and gas operations, specific underlying MIC mechanisms in pipelines remain largely enigmatic.

Emerging mechanistic understanding of methanogenic MIC derived from pure culture work

allowed us to develop a qPCR assay that distinguishes technically problematic from benign

methanogens in a West African oil field. Detection of the same gene in geographically diverse

samples from North America hints at the widespread applicability of this assay. The research

presented here offers a step towards a mechanistic understanding of biocorrosion in oil fields and

introduces a binary marker for (methanogenic) MIC that can find application in corrosion

management programs in industrial settings.

INTRODUCTION

Microbially influenced corrosion (MIC) is problematic to oil field operations when it leads

to extensive damage requiring the repair or replacement of infrastructure such as carbon steel

pipelines. While some metal loss is expected and accounted for during the design of the

infrastructure (e.g. 0.1 mm yr^{-1} for a pipeline designed with 3 mm corrosion allowance for 30 years

design life), higher rates of corrosion, unless detected and mitigated in a timely manner, can

necessitate costly repairs or replacements long before the design service life has been actualized.

The most common oil field corrosion mechanisms are linked to CO_2 and/or hydrogen

sulfide (H_2S) which are present in oil-bearing formations and readily dissolve into the water that

is associated with production fluids (termed produced water). The deleterious effects of these acid

gases are managed through injection of corrosion inhibitors (CIs), typically film-forming

surfactants that act as a diffusion barrier between steel and the aqueous corrosive environment (1,

2). Acid gas corrosion can be modeled *in silico* (3) or simulated in laboratory reactors (4) to

understand the rates of metal loss expected under specific field conditions (i.e. flow, temperature,

brine chemistry and partial pressure of acid gases). Furthermore, laboratory testing provides a

robust approach to ensure CI effectiveness (4, 5). Microbial corrosion, on the other hand, cannot

be adequately modeled and laboratory qualification of oil field biocides, applied to control MIC,

typically falls short at predicting product effectiveness in the field. As a consequence, field-based

detection and monitoring is particularly important for effective management of this corrosion

mechanism.

In environments devoid of oxygen, MIC has been linked to a variety of anaerobic

microorganisms ((6) and references therein); yet most attention has historically been given to the

sulfate-reducing bacteria (SRB) due to their well-documented ability to cause severe corrosion in

laboratory studies and their prevalence in production systems ((7) and references therein). SRB

impact metal integrity by producing hydrogen sulfide (H_2S) as a corrosive metabolic end-product

of sulfate reduction with (usually) organic electron donors. A small number of lithotrophic SRB

isolates have further been shown to severely accelerate corrosion of steel in laboratory tests by

utilizing cathodic electrons for their metabolism (8–10). It was proposed that outer membrane c-

type cytochromes enable the direct uptake of electrons from steel in one such isolate, *Desulfovibrio*

ferrophilus strain IS5 (11). In addition to SRB, also methanogenic archaea are increasingly viewed

as prime culprits in the corrosion of steel (12–19). Some methanogens have been shown to utilize

metallic iron (Fe^0) in carbon steel as the sole electron donor for methanogenesis (13, 14, 19, 20).

Electrochemical studies suggested a mediator-free direct electron uptake mechanism for one of

these Fe^0-utilizing isolates, *Methanobacterium*-like strain IM1 (21). The potential technical

relevance of this microorganism has been demonstrated in laboratory studies where strain IM1 was

grown in flow-through systems (22).

A deeper understanding of the underlying biochemical basis of Fe^0 utilization by

methanogenic archaea has recently been provided. By working with filtered spent culture medium

as well as hydrogenase-negative mutants of *Methanococcus maripaludis* strain MM901,

Deutzmann and colleagues demonstrated that free, steel-associated hydrogenases from this strain

catalyzed the production of hydrogen (H_2) from Fe^0 granules (23). Whether these hydrogenases

originated from partial lysis of the laboratory culture (e.g. in stationary phase) or were actively

excreted is currently unknown. Likewise, it is unclear whether this mechanism can produce

technically relevant MIC in laboratory or oil field settings. Tsurumaru and colleagues performed

comparative genomics on multiple strains of *Methanococcus maripaludis* and identified a 12 kb

genomic region (termed 'MIC island') that was unique to pure cultures of strain OS7, the only

strain of *M. maripaludis* that accelerated Fe^0 oxidation (corrosion) in their tests (24). This 'MIC

island' encoded for a novel type of [NiFe] hydrogenase along with an extracellular transport

system. It was postulated that the secreted [NiFe] hydrogenase would catalyze the reduction of H^+

to molecular hydrogen on iron surfaces, thereby accelerating the oxidation of the provided iron

granules.

These recent insights into the molecular mechanisms of MIC by methanogenic archaea

prompted us to investigate the role of methanogens in the corrosion of oil and gas infrastructure.

Since MIC is a biofilm-associated phenomenon (25), we began by surveying the archaeal

microbiomes of steel-associated solids from pipelines in North America, East Asia and West

Africa. We then performed a comprehensive study of MIC using produced waters from one of

these locations in controlled laboratory reactors that allowed for the growth of methanogenic

archaea. The extent of corrosion as well as associated microbial communities were investigated

under various enrichment conditions with natural oil field waters, as well as synthetic brines to

specifically enrich for lithotrophic microorganisms. Building on these laboratory tests, we gained

insights into the molecular mechanisms of MIC through shotgun DNA sequencing and

metagenomic analysis of a highly corrosive, lithotrophic biofilm grown under simulated pipeline

conditions. Lastly, we developed a novel qPCR assay for the detection of the abovementioned

[NiFe] hydrogenase and demonstrated the applicability of this proposed MIC biomarker assay in

industrial settings.

RESULTS

Methanogenic archaeal communities on carbon steel pipeline walls

Maintenance of oil field pipelines involves the periodic use of devices with blades or

brushes (termed 'pig', pipeline intervention gadget) to mechanically clean out rust, wax, scale and

biofilm (collectively termed 'pig debris'). This practice offers the opportunity to access steel-

associated microorganisms from pressurized hydrocarbon pipelines. We obtained pig debris from

nine different pipelines in seven geographically distinct oil field operations in North America, East

Asia and West Africa to survey the prevalence of methanogenic archaea (Fig. 1). Estimated 16S

rRNA gene abundances of $1.6 \cdot 10^7$ - $1.3 \cdot 10^{10}$ gene copies per g of pig debris suggested moderately

dense microbial colonization of pipe wall-associated solids. Archaeal sequences accounted for 0.2

– 21.6% of total reads, and most of the detected archaea were classified as members of

methanogenic archaeal families (0.2 – 9.3% of total reads). Members of the *Methanococcaceae*,

Methanobacteriaceae, and *Methanosarcinaceae* have been implicated in MIC through laboratory

investigations (13, 17, 19, 24). However, there was no apparent correlation between the types or

abundances of methanogens, and the perceived severity of MIC in the surveyed pipelines (Fig. 1).

For example, pipelines [A] – [C] had no indications of active internal corrosion (MIC or otherwise)

in recent in-line inspections (ILI, data not shown) despite the presence of microorganisms

affiliating with the abovementioned putatively corrosive archaeal families.

Assessment of MIC under mesophilic and thermophilic conditions

The detection of methanogenic archaea in all surveyed pipelines necessitated a more

nuanced understanding of their potential role in corrosion; a question that was approached through

laboratory cultivation. We hence obtained anoxic production fluids from a West African oil field

with a history of MIC (Fig. 1, pipelines [G] and [I]). Carbon steel infrastructure typically spans

broad temperature gradients within the same oil field due to hot production fluids from reservoirs

(often >> 60ºC) cooling as they pass through networks of pipelines, pressure vessels and piping.

Fluids from subsea pipeline [I] had an average temperature of 32ºC at the time of sampling. In the

laboratory, the sulfate-free (< 20 μM) produced water was transferred into glass bottles with

specially designed carbon steel coupon holders with rubber stoppers and an anoxic headspace of

N_2-CO_2. Bottles were incubated at 32°C and 60°C on rotary shakers (75 rpm) for 13 weeks; under

conditions that are most representative of process dead legs or idled pipelines (i.e. stagnant to very

low flow). Indeed, methanogenic biofilms developed on carbon steel surfaces exposed to the

sulfate-free produced water, as evidenced by accumulation of CH_4 in the test bottles (Fig. 2A) and

detection of high numbers of steel-attached methanogenic archaea through qPCR and 16S rRNA

gene sequencing (Fig. 2A and B). Methanogens accounted for 17.0 – 54.4% of the steel-attached

biofilms. Archaeal communities grown at 32°C showed high abundances of hydrogenotrophic (i.e.

lithotrophic) *Methanobacterium* spp. and *Methanocalculus* spp., with minor fractions of

Methanococcus spp. Incubation at higher temperatures (60°C) led to formation of biofilms with

prominent fractions of hydrogenotrophic *Methanothermobacter* spp. and, at lower prevalence, the

acetoclastic *Methanosaeta* spp. (Fig. 2B). Mesophilic bacterial communities (32°C) contained

high fractions of *Syntrophomonas* spp., *Kosmotoga* spp. and *Halomonas* spp. that might have

grown through fermentation of residual organic compounds in the produced water, thereby

producing acetate, CO_2 and H_2 (26–28). The majority of the biofilm community in bottles

incubated at 60°C consisted of mesophilic bacteria unlikely to grow at that temperature (Fig. 2C).

However, some thermophilic bacteria such as *Thermotoga*, *Fervibacterium* and *Caldithrix* were

detected and could have grown via a fermentative metabolism (29–31). Consistent with the lack

of sulfate in these natural oil field waters, we only detected minor fractions of SRB in steel-

attached biofilms (cumulatively < 0.6% per biofilm). The different incubation temperatures

resulted in markedly different metal damage (Fig. 2A). Microbial activity had negligible impact

on carbon steel at 60°C, with an increase in corrosion rates of approximately 40% compared to

sterile controls, but a low average corrosion rate of 0.02 ± 0.01 mm Fe^0 yr^{-1}. Mesophilic

microorganisms, on the other hand, accelerated corrosion by a factor of 12 and led to localized

damage with features as deep as 399 μm developing over 3 months (Fig. 2A and Fig. S1). The

National Association of Corrosion Engineers (NACE) categorizes corrosion rates of carbon steel

coupons > 0.13 mm Fe^0 yr^{-1} as *high* and > 0.25 mm Fe^0 yr^{-1} as *severe* (NACE SP0775-2013).

Interestingly, despite the profoundly different impacts on corrosion, biofilms grown at 32°C and

60°C contained similar numbers of active methanogens (Fig. 2A). This observation implied that

intrinsic properties of the mesophilic biofilm community rather than the overall cell number or

methanogenic activity were linked to the observed acceleration of corrosion kinetics.

Identification of potential methanogenic corrosion mechanisms

Tsurumaru and colleagues recently linked the accelerated oxidation of Fe^0 (i.e. corrosion)

in cultures of *M. maripaludis* strain OS7 to a novel [NiFe] hydrogenase (24). A protein sequence

comparison of the large subunit of this hydrogenase against the National Center for Biotechnology

Information's (NCBI) protein sequence database revealed that three sequenced members of the

Methanobacteriales contain similar proteins (90.7 to 93.5% protein sequence identity), while all

other deposited sequences showed ≤ 40% protein sequence identity (Table S1). The high degree

of protein sequence resemblance suggested functional similarity within this protein cluster and

prompted us to develop a specific qPCR assay. We developed a degenerated primer pair and

Taqman™ probe (Table 1) to detect and quantify the gene of the large subunit of the [NiFe]

hydrogenase (referred to here as *micH*) in strain OS7 and the three other methanogenic strains.

This assay allows for probing of mixed microbial biofilms for their ability to carry out a proven

microbial corrosion mechanism, i.e. the enzymatic catalysis of Fe^0 oxidation via an extracellular

hydrogenase. Intriguingly, we could detect $3.3 \cdot 10^2$ and $1.6 \cdot 10^3$ *micH* gene copies per cm^2 in

corrosive biofilms at 32°C while the *micH* gene was undetectable in non-corrosive biofilms grown

at 60°C (Fig. 2A). This raised the possibility that mesophilic, lithotrophic methanogens, likely of

the genera *Methanococcus* or *Methanobacterium,* had caused the observed high rates of corrosion.

Enrichment of organotrophic and lithotrophic oil field communities

We sought to reproduce our observations and collected a new batch of production fluids

from the same West African oil field. Traces of H_2S (approx. 100 ppm) measured in the gas phase

of the sample collection drums upon arrival in our laboratories indicated sulfate reduction, so we

amended the next tranche of corrosion bottle tests with sulfate to allow for the growth of SRB.

Again, highly corrosive mesophilic biofilms developed in these produced waters and putatively

corrosive *Methanococcus* spp., as well as *Methanocalculus* spp. were detected in large fractions

(Figs. 2D and 2E). Furthermore, these biofilms contained *micH* at even higher numbers than

previous cultures with $1.1 \cdot 10^5 - 7.4 \cdot 10^5$ gene copies per cm^2 (Fig. 2D).

The use of actual produced waters for laboratory studies offers the opportunity to closely

simulate oil field MIC in laboratory settings. However, it also complicates data interpretation,

since the presence of complex organic matter can allow for a multitude of fermentative and

oxidative metabolisms. We therefore dissected experimental conditions by working with defined

cultivation media which were modelled after the major ion composition of the original produced

water (+ sulfate). Organotrophic and lithotrophic enrichment cultures containing steel coupons

were set up with or without addition of organic acids (12.1 mM acetate and 1.6 mM propionate),

respectively. This reduced the number of potential biological transformations and, in the case of

tests without the organic acids, limited growth to those microorganisms capable of utilizing

metallic iron (Fe^0) as an electron donor. Transfer of produced water as inoculum (0.5% vol/vol)

into synthetic media reduced microbial corrosion rates to moderate rates (< 0.08 mm Fe^0 yr^{-1}) in

all but one of the bottle tests (Fig. 2D). Remarkably, this lithotrophic culture caused corrosion at

severe rates of 0.76 ± 0.15 mm Fe^0 yr^{-1}, with up to 370 µm deep corrosion features developing on

carbon steel coupons over 3 months (Fig. 2D and Fig. S2). All biofilms in the synthetic produced

water media were numerically dominated by sulfate-reducing bacteria, in particular *Desulfovibrio*

spp., *Desulfobulbus* spp. and *Desulfotignum* spp. (Fig. 2F). The distinguishing feature of the

severely corrosive lithotrophic biofilm, however, appeared to be the enrichment of a sub-

population of *Methanococcus* spp., and the detection of the special [NiFe] hydrogenase *micH*

(Figs. 2D and 2E).

Corrosion under simulated pipeline condition

The preceding bottle tests demonstrated the potential for severe MIC in stagnant water

bodies within infrastructure of the investigated oil field. However, the pipelines that transport

multi-phasic fluids (e.g. from offshore production wells) usually experience high flow and, as a

result, wall shear stresses, which greatly increase the rates of acid gas corrosion resulting from

CO_2 (32). Likewise, biofilm formation can be affected by the physical stresses imposed by flow

(33).

We therefore evaluated corrosion in customized test reactors (corrosion kettles) that allow

for close simulation of pipeline conditions by controlling shear stress, pH and acid gas composition

(Fig. 3A). First, a test with sterile synthetic produced water was performed to establish the baseline

corrosion from CO_2. These tests revealed that abiotic conditions alone could cause severe

corrosion of 0.34 ± 0.01 mm Fe^0 yr^{-1} (Fig. 3B and Fig. S3) under conditions that model pipelines

[G] and [I].

Still, inclusion of oil field microorganisms in these tests demonstrated the pronounced

biotic component of pipeline corrosion under the studied conditions; a second tests with actual

produced water increased averaged corrosion rates beyond the CO_2 baseline to 0.54 ± 0.14 mm

Fe^0 yr^{-1} (Fig. 3B), and resulted in irregular and localized pitting corrosion at extrapolated rates of

1.57 ± 0.61 mm yr^{-1} (Fig. 3B and Fig. S3). Operation of a third corrosion kettle with lithotrophic

produced water medium inoculated with a pre-enriched Fe^0-utilizing culture (asterisk in Fig. 2D)

resulted in even more aggressive metal damage. This culture catalyzed iron oxidation at rates of

1.62 ± 0.72 mm Fe^0 yr^{-1}, leading to macroscopic localized corrosion features with an extrapolated

growth rate of 5.24 ± 2.21 mm yr^{-1} over 7 weeks (Fig. 3C). Microbially catalyzed metal oxidation

at these rates, if left unmitigated, would profoundly challenge pipeline integrity.

High copy numbers of *micH* ($> 10^6$ copies per cm^2) and high relative fractions of 28% and

42% of *Methanococcus* spp. were detected in biofilms grown in corrosion kettles operated with

actual (organotrophic) and synthetic (lithotrophic) produced water, respectively (Fig. 3B and Fig.

S4). Other dominant microorganisms detected in corrosive biofilms in both reactors included

Desulfovibrio spp. (Fig. S4).

A fourth corrosion kettle was set up with synthetic produced water medium containing organic acids and was inoculated with an organotrophic subculture from the West African oil field. This test did not produce the previously observed high corrosion rates, despite formation of similar biofilms as measured by 16S rRNA gene abundance (Fig. 3B). Corrosion of coupons underneath these biofilms containing *Desulfovibrio*, *Desulfobulbus* and *Methanolobus* species (Fig. S4) was considerably lower than the sterile control, at 0.073 ± 0.001 mm Fe^0 yr^{-1} and resulted in rather uniform metal loss (Fig. 3B and Fig. S3). This may be an indication that the biofilm limited CO_2 corrosion by forming a passivating barrier, a phenomenon seen before in laboratory tests (Kip and van Veen 2015 and references within). Notably, this 'protective' biofilm did not contain any *Methanococcus* spp. or *Methanobacterium* spp. and tested negative for *micH* (Figs. 3B and S5).

Genomes recovered from a severely corroded carbon steel coupon

Shotgun metagenome analysis can be a useful tool to probe for blueprints of biochemical reactions in mixed microbial communities. We wanted to further investigate the molecular mechanisms of MIC seen in this study, and hence extracted and sequenced DNA of a biofilm that was i) associated with severe corrosion, ii) contained high fractions of potential culprit organisms such as *Methanococcus* spp. and *Desulfovibrio* spp. and iii) was grown under pipeline-like conditions (see asterisk in Fig. 3B for selected sample).

We were able to obtain six near complete metagenome-assembled genomes (MAGs) from this sample (Table 2). Taxonomic classification by protein marker analysis indicated that one of the MAGs affiliated closest with *Methanococcus maripaludis*. The *micH* gene in *M. maripaludis*

strain OS7 is co-located on a 12 kb 'MIC island' with genes hypothesized to be essential for the

functioning and secretion of this hydrogenase (24). A sequence similarity search revealed that a

micH homolog was indeed present in one of the assembled contigs of the *M. maripaludis* MAG.

Furthermore, we discovered that the genetic arrangement of the 'MIC island' in this MAG and

strain OS7 was in fact identical (Fig. 4). Notably, the genetic island contained genes for both

subunits of the putative [NiFe] hydrogenase, as well as the twin-arginine translocation system for

secretion of the mature hydrogenase in strain OS7 (24). Protein sequence comparison further

confirmed a high resemblance (98.8 – 100% amino acid sequence identity) between both clusters

(Fig. 4).

Traditionally, SRB have been viewed as prime suspects of MIC (7). While all SRB can

produce corrosive H_2S under suitable organotrophic growth conditions, some specialized

lithotrophic SRB strains have recently received much attention as they can cause particularly

severe corrosion through a more direct mechanism (8, 9, 13). It had been proposed that these

organisms oxidize metal through direct electron uptake via outer-membrane c-type cytochromes

(OMCs, (13)), with recent evidence supporting this hypothesis in *D. ferrophilus* strain IS5 (11). In

this study, we obtained three near complete *Desulfovibrionaceae* genomes (Table 2). A reliable

taxonomic classification was possible for one genome, which was assigned to a strain of

Desulfovibrio alaskensis. However, despite presence of three near complete *Desulfovibrionaceae*

genomes, no evidence for a homologous OMC system to the one detected in strain IS5 was found

in this metagenomic dataset. This suggest that a direct electron uptake via extracellular c-type

cytochromes may not have contributed to MIC in our experiments.

The detection of *micH* in a metagenome-assembled genome from a highly corrosive

biofilm further strengthened the applicability of this gene as a potential marker for MIC. We

confirmed the presence of *micH* (up to $1.6 \cdot 10^6$ gene copies per g) in pig debris from the West

African oil field (pipelines [G] and [I] in Fig. 1). Intriguingly, we also detected $3.9 \cdot 10^3 – 2.8 \cdot 10^4$

micH gene copies per g in three geographically separated pipelines in North America (Fig. 1).

DISCUSSION

Methanogenic archaea are commonplace members of the oil field microbiome (16, 17, 34,

35). However, unlike SRB which produce corrosive sulfides as a metabolic product, methanogenic

archaea are not intrinsically corrosive (24, 36); they oxidize molecular hydrogen or a limited

spectrum of small organic compounds and produce chemically inert CH_4. We surveyed surface-

associated deposits from nine pipelines in seven geographically distinct oil field operations and

detected methanogenic archaea in all instances, despite vast differences in the perceived severity

of MIC (Fig. 1). For example, methanogens affiliated with the *Methanobacteriaceae*,

Methanococcaceae and *Methanosarcinaceae* were detected in steel-associated solids from

pipelines [A] - [C]. Members of these archaeal families have been implicated in MIC through

laboratory studies (13, 17, 19, 24), yet recent inspections of the pipelines [A] – [C] did not reveal

any indications of internal corrosion. Similarly, biofilms containing *Methanosaeta* spp.,

Methanobacterium spp., *Methanolobus* spp. and *Methanothermobacterium* spp. caused only

negligible corrosion (< 0.08 mm Fe^0 yr^{-1}) in laboratory reactors that simulated oil field conditions

(Figs. 2, 3 and S5). These data highlight that the mere presence of methanogenic biofilms on steel

does not entail corrosion.

Corrosion of metallic iron in the absence of oxygen can be depicted as follows:

$$Fe^0 \leftrightarrow Fe^{2+} + 2e^- \tag{1}$$

$$2e^- + 2H^+ \leftrightarrow H_2 \tag{2}$$

$$316 \qquad\qquad\qquad\qquad Fe^0 + 2H^+ \leftrightarrow Fe^{2+} + H_2 \qquad\qquad\qquad\qquad (3)$$

Where the anodic oxidation of iron (reaction 1) is coupled to the cathodic reduction of a suitable

oxidant, in anoxic environments usually H^+ (reaction 2), so that the net reaction involves formation

of molecular H_2 (reaction 3). Reaction 2 is kinetically impeded and as a result the corrosion of

steel is slow in anoxic environment at near-neutral pH (9, 37, 38). However, corrosion in (slightly)

acidic oil field waters can be pronounced in the presence of weak acids, as loosely bound protons

from carbonic acid, organic acids or sulfide dramatically increase the availability of H^+ ions as

oxidants at the steel surface, particularly in high flow scenarios (39).

Historic models of MIC had postulated that the consumption of cathodic molecular

hydrogen by hydrogenotrophic microorganisms (incl. methanogens) would accelerate corrosion

(40–42). However, this view has been disputed based on kinetic and thermodynamic

considerations (8, 9, 43), as well as through copious experimental observations (8, 13, 14, 24, 36).

However, while the majority of tested hydrogenotrophic methanogenic archaea does not influence

steel oxidation to any significant extent, some strains have shown a pronounced impact on

corrosion kinetics in laboratory experiments (13, 14, 24, 36). Recently evidence has emerged that

some pure cultures of methanogenic archaea accelerate corrosion when they produce extracellular

hydrogenases that catalyze reaction 2 on steel surfaces (23, 24).

Mesophilic methanogens in highly corrosive oil field biofilms contain a special MIC

hydrogenase

In this study we reproduced oil field corrosion using fluids from an offshore production

site in West Africa. Formation of mesophilic biofilms considerably increased corrosion rates over

sterile controls, both in *de facto* stagnant bottle test, as well as in corrosion kettles simulating flow

and field-like partial pressures of CO_2 (Figs. 2 and 3). Technically highly relevant MIC rates (0.15

– 1.62 mm Fe^0 yr^{-1}) and severe pitting were observed in several of these bioreactors. By using

specially formulated synthetic produced water media we could further demonstrate that the

observed Fe^0 oxidation was in fact a lithotrophic process. Some hydrogenotrophic *Methanococcus*

spp. and *Methanobacterium* spp. have been shown to effectively utilize Fe^0 and were found in

substantial numbers (> $3.7 \cdot 10^5$ 16S rRNA gene copies per cm^2) in highly corrosive biofilms (Figs.

2 and 3; Fig. S5B). However, both genera were also present in nearly all other (non-corrosive)

biofilms, confirming that hydrogenotrophy itself does not accelerate corrosion kinetics.

Tsurumaru and colleagues recently discovered that only a few known strains of *M.*

maripaludis and *Methanobacterium* spp. encode for a unique hydrogenase that catalyzes the

reduction of H^+ to H_2 on Fe^0 granules and thereby considerably accelerates iron oxidation (24).

The apparent high conservation amongst proteins from members of *Methanococcaceae* and

Methanobacteriaceae allowed us to develop a specific qPCR assay targeting the gene of the large

subunit, *micH*, of this hydrogenase. This assay did in fact distinguish biofilms causing technically

relevant corrosion (> 0.13 mm Fe^0 yr^{-1}) from those that did not (< 0.08 mm Fe^0 yr^{-1}) in our

experiments with actual and synthetic produced waters (Fig. S5B, Figs. 2 and 3). *M. maripaludis*

strain OS7 harbors this unique hydrogenase (*micH*) on a 12 kbp long genetic island along with

several other genes assumed to be essential for a fully functional extracellular enzyme (24). We

were able to retrieve a near complete genome of a *Methanococcus maripaludis* strain that carried

micH in an identical genetic arrangement as strain OS7 (Fig. 4). This indicated that *micH* was

associated with a corrosive *Methanococcus maripaludis* strain in our laboratory tests. Indeed,

corrosive biofilms consistently contained both, methanococcal 16S rDNA and the *micH* gene (Fig.

S5B).

There was no linear correlation between the extent of corrosion and copy numbers of *micH*

(Fig. S5). High corrosion rates were observed on coupons containing as few as $3.3 \cdot 10^2$ gene copies

per cm^2 at the time of biofilm collection (Fig. 2A). It should be noted though that corrosion rates

were averaged from metal loss over the entire experimental period (e.g. 3 months), while

quantification and characterization of target genes in biofilms was only performed at test takedown

and hence only represents endpoint conditions. Methanogens precipitate siderite ($FeCO_3$) which

can passivate steel surfaces (18, 44) and could have buried initially corrosive methanogens in some

tests, possibly allowing for the degradation of 'forensic evidence'. This could explain low copy

numbers in some highly corrosive biofilms. More importantly though, we do not envision gene

copy numbers of *micH* to correlate with the final abundance of the actual enzyme that catalyzes

iron oxidation. Still, *micH* in biofilms served as a binary genetic marker for technically relevant

microbial corrosion in our tests with West African produced waters.

Methanogenic archaea constituted only a part, and in some instances a minor part of the

biofilm communities that developed under simulated oil field conditions. In addition to organic

compounds in the produced waters and the organotrophic synthetic produced water medium (e.g.

acetate and propionate), also small quantities of cathodic hydrogen from abiotic corrosion

according to reaction 3 will have served as a readily available electron donor, e.g. for sulfate-

reducing bacteria. It is tempting to speculate that enzymatically catalyzed H_2 formation from

extracellular hydrogenases could have fed additional electron donors into the biofilm community.

A potential role of electroactive H_2-forming microorganisms as 'ecosystem engineers' has been

proposed elsewhere (45).

The role of sulfate-reducing bacteria in corrosion

The importance of sulfate-reducing bacteria in microbial corrosion has long been

established ((7) and references therein) and the underlying mechanisms as well as their regulation

are still an active area of research (11, 46–48). While we cannot exclude contribution of SRB to

corrosion, we inferred that they had likely played a minor role in our experiments. Firstly,

Desulfovibrio sp. were found in high abundances in all biofilms under sulfate-reducing conditions,

but high or severe corrosion only occurred in the presence of *micH*-positive methanogens (Figs.

2D and 3B; Fig. S5). Secondly, high microbial corrosion rates were also observed in sulfate-free

produced water (Fig. 2A). Thirdly, only few lithotrophic SRB isolates have been demonstrated to

cause corrosion to an extent similar to what was observed in this study (7, 8); the extracellular

multiheme c-type cytochromes that have been linked to direct electron uptake in those corrosive

strains (11) were absent in the metagenomic dataset. The low to moderate corrosion rates in the

absence of *micH*-positive *Methanococcus* spp. agree with corrosion rates documented for

sulfidogenic cultures of *D. alaskensis* (≤ 0.1 mm Fe^0 yr^{-1}; (22, 48, 49)). We cannot, however,

exclude that hitherto unknown enzymatic mechanisms may have affected corrosion in our

experiments.

Proposed use of *micH* as a genetic marker for methanogenic MIC

Microbial corrosion of oil field infrastructure is difficult to detect and monitor, in large part

because the responsible microorganisms and underlying mechanisms remain enigmatic (50). For

example, the mere presence of large numbers of methanogenic archaea in pipeline-associated

debris or laboratory-grown biofilms proved to be a poor indicator of MIC in this study (Fig. 1 and

Fig. S5). A deeper mechanistic understanding of MIC in methanogens and other environmental

microorganisms offers a route to a more granular analysis and interpretation of microbiological

monitoring data in oil fields and other industrial settings. Enzymatic acceleration of corrosion via

hydrogenases is one such potentially relevant corrosion mechanism. This was recently evidenced

through careful experimentation with pure cultures of methanogenic archaea (24) and

demonstrated in this study with mixed microbial communities in bioreactors simulating oil field

corrosion. We designed an assay to quantify the gene encoding for an extracellular hydrogenase

(*micH*) in methanogens and demonstrated its ability to serve as a binary marker for MIC in

experiments with oil field cultures grown under stagnant and pipeline flow-simulating conditions

(Fig. S5B). The proposed MIC biomarker was detected in high concentrations (up to $1.6 \cdot 10^6$ gene

copies per g) in pipeline-associated solids from a West African oil field with a history of MIC

(pipeline [I] in Fig. 1). Interestingly, we also detected *micH* in similar solids from pipelines on the

West Coast and Gulf Coast of the United States (Fig. 1). The genetic island carrying this gene was

first detected in *M. maripaludis* strain OS7, which originated from an underground oil storage tank

in Japan and was further detected in the genome of *Methanobacterium congolense* Buetzberg by

the same group (24). Strain Buetzberg was originally isolated from a biogas plant in Germany (51).

The fact that we were able to reconstruct a near identical 'MIC island' from a West African oil

field strain of *M. maripaludis* (Fig. 4) suggests an extremely high level of conservation of the 'MIC

island' and presence of these corrosive methanogens in industrial facilities across four continents.

Future work may focus on developing a better understanding for the quantitative interpretation of

micH in solid and liquid samples to enable early detection and mitigation of severe cases of

microbially influenced corrosion in industrial settings.

MATERIALS AND METHODS

Collection of solid samples (pig debris) from pipelines

Solids from nine carbon steel pipelines were collected between July 2014 and June 2017

to study the microbiomes within hydrocarbon-transporting infrastructure. Subsea pipelines [G] and

[I] transport fluids from one oil field offshore Nigeria. This field produces oil and sweet natural

gas (i.e. no H_2S). Subsea pipelines [C] and [H] transport fluids from an offshore oil field on the

U.S. West Coast. The other five pipelines each carry fluids from separate oil and gas fields on the

U.S. West Coast [E], Midwest [F] and Gulf Coast [B, D], as well as from East Asia (A). Samples

were collected following the (internal) mechanical cleaning of these pipelines with maintenance

pigs that remove and push out surface-associated and settled debris. These solid samples (collected

in the pig trap) were carefully transferred into sterile containers, immediately refrigerated with ice

packs and frozen in common household freezers within 4 hours of collection. Samples were then

shipped frozen to Houston (USA) where they were stored at -80ºC until further analysis.

Bottle corrosion testing with original produced water

Production fluids (oil with associated water and gas) were collected at a pipeline outlet [I]

in a large oil field offshore Nigeria in December 2014. The fluids were filled into an internally

PTFE-lined steel drum (approx. 20 L) all the way to the brim and capped gas-tight. In the

laboratory, the content of the gas-tight drum was purged with N_2-CO_2 (79:21) to remove any

biogenic H_2S that had formed in the drum during transit (8 weeks). Thereafter, anoxic and sterile

technique was used to transfer the gravity-separated produced water into 1 L glass bottles (600 mL

each; pH 6.6 – pH 6.7) with butyl rubber stoppers under a N_2-CO_2 (79:21) headspace. For sterile

incubations, the capped produced water bottles were autoclaved (anaerobically) at 121ºC for 20

minutes. Three sterilized carbon steel coupons (3 x 1.25 cm^2) in a coupon holder made of polyether

ether ketone (PEEK) were added to each incubation (see Lahme et al., 2019 for details). Bottles

were placed on rotary shakers (75 rpm) and incubated at 32ºC or 60ºC for 13 weeks.

In March 2016, a second batch of production fluids was collected at a location further

downstream from the same pipeline [I], shipped to the laboratory (transit time: 5 weeks) and

processed as described above. Here, bottles with anoxic produced water (pH 6.6) were amended

with 1 mM sodium sulfate (Na_2SO_4) and incubated at 32ºC for 6 weeks.

Bottle corrosion testing with synthetic produced water medium

To study microbial corrosion under more defined conditions, bottle tests with synthetic

produced water medium were set up. The medium was modeled after the Nigerian produced water

(collected in March 2016 referred to below as PW-2016) and contained (all Sigma-Aldrich,

reagent-grade chemical in RO-DI water): NaCl (15.31 g/L), $MgCl_2 \cdot 6H_2O$ (0.562 g/L), $CaCl_2 \cdot 2H_2O$

(0.434 g/L), KCl (0.121 g/L) and NaBr (0.064 g/L). Additionally, Na_2SO_4 (1.48 g/L) was added

to allow for microbial sulfidogenesis. The brine was aliquoted (600 mL) into 1 L glass bottles,

purged with N_2-CO_2 (79:21), sealed with butyl rubber stoppers and autoclaved. After cooling, 24

mL/L of a sterile 1M $NaHCO_3$ stock solution (equilibrated with pure CO_2) was added.

Subsequently, the brines were supplemented with thiamine, a vitamin mixture, riboflavin, vitamin

B_{12}, a trace element mixture, selenite and tungstate, potassium phosphate and ammonium chloride

from sterile stock solutions (1 ml/L each), prepared as described previously (52). For

organotrophic test conditions, the medium was further supplemented with sodium acetate

($NaCH_3CO_2$; 0.996 g/L) and sodium propionate ($NaC_3H_5O_2$; 0.157 g/L). The pH of the synthetic

produced water medium ranged from pH 6.6 to pH 6.7. Sterile carbon steel coupons in PEEK

coupon holders were added as described above, bottles were inoculated with 0.5% (vol/vol) of the

original field produced water and then incubated on rotary shakers (75 rpm) at 32°C for 11 weeks.

Kettle corrosion testing

Customized corrosion kettles were used to simulate the influence of pipeline flow on CO_2

corrosion and MIC (Fig. 3A). These reactors contained inward-facing corrosion coupons that were

flush-mounted in an inert coupon holder cage (PEEK) and thus arranged around a central impeller

with Rushton blades. The rotational speed was set to 500 rpm to correspond to an average coupon

wall shear stress of 7 Pa (7 kg m^{-1} s^{-2}), which was deemed representative of pipeline conditions

based on multi-phase flow modeling previously performed at this field. The glass reactor

containing 1.5 L of test brine was sealed air-tight, with continuous purging of N_2-CO_2 (79:21;

equivalent to 3 psia CO_2) through a diffusor (250 mL/min) and a gas outlet with refrigerated

condenser tube to minimize loss of liquids via evaporation. Corrosion kettles were temperature-

controlled at 32ºC by means of a heating jacket with thermo-couple. Control of pH was achieved

through titration with 1 M HCl via syringe pumps coupled to on-line pH monitoring and a set point

of pH 6.6. All tests contained four carbon steel coupons (5 cm^2 each) and were operated for 7

weeks, unless otherwise stated.

Prior to test setup, corrosion kettles were rigorously cleaned and then "de-contaminated"

through liberal application of acetone. Sterile test conditions cannot be achieved in corrosion

kettles. To minimize the growth of environmental contaminants, abiotic corrosion tests were

amended with the antibiotics kanamycin (100 mg/L), chloramphenicol (25 mg/L) and tetracycline

(20 mg/L), which did not affect acid gas corrosion rate or morphology in 7-day tests (Fig. S6).

Furthermore, vitamins, trace elements, phosphate and ammonium were omitted from abiotic

corrosion tests.

Corrosion testing was initially performed with the original PW-2016. This test included

1% (vol/vol) crude oil, was amended with sodium sulfate (10.4 mM; Na_2SO_4) and spiked with an

Fe^0-containing, sulfate-amended PW pre-enrichment as additional inoculum (3% vol/vol). Testing

under lithoautotrophic conditions was performed in synthetic produced water medium (no acetate,

propionate, or oil), inoculated with the first passage of a lithoautotrophic enrichment culture (0.5%

vol/vol) obtained from PW-2016. Finally, kettle corrosion testing was also performed with

synthetic produced water medium containing sodium acetate and sodium propionate as organic

electron donors for microbial metabolism and growth. This test was inoculated with the third

subculture of an organotrophic, Fe^0-containing enrichment (0.5% vol/vol) obtained from PW-

2016.

Gas chromatography

Methane in gaseous samples (10 mL) was quantified using an Agilent 490 Micro gas

chromatograph with thermal conductivity detector. Chromatography was performed on a heated

Agilent PoraPlot U column (50°C, 22.1 psi, 10 m), using argon as the carrier gas. Injector and

sample line temperature were set to 100°C.

Weight loss corrosion analysis

API 5L X52 carbon steel coupons ($\leq$ 0.26% C, $\leq$ 0.45% Si, $\leq$ 1.6% Mn, < 0.03% P, $\leq$

0.03% S, balance Fe) were successively sonicated in hexane, acetone and methanol (5 min each),

dried in a stream of air and placed under vacuum overnight. The weight of each coupon was

measured three times on an analytical balance before placing into PEEK coupon holders. Coupon

holders containing corrosion coupons were sterilized by soaking in ethanol (96%) for 10 minutes.

Excess ethanol was dried with a stream of filtered N_2 gas.

At test end, corrosion products and other deposits were dissolved from coupons in a warm

(70°C) 1.8 N HCl solution containing 2% propargyl alcohol (1 min). Wet coupons were then

neutralized in saturated calcium hydroxide solution (30 sec) and scrubbed with a nylon brush while

being rinsed with deionized water. This procedure was performed twice. Coupons were then rinsed

in acetone, dried under a stream of air and placed under vacuum overnight. To determine weight

loss, each coupon was weighed three times. Corrosion rates were calculated by considering the

weight loss, exposed surface area, steel density (7.87 g/cm^3) and exposure time.

Localized corrosion analysis

522 To visualize and measure localized corrosion, the topography of cleaned carbon steel

523 coupons was mapped with a Keyence VR-3000K Wide-Area 3D profile measuring macroscope

524 (Keyence Corp., Itasca, IL). Corrosion features (≥ 25 μm in depth) were quantified by referencing

525 the original (pre-corrosion) surface height. Pitting corrosion rates, expressed as millimeter per

526 year, were calculated by linear extrapolation.

DNA sampling and extraction

Coupon holders were removed from bioreactors (bottles or corrosion kettles) and

thoroughly rinsed with sterile phosphate buffered saline (PBS) solution to remove loose

(planktonic) microorganisms. Steel-attached biofilms were then sampled using sterile swabs

(minimum of two swabs per coupon) and frozen at -80°C.

Frozen samples (pig debris or biofilm swabs) were shipped on ice to Microbial Insights

Inc. (Knoxville, TN) and DNA was extracted with the DNA Power Soil Total DNA Isolation kits

(MO BIO Laboratories, Inc., Solana Beach, CA) according to manufacturer's instructions. DNA

quantity and purity were assessed with a NanoDrop® ND-1000 spectrometer (Thermo Fisher

Scientific, Waltham, MA).

Quantitative polymerase chain reaction

Quantitative PCR was performed on a QuantStudio™ 12K Flex Real-Time PCR System

using a Taqman™ Universal PCR Mastermix (Applied Biosystems, Grand Island, NY). For the

quantification of eubacteria and archaea, primers and Taqman™ probes that target highly conserved

regions of the 16S rRNA gene were used as described elsewhere (53, 54). Forward and reverse

primers were obtained from Integrated DNA Technologies (Corralville, IA), while Taqman™

probes were synthesized by Thermo Fisher Scientific.

For the qPCR assay targeting the large subunit of the specific [NiFe] hydrogenase (here

referred to as *micH*) found in highly corrosive methanogenic archaea ((24) and this study), a

degenerated primer pair and Taqman™ probe were designed based on conserved regions in

homologous genes (Table 1, Fig. S7). Appropriate primer pairs and probes were selected using the

Primer Express™ software (Thermo Fisher Scientific) and initial specificity was assessed by

BLASTN searches against NCBI's nucleotide database (55). The qPCR reaction was performed

in 20 µl using the Taqman™ Universal PCR Mastermix. Forward and reverse primers, as well as

the probe were adjusted to a final concentration of 300 nM. For calibration and as positive control

a synthetic fragment of the *micH* gene was used (Fig. S7 and S8). The qPCR reaction conditions

were as follows: one cycle of 2 min at 50°C, followed by one cycle of 10 min at 95°C, 40 cycles

of 15 s at 95°C and 1 min at 60°C. The specificity of the qPCR reaction was verified by PCR melt

curve analysis and Sanger sequencing of final PCR products. In addition, potential cross reactions

were excluded by running the newly developed qPCR assay on genome-sequenced cultures (Table

S2) that lack the special [NiFe] hydrogenase (*micH*).

16S rDNA amplicon sequencing and analysis

16S rDNA amplicon sequencing was performed by GENEWIZ Inc. (South Plainfield, NJ).

DNA quality was assessed by agarose gel electrophoresis and quantified on a Qubit 2.0

Fluorometer (Invitrogen, Carlsbad, CA). Barcoded amplicons covering the V3 to V5 region of the

16S rRNA gene were generated using GENEWIZ's proprietary 16S MetaVx™ amplification

protocols and library preparation kit. Sequencing libraries were evaluated on an Agilent 2100

Bioanalyzer (Agilent Technologies, Palo Alto, CA) and quantified on a Qubit Fluorometer as well

as through qPCR. Paired-end sequencing (2×250 bp) of multiplexed DNA libraries was performed

on an Illumina MiSeq platform (Illumina, San Diego, CA).

The 16S rRNA data was analyzed using the QIIME pipeline (56). Joined reads were quality

filtered, discarding reads with a mean quality score ≤ 20, a read length < 200 bp and reads

containing any ambiguous bases. Chimeric sequences were detected using the UCHIME algorithm

(https://drive5.com/uchime/uchime_download.html) and the Ribosomal Database Program (RDP)

Gold Database (57). After removal of chimeric sequences, the remainder of sequences was

assigned into operational taxonomic units (OTU) with the VSEARCH (v1.9.6) clustering program

and the SILVA 119 database (58), pre-clustered at 97% identity. Taxonomic categories were

assigned to all OTUs at a confidence threshold of 0.8 by the RDP classifier.

Shotgun metagenome sequencing and analysis

Shotgun sequencing of extracted DNA was performed by GENEWIZ Inc. The quality of

extracted DNA was assessed by agarose gel electrophoresis and quantified on a Qubit 2.0

Fluorometer. DNA libraries were prepared using the NEBNext® Ultra™ DNA Library Prep Kit

(New England BioLabs Inc., Ipswich, MA) according to manufacturer's instructions. Quality of

DNA libraries was evaluated using Agilent TapeStation and quantified using a Qubit Fluorometer.

Libraries were quantified by qPCR and then loaded on to an Illumina HiSeq 4000 platform

according to manufacturer's recommendations and sequenced using the paired-end (2×150 bp)

configuration.

Subsequent bioinformatics analysis of paired-end sequencing reads was done in the KBase

environment (59). In summary, following quality trimming and adapter removal, the remaining

126 M paired-end reads were assembled with MetaSPAdes (v3.13.0) and a minimum contig size

of 500 bp (60). The assembled contigs were binned using the MetaBAT2 (v1.7) binning algorithm

(61). The quality of the resulting ten bins was evaluated using the CheckM (v1.0.18) software

package (62). Taxonomy was assigned to individual bins using the Genome Taxonomy Database

Toolkit (GTDB-Tk), which utilizes domain-specific, concatenated marker protein reference trees,

relative evolutionary divergence and average nucleotide identity for taxonomic classification (63).

Structural and functional annotation of binned contigs was achieved with NCBI's prokaryotic

annotation pipeline (64, 65). Additional annotations of unbinned contigs were obtained using the

Prokka software package (66).

Data availability

16S rRNA amplicon sequencing reads and shotgun metagenome reads used for assembly

and binning of individual genomes have been deposited to NCBI's sequencing reads archive and

the annotated draft genomes have been deposited at GenBank. The data can be accessed under the

bioproject PRJNA644413.

ACKNOWLEDGEMENT

We thank Manuel Castelan, Benny Chacko and Yao Xiong for their thoughtful discussions and

technical support throughout this project. We also greatly acknowledge the assistance provided by

Kingsley Oparaodu in obtaining several of the oil field samples.

REFERENCES

1.   Migahed MA, Al-Sabagh AM. 2009. Beneficial role of surfactants as corrosion inhibitors in

petroleum industry: A review article. Chem Eng Commun 196:1054–1075.

607 2. Popoola LT, Grema AS, Latinwo GK, Gutti B, Balogun AS. 2013. Corrosion problems
608   during oil and gas production and its mitigation. Int J Ind Chem 4:35.

609 3. Nešić S. 2007. Key issues related to modelling of internal corrosion of oil and gas pipelines
610   – A review. Corros Sci 49:4308–4338.

611 4. Xiong Y, Fischer D, Cao F, Pacheco J. 2017. Impact of pre-corrosion on corrosion inhibitor
612   performance: Can we protect aged pipelines, paper NACE-2017-8919. NACE International,
613   NACE.

614 5. Xiong Y, Fischer D, Cao F, Pacheco J. 2019. Impact of steel metallurgy on corrosion inhibitor
615   performance: Another gap in industry practice, paper NACE-2019-12976. NACE
616   International, NACE.

617 6. Kip N, van Veen JA. 2015. The dual role of microbes in corrosion. The ISME Journal 9:542–
618   551.

619 7. Enning D, Garrelfs J. 2014. Corrosion of iron by sulfate-reducing bacteria: New views of an
620   old problem. Appl Environ Microbiol 80:1226–1236.

621 8. Enning D, Venzlaff H, Garrelfs J, Dinh HT, Meyer V, Mayrhofer K, Hassel AW, Stratmann
622   M, Widdel F. 2012. Marine sulfate-reducing bacteria cause serious corrosion of iron under
623   electroconductive biogenic mineral crust. Environ Microbiol 14:1772–1787.

624 9. Venzlaff H, Enning D, Srinivasan J, Mayrhofer KJJ, Hassel AW, Widdel F, Stratmann M.
625   2013. Accelerated cathodic reaction in microbial corrosion of iron due to direct electron
626   uptake by sulfate-reducing bacteria. Corros Sci 66:88–96.

10. Sharma M, Liu H, Chen S, Cheng F, Voordouw G, Gieg L. 2018. Effect of selected biocides

on microbiologically influenced corrosion caused by *Desulfovibrio ferrophilus* IS5. 1. Sci

Rep 8:16620.

11. Deng X, Dohmae N, Nealson KH, Hashimoto K, Okamoto A. 2018. Multi-heme cytochromes

provide a pathway for survival in energy-limited environments. Sci Adv 4:eaao5682.

12. Zhang T, Fang HHP, Ko BCB. 2003. Methanogen population in a marine biofilm corrosive

to mild steel. Appl Microbiol Biotechnol 63:101–106.

13. Dinh HT, Kuever J, Mußmann M, Hassel AW, Stratmann M, Widdel F. 2004. Iron corrosion

by novel anaerobic microorganisms. Nature 427:829–832.

14. Uchiyama T, Ito K, Mori K, Tsurumaru H, Harayama S. 2010. Iron-corroding methanogen

isolated from a crude-oil storage tank. Appl Environ Microbiol 76:1783–1788.

15. Usher KM, Kaksonen AH, MacLeod ID. 2014. Marine rust tubercles harbour iron corroding

archaea and sulphate reducing bacteria. Corros Sci 83:189–197.

16. Okoro C, Smith S, Chiejina L, Lumactud R, An D, Park HS, Voordouw J, Lomans BP,

Voordouw G. 2014. Comparison of microbial communities involved in souring and corrosion

in offshore and onshore oil production facilities in Nigeria. J Ind Microbiol Biotechnol

41:665–678.

17. Mand J, Park HS, Okoro C, Lomans BP, Smith S, Chiejina L, Voordouw G. 2016. Microbial

methane production associated with carbon steel corrosion in a Nigerian oil field. Front

Microbiol 6:1538.

18. Kip N, Jansen S, Leite MFA, de Hollander M, Afanasyev M, Kuramae EE, Veen JAV. 2017.

Methanogens predominate in natural corrosion protective layers on metal sheet piles. Sci Rep

7:11899.

19. Palacios PA, Snoeyenbos-West O, Löscher CR, Thamdrup B, Rotaru A-E. 2019. Baltic Sea

methanogens compete with acetogens for electrons from metallic iron. 12. ISME J 13:3011–

3023.

20. Daniels L, Belay N, Rajagopal BS, Weimer PJ. 1987. Bacterial methanogenesis and growth

from CO_2 with elemental iron as the sole source of electrons. Science 237:509–511.

21. Beese-Vasbender PF, Grote J-P, Garrelfs J, Stratmann M, Mayrhofer KJJ. 2015. Selective

microbial electrosynthesis of methane by a pure culture of a marine lithoautotrophic

archaeon. Bioelectrochemistry 102:50–55.

22. An BA, Kleinbub S, Ozcan O, Koerdt A. 2020. Iron to gas: Versatile multiport flow-column

revealed extremely high corrosion potential by methanogen-induced microbiologically

influenced corrosion (Mi-MIC). Front Microbiol 11:527.

23. Deutzmann JS, Sahin M, Spormann AM. 2015. Extracellular enzymes facilitate electron

uptake in biocorrosion and bioelectrosynthesis. mBio 6:e00496-15.

24. Tsurumaru H, Ito N, Mori K, Wakai S, Uchiyama T, Iino T, Hosoyama A, Ataku H, Nishijima

K, Mise M, Shimizu A, Harada T, Horikawa H, Ichikawa N, Sekigawa T, Jinno K, Tanikawa

S, Yamazaki J, Sasaki K, Yamazaki S, Fujita N, Harayama S. 2018. An extracellular [NiFe]

hydrogenase mediating iron corrosion is encoded in a genetically unstable genomic island in

Methanococcus maripaludis. Sci Rep 8:15149.

25.   Skovhus TL, Eckert RB, Rodrigues E. 2017. Management and control of microbiologically

influenced corrosion (MIC) in the oil and gas industry—Overview and a North Sea case

study. J Biotechnol 256:31–45.

26.   Kaye JZ, Márquez MC, Ventosa A, Baross JA. 2004. *Halomonas neptunia* sp. nov.,

Halomonas sulfidaeris sp. nov., *Halomonas axialensis* sp. nov. and *Halomonas*

hydrothermalis sp. nov.: halophilic bacteria isolated from deep-sea hydrothermal-vent

environments. Int J Syst Evol Microbiol 54:499–511.

27.   Sousa DZ, Smidt H, Alves MM, Stams AJM. 2007. *Syntrophomonas zehnderi* sp. nov., an

anaerobe that degrades long-chain fatty acids in co-culture with *Methanobacterium*

formicicum. Int J Syst Evol Microbiol 57:609–615.

28.   Nunoura T, Hirai M, Imachi H, Miyazaki M, Makita H, Hirayama H, Furushima Y,

Yamamoto H, Takai K. 2010. *Kosmotoga arenicorallina* sp. nov. a thermophilic and

obligately anaerobic heterotroph isolated from a shallow hydrothermal system occurring

within a coral reef, southern part of the Yaeyama Archipelago, Japan, reclassification of

Thermococcoides shengliensis as *Kosmotoga shengliensis* comb. nov., and emended

description of the genus *Kosmotoga*. Arch Microbiol 192:811–819.

29.   Huber R, Woese CR, Langworthy TA, Kristjansson JK, Stetter KO. 1990. *Fervidobacterium*

islandicum sp. nov., a new extremely thermophilic eubacterium belonging to the

Thermotogales. Arch Microbiol 154:105–111.

30. Ravot G, Ollivier B, Magot M, Patel B, Crolet J, Fardeau M, Garcia J. 1995. Thiosulfate

reduction, an important physiological feature shared by members of the order *Thermotogales.*

Appl Environ Microbiol 61:2053–2055.

31. Miroshnichenko ML, Kostrikina NA, Chernyh NA, Pimenov NV, Tourova TP, Antipov AN,

Spring S, Stackebrandt E, Bonch-Osmolovskaya EA. 2003. *Caldithrix abyssi* gen. nov., sp.

nov., a nitrate-reducing, thermophilic, anaerobic bacterium isolated from a Mid-Atlantic

Ridge hydrothermal vent, represents a novel bacterial lineage. Int J Syst Evol Microbiol

53:323–329.

32. Waard C de, Lotz U, Dugstad A. 1995. Influence of liquid flow velocity on CO_2 corrosion:

A semi-empirical model. paper 106125, Corrosion '95 conference, NACE International,

NACE.

33. Liu T, Cheng YF, Sharma M, Voordouw G. 2017. Effect of fluid flow on biofilm formation

and microbiologically influenced corrosion of pipelines in oilfield produced water. J Petrol

Sci Eng 156:451–459.

34. Duncan KE, Gieg LM, Parisi VA, Tanner RS, Tringe SG, Bristow J, Suflita JM. 2009.

Biocorrosive thermophilic microbial communities in Alaskan North Slope oil facilities.

Environ Sci Technol 43:7977–7984.

35. Vigneron A, Alsop EB, Chambers B, Lomans BP, Head IM, Tsesmetzis N. 2016.

Complementary microorganisms in highly corrosive biofilms from an offshore oil production

facility. Appl Environ Microbiol 82:2545–2554.

36. Mori K, Tsurumaru H, Harayama S. 2010. Iron corrosion activity of anaerobic hydrogen-

consuming microorganisms isolated from oil facilities. J Biosci Bioeng 110:426–430.

37. Bockris JO, Reddy AKN, Gamboa-Aldeco ME. 2000. Modern electrochemistry 2A:

Fundamentals of electrodics, Springer-Verlag, New York, NY

38. Kaesche H. 2003. Corrosion of metals: Physicochemical principles and current problems.

Springer-Verlag, Berlin Heidelberg.

39. Kahyarian A, Brown B, Nešić S. 2020. The unified mechanism of corrosion in aqueous weak

acids solutions: A review of the recent developments in mechanistic understandings of mild

steel corrosion in the presence of carboxylic acids, carbon dioxide, and hydrogen sulfide.

Corrosion 76:268–278.

40. von Wolzogen Kühr CAH, van der Vlugt LS. 1934. The graphitization of cast iron as an

electrobiochemical process in anaerobic soil. Water 18:147–165.

41. Starkey RL. 1947. Sulfate reduction and the anaerobic corrosion of iron. Antonie van

Leeuwenhoek 12:193–203.

42. Butlin KR, Adams ME, Thomas M. 1949. Sulphate-reducing bacteria and internal corrosion

of ferrous pipes conveying water. Nature 163:26–27.

43. Cord-Ruwisch R. 2000. Microbially influenced corrosion of steel, p. 159–173. *In* Loveley

DR (ed), Environmental microbe-metal interactions. ASM Press, Washington, DC.

44. Barker R, Burkle D, Charpentier T, Thompson H, Neville A. 2018. A review of iron carbonate

($FeCO_3$) formation in the oil and gas industry. Corros Sci 142:312–341.

45. Deutzmann JS, Spormann AM. 2017. Enhanced microbial electrosynthesis by using defined
co-cultures. 3. ISME J 11:704–714.

46. Chen Y, Tang Q, Senko JM, Cheng G, Zhang Newby B, Castaneda H, Ju L-K. 2015. Long-
term survival of *Desulfovibrio vulgaris* on carbon steel and associated pitting corrosion.
Corros Sci 90:89–100.

47. Deng X, Dohmae N, Kaksonen AH, Okamoto A. 2020. Biogenic iron sulfide nanoparticles
to enable extracellular electron uptake in sulfate-reducing bacteria. Angew Chem Int Ed
132:6051–6055.

48. Krantz GP, Lucas K, Wunderlich EL-, Hoang LT, Avci R, Siuzdak G, Fields MW. 2019.
Bulk phase resource ratio alters carbon steel corrosion rates and endogenously produced
extracellular electron transfer mediators in a sulfate-reducing biofilm. Biofouling 35:669–
683.

49. Wikieł AJ, Datsenko I, Vera M, Sand W. 2014. Impact of *Desulfovibrio alaskensis* biofilms
on corrosion behaviour of carbon steel in marine environment. Bioelectrochemistry 97:52–
60.

50. Little BJ, Blackwood DJ, Hinks J, Lauro FM, Marsili E, Okamoto A, Rice SA, Wade SA,
Flemming H-C. 2020. Microbially influenced corrosion—Any progress? Corros Sci
170:108641.

51. Tejerizo GT, Kim YS, Maus I, Wibberg D, Winkler A, Off S, Pühler A, Scherer P, Schlüter
A. 2017. Genome sequence of *Methanobacterium congolense* strain Buetzberg, a

hydrogenotrophic, methanogenic archaeon, isolated from a mesophilic industrial-scale

biogas plant utilizing bio-waste. J Biotechnol 247:1–5.

52. Widdel F, Bak F. 1992. Gram-negative mesophilic sulfate-reducing bacteria, p. 3352–3378.

In Balows A, Truper HG, Dworkin M, Harder W, Schleifer K-H (ed), The prokaryotes, 2nd

ed, vol 4. Springer-Verlag, New York, NY.

53. Suzuki MT, Taylor LT, DeLong EF. 2000. Quantitative analysis of small-subunit rRNA

genes in mixed microbial populations via 5′-nuclease assays. Appl Environ Microbiol

66:4605–4614.

54. Yu Y, Lee C, Kim J, Hwang S. 2005. Group-specific primer and probe sets to detect

methanogenic communities using quantitative real-time polymerase chain reaction.

Biotechnol Bioeng 89:670–679.

55. Altschul SF, Gish W, Miller W, Myers EW, Lipman DJ. 1990. Basic local alignment search

tool. J Mol Biol 215:403–410.

56. Caporaso JG, Kuczynski J, Stombaugh J, Bittinger K, Bushman FD, Costello EK, Fierer N,

Peña AG, Goodrich JK, Gordon JI, Huttley GA, Kelley ST, Knights D, Koenig JE, Ley RE,

Lozupone CA, McDonald D, Muegge BD, Pirrung M, Reeder J, Sevinsky JR, Turnbaugh PJ,

Walters WA, Widmann J, Yatsunenko T, Zaneveld J, Knight R. 2010. QIIME allows analysis

of high-throughput community sequencing data. Nat Methods 7:335–336.

57. Cole JR, Wang Q, Fish JA, Chai B, McGarrell DM, Sun Y, Brown CT, Porras-Alfaro A,

Kuske CR, Tiedje JM. 2014. Ribosomal database project: data and tools for high throughput

rRNA analysis. Nucleic Acids Res 42:D633–D642.

58. Quast C, Pruesse E, Yilmaz P, Gerken J, Schweer T, Yarza P, Peplies J, Glöckner FO. 2013.

The SILVA ribosomal RNA gene database project: improved data processing and web-based

tools. Nucleic Acids Res 41:D590–D596.

59. Arkin AP, Cottingham RW, Henry CS, Harris NL, Stevens RL, Maslov S, Dehal P, Ware D,

Perez F, Canon S, Sneddon MW, Henderson ML, Riehl WJ, Murphy-Olson D, Chan SY,

Kamimura RT, Kumari S, Drake MM, Brettin TS, Glass EM, Chivian D, Gunter D, Weston

DJ, Allen BH, Baumohl J, Best AA, Bowen B, Brenner SE, Bun CC, Chandonia J-M, Chia

J-M, Colasanti R, Conrad N, Davis JJ, Davison BH, DeJongh M, Devoid S, Dietrich E,

Dubchak I, Edirisinghe JN, Fang G, Faria JP, Frybarger PM, Gerlach W, Gerstein M, Greiner

A, Gurtowski J, Haun HL, He F, Jain R, Joachimiak MP, Keegan KP, Kondo S, Kumar V,

Land ML, Meyer F, Mills M, Novichkov PS, Oh T, Olsen GJ, Olson R, Parrello B, Pasternak

S, Pearson E, Poon SS, Price GA, Ramakrishnan S, Ranjan P, Ronald PC, Schatz MC, Seaver

SMD, Shukla M, Sutormin RA, Syed MH, Thomason J, Tintle NL, Wang D, Xia F, Yoo H,

Yoo S, Yu D. 2018. KBase: The United States department of energy systems biology

knowledgebase. Nat Biotechnol 36:566–569.

60. Nurk S, Meleshko D, Korobeynikov A, Pevzner PA. 2017. metaSPAdes: a new versatile

metagenomic assembler. Genome Res 27:824–834.

61. Kang DD, Li F, Kirton E, Thomas A, Egan R, An H, Wang Z. 2019. MetaBAT 2: an adaptive

binning algorithm for robust and efficient genome reconstruction from metagenome

assemblies. PeerJ 7:e7359.

62. Parks DH, Imelfort M, Skennerton CT, Hugenholtz P, Tyson GW. 2015. CheckM: assessing

the quality of microbial genomes recovered from isolates, single cells, and metagenomes.

Genome Res 25:1043–1055.

63. Chaumeil P-A, Mussig AJ, Hugenholtz P, Parks DH. 2020. GTDB-Tk: a toolkit to classify

genomes with the Genome Taxonomy Database. Bioinformatics 36:1925–1927.

64. Tatusova T, DiCuccio M, Badretdin A, Chetvernin V, Nawrocki EP, Zaslavsky L, Lomsadze

A, Pruitt KD, Borodovsky M, Ostell J. 2016. NCBI prokaryotic genome annotation pipeline.

Nucleic Acids Res 44:6614–6624.

65. Haft DH, DiCuccio M, Badretdin A, Brover V, Chetvernin V, O'Neill K, Li W, Chitsaz F,

Derbyshire MK, Gonzales NR, Gwadz M, Lu F, Marchler GH, Song JS, Thanki N, Yamashita

RA, Zheng C, Thibaud-Nissen F, Geer LY, Marchler-Bauer A, Pruitt KD. 2018. RefSeq: an

update on prokaryotic genome annotation and curation. Nucleic Acids Res 46:D851–D860.

66. Seemann T. 2014. Prokka: rapid prokaryotic genome annotation. Bioinformatics 30:2068–

2069.

TABLE AND FIGURE CAPTIONS

Table 1 Sequences of degenerate primer pair and probe used in qPCR assays to detect the

proposed methanogenic MIC biomarker *micH*.

Table 2 Metagenome-assembled genomes (MAG) of methanogenic and sulfate-reducing

microorganisms in severely corrosive biofilm.

Figure 1 Archaeal community composition in solid samples (pig debris) collected from carbon

steel pipelines. Archaeal sequences accounted for between 0.2% and 21.6% of all reads from 16S

rRNA gene sequencing of DNA extracted from pipeline solids (top row). Total 16S rRNA gene

numbers (archaeal + bacterial) and gene copy numbers of the proposed methanogenic MIC

biomarker *micH* are also plotted for each sample. Pipelines (A – H) are ordered according to their

perceived severity of MIC (increasing from left to right, as indicated by arrow). The perceived

(qualitative) severity of MIC is based on inspection data (in-line inspection, ILI), field and

laboratory studies, as well as operator experience. A: Offshore multi-phase pipeline (East Asia).

B: Offshore crude transmission pipeline (U.S. Gulf of Mexico). C: Offshore multi-phase pipeline

(U.S. West Coast). D: Onshore crude transmission pipeline (U.S. Gulf Cast). E: Onshore crude

transmission pipeline (U.S. West Coast). F: Onshore produced water pipeline (U.S. Midwest). G:

Offshore multi-phase pipeline (Nigeria). H: Offshore multi-phase pipeline (U.S. West Coast). I:

Offshore multi-phase pipeline (Nigeria).

Figure 2 Growth of steel-attached oil field biofilms in bottle tests. A – C Tests with sulfate-free

anoxic produced water as obtained from the West African oil field and incubated under mesophilic

(32°C) and thermophilic (60°C) conditions. D – F Tests with sulfate-amended produced water, as

well as synthetic produced water media (+ sulfate) in the presence or absence of propionate and

acetate (organotrophic and lithotrophic conditions, respectively).). A and D Averaged weight loss

corrosion rates (CR), total 16S rRNA gene (archaeal + bacterial) quantification and gene copy

numbers of the proposed archaeal MIC biomarker *micH*. A threshold denoting technically relevant,

high corrosion rates (≥ 0.13 mm Fe^0 yr^{-1}) is indicated by the dashed red line. Methane formation

is depicted as final concentration in headspace after 3 months (A). Archaeal (B and E) and bacterial

(C and F) community composition was assessed by 16S rRNA gene sequencing of DNA extracted

from biofilms grown on carbon steel coupons. Archaeal sequences account for 0.1 – 54.4% and

bacterial sequences for 40.3 – 99.8% of the total sequencing reads. The enrichment culture that

was used for a subsequent lithotrophic corrosion kettle test is indicted by an asterisk.

Figure 3 Growth of steel-attached oil field biofilms in corrosion kettle tests. A) Schematic of

customized corrosion kettles for the study of CO_2 corrosion and MIC under pipeline-simulating

conditions (flow and acid-gas purging). B) Averaged weight loss corrosion rates (CR) in anoxic

kettle tests containing oil field microorganisms in West African produced water, as well as

synthetic produced water media with or without addition of the organic electron donors acetate

and propionate (organotrophic and lithotrophic conditions, respectively). A sterile control test

quantifying CO_2 corrosion was also included. Total 16S rRNA gene (archaeal + bacterial)

quantification and gene copy numbers of the proposed archaeal MIC biomarker *micH* in coupon

biofilms are plotted for each test. A threshold denoting technically relevant, high corrosion rates

(≥ 0.13 mm Fe^0 yr^{-1}) is indicated by the dashed red line. False color images show the topography

of coupons at the end of the experiments after removal of corrosion products. The average maximal

feature depth from four steel coupons per test and corresponding linearly extrapolated pitting

corrosion rates are provided in the sub-panel. The asterisk indicates the test selected for

metagenomic analysis.

Figure 4 Comparison of the genetic arrangement of the 'MIC island' in *Methanococcus*

maripaludis strain OS7 (MMOS7) and the metagenome-assembled genome (MIC098Bin5) of a

M. maripaludis strain grown on severely corroded steel surfaces. The scale bars indicate the

nucleotide position in the individual genomes.

Figure 1 Archaeal community composition in solid samples (pig debris) collected from carbon steel pipelines. Archaeal sequences accounted for between 0.2% and 21.6% of all reads from 16S rRNA gene sequencing of DNA extracted from pipeline solids (top row). Total 16S rRNA gene numbers (archaeal + bacterial) and gene copy numbers of the proposed methanogenic MIC biomarker *micH* are also plotted for each sample. Pipelines (A – H) are ordered according to their perceived severity of MIC (increasing from left to right, as indicated by arrow). The perceived (qualitative) severity of MIC is based on inspection data (in-line inspection, ILI), field and laboratory studies, as well as operator experience. A: Offshore multi-phase pipeline (East Asia). B: Offshore crude transmission pipeline (U.S. Gulf of Mexico). C: Offshore multi-phase pipeline (U.S. West Coast). D: Onshore crude transmission pipeline (U.S. Gulf Cast). E: Onshore crude transmission pipeline (U.S. West Coast). F: Onshore produced water pipeline (U.S. Midwest). G: Offshore multi-phase pipeline (Nigeria). H: Offshore multi-phase pipeline (U.S. West Coast). I: Offshore multi-phase pipeline (Nigeria).

Figure 2 Growth of steel-attached oil field biofilms in bottle tests. A – C Tests with sulfate-free anoxic produced water as obtained from the West African oil field and incubated under mesophilic (32°C) and thermophilic (60°C) conditions. D – F Tests with sulfate-amended produced water, as well as synthetic produced water media (+ sulfate) in the presence or absence of propionate and acetate (organotrophic and lithotrophic conditions, respectively).). A and D Averaged weight loss corrosion rates (CR), total 16S rRNA gene (archaeal + bacterial) quantification and gene copy numbers of the proposed archaeal MIC biomarker *micH*. A threshold denoting technically relevant, high corrosion rates ($\geq$ 0.13 mm Fe0 yr-1) is indicated by the dashed red line. Methane formation is depicted as final concentration in headspace after 3 months (A). Archaeal (B and E) and bacterial (C and F) community composition was assessed by 16S rRNA gene sequencing of DNA extracted from biofilms grown on carbon steel coupons. Archaeal sequences account for 0.1 – 54.4% and bacterial sequences for 40.3 – 99.8% of the total sequencing reads. The enrichment culture that was used for a subsequent lithotrophic corrosion kettle test is indicted by an asterisk.

Figure 3 Growth of steel-attached oil field biofilms in corrosion kettle tests. A) Schematic of customized corrosion kettles for the study of CO_2 corrosion and MIC under pipeline-simulating conditions (flow and acid-gas purging). B) Averaged weight loss corrosion rates (CR) in anoxic kettle tests containing oil field microorganisms in West African produced water, as well as synthetic produced water media with or without addition of the organic electron donors acetate and propionate (organotrophic and lithotrophic conditions, respectively). A sterile control test quantifying CO_2 corrosion was also included. Total 16S rRNA gene (archaeal + bacterial) quantification and gene copy numbers of the proposed archaeal MIC biomarker *micH* in coupon biofilms are plotted for each test. A threshold denoting technically relevant, high corrosion rates (≥ 0.13 mm Fe^0 yr^{-1}) is indicated by the dashed red line. False color images show the topography of coupons at the end of the experiments after removal of corrosion products. The average maximal feature depth from four steel coupons per test and corresponding linearly extrapolated pitting corrosion rates are provided in the sub-panel. The asterisk indicates the test selected for metagenomic analysis.

Figure 4 Comparison of the genetic arrangement of the 'MIC island' in *Methanococcus maripaludis* strain OS7 (MMOS7) and the metagenome-assembled genome (MIC098Bin5) of a *M. maripaludis* strain grown on severely corroded steel surfaces. The scale bars indicate the nucleotide position in the individual genomes.

Table 1 Sequences of degenerate primer pair and probe used in qPCR assays to detect the proposed methanogenic MIC biomarker *micH*.

Primer/Probe	Sequence (5' → 3')[a]	Product length (bp)
micH-fwd	AA(Y)CTTCTAACACCAA(M)TGA(Y)GGAAC	95
micH-rev	TCAAATCCTCTAAATTCTGTGACACA	
micH-probe	TACCAACAGATAATGCTGCA	

[a] M = A or C; Y = C or T

Table 2 Metagenome-assembled genomes (MAG) of methanogenic and sulfate-reducing microorganisms in severely corrosive biofilm.

Taxonomic assignment [a]	Total sequence length (bp)	No. Contigs	N50	L50	Completeness [b]	Contamination [b]
Methanococcus maripaludis	1,702,487	5	989,172	1	99.5%	0.5
Desulfovibrio alaskensis	3,270,933	67	84,479	12	99.4%	0.0
Desulfovibrionaceae	3,278,183	87	63,483	16	99.4%	0.0
Desulfovibrionaceae	4,247,882	120	82,594	15	99.4%	0.0

[a] Taxonomic assignment is based on GTDB-Tk classification; [b] Completeness and contamination was estimated using CheckM