Auxetic Two-Dimensional Nanostructures from DNA

Ruixin Li[†], Haorong Chen[†], and Jong Hyun Choi*.
School of Mechanical Engineering, Purdue University, West Lafayette, Indiana 47907
*Corresponding author: jchoi@purdue.edu
† Equal contribution

ABSTRACT
Architectured materials exhibit negative Poisson's ratios and possess enhanced mechanical properties compared with regular materials. Their auxetic behaviors emerge from periodic cellular structures rather than chemistry. The majority of such metamaterials are constructed by top-down approaches and macroscopic with unit cells of microns or larger. On the other extreme, there are molecular-scale auxetics including naturally-occurring crystals which are not designable. There is a gap from few nanometers to microns, which may be filled by bottom-up biomolecular self-assembly. Here we demonstrate two-dimensional (2D) auxetic nanostructures using DNA origami. Structural deformation experiments are performed by strand displacement and complemented by mechanical deformation studies using coarse-grained molecular dynamics (MD) simulations. We find that the auxetic properties of DNA nanostructures are mostly defined by geometrical designs, yet materials' chemistry also plays a role. From elasticity theory, we introduce a set of design principles for auxetic DNA materials which should be useful for diverse applications.

KEYWORDS
DNA origami, self-assembly, auxetic, metamaterials, negative Poisson's ratio, mechanics

INTRODUCTION

Architectured auxetic materials have received significant attention due to their exotic behaviors and properties. They exhibit a negative Poisson's ratio (v) and possess significantly improved indentation resistance[1], greater shear modulus[2], and enhanced fracture toughness[3] compared with regular materials. These characteristics are believed to emerge from their periodic cellular structures rather than materials and related chemistries, forming the basis of mechanical metamaterials.[4] Most of auxetic architectures are manufactured by top-down approaches using metals[5], polymers[6], and fibers[7]. Their unit cells range from microns to centimeters, forming macroscopic bulk materials. On the other extreme, there are molecular-scale auxetics, including α-cristobalite and cubic metals, whose unit cell sizes are on the order of few chemical bond lengths.[8-10] These naturally-occurring crystals are not designable. Synthetically, metal-organic frameworks (MOFs) have been theorized as auxetic building blocks, yet the concept has not been demonstrated clearly through experiments.[11,12] Thus, there is a wide gap from few nanometers to microns for well-defined auxetic unit structures. As part of bottom-up approaches, biomolecular self-assembly is ideal to create custom-designed auxetic nanoarchitectures, filling the gap. Further, such nanostructures could also serve as a platform to examine any possible effects of materials on auxetic behaviors and mechanical properties, which have been difficult to study to date.

Here we demonstrate auxetic two-dimensional (2D) nanostructures using wireframe DNA origami and elucidate relevant mechanics. DNA origami is a widely used self-assembly method for creating arbitrary nanoarchitectures with excellent programmability and structural predictability.[13-16] We constructed DNA nanostructures, composed of one or few unit cells, and achieved their auxetic transformations via strand displacement. Atomic force microscopy (AFM) measured the origami conformations, from which Poisson's ratios were calculated. Coarse-grained molecular dynamics (MD) simulations were performed to observe mechanical deformations upon compressive and tensile forces, extracting structural properties. We found that the auxetic behaviors are largely defined by geometrical designs, but materials' chemistry also plays a role, which shall not be ignored at this very small scale. Based on elastic beam theory, we developed a model that accounts for edge rigidity and joint flexibility, yielding a set of guiding principles for auxetic DNA materials.

Auxetic vs. Regular Structures

To demonstrate DNA auxetics, we chose a well-studied, re-entrant honeycomb structure[17]. When expanding (or shrinking) in one direction, this periodic structure will react the same way in the orthogonal direction, as illustrated by (i)–(iii) in Figure 1a. In contrast, its conjugate, regular honeycomb, will do the opposite ((iii)–(v) in Figure 1a). In our design, each origami includes four intact unit cells (bold lines in Figure 1a), where edges and multi-arm joints at vertices form a wireframe structure.[18-21] Specifically, two double-stranded DNA (dsDNA) helices form an edge (Figure 1b, black), and single-stranded DNA (ssDNA) segments are used for the joint (Figures S2, S3, also see SI for design details). In addition, we added 'jack' edges shown in red in Figure 1b whose length can be changed to modulate the angle (γ indicated by the red dot) and have different conformations. For example, the structure is largest at 90° with the jacks fully stretched. As the jack length is shortened to make the angle 60° and then 30°, both the height and width, represented by y_1 and x_1, respectively, become shorter, thus resulting in a shrinkage of the entire structure ((i)–(iii) in Figure 1b). The Poisson's ratio may be expressed as a function of γ,

$$v = \frac{(\cos\gamma - l/s)\cos\gamma}{\sin^2\gamma} \tag{1}$$

where l and m are lengths of edges. Equation 1 is plotted as black curve in Figure 1c. v is 0 at 90° and marches toward negative and positive infinity at $\gamma = 0$° and 180°, respectively.

To induce positive v, the jacks must be elongated, forming the regular honeycomb. Due to the size limitation of the scaffold (M13mp18), we designed another, smaller regular honeycomb that can stretch as the jack length increases and the angle transforms from 90° to 120° and then to 145° as shown in (iv)–(vi) of Figure 1b (also see Figure S2, S3). Our design includes joints with different lengths of ssDNA for a range of γ (Tables S3.1, S3.2). For example, 6 nucleotides (6-nt) were used at a joint for 90–145°. The ssDNA joint provides a degree of freedom and flexibility for structural transformation. Since the scales of re-entrant and regular honeycomb structures are different, dimensionless width and height (x/x_0 and y/y_0) are plotted as a function of γ with the reference states (x_0 and y_0) set at $\gamma = 90$° (Figure 1d). It is evident that the width increases monotonically with γ, while the height shows opposite trends for negative and positive γ. The height vs. width plot in Figure 1e shows that the height of the re-entrant structure increases with expanding width, whereas it decreases in the regular honeycomb.

MD simulations were performed based on the coarse-grained model using oxDNA[22,23] to estimate the origami conformations. The structures with different jack edges were created in caDNAno2[24] and subsequently converted into oxDNA files for initial conformations. Each conformation was then set at 4 °C to reach an equilibrium state in the simulation. Figure 1f presents the equilibrium conformations where all the unit cells show symmetry within themselves and between neighboring units. The simulated structures reasonably follow the corresponding designs in Figure 1b. Origami structures were synthesized and visualized by AFM (see SI for experimental details and additional AFM images). The AFM images look alike the corresponding designs and simulations (Figure 1g, Figure S25–S30). In the structures with short jacks, the unused scaffold segments also show up in the AFM images, somewhat interfering with the geometrical designs. Measurements on the experimental results are plotted as filled circles in Figure 1c–e, along with the theoretical calculations (Figures S8). The computational and experimental results suggest the feasibility of the origami-based approach for nanoscale auxetics.

Structural Transformation via Chemical Stimuli
To demonstrate auxetic deformation, we used a simpler, re-entrant triangle structure (Figure 2a). The re-entrant triangle may be considered as a reduced structure from the re-entrant honeycomb where two edges are shrunk to a point (see Figure S4). It thus behaves alike the re-entrant honeycomb and can display simultaneous expansion (or compression) in two orthogonal directions. In our design, the re-entrant triangle origami has quadrilateral unit-cells (Figure 2b), where each edge is made of two dsDNA and every joint consists of ssDNA segments (Figure S5). The jack edges, shown in red, are also included to enable structural deformation. Despite the structural simplicity, it is still difficult to apply mechanical loads accurately onto nanostructures.[25] Hence, we used chemical loads instead to modulate the jack length through toehold-mediated strand displacement,[26-28] thereby resulting in reconfiguration, either expansion or shrinkage. For example, the re-entrant triangle can switch between 30° and 58° as shown in Figure 2b, by modulating the jack length of approximately 45 or 59 nm (6 or 8 full turns), respectively.

Figure 2c–d shows the re-entrant triangle structures in two distinct states from MD simulations and AFM measurements (Figures S31, S32). Experimentally, we first added invading strands to

remove the staples from the jack edges initially in an equilibrium, followed by addition of another set of staples to form the jacks with a different length. As a result, the triangle can transform from 58° to 30°, and vice versa. Figure 2e presents the angle dependence of v based on the measurements from experiments and simulations. Although the computational and experimental results generally follow the designs, curved edges and blunt joints are quite noticeable. These issues are caused by the design model which fundamentally assumes infinitely rigid edges and infinitely flexible joints (termed *infinite* model), as in typical architectured metamaterials studies. They may be more pronounced at the nanoscale where materials properties must be accounted for (*vide infra*).

Mechanical Deformation in MD Simulations
Next, we performed mechanical deformations using oxDNA simulations, where external mechanical forces were applied directly on the re-entrant triangle origami. In the equilibrium structure, the jack edges were cut to free up space (Figure 3a–b; Figure S24) which was subsequently subject to loading. During the deformation, forces and displacements were recorded and converted into stress-strain (Figure 3c, solid triangles), from which Young's modulus E in loading direction (E_1) was calculated. The computational results show the angle dependence, and E_1 is on the order of few pN/nm^2, significantly lower than that of dsDNA (~100 pN/nm^2).[29-31] The small Young's modulus is common in cellular structures, especially due to ssDNA (~1 pN/nm^2) at the joints,[32] serving as the determinant of E_1. To better understand the mechanics, we developed a model that accounts for finite rigidity in edges and finite flexibility in joints (which we term *finite* model; see detailed derivation in S4.2). The model includes three deformation modes, flexing, stretching and hinging, which all resemble the Hooke's law.[33]

$$K_{\text{mode}} = \left(\frac{F}{\delta}\right)_{\text{mode}} \tag{2}$$

With all the force constants (K_f, K_s, and K_h), displacement in the loading direction Δx can be expressed as a sum of displacements in different modes (δ_{mode}) projected along the loading direction, yielding the relationship between the force and displacement at any given angle. By integration, the total force (F_{total}) that transforms the origami from the initial (γ_i) to the final angle (γ_f) is calculated. With knowledge of F_{total} vs. Δx, the stress (σ_{total}) and the strain ($\varepsilon_{1,\text{total}}$) are calculated, from which E_1 is obtained.

$$E_1 = \frac{\sigma_{\text{total}}}{\varepsilon_{1,\text{total}}} \tag{3}$$

This model predicts the angle dependence of E_1 (Figure 3c, black curve). As γ decreases, for example, E_1 increases, implying that it is harder to compress the structure as it deforms. The theoretical prediction is in excellent agreement with the data from MD calculations. It should be noted that the finite model also matches well with experiment and simulation results in Figure 2e. Moreover, it shows that even though the components are assumed to have linear elasticity, the overall elastic properties can be nonlinear due to the cellular geometry.

Design Principles
The finite model also allowed us to study curved edges. Upon external loads (F), an internal horizontal force (F_i) is generated to hold the edges in place against falling apart (Figure 3d). As γ increases, F_i/F increases due to an increased tendency to break at larger angles. In contrast, flexure of the edge l per loads (δ_f/F) is not a monotonic function of γ. It increases with γ when γ is small, reaches a plateau, and then decreases at larger angles. This trend results from the competing effects of F_i and F. When γ is small, F_i is the major driving force for δ_f as their directions are almost

aligned. Nearly all F_i contributes to δ_f. However, F_i/F is small at small γ. Thus, δ_f/F is small as well. As γ increases, F_i/F increases, but the directions of F_i and δ_f will diverge. As a result, δ_f/F decreases with increasing γ at large angles. The δ_f/F vs. γ plot reflects, inversely, the trend of overall spring constant of the edge.

As seen in Figure 3c, the structure becomes more rigid as γ decreases. Therefore, to enable compression, the external loads must increase as the structure shrinks. By combining δ_f/F and F, we obtain δ_f/l as a function of γ as shown in Figure 3e where δ_f/l decreases monotonically with increasing γ. Notably, Figure 3e shows significant flexure, particularly at small angles, suggesting a compromised structural integrity. To suppress δ_f, we propose that δ_f should be less than maximum thickness of the edge (t_{max}). To simplify, we consider the loads that contribute directly to the flexure and the linear elastic range that is significantly less than buckling forces (*e.g.*, ≤10%). Thus, we obtain a design requirement on t_{max}/l (see S4.3 for details).

$$\frac{t_{max}}{l} \geq \frac{\pi^2}{120} \approx 0.1 \tag{4}$$

This criterion, shown as the blue shade in Figure 3e, suggests that an edge must have a thickness larger than 10% of its length to avoid any significant curvature.

It is also important to examine the flexibility in multi-edge joints. Auxetic designs assume that a joint at a vertex provides flexibility, allowing the structure to deform in response to external loads. Experimentally, flexibility is realized by adding a ssDNA segment, and the longer segment will have more flexibility. Such a soft joint, however, creates a distance between edges at a joint, resulting in structural uncertainties. Therefore, a balance between structural accuracy and flexibility must be reached in DNA origami. To quantify the flexibility and integrity of a joint, we define the stretch ξ as the ratio of the displacement of ssDNA to the distance. For example, 0% stretch implies that the joint is in a complete relaxation (*i.e.*, loose joint), while 100% indicates a full stretch (*i.e.*, not flexible).

In theory, the structural accuracy is better maintained with a shorter ssDNA segment. We hypothesize that the displacement must be less than the minimum thickness of the edge, for example, $\Delta d \leq 0.8 \times t_{min}$. This criterion yields $\xi \geq 55\%$. In parallel, the joint shall have enough flexibility such that as neighboring edges are pulled around the joint upon loading, the curvature of the edges can be avoided. To satisfy this condition, we propose that δ_f/l must be less than 10%, yielding another criterion of $\xi \leqslant 70\%$ (Figures S19). Combining the two criteria, we obtain a guiding principle for multi-edge joints as indicated as blue shade in Figure 3f.

$$55\% \leq \xi \leq 70\% \tag{5}$$

The equations (4) and (5) provide recommended designs to ensure appropriate edge rigidity and joint stretch/flexibility. To ensure rigid edges without significant flexure, the thickness must meet the requirement; as for the stretch of ssDNA at the vertex, the joint should be in a good balance between structural accuracy and flexibility. The re-entrant triangle deviates the edge criterion at $\gamma \leqslant 26°$ as shown in Figure 3e. The MD simulations also suggest that the stretch of ssDNA joints is approximately 45% (Figure 3f). Thus, the structure appears to have curved edges with blunt joints.

Stiffness Reinforced Rotating Square

We examined the validity of the design strategies with another structure, rotating-square (Figure 4a). This structure, unlike re-entrant honeycomb and triangle, is an isotropic, single unit design (Figure 4b). In theory, 2D isotropic materials should have a range of the Poisson's ratio from -1 to 1, whereas anisotropic structures can have any values of v.[34] The rotating square in particular is centrosymmetric with v = -1. In comparison, the Poisson's ratio of the re-entrant triangle can go below -1.5 and is at approximately -2 at γ = 30°.[35,36]

In our origami design, each edge is stiffened with four dsDNA helices (such that t_{max}/l = 0.1) as shown in the inset of Figure 4b (Figures S6d–m, S14b), and shorter ssDNA segments are used for the joint (Table S3.3), reaching ~60% of stretch. Jack edges are also used, shown in red in Figure 4b. Figure 4c–d shows the MD simulation and experimental results at various angles. It is evident that each edge is nearly straight, there are no blunt joints, and the overall structures are well formed. The agreement between design, simulation, and experiment confirms the applicability of the recommended design guidelines. The measured Poisson's ratios are approximately -1 (Figure 4e). The flexure of the edges and the stretch of the joints are extracted from simulations (Figure 4f, g). The flexure is below the threshold at all angles, suggesting that the edges are strong enough to resist flexing deformation. The stretch ranges from 55 to 70%, indicating that the joints are in modest tension. Compared with re-entrant honeycomb and triangle, the rotating square demonstrates significantly improved structural accuracy. The design guidelines should be generic with various edge cross-section and joint designs.

DISCUSSION
Chemical vs. Mechanical Deformations. In this study, we explored chemical and mechanical loads to enable structural deformations. There are two major steps in chemical deformation: (i) jack-staple release process via toehold-mediated strand-displacement and (ii) recombination process via reannealing. A set of staples for jack edges are removed by fully complementary releaser strands, during which no forces are induced to the structure. After the release process, a new set of staples are added for jack edges, where forces towards the target state are introduced. Therefore, the deformation forces can be estimated by considering the free energy change (ΔG) and the displacement during the recombination process (see S4.5 for details). The averaged force per jack edge in Figure 2 is estimated to be around 55 pN. Since the free energy change is the maximum driving potential for structural transformation, this should be the upper limit of the force. In the computational studies, the displacements are caused directly by the applied forces. During the structural deformations, the force is relatively small at the beginning, and then it increases and reach the final value of ~41 pN in Figure 3. The calculated force is the minimum needed for mechanical deformation, thus it is smaller than the force associated with chemical deformation.

Validity of Design Requirements. The design requirements in equations 4 and 5 are consistent with previous reports. Yan *et al.* explored the edge rigidity in wireframe DNA origami using single and two dsDNA helices.[18,21] The t_{max}/l used is $\geq$ 0.1 for single and two dsDNA, which satisfies equation 4. Seeman and colleagues found that the more helices are used, the longer the persistence length a DNA edge has.[37] They further noted that the increase of persistence length does not result from the addition of helices, but rather originate from the enhanced thickness associated with a given bend axis. This directional dependence is accounted for in our derivation and simplified using the maximum thickness in equation 4.

For joint flexibility, Saleh and coworkers studied the elasticity of ssDNA with different sequences and found that when the strands are in 60% or greater of their fully-stretched lengths, their mechanical behaviors are similar regardless of sequences.[38] Under this condition, base-stacking, a sequence-dependent interaction, is no longer effective such that Young's modulus of ssDNA becomes nearly uniform. This sequence independence is critical for the design process because it is difficult to specify the sequence of ssDNA joints for a given scaffold. Bathe and colleagues reported multiple autonomously designed wireframe DNA origami structures using 0.42 nm/base for ssDNA segments at the joints.[39] Assuming the length of fully stretched ssDNA of ~0.63 nm/base,[40] the stretch used was approximately 67%, agreeing with equation 5.

We also examined the design requirements for edges and joints using honeycomb structures. The stretch values are mostly lower than 55% in both regular and re-entrant honeycombs (Figure S21), indicating the joints are under-stretched (*i.e.*, too loose). Their edges are slightly less rigid than the requirement by equation 4 (Table S4.2). As a result, the honeycombs show blunt joints and minor curved edges as seen in Figure 1f–g. In addition, we tested another control design of re-entrant triangle with weak edges and loose joints. Its designed t_{max}/l is ~5%, significantly lower than the requirement set by equation 4 (Figure S7, Table S4.2), and the joints are mostly under-stretched (Figure S22). As a result, this control structure does not reasonably follow the re-entrant triangle design and appears significantly worse than the original re-entrant triangle (Figure S36–37). Overall, the edges and joints must satisfy the respective design requirements, together ensuring the integrity of the periodic cellular structures.

Infinite vs. Finite Models. This study explores both infinite and finite models using wireframe DNA origami for nanoscale auxetics. The infinite model describes ideal design strategies for auxetic metamaterials, while the finite model accounts for the mechanics of DNA. Regardless of the model used in the design, the requirement on edges in equation 4 should be met if possible. Under the infinite model, the most suitable cross-section of edges and the overall size of the structure are determined by the total length of the scaffold. Ideally, a joint is a flexible point connecting edges. However, a wireframe origami uses soft spacers made of ssDNA. The number of nucleotides at a joint may be calculated based on the stretch level (*e.g.* ~60% or ~0.38 nm/base) to ensure sufficient flexibility while maintaining structural integrity. In most cases, this is a quick and reasonable approach, especially when the structures are static. For dynamic structures, it may be difficult to find a joint design that satisfies the requirement in the whole range of deformation. For example, a ssDNA segment for an angle between 30° and 60° will be different from the spacer designed for the 60°~150° range. Thus, detailed calculations based on the finite model should be performed to reach a good balance between structural accuracy and flexibility. It is important to note that the effects of structural mechanics are not as critical in macroscopic metamaterials because the edges are typically made of stiff materials (~10^3 pN/nm^2) and the deformations are either often limited ($\leq 10\%$)[41] or accommodated using specially designed hinges for a wide range of reconfiguration.[42]

Biomolecular Auxetics. The sizes of auxetic unit cells made of various materials via different manufacturing methods are summarized in Figure S1. There is a wide gap between molecular auxetics and macroscopic metamaterials. Both DNA and proteins may serve as self-assembling building blocks to fill the gap. With the ability to form rigid components and flexible parts, they could be ideal candidates for periodic auxetic architectures with well-defined unit cells. Proteins,

when folded, can be rigid, while unfolded parts are more flexible. Tezcan and coworkers constructed micron-sized, isotropic 2D networks of protein assemblies based on disulfide bonds and metal-coordination.[43] They demonstrated stimuli-responsive, centrosymmetric transformation of the protein crystals, exhibiting $\nu = \sim$-1.

In comparison, DNA self-assembly uses base-pairing and strand displacement based on hydrogen bonding. With the chemical and structural simplicity, DNA origami may be more advantageous in achieving geometrical complexity and controllability. Complex architectured materials may be constructed through sequence design and arrangement. DNA structures are not limited to any specific shapes, and both isotropic and anisotropic geometries are possible as shown in this work. Auxetic 3D structures should be also achievable. The DNA origami in this work includes one or few unit cells, yet polymerization via sticky ends or increased ionic strength could lead to large-scale structures.[44,45] Further, other strategies such as DNA bricks[46] and 3D DNA crystals[47] may be employed to create macroscopic mechanical metamaterials.

In conclusion, auxetic 2D nanostructures are realized using DNA origami. Their elastic properties rely largely on the designed cellular structures and may be estimated quickly and roughly through the infinite model. However, the finite rigidity of edges and the flexibility of joints will affect the structural behaviors, for which DNA properties must be considered in the design. Mechanics-based guiding principles are developed to prevent curved edges and loose joints. As a bottom-up approach, DNA origami opens the opportunities for constructing well-defined auxetic unit cells and, with proper scale-up strategies, macroscopic metamaterials in 2D and 3D.

ACKNOWLEDGMENT
This work was financially supported by the U.S. Department of Energy. J.H.C. acknowledges partial support from the U.S. National Science Foundation.

REFERENCES

Chan, N. & Evans, K. E. Indentation Resilience of Conventional and Auxetic Foams. *Journal of Cellular Plastics* **34**, 231-260 (1998).

Scarpa, F. & Tomlin, P. J. On the Transverse Shear Modulus of Negative Poisson's Ratio Honeycomb Structures. *Fatigue & Fracture of Engineering Materials & Structures* **23**, 717-720 (2000).

Choi, J. B. & Lakes, R. S. Fracture Toughness of Re-Entrant Foam Materials with a Negative Poisson's Ratio: Experiment and Analysis. *International Journal of Fracture* **80**, 73-83 (1996).

Lee, J. H., Singer, J. P. & Thomas, E. L. Micro-/Nanostructured Mechanical Metamaterials. *Advanced Materials* **24**, 4782-4810 (2012).

Schwerdtfeger, J., Heinl, P., Singer, R. F. & Körner, C. Auxetic Cellular Structures Through Selective Electron-Beam Melting. *Physica Status Solidi (B)* **247**, 269-272 (2010).

Hengsbach, S. & Lantada, A. D. Direct Laser Writing of Auxetic Structures: Present Capabilities and Challenges. *Smart Materials and Structures* **23**, 085033 (2014).

Subramani, P., Rana, S., Oliveira, D. V., Fangueiro, R. & Xavier, J. Development of Novel Auxetic Structures Based on Braided Composites. *Materials & Design* **61**, 286-295 (2014).

Milstein, F. & Huang, K. Existence of a Negative Poisson Ratio in FCC Crystals. *Physical Review B* **19**, 2030-2033 (1979).

Baughman, R. H., Shacklette, J. M., Zakhidov, A. A. & Stafström, S. Negative Poisson's Ratios as a Common Feature of Cubic Metals. *Nature* **392**, 362-365 (1998).

Yeganeh-Haeri, A., Weidner, D. J. & Parise, J. B. Elasticity of α-Cristobalite: A Silicon Dioxide with a Negative Poisson's Ratio. *Science* **257**, 650-652 (1992).

Ortiz, A. U., Boutin, A. & Coudert, F.-X. Prediction of Flexibility of Metal–Organic Frameworks CAU-13 and NOTT-300 by First Principles Molecular Simulations. *Chemical Communications* **50**, 5867-5870 (2014).

Tan, J.-C., Civalleri, B., Erba, A. & Albanese, E. Quantum Mechanical Predictions to Elucidate the Anisotropic Elastic Properties of Zeolitic Imidazolate Frameworks: ZIF-4 vs. ZIF-zni. *CrystEngComm* **17**, 375-382 (2015).

Rothemund, P. W. K. Folding DNA to Create Nanoscale Shapes and Patterns. *Nature* **440**, 297-302 (2006).

Castro, C. E., Kilchherr, F., Kim, D.-N., Shiao, E. L., Wauer, T., Wortmann, P., Bathe, M. & Dietz, H. A Primer to Scaffolded DNA Origami. *Nature methods* **8**, 221-229 (2011).

Ke, Y., Meyer, T., Shih, W. M. & Bellot, G. Regulation at a Distance of Biomolecular Interactions Using a DNA Origami Nanoactuator. *Nature Communications* **7**, 1-8 (2016).

Kopperger, E., List, J., Madhira, S., Rothfischer, F., Lamb, D. C. & Simmel, F. C. A Self-Assembled Nanoscale Robotic Arm Controlled by Electric Fields. *Science* **359**, 296-301 (2018).

Masters, I. G. & Evans, K. E. Models for the Elastic Deformation of Honeycombs. *Composite Structures* **35**, 403-422 (1996).

Han, D., Pal, S., Yang, Y., Jiang, S., Nangreave, J., Liu, Y. & Yan, H. DNA Gridiron Nanostructures Based on Four-Arm Junctions. *Science* **339**, 1412-1415 (2013).

Körner, C. & Liebold-Ribeiro, Y. A Systematic Approach to Identify Cellular Auxetic Materials. *Smart Materials and Structures* **24**, 025013 (2014).

Simmel, S. S., Nickels, P. C. & Liedl, T. Wireframe and Tensegrity DNA Nanostructures. *Accounts of Chemical Research* **47**, 1691-1699 (2014).

Zhang, F., Jiang, S., Wu, S., Li, Y., Mao, C., Liu, Y. & Yan, H. Complex Wireframe DNA Origami Nanostructures with Multi-Arm Junction Vertices. *Nature Nanotechnology* **10**, 779-784 (2015).

Snodin, B. E. K., Randisi, F., Mosayebi, M., Šulc, P., Schreck, J. S., Romano, F., Ouldridge, T. E., Tsukanov, R., Nir, E., Louis, A. A. & Doye, J. P. K. Introducing Improved Structural Properties and Salt Dependence into a Coarse-Grained Model of DNA. *Journal of Chemical Physics* **142**, 234901 (2015).

Shi, Z., Castro, C. E. & Arya, G. Conformational Dynamics of Mechanically Compliant DNA Nanostructures from Coarse-Grained Molecular Dynamics Simulations. *ACS Nano* **11**, 4617-4630 (2017).

Douglas, S. M., Marblestone, A. H., Teerapittayanon, S., Vazquez, A., Church, G. M. & Shih, W. M. Rapid Prototyping of 3D DNA-Origami Shapes with CaDNAno. *Nucleic Acids Research* **37**, 5001-5006 (2009).

Goodman, R. P., Schaap, I. A., Tardin, C. F., Erben, C. M., Berry, R. M., Schmidt, C. F. & Turberfield, A. J. Rapid Chiral Assembly of Rigid DNA Building Blocks for Molecular Nanofabrication. *Science* **310**, 1661-1665 (2005).

Zhang, D. Y. & Winfree, E. Control of DNA Strand Displacement Kinetics Using Toehold Exchange. *Journal of the American Chemical Society* **131**, 17303-17314 (2009).

Chen, H., Weng, T.-W., Riccitelli, M. M., Cui, Y., Irudayaraj, J. & Choi, J. H. Understanding the Mechanical Properties of DNA Origami Tiles and Controlling the Kinetics of Their Folding and Unfolding Reconfiguration. *Journal of the American Chemical Society* **136**, 6995-7005 (2014).

Li, F., Chen, H., Pan, J., Cha, T.-G., Medintz, I. L. & Choi, J. H. A DNAzyme-Mediated Logic Gate for Programming Molecular Capture and Release on DNA Origami. *Chemical Communications* **52**, 8369-8372 (2016).

Hogan, M. & Austin, R. H. Importance of DNA Stiffness in Protein–DNA Binding Specificity. *Nature* **329**, 263-266 (1987).

Li, L., Liu, L., Tabata, O. & Li, W. J. in *9th IEEE International Conference on Nano/Micro Engineered and Molecular Systems (NEMS).* 684-687 (IEEE).

Kauert, D. J., Kurth, T., Liedl, T. & Seidel, R. Direct Mechanical Measurements Reveal the Material Properties of Three-Dimensional DNA Origami. *Nano letters* **11**, 5558-5563 (2011).

Kim, D.-N., Kilchherr, F., Dietz, H. & Bathe, M. Quantitative Prediction of 3D Solution Shape and Flexibility of Nucleic Acid Nanostructures. *Nucleic Acids Research* **40**, 2862-2868 (2012).

Gibson, L. J. & Ashby, M. F. *Cellular Solids: Structure and Properties*. (Cambridge University Press, 1999).

Grima, J. N., Alderson, A. & Evans, K. E. Auxetic Behaviour from Rotating Rigid Units. *Physica Status Solidi (B)* **242**, 561-575 (2005).

Zhang, W., Ma, Z. & Hu, P. Mechanical Properties of a Cellular Vehicle Body Structure with Negative Poisson's Ratio and Enhanced Strength. *Journal of Reinforced Plastics and Composites* **33**, 342-349 (2014).

Elipe, J. C. Á. & Lantada, A. D. Comparative Study of Auxetic Geometries by Means of Computer-Aided Design and Engineering. *Smart Materials and Structures* **21**, 105004 (2012).

Wang, T., Schiffels, D., Martinez Cuesta, S., Kuchnir Fygenson, D. & Seeman, N. C. Design and Characterization of 1D Nanotubes and 2D Periodic Arrays Self-Assembled from DNA Multi-Helix Bundles. *Journal of the American Chemical Society* **134**, 1606-1616 (2012).

McIntosh, D. B., Duggan, G., Gouil, Q. & Saleh, O. A. Sequence-Dependent Elasticity and Electrostatics of Single-Stranded DNA: Signatures of Base-Stacking. *Biophysical Journal* **106**, 659-666 (2014).

Jun, H., Zhang, F., Shepherd, T., Ratanalert, S., Qi, X., Yan, H. & Bathe, M. Autonomously Designed Free-Form 2D DNA Origami. *Science Advances* **5**, eaav0655 (2019).

Murphy, M., Rasnik, I., Cheng, W., Lohman, T. M. & Ha, T. Probing Single-Stranded DNA Conformational Flexibility Using Fluorescence Spectroscopy. *Biophysical Journal* **86**, 2530-2537 (2004).

Alderson, A., Rasburn, J., Ameer-Beg, S., Mullarkey, P. G., Perrie, W. & Evans, K. E. An Auxetic Filter: A Tuneable Filter Displaying Enhanced Size Selectivity or Defouling Properties. *Industrial & Engineering Chemistry Research* **39**, 654-665 (2000).

Wang, K., Chang, Y.-H., Chen, Y., Zhang, C. & Wang, B. Designable Dual-Material Auxetic Metamaterials Using Three-Dimensional Printing. *Materials & Design* **67**, 159-164 (2015).

Suzuki, Y., Cardone, G., Restrepo, D., Zavattieri, P. D., Baker, T. S. & Tezcan, F. A. Self-Assembly of Coherently Dynamic, Auxetic, Two-Dimensional Protein Crystals. *Nature* **533**, 369-373 (2016).

Tikhomirov, G., Petersen, P. & Qian, L. Fractal Assembly of Micrometre-Scale DNA Origami Arrays with Arbitrary Patterns. *Nature* **552**, 67-71 (2017).

Wagenbauer, K. F., Sigl, C. & Dietz, H. Gigadalton-Scale Shape-Programmable DNA Assemblies. *Nature* **552**, 78-83 (2017).

Ong, L. L., Hanikel, N., Yaghi, O. K., Grun, C., Strauss, M. T., Bron, P., Lai-Kee-Him, J., Schueder, F., Wang, B., Wang, P., Kishi, J. Y., Myhrvold, C., Zhu, A., Jungmann, R., Bellot, G., Ke, Y. & Yin, P. Programmable Self-Assembly of Three-Dimensional Nanostructures from 10,000 Unique Components. *Nature* **552**, 72-77 (2017).

Zheng, J., Birktoft, J. J., Chen, Y., Wang, T., Sha, R., Constantinou, P. E., Ginell, S. L., Mao, C. & Seeman, N. C. From Molecular to Macroscopic via the Rational Design of a Self-Assembled 3D DNA Crystal. *Nature* **461**, 74-77 (2009).

Figure 1. Re-entrant and regular honeycombs. (a) Schematics of the honeycombs in different conformations. The angle (γ), noted by red dots, are 30° (i), 60° (ii), 90° (iii), 120° (iv), and 145° (v). (b) Designs of honeycombs including four intact unit cells. The black lines represent the regular edges, while jack edges are shown in red. The coordinates, x and y, and the edges, l and m, are also noted. Subscript 1 indicates re-entrant structures ((i)–(iii)), whereas 2 represents regular honeycombs ((iv)–(vi)). Subscript 0 denotes the reference states ((iii) and (iv), $\gamma = 90°$). (c)–(d) Poisson's ratio (v), x/x_0, and y/y_0 as a function of γ. (e) x/x_0 versus y/y_0. Solid lines represent theoretical predictions of re-entrant honeycombs for $\gamma \leq 90°$ ($x/x_0 \leq 1.0$) and regular structures for $\gamma \geq 90°$ ($x/x_0 \geq 1.0$). The dashed curves represent theoretical predictions of the regular structures that would be imaginary conjugates of the re-entrant honeycombs, if elongated jack edges were used. (f) Equilibrium conformations of DNA origami honeycombs from coarse-grained MD simulations. (g) AFM images of DNA origami structures corresponding to the designs in (b) and the simulations in (f). Unused scaffold and jack segments slightly blur the images. Scale bar: 100 nm. The experimental data are also shown as filled circles with error bars in (c)–(e).

Figure 2. Structural transformation of the re-entrant triangle via chemical stimuli. (a)–(b) Schematics and designs in different conformations. The red dot indicates the angle γ. The black lines denote the regular edges, while jack edges are shown in red. (c) Equilibrium conformations of DNA origami from oxDNA simulations. (d) AFM images of DNA origami after reconfiguration. Unused scaffold and jack segments slightly blur the images. Scale bar: 100 nm. (e) Poisson's ratio versus angle. The line represents the theoretical prediction based on the finite model. Solid circles represent the experimental data with error bars, while the circles with a cross show the MD simulations of equilibrium structures. Solid triangles denote the simulation results of structural deformation by mechanical loading.

Figure 3. Mechanical deformation of the re-entrant triangle in MD simulations. (a) Schematics of the simulation domain with the jack edges removed. The applied compressive and tensile forces are shown in purple and green, respectively. (b) Simulation results of the re-entrant triangle under mechanical loads. (c) Young's modulus in the loading direction (E_1) versus angle γ. (d) Dimensionless internal horizontal force (F_i/F) and flexure of edge l per loads (δ_f/F) as a function of γ. The inset shows the edge l with the forces and flexure. (e)–(f) Dimensionless flexure (δ_f/l) and joint stretch (ξ). Curved lines show theoretical predictions based on the finite model. Solid triangles denote the simulation data. Blue shades indicated the design requirement.

Figure 4. Stiffness reinforced rotating square. (a)–(b) Schematics and designs of the rotating square under different deformations. The angle $\gamma = 35°$ (i), $90°$ (ii), and $140°$ (iii). Regular and jack edges are shown in black and red. The inset shows the edge cross-section, where four double helices (black) are used in a hexagonal arrangement. (c) MD simulations and (d) AFM images of the rotating square DNA origami. There are unused scaffold segments around the origami and not fully extended jacks, which blur the image. Scale bar: 100 nm. (e) Poisson's ratio versus angle plot, where solid circles show the experimental data with error bars, while the dashed line represents theoretical values. (f) Dimensionless flexure of edge l and (g) joint stretch as a function of γ. Black circles indicate the MD simulation data that meet the design requirements denoted by blue shades.