Single particle-resolution fluorescence microscopy of nanoplastics

Content Type: Letter

Authors

Brian Nguyen†, Nathalie Tufenkji†

Affiliations

†Department of Chemical Engineering, McGill University, 3610 University street,
Montreal, Quebec H3A 0C5, Canada

Abstract

Understanding of nanoplastic prevalence and toxicology is limited by imaging challenges
resulting from their small size. Fluorescence microscopy is widely applied to track and identify
microplastics in laboratory studies and environmental samples. However, conventional
fluorescence microscopy, due to diffraction, lacks the resolution to precisely localize nanoplastics
in tissues, distinguish them from free dye, or quantify them in environmental samples. To address
these limitations, we developed techniques to label nanoplastics for imaging with Stimulated
Emission Depletion (STED) microscopy to achieve resolution at an order of magnitude superior
to conventional fluorescence microscopy. These techniques include (1) passive sorption; (2) swell
incorporation; and (3) covalent coupling of STED-compatible fluorescence dyes to nanoplastics.
We demonstrate that our labeling techniques, combined with STED microscopy, can be used to
resolve nanoplastics of different shapes and compositions as small as 50 nm. The longevity of the
dye labeling is demonstrated in different media and conditions of biological and environmental
relevance. We also test STED imaging of nanoplastics in exposure experiments with the model
worm *C. elegans*. These techniques will allow more precise localization and quantification of
nanoplastics in complex matrices.

Main

The visibility of plastic pollution and the potential effects on biota have garnered considerable
attention. The vast majority of plastics produced ends up in landfills or the environment[1]. Once in
the environment, plastic can fragment into smaller pieces known as secondary plastics, via
mechanical, thermal, or other mechanisms of degradation [2–7]. As a result, the smallest size
fractions of plastic pollution often dominate particle counts in the environment [8,9]. Despite their
potential prevalence, little is known about the toxicological effects and mechanisms of the
smallest particles (i.e., nanoplastics) in part due to the difficulty of visualizing them in wet
matrices including biological tissues.

Fluorescence microscopy allows sensitive and quantitative imaging with specific labeling of
particles and biological structures. Consequently, fluorescence imaging has been widely applied
to localize labeled microplastic particles used in exposure studies to track uptake and potential
translocalization in live organisms [11–13]. Typically, microplastics are large enough to be
individually resolved with light microscopy [11–13], allowing localization of fluorescently-labeled
microplastics even if there is significant background signal from autofluorescence or dye
leaching[14,15]. However, because of the optical ~200 nm diffraction limit on resolution,
nanoplastics are typically too small to be individually resolved with fluorescence microscopy
techniques currently applied in plastics research, including Laser-Scanning Confocal

Microscopy[14,16] and widefield epifluorescence microscopy [17,18]. Consequently, with conventional light microscopy, nanoplastics are typically only visualized as diffraction limited spots and cannot be precisely localized in tissues nor distinguished from free dye or autofluorescence[14]. While electron microscopy resolution is well beyond the diffraction limit for light microscopy, electron microscopy lacks the labelling flexibility, matrix flexibility, and the ease of sample preparation of fluorescence microscopy.

Nanoplastic exposure experiments disproportionately employ spherical polystyrene nanoparticles, in part due to the limited commercial availability of other types of labeled nanoplastics [19,20]. These polystyrene spheres are not representative of the diversity of environmentally relevant plastic contamination [19,20]. Techniques have been developed to label microplastics of arbitrary shapes and compositions [11] and Stimulated Emission Depletion (STED) microscopy has been used to image nano-sized polystyrene latex with pre-loaded proprietary fluorophores [21]. However, methods to fluorescently label nanoplastics of different shapes and polymer types are limited. Consequently, a method to label nanoplastic particles of various shapes and composition would allow more environmentally relevant study of nanoplastics transport, uptake and translocation.

In this work, we developed techniques to label nanoplastics of various shapes, sizes, and polymer types with STED-compatible dyes to image at diffraction-unlimited resolution. We show that nanoplastics can be labeled either by (1) passive sorption; (2) swell incorporation; or (3) covalent coupling of STED-compatible fluorescence dyes. We display STED-compatible labeling and fluorescent imaging of multiple types of nanoplastics, including secondary nanoplastics, of different shapes and polymer types as well as nano-scale resolution imaging of nanoplastics in *Caenorhabditis elegans,* a model nematode worm. We expect that these techniques will enable localization and identification of nanoplastic translocation at the nano-scale in cells, tissues, and smaller organisms in exposure experiments.

Nanoplastic labeling and imaging at nanoscale resolution

Fig. 1: STED-compatible dye labeling techniques. In this work, all labeled plastics are dialyzed prior to imaging to remove free dye. (a) Passively-labeling with Atto 647N where the dye solution and the plastic are simply mixed together; (b) Swell-labeling with Atto 647N/iDye Poly Blue where the plastic is heated in the dye solution to swell the polymer matrix and allow the dye to enter the polymer matrix (with Atto 647N, THF, a solvent, is added to aid in swelling), after swelling the plastic is cooled and resuspended in DI water to deswell and remove excess dye; (c) Covalent labeling by coupling NHS-functionalized Atto 647N to amine groups on functionalized plastic; (d) STED image of passively-labeled 100 nm PS beads with Atto 647N; (e) STED image of swell-labeled 100 nm PS beads

with Atto 647N; (f) STED image of swell-labeled 100 nm PS beads with iDye Blue; (g) STED image of covalently-
labeled 100 nm PS beads with Atto 647N.

Labeling and Resolution

STED microscopy achieves sub-diffraction resolution by scanning a sample with two lasers
simultaneously: an excitation laser with a circular spot and an overlapping depletion laser with a
donut-shaped spot[17]. The depletion laser suppresses fluorescence emission from the periphery of
the excitation laser spot, effectively decreasing the size of the emission spot which improves
resolution beyond the diffraction limit. This results in an order of magnitude improvement in
resolution. However, the dye compatibility of STED microscopy is limited due to the need for the
dye to efficiently undergo stimulated emission and to have high photostability to limit excessive
photobleaching[22,23]. Nevertheless, multiple colours of fluorescent dyes compatible with STED
microscopy are available [24]. Still, the suitability of these dyes to labeling nanoplastics of different
shapes and polymer types has not yet been established.
102
We tested labeling with Atto 647N either via passive sorption, heat/solvent swelling[11] or covalent
coupling (**Fig. 1a-c**). We also tested swell labeling with iDye Poly Blue ("iDye"). The methods to
label nanoplastic that we describe here all successfully labeled nanoplastic for STED imaging
(**Fig. 1d-g**). **Fig. 2** compares identical fields of view imaged with standard laser-scanning
confocal imaging with those obtained using STED imaging. As expected, the resolution of the
laser-scanning confocal images was diffraction-limited. Individual particles appear as a
diffraction-limited spot significantly larger than their actual size. When particles are close to each
other, multiple particles appear as a single body rather than distinct particles. In contrast, with
STED imaging using Atto 647N, the size and shape of individual nanoplastic particles as small as
50 nm can be resolved as shown by the images (**Fig. 2**) and corresponding point-spread functions
(**Supplementary Fig. 1**). Consequently, STED imaging can detect single nanoplastic particles
provided that they are in the field of view of the microscope.
115

Fig. 2: Comparison of Laser-Scanning Confocal images and STED images of identical fields of view where the nanoplastics are passively labeled with Atto 647N. (a) Confocal image of 50 nm polystyrene beads; (b) STED image of 50 nm polystyrene beads; (c) Confocal image of 100 nm polystyrene beads; (d) STED image of 100 nm polystyrene beads; (e) Close up confocal image of 100 nm polystyrene beads; (f) Point spread function and Gaussian fit of 100 nm polystyrene bead with confocal imaging; (h) Close up STED image of 100 nm polystyrene beads; (i) Point spread function and Gaussian fit of 100 nm polystyrene bead with STED imaging.

STED imaging with iDye also showed a resolution improvement over conventional laser-scanning confocal microscopy. The point spread functions of STED images are shown in **Supplementary Fig. 1-4**. However, the resolution with iDye labeling (**Supplementary Fig. 3**) was lower compared to Atto 647N. This result is unsurprising since Atto 647N is well known to perform well with STED microscopy[23] whereas iDye is a repurposed fabric dye, not a purpose-designed fluorophore. Particles dyed with iDye were also not as bright as those dyed with Atto

647N and thus required 5 times more intense excitation light and twice the pixel dwell time to
achieve comparable signal strengths (**Supplementary Table 1**).

Longevity

We tested the longevity of the labeled nanoplastic particles in both water and oil to simulate the
polar and non-polar environments that the particles might experience pre- and post-
internalization by organisms. The ability to visualize particles at diffraction-unlimited resolution
was maintained in the particles labeled using the techniques we present here for typical exposure
timescales. Particularly, all the methods that employ Atto 647N remain visible for at least 49 days
(**Fig. 3a-f**). While there was variability day to day in the precise average signal intensity, at all
points during this test, the nanoplastic particles were clearly visible with STED imaging
throughout the duration of the test. Surprisingly, even plastics labeled passively with Atto 647N
were stable in oil (**Fig. 3b**), a non-polar environment. Suspending the plastics in mineral oil did
not significantly diminish the fluorescent signal localized to the plastic particle. Moreover, we did
not detect a fluorescent signal in the oil phase surrounding plastic particles (directly measured
with fluorescence microscopy), indicating that dye transfer to the oil phase is limited.

150
151
Fig. 3: Longevity of different STED-compatible labeling techniques using 100 nm beads. Passive labeling with Atto
647N in (a) DI water and (b) mineral oil; Swell labeling with Atto 647N in (c) DI water and (d) mineral oil; Covalent
labeling with NHS-functionalized Atto 647N to amine groups on the particle surface in (e) DI water and (f) mineral
oil; Swell labeling with iDye Poly Blue in (g) DI water and (h) mineral oil. Each point represents the average single
particle grey value for STED images of triplicate samples acquired with identical settings within treatments. Error
bars represent standard error.

158
159
The longevity of passively labeled nanoplastics with Atto 647N contrasts with that of Nile Red, a
dye more commonly used to stain plastics[12,25]. Previous work[11] shows that plastics passively
stained with Nile Red, do not retain the dye when exposed to mineral oil. This suggests that Atto
647N has a higher affinity to plastic surfaces compared to Nile Red and that the mechanism by
which Atto 647N sorbs to plastics is not solely via hydrophobic interaction. Other potential
mechanisms of sorption could include interaction between the plastic surface and the charged
regions of Atto 647N and/or passive diffusion and subsequent intercalation into the polymer
matrix.

To further test the longevity of the labeling in different biologically and environmentally-relevant
media and conditions, we also tested the longevity of the different Atto 647N labeling methods on
50 nm polystyrene beads in pitcher plant digestive fluid, soil water, 2.5 pH hydrochloric acid, and
at elevated temperature (40 °C) over 21 days (**Fig. 4).** Similar to the tests in water and oil, we
found that we were able to visualize the labeled plastics over the period of exposure.
174

175
176
Fig. 4: Longevity of different STED-compatible labeling techniques using 50 nm beads. Passive labeling with Atto
647N in (a) pitcher plant fluid; (b) soil water; (c) elevated temperature (40 °C); and (d) hydrochloric acid (pH 2.5).
Swell labeling with Atto 647N in (e) pitcher plant fluid; (f) soil water; (g) elevated temperature (40 °C); and (h)

hydrochloric acid (pH 2.5). Covalent labeling with Atto 647N in (i) pitcher plant fluid; (j) soil water; (k) elevated
temperature (40 °C); and (l) hydrochloric acid (pH 2.5). Each point represents the average single particle grey value
for STED images of triplicate samples acquired with identical settings within treatments. Error bars represent
standard error.

Theoretically, swell and covalent labeling potentially provide greater labeling longevity compared
to passive labeling alone. However, these techniques are comparatively more complicated to carry
out. Particularly, with covalent labeling, specific functional groups on the surface of the plastic
are required for labeling. Nevertheless, depending on the target application, swell or covalent
labeling may be useful when greater resistance to external solvents is desirable.

As with any fluorescent labeling method, the fluorescent signal will be susceptible to
photobleaching[11]. Consequently, if experimental exposures require intense light, duration of the
exposure while maintaining a fluorescent signal may be more limited. Nevertheless, Atto 647N is
generally a photostable dye[26]. Furthermore, despite the resolution advantages that we show,
STED microscopy results in a greater degree of photobleaching compared to conventional
widefield or confocal fluorescence microscopy since bleaching can also occur via stimulated
emission in addition to fluorescence[23]. Consequently, the ability to observe dynamics and image
multiple z-slices is limited, in a sample dependent manner, compared to conventional laser-
scanning confocal or widefield microscopy. Moreover, to achieve nanoscale resolution, high
numerical aperture objectives must be used. Typically, these objectives have limited working
distances. Consequently, the maximum imaging depth with STED microscopy while maintaining
high resolution is limited and is most suited for imaging cells, tissue sections, small anatomy, or
micro-scale organisms.

In terms of performance with STED microscopy, Atto 647N was superior to iDye in brightness,
longevity and resolution. Nevertheless, dyeing with iDye may be more practical when cost is a
concern. In contrast to Atto 647N, which currently costs $288 CAD per mg, iDye Poly Blue can
be purchased for less than $0.50 CAD per g. Nonetheless, typically, a much lower amount of Atto
647N would be required to effectively label nanoplastics compared to iDye Poly Blue.

Labeling and imaging various types of nanoplastic

While techniques have been developed to label microplastics of arbitrary shapes and
compositions[11], methods to fluorescently label nanoplastics of different shapes and polymer types
are limited. Addressing this limitation, our methods are compatible with different shapes and
compositions of nanoplastic, beyond commercially available spherical nanoplastics (**Fig. 5**). With
STED microscopy, we were able to resolve the shapes of secondary nanoplastics produced by
heating expanded polystyrene to 90 °C for 7 days (**Fig. 5b**) as well as polystyrene sanding debris
(**Fig. 5d**). As confirmed by SEM (**Supplementary Fig. 9**), the secondary nanoplastics produced
by heating are roughly spherical while those produced by sanding are irregular in shape. The
images in **Fig. 5a,c** show that such particle visualization was not possible with conventional
confocal fluorescence microscopy. We also tested imaging with commercially-available PTFE
nanoparticles (**Fig. 5e,f**) as a low surface energy plastic and PMMA nanoparticles (**Fig. 5g,h**) as a
relatively high surface energy plastic[27]. The PTFE particles are representative of engineered PTFE
nanoparticles used for lubrication and hydrophobic coatings. PMMA (also known as "Plexiglas")
is widely used as a glass substitute for transparent windows.

228
229 **Fig. 5:** Passive labeling and fluorescent imaging of various nanoplastic types with Atto 647N. Confocal (a) and
230 STED (b) image of debris released from an expanded polystyrene plate exposed to 90 °C in DI water; (c) Confocal
231 and (d) STED image of sanding debris from a polystyrene Petri dish; (e) Confocal and (f) STED image of PTFE
232 particles; (g) Confocal and (h) STED image of PMMA particles. Confocal and STED images are of the same fields of
233 view.

234
235

Application to C. elegans exposure

To test the ability of this technique to image nanoplastics in a model organism, as a proof of
concept, we exposed *C. elegans* KWN117[28] to 100 ppm of 50 nm polystyrene beads passively
labeled with Atto 647N (**Fig. 6**). We used the 50 nm polystyrene beads due to their availability in
sufficient quantities to conduct the exposures as well as a more challenging size to detect.
KWN117 is a transgenic strain that expresses Green Fluorescent Protein (GFP) in the body wall
and mCherry in apical intestinal membrane cells[28]. As when imaging the nanoplastics alone,

STED imaging allows visualization of nanoplastic along sections of the digestive tract including
the mouth (**Fig. 6a,b,c**), pharynx (**Fig. 6d,e,f**), and intestine (**Fig. 6g,h,i**). While 100 ppm is
higher than typical plastic concentrations for aquatic environments it is in line with concentrations
in some soil environments [29,30].
248
249 Notably, fluorescent signal in the confocal images, which may initially be interpreted as
250 nanoplastic, is revealed to be background signal from free dye and/or autofluorescence with
251 STED imaging. In control worms (**Supplementary Fig. 8**), no nanoplastic particles were visible
252 with STED imaging, however spots of background and autofluorescence signal were visible that
253 could have been misidentified as nanoplastic with lower-resolution imaging.
254

255
Fig. 6: Imaging 50 nm polystyrene nanoplastics passively labeled with Atto 647N (red) in *C. elegans* KWN117 adult
expressing GFP (green) in the body wall and mCherry (yellow) in the apical intestinal membrane. Confocal
overview, and high resolution of confocal and STED images of scanned area indicated by white boxes for parts of the
digestive track in the mouth (a,b,c), pharynx (d,e,f), and intestine (g,h,i). Insets in STED images correspond to the
areas indicated by white boxes. Arrows indicate potential false positive signal from confocal imaging where STED
imaging reveals that the signal is inconsistent with 50 nm particles.

We expect that for typical organism exposure experiments, including the imaging in *C. elegans* we show here, STED microscopy combined with passive staining with Atto 647N would generally be a convenient method of observing nanoplastics fluorescently without significantly compromising labeling longevity. Overall, the ability to precisely localize the distribution of nanomaterials, including nanoplastics, in organisms may help facilitate study into the lethal and sub-lethal effects observed in exposure experiments. Localization can also provide insight into longer term effects of exposure that may not be detected over relatively short experimental timescales. Specifically, translocation of materials to certain parts of organisms can be indicative of long-term effects. Since our methods are compatible with different shapes and compositions of nanoplastic, these techniques will allow researchers to more thoroughly explore the impact of shape, size, and composition of nanoplastics on toxicity and translocation in live organisms. This broad compatibility of STED microscopy to localize fluorescently-labeled nanomaterials at nanoscale resolution can be further extended to better understand the environmental toxicology of nanomaterials beyond nanoplastics. While STED microscopy has been applied to understand the interaction of engineered nanomaterials with cells *in vitro* in the biomedical context[31–33], our work demonstrates the utility of STED microscopy to study nanomaterial interactions with organisms in environmentally-relevant exposure scenarios and with environmentally-relevant contaminants.

Methods

Nanoplastic sources

Plain polystyrene spheres with a nominal diameter of 100 nm (actual diameter averaged 88 nm according to manufacturer specifications) and 50 nm (actual diameter averaged 50 nm according to manufacturer Dynamic Light Scattering specifications) were purchased from Polysciences Inc. Amine-functionalized 100 nm (actual diameter averaged 113 nm according to manufacturer Dynamic Light Scattering specifications) polystyrene spheres was purchased from Polysciences Inc. Plain 50 nm (actual diameter averaged 50 nm according to manufacturer specifications) Poly(methyl methacrylate) spheres were purchased from Phosphorex Inc. These commercially available spherical particles are typical of those used in most current nanoplastic studies[14,16]. A dispersion of polytetrafluoroethylene (PTFE) nanoparticles (Teflon™ 30B) was purchased from Polysciences Inc. This dispersion has typical average particle diameters around 200 nm but are not monodisperse and contain a variety of particle sizes including much smaller particles.

We also obtained nano-sized debris from plastic labware and consumer items using a variety of weathering methods. Debris was obtained from a polystyrene Petri dish by mechanical abrasion with a 100 nm diamond lapping film (3M) and from an expanded polystyrene plate by submerging it in approximately 1 L of DI water at approximately 90 °C for 7 days and sampling the water by pipetting into a glass vial. These secondary nanoplastic particles represent nanoplastics that can be released from common single-use plastic consumer goods[7,34,35].

Labeling nanoplastics

Passive Staining of Nanoplastics. We labeled nanoplastic via passive sorption with Atto 647N (Sigma 04507) (ex. 646 nm / em. 664 nm). We chose to use Atto 647N because of its good STED performance with a 775 nm depletion laser. To passively label nanoplastic, we suspended 0.125% w/v nanoplastic in a solution of 2 mg/L Atto 647N in DI water for 2 h at room temperature (~ 25 °C). The excess dye was removed from the suspension via dialysis using 12-14 kDa molecular weight cutoff (MWCO) dialysis membranes (Frey Scientific) for 7 days with daily water changes in stirred 2 L glass beakers.

Swell Incorporation of Dye to Nanoplastics. We also adapted the microplastic dyeing methods developed previously by Karakolis et al.[11] to label nanoplastics with iDye (Jacquard Products), an inexpensive commercially available fabric dye. While we expected that iDye would be inferior to Atto 647N in terms of fluorescence imaging, we tested it due to the convenience and low cost of labeling with the iDye Poly Blue[11]. Briefly, nanoplastics were incubated in a 0.1 mg/mL solution of iDye Poly Blue in DI water heated to 70 °C for 2 h followed by cooling to room temperature. During the heating, the dye is able to diffuse into the polymer matrix due to thermal swelling. Since iDye Poly is only sparingly soluble, the excess dye was removed via centrifugation (12,000g for 45 min), washing the dyed particles twice with 25% isopropanol and three times with DI water. We also tested a similar method using Atto 647N in place of iDye Poly Blue. However, for swell incorporation of Atto 647N, we added 10% tetrahydrofuran to the dye solution to aid in the swelling in addition to heating to 70 °C. We added the tetrahydrofuran since Atto 647N is not packaged with dispersants or other agents which are typically included in commercial fabric dye formulations. We were also able to remove excess dye using dialysis since Atto 647N is more water soluble[36].

Covalent Coupling of Dye to Nanoplastics. We coupled N-hydroxysuccinimide (NHS)-terminated Atto 647N (Sigma 18373) to amine-functionalized plastic by incubating 0.125% w/v nanoplastic in a solution of 2 mg/L Atto 647N in phosphate buffered saline at pH 7.4. At this pH, the NHS group reacts with the amine groups on the surface of the plastic, covalently binding the dye to the plastic[37]. The excess dye was removed from the suspension via dialysis using a 12-14 kDa MWCO dialysis membranes (Frey Scientific) for 7 days with daily water changes in stirred 2 L glass beakers[13].

Fluorescence Imaging

We completed all imaging using an Abberior Expert Line STED microscope using an Olympus Plan-Apo 100x/1.40NA Oil immersion objective. We used a 640 nm laser for excitation and a 775 nm laser for depletion. The microscope was equipped with avalanche photodetectors. We performed both standard laser-scanning confocal and STED imaging on the same microscope. All image analysis was done in ImageJ.

Oil Longevity Testing

To test the longevity of the dye-labeled nanoplastic in a non-polar solvent, we mounted labeled 100 nm (nominal) polystyrene beads in mineral oil (Sigma M5904) on sealed glass microscope slides stored at room temperature (25 °C) in the dark. Specifically, we spread a 5 µL drop of the nanoplastic suspension on glass slides with a pipette tip, allowed the water to dry and then applied a 20 µL drop of mineral oil onto the slide. We then covered the oil with a #1.5 coverslip and sealed the edges with CoverGrip Coverslip Sealant (Biotium, Inc.). Samples were imaged at each time point using identical imaging settings (10% excitation laser power, 50% depletion laser power, 10 nm pixel size, 10 µs dwell time and 1.0 AU pinhole-See **Supplementary Table 1** for imaging settings).

Aqueous Media Longevity Testing

As water is more volatile than the mineral oil we used, we tested longevity in aqueous solutions, including simulated environmental media, in 1 mL suspensions of labeled nanoplastic in glass vials at room temperature (~ 25 °C) or at elevated temperature (40 °C). Pitcher plant fluid was a

gift from Brad's Greenhouse (Vancouver Island, British Columbia, Canada). Soil water was obtained by mixing 200 mL of DI water with 100 g of dry agricultural soil from McGill University's MacDonald Campus (Sainte-Anne-de-Bellevue, Quebec, Canada) for 48 h and taking the supernatant after the soil was allowed to settle.

At each time point, we mounted a sample from each suspension onto microscope slides for imaging. Specifically, we spread a 5 µL drop of the nanoplastic suspension on glass slides with a pipette tip, allowed the water to dry and then applied a 20 µL drop of water onto the slide. Samples were imaged at each time point using identical imaging settings (10% excitation laser power, 50% depletion laser power, 10 nm pixel size, 10 µs dwell time and 1.0 AU pinhole for 100 nm particles and 20% excitation laser power, 50% depletion laser power, 5 nm pixel size, 10 µs dwell time and 1.0 AU pinhole for 50 nm particles and -See **Supplementary Table 1** for imaging settings).

C. elegans culture and exposure

C. elegans strain KWN117 worms were obtained from the Caenorhabditis Genetics Center at the University of Minnesota and maintained at 23 °C on Nematode Growth Medium (NGM) plates seeded with *E. coli* OP50 as a food source. KWN117 expresses GFP (488 nm excitation/507 nm emission) in the body wall as well as mCherry (587 nm excitation/610 nm emission) in the apical intestinal membrane[28].

Prior to exposing the worms to nanoplastic, worms were washed from NGM agar plates with 5 mL of M9 buffer and washed with M9 buffer three times by allowing the worms to settle in 15 mL centrifuge tubes for ~ 10 min and replacing the supernatant with fresh M9 buffer. To expose the worms to nanoplastic, the worms were resuspended in 100 µL of M9 buffer containing nanoplastics and then pipetted onto NGM agar plates. Control worms were prepared similarly but were resuspended in M9 buffer with dialyzed dye solution before pipetting on NGM agar plates. We expect that the dye would be largely removed from the solution with this process. For imaging, the worms were washed off the NGM with M9 buffer and immobilized in low-melting point agarose on microscope slides covered with #1.5 coverslips.

References
1.   Geyer, R., Jambeck, J. R. & Law, K. L. Production , use , and fate of all plastics ever made. 25–29 (2017).
2.   Moore, C. J. Synthetic polymers in the marine environment: A rapidly increasing, long-term threat. *Environ. Res.* **108**, 131–139 (2008).
3.   Thompson, R. C., Moore, C. J., Saal, F. S. V. & Swan, S. H. Plastics, the environment and human health: Current consensus and future trends. *Philos. Trans. R. Soc. B Biol. Sci.* **364**, 2153–2166 (2009).
4.   Thompson, R. C., Swan, S. H., Moore, C. J. & Vom Saal, F. S. Our plastic age. *Philos. Trans. R. Soc. B Biol. Sci.* **364**, 1973–1976 (2009).
5.   Magrì, D. *et al.* Laser ablation as a versatile tool to mimic polyethylene terephthalate nanoplastic pollutants: Characterization and toxicology assessment. *ACS Nano* **12**, 7690–7700 (2018).
6.   Dawson, A. L. *et al.* Turning microplastics into nanoplastics through digestive fragmentation by Antarctic krill. *Nat. Commun.* **9**, 1001 (2018).
7.   Hernandez, L. M. *et al.* Plastic Teabags Release Billions of Microparticles and Nanoparticles into Tea. *Environ. Sci. Technol.* **53**, 12300–12310 (2019).

8. Mintenig, S. M., Bäuerlein, P. S., Koelmans, A. A., Dekker, S. C. & van Wezel, A. P. Closing the gap between small and smaller: towards a framework to analyse nano- and microplastics in aqueous environmental samples. *Environ. Sci. Nano* (2018). doi:10.1039/C8EN00186C

9. Silva, A. B. *et al.* Microplastics in the environment: Challenges in analytical chemistry - A review. *Anal. Chim. Acta* **1017**, (2018).

10. Nguyen, B. *et al.* Separation and Analysis of Microplastics and Nanoplastics in Complex Environmental Samples. *Acc. Chem. Res.* **52**, 858–866 (2019).

11. Karakolis, E. G., Nguyen, B., You, J. B., Rochman, C. M. & Sinton, D. Fluorescent Dyes for Visualizing Microplastic Particles and Fibers in Laboratory-Based Studies. *Environ. Sci. Technol. Lett.* **6**, 334–340 (2019).

12. Cole, M. A novel method for preparing microplastic fibers. *Sci. Rep.* **6**, 34519 (2016).

13. Pikuda, O., Xu, E. G., Berk, D. & Tufenkji, N. Toxicity Assessments of Micro- and Nanoplastics Can Be Confounded by Preservatives in Commercial Formulations. *Environ. Sci. Technol. Lett.* **6**, 21–25 (2019).

14. Schür, C. *et al.* When Fluorescence Is not a Particle: The Tissue Translocation of Microplastics in Daphnia magna Seems an Artifact. *Environ. Toxicol. Chem.* **38**, 1495–1503 (2019).

15. Catarino, A. I., Frutos, A. & Henry, T. B. Use of fluorescent-labelled nanoplastics (NPs) to demonstrate NP absorption is inconclusive without adequate controls. *Sci. Total Environ.* **670**, 915–920 (2019).

16. Sun, X. D. *et al.* Differentially charged nanoplastics demonstrate distinct accumulation in Arabidopsis thaliana. *Nat. Nanotechnol.* (2020). doi:10.1038/s41565-020-0707-4

17. Hell, S. W. & Wichmann, J. Breaking the diffraction resolution limit by stimulated emission: stimulated-emission-depletion fluorescence microscopy. *Opt. Lett.* **19**, 780 (1994).

18. Betzig, E. *et al.* Imaging Intracellular Fluorescent Proteins at Nanometer Resolution. **x**, 1642–1646 (2006).

19. Rochman, C. M. *et al.* Rethinking microplastics as a diverse contaminant suite. *Environ. Toxicol. Chem.* **38**, 703–711 (2019).

20. Wagner, S. & Reemtsma, T. Things we know and don't know about nanoplastic in the environment. *Nat. Nanotechnol.* **14**, 300–301 (2019).

21. Harke, B. *et al.* Resolution scaling in STED microscopy. *Opt. Express* **16**, 4154 (2008).

22. Wurm, C. A. *et al.* Novel red fluorophores with superior performance in STED microscopy. *Opt. Nanoscopy* **1**, 1–7 (2012).

23. Oracz, J., Westphal, V., Radzewicz, C., Sahl, S. J. & Hell, S. W. Photobleaching in STED nanoscopy and its dependence on the photon flux applied for reversible silencing of the fluorophore. *Sci. Rep.* **7**, 1–14 (2017).

24. Sednev, M. V., Belov, V. N. & Hell, S. W. Fluorescent dyes with large Stokes shifts for super-resolution optical microscopy of biological objects: A review. *Methods Appl. Fluoresc.* **3**, (2015).

25. Maes, T., Jessop, R., Wellner, N., Haupt, K. & Mayes, A. G. A rapid-screening approach to detect and quantify microplastics based on fluorescent tagging with Nile Red. *Nat. Publ. Gr.* 1–10 (2017). doi:10.1038/srep44501

26. Zheng, Q., Jockusch, S., Zhou, Z. & Blanchard, S. C. The contribution of reactive oxygen species to the photobleaching of organic fluorophores. *Photochem. Photobiol.* **90**, 448–454 (2014).

27. Park, J. S., Lee, S. M., Joo, B. S. & Jang, H. The effect of material properties on the stick–slip behavior of polymers: A case study with PMMA, PC, PTFE, and PVC. *Wear* **378**–**379**, 11–16 (2017).

28. Allman, E., Johnson, D. & Nehrke, K. Loss of the apical V-ATPase a-subunit VHA-6 prevents acidification of the intestinal lumen during a rhythmic behavior in C. elegans. *Am. J. Physiol. - Cell Physiol.* **297**, 1071–1081 (2009).

29. Scheurer, M. & Bigalke, M. Microplastics in Swiss Floodplain Soils. *Environ. Sci. Technol.* **52**, 3591–3598 (2018).

30. Fuller, S. & Gautam, A. A Procedure for Measuring Microplastics using Pressurized Fluid Extraction. *Environ. Sci. Technol.* **50**, 5774–5780 (2016).

31. Schübbe, S. *et al.* Size-dependent localization and quantitative evaluation of the intracellular migration of silica nanoparticles in Caco-2 cells. *Chem. Mater.* **24**, 914–923 (2012).

32. Tzeng, Y. K. *et al.* Superresolution imaging of albumin-conjugated fluorescent nanodiamonds in cells by stimulated emission depletion. *Angew. Chemie - Int. Ed.* **50**, 2262–2265 (2011).

33. Pujals, S. & Albertazzi, L. Super-resolution Microscopy for Nanomedicine Research. *ACS Nano* **13**, 9707–9712 (2019).

34. Lambert, S. & Wagner, M. Characterisation of nanoplastics during the degradation of polystyrene. *Chemosphere* **145**, 265–268 (2016).

35. Ekvall, M. T. *et al.* Nanoplastics formed during the mechanical breakdown of daily-use polystyrene products. *Nanoscale Adv.* **1**, 1055–1061 (2019).

36. Hughes, L. D., Rawle, R. J. & Boxer, S. G. Choose your label wisely: Water-soluble fluorophores often interact with lipid bilayers. *PLoS One* **9**, (2014).

37. Karakolis, E. G. *et al.* Digestible Fluorescent Coatings for Cumulative Quantification of Microplastic Ingestion. *Environ. Sci. Technol. Lett.* **5**, 62–67 (2018).

Acknowledgments

General: The authors acknowledge Dr. Rachel Genthial, Kamila Mustafina, Dr. Thomas Stroh, the Integrated Quantitative Biology Initiative, and the Montreal Neurological Institute Microscopy Unit for assistance with STED microscopy. The authors also acknowledge Amin Valiei for assistance with SEM. *C. elegans* were provided by the CGC, which is funded by NIH Office of Research Infrastructure Programs (P40 OD010440).

Funding: B.N. gratefully acknowledges funding from the Natural Sciences and Engineering Research Council Postdoctoral Fellowships program and the Eugenie Ulmer Lamothe fund in the Department of Chemical Engineering at McGill University. N.T. acknowledges funding from the Canada Research Chairs program, the Natural Sciences and Engineering Research Council of Canada, and the Canada Foundation for Innovation. This Project was supported partially by a financial contribution from Fisheries and Oceans Canada.

Author contributions: B.N. developed the methodology and performed the experiments. B.N. and N.T conceived the concepts and contributed to manuscript drafting and editing.

Competing interests: The authors do not have any competing interests to declare.

510　　　　**Data Availability:** The data that support the findings of this study are available from the
511　　　　corresponding author upon reasonable request. Figure 3 and Supplementary Figures 1-4
512　　　　have associated raw data.
513

 Supplementary Information

 Supplementary Table 1: STED imaging settings

Sample	640 nm excitation laser power	775 nm depletion laser power	Pixel Size	Dwell Time	Pinhole
50 nm polystyrene for testing resolution	20%	100%	10 nm	10 μs	1.0 AU
100 nm polystyrene for testing resolution	10%	50%	10 nm	10 μs	1.0 AU
Atto 647N-labeled longevity testing for 100 nm beads (oil and water)	10%	50%	10 nm	10 μs	1.0 AU
Atto 647N-labeled longevity testing for 50 nm beads (elevated temperature, pitcher plant fluid, acid, and soil water)	20%	50%	5 nm	10 μs	1.0 AU
iDye-labeled plastic longevity testing (oil and water)	50%	100%	10 nm	20 μs	1.0 AU
Expanded polystyrene debris	40%	50%	10 nm	10 μs	1.0 AU
Polystyrene sanding debris	5%	35%	10 nm	10 μs	1.0 AU
50 nm PMMA	10%	50%	10 nm	10 μs	1.0 AU
PTFE suspension	10%	50%	10 nm	10 μs	1.0 AU
C. elegans	35%	75%	10 nm	10 μs	1.0 AU

a

b

520 **Supplementary Figure 1:** Image (a) and (b) point spread function across indicated line (Gaussian fit) of a 50 nm
521 polystyrene bead passively labeled with Atto 647N. Scale bar is 50 nm.

a

b

523 **Supplementary Figure 2:** Image (a) and (b) point spread function across indicated line (Gaussian fit) of a 100 nm
524 polystyrene bead passively labeled with Atto 647N. Scale bar is 100 nm.

a   b

527 **Supplementary Figure 3:** Image (a) and (b) point spread function across indicated line (Gaussian fit) of a 100 nm
528 polystyrene bead swell labeled with iDye Blue. Scale bar is 100 nm.

a   b

530
531
532 **Supplementary Figure 4:** Image (a) and (b) point spread function across indicated line (Gaussian fit) of a
533 polystyrene sanding debris passively labeled with Atto 647N. Scale bar is 100 nm.

Supplementary Figure 5: Comparison between images of 100 nm polystyrene beads initially and after 49 days in water for passive (a,b), swell (c,d), and covalent (e,f) labeling with Atto 647N.

Supplementary Figure 6: Comparison between images of 100 nm polystyrene beads initially and after 49 days in oil for passive (a,b), swell (c,d), and covalent (e,f) labeling with Atto 647N.

Supplementary Figure 7: Free dye dialyzed control STED image. No detectable signal from dialyzed solution, suggesting that free dye was largely removed with the dialysis step.

Supplementary Figure 8: Imaging *C. elegans* KWN117 adult exposed to dialyzed dye solution (no nanoparticles) expressing GFP (green) in the body wall and mCherry (yellow) in the apical intestinal membrane. Confocal overview, and high resolution of confocal and STED images of scanned area indicated by white boxes for parts of the digestive track in the intestine (a,b,c) and mouth (d,e,f). Note that while nanoparticles are not seen there is still some signal, likely from autofluorescence, that would have potentially been misinterpreted as labeled nanoplastic particles, due to a truer image size, but for the resolution provided by STED microscopy. Arrows indicate potential false positive signal from confocal imaging where STED imaging reveals that the signal is inconsistent with 50 nm particles.

558
559 **Supplementary Figure 9:** SEM images of samples including (a) 100 nm plain polystyrene beads, (b) 100 nm amine-
560 modified polystyrene beads, (c) 50 nm plain polystyrene beads, (d) PTFE particle suspension, (e) debris from a
561 heated polystyrene plate, and (f) debris from sanding a polystyrene petri dish.