Longitudinal *in vivo* micro-CT-based approach allows spatio-temporal characterization of fracture healing patterns and assessment of biomaterials in mouse femur defect models

Esther Wehrle[1], Duncan C Tourolle né Betts[1], Gisela A Kuhn[1], Erica Floreani[1], Malavika H Nambiar[1], Bryant J Schroeder[1], Sandra Hofmann[1,2], Ralph Müller[1]

[1] Institute for Biomechanics, ETH Zurich, Zurich, Switzerland, [2] Department of Biomedical Engineering and Institute for Complex Molecular Systems, Eindhoven University of Technology, The Netherlands.

Corresponding author:

Ralph Müller, PhD

Institute for Biomechanics

ETH Zurich

Leopold-Ruzicka-Weg 4

8093 Zurich, Switzerland

Email: ram@ethz.ch

Abstract

Thorough preclinical evaluation of novel biomaterials for treatment of large bone defects is

essential prior to clinical application. Using *in vivo* micro-computed tomography (micro-CT)

and mouse femoral defect models with different defect sizes, we were able to detect spatio-

temporal healing patterns indicative of physiological and impaired healing in three defect

sub-volumes and the adjacent cortex. The time-lapsed *in vivo* micro-CT-based approach was

then applied to evaluate the bone regeneration potential of biomaterials using collagen and

BMP-2 as test materials. Both collagen and BMP-2 treatment led to distinct changes in bone

turnover in the different healing phases. Despite increased periosteal bone formation, 87.5%

of the defects treated with collagen scaffolds resulted in non-unions. Additional BMP-2

application significantly accelerated the healing process and increased the union rate to

100%. This study further shows potential of time-lapsed *in vivo* micro-CT for capturing

spatio-temporal deviations preceding non-union formation and how this can be prevented

by application of biomaterials.

This study therefore supports the application of longitudinal *in vivo* micro-CT for

discrimination of normal and disturbed healing patterns and for the spatio-temporal

characterization of the bone regeneration capacity of biomaterials.

Introduction

Regeneration and healing of large bone defects (e.g. caused by trauma, infection, tumor resection, congenital skeletal disorders) is a treatment challenge in orthopedic surgery with as much as 10-20% of patients experiencing delayed or non-unions [1-3]. Recent advances in tissue engineering and material sciences (e.g. 3D-bioprinting) enabled the development of diverse biomaterials, which can be functionalized with biochemical factors (e.g. growth factors) and combined with cell therapeutic approaches [3-5]. In order to facilitate the clinical application of these innovative approaches for the treatment of large bone defects, their bone regeneration capacity needs to be systematically and thoroughly characterized in preclinical studies [6-8]. For this purpose, critical size defect models have been developed for load-bearing and non-load-bearing bones in small and large animals [7,9-13]. So far, most of these studies focused their evaluation on end-point radiological and histological analysis [14-16]. However, recent studies indicate that longitudinal non-invasive imaging could improve the evaluation of a biomaterial's bone regeneration capacity, due to the ability to follow the regeneration process in the same animal over time, thereby also reducing animal numbers according to the 3R's of animal welfare [17,18]. Particularly, *in vivo* micro-CT was shown to be suitable for the assessment of bone tissue formation and mineralization after biomaterial application in critical size defect models [17-19]. A further development is the consecutive registration of time-lapsed *in vivo* images [20]. We recently developed a longitudinal *in vivo* micro-CT-based approach for healing-phase-specific monitoring of fracture repair in mouse femur defect models [21]. Registration of consecutive scans using a branching scheme (bridged vs. unbridged defect) combined with a two/multi-threshold approach enabled the assessment of localized bone turnover and mineralization kinetics relevant for monitoring

callus remodelling [21,22]. Furthermore, we showed that longitudinal *in vivo* micro-CT imaging

itself did not significantly affect callus formation and remodelling [22].

It is well accepted that longitudinal non-invasive imaging of the healing process is

advantageous compared to cross-sectional study designs[22]. In order to apply *in vivo* micro-

CT-based longitudinal monitoring approaches for the evaluation of biomaterials, it has to be

assessed, whether these approaches allow for reliable discrimination between normal and

impaired healing conditions (e.g. critical-sized defects). So far, preclinical studies were often

not able to reliably capture the bone healing potential of biomaterials due to limitations in

study design: (I) cross-sectional setup, (II) assessment not considering defect sub-volumes,

(III) assessment not specific to the healing phases.

Therefore, this study assesses whether our recently developed time-lapsed micro-CT based

monitoring approach is suitable for discrimination of healing patterns associated with

physiological and impaired bone healing conditions using mouse femur defect models with

different gap sizes. In a second step, we evaluated whether the time-lapsed *in vivo* micro-CT-

based monitoring approach is suitable for profound characterization of the bone

regeneration capacity of biomaterials using well characterized porous collagen scaffolds and

bone morphogenetic protein (BMP-2) as example materials.

<u>Results</u>

In Experiment 1, we assessed the potential of time-lapsed *in vivo* micro-CT for reliable

discrimination between physiological and impaired fracture healing patterns. We compared

the healing process (week 0-6) in mice receiving either a small (0.9mm, n=10) or large femur

defect (2mm, n=8; Fig. 1; Supplementary Video 1). Via registration of consecutive micro-CT

scans, structural and dynamic callus parameters were followed in three callus sub-volumes

(defect center, DC; defect periphery, DP; cortical fragment periphery, FP) and the adjacent

cortical fragments (FC) over time (Fig. 1, 2). In Experiment 2, we applied the same time-

lapsed *in vivo* imaging approach to assess the bone regeneration capacity of collagen

scaffolds (n=8) and collagen scaffolds+BMP-2 (n=8; Fig. 3, 4, Supplementary Video 2; for

detailed study design see Supplementary Table S1).

General physical observation

Post-operative monitoring was performed with a scoring system defined in licence number

36/2014 (Kantonales Veterinäramt Zürich, Zurich, Switzerland), evaluating the following

parameters: social behaviour, body position, motion, load bearing of operated limb, habitus,

surgery wound. Scoring values: 0-4 (0=normal, 4=severely impaired, end-point criteria:

scored 4 in one category or overall score ≥8). Monitoring schedule: evening of surgery day,

day 1-3: morning and evening, day 4 until end of experiment: 3x/week, daily if scored ≥2 in

one criterion. All mice recovered rapidly from surgery. However, one animal from the 0.9mm

defect group only showed minor load bearing of the operated limb in the first post-operative

week, which then gradually increased, reaching normal values after 2 weeks. The body

weight did not significantly change during the healing period and did not differ between the

groups in Experiment 1 and 2 (see Supplementary Fig. 1 and 2). Social interaction between

mice and nesting behaviour did not differ from pre-surgical observations and were similar

for animals from all groups.

VOIs for evaluation by time-lapsed *in vivo* micro-CT

Experiment 1:

In order to exclude bias in the further micro-CT analyses, we compared the size of the two

central VOIs (DC, FC) used for normalization of CT parameters (depicted in Fig. 2) between

groups. One animal from the 2.0mm group could not be included in the analysis due to

incorrect registration caused by differences in leg alignment between micro-CT scans. The

two central VOIs encompassed the following volume for the 0.9mm group (n=10) and the

2.0mm group (n=7) with significant group differences given in brackets: $1.64\pm0.19mm^3$ vs.

$3.45\pm0.18mm^3$ for DC (p<0.0001), and $3.18\pm0.12mm^3$ vs. $0.94\pm0.30mm^3$ for FC (p<0.0001).

Experiment 2:

The DC and FC VOIs encompassed the following volume for the collagen group (n=8) and the

collagen+BMP-2 group (n=8): $3.09\pm0.22mm^3$ vs. $3.15\pm0.22mm^3$ for DC and $1.25\pm0.26mm^3$ vs.

$1.47\pm0.19mm^3$ for FC. No significant group differences in VOI size were detected between

the two groups.

Longitudinal monitoring of fracture healing by time-lapsed *in vivo* micro-CT in non-critical

and critical-sized femur defects (Experiment 1)

In both groups the repeated micro-CT scans (1x/week, Fig. 1, Supplementary Video 1)

covered the period from the day of the defect surgery (d0) until post-operative week 6. In

the 0.9mm group, distinct callus characteristics indicative of the different healing phases

(inflammation, repair, remodelling) were seen in the three callus VOIS (DC, DP, FP; Fig. 1 and

Fig. 2) as previously described in the same femur defect model [22]. Specifically, a strong

increase in bone formation with maximum values in week 1-2 (BFR: DC - 3.67±1.50%) and

week 2-3 (BFR: DP - 2.44 ±1.31%, FP - 2.50±0.89%; Fig. 2) indicated the progression from the

inflammation to the repair phase. This triggered bone resorption with maximum values seen

in week 2-3 (BRR: DC - 1.15±0.48%) and week 3-4 (BRR: DP - 0.82±0.74%, FP - 0.86±0.48%)

indicating progression to the remodelling phase. In all callus VOIs a significant up to 95x (DP)

increase (p<0.0001 for all VOIs) in bone volume was seen over time with maximum values

observed in week 4 (BV/TV: DC - 44±9%, DP - 24±10%, FP - 29±8%). From week 2 onwards,

the fraction of highly mineralized bone continuously increased in all callus VOIs until the

study endpoint (week 6).

In the 2.0mm defect group, only a slight onset in bone formation was seen in the callus VOIs

from week 0-1 to week 1-2 without characteristic peak values in the further healing process

(Fig. 1 and 2). We could also not observe any significant gain in bone volume throughout the

healing period, indicating an impaired and delayed healing pattern. Nevertheless, we saw a

continuous increase in the fraction of highly mineralized bone in all callus VOIs, indicating no

substantial disturbances of callus mineralization, despite the small callus volume.

Comparison of both groups (0.9mm defect, 2.0mm defect) showed similar patterns in

healing initiation with bone formation, first starting in the defect center (DC) and the cortical

fragment periphery (FP) from week 0-1 to week 1-2. However, in the DC VOI the increase in

bone formation (6x) was significantly lower (p=0.001) in the 2mm group compared to the

0.9mm group (19x) and the bone formation rates then remained stable at low values

(≤0.95%/day) throughout the healing period associated with only little endosteal callus

formation. In the FP VOI, the increase in bone formation from week 0-1 to week 1-2 was

similar for both groups, but the 2.0mm defect group then showed a sudden decline (-40%) in

bone formation (week 1-2 vs week 2-3) leading to premature cessation of periosteal callus

formation. In the defect periphery (DP) hardly any callus formation (BFR ≤0.21%/day) was

seen in the 2.0mm defect group throughout the healing period leading to significantly

smaller callus dimensions compared to the 0.9mm group from week 3 until the study end

(p=0.0001). With respect to bone resorption, no significant differences between the two

defect groups were seen in the early healing period (week 0-1, week 1-2) in any of the callus

sub-volumes. However, in the later healing period, bone resorption was significantly lower in

the 2.0mm defect group compared to the 0.9mm defect group in the DC (week 2-3: p=0.047,

week 4-5: p=0.0064), FP (week 2-3: p= 0.0045, week 5-6: p=0.0048) and DP (week 4-5:

p=0.0157, week 5-6: p=0.0177) VOIs, indicating impaired bone remodelling. By week 6, not

only the bone volume, but also the fraction of highly mineralized bone was lower in all callus

sub-volumes in the 2.0mm defect group compared to the 0.9mm defect group with

significant differences (p=0.0383) being observed in the DP sub-volume (BV_{645}/BV_{395}: 2.0mm

group - 63±11%, 0.9mm group - 82±4%).

To assess functional healing outcome, we particularly focused on the defect VOIs (DC+DP)

which are most important for evaluating later healing time points during the remodelling

phase of fracture healing. The previously observed differences in bone turnover, bone

volume and mineralization between the two groups also affected cortical bridging.

According to the standard clinical evaluation of X-rays, the number of bridged cortices per

callus was evaluated in two perpendicular planes and animals with ≥3 bridged cortices were

categorized as healed. Cortical bridging first occurred by week 3 in 70% of the animals in the

0.9mm defect group, whereas none of the animals in the 2.0mm group showed bridged

cortices at this time point (Table 1). By week 6, 90% of the 0.9mm defects were categorized

as healed with only 1 defect being classified as non-union. In contrast, in the 2.0mm defect

group only 1 animal showed cortical bridging and 87.5% manifested as non-unions.

Bone turnover in the cortical fragments (FC) showed a similar pattern in both groups,

without characteristic peak values in bone formation and resorption rates. Specifically,

maximum bone formation rates were significantly lower (0.9mm group: -80%, p<0.0001,

2.0mm group: -58%, p=0.004) compared to those observed in the periosteal region (FP).

Furthermore, a negative bone turnover was seen with maximum resorption rates (BRR in

week 2-3; 0.79±0.15%) exceeding bone formation rates (BFR in week 2-3: 0.49±0.37%) in the

0.9mm group. This resulted in a decrease in bone volume over time (0.9mm group: -19%,

2.0mm group: -57%). Additionally, a significant 8% (0.9mm group, p=0.0017) and 11%

(2.0mm group, p=0.0072) decrease in the fraction of highly mineralized bone was seen from

week 1 to week 3 suggesting reorganization of the cortical bone adjacent to the forming and

remodelling fracture callus.

Longitudinal assessment of biomaterials by time-lapsed *in vivo* micro-CT in critical-sized

femur defects (Experiment 2)

In the collagen group, no significant weekly changes in bone formation rate were seen in the

central defect VOIs (DC, DP; Fig. 3 and 4; Supplementary Video 2). Bone resorption rates

slightly but significantly increased during the early healing period (DC: 7.6x from week 0-1 to

week 1-2, DP: 4.3x from week 0-1 to week 1-2) and then decreased (DC) or remained stable

(DP) from week 2-3 to week 5-6. This led to only little callus formation in these central VOIs,

as similarly seen in the 2mm defect group from Experiment 1, indicating an impaired

endosteal fracture healing pattern associated with the application of the collagen scaffolds.

In the periosteal VOI (FP) a significant 3.2x increase in bone formation rate was seen from

week 0-1 to week 1-2, which remained stable during the subsequent week, before

decreasing after week 2-3 reaching baseline values by week 5-6. No significant changes were

seen in the bone resorption rate throughout the healing process. Compared to the 2mm

defect group from Experiment 1, similar periosteal callus volumes were observed in the early

healing period (BV/TV in week 2: collagen group: 13.08±4.88%, 2mm defect group:

15.99±5.09%). In the collagen group, the periosteal callus volume further increased (+53%)

from week 2 to week 3, whereas it decreased (-30%) in the 2mm defect group during the

same period, suggesting changes in periosteal callus formation potentially associated with

the application of the collagen scaffolds.

In the collagen+BMP-2 group a similar healing pattern compared to the collagen group was

seen in the defect center (DC). Nevertheless, BMP-2 application led to a significantly 2.1x

increased bone formation rate in week 1-2 compared to the collagen group, which was also

associated with a transiently increased mineralized callus volume in this endosteal VOI in

week 2. However, in week 6, both groups showed similar callus volumes and fraction of

highly mineralized bone, indicating only a slight and transient BMP-2 associated effect on

callus formation and remodelling in the defect center. In contrast, in DP and FP VOIs a

completely different picture was seen: Compared to the collagen group, a sudden 17x (DP)

and 3.6x (FP) induction in BFR already from week 0-1 to week 1-2 was detected. This

indicates that collagen+BMP-2 scaffolds are able to induce bone formation at defect

locations distant to the cortical bone potentially allowing healing of large defects. The BMP-2

induced increase in the bone formation rate was higher but persisted shorter compared to

the 0.9mm defect group with uncompromised healing in Experiment 1. This led to a

significant 318x (DP) and 9.1x (FP) increase in bone volume by week 2 (DP: $p<0.0001$; FP:

$p=0.0002$). The periosteal callus volume significantly ($p<0.0001$ for DP and FP) exceeded the

values of the collagen group and was also higher compared to the 0.9mm group from

Experiment 1. In both VOIs a significant 63x (DP) and 10x (FP) increase in bone resorption

was seen from week 1-2 to week 2-3 ($p<0.0001$ for both VOIs), indicating early onset of

callus remodelling. The bone resorption rates then remained at significantly higher levels

compared to the collagen group and both groups from Experiment 1, indicating pronounced

callus remodelling in the collagen+BMP-2 group. The fraction of highly mineralized tissue

remained significantly lower in the collagen+BMP-2 group indicating that the remodelling

process was still ongoing, whereas the bone healing process had finished in all other groups.

Despite the BMP-2 associated improved healing outcome, the healing pattern was

completely different compared to the 0.9mm defect group with uncompromised healing. In

the collagen+BMP-2 group bone formation mainly took place in the periosteal regions and

the defect periphery, whereas in the 0.9mm defect group bone formation mainly took place

in the defect center. The collagen group showed similar values compared to the 2.0mm

defect group indicating impaired healing, suggesting that the collagen scaffold might have

blocked endosteal callus formation.

In the FC VOI, we saw a similar pattern in all indices for the collagen and the collagen+BMP-2

group without any significant differences between groups. Specifically, the bone formation

rate did not significantly change over time in both groups. Similar to the 2mm defect group

from Experiment 1, a significant induction of bone resorption rate was seen from week 0-1

to week 1-2. From week 1 until the study end, the bone volume significantly ($p<0.0001$)

decreased in both groups (collagen group: -48%, collagen+BMP-2 group: -44%). Furthermore, a significant decline in the fraction of highly mineralized bone was observed in both groups from week 0 to week 6 (collagen group: -9%, $p=0.0002$; collagen+BMP-2 group: -13%, $p<0.0001$), as similarly observed for the 2mm defect group in Experiment 1 (-16%, $p=0.003$).

Cortical bridging occurred by week 2 in 100% of the animals in the collagen+BMP-2 group, whereas no animal in the collagen group showed bridged cortices at this time point (Table 2). In the BMP-2 treated defects, cortical bridging also occurred 1 week earlier compared to the 0.9mm defect group from Experiment 1. In contrast, in the collagen group only 1 animal showed cortical bridging and 87.5% manifested as non-unions.

Histology

As shown by Safranin-O staining six weeks after osteotomy, hardly any cartilage residuals were present in the defect region in all groups, indicating progression of the healing process to the final remodelling stage (Fig. 5, Row 1 and 2). To visualize potential remnants of the collagen scaffolds in Experiment 2, 1-2 samples/group were stained with Sirius-Red (Fig. 5, Row 3 and 4). For comparisons, we also included sections of the original collagen scaffolds (Fig. 5, Row 5), where red color of the filaments is indicative of collagen. In contrast, no red signal indicative of collagen was seen in the defect center of both groups (Fig. 5, Row 4). This suggested complete degradation of the scaffolds with accumulation of fat cells in the defect (unbridged defects in collagen group and in the restored medullary cavity, bridged defects in the collagen+BMP-2 group; Fig. 5, Row 4).

<u>Discussion</u>

In this study, we showed that time-lapsed *in vivo* micro-CT allows for spatio-temporal

discrimination between physiological and impaired fracture healing patterns in a mouse

femur defect model. For this purpose, we compared the healing pattern in three callus sub-

volumes and the adjacent cortical fragments in a small (0.9mm) and a large (2.0mm) defect

group using a previously developed two-threshold density micro-CT protocol [21,22]. In a

second step, we applied the micro-CT based monitoring approach for the characterization of

the bone regeneration capacity of biomaterials using porous collagen scaffolds +/- bone

morphogenetic protein (BMP-2) as test materials.

By registering consecutive scans, we were able to include dynamic parameters such as bone

formation and resorption in our micro-CT based monitoring approach as previously

described [21]. In the small defect group (0.9mm), this allowed for characterization of the

different healing phases seen by changes in formation and resorption in the osseous callus

volume. Specifically, we saw that the initiation of bone formation (maximum in week 1-2),

indicating the onset of the reparative phase, triggered bone resorption (maximum in week 2-

3) thereby initiating the remodelling phase. Maximum osseous callus volumes were

observed in week 3, which remained stable until the study end, while the callus

mineralization increased throughout the healing period. The observed bone turnover (bone

formation triggering bone resorption) and callus maturation (increasing mineralization of

initial callus) patterns are similar to a recent study in 1.5mm defects, which showed an

uncompromised healing pattern [22]. However, the smaller defect size (- 40%) in the current

study, changed the temporal occurrence of peaks in bone formation and resorption, which

were seen one week earlier compared to the previous study in 1.5mm defects, indicating

faster healing progression.

As expected from literature [23], the larger defects (2.0mm) showed impaired healing

predominantly leading to non-unions in 7 of 8 animals at the study end (Fig. 2, Table 1). This

is in line with a study by Zwingenberger at al. [23], which previously showed a strong

correlation of the defect size and non-unions assessed via *in vivo* x-ray measurements as

well as end point micro-CT and histological analyses in a similar defect model. Via

registration of consecutive *in vivo* micro-CT scans, we were now able to reveal and visualize

the preceding spatio-temporal deviations in callus formation and remodelling compared to

the uncompromised healing pattern seen in the 0.9mm defect group. Deviations from

normal healing occurred in all callus sub-volumes (defect center, defect periphery, cortical

fragment periphery), although initiation of bone formation was not changed spatio-

temporally, starting in the same sub-volumes (DC, FP) and at the same time (week 0-1 to

week 1-2). However, the rise in bone formation was significantly lower endosteally and the

duration of the bone formation was reduced periosteally compared to the 0.9mm defect

group. This also led to only small endosteal and peripheral callus dimensions with the

periosteal callus volume even decreasing to baseline values by the study end. Under normal

healing conditions, callus formation in this femur defect model proceeds from both the

endosteal and the periosteal regions to the defect periphery [22,24], whereas in large defects

hardly any bone formation was seen here, suggesting early termination of the fracture

healing process.

It is important to separately look at the adjacent cortical fragments [22], where we previously

saw an opposite trend in bone turnover compared to the callus sub-volumes. Whereas bone

formation was the dominant factor in the callus VOIs, bone resorption was the main factor in

the adjacent cortex. In the current study, increased defect size was associated with a

significant higher decline in cortical bone volume (-67% vs. -19%) and bone mineral density (-

16% vs. -6%; Fig. 1 and Fig. 2). Peri-fracture bone resorption and demineralization of cortical

bone have also been previously reported in preclinical and clinical studies and were

associated with stiff fixation leading to stress shielding of the bone [25,26]. Our recently

developed time-lapsed *in vivo* micro-CT monitoring approach therefore allowed to precisely

characterize the spatio-temporal changes in structural and dynamic callus parameters

preceding non-unions.

In a next step, we applied this monitoring approach to evaluate the bone regeneration

potential of biomaterials using collagen +/- BMP-2 as test materials. We selected collagen as

test material due to its wide usage in scaffolds intended for promotion of bone regeneration

and the comprehensive literature on its performance in *in vitro*, preclinical and clinical

applications [27-29]. In our study, the application of collagen scaffolds did not significantly

improve bone regeneration compared to empty defects of the same size, with the same

non-union rates being observed at the study end (87.5% in both groups). Although periosteal

bone formation was more pronounced in the collagen group, the fracture healing outcome

was not different between groups. This is in line with previous bone defect studies in

different rodent models (loaded and non-loaded bones) reporting no significant effect of

collagen scaffolds on bone regeneration with incomplete bone union or non-unions at the

study end [30,31]. Similarly, in large animal models collagen scaffolds either failed to prevent

non-unions [32] or to restore the mechanical bone properties [33]. The low regeneration

potential of collagen scaffolds has been attributed to a general lack of bioactivity of collagen

despite its overall favorable features such as low antigenicity, high biodegradability and high biocompatibility [27-29]. Furthermore, studies indicate a high relevance of the pore size in the collagen scaffolds, with smaller pores potentially being affected by cellular occlusion, and preventing cellular penetration, production of extracellular matrix and neovascularization of the inner areas of the scaffold [28]. In contrast, larger pores have been associated with low mechanical scaffold properties and early scaffold degradation [34,35]. A major limitation of most studies is that they did not include empty defect and positive controls, which would be essential for better understanding of specific changes in healing patterns mediated by different biomaterials.

To further promote bone healing, scaffolds have been incubated in solutions containing growth factors (e.g. BMP-2, BMP-7; [36,37]). Especially BMP-2 has been widely applied in preclinical studies to promote healing of critical sized defects (for review see [38]) and in clinical settings. However, studies reported BMP-2 associated adverse events and complications (e.g. antibody formation, inflammation, ectopic bone formation, carcinogenicity [39-41]). Therefore, using low BMP-2 dosages seems crucial in order to avoid adverse effects while preserving its osteoanabolic potential [42]. So far preclinical studies used a wide range of BMP-2 dosages (0.1-150.000 µg BMP-2 per defect in small animals as summarized in a comprehensive review by Gothard et al. [38]). In this study, we therefore down-scaled the BMP-2 dosages from previous studies (low BMP-2 dosages with beneficial effect on bone healing; 10/75 µg BMP-2 per defect [43,44]) to the volume of our scaffold (2 µg BMP-2 per defect). Similar to other studies [38], BMP-2 application significantly accelerated the healing process leading to early cortical bridging. However, when looking at the defect sub-volumes separately, we saw that the spatio-temporal healing pattern largely differed from the physiological healing pattern seen in the 0.9mm group. In the collagen+BMP-2

group the increase in the bone formation rate was higher but persisted for a shorter amount

of time compared to the 0.9mm defect group. Furthermore, bone formation mainly took

place in the periosteal regions and the defect periphery, whereas in the 0.9mm defect group

bone formation was predominantly seen in the defect center. This supports the assumption

that the collagen scaffold itself might have hindered cells from migrating into the defect

center. In line with other studies [30,45], the collagen scaffolds were degraded in both groups

by the end of the study as shown by absence of collagen fibers in the defect center via Sirius

Red staining of histological sections. Accumulation of fat cells inside the formed cortical shell

(unions) or in the defect center (non-unions) indicated differentiation of mesenchymal stem

cells (MSCs) towards the adipogenic lineage in the later healing period. Concluding from the

time-lapsed *in vivo* micro-CT evaluation, strong BMP-2 induced bone formation associated

with osteogenic differentiation of MSCs was only transiently observed in the early healing

period. Removal of the BMP-2 induced stimulus in later healing phases might have caused a

change from osteogenic to adipogenic differentaion of MSCs. This shift might have been

further strengthened by stress shielding of the defect region associated with stiff external

fixation [46].

Our study therefore shows that sub-volume specific characterization of biomaterials seems

crucial for assessing their bone regeneration potential. The study further indicates that time-

lapsed *in vivo* micro-CT combined with our recently developed two-threshold density

approach should be used in future studies to identify parameters for prediction of non-

unions in early healing phases. Via registration of consecutive scans as described recently,

we were able to precisely characterize and understand which spatio-temporal deviations led

to non-union formation and how this was prevented by BMP-2 application. Using collagen

and BMP-2 as test materials, the time-lapsed *in vivo* micro-CT-based monitoring approach was shown to be suitable for spatio-temporal assessment of callus formation and remodelling patterns and could be used in future studies to characterize and precisely understand the regeneration capacity of novel biomaterials.

The current study has several limitations. We did not track the degradation of the collagen scaffolds over time and only performed end-point histological assessment of collagen residuals via Sirius Red staining. Future studies should apply fluorescent biomaterials and reporters, which could be visualized via *in vivo* optical imaging [47-49]. We did also not measure the BMP-2 release kinetics. This could be similarly achieved via the use of fluorescently-labeled growth factors[50] in combination with multimodal imaging (e.g. photoacoustic imaging, PET, SPECT, micro-CT)[17,51]. Furthermore, in order to reliably create critical-sized defects, the defect size would need to be increased by ca. 25% in future studies.

Nevertheless, application of time-lapsed *in vivo* micro-CT allows faster and more precise evaluation of biomaterials for bone regeneration, thereby also reducing the animal numbers involved according to the 3R's of animal welfare. It could further be used for early prediction of non-union formation and identification of biomarkers. The approach could be supplemented with the registration of 2D-histology section into the 3D-micro-CT volume[52], potentially allowing for a spatio-temporal understanding of molecular and cellular changes induced by different biomaterials. To better mimic the clinical situation, future studies should also assess the performance of biomaterials under load application, which could be achieved using a recently developed loading fixator[53]. By combining our *in vivo* time-lapsed micro-CT based monitoring approach with individualized loading regimes, this would allow for thorough characterization of biomaterials under clinically relevant loading conditions.

To conclude, *in vivo* time-lapsed micro-CT allows (1) spatio-temporal discrimination between normal and disturbed healing patterns relevant for the detection of distinct features associated with different medical conditions and (2) spatio-temporal characterization of the bone regeneration capacity of biomaterials.

Materials and Methods

Animals

All animal procedures were approved by the local authorities (licence number: 36/2014; Kantonales Veterinäramt Zürich, Zurich, Switzerland). We confirm that all methods were carried out in accordance with relevant guidelines and regulations (Swiss Animal Welfare Act and Ordinance (TSchG, TSchV)) and reported considering ARRIVE guidelines. Female 12 week-old C57BL/6J mice were purchased from Janvier (Saint Berthevin Cedex, France) and housed in the animal facility of the ETH Phenomics Center (EPIC; 12h:12h light-dark cycle, maintenance feed (3437, KLIBA NAFAG, Kaiseraugst, Switzerland), 5 animals/cage). At an age of 20 weeks, all animals received a femur defect. In Experiment 1, one group of animals received a small defect (defect length: 0.86±0.09mm, n=10) and a second group received a large defect (defect length: 2.00±0.19mm, n=8; housing after surgery: 2-3 animals/cage). In Experiment 2 both groups received a 2mm femur defect with application of either collagen scaffolds (d=2mm, h=2mm; ILS, Saint Priest, France; n=8) or collagen scaffolds+BMP-2 (2.5µg/scaffold; PeproTech, London, UK; n=8). Perioperative analgesia (25 mg/L, Tramal®, Gruenenthal GmbH, Aachen, Germany) was provided via the drinking water two days before surgery until the third postoperative day. For surgery and micro-CT scans, animals were anesthetized with isoflurane (induction/maintenance: 5%/1-2% isoflurane/oxygen).

Femur defect

An external fixator (Mouse ExFix, RISystem, Davos, Switzerland; stiffness: 24N/mm[21]) was

positioned at the craniolateral aspect of the right femur and attached using four mounting

pins. First, the most distal pin was inserted approximately 2mm proximal to the growth

plate, followed by placement of the most proximal and the inner pins. Subsequently, a femur

defect was created using 1 and 2 Gigli wire saws for the small and the large defect,

respectively.

Time-lapsed *in vivo* micro-CT

Immediate post-surgery correct positioning of the fixator and the defect was visualized using

a vivaCT 40 (Scanco Medical AG, Brüttisellen, Switzerland) (isotropic nominal resolution: 10.5

µm; 55 kVp, 145 µA, 350 ms integration time, 500 projections per 180°, 21 mm field of view

(FOV), scan duration ca. 15 min). Subsequently, the defect region as well as the adjacent

cortex were scanned weekly (week 1-6) with the same settings and morphometric indices

and mineralization progression were determined in four volumes of interest (for details on

methods see [21,22]): defect center (DC), defect periphery (DP), cortical fragment center (FC),

and fragment periphery (FP). Data were normalised to the central VOIs: DC/DC, DP/DC,

FC/FC, FP/FC. Cortical bridging was assessed as previously described in [22].

Animations

448 To further visualize the defect healing process and the VOIs involved, 3-dimensional

449 computer renderings were created from the time-lapsed micro-CT data for one mouse in

each respective group across both experiments (0.9mm defect group, 2.0mm defect group, collagen scaffold, collagen scaffold+BMP-2), then animated and captioned to create videos (Supplementary Video 1, Supplementary Video 2). Bone mineral density data was single-value thresholded (BMD = 395 mg HA/cm^3) at each time point to create a binary array, simplifying the rendering process. This binarized bone location data was interpolated using a Euclidean Distance Transform, generating data for time points in between each weekly measurement. This data was used to create smooth, animated transitions from one measurement to the next, for visualization purposes, and was not used in any analysis. To indicate bone formation and resorption between each time point, bone remodelling data from the time-lapsed *in vivo* micro-CT method was taken [21]. Depictions of the VOIs were rendered directly from their location data used in this approach. All renderings of the 3D data were performed in Paraview (Kitware, Version 5.6). All numerical analysis used for the animations was done using custom Python 3 scripts. Video editing and captioning was done in Hitfilm Express (FXhome, Version 13).

Histology

To exemplarily visualize the defect region, histology was performed in 1-2 animals/group. On day 42 femurs were excised, the femoral head was removed, and the samples were placed in 4% neutrally buffered formalin for 24 hours and subsequently decalcified in 12.5% EDTA for 10-14 days. The samples were embedded in paraffin and 4.5 μm longitudinal sections were stained with Safranin-O/Fast Green: Weigert's iron haematoxylin solution (HT1079, Sigma-Aldrich, St. Louis, MO) - 4min, 1:10 HCl-acidified 70% ethanol – 10s, tap water - 5min, 0.02% Fast Green (F7258, Sigma-Aldrich, St. Louis, MO) - 3min, 1% acetic acid - 10s, 0.1% Safranin-

O (84120, Fluka, St. Louis, MO) - 5min. In order to visualize remnants of the collagen

scaffolds, Sirius Red staining was performed in 1 animal from the collagen and 1 animal from

the collagen+BMP-2 group. For comparison, we also stained sections of the original collagen

matrix with Sirius-Red: Weigert's iron haematoxylin solution (HT1079, Sigma-Aldrich, St.

Louis, MO) - 8min, tap water - 10min, 1:9 Picro-Sirius Red solution (Picric acid: 80456, Fluka,

St. Louis, MO; Direct Red 80: AB133584, ABCR, Karlsruhe, Germany) - 1h, 5% acetic acid

2x10s. For both stainings, images were taken with Slide Scanner Pannoramic 250 (3D

Histech, Budapest, Hungary) at 20x magnification.

Statistics

CT analysis: Data were tested for normal distribution (Shapiro-Wilk-Test) and homogeneity

of variance (Levene-Test). Depending on the test outcome, group comparisons of data

derived at single time points were done by Student's t-test or Mann-Whitney U-tests (IBM

SPSS Statistics Version 23). For statistical evaluation of repeated measurements two-way

ANOVA with Geisser-Greenhouse correction and Bonferroni correction (GraphPad Prism 8)

were performed. The level of significance was set at $p < 0.05$.

Author Contributions Statement

The study was designed by E.W., G.A.K., S.H. and R.M.. The *in vivo* experiments were

performed by E.W., G.A.K. and E.F.. Histological stainings were performed by E.W. and

M.H.N.. Data analyses were performed by E.W. and D.C.T.B.. Illustrations of VOIs and

animations on callus formation and remodelling were made by B.J.S.. The manuscript was

written by E.W. and reviewed and approved by all authors.

Data availability

All necessary data generated or analyzed during the present study are included in this published article and its Supplementary Information files (preprint available on BioRxiv (BIORXIV/2020/). Additional information related to this paper may be requested from the authors.

Competing Interests

The authors declare no competing interests.

Acknowledgements

The authors gratefully acknowledge support from the EU (BIODESIGN FP7-NMP-2012-262948 and ERC Advanced MechAGE ERC-2016-ADG-741883). E. Wehrle received funding from the ETH Postdoctoral Fellowship Program (MSCA-COFUND, FEL-25_15-1).

References

1   Giannoudis, P., Tzioupis, C., Almalki, T. & Buckley, R. Fracture healing in osteoporotic fractures: is it really different? A basic science perspective. *Injury* **38 Suppl 1**, S90-99, doi:10.1016/j.injury.2007.02.014 (2007).
2   Syed, A. A., Agarwal, M., Giannoudis, P. V., Matthews, S. J. E. & Smith, R. M. Distal femoral fractures: long-term outcome following stabilisation with the LISS. *Injury-International Journal of the Care of the Injured* **35**, 599-607, doi:10.1016/S0020-1383(03)00247-X (2004).

3   Winkler, T., Sass, F. A., Duda, G. N. & Schmidt-Bleek, K. A review of biomaterials in bone
defect healing, remaining shortcomings and future opportunities for bone tissue engineering
THE UNSOLVED CHALLENGE. *Bone Joint Res* **7**, 232-243, doi:10.1302/2046-3758.73.Bjr-2017-
0270.R1 (2018).

4   Przekora, A. The summary of the most important cell-biomaterial interactions that need to
be considered during in vitro biocompatibility testing of bone scaffolds for tissue engineering
applications. *Mat Sci Eng C-Mater* **97**, 1036-1051, doi:10.1016/j.msec.2019.01.061 (2019).

5   Stevens, M. M. Biomaterials for bone tissue engineering. *Mater Today* **11**, 18-25, doi:Doi
10.1016/S1369-7021(08)70086-5 (2008).

6   Hulsart-Billstrom, G. *et al.* A Surprisingly Poor Correlation between in Vitro and in Vivo
Testing of Biomaterials for Bone Regeneration: Results of a Multicentre Analysis. *Eur Cells*
Mater **31**, 312-322, doi:10.22203/eCM.v031a20 (2016).

7   Pearce, A. I., Richards, R. G., Milz, S., Schneider, E. & Pearce, S. G. Animal models for implant
biomaterial research in bone: A review. *Eur Cells Mater* **13**, 1-10 (2007).

8   Peric, M. *et al.* The rational use of animal models in the evaluation of novel bone
regenerative therapies. *Bone* **70**, 73-86, doi:10.1016/j.bone.2014.07.010 (2015).

9   Gomes, P. S. & Fernandes, M. H. Rodent models in bone-related research: the relevance of
calvarial defects in the assessment of bone regeneration strategies. *Lab Anim-Uk* **45**, 14-24,
doi:10.1258/la.2010.010085 (2011).

10   Harris, J. S., Bemenderfer, T. B., Wessel, A. R. & Kacena, M. A. A review of mouse critical size
defect models in weight bearing bones. *Bone* **55**, 241-247, doi:10.1016/j.bone.2013.02.002
(2013).

11   Holstein, J. H. *et al.* Mouse Models for the Study of Fracture Healing and Bone Regeneration.
Osteoporosis Research: Animal Models, 175-191, doi:10.1007/978-0-85729-293-3_14 (2011).

12   Horner, E. A. *et al.* Long Bone Defect Models for Tissue Engineering Applications: Criteria for
Choice. *Tissue Eng Part B-Re* **16**, 263-271, doi:10.1089/ten.teb.2009.0224 (2010).

13   van Griensven, M. Preclinical testing of drug delivery systems to bone. *Adv Drug Deliver Rev*
94, 151-164, doi:10.1016/j.addr.2015.07.006 (2015).

14   Gauthier, O. *et al.* In vivo bone regeneration with injectable calcium phosphate biomaterial:
A three-dimensional micro-computed tomographic, biomechanical and SEM study.
Biomaterials **26**, 5444-5453, doi:10.1016/j.biomaterials.2005.01.072 (2005).

15   Martino, M. *et al.* Growth factors engineered for super-affinity to extracellular matrix
enhance tissue healing. *J Tissue Eng Regen M* **8**, 35-36 (2014).

16   Meinel, L. *et al.* Silk based biomaterials to heal critical sized femur defects. *Bone* **39**, 922-931,
doi:10.1016/j.bone.2006.04.019 (2006).

17   Lienemann, P. S. *et al.* Longitudinal in vivo evaluation of bone regeneration by combined
measurement of multi-pinhole SPECT and micro-CT for tissue engineering (vol 5, 10238,
2015). *Sci Rep-Uk* **5**, doi:ARTN 1239110.1038/srep12391 (2015).

18   van Lenthe, G. H. *et al.* Nondestructive micro-computed tomography for biological imaging
and quantification of scaffold-bone interaction in vivo. *Biomaterials* **28**, 2479-2490,
doi:10.1016/j.biomaterials.2007.01.017 (2007).

19   Boerckel, J. D. *et al.* Effects of protein dose and delivery system on BMP-mediated bone
regeneration. *Biomaterials* **32**, 5241-5251, doi:10.1016/j.biomaterials.2011.03.063 (2011).

20   Mehta, M., Checa, S., Lienau, J., Hutmacher, D. & Duda, G. N. In Vivo Tracking of Segmental
Bone Defect Healing Reveals That Callus Patterning Is Related to Early Mechanical Stimuli.
Eur Cells Mater **24**, 358-371, doi:DOI 10.22203/eCM.v024a26 (2012).

21   Tourolle né Betts, D. W., E.; Paul, GR; Kuhn, GA; Christen, P; Hofmann, S; Müller, R. The
association between mineralised tissue formation and the mechanical local in vivo
environment: Time-lapsed quantification of a mouse defect healing model. *Sci Rep-Uk* **10**,
1100, doi:doi: https://doi.org/10.1038/s41598-020-57461-5 (2020).

568 569 570	22	Wehrle E, T. n. B. D., Kuhn GA, Scheuren AC, Hofmann S, Müller R. Evaluation of longitudinal time-lapsed in vivo micro-CT for monitoring fracture healing in mouse femur defect models. *Sci Rep-Uk* **9**, 17445, doi:doi: https://doi.org/10.1038/s41598-019-53822-x (2019).
571 572	23	Zwingenberger, S. *et al.* Establishment of a femoral critical-size bone defect model in immunodeficient mice. *J Surg Res* **181**, E7-E14, doi:10.1016/j.jss.2012.06.039 (2013).
573 574 575	24	Borgiani, E. *et al.* Age-Related Changes in the Mechanical Regulation of Bone Healing Are Explained by Altered Cellular Mechanoresponse. *J Bone Miner Res*, doi:10.1002/jbmr.3801 (2019).
576 577 578	25	Al-Tamimi, A. A., Peach, C., Fernandes, P. R., Cseke, A. & Bartolo, P. J. D. S. Topology Optimization to reduce the stress shielding effect for orthopedic applications. *Proc Cirp* **65**, 202-206, doi:10.1016/j.procir.2017.04.032 (2017).
579 580	26	Bobyn, J. D. *et al.* The effect of stem stiffness on femoral bone resorption after canine porous-coated total hip arthroplasty. *Clin Orthop Relat Res*, 196-213 (1990).
581 582 583	27	Zhang, D. W., Wu, X. W., Chen, J. D. & Lin, K. L. The development of collagen based composite scaffolds for bone regeneration. *Bioact Mater* **3**, 129-138, doi:10.1016/j.bioactmat.2017.08.004 (2018).
584 585	28	Ferreira, A. M., Gentile, P., Chiono, V. & Ciardelli, G. Collagen for bone tissue regeneration. *Acta Biomater* **8**, 3191-3200, doi:10.1016/j.actbio.2012.06.014 (2012).
586 587	29	Glowacki, J. & Mizuno, S. Collagen scaffolds for tissue engineering. *Biopolymers* **89**, 338-344, doi:10.1002/bip.20871 (2008).
588 589 590	30	Hertweck, J. *et al.* CD34(+) cells seeded in collagen scaffolds promote bone formation in a mouse calvarial defect model. *J Biomed Mater Res B Appl Biomater* **106**, 1505-1516, doi:10.1002/jbm.b.33956 (2018).
591 592 593	31	Stuckensen, K. *et al.* Anisotropic Cryostructured Collagen Scaffolds for Efficient Delivery of RhBMP-2 and Enhanced Bone Regeneration. *Materials (Basel)* **12**, doi:10.3390/ma12193105 (2019).
594 595 596	32	Cipitria, A. *et al.* BMP delivery complements the guiding effect of scaffold architecture without altering bone microstructure in critical-sized long bone defects: A multiscale analysis. *Acta Biomater* **23**, 282-294, doi:10.1016/j.actbio.2015.05.015 (2015).
597 598 599	33	Sarkar, M. R. *et al.* Bone formation in a long bone defect model using a platelet-rich plasma-loaded collagen scaffold. *Biomaterials* **27**, 1817-1823, doi:10.1016/j.biomaterials.2005.10.039 (2006).
600 601	34	Karageorgiou, V. & Kaplan, D. Porosity of 3D biomaterial scaffolds and osteogenesis. *Biomaterials* **26**, 5474-5491, doi:10.1016/j.biomaterials.2005.02.002 (2005).
602 603	35	Luo, Z. W. *et al.* Effect of Pore Size on the Biodegradation Rate of Silk Fibroin Scaffolds. *Adv Mater Sci Eng*, doi:Artn 31539710.1155/2015/315397 (2015).
604 605 606	36	Begam, H., Nandi, S. K., Kundu, B. & Chanda, A. Strategies for delivering bone morphogenetic protein for bone healing. *Mat Sci Eng C-Mater* **70**, 856-869, doi:10.1016/j.msec.2016.09.074 (2017).
607 608	37	Salazar, V. S., Gamer, L. W. & Rosen, V. BMP signalling in skeletal development, disease and repair. *Nat Rev Endocrinol* **12**, 203-221, doi:10.1038/nrendo.2016.12 (2016).
609 610 611	38	Gothard, D. *et al.* Tissue Engineered Bone Using Select Growth Factors: A Comprehensive Review of Animal Studies and Clinical Translation Studies in Man. *Eur Cells Mater* **28**, 166-208, doi:DOI 10.22203/eCM.v028a13 (2014).
612 613	39	James, A. W. *et al.* A Review of the Clinical Side Effects of Bone Morphogenetic Protein-2. *Tissue Eng Part B-Re* **22**, 284-297, doi:10.1089/ten.teb.2015.0357 (2016).
614 615	40	Skovrlj, B. *et al.* Association Between BMP-2 and Carcinogenicity. *Spine* **40**, 1862-1871, doi:10.1097/Brs.0000000000001126 (2015).
616 617	41	Tannoury, C. A. & An, H. S. Complications with the use of bone morphogenetic protein 2 (BMP-2) in spine surgery. *Spine J* **14**, 552-559, doi:10.1016/j.spinee.2013.08.060 (2014).

42 Schmidt-Bleek, K., Willie, B. M., Schwabe, P., Seemann, P. & Duda, G. N. BMPs in bone
regeneration: Less is more effective, a paradigm-shift. *Cytokine Growth F R* **27**, 141-148,
doi:10.1016/j.cytogfr.2015.11.006 (2016).
43 Karageorgiou, V. *et al.* Porous silk fibroin 3-D scaffolds for delivery of bone morphogenetic
protein-2 in vitro and in vivo. *J Biomed Mater Res A* **78**, 324-334, doi:10.1002/jbm.a.30728
(2006).
44 Zhang, W. *et al.* VEGF and BMP-2 promote bone regeneration by facilitating bone marrow
stem cell homing and differentiation. *Eur Cell Mater* **27**, 1-11; discussion 11-12,
doi:10.22203/ecm.v027a01 (2014).
45 Hollinger, J. O. *et al.* Recombinant human bone morphogenetic protein-2 and collagen for
bone regeneration. *J Biomed Mater Res* **43**, 356-364, doi:10.1002/(sici)1097-
4636(199824)43:4<356::aid-jbm3>3.0.co;2-7 (1998).
46 Herberg, S. *et al.* Combinatorial morphogenetic and mechanical cues to mimic bone
development for defect repair. *Sci Adv* **5**, doi:ARTN eaax247610.1126/sciadv.aax2476 (2019).
47 Fragogeorgi, E. A. *et al.* In vivo imaging techniques for bone tissue engineering. *J Tissue Eng*
10, doi:Artn 204173141985458610.1177/2041731419854586 (2019).
48 Gil, C. J. *et al.* In Vivo Tracking of Tissue Engineered Constructs. *Micromachines-Basel* **10**,
doi:ARTN 47410.3390/mi10070474 (2019).
49 Li, K. & Liu, B. Polymer-encapsulated organic nanoparticles for fluorescence and
photoacoustic imaging. *Chem Soc Rev* **43**, 6570-6597, doi:10.1039/c4cs00014e (2014).
50 Mafina, M. K., Sullivan, A. C. & Hing, K. A. Use of a fluorescent probe to monitor the
enhanced affinity of rh-BMP-2 to silicated-calcium phosphate synthetic bone graft
substitutes under competitive conditions. *Mat Sci Eng C-Mater* **80**, 207-212,
doi:10.1016/j.msec.2017.05.142 (2017).
51 Hulsart-Billstrom, G. *et al.* Non-invasive tri-modal visualisation via PET/SPECT/mu CT of
recombinant human bone morphogenetic protein-2 retention and associated bone
regeneration: A proof of concept. *J Control Release* **285**, 178-186,
doi:10.1016/j.jconrel.2018.07.012 (2018).
52 Taylor, C., Scheuren, A., Trüssel, A. & R., M. 3D local in vivo environment (LivE) imaging for
single cell protein analysis of bone tissue. . *Current Directions in Biomedical Engineering* **2**
(2016).
53 Wehrle E., P. G. R., Betts D.C., Kuhn G.A., Müller R. Individualized cyclic mechanical loading
improves callus properties in novel femur fracture loading model as assessed by time-lapsed
in vivo imaging and real-time micro-finite element analysis. . *Trans. Orthop. Res. Soc.* **44**,
1526 (2019).

Figure legends

Figure 1. Representative images (threshold: 645 mg HA/cm^3) of the defect region from

animals of the 0.9mm group (top) and the 2.0mm group (bottom).

Visualization of bone formation (orange) and resorption (blue) via registration of micro-CT

scans from weeks 1-6 to weeks 0-5.

Figure 2. Micro-CT based evaluation of bone parameters in the 0.9mm group (blue) and the

2.0mm group (red) using different VOIS: defect center (DC; a-c), defect periphery (DP; d-f),

cortical fragment center (FC; g-i), cortical fragment periphery (FP; j-l). a, d, g, j: Bone

formation rate (solid line) and bone resorption rate (dashed line) given in percent per day. b,

e, h, k: Bone volume (BV) normalized to TV (DC for DC and DP, FC for FC+FP). c, f, i, l: Degree

of bone mineralization given as ratio of bone volume with a density $\geq$645 mg HA/cm^3 to the

total osseous volume (threshold $\geq$395 mg HA/cm^3). n=7/10; a,d,g,j: * indicates $p < 0.05$

between consecutive weeks; [#] indicates $p < 0.05$ between groups. b,c,e,f,h,l,k,l: * indicates p

< 0.05 between groups; [#] indicates $p < 0.05$ between consecutive weeks.

Figure 3. Representative images (threshold: 645 mg HA/cm^3) of the defect region from

animals of the collagen group (top) and the collagen+BMP-2 group (bottom). Visualization of

bone formation (orange) and resorption (blue) via registration of micro-CT scans from weeks

1-6 to weeks 0-5.

Figure 4. Micro-CT based evaluation of bone parameters in the collagen group (blue) and the

collagen+BMP-2 group (red) using different VOIS: defect center (DC; a-c), defect periphery

(DP; d-f), cortical fragment center (FC; g-i), cortical fragment periphery (FP; j-l). a, d, g, j:

Bone formation rate (solid line) and bone resorption rate (dashed line) given in percent per

day. b, e, h, k: Bone volume (BV) normalized to TV (DC for DC and DP, FC for FC+FP). c, f, i, l:

Degree of bone mineralization given as ratio of bone volume with a density $\geq$645 mg HA/cm^3

to the total osseous volume (threshold $\geq$395 mg HA/cm^3). n=7/10; a,d,g,j: * indicates p $<$

0.05 between consecutive weeks; [#] indicates $p < 0.05$ between groups. b,c,e,f,h,l,k,l: *

indicates $p < 0.05$ between groups; [#] indicates $p < 0.05$ between consecutive weeks.

Figure 5. Histology of longitudinal sections of fractured femora 6 weeks after defect surgery.

Row 1: Safranin-O staining of 0.9mm and 2.0mm defect groups - overview images, scale bar

= 1 mm and area between inner pins of fixator, scale bar = 100 μm. Row 2: Safranin-O

staining of collagen and collagen+BMP-2 groups - overview images, scale bar = 1 mm and

area between inner pins of fixator, scale bar = 100 μm. Row 3: Sirius-Red staining of collagen

and collagen+BMP-2 groups - overview images, scale bar = 1 mm and area centered between

inner pins of fixator, scale bar = 100 μm. Row 4: Sirius-Red staining of defect center of

collagen group and collagen+BMP-2 group, scale bar = 50 μm. Row 5: Sirius-Red staining of

original collagen matrix, scale bar = 500 μm (left image) and 50 μm (right image).

    Tables

696   **Table 1.** Number of bridged cortices per callus evaluated weekly in two perpendicular planes

697   and number of mice with successful fracture healing in the 0.9mm and the 2.0mm defect

698   groups (≥ 3 bridged cortices, threshold 395 mg HA/cm^3).

Week	Group	Number of bridged cortices					Fracture healing outcome	
		0	1	2	3	4	Not healed	Healed
0	0.9mm	10	0	0	0	0	10	0
	2.0mm	8	0	0	0	0	8	0
1	0.9mm	10	0	0	0	0	10	0
	2.0mm	8	0	0	0	0	8	0
2	0.9mm	7	3	0	0	0	10	0
	2.0mm	8	0	0	0	0	10	0
3	0.9mm	1	0	2	6	1	3	7
	2.0mm	7	1	0	0	0	8	0
4	0.9mm	1	0	1	5	3	2	8
	2.0mm	7	0	0	1	0	7	1
5	0.9mm	1	0	0	4	5	1	9
	2.0mm	7	0	0	1	0	7	1
6	0.9mm	1	0	0	4	5	1	9
	2.0mm	7	0	0	1	0	7	1

Table 2. Number of bridged cortices per callus evaluated weekly in two perpendicular planes and number of mice with successful fracture healing in the collagen and the collagen+BMP-2 groups (≥ 3 bridged cortices, threshold 395 mg HA/cm^3).

Week	Group	Number of bridged cortices					Fracture healing outcome	
		0	1	2	3	4	Not healed	Healed
0	collagen	8	0	0	0	0	8	0
	collagen+BMP	8	0	0	0	0	8	0
1	collagen	8	0	0	0	0	8	0
	collagen+BMP	8	0	0	0	0	8	0
2	collagen	7	0	1	0	0	8	0
	collagen+BMP	0	0	0	0	8	0	8
3	collagen	7	0	0	1	0	7	1
	collagen+BMP	0	0	0	0	8	0	8
4	collagen	7	0	0	1	0	7	1
	collagen+BMP	0	0	0	0	8	0	8
5	collagen	7	0	0	1	0	7	1
	collagen+BMP	0	0	0	0	8	0	8
6	collagen	7	0	0	1	0	7	1
	collagen+BMP	0	0	0	0	8	0	8

Figure 1

Defect size	week 0	week 0-1	week 1-2	week 2-3	week 3-4	week 4-5	week 5-6
0.9 mm							
2.0 mm							

Figure 2

Figure 3

Group	week 0	week 0-1	week 1-2	week 2-3	week 3-4	week 4-5	week 5-6
Collagen							
Collagen + BMP-2							

Figure 4

Figure 5

	Femur overview	Defect center	Femur overview	Defect center

Experiment 1

Safranin-O — 0.9 mm defect group / 2.0 mm defect group

Experiment 2

Safranin-O — Collagen group / Collagen + BMP-2 group

Sirius Red — Collagen group / Collagen + BMP-2 group

Sirius Red — Collagen group / Collagen + BMP-2 group

Sirius Red — Collagen matrix / Collagen matrix