Discovery of deformation mechanisms and constitutive response of soft material surrogates of biological tissue by full-field characterization and data-driven variational system identification

Z. Wang,* J.B. Estrada,† E.M. Arruda,‡ & K. Garikipati§

October 13, 2020

Abstract

We present a novel, fully three-dimensional approach to soft material characterization and constitutive modeling with relevance to soft biological tissue. Our approach leverages recent advances in experimental techniques and data-driven computation. The experimental component of this approach involves *in situ* mechanical loading in a magnetic field (using MRI), yielding the entire deformation tensor field throughout the specimen regardless of the possible irregularities in its three-dimensional shape. Characterization can therefore be accomplished with data at a reduced number of deformation states. We refer to this experimental technique as MR-$\boldsymbol{u}$. Its combination with powerful approaches to inverse modelling, specifically methods of model inference, would open the door to insightful mechanical characterization for soft materials. In recent computational advances that answer this need, we have developed new, data-driven inverse techniques to infer the model that best explains the physics governing observed phenomena from a spectrum of admissible ones, while maintaining parsimony of representation. This approach is referred to as Variational System Identification (VSI). In this communication, we apply the MR–$\boldsymbol{u}$ approach to characterize soft biological tissue and polymers, and using VSI, we infer the physically best-suited and parsimonious mathematical models of their mechanical response. We demonstrate the performance of our methods in the face of noisy data with physical constraints that challenge the identification of mathematical models, while attaining high accuracy in the predicted response of the inferred models.

1   Introduction

Experimental measurements of full-field deformation are commonly restricted to in-plane or surface assessment of motion, e.g. with tracked deformation of a grid or speckle pattern [11, 6, 5, 32]. In many geometries, this can be considered representative of the through-thickness deformation (i.e. if plane stress or strain can be assumed) and a material sample can be inversely characterized accordingly. However, the plane stress or strain assumptions frequently break down in cases of biological materials, in which there are not only geometric complexities, but internal structural hierarchy and finite deformations as well. Thus, for applications aiming to characterize tissues, a fully three-dimensional measurement capability is a necessity. Furthermore, the class of three-dimensional imaging technique is an important consideration, as even if opacity is mitigated, conventional optical setups have a higher resolution in-plane versus out-of-plane. For these reasons, we have developed a magnetic resonance imaging- (MRI) based approach rooted in displacement-encoded MRI, in which alternating pulse field gradients in conjunction with synchronous sample motion and stimulated echoes provide phase-based images of the 3D displacement field [21]. This technique, termed alternating pulse field gradient stimulated echo imaging (APGSTEi), in a nod to the non-imaging variant pioneered by Cotts et al. [12], is presented in detail in Scheven et al. [31].

---

*Mechanical Engineering, University of Michigan
†Mechanical Engineering, University of Michigan
‡Mechanical Engineering, Biomedical Engineering, Macromolecular Science and Engineering, University of Michigan
§Mechanical Engineering, Mathematics and Michigan Institute for Computational Discovery & Engineering, University of Michigan; corresponding author

Given that testing of our class of samples necessitates measurement of full-field volumetric deformation for any combination of optical, mechanical, and/or biological material properties and geometry, we turn our attention to methodologies in which deformation measurements are translated into characterization directly. In general, this means solving the inverse problem – determining material properties by minimizing the error between the model solution and data, while respecting consistency with governing equations. One approach is to directly minimize the mismatch in the weak form of the momentum balance equation, the principle of virtual work. This class of material property identification techniques includes the constitutive equation gap method (CEGM) [15] and the virtual fields method (VFM) [25], which have been broadly expanded to a variety of applications in the past few decades including characterization of linear [18, 14, 16, 24, 37] and non-linear [17, 9] anisotropic metals and composites, hyperelastic rubbers [3, 26], and biological tissues [4, 29, 7, 38]. In particular, the VFM assumes a constitutive form for the material model and iteratively adjusts material parameters within that constitutive law until the mismatch between the internal virtual work and applied external virtual work is minimized. Thus, for simple materials where the constitutive model is known, the virtual fields method is an excellent candidate for inverse characterization; the aforementioned APGSTEi technique is used as the imaging platform for VFM-based material characterization of silicone rubber samples in our prior work [13], and therein termed MR-$\boldsymbol{u}$. However, soft and bio-materials have a variety of complicated material behavior and physics owing to chemistry and structural hierarchy; in many cases, the choice of material model is not firmly established. Furthermore, systematic and random error sources that require data filtering may in general have non-trivial implications in the resulting material parameter fits. In these cases – those where the underlying constitutive behavior and exact noise calibrations are not known *a priori* – the VFM is procedurally limited.

If our goal is not just to find parameter fits for a single chosen model and experimental noise correction method, but to describe the underlying physics with fidelity, we require a method that adjusts procedurally to reflect the true constitutive behavior itself. Hence, we expect to gain insight to the fundamental deformation mechanisms of native and engineered tissue, which, in turn, are critical for advances in tissue engineering, and orthopedic surgery. Therefore, we will adopt a novel method that can discover the proper physics from a large range of possible mechanisms, which is described next. This is the central thrust of the computational component of this work.

We have developed a class of inverse modeling techniques that allows physics discovery from experimental data. Our first step in this direction was motivated by an interest in discovering mechanisms that govern the physics of dynamic pattern formation in materials. As background, these processes lead to microstructures via reaction-diffusion and phase transition phenomena. Our approach is based on the insight that, in any model, the forms of mathematical operators encode physical mechanisms. In the case of dynamic pattern formation in materials, the physics is governed by first-order (in time) partial differential equations–a class that includes the time-dependent reaction-diffusion and phase field equations. In this context, algebraic operators acting on concentrations represent (coupled) reactions between components of the material, while the differential, Laplacian operator represents Fickian diffusion. We have extended and exploited connections of other mathematical operators, including higher-order ones, to more complex physical mechanisms. The products of algebraic and differential operators reveal non-linearities, often introduced due to coupling that originates in the thermodynamics. Our aim is to discover physics governing observed phenomena by identifying the minimal set of operators whose combination into partial differential equations completely describes the data at hand. It works through the weak form of the governing system of equations. We therefore refer to it as Variational System Identification or VSI [35, 34, 1]. It uses step-wise regression, a statistical test, penalization on loss functions to control over-fitting, mathematically rigorous operator staggering and physically well-founded approaches to mechanism elimination.

VSI works with spatially well-resolved as well as sparse data that may be noisy. In more recent developments, we have extended VSI to problems in which the data are spatially non-overlapping at distinct times, and also are temporally sparse, as is the case with many techniques of materials processing and characterization. This extension leverages the definition of experimentally realizable quantities of interest by manipulation of the weak form, and, via consistency tests, provides mathematical guarantees on the discovery of mechanisms [34]. A crucial ingredient in VSI is the recognition of universal aspects of the physics to intelligently constrain the paring down of operators. Thus, we have exploited the understanding of steady state *versus* transient phenomena [34], and here we extend it to physical stability of the inferred model. In related research, we also have developed Bayesian approaches to quantify the uncertainty in the discovered physics [1], and techniques that account for spatial and temporal heterogeneity of the physical mechanisms [36]. In this communication, we apply VSI to discover, from a range of possible candidates, the mechanisms of deformation of soft polymeric material from MR-$\boldsymbol{u}$ data.

Our approach to system identification is related to the Sparse Identification of Nonlinear Dynamics (SINDy) [8, 22, 30, 20], but differs in our use of the weak form rather than the strong form for identification of governing

equations. VSI inherits many advantages from the weak form, including (a) the natural identification of boundary conditions, (b) introduction of basis functions to interpolate the data, which can be chosen to have high regularity, (c) transfer of derivatives to variations, thus lowering the regularity required in the data, and (d) isolating operators on the data by judicious choice of variations. A different approach to physics discovery by Raissi and co-workers has focused upon determination of unknown coefficients in known systems of equations using Gaussian Processes [27] and deep neural networks [28]. However, in assuming the governing equations to have certain specific, classical forms, such as the Navier-Stokes equations, and seeking the corresponding coefficients, this approach takes a different path from ours. We seek to discover physics encapsulated in mathematical forms of equations and response functions: Our methods, apart from obeying broad physical principles of conservation laws and symmetry, and exploiting transient *versus* steady state phenomena and stability, do not impose specific physics. Instead, we aim to discover the physical mechanisms of deformation by considering a wide range of mechanisms that are encompassed within the conservation laws and symmetry restrictions. Here, we extend our techniques for application to soft material surrogates for biological tissue.

The experimental methods are described in Section 2. Section 3 details the VSI technique. Our results for inferring deformation mechanisms of soft biological tissue and polymeric materials from synthetic and experimental data appear in Section 4. A discussion and conclusions are presented in Section 5.

2   Methods

Figure 1: Schematic of the experimental setup (top view) for full-field displacement capture. A linear actuator prescribes a periodic, constant-amplitude, encoder-verified displacement of one edge of a sample, synchronous with a custom NMR pulse sequence which acquires slices of the entire full-field 3D displacement between reference states. A load cell measures the applied force on the sample, which is balanced by a force-return G10 tube and custom polyetherimide (Ultem) sample chamber [13].

2.1   Full-field displacement capture (FFDC)

The acquisition of fully three-dimensional displacement fields from samples undergoing finite deformations was demonstrated by a combination of a custom magnetic resonance pulse sequence, cyclic actuated loading, and a subsequent data analysis procedure. The specific details of the apparatus and pulse sequence can be found in [31], while exact data processing procedures are presented in more detail in [13]. However, a brief procedure is reproduced for the ease of the reader below.

Material samples rigidly fixed on either end by two grips or platens are loaded in global uniaxial tension inside the center of a 7T small-animal MRI system. One end of the sample is fixed rigidly to the stationary end of a custom polyetherimide chamber, while the other side is permitted to move in the free axis by a prescribed global displacement. This displacement is set by a captive linear actuator (L5918S2008-T10X2-A50, Nanotec Electronic GmbH and Co. KG, Germany) acting at a sufficient distance from the MRI to avoid interaction with the strong magnetic field.

Samples are then loaded and imaged synchronously and cyclically. Global uniaxial deformation is applied to the sample, which then is put into a state of tension and, at high loads, concurrently measured with a load cell (LCM300, Futek Advanced Sensor Technology Inc., Irvine, CA). For low forces (<10 N), loads at the equivalent global deformation states were measured externally and quasistatically using an ADMET materials testing system platform (ADMET, Inc., Norwood, MA, USA) equipped with a 25 N load cell. Briefly described,

the imaging procedure proceeds by encoding magnetic spins into the sample in the deformed state via a set of alternating pulsed field gradients, storage of those spins during a macroscopic return of the sample to the reference configuration, and subsequently unencoding via a second, identical pulsed field gradient pair. The result is a 3D map of accumulated phase of voxels in the reference configuration during the course of a deformation cycle, corresponding to the chosen Cartesian encoding direction, and is wrapped to 2π. Repeating this process – encoding for each of the three Cartesian directions – results in the wrapped displacement field as a function of 3D position in the tested sample.

The stored phases corresponding to displacement can then be either unwrapped, e.g. via custom implementation of algorithms such as described in [2] or numerically differentiated directly by a division analogue to filter convolution (termed *divolution*), described in more detail in [13]. The choice of spatial filter on the data and when to apply it is, in general, left to the user; both thermal and systematic detector noise are practical considerations for the inclusion of Gaussian, or window-type Hamming filters. For the purposes of this study, the displacement fields are numerically differentiated and cast in the form of the deformation gradient tensor, from which other finite strain tensors may be determined in a straightforward manner (see Section 3 for details on the mathematical formulation).

3 Discovery of deformation mechanisms in soft materials by Variational System Identification

We describe VSI for the discovery of constitutive laws from three-dimensional, full-field deformation data in soft materials obtained by the MR-$\boldsymbol{u}$ approach. Focusing on nonlinear hyperelasticity in this communication, we develop our methods in the context of the strain energy density function. In this setting, the relevant mechanisms of volumetric, isochoric, and anisotropic deformation are resolved by functions of the right Cauchy-Green strain tensor.

The displacement field is written as $\boldsymbol{u}(\boldsymbol{X})$, where $\boldsymbol{X}$ is the reference position, the deformation gradient tensor is $\boldsymbol{F} = \boldsymbol{1} + \partial\boldsymbol{u}/\partial\boldsymbol{X}$, and the right Cauchy-Green tensor is $\boldsymbol{C} = \boldsymbol{F}^{\mathrm{T}}\boldsymbol{F}$. It follows that volumetric response is entirely determined by $J = \det\boldsymbol{C}$ and the isochoric (volume preserving) response is determined by $\overline{\boldsymbol{C}} = J^{-2/3}\boldsymbol{C}$. Defining the first principal invariant $\overline{I}_1(\boldsymbol{C}) = \mathrm{tr}\overline{\boldsymbol{C}}$, a commonly used constitutive model for isotropic and nearly incompressible soft biological tissue and polymers is the neo-Hookean strain energy density function,

$$W(\boldsymbol{C}) = \frac{1}{2}\kappa(J-1)^2 + \frac{1}{2}\mu(\overline{I}_1 - 3),\tag{1}$$

where the bulk modulus is κ and the shear modulus is μ. Our goal in this communication is to go beyond the limitation of such prescribed models. As prefaced in the Introduction, we now prepare to present VSI for the inference of models that represent the physics in sufficient detail ("expressiveness" in machine learning terms) while maintaining efficiency of representation. The building blocks of our approach are mathematical terms that encapsulate the relevant deformation mechanisms and lead to operators in the equations below.

VSI works by considering a number of deformation mechanisms as *possible* candidates in the strain energy density function. As candidate deformation mechanisms for soft biological tissue and polymers we consider volumetric, isochoric, and orthotropic mechanisms, via the additional principal tensor invariant $\overline{I}_2(\boldsymbol{C}) = \frac{1}{2}((\mathrm{tr}\overline{\boldsymbol{C}})^2 - \mathrm{tr}(\overline{\boldsymbol{C}}^2))$, and $\overline{I}_a(\boldsymbol{C}) = \boldsymbol{a}\cdot\overline{\boldsymbol{C}}\boldsymbol{a}$ the squared stretch along a direction $\boldsymbol{a}$ by adding terms with coefficients $\theta_1, \theta_2, \ldots$ beyond those used in Equation (1):

$$W(\boldsymbol{C}) = \underbrace{\frac{1}{2}\kappa(J-1)^2}_{\text{volumetric}} + \underbrace{\frac{1}{2}\mu(\overline{I}_1 - 3) + \theta_1(\overline{I}_1 - 3)^2 + \theta_2(\overline{I}_2 - 3) + \theta_3(\overline{I}_2 - 3)^2}_{\text{isochoric}} + \underbrace{\theta_4(\overline{I}_a - 1) + \theta_5(\overline{I}_a - 1)^2}_{\text{orthotropic}}.\tag{2}$$

The first Piola-Kirchhoff stress tensor is $\boldsymbol{P} = \partial W/\partial\boldsymbol{F}$ and leads to the form

$$\boldsymbol{P} = \kappa\boldsymbol{P}_0(J, \boldsymbol{F}) + \mu\boldsymbol{P}_{\mathrm{s}}(\overline{I}_1, \boldsymbol{F}) + \theta_1\boldsymbol{P}_1(\overline{I}_1, \boldsymbol{F}) + \theta_2\boldsymbol{P}_2(\overline{I}_2, \boldsymbol{F}) + \theta_3\boldsymbol{P}_3(\overline{I}_2, \boldsymbol{F}) + \theta_4\boldsymbol{P}_4(\overline{I}_a, \boldsymbol{F}) + \theta_5\boldsymbol{P}_5(\overline{I}_a, \boldsymbol{F})\tag{3}$$

For the sake of brevity, we have omitted the explicit forms of the stress operators $\boldsymbol{P}_0$–$\boldsymbol{P}_5$. VSI works with the weak form of the stress equilibrium equation, written as:

$$\int_{\Omega}\frac{\partial\boldsymbol{w}}{\partial\boldsymbol{X}} : (\kappa\boldsymbol{P}_0 + \mu\boldsymbol{P}_{\mathrm{s}} + \theta_1\boldsymbol{P}_1 \cdots + \theta_5\boldsymbol{P}_5)\,\mathrm{d}V - \int_{\Gamma_T}\boldsymbol{w}\cdot\boldsymbol{T}\mathrm{d}S = \boldsymbol{0}\tag{4}$$

where $\boldsymbol{w}$ is the weighting function (the variation on the displacement field) and we have used Equation (3) for the stress. The solid volume is represented by Ω and Γ_T is the part of the boundary over which traction loading, $\boldsymbol{T}$, is applied.

Given MR-$\boldsymbol{u}$ data as a set of three-dimensional displacement vectors, $\boldsymbol{d}_i$, where $i = 1, \ldots, N$ enumerate the points $\boldsymbol{X}_i$ throughout the reference configuration of the sample where data has been obtained, we construct a finite element mesh with nodes at $\boldsymbol{X}_i$. Using appropriate finite element interpolation functions, $N^A(\boldsymbol{X})$, where $A = 1, \ldots, n_{\text{nel}}$ runs over the number of nodes in the element, we construct the displacement field $\boldsymbol{u}$ and weighting function, $\boldsymbol{w}$, defined within each element (subscripts/superscripts denoting elements are suppressed),

$$\boldsymbol{u}(\boldsymbol{X}) = \sum_{A=1}^{n_{\text{nel}}} N^A(\boldsymbol{X})\boldsymbol{d}_A; \qquad \boldsymbol{w}(\boldsymbol{X}) = \sum_{A=1}^{n_{\text{nel}}} N^A(\boldsymbol{X})\boldsymbol{c}_A, \tag{5}$$

where, as is well-known in finite element methods, $\boldsymbol{c}_A$ are arbitrary nodal weighting function values. For an element node A located at $\boldsymbol{X}_i$, we have $\boldsymbol{d}_A = \boldsymbol{d}_i$. The element deformation gradient tensor $\boldsymbol{F}$, the kinematic quantities $J, \overline{\boldsymbol{C}}, \bar{I}_1, \bar{I}_2$ and $\bar{I}_a$ can all be computed from the data using the finite element interpolations in Equation (5).

Using Equation (5) in Equation (4) we arrive at the Galerkin weak form in terms of the stress operators, now written as $\boldsymbol{P}_0^{\text{d}}$–$\boldsymbol{P}_5^{\text{d}}$ with subscripts $(\bullet)^{\text{d}}$ emphasizing that the stress is computed from the known *data*.

$$\underset{e}{\boldsymbol{A}} \left[\int_{\Omega_e} \sum_A \nabla N^A \boldsymbol{c}^A : \left(\kappa \boldsymbol{P}_0^{\text{d}} + \mu \boldsymbol{P}_{\text{s}}^{\text{d}} + \theta_1 \boldsymbol{P}_1^{\text{d}} \cdots + \theta_5 \boldsymbol{P}_5^{\text{d}} \right) \mathrm{d}V - \int_{\Gamma_{T_e}} \sum_A N^A \boldsymbol{c}^A \boldsymbol{T} \mathrm{d}S \right] = \boldsymbol{0} \tag{6}$$

where $\underset{e}{\boldsymbol{A}}$ is the finite element assembly operator over elements.

Following the standard procedure in finite element computations, Equation (6) leads to the residual vector after accounting for the arbitrariness of weighting function degrees of freedom:

$$\boldsymbol{R}\left(\kappa, \mu, \boldsymbol{\theta}; \boldsymbol{P}_0^{\text{d}}(\boldsymbol{d}_i), \ldots, \boldsymbol{P}_5^{\text{d}}(\boldsymbol{d}_i)\right)_{i=1,\ldots N} = \boldsymbol{0}. \tag{7}$$

The above notation indicates that $\boldsymbol{R}$ has a *functional dependence* on κ, μ, and the additional coefficients $\boldsymbol{\theta} = \{\theta_1, \ldots \theta_5\}$. Also note that since the stress is *parameterized* by the data $\boldsymbol{d}_i$ via the operators $\boldsymbol{P}_0^{\text{d}}, \ldots \boldsymbol{P}_5^{\text{d}}$, we have chosen to highlight this dependence directly, rather than through the deformation gradient and other kinematic quantities as in Equation (3). The residual vector is assembled from the element contributions and is defined here as

$$\boldsymbol{R} = - \underset{e}{\boldsymbol{A}} \left[\int_{\Omega_e} \nabla \boldsymbol{N} \cdot \left(\kappa \boldsymbol{P}_0^{\text{d}} + \mu \boldsymbol{P}_{\text{s}}^{\text{d}} + \theta_1 \boldsymbol{P}_1^{\text{d}} \cdots + \theta_5 \boldsymbol{P}_5^{\text{d}} \right) \mathrm{d}V - \int_{\Gamma_{T_e}} \boldsymbol{N} \otimes \boldsymbol{T} \mathrm{d}S \right] \tag{8}$$

where $\boldsymbol{N} = \{N^1, \ldots, N^{n_{\text{nel}}}\}$ is the vector of interpolation functions in an element.

3.1 Basis operators

VSI associates deformation mechanisms with basis operators that are written in weak form. The known boundary traction term serves as the label:

$$\boldsymbol{y} = \underset{e}{\boldsymbol{A}} \int_{\Gamma_{T_e}} \boldsymbol{N} \otimes \boldsymbol{T} \mathrm{d}S \tag{9}$$

The Piola-Kirchhoff stress contributions arising from the various terms in the strain energy density lead to operators that we express in the general form:

$$\boldsymbol{\Xi}_\alpha = \underset{e}{\boldsymbol{A}} \int_{\Omega_e} \nabla \boldsymbol{N} \cdot \boldsymbol{P}_\alpha^{\text{d}} \mathrm{d}V, \quad \alpha = 0, \text{s}, 1, \ldots, 5 \tag{10}$$

The residual then follows from Equations (9) and (10) as

$$\boldsymbol{R}(\kappa,\mu,\boldsymbol{\theta}) = \boldsymbol{y} - \begin{bmatrix} \boldsymbol{\Xi}_0 & \boldsymbol{\Xi}_{\mathrm{s}} & \boldsymbol{\Xi}_1 & \boldsymbol{\Xi}_2 & \boldsymbol{\Xi}_3 & \boldsymbol{\Xi}_4 & \boldsymbol{\Xi}_5 \end{bmatrix} \begin{Bmatrix} \kappa \\ \mu \\ \theta_1 \\ \theta_2 \\ \theta_3 \\ \theta_4 \\ \theta_5 \end{Bmatrix} \tag{11}$$

We write $\boldsymbol{\theta} = \{\theta_1,\ldots,\theta_5\}^{\mathrm{T}}$, but in the interest of transparency, we continue to delineate the bulk and shear moduli, κ and μ in what follows. We also use $\boldsymbol{\Xi} = [\boldsymbol{\Xi}_0\,\boldsymbol{\Xi}_{\mathrm{s}}\,\boldsymbol{\Xi}_1\,\boldsymbol{\Xi}_2\,\boldsymbol{\Xi}_3\,\boldsymbol{\Xi}_4\,\boldsymbol{\Xi}_5]$.

VSI enables physics discovery by eliminating some and accepting other deformation mechanisms, and thus reducing the coefficients $\kappa,\mu,\boldsymbol{\theta}$ to a minimal set of non-zero values. A loss function is defined as

$$\ell(\kappa,\mu,\boldsymbol{\theta}) = |\boldsymbol{R}(\kappa,\mu,\boldsymbol{\theta})|^2 \tag{12}$$

Ridge regression is applied with regularization of the coefficients via a penalty term to prevent overfitting

$$\{\kappa,\mu,\boldsymbol{\theta}\} = \arg\min_{\widetilde{\kappa},\widetilde{\mu},\widetilde{\boldsymbol{\theta}}} \ell(\widetilde{\kappa},\widetilde{\mu},\widetilde{\boldsymbol{\theta}}) + \frac{1}{2}\lambda\left(\kappa^2 + \mu^2 + |\boldsymbol{\theta}|^2\right) \tag{13}$$

where λ is the penalty coefficient. This step yields

$$\begin{Bmatrix} \kappa \\ \mu \\ \boldsymbol{\theta} \end{Bmatrix} = \left(\boldsymbol{\Xi}^{\mathrm{T}}\boldsymbol{\Xi} + \lambda\mathbf{1}\right)^{-1}\boldsymbol{\Xi}^{\mathrm{T}}\boldsymbol{y} \tag{14}$$

3.2 Stepwise regression

An iterative procedure is followed to identify and eliminate inactive deformation mechanisms by setting their coefficients to vanish in the set $\{\kappa,\mu,\boldsymbol{\theta}\}$. The corresponding algorithm for standard regression uses the statistical F-test, which evaluates the significance of the increase in loss $\ell(\kappa,\mu,\boldsymbol{\theta})$ relative to the gain in efficiency of representation [35]. This approach is formally equivalent to using sparsity-inducing norms on the loss function, such as the L^1-norm coupled with cross-validation or LASSO (least average shrinkage and selection operator). However, we have found step-wise regression to perform better, and the use of the other methods to need insightful choices of priors for the coefficients $(\kappa,\mu,\boldsymbol{\theta})$. We use backward model selection by stepwise regression [19], which, as we have demonstrated previously, delivers parsimonious results with VSI [35, 34]. The algorithm is summarized below.

Algorithm 1: Stepwise regression with the F-test:

```
Step 0:
    Establish label vector y and matrix of bases Ξ⁰.
    i = 0
```

Step 1: %Stepwise regression
    Solve $\{\kappa,\mu,\boldsymbol{\theta}\}^i$ by ridge regression, Equation (14), or from Step 2.
    Calculate the loss function, ℓ^i, at this iteration or use $\ell^i = \ell^i_{\tilde{\beta}}$ from Step 2.

Step 2: %Find the least significant basis by the F-test
    Define $\boldsymbol{\Xi}^{i+1,\beta}$: set to zero the column of $\boldsymbol{\Xi}^i$ corresponding to coeff $\beta \neq 0$, $\beta \in \{\kappa,\mu,\boldsymbol{\theta}\}^i$
    Perform ridge regression with $\boldsymbol{\Xi} = \boldsymbol{\Xi}^{i+1,\beta}$ in Equation (14). Calculate loss ℓ^{i+1}_{β}
    Evaluate F-value on reduced operator matrix $\boldsymbol{\Xi}^{i+1,\beta}$ with $\beta = \arg\min_{\tilde{\beta}} \ell^{i+1}_{\tilde{\beta}}$.

Step 3: %Stepwise regression
    IF $F < \alpha$ %α is a tolerance
    THEN define $\boldsymbol{\Xi}^{i+1} = \boldsymbol{\Xi}^{i+1,\beta}$.
        define $\{\kappa,\mu,\boldsymbol{\theta}\}^{i+1} = \{\kappa,\mu,\boldsymbol{\theta}\}^i$ with $\beta \in \{\kappa,\mu,\boldsymbol{\theta}\}^i$ s.t. $\beta = 0$
     GOTO Step 1.
    ELSE Exit % Beyond this, ℓ increases dramatically for further elimination of operators.

There are several choices for the criterion for eliminating deformation mechanisms via the operators in $\boldsymbol{\Xi}$. Here, we adopt a widely used statistical criterion called the F-test, also used by us previously [35, 34]. The significance of the change between the model at iterations $i + 1$ and i is evaluated by:

$$F = \frac{\frac{\ell^{i+1} - \ell^i}{p^i - p^{i+1}}}{\frac{\ell^i}{m - p^i}} \tag{15}$$

where p^i is the number of operators at iteration i and $m = 7$ is the total number of operators. The F test normalizes the increase in loss function by the gain in efficiency of representation (decreasing model complexity). If F exceeds a pre-defined tolerance, α (Step 3 in Algorithm 1), stepwise regression terminates without further elimination of operators.

The penalty coefficient in ridge regression, λ, is chosen to lie in the range $[1, 10]$ by leave-one-out cross-validation at each iteration. We illustrate Algorithm 1 for stepwise regression algorithm with the F-test in Figure 2.

Figure 2: Schematic of Algorithm 1 for stepwise regression with the F-test.

Some remarks are relevant on the use of the weak form in VSI: As is well-known, the weak form transfers spatial derivatives from the differential operators acting on the data to the weighting function in Equation (4). Combined with the use of smooth basis functions (such as splines) in Equation (5), this contributes to the robustness of VSI when confronted by noisy data [35, 34], relative to other related techniques that use the partial differential equation in strong form [8, 30, 10]. As we have shown in Ref. [35], VSI also is able to identify boundary conditions on the data, which the other techniques cannot.

3.3   Staggered VSI with physically based operator suppression

Noise in the the MR-$\boldsymbol{u}$ data can mask physically meaningful constraints, such as near-incompressibility of the response ($J \sim 1$). We have developed a staggered approach to discovering the deformation mechanisms in order to circumvent this difficulty: In a first step we exclude the volumetric term from the mechanisms in Equation (2), effectively assuming $J = 1$. With the traction loading term as the label, we collect into $\boldsymbol{y}^{\text{surf}}$ only those elements of the residual vector that correspond to boundary degrees of freedom, noting that $\text{DIM}[\boldsymbol{y}^{\text{surf}}] < \text{DIM}[\boldsymbol{R}]$. We gather the rows of $\boldsymbol{\Xi}_{\text{s}}, \boldsymbol{\Xi}_1, \ldots, \boldsymbol{\Xi}_5$ that correspond to boundary degrees of freedom into $\boldsymbol{\Xi}^{\text{surf}}$ and the others in its complement $\boldsymbol{\Xi}^{\text{in}}$, and similarly partition $\boldsymbol{R}$ into $\boldsymbol{R}^{\text{surf}}$ and $\boldsymbol{R}^{\text{in}}$ to rewrite Equation (11) as

$$\begin{bmatrix} \boldsymbol{R}^{\text{surf}} \\ \boldsymbol{R}^{\text{in}} \end{bmatrix} = \begin{bmatrix} \boldsymbol{y}^{\text{surf}} \\ \boldsymbol{0} \end{bmatrix} - \begin{bmatrix} \boldsymbol{\Xi}^{surf} \\ \boldsymbol{\Xi}^{\text{in}} \end{bmatrix} \left\{ \begin{array}{c} \kappa \\ \mu \\ \boldsymbol{\theta} \end{array} \right\} \tag{16}$$

For the reduced vector of coefficients with $\langle 0, \mu, \boldsymbol{\theta} \rangle^{\text{T}}$, we first carry out VSI via Algorithm 1 with the residual

$\boldsymbol{R}^{\mathrm{surf}}$ given by

$$\boldsymbol{R}^{\mathrm{surf}} = \boldsymbol{y}^{\mathrm{surf}} - \boldsymbol{\Xi}^{\mathrm{surf}} \left\{ \begin{array}{c} 0 \\ \widetilde{\mu} \\ \widetilde{\boldsymbol{\theta}} \end{array} \right\} \tag{17}$$

instead of $\boldsymbol{R}$. In this step we detect the active operator set consisting of $\boldsymbol{\Xi}^{\mathrm{surf}}$, paired with predictor coefficient values $\{0, \widetilde{\mu}, \widetilde{\boldsymbol{\theta}}\}$. The volumetric operator is excluded at this step since the corresponding coefficient is set to zero.

We next reintroduce the volumetric operator with coefficient $\widetilde{\kappa}$ to the interior part of the residual, which is then reduced to:

$$\boldsymbol{R}^{\mathrm{in}} = - \left(\widetilde{\kappa} \boldsymbol{\Xi}_0^{\mathrm{in}} + \widetilde{\mu} \boldsymbol{\Xi}_{\mathrm{s}}^{\mathrm{in}} + \widetilde{\theta}_1 \boldsymbol{\Xi}_1^{\mathrm{in}} + \ldots \widetilde{\theta}_5 \boldsymbol{\Xi}_5^{\mathrm{in}} \right) \tag{18}$$

Holding $\widetilde{\mu}$ and $\widetilde{\boldsymbol{\theta}}$ fixed, and using ridge regression, we find a predictor for $\widetilde{\kappa}$. At this stage of the staggered VSI algorithm, we note that with the predictor coefficient set $\{\widetilde{\kappa}, \widetilde{\mu}, \widetilde{\boldsymbol{\theta}}\}$ the surface residual $\boldsymbol{R}^{\mathrm{surf}} = \boldsymbol{y}^{\mathrm{surf}} - \boldsymbol{\Xi}^{\mathrm{surf}} \langle \widetilde{\kappa}, \widetilde{\mu}, \widetilde{\boldsymbol{\theta}} \rangle^{\mathrm{T}}$ yields a value for $|\boldsymbol{R}^{\mathrm{surf}}|$ that exceeds the value attained by stepwise regression with $\boldsymbol{R}^{\mathrm{surf}}$ defined in Equation (17). We therefore consider a linear scaling, $(\gamma \widetilde{\kappa}, \gamma \widetilde{\mu}, \gamma \widetilde{\boldsymbol{\theta}})$, thus similarly scaling $|\boldsymbol{R}^{\mathrm{in}}|$ as defined by Equation (18), but not affecting its minimizer. However, it allows us to find a new minimum for $|\boldsymbol{R}^{\mathrm{surf}}|$ in the full coefficient space. Returning to the upper row block form of Equation (16), we impose $\{\kappa, \mu, \boldsymbol{\theta}\} = \gamma \{\widetilde{\kappa}, \widetilde{\mu}, \widetilde{\boldsymbol{\theta}}\}$ in

$$\boldsymbol{R}^{\mathrm{surf}} = \boldsymbol{y}^{\mathrm{surf}} - \boldsymbol{\Xi}^{\mathrm{surf}} \left\{ \begin{array}{c} \kappa \\ \mu \\ \boldsymbol{\theta} \end{array} \right\} \tag{19}$$

to find γ that thus defines a constrained minimizer $\{\kappa, \mu, \boldsymbol{\theta}\}$ of $|\boldsymbol{R}^{\mathrm{surf}}|$ by Algorithm 1. We thus attain minima of $|\boldsymbol{R}^{\mathrm{surf}}|$ and $|\boldsymbol{R}^{\mathrm{in}}|$, and because of the quadratic dependence on $(\kappa, \mu, \boldsymbol{\theta})$, of $|\boldsymbol{R}|$ as well. This staggered approach to stepwise regression leads to robust VSI in the incompressible limit even with noisy data.

3.3.1 Operator suppression

The available data may be restricted to a regime in which some of the operators arising from the deformation mechanisms in Equation (2) display near-linear dependence. The inferred set $\{\kappa, \mu, \boldsymbol{\theta}\}$ can then harbor non-physical results such as a negative bulk modulus, κ, or a vanishing shear modulus, μ. Recognizing $\kappa, \mu \leq 0$ as a loss of pointwise mechanical stability, this suggests an approach in which only one of the operators with linear dependence be admitted while suppressing the others in implementing the above staggered VSI. This represents the generally applicable principle of stability as a physics constraint incorporated within the inference techniques that constitute VSI. We have previously used the distinction between steady state and transient regimes of problems with first-order dynamics as a principle to strengthen VSI inference [34], and the stability-based criterion is in a similar spirit. We list the algorithm below:

```
Algorithm 2: Staggered VSI with operator suppression:

Step 1:  Staggering
    Identify the active operator set paired with predictor coefficient values {0, μ̃, θ̃} by
Algorithm 1, with residual R^surf, where:
```

$$\boldsymbol{R}^{\mathrm{surf}} = \boldsymbol{y}^{\mathrm{surf}} - \boldsymbol{\Xi}^{\mathrm{surf}} \left\{ \begin{array}{c} 0 \\ \widetilde{\mu} \\ \widetilde{\boldsymbol{\theta}} \end{array} \right\}$$

```
Step 2:  Staggering
    Infer the predictor for κ̃ by regression to minimize |R^in| where:
```

$$\boldsymbol{R}^{\mathrm{in}} = - \left(\widetilde{\kappa} \boldsymbol{\Xi}^{\mathrm{in}}_0 + \widetilde{\mu} \boldsymbol{\Xi}^{\mathrm{in}}_{\mathrm{s}} + \widetilde{\theta}_1 \boldsymbol{\Xi}^{\mathrm{in}}_1 + \ldots \widetilde{\theta}_5 \boldsymbol{\Xi}^{\mathrm{in}}_5 \right)$$

```
Step 3:  Staggering
    Infer the constant scalar γ by regression to minimize |R^surf| where:
```

$$\boldsymbol{R}^{\mathrm{surf}} = \boldsymbol{y}^{\mathrm{surf}} - \gamma \boldsymbol{\Xi}^{\mathrm{surf}} \left\{ \begin{array}{c} \widetilde{\kappa} \\ \widetilde{\mu} \\ \widetilde{\boldsymbol{\theta}} \end{array} \right\}$$

```
Step 4:  Operator suppression
    IF {κ, μ, θ} = γ{κ̃, μ̃, θ̃} are nonphysical %i.e., ≤ 0
    THEN set β = 0 for β ∈ {κ, μ, θ}
      GOTO Step 1
```

3.4   PDE-constrained minimization following VSI

After the deformation mechanisms are identified by Algorithm 1, with Algorithm 2 applied as needed, the preliminary, predicted values of coefficients corresponding to the identified operators can be further refined by minimizing the error on $\boldsymbol{u}$ subject to the identified physics:

$$\{\kappa, \mu, \boldsymbol{\theta}\} = \arg \min_{\widehat{\kappa}, \widehat{\mu}, \widehat{\boldsymbol{\theta}}} \left\{ \sum_{k=1}^{N} \int_{\Omega} (\boldsymbol{u}_k^{\mathrm{FE}} - \boldsymbol{u}_k)^2 \mathrm{d}v + \frac{1}{2} \chi \left(\widehat{\kappa}^2 + \widehat{\mu}^2 + |\widehat{\boldsymbol{\theta}}|^2 \right) \right\} \tag{20}$$

$$\text{subject to: } \boldsymbol{R} = \boldsymbol{0} \tag{21}$$

where N is the total number of loading cases, $\boldsymbol{u}_k^{\mathrm{FE}}$ is the displacement field from the forward finite element solution obtained with the current values of coefficients $\{\widehat{\kappa}, \widehat{\mu}, \widehat{\boldsymbol{\theta}}\}$ for the kth loading, $\boldsymbol{u}_k$ is the corresponding MR-$\boldsymbol{u}$ data and χ is a penalty coefficient for regularization. Such PDE-constrained optimization needs the gradient of the corresponding loss function $\ell_i := \sum_{i}^{N} \int_{\Omega} (\boldsymbol{u}^{\mathrm{FE}} - \boldsymbol{u})^2 \mathrm{d}v + \frac{1}{2} \chi \left(\widehat{\kappa}^2 + \widehat{\mu}^2 + |\widehat{\boldsymbol{\theta}}|^2 \right)$ with respect to the parameters $\{\kappa, \mu, \boldsymbol{\theta}\}$. One approach to approximating the gradient is by finite differences, which requires a large number of solutions of the PDE constraint to construct numerical derivatives. Here, we adopt the adjoint method to evaluate the gradient, which requires a single solve of the (linear) adjoint equation of the original PDE constraint and a nonlinear solution for the parameter set $\{\widehat{\kappa}, \widehat{\mu}, \widehat{\boldsymbol{\theta}}\}$.

Since this is a standard implementation of adjoint-based gradient optimization with PDE constraints, we do not elaborate on it any further. In this work we use the L-BFGS-B optimization algorithm from the `SciPy` package [33] and the `dolfin-adjoint` software library [23] to solve the PDE-constrained minimization.

4   Results

4.1   Synthetic data

We first applied VSI to synthetic data generated from forward computations of tensile loading on rectangular prismatic blocks ($42 \times 6 \times 6$ mm^3). These simulations had fully constrained displacement boundary conditions

Table 1: VSI results for synthetic data allowing all deformation mechanisms in (2)

Data origin	Identified strain energy density function (kPa)	ν
True model	$W = 4000(J-1)^2 + 40(\bar{I}_1 - 3)$	0.495
Noise-free data	$W = 4000.0(J-1)^2 + 40.0(\bar{I}_1 - 3)$	0.495
$\sigma = 1.0 \times 10^{-3}$ mm	$W = 3996.6(J-1)^2 + 18.57(\bar{I}_a - 1)$	nonphys.
$\sigma = 1.0 \times 10^{-2}$ mm	$W = 2288.8(J-1)^2 + 22.8(\bar{I}_a - 1)$	nonphys.
True model	$W = 40000(J-1)^2 + 40(\bar{I}_1 - 3)$	0.4995
Noise-free data	$W = 40000.0(J-1)^2 + 40.0(\bar{I}_1 - 3)$	0.4995
$\sigma = 1.0 \times 10^{-3}$ mm	$W = 27556.2(J-1)^2 + 20(\bar{I}_a - 1)$	nonphys.
$\sigma = 1.0 \times 10^{-2}$ mm	$W = 537.2(J-1)^2 + 26.5(\bar{I}_a - 1)$	nonphys.

Table 2: VSI results for synthetic data by suppression of anisotropic terms.

Model	Identified strain energy density function (kPa)	ν
True model	$W = 4000(J-1)^2 + 40(\bar{I}_1 - 3)$	0.495
Noise-free data	$W = 4000.0(J-1)^2 + 40.0(\bar{I}_1 - 3)$	0.495
$\sigma = 1.0 \times 10^{-3}$ mm	$W = 4052.1(J-1)^2 + 40.4(\bar{I}_1 - 3)$	0.495
$\sigma = 1.0 \times 10^{-2}$ mm	$W = 2344.3(J-1)^2 + 49.3(\bar{I}_1 - 3)$	0.49
True model	$W = 40000(J-1)^2 + 40(\bar{I}_1 - 3)$	0.4995
Noise-free data	$W = 40000.0(J-1)^2 + 40.0(\bar{I}_1 - 3)$	0.4995
$\sigma = 1.0 \times 10^{-3}$ mm	$W = 25912.5(J-1)^2 + 46.86(\bar{I}_1 - 3)$	0.4991
$\sigma = 1.0 \times 10^{-2}$ mm	$W = 446.9(J-1)^2 + 58.7(\bar{I}_1 - 3)$	0.437

on one face and traction loading on the opposite face in order to create three-dimensional states of deformation. The traction was increased in nine steps of: 0.16, 0.30, 0.58, 0.84, 1.09, 1.21, 1.32, 1.54, 1.74 N. We used the neo-Hookean strain energy density function, Equation (1), with true values of the coefficients appearing in Table 1. Note that that with these coefficient ranges the neo-Hookean model represents a spectrum of soft biological tissue and polymers. Also included is the Poisson ratio that would be computed for the linear regime of infinitesimal strain with this model. As this initial Poisson ratio increases from $\nu = 0.495$ to $\nu = 0.4995$, the response tends toward near incompressibility.

We were able to re-identify the correct mechanisms of volumetric, isochoric, and isotropic deformation from a larger library of candidate operators appearing in Equation (2). As shown in Table 1, for noise-free synthetic data, the nearly incompressible, isotropic response was correctly identified, and coefficients were obtained with high accuracy even without the final stage of PDE-constrained optimization. Figure 3 illustrates the functioning of Algorithms 1 and 2 of VSI via a stem and leaf plot and the iterate-wise loss curve for the noise-free synthetic data. Step 1 of staggering (Algorithm 2) is shown, for which reason only the updated values of $\mu, \theta_1 \ldots \theta_5$, are shown at each iteration. On the right in Figure 3, the plot shows the iterate-wise loss remaining low until a single mechanism, corresponding to the shear coefficient μ, remains. Steps 2 and 3 of Algorithm 2 provide the final values for κ. Since this instance of VSI corresponds to the noise-free synthetic data in Table 1, Step 4 of Algorithm 2 was not activated. The true values $\kappa = 4000$ kPa, $\mu = 40$ kPa, and $\theta_1, \ldots, \theta_5 = 0$ were identified without PDE-constrained optimization. Noise was then added to the displacement solution with magnitude drawn from a Gaussian distribution with zero mean and standard deviations $\sigma = 10^{-3}$ mm and $\sigma = 10^{-2}$ mm. This is to be compared against a maximum displacement over the domain of ~ 9 mm. Incorrect mechanisms are identified, as reflected by a vanishing shear modulus corresponding to a loss of material stability and a nonphysical model. This is because the two orthotropic terms, corresponding to $(\bar{I}_a - 1)$ and $(\bar{I}_a - 1)^2$ components in the candidate free energy density function (Equation 2), display near linear dependence with the shear term as shown in Figure 4. However, using Algorithm 2 for staggering and suppression of the anisotropic operators, VSI was successful in identifying a physically meaningful set of deformation mechanisms even in the incompressible limit with noise, although the loss in accuracy of coefficients increases with the approach to incompressibility and higher noise.

(PDE-constrained optimization was not used.) See Table 2.

Figure 3: Left: Stem and leaf plot demonstrating step-wise regression via Algorithms 1 and 2 in staggered VSI: The coefficients $\mu, \theta_1, \ldots, \theta_5$ corresponding to the non-volumetric terms in Equation (2). VSI sets coefficient θ_3 to zero in Iteration 2, and the algorithm proceeds until θ_4 is set to zero in Iteration 6. Right: the loss corresponding to each iteration of step-wise regression.

Figure 4: The two orthotropic terms, corresponding to $(\overline{I}_a - 1)$ and $(\overline{I}_a - 1)^2$ in the candidate free energy density function display near linear dependence on, and even proportionality with, the basis term corresponding to the $\overline{I}_1 - 3$ component.

4.2 MR-u data from uniaxial loading on a soft elastomer

We next applied VSI to MR-u data obtained from uniaxial loading on a soft elastomer as a surrogate for biological tissue. A rectangular prismatic block ($41.5 \times 8 \times 7.5$ mm^3) of a commercially available elastomer (Dragon Skin, Smooth-On Inc., Macungie, PA) was subject to fully constrained displacement boundary conditions on one face and tensile traction loading on the opposite face, as in the computation used to generate synthetic data (Section 4.1). The reference configuration and reconstructed deformed configuration for the first and ninth load increments (of nine) appear in Figure 5. The MR-u data were obtained over a field of size $95 \times 13 \times 13$ voxels.

The increments applied were the same as for generating the synthetic data: 0.16, 0.30, 0.58, 0.84, 1.09, 1.21, 1.32, 1.54, 1.74 N, yielding maximum displacements: 0.55, 1.09, 2.14, 3.25, 4.31, 4.89, 5.43, 6.46, 7.57 mm, respectively. Field data were obtained for the displacement and for the deformation gradient tensor using the MR-u technique and smoothed by Hamming filters (which are typical in MR image processing) with different kernel sizes. As an alternate approach to smoothing, we fit the displacement data to polynomials and obtained a global quadratic field. The MR-u data as displacements and deformation gradient tensors and subject to these

Figure 5: Reconstructed deformation from data on a soft elastomer showing the reference (left), first deformed (middle), and ninth deformed (right) configurations. VSI discovers deformation mechanisms from these data.

Table 3: VSI results for the rectangular prism-shaped soft elastomer without suppression of any of the deformation mechanisms in Equation (2).

Filter and field for $(\boldsymbol{u}^{\mathrm{d}}/\boldsymbol{F}^{\mathrm{d}})$	Identified strain energy function (kPa)
No filter: $\boldsymbol{u}^{\mathrm{d}}$	$W = -84.76(J-1)^2 + 89.3(\bar{I}_a - 1)^2$
No filter: $\boldsymbol{F}^{\mathrm{d}}$	$W = 309.6(J-1)^2 + 58.5(\bar{I}_a - 1)^2$
Hamming filter: 1^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = -56.9(J-1)^2 + 97.4(\bar{I}_a - 1)^2$
Hamming filter: 1^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 407.96(J-1)^2 + 42.2(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 457.8(J-1)^2 + 92.9(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 436.1(J-1)^2 + 38.4(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 340(J-1)^2 + 113.7(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 579.2(J-1)^2 + 23(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 139.9(J-1)^2 + 88.3(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 770.6(J-1)^2 + 46.1(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 52.7(J-1)^2 + 83.3(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 715(J-1)^2 + 17.3(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 49.4(J-1)^2 + 82.3(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 758.6(J-1)^2 + 17.1(\bar{I}_a - 1)^2$
Quadratic polynomial smoothing on $\boldsymbol{u}^{\mathrm{d}}$	$W = 355.6(J-1)^2 + 33.6(\bar{I}_1 - 3)$

different smoothing techniques was then used for VSI. Because of the noise that remained even after smoothing, staggering and operator suppression (Algorithm 2) were used.

We first consider the strain energy density function including all the deformation mechanisms in Equation (2). For the unsmoothed MR-$\boldsymbol{u}$ data, or if smoothed by Hamming filters, the staggered VSI approach identifies the single orthotropic term of the form $(\bar{I}_a - 1)^2$ as the sole non-volumetric deformation mechanism. However, this manifests in nonphysical results via either (a) a negative bulk modulus or (b) in a vanishing shear modulus, because the $\bar{I}_1 - 3$, $\bar{I}_2 - 3$, $(\bar{I}_1 - 3)^2$ and $(\bar{I}_2 - 3)^2$ terms are eliminated. Both situations imply a mechanically unstable material. These results are summarized in Table 3. However, the direct use of polynomial smoothing does not display this pathology, and identifies physically admissible mechanisms of volumetric and shear deformation. For the data subject to Hamming filters, we therefore reran Algorithms 1 and 2 with suppression of the orthotropic mechanism as described in Section 3.3.1. The corresponding results appear in Table 4. For displacement data without filtering, and with the Hamming filter of width 1^3, the final results remain nonphysical, with a negative bulk modulus even using operator suppression. However, we get physically meaningful results using the remaining kernels and with polynomial smoothing on $\boldsymbol{u}^{\mathrm{d}}$, as well as for all Hamming filters with $\boldsymbol{F}^{\mathrm{d}}$.

Following discovery of the deformation mechanisms by VSI, the coefficient values, specifically the bulk and shear moduli κ and μ, were further refined by PDE-constrained minimization with adjoints as described in Section 3.4. This leads to a lower shear modulus and a notably higher bulk modulus–see Table 5. VSI combined with PDE-constrained minimization thus confirms that the material is indeed nearly incompressible. For the values of κ and μ corresponding to the Hamming filters with kernel size $\leq 4^3$ voxels, and the second-order polynomial smoothing in Table 5, the Poisson's ratios range from $\nu = 0.492$ to $\nu = 0.4926$. However, with wider Hamming filters, a more compressible response is inferred; the Poisson ratios decline to 0.491 and 0.4881 for the

Table 4: VSI results for the rectangular prism-shaped soft elastomer with operator suppression. The identified strain energy density function has volumetric and isochoric terms of the form $W = \frac{1}{2}\kappa(J - 1)^2 + \frac{1}{2}\mu(\bar{I}_1 - 3)$

Hamming Filter and field ($\boldsymbol{u}^\mathrm{d}/\boldsymbol{F}^\mathrm{d}$)	Identified strain energy function (kPa)	Suppressed term
No filter: $\boldsymbol{u}^\mathrm{d}$	-	All
No filter: $\boldsymbol{F}^\mathrm{d}$	$W = 249(J - 1)^2 + 101.3(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 1^3 voxel on $\boldsymbol{u}^\mathrm{d}$	-	All
Hamming filter: 1^3 voxel on $\boldsymbol{F}^\mathrm{d}$	$W = 369(J - 1)^2 + 72.8(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{u}^\mathrm{d}$	$W = 313.7(J - 1)^2 + 148.3(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{F}^\mathrm{d}$	$W = 472(J - 1)^2 + 53(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{u}^\mathrm{d}$	$W = 190.4(J - 1)^2 + 165.1(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{F}^\mathrm{d}$	$W = 554.3(J - 1)^2 + 39(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{u}^\mathrm{d}$	$W = 76.8(J - 1)^2 + 135(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{F}^\mathrm{d}$	$W = 639.6(J - 1)^2 + 31.8(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{u}^\mathrm{d}$	$W = 7.8(J - 1)^2 + 133(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{F}^\mathrm{d}$	$W = 690.6(J - 1)^2 + 29.6(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{u}^\mathrm{d}$	$W = 14.8(J - 1)^2 + 135(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{F}^\mathrm{d}$	$W = 734(J - 1)^2 + 29.3(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Quadratic polynomial smoothing on $\boldsymbol{u}^\mathrm{d}$	$W = 355.6(J - 1)^2 + 33.6(\bar{I}_1 - 3)$	None

8^3 and 12^3 Hamming filters. We then computed the volume-averaged L^2-error defined as

$$\|\boldsymbol{u} - \boldsymbol{u}^\mathrm{d}\|_2 = \sqrt{\frac{1}{V}\int_\Omega |\boldsymbol{u} - \boldsymbol{u}^\mathrm{d}|^2 \mathrm{d}v} \tag{22}$$

for each load step. As the applied loads increase, higher maximum displacements are obtained in the MR-$\boldsymbol{u}$ data. The corresponding volume-averaged L^2-error after VSI and PDE-constrained optimization also grows with applied load; however its ratio to the maximum displacement decreases. This is because the PDE-constrained minimization places greater weightage on the load steps with higher displacement, and therefore higher error, as it minimizes the overall loss. Furthermore, focusing on the final load step, we note that while the volume-averaged L^2-error is $\lesssim 1\%$ for Hamming filters with kernel size $\leq 4^3$ voxels, and for quadratic polynomial smoothing, it increases for wider Hamming filters. The volume-averaged L^2-errors corresponding to each load are summarized in Table 9 in the Appendix.

In order to arrive at confidence intervals on the inferred model parameters, we ran 300 steps of Markov Chain Monte Carlo (MCMC) sampling for varying κ and μ on a Cartesian grid in the neighborhood of their values reported in Table 5 for each data set with filtering or polynomial smoothing. For all data sets except the case with Hamming filter 16^3, we uniformly sampled $\kappa \in [500, 3000]$ kPa and $\mu \in [30, 33]$ kPa. For data with the Hamming filter of kernel size 16^3 voxels, we sampled $\kappa \in [30, 77]$ and $\mu \in [30, 49]$. These ranges were chosen to encompass suitable sampling intervals containing the corresponding values reported in Table 5. Figure 6, shows contours with the indicated ratios of volume-averaged L^2-error with respect to the minimum error attained on the innermost contour. As seen, the confidence intervals span a wider range of κ than of μ. Furthermore, while the confidence intervals are about the same for data sets with Hamming filters of kernel size $\leq 4^3$ voxels, they increase for larger Hamming filters and for quadratic polynomial smoothing. Also note that the upper bound of the confidence intervals for κ exceeds the sample range for Hamming filters with kernel size of 16^3 voxels.

4.3   MR-$\boldsymbol{u}$ data on an "S-shaped" soft elastomer

As the final study of inference in this communication, we applied VSI to MR-$\boldsymbol{u}$ data obtained for an "S-shaped" soft elastomer as a surrogate for irregularly shaped soft biological tissue. Tensile loading was applied on a commercially available elastomer (Dragon Skin, Smooth-On Inc., Macungie, PA) with fixed displacement boundary conditions on one face and tensile traction loading on the opposite face. The reference configuration, boundary conditions and reconstructed deformed configuration for the final load increment (of six) appear in

Table 5: Parameters corresponding to isotropic response with bulk and shear moduli κ and μ that are further refined by PDE-constrained minimization. The initial guesses are the results of VSI using the data with the corresponding filter on $\boldsymbol{F}^{\mathrm{d}}$, or with polynomial smoothing. The errors are reported for the ninth load step and should be compared with the maximum displacement of 7.57 mm. The details of the volume-averaged L^2-error for each load step are summarized in Table 9 in the Appendix.

Filter	κ (kPa)	μ (kPa)	Vol. ave. L_2-error(mm)
No filter: $\boldsymbol{F}^{\mathrm{d}}$	2032	30.2	<0.11
Hamming filter: 1^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	1923	30.2	<0.1
Hamming filter: 2^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	1953	30.2	<0.1
Hamming filter: 4^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	1945.6	30.3	<0.1
Hamming filter: 8^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	1674.2	30.4	<0.1
Hamming filter: 12^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	1281.8	30.6	<0.1
Hamming filter: 16^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	42.8	41.1	<0.1
Second-order polynomial smoothing on $\boldsymbol{u}^{\mathrm{d}}$	1895	30.3	<0.1

Figure 7. The increments applied were: 1.06, 1.58, 2.06, 2.99, 3.87, 4.70 N, yielding maximum displacements: 0.99, 1.48, 1.99, 3.02, 4.02, 5.06 mm, respectively. The displacement vector field and the deformation gradient tensor field were directly obtained from MR-$\boldsymbol{u}$, and Hamming filters were applied with different kernel sizes. Polynomial smoothing was also carried out on the displacement data, and were best fit by globally quintic forms. As previously, the operators in Equation (3) corresponding to deformation mechanisms in Equation (2) were constructed with the traction term as the label in Equation (9).

Following the approach used for the rectangular prismatic shape, we first included all the deformation mechanisms in Equation (2). In all cases the staggered VSI approach identified the single orthotropic term of the form $(\bar{I}_a - 1)^2$ as the sole non-volumetric deformation mechanism. However, this manifested in nonphysical results via either (a) a negative bulk modulus or (b) in a vanishing shear modulus, because the $\bar{I}_1 - 3$, $\bar{I}_2 - 3$, $(\bar{I}_1 - 3)^2$ and $(\bar{I}_2 - 3)^2$ terms were eliminated. Both situations imply a mechanically unstable material. These results are summarized in Table 6. We then applied Algorithms 1 and 2 with staggering and operator suppression of this orthotropic term based on linear dependence, as in Section 3.3.1. Use of unsmoothed displacement data or with the Hamming filter kernel size of 1^3 voxels still led to nonphysical final results with a negative bulk modulus even when operator suppression was used. But the use of field data on the deformation gradient tensor with the Hamming filter and quintic polynomial smoothing on the displacement data led to physically meaningful results (See Table 7).

Following discovery of deformation mechanisms by staggered VSI with operator suppression, the identified bulk and shear moduli κ and μ were further refined by PDE-constrained minimization with adjoints. This led to a lower shear modulus and a notably higher bulk modulus with the Poisson ratio $\nu \sim 0.49$–see Table 8. The volume-averaged L^2-error at the maximum applied load was nearly identical and $\lesssim 4\%$ of the maximum displacement across data sets that were subject to Hamming filters with kernel size $\leq 4^3$ voxels, and for quintic polynomial smoothing, suggesting acceptability of these different imaging filter sizes for data processing purposes. In contrast, the volume-averaged L^2-error increased with larger filter sizes, suggesting that overly aggressive data smoothing reduces displacement field agreement. The details of the volume-averaged L^2-errors corresponding to each load are summarized in Table 10 in the Appendix. VSI combined with PDE-constrained minimization thus confirms that the material is indeed nearly incompressible and delivers consistent results for Hamming filtered data on $\boldsymbol{F}^{\mathrm{d}}$, and polynomial smoothing of $\boldsymbol{u}^{\mathrm{d}}$.

We repeated the MCMC sampling techniques of Section 4.2 to generate confidence intervals. For Hamming filters with kernel size $\leq 4^3$ voxels and for polynomial smoothing, we sampled $\kappa \in [2000, 50000]$ kPa and $\mu \in]140, 169]$ kPa. The sampling was over $\kappa \in [100, 10000]$ kPa and $\mu \in]135, 235]$ kPa for Hamming filters with kernel size 12^3 voxels, and $\kappa \in [20, 10000]$ kPa and $\mu \in]100, 390]$ kPa for Hamming filters with kernel size 16^3 voxels. As in Section 4.2, these ranges were chosen based on the PDE-constrained optimization results reported in Table 8. The contours in Figure 8 are defined identically to Section 4.2: ratios of volume-averaged L^2-error relative to minimum error of the innermost contour. The confidence intervals are wider for κ than μ. For all data sets, the upper bounds of the confidence intervals over κ exceed the sampling range. Since the error remains the same over each contour for arbitrarily large κ this suggests that these values are already detecting near-incompressibility.

Table 6: VSI results for the "S-shaped" soft elastomer without suppression of any of the deformation mechanisms in (2).

Filter and field ($\boldsymbol{u}^{\mathrm{d}}/\boldsymbol{F}^{\mathrm{d}}$)	Identified strain energy function (kPa)
No filter: $\boldsymbol{u}^{\mathrm{d}}$	$W = -190(J-1)^2 + 152.4(\bar{I}_a - 1)^2$
No filter: $\boldsymbol{F}^{\mathrm{d}}$	$W = 1442.3(J-1)^2 + 130.9(\bar{I}_a - 1)^2$
Hamming filter: 1^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = -64.6(J-1)^2 + 158.3(\bar{I}_a - 1)^2$
Hamming filter: 1^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 1994.1(J-1)^2 + 125.3(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 446.9(J-1)^2 + 141.8(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 2472.3(J-1)^2 + 120.3(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 469(J-1)^2 + 141.5(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 3327.2(J-1)^2 + 106.2(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 417.6(J-1)^2 + 186.4(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 3288.3(J-1)^2 + 79(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 336.2(J-1)^2 + 232.1(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 3196.3(J-1)^2 + 74(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 289.7(J-1)^2 + 318.9(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 2524.2(J-1)^2 + 73.3(\bar{I}_a - 1)^2$
Fifth-order polynomial smoothing on $\boldsymbol{u}^{\mathrm{d}}$	$W = 475.6(J-1)^2 + 145.1(\bar{I}_a - 1)^2$

Table 7: VSI results for the "S-shaped" soft elastomer with operator suppression. The identified strain energy density function has volumetric and isochoric terms of the form $W = \frac{1}{2}\kappa(J-1)^2 + \frac{1}{2}\mu(\bar{I}_1 - 3)$

Filter and field ($\boldsymbol{u}^{\mathrm{d}}/\boldsymbol{F}^{\mathrm{d}}$)	Identified strain energy function (kPa)	Suppressed terms
No filter: $\boldsymbol{u}^{\mathrm{d}}$	-	All
No filter: $\boldsymbol{F}^{\mathrm{d}}$	$W = 1586.8(J-1)^2 + 206.3(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 1^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	-	All
Hamming filter: 1^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 2163.1(J-1)^2 + 195.2(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 275.8(J-1)^2 + 243.2(\bar{I}_2 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 2^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 2731.7(J-1)^2 + 184.6(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 329.1(J-1)^2 + 243.3(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 4^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 3514.8(J-1)^2 + 162.4(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 315.3(J-1)^2 + 305(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 8^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 3369.3(J-1)^2 + 121.3(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 201.2(J-1)^2 + 384.7(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 12^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 3285.7(J-1)^2 + 113.4(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Hamming filter: 16^3 voxel on $\boldsymbol{u}^{\mathrm{d}}$	$W = 138.3(J-1)^2 + 513.6(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2, (\bar{I}_a - 1)$
Hamming filter: 16^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	$W = 2512.4(J-1)^2 + 115.9(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$
Quintic polynomial smoothing on $\boldsymbol{u}^{\mathrm{d}}$	$W = 476.9(J-1)^2 + 233.5(\bar{I}_1 - 3)$	$(\bar{I}_a - 1)^2$

Figure 6: Contours of the ratio of volume averaged L^2-error with sampling over κ and μ for the rectangular specimen. The ratio of error corresponding to each contour with respect to the error for the innermost contour is reported. This ratio for the solid curves is $\frac{\text{error}_{\text{solid}}}{\text{error}_{\text{min}}} = 1.1$.

Figure 7: Reconstructed deformation from data on an "S-shaped" soft elastomer showing the reference (left), and final deformed (right) configurations.

5 Discussion

This work represents the first foray into solid mechanics of soft biological tissue and polymers using the framework of Variational System Identification, originally developed for inference of the physics of pattern formation in materials [35, 34, 1], and recently used to explore identification of the canonical equations of infectious disease modelling [36]. Guided by the modern treatment of soft tissue continuum mechanics at finite strain, we have based our development of VSI on hyperelasticity. We have approached constitutive modelling in the spirit of the discovery of deformation mechanisms from data. Accordingly, we have considered a range of deformation mechanisms in the strain energy density function. The premise of VSI is to then use data-driven methods of system inference to find an expressive, yet efficient representation that explains the physics as constrained by the data, and in so doing, to pinpoint the deformation mechanisms that the material admits. Recognizing the depth of existing insight to the mechanics of soft material (including our own work in this area), we have restricted ourselves to volumetric, isochoric, isotropic, and orthotropic mechanisms (Equation (2)) in this, our first communication on the problem. With the hyperelastic treatment, this directly leads to algebraic operators for the first Piola-Kirchhoff stress tensor, which features in the governing equation of stress equilibrium (balance of linear momentum). This governing partial differential equation is the form in which the considered mechanisms are then sorted and culled by VSI. Unlike our earlier work on the discovery of physics in pattern forming materials, the differential operators are not in question here.

An algorithm centered on stepwise regression and the application of the statistical F-test is at the heart of VSI. Here we also introduced the staggered VSI approach, guided by the recognition that noise could drown out physical constraints such as the near incompressibility in the signal. Another injection of physical insight was

Table 8: Bulk and shear moduli for the "S-shaped" elastomer further refined by PDE-constrained minimization with initial guesses taken from VSI results with the corresponding filter on $\boldsymbol{F}^{\mathrm{d}}$, or with polynomial smoothing. The errors are reported for the sixth load step and should be compared with the maximum displacement of 5.06 mm. The details of the volume-averaged L^2-error for each load step are summarized in Table 10 in the Appendix.

Filter	κ (kPa)	μ (kPa)	vol. ave. L_2-error (mm)
No filter: $\boldsymbol{F}^{\mathrm{d}}$	7612.7	149.3	<0.2
Hamming filter: 1^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	7604.1	149.3	<0.2
Hamming filter: 2^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	7592.2	149.2	<0.2
Hamming filter: 4^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	7725.8	148.9	<0.2
Hamming filter: 8^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	7718.4	149.3	<0.2
Hamming filter: 12^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	408.4	176.2	<0.3
Hamming filter: 16^3 voxel on $\boldsymbol{F}^{\mathrm{d}}$	121.58	256.6	<0.35
Fifth-order polynomial smoothing on $\boldsymbol{u}^{\mathrm{d}}$	7369.4	149.2	<0.2

introduced by first assuming perfect incompressibility to eliminate the volumetric term in a predictor step. This allows the robust discovery of the isochoric, isotropic (shear) mechanisms, following which the reintroduction of the volumetric mechanism as a candidate led to its discovery, as well. The staggered VSI approach is incorporated in Algorithm 2 and leverages the core Algorithms 1 of stepwise regression and the F-test.

The mechanics of soft biological tissue and polymeric materials presents challenges: some encountered previously and others novel. Noise in the data, which is nearly unavoidable in experiments, is the first of these challenges as seen in the results with synthetic data on which we superposed Gaussian noise (Table 1). As expected, the naïve application of VSI yields very accurate inference in the absence of noise but degrades to nonphysical results, indicated by the introduction of material instabilities with increasing noise. We did not scale the noise by the reported displacement; a step that would lead to greater discrepancies in the reported inference. Here, guided by the broadly applicable principle of stability we introduced operator suppression resulting in successful inference, albeit with some loss in fidelity in the nearly incompressible response expected (Table 2).

Taking this forward to real data on the tensile response of the rectangular prismatic elastomeric specimen as a surrogate for soft biological tissue, we used suppression of the orthotropic deformation mechanism, because it was found to survive stepwise regression but led to nonphysical results implying instability of the volumetric and shear responses. However, the combination of staggering and operator suppression via Algorithm 2 delivered physically meaningful inference of deformation mechanisms that parsimoniously identified volumetric and shear mechanisms, rejecting five other candidates of isochoric and orthotropic response. In this application, we also found Hamming filtering of the deformation gradient field and polynomial smoothing of the displacement to be effective in reducing the noise of the raw data. As a final step, PDE-constrained optimization with adjoints used for gradients resulted in highly refined final coefficient values for the bulk and shear modulus that indeed identified a nearly incompressible response. The resulting error in the forward solution computed with the inferred deformation mechanisms and parameters resulted in volume-averaged L^2-error $\lesssim 3.5\%$ when averaged over the nine steps of loading.

The strong suit of this work is that the experimental characterization via MR-$\boldsymbol{u}$ makes available three-dimensional deformation field data for experimental characterization, and VSI identifies deformation mechanisms while maintaining efficiency of representation with these data. The rectangular prismatic specimen does indeed provide us with three-dimensional data, although the prominent deformation is along the tensile direction. The final data set, coming from an "S-shaped" elastomeric specimen surrogate for soft biological tissue, was loaded parallel to its longer dimension. However, this specimen yielded relatively larger and nonuniform lateral displacements, and with more noise. In this case, the same combination as above: suppression of the orthotropic deformation mechanism that otherwise leads to nonphysical material instability in the inferred physics, with staggered VSI and finally PDE-constrained optimization using adjoints predicts nearly incompressible response with volume-averaged L^2-errors of $\lesssim 7.5\%$ over the six steps of loading.

We note that filtering of the data has its limitations: Hamming filters of up to 4^3 voxels work well for data collection with MR-$\boldsymbol{u}$, while larger filters distort the displacement fields. This data distortion can lead to either non-physical inferred results (vanishing or negative moduli), or to the suppression of properties such as the degree of incompressibility, in this case.

Figure 8: Contours of the ratio of volume averaged L^2-error with sampling over κ and μ for the "S-shaped" specimen. The ratio of error corresponding to each contour with respect to the error for the innermost contour is reported. This ratio for the solid curves is $\frac{\text{error}_{\text{solid}}}{\text{error}_{\text{min}}} = 1.1$.

Notably, the above array of techniques in VSI combined with PDE-constrained optimization using adjoints also sheds light on optimal experimental conditions. The use of larger kernels on the Hamming filters leads to higher errors and a more compressible volumetric response. This suggests approaches by which the optimal filter size and type could be chosen. In order to obtain confidence bounds on the inferred coefficients, we performed MCMC sampling in the $\kappa-\mu$ space around the lowest error results emerging from the PDE-constrained optimization following VSI for the rectangular and "S-shaped" specimens. Using an MCMC procedure driven by error thresholds, we have reported the spread in κ and μ each type of smoothing used.

In materials with well-understood physical mechanisms for deformation, the MR-$\boldsymbol{u}$ + VSI procedure can be harnessed to not only determine material properties, but additionally has potential to elucidate, for example, sources of experimental error. MRI inherently reconstructs image information from sampling magnetic response in frequency space; detector error associated with specific frequency content can be isolated by procedurally testing filter parameters as included variables. In this way, individual experiments run with identical setup parameters can have systematic effects identified independently of random (thermal) noise fluctuations. Similarly, error may in general be associated with load level (or global displacement); incorporating specific forms of this error into our analysis allows for testing of specific error-generation hypotheses which in turn serve to optimize our experimental procedure.

We note that the anisotropic mechanism considered in this work involved a chosen direction of orthotropy. However, in ongoing work, we have found VSI to be effective in inferring the axes of symmetry without having to resort to elimination from among a chosen set of mechanisms with different directions. This takes VSI out of the realm of linear regression to general nonlinear optimization in Algorithms 1 and 2. Furthermore, we have shown in recent work [36] that VSI and PDE-constrained optimization using adjoints also successfully infer spatio-temporally varying mechanisms and parameters. This result also is relevant to soft biological tissues with varying axes of symmetry. When combined with the ability to infer such axes without *a priori* inclusion of a discrete set of directions, this opens the door to inferring spatially varying, and unknown axes of anisotropy that characterize soft biological materials.

Appendix

Table 9: Detailed results on forward predictions after VSI and PDE-constrained optimization for the rectangular elastomer.

Raw data									
Applied load (N)	0.16	0.30	0.58	0.84	1.09	1.21	1.32	1.54	1.74
max. displacements(mm)	0.55	1.09	2.14	3.25	4.31	4.89	5.43	6.46	7.57

Identified model using data with different filtering									
No filter									
Vol. ave. L_2-error(mm)	0.042	0.057	0.097	0.1	0.11	0.09	0.086	0.09	0.073
ratio to max. disp.	7.64%	5.23%	4.53%	3.08%	2.55%	1.84%	1.58%	1.39%	0.96%
Hamming filter: 1^3 voxel									
Vol. ave. L_2-error(mm)	0.04	0.06	0.1	0.1	0.1	0.1	0.9	0.1	0.076
ratio to max. disp.	7.27%	5.5%	4.67%	3.08%	2.32 %	2.04%	1.66%	1.55%	1.%
Hamming filter: 2^3 voxel									
Vol. ave. L_2-error(mm)	0.04	0.06	0.095	0.1	0.1	0.095	0.09	0.095	0.074
ratio to max. disp.	7.27%	5.5%	4.44%	3.08%	2.32 %	1.94%	1.66%	1.47%	0.98%
Hamming filter: 4^3 voxel									
Vol. ave. L_2-error(mm)	0.04	0.05	0.09	0.096	0.1	0.09	0.084	0.09	0.076
ratio to max. disp.	7.27%	4.59%	4.21%	2.95%	2.32 %	1.84%	1.55%	1.39%	1.%
Hamming filter: 8^3 voxel									
Vol. ave. L_2-error(mm)	0.04	0.05	0.1	0.1	0.1	0.1	0.1	0.1	0.1
ratio to max. disp.	7.27%	4.59%	4.67%	3.08%	2.32 %	2.04%	1.84%	1.55%	1.32%
Hamming filter: 12^3 voxel									
Vol. ave. L_2-error(mm)	0.04	0.05	0.1	0.1	0.13	0.12	0.13	0.14	0.15
ratio to max. disp.	7.27%	4.59%	4.67%	3.08%	3.02 %	2.45%	2.39%	2.17%	1.98%
Hamming filter: 16^3 voxel									
Vol. ave. L_2-error(mm)	0.04	0.06	0.1	0.1	0.1	0.1	0.13	0.14	0.15
ratio to max. disp.	7.27%	5.5%	4.67%	3.08%	2.32 %	2.04%	2.39%	2.17%	1.98%
Second-order polynomial smoothing									
Vol. ave. L_2-error(mm)	0.03	0.055	0.9	0.096	0.1	0.08	0.08	0.08	0.067
ratio to max. disp.	5.45%	5.05%	4.21%	2.95%	2.32 %	1.64%	1.47%	1.24%	0.89%

Table 10: Detailed results on forward predictions after VSI and PDE-constrained optimization for the "S-shaped" elastomer

Raw data						
Applied load (N)	1.06	1.58	2.06	2.99	3.87	4.7
max. displacements(mm)	0.99	1.48	1.99	3.02	4.02	5.06
Identified model using data with different filtering						
No filter						
Vol. ave. L_2-error(mm)	0.06	0.1	0.1	0.16	0.19	0.2
ratio to max. disp.	6.06%	6.76%	5.03%	5.3%	4.73%	3.95%
Hamming filter: 1^3 voxel						
Vol. ave. L_2-error(mm)	0.06	0.1	0.1	0.16	0.19	0.2
ratio to max. disp.	6.06%	6.76%	5.03%	5.3%	4.73%	3.95%
Hamming filter: 2^3 voxel						
Vol. ave. L_2-error(mm)	0.06	0.1	0.1	0.16	0.19	0.2
ratio to max. disp.	6.06%	6.08%	5.03%	5.3%	4.73%	3.95%
Hamming filter: 4^3 voxel						
Vol. ave. L_2-error(mm)	0.06	0.1	0.1	0.16	0.19	0.2
ratio to max. disp.	6.06%	6.08%	5.03%	5.3%	4.73%	3.95%
Hamming filter: 8^3 voxel						
Vol. ave. L_2-error(mm)	0.06	0.1	0.1	0.16	0.19	0.2
ratio to max. disp.	6.06%	6.08%	5.03%	5.3%	4.73%	3.95%
Hamming filter: 12^3 voxel						
Vol. ave. L_2-error(mm)	0.07	0.1	0.12	0.17	0.2	0.23
ratio to max. disp.	7.07%	6.73%	6.03%	5.56%	4.93%	4.55%
Hamming filter: 16^3 voxel						
Vol. ave. L_2-error(mm)	0.058	0.1	0.19	0.26	0.3	0.35
ratio to max. disp.	5.86 %	6.76%	9.55%	8.61%	7.46 %	6.92%
Second-order polynomial smoothing						
Vol. ave. L_2-error(mm)	0.06	0.1	0.1	0.16	0.19	0.2
ratio to max. disp.	6.06%	6.76%	5.03%	5.3%	4.73 %	3.95%

References

[1] "A perspective on regression and Bayesian approaches for system identification of pattern formation dynamics". In: *Theoretical Applied Mechanics Letters* 10., pages = ().

[2] H.S. Abdul-Rahman, M.A. Gdeisat, D.R. Burton, F. Lilley, and C.J. Moore. "Fast and robust three dimensional best path phase unwrapping algorithm". In: *Applied Optics* 46.26 (2007), pp. 6623–6635.

[3] S. Avril, J. M. Huntley, F. Pierron, and D. D. Steele. "3D Heterogeneous Stiffness Reconstruction Using MRI and the Virtual Fields Method". In: *Experimental Mechanics* 48.4 (2008), pp. 479–494.

[4] Stéphane Avril, Pierre Badel, and Ambroise Duprey. "Anisotropic and hyperelastic identification of in vitro human arteries from full-field optical measurements". In: *Journal of Biomechanics* 43.15 (2010), pp. 2978 –2985. ISSN: 0021-9290. DOI: https://doi.org/10.1016/j.jbiomech.2010.07.004. URL: http://www.sciencedirect.com/science/article/pii/S0021929010003738.

[5] E. Bar-Kochba, J. Toyjanova, E. Andrews, K. S. Kim, and C. Franck. "A Fast Iterative Digital Volume Correlation Algorithm for Large Deformations". In: *Experimental Mechanics* 55.1 (2015), pp. 261–274.

[6] B. K. Bay, T. S. Smith, D. P. Fyhrie, and M. Saad. "Digital volume correlation: Three-dimensional strain mapping using X-ray tomography". In: *Experimental Mechanics* 39.3 (1999), pp. 217–226.

[7] Matthew R. Bersi, Chiara Bellini, Paolo Di Achille, Jay D. Humphrey, Katia Genovese, and Stéphane Avril. "Novel Methodology for Characterizing Regional Variations in the Material Properties of Murine Aortas". In: *Journal of Biomechanical Engineering* 138.7 (June 2016).

[8] S. L. Brunton, J. L. Proctor, and J. N. Kutz. "Discovering governing equations from data by sparse identification of nonlinear dynamical systems". In: *Proc. Natl. Acad. Sci.* 113 (2016).

[9] H. Chalal, S. Avril, F. Pierron, and F. Meraghni. "Experimental identification of a nonlinear model for composites using the grid technique coupled to the virtual fields method". In: *Composites Part A: Applied Science and Manufacturing* 37.2 (2006). CompTest 2004, pp. 315 –325. ISSN: 1359-835X. DOI: https://doi.org/10.1016/j.compositesa.2005.04.020. URL: http://www.sciencedirect.com/science/article/pii/S1359835X05002460.

[10] K. P. Champion, S. L. Brunton, and J. N. Kutz. "Discovery of Nonlinear Multiscale Systems: Sampling Strategies and Embeddings". In: *SIAM J. Appl. Dyn. Syst.* 18 (2019).

[11] T. C. Chu, W. F. Ranson, and M. A. Sutton. "Applications of digital-image-correlation techniques to experimental mechanics". In: *Experimental Mechanics* 25.3 (1985), pp. 232–244.

[12] R. M. Cotts, M. J. R. Hoch, T. Sun, and J. T. Markert. "Pulsed field gradient stimulated echo methods for improved NMR diffusion measurements in heterogeneous systems". In: *J. Magn. Res.* 83 (1989), pp. 252–266.

[13] J.B. Estrada, U.M. Scheven, C.M. Luetkemeyer, and E.M. Arruda. "MR-u: Material Characterization using 3D Displacement-Encoded Magnetic Resonance and the Virtual Fields Method". in press. 2020.

[14] "General framework for the identification of constitutive parameters from full-field measurements in linear elasticity". In: *International Journal of Solids and Structures* 44.14 (2007), pp. 4978 –5002.

[15] Giuseppe Geymonat, François Hild, and Stéphane Pagano. "Identification of elastic parameters by displacement field measurement". In: *Comptes Rendus Mecanique* 330.6 (2002), pp. 403–408.

[16] M. Grédiac, F. Pierron, and Y. Surrel. "Novel procedure for complete in-plane composite characterization using a single T-shaped specimen". In: *Experimental Mechanics* 39.2 (1999), pp. 142–149.

[17] Michel Grédiac and Fabrice Pierron. "Applying the Virtual Fields Method to the identification of elasto-plastic constitutive parameters". In: *International Journal of Plasticity* 22.4 (2006), pp. 602 –627. ISSN: 0749-6419. DOI: `https://doi.org/10.1016/j.ijplas.2005.04.007`. URL: `http://www.sciencedirect.com/science/article/pii/S0749641905000896`.

[18] "Identification of the through-thickness moduli of thick composites from whole-field measurements using the Iosipescu fixture: theory and simulations". In: *Composites Part A: Applied Science and Manufacturing* 31.4 (2000), pp. 309 –318.

[19] G. James, D. Witten, T. Hastie, and R. Tibshirani. "An Introduction to Statistical Learning". In: *Springer New York, Inc., New York, NY, USA.* (2013).

[20] E. Kaiser, J. N. Kutz, and S. L. Brunton. "Discovering conservation laws from data for control". In: *IEEE Conference on Decision and Control* (2018).

[21] C.M. Luetkemeyer, L. Cai, C.P. Neu, and E.M. Arruda. "Full-Volume Displacement Mapping of Anterior Cruciate Ligament Bundles with dualMRI". In: *Extreme Mechanics Letters* 19 (2018), pp. 7–14.

[22] N. M. Mangan, S. L. Brunton, J. L. Proctor, and J. N. Kutz. "Inferring biological networks by sparse identification of nonlinear dynamics". In: *IEEE Trans. Mol. Biol. Multi-Scale Commun.* 2 (2016).

[23] Sebastian K. Mitusch, Simon W. Funke, and Jørgen S. Dokken. "dolfin-adjoint 2018.1: automated adjoints for FEniCS and Firedrake". In: *Journal of Open Source Software* 4.38 (2019), p. 1292. DOI: `10.21105/joss.01292`. URL: `https://doi.org/10.21105/joss.01292`.

[24] F. Pierron, G. Vert, R. Burguete, S. Avril, R. Rotinat, and M. R. Wisnom. "Identification of the Orthotropic Elastic Stiffnesses of Composites with the Virtual Fields Method: Sensitivity Study and Experimental Validation". In: *Strain* 43.3 (2007), pp. 250–259.

[25] Fabrice Pierron and Michel Grédiac. *The virtual fields method: extracting constitutive mechanical parameters from full-field deformation measurements.* Springer Science & Business Media, 2012.

[26] Nattawit Promma, Bumedijen Raka, Michel Grediac, Evelyne Toussaint, J-B Le Cam, Xavier Balandraud, and François Hild. "Application of the virtual fields method to mechanical characterization of elastomeric materials". In: *International Journal of Solids and Structures* 46.3-4 (2009), pp. 698–715.

[27] M. Raissi and G.E. Karniadakis. "Hidden physics models: Machine learning of nonlinear partial differential equations". In: *J. Comput. Phys* 357 (2018), pp. 125–141.

[28] M. Raissi, P. Perdikaris, and G.E. Karniadakis. "Physics-informed neural networks: A deep learning framework for solving forward and inverse problems involving nonlinear partial differential equations". In: *J. Comput. Phys.* 378 (2019).

[29] Aaron Romo, Pierre Badel, Ambroise Duprey, Jean-Pierre Favre, and Stéphane Avril. "In vitro analysis of localized aneurysm rupture". In: *Journal of Biomechanics* 47.3 (2014), pp. 607 –616. ISSN: 0021-9290. DOI: `https://doi.org/10.1016/j.jbiomech.2013.12.012`. URL: `http://www.sciencedirect.com/science/article/pii/S0021929013006398`.

[30] S. H. Rudy, S. L. Brunton, J. L. Proctor, and J. N. Kutz. "Data-driven discovery of partial differential equations". In: *Sci. Adv.* 3 (2017).

[31] U.M. Scheven, J.B. Estrada, C.M. Luetkemeyer, and E.M. Arruda. "Robust High Resolution Imaging by Alternating Pulsed Field Gradient Stimulated Echo Imaging (APGSTEi) at 7 Tesla". In: *Journal of Magnetic Resonance* 310 (2020), pp. 106620–106626.

[32] D.A. Stout, E. Bar-Kochba, J.B. Estrada, J Toyjanova, H. Kesari, J.S. Reichner, and C. Franck. "Mean deformation metrics for quantifying 3D cell–matrix interactions without requiring information about matrix material properties". In: *Proceedings of the National Academy of Sciences* 113.11 (2016), pp. 2898–2903.

[33] Pauli Virtanen, Ralf Gommers, Travis E. Oliphant, Matt Haberland, Tyler Reddy, David Cournapeau, Evgeni Burovski, Pearu Peterson, Warren Weckesser, Jonathan Bright, Stéfan J. van der Walt, Matthew Brett, Joshua Wilson, K. Jarrod Millman, Nikolay Mayorov, Andrew R. J. Nelson, Eric Jones, Robert Kern, Eric Larson, CJ Carey, İlhan Polat, Yu Feng, Eric W. Moore, Jake Vand erPlas, Denis Laxalde, Josef Perktold, Robert Cimrman, Ian Henriksen, E. A. Quintero, Charles R Harris, Anne M. Archibald, Antônio H. Ribeiro, Fabian Pedregosa, Paul van Mulbregt, and SciPy 1. 0 Contributors. "SciPy 1.0: Fundamental Algorithms for Scientific Computing in Python". In: *Nature Methods* 17 (2020), pp. 261–272.

[34] Z. Wang, X. Huan, and K. Garikipati. "Identification of the partial differential equations governing microstructure evolution in materials: Inference over incomplete, sparse and spatially non-overlapping data". In: (). arXiv:2001.04816.

[35] Z. Wang, X. Huan, and K. Garikipati. "Variational system identification of the partial differential equations governing the physics of pattern-formation: Inference under varying fidelity and noise". In: *Computer Methods in Applied Mechanics and Engineering* 356 (2019), pp. 44 –74. ISSN: 0045-7825. DOI: `https://doi.org/10.1016/j.cma.2019.07.007`.

[36] Z. Wang, X. Zhang, G.H. Teichert, M. Carrasco-Teja, and K. Garikipati. "System inference for the spatio-temporal evolution of infectious diseases: Michigan in the time of COVID-19". In: *Computational Mechanics* (2020). arXiv: `2007.00865 [q-bio.PE]`.

[37] José Xavier, Stéphane Avril, Fabrice Pierron, and José Morais. "Novel experimental approach for longitudinal-radial stiffness characterisation of clear wood by a single test". In: *Holzforschung* 61.5 (2007), pp. 573 –581. DOI: `https://doi.org/10.1515/HF.2007.083`. URL: `https://www.degruyter.com/view/journals/hfsg/61/5/article-p573.xml`.

[38] Liang Zhang, Sri Gowtham Thakku, Meghna R. Beotra, Mani Baskaran, Tin Aung, James C. H. Goh, Nicholas G. Strouthidis, and Michael J. A. Girard. "Verification of a virtual fields method to extract the mechanical properties of human optic nerve head tissues in vivo". In: *Biomechanics and Modeling in Mechanobiology* 16.3 (2017), pp. 871–887.