Avoiding tensional equilibrium in cells migrating on a matrix with cell-scale stiffness-heterogeneity

Authors: Hiroyuki Ebata[1], Satoru Kidoaki[1*]

Author affiliation: [1] Laboratory of Biomedical and Biophysical Chemistry, Institute for Materials Chemistry and Engineering, Kyushu University, CE41-204, 744 Motooka, Nishi-ku, Fukuoka 819-0395, Japan

Corresponding author:
Satoru Kidoaki
E-mail: kidoaki@ms.ifoc.kyushu-u.ac.jp

Abstract

Intracellular stresses affect various cell functions, including proliferation, differentiation and movement, which are dynamically modulated in migrating cells through continuous cell-shaping and remodeling of the cytoskeletal architecture induced by spatiotemporal interactions with extracellular matrix stiffness. When cells migrate on a matrix with cell-scale stiffness-heterogeneity, which is a common situation in living tissues, what intracellular stress dynamics (ISD) emerge? In this study, to explore this issue, finite element method-based traction force microscopy was applied to cells migrating on microelastically patterned gels. Two model systems of microelastically patterned gels (stiff/soft stripe and stiff triangular patterns) were designed to characterize the effects of a spatial constraint on cell-shaping and of the presence of different types of cues to induce competing cellular taxis (usual and reverse durotaxis) on the ISD, respectively. As the main result, the prolonged fluctuation of traction stress on a whole-cell scale was markedly enhanced on single cell-size triangular stiff patterns compared with homogeneous gels. Such ISD enhancement was found to be derived from the interplay between the nomadic migration of cells to regions with different degrees of stiffness and domain shape-dependent traction force dynamics, which should be an essential factor for keeping cells far from tensional equilibrium.

Keywords: traction force microscopy, intracellular stress dynamics, tensional equilibrium, reverse durotaxis, cell migration

Introduction

Changes in intracellular stress brought about by cell deformation and shaping have been shown to affect various cell functions. For example, cell contractility sensitively regulates DNA synthesis/cell proliferation[1, 2, 3, 4], lineage-specific gene expression/cell differentiation[5, 6, 7, 8], and the generation of cell-polarity/directed cell movement[9, 10, 11]. The strength and spatial distribution of intracellular stresses are determined by the interaction between mechanical properties of the extracellular matrix (ECM) and intrinsic cellular prestress which the cell actively generates inside itself as a result of the activities of adhesion machinery and cytoskeletal architecture [12, 13, 14, 15]. In principle, this interaction is dynamic because of continuous cell-shaping and remodeling of the cytoskeletal architecture during cell movement. Since cells *in vivo* generally migrate in tissues with characteristic mechanical properties under a microscopic spatial distribution, intracellular stress dynamics (ISD) provide fingerprint-like information on the mechanical interactions between cells and ECM. Especially when the surrounding mechanical field is heterogeneous comparable to a cell-size scale[16, 17, 18, 19], ISD in an entire cell should exhibit temporal fluctuations that are markedly different from those observed on a homogeneous mechanical field. Although this situation is rather common *in vivo*, the detailed characteristics of ISD on a matrix with cell-scale heterogeneity remain unclear.

To better understand the actual nature of ISD, traction force microscopy (TFM) is a powerful tool for determining the traction behavior at cell adhesion interfaces which reflect cellular contractility and intracellular stresses. Various types of TFM have been proposed for 2D and 3D analyses[20, 21, 22, 23]. When a cell adheres to a flat homogeneous gel surface, analytical solutions of linear elastic theory, the Boussinesq solution, are often used to reconstruct the traction force[20, 21]. However, for a matrix with cell-scale stiffness-heterogeneity, such as a microelastically patterned substrate, the elastic modulus sharply changes within the adhered area of a single cell, and an analytical solution for the equation of equilibrium cannot be obtained in general. Thus, for micromechanically-heterogeneous systems, TFM based on a numerical calculation such as with the finite element method (FEM) must be applied [22, 24]. In addition, the time-scale for analysis is essential for investigating the effect of cell-scale stiffness-heterogeneity on ISD. In particular, the long-period fluctuation of traction force in an entire cell is important since it can cause field size-dependent periodic perturbation of the tensional steady-state of the cells. To analyze this phenomenon, TFM should be performed for more than several tens of hours.

In this study, to reveal the feature of ISD affected by cell-scale stiffness-heterogeneity, we sought to determine the long-term and whole cell-scale dynamics of traction force for

cells migrating on a heterogeneous matrix. By employing FEM-based TFM[22, 24], we measured the long-term dynamics of traction force of mesenchymal stem cells (MSCs) cultured on microelastically patterned hydrogels[25, 26]. Several tens of microns-scaled patterns were applied with stiff/soft stripes and periodic triangular stiff domains. In contrast to previous typical TFM results on a single linear elasticity gradient with pillar arrays[27, 28], the size and curvature of the stiff domain were found to crucially affect the magnitude of the traction stress. We clarified that cell-scale variability of stiffness in an adhesion area determines the magnitude of the traction force as well as the local stiffness of the substrate. Reflecting these behaviors, the long-term computation of traction force dynamics revealed that cell-scale stiffness-heterogeneity strongly enhances the strength and frequency of fluctuation of the ISD in migrating MSCs in comparison to those on homogeneous gels.

Materials and methods

Preparation of photocurable sol solution

Photocurable styrenated gelatin (StG) was used for photolithographic microelasticity patterning of the gel, which was prepared as described previously[25, 26, 29]. StG (30 wt %) and sulfonyl camphorquinone (3.0 wt % gelatin; Toronto Research Chemicals, ON, Canada) were dissolved in phosphate-buffered saline (PBS). The mixed solution was centrifuged (MX-301; TOMY, Tokyo, Japan) at 14,000 rpm (17,800 g) and 30 °C for 1h, and deposits were removed. The clear sol solution was aspirated for 1h at 45 °C to exclude dissolved oxygen. The sol solution was then conditioned for 10 min using an AR-100 deforming agitator (THINKY Corp., Tokyo, Japan).

Photolithographic microelasticity patterning of gelatinous gel

Photolithographic microelasticity patterning gel with fluorescent beads was prepared as follows. First, a normal glass substrate was coated with poly(N-isopropylacrylamide) (PNIPAAm, Sigma Aldrich, St. Louis, MO) at 5 krpm for 60s. Next, we prepared diluted StG solution A; 10 wt % StG sol solution with 1.0 wt % sulfonyl camphorquinone and 0.1 wt % Tween 20. Sixty-five μl of the StG solution A was spin-coated on the NIPAAm-coated glass at 5 krpm for 20s. Next, we prepared diluted StG solution B; 10 wt % StG sol solution with 1.0 wt % sulfonyl camphorquinone, 0.1 wt % Tween 20, and fluorescent beads (Fluorospheres® Carboxylate-Modified Microspheres, 0.2 μm, red fluorescence (580/605), Invitrogen). 65 μl of the StG solution B was spin-coated on the StG sol / NIPAAm-coated glass at 5 krpm for 20s. We added Tween 20 to improve wettability. Throughout the procedure, we warmed the glass and solutions at 45 °C to prevent

dissolution of the NIPAAm layer. Next, 25 µl of the 30 wt % StG sol solution was spread between vinyl-glass and StG sol with beads / StG sol / NIPAAm-coated glass.

A soft base gel was prepared by irradiation of the entire sample with visible light for 120s – 210s (45 – 50 mW / cm^2 at 488 nm; light source: MME-250; Moritex Saitama, Japan). Next, stiff regions were prepared by local irradiation of the base gel using a set irradiation pattern and a custom-built, mask-free, reduction-projection-type photolithographic system. Equilateral-triangular irradiated regions with side lengths L of 150 µm and 250 µm were projected on the gel using an EB-1770W liquid crystal display projector (SEIKO EPSON, Nagano, Japan). The center of the triangle was periodically placed on the honeycomb lattice. The distance W between the corners of the triangles was 120 µm (Fig. 1 (inset)). Finally, the gels were detached from the NIPAAm-coated normal glass substrate and washed thoroughly with PBS at 28 °C to remove the adsorbed PNIPAAm and Tween20. Stripe patterns with a unit length L of 100 and 600 µm (Fig. 1 (inset)) and homogeneous gels were also prepared.

Measurement of the surface elasticity distribution around the elasticity boundary

The surface elasticity of the StG gel was determined by nano-indentation analysis using an atomic force microscope (JPK NanoWizard 4, JPK Instruments, Bruker Nano GmbH, Germany). A commercial silicone-nitride cantilever with a nominal spring constant of 0.03 - 0.09 N/m was used (qp-BioAC-CI CB3, Nanosensors). Young's moduli of the surface were evaluated from force-indentation curves by nonlinear least-square fitting to the Hertz model in the case of a parabolic indenter (tip radius of curvature 30 nm; Poisson ratio µ: 0.5). To make a spatial distribution of elasticity in the triangular pattern gel, we measured about 100 tiles of a 40 x 40 µm elasticity map with a distance of 2 µm between each measured point. Next, we reconstructed the spatial distribution of elasticity from the tiles.

The topographic condition of the sample surface was also measured by using the atomic force microscope. Although the soft regions were 15 – 25 µm higher than the stiff regions, the connection between the two regions was smooth enough to not disturb natural durotaxis. In addition, we did not observe the accumulation of MSCs at the basin of the topography of triangular-pattern gel. Thus, in our experiment, curvotaxis is expected to have little effect[30].

Cell culture

Human bone marrow mesenchymal stem cells (hMSC, Lonza) were cultured in mesenchymal stem cell basal medium (MSCBM, Lonza) at 37°C in a humidified atmosphere containing 5% CO_2.

Time-lapse observation of cell movement

The migratory motion of cells on the microelastically patterned gel was monitored using an automated all-in-one microscope with a temperature- and humidity-controlled cell chamber (BZ-X700; Keyence Corporation, Osaka, Japan). Prior to the time-lapse observations, cells were seeded onto the gel surface at a density of 1×10^3 cells / cm^2 and cultured in DMEM containing 10% FBS for 18 – 22 hours under 5 % CO_2. Phase-contrast images of cells and fluorescent images of beads were captured every 15 min for 24 h. We used a 20×(NA = 0.30) Plan Fluor objective lens. For each experiment, we collected images from 11 – 20 positions of 1 - 2 gel samples. For each position, we stacked the image of fluorescent beads for the *z*-direction. Next, we made an extended depth of field from the *z*-stacks using Image J[31]. To calculate the displacement field of the gels, we detached the cells after the time lapse. We replaced the medium with DMEM containing 0.3% Tween 20, and incubated the mixture for 30 min to kill the cells. Next, we washed the gel 3 times with DMEM. After incubation with DMEM for 30 min, we measured the reference image of the fluorescent beads.

Analysis of cell-shaping dynamics

Movement trajectories and the shapes of the cells were determined and analyzed using MATLAB software. Based on edge-detection of a cell, we extracted the shape of the cell from phase-contrast images. The details of image-processing have been explained previously [32]. We traced each cell and measured the time evolution of the trajectory and shape. If the cells collided with each other or if a cell was divided, we stopped the trace. When the cells separated again, we renumbered the cells and restarted the trace. Through the image analysis, cell trajectories *x*(*t*) were calculated.

Traction force microscopy

To calculate the traction force of the cells, we used finite-element-method (FEM) based traction force microscopy[22, 24]. The displacement field of fluorescent beads was measured by comparing images with and without cells. The displacement of the beads was calculated using commercial PIV software (Flownizer 2D; Detect Corporation, Tokyo, Japan). In the calculation of FEM, a hexahedron was used for discretization (the size of

the unit is about 8 x 8 x 8 μm). The nodes of a hexahedron at the substrate surface were chosen to be identical to the nodes of PIV. We assume that the patterned gel is a linear elastic body with spatial modulation according to Young's modulus $E(x)$:

$$\sigma_{ik} = \frac{E(x)}{1+v}\left(u_{ik} + \frac{v}{1-2v}u_{ll}\delta_{ik}\right),$$
(1)

where i, j, and k are x, y, z. σ_{ik} and u_{ik} are the stress tensor and strain tensor, respectively. v is the Poisson ratio. In our calculation, we use $v = 0.4$. For homogeneous gels, $E(x)$ is constant. For patterned gels, we assume

$$E(x) = E_0 + \sum\left(A_{kx,ky}\cos\left(k_x x + k_y y\right) + B_{kx,ky}\sin\left(k_x x + k_y y\right)\right),$$
(2)

where E_0, $A_{kx,ky}$, and $B_{kx,ky}$ were fitted by the data from the AFM measurement. With FEM, the equilibrium equation for a linear elastic body, Eq. (1), is discretized as

$$K_{ijkl}U_{ik} = F_{jl},$$
(3)

where K_{ijkl} is a stiffness matrix, U_{ik} is displacement of the k component at node i, and F_{jl} is force in the l direction applied at node j. From Eq. (3), we calculate a response function M_{ijkl} of the gel against the point force, where M_{ijkl} is the k component of the displacement at node i when a unit force is applied in the l direction at node j. Since we do not observe the z direction of displacement, we only consider the x and y components in force reconstruction as in ordinary TFM in 2D. For simplicity, we introduce the following matrix and vectors.

$$M = \begin{pmatrix} M_{11xx} & M_{11xy} & \cdots & M_{1Nxy} \\ M_{11yx} & M_{11yy} & \cdots & M_{1Nyy} \\ \vdots & \vdots & \ddots & \vdots \\ M_{J1yx} & M_{J1yy} & \cdots & M_{JNyy} \end{pmatrix},$$
(4)

$$F = \begin{pmatrix} F_{1x} & F_{1y} & \cdots & F_{Ny} \end{pmatrix}^{T},$$
(5)

$$U = \begin{pmatrix} U_{1x} & U_{1y} & \cdots & U_{Jy} \end{pmatrix}^{T},$$
(6)

where ^{T} denotes the transposition. N is the number of the node where the force is reconstructed. J is the number of the node where the displacement is measured experimentally. In the case that the forces are distributed on surface nodes, displacement of the surface U can be expressed by using M:

$$U = MF$$
(7)

By solving the inverse problem of Eq. (7), we can reconstruct the distribution of the force. The flow chart of FEM-based TFM is shown in Fig. S1. Because of the ill posed nature of force reconstruction, some filtering schemes are required to reduce the noise. In this paper, F is reconstructed by minimizing function S, which is a combination of the least-square displacement error and a weighted norm of the forces:

$$\begin{aligned} S &= \|U_r - U\|^2 + F^T A F \\ &= \|U_r - MF\|^2 + F^T A F \end{aligned} \tag{8}$$

where U_r is displacement of the substrate measured experimentally. The matrix A is a diagonal matrix containing the local penalty weights. Next, we calculate F, which gives the minimum of S, $dS/dF = 0$:

$$F = \left(M^T M + A\right)^{-1} M^T U_r, \tag{9}$$

We then iteratively change A depending on the estimated force. We use a local penalty matrix that was proposed previously [33].

$$\begin{aligned} A_{ii} &= \alpha, \quad |F_i| < 1.345 \cdot median\left(|F|\right) \\ A_{ii} &= 1.345\alpha \frac{median\left(|F|\right)}{|F_i|}, \quad |F_i| > 1.345 \cdot median\left(|F|\right) \end{aligned} \tag{10}$$

We repeatedly calculate Eqs. (9) and (10) until convergence is reached. When the regulation parameter α is sufficiently small compared to a typical value of $M^T M$, the reconstructed traction field becomes very noisy. If α is too large, traction stress tends to be underestimated. Since $M^T M$ is inversely proportional to the square of the elasticity of the substrate, we vary α depending on the magnitude of $M^T M$. We set regulation parameter α as

$$\alpha = \max\left(M^T M\right)/2 \tag{11}$$

The validity and accuracy of FEM-based TFM are discussed in the SI (Figs. S2 and S3).

Calculation of the force spot

To identify the force spot, we calculated the threshold of the traction stress. As reported previously [34], the cumulative distribution of the traction stress around the cell had exponential tails (Fig. S4):

$$Prob\left(Tr\right) \sim \exp\left(-\frac{Tr}{P_0}\right) \tag{12}$$

where the P_0 is the typical traction stress of the cell. Since P_0 does not depend on segmentation of the cell shape, we used P_0 as the threshold for the force spot.

Definitions of mean traction stress and mean elasticity

The mean traction stress $Tr_m(t)$ of a cell and mean elasticity $E_m(t)$ just below a cell are defined as

$$Tr_m(t) = \int_{\Omega(t)} Tr(x,y,t)dxdy / \int_{\Omega(t)} dxdy$$
$$E_m(t) = \int_{\Omega(t)} E(x,y)dxdy / \int_{\Omega(t)} dxdy$$

$$(13)$$

where $Tr(x,y,t)$ and $E(x,y)$ are the traction stress and elasticity at point (x,y). $\Omega(t)$ is the area of the cell that was calculated from the segmentation of the phase-contrast image.

Definitions of magnitude of fluctuation of traction stress and other variables

Similar to the approach described in the literature[35], we used the normalized standard deviation of $Tr_m(t)$ as the magnitude of fluctuation of traction stress. It is defined as the ratio of the standard deviation to the mean of the time series.

$$Fluc(Tr) = \frac{\sigma(Tr_m)}{\langle Tr_m \rangle_t}$$

$$(14)$$

where $\sigma(Tr_m)$ and $\langle Tr_m \rangle_t$ are the standard deviation and time average of $Tr_m(t)$. The magnitude of the fluctuations of gel deformation, the cell aspect ratio, and cell area were calculated in a similar manner.

Results
Microelastically patterned substrates with cell-scale stiffness-heterogeneity

To investigate the effect of cell-scale stiffness-heterogeneity on cell migration and ISD, we prepared two types of microelastically patterned substrates by photolithography with photocurable styrenated gelatin (StG) (Fig. 1) [25, 26]. One was a striped gel with alternating stiff and soft bands of different widths (targeted unit width L: 100 μm and 600 μm: Figs. 1a and b, designated Stripe-100 and Stripe-600, respectively). The other was a triangular-patterned gel with different side-lengths of a triangular stiff domain (targeted side length: 150 μm and 250 μm: Figs. 1c and d, designated Triangle-150 and Triangle-250, respectively). As controls, we also prepared homogenous soft and stiff gels, designated Plain-soft and Plain-stiff, respectively. To avoid the influence of the topography of the gel surface on natural cell movement, the focus condition of lithographic photoirradiation

Figure 1. Striped- and triangular-patterned gels. (a – d) Phase-contrast microscopic images of Stripe-100 (a), Stripe-600 (b), Triangle-150 (c), and Triangle-250 (d). Scale bars denote 100 μm. (inset) Schematic illustration of the photomask. White indicates the irradiated region. Stripe: *L* is the unit width of a stripe. Triangle: *L* is the side length. *W* is the distance between the corners of the triangles, set at 120 μm. **(e, f)** Distribution of Young's modulus *E* for Stripe-100 (e) and Stripe-600 (f). Distributions of a half unit-stripe are shown. **(g)** Schematic illustration of the spatial distribution of elasticity for triangular pattern. Blue and yellow colors indicate soft and stiff domains. The region surrounded by white dashed lines represents a unit triangle of the pattern. **(h, i)** Spatial distribution of Young's modulus for Triangle-150 (h) and Triangle-250 (i).

was optimized. The conditions and Young's moduli of the stiff and soft domains are shown in Table 1.

For the striped gels, the unit widths of 100 μm and 600 μm were designed to model single cell-size and multicellular-size of MSCs, respectively. Young's modulus was ca. 10 kPa for the soft regions and ca. 40 kPa for stiff regions over a transition region of ~50 μm in width (Figs. 1e and f). A stiffness gradient of 30 kPa / 50 μm with a 10 kPa soft region has been previously clarified to have differential effects on the induction of durotaxis between these two unit widths, i.e., durotaxis is induced in the 100 μm-wide stripes, but not in the 600 μm-wide stripes depending on the cell-scale stiffness-heterogeneity[29]. To better understand the reason for these differential behaviors in

Designation	L	W	Young's Modulus of the soft region	Young's Modulus of the stiff region
Plain-soft	-----	-----	5 ± 2 kPa	-----------------
Plain-stiff	-----	-----	-----------------	21 ± 7 kPa
Stripe-100	100 μm	-----	9 ± 1 kPa	43 ± 7 kPa
Stripe-600	600 μm	-----	11 ± 1 kPa	40 ± 6 kPa
Triangle-150	150 μm	120 μm	4 ± 1 kPa	23 ± 4 kPa
Triangle-250	250 μm	120 μm	5 ± 1 kPa	21 ± 3 kPa

Table 1. Size and Young's moduli of the soft and stiff domains of microelastically patterned gels.

durotaxis from the perspective of a traction force analysis, the present stiffness gradient was adopted.

For the triangular patterned gels, the side lengths of a stiff equilateral triangle *L* were designed to be 150 μm and 250 μm to model single cell-size and multiple cell-size, and the unit sizes of the as-prepared soft triangular base including stiff triangles were 254 μm and 354 μm, respectively. (Figs. 1c, d, and g). We changed *L* with a fixed width of soft regions *W* (see Fig. 1c and d inset). Young's modulus varied from around 4 kPa to 20 kPa over a transition region of ca. 80 μm in width (Figs. 1h and i). The corner of a stiff triangle has a convex elasticity boundary toward the soft region with a curvature radius of less than 50 μm, where reverse durotaxis from stiff to soft regions can be induced, as we previously reported[26]. Thus, the triangular stiff domains are expected to induce both usual soft-to-stiff durotaxis[36] and reverse stiff-to-soft durotaxis at the side and at the corner of the triangle, respectively. Such a system can be applied as a model of the microscopic mechanical environment of ECM in which different types of elasticity boundary in terms of curvature closely coexist. In living tissue, the presence of curved architecture and the coexistence of stiffness gradients with different nonlinearities are rather common [19, 37]. What features of ISD emerge in a system with different types of cues of competing cellular taxis? To investigate this issue, triangular-patterned gels with a similar range of stiffness gradient as with striped-patterned gels were used for comparisons.

Stripe width-dependent modulation of traction force

We previously reported that, generally, the stiffness gradient required to induce durotaxis is altered by the size of the stiff/soft regions [29]. The mechanism for this phenomenon can be explained in part by the different characteristic features of cell-shaping dynamics depending on the size of stiff domains. However, an exact understanding for ISD behavior remains unclear. To clarify this issue, traction forces were

Figure 2. Dependence of traction force on the width of striped-patterned gels. (a) Probability distribution functions of the centroid of MSCs in a cycle of stripe. Horizontal axis denotes the position *x* normalized by the unit width *L* of the stripe. Blue: Stripe-100. Red: Stripe-600. (b) Deformation fields measured on Stripe-100. (c) Distribution of the traction forces estimated from Fig. 3 (b). (d) Deformation fields measured on Stripe-600. (e) Distribution of the traction forces estimated from Fig. 3 (d). (b - e) A vector field of different time points was superimposed on the figure. A longer vector represents greater deformation and force. As the color of the vector changes from blue to red, deformation and force increase. (f) An example of a color map of traction stress (left) and the corresponding force spots (right). (g, h) Magnitude of traction stress of the force spot as a function of the position *x* for Stripe-100 (g) and Stripe-600 (h). Solid lines indicate median values. Shaded regions cover 0.25 and 0.75 quantiles. The Mann–Whitney U test was used to calculate the P value. *** P < 0.001. n =32 for Stripe-100. n =25 for Stripe-600.

analyzed for the differential responses of durotaxis on different stripe widths with the same stiffness gradient.

As shown in Fig. 2a, MSCs in the stiff regions of Stripe-100 exhibit usual durotaxis (blue). On the other hand, on Stripe-600, except in the transition region, they stayed almost equally in soft and stiff regions (red). On Stripe-600, cells tended to accumulate at the elasticity boundary, because MSCs readily aligned along the stripes, as observed previously[29]. Even though the strength of a stiffness gradient is set to be the same for these two conditions, only Stripe-100 induced durotaxis affected by the size of the stiff region. The mechanobiological basis for this differential induction of durotaxis was explored by using FEM-based TFM.

Figures 2b and c show a representative deformation field and reconstructed traction field generated by a MSC on Stripe-100. The background black/white shading represents the elasticity field of the gel. As the shading becomes dark, the gel becomes stiffer. Although the gel was highly deformed on soft regions (Fig. 2b), the magnitude of the traction force tended to be large on stiff regions (Fig. 2c). On the other hand, Figs. 2d and e show these fields on Stripe-600. Compared with the results for Stripe-100, large traction forces were exerted on both soft and stiff regions (Fig. 2e). These observations suggested that the striped pattern with a single-cell size could enhance the magnitude of traction force on a stiff domain.

This effect of stripe width on the traction force seemed to dominantly arise at the force spots where large traction stress was localized[34]. Therefore, we next analyzed the dependence of the force magnitude in the force spot on the spatial heterogeneity of stiffness. From the cumulative distribution of the traction stress of an entire cell, we calculated the threshold of traction stress to identify the force spots (Fig. 2f and Method). The left side of Fig. 2f shows an example of the spatial distribution of traction stress of a representative cell. Yellow domains on the right side of Fig. 2f represent the force spots calculated from the left side of Fig. 2f. Next, we calculated the magnitude of traction stress in force spots as a function of the position in the stripes (Figs. 2g and h). For Stripe-100, the traction stress of force spots became significantly large at the center of the stiff regions (right-hand edge of Fig. 2g). On the other hand, for Stripe-600, traction stress significantly increased in soft regions (left-hand edge of Fig. 2h). The smaller traction stress on stiff regions should not derive from the underestimation of the traction force during the force reconstruction process, because the traction stress of a force spot on the homogeneous stiff gel (0.48 kPa) became significantly larger than that on the homogeneous soft gel (0.38 kPa, see Fig. S5).

This analysis clarified that the traction forces in durotactic cells are sensitively modulated depending on the size of the stiff/soft regions even with the same stiffness gradient which does not originally induce durotaxis in a control linear elasticity boundary. A narrow stiff region enhanced the strength of traction stress enough to induce durotaxis, while a wide stiff region did not, which was found to be the cause of the emergence of differential responses of durotaxis for the same stiffness gradient.

Traction forces around the triangular stiff domains

In the above case of mechanically striped-patterned gels, only the linear stiffness gradient across an elasticity boundary existed on the gels, and the substrate mechanics-dependent taxis cue could induce one-way directed cell movement, i.e., soft-to-stiff

Figure 3. Dependence of the traction force on the convex shape of the stiff domain. (a, b) Trajectories of the centroid of the cells on Triangle-150 (a) and Triangle-250 (b). Gray-scaled background indicates the elasticity distribution of the gels. White and black indicate soft and stiff regions, respectively. Elasticity distribution was estimated from Figs. 1e and f. **(c, d)** Probability distribution of the cell position on unit triangular patterns of Triangle-150 (c) and Triangle-250 (d). Considering the spatial symmetry, the smallest stiff unit was surrounded by white dashed lines. We calculated the probability distribution on the smallest unit. Next, we replicated the smallest unit to construct the unit triangle. Thus, the probability distribution is highly symmetric. **(e)** Deformation fields measured on Triangle-150. **(f)** Distribution of the traction forces estimated from Fig. 4 (e). (e, f) A vector field of different time points was superimposed on a figure. A longer vector represents greater deformation and force. As the color of the vector changes from blue to red, deformation and force increase. **(g, h)** Color map of the traction stress of the force spot as a function of the position x and y. The Mann–Whitney U test was used to calculate the P value. *** $P < 0.001$. n =46 for Triangle-150. n =23 for Triangle-250.

durotaxis. However, stiffness-heterogeneity in a natural living body should not exhibit such a simple situation, and rather includes a variety of nonlinear stiffness gradients, such as a curved elasticity boundary. As mentioned above, microscopic stiffness-heterogeneity of ECM may provide different effects for cellular taxis which may compete with each other. To model this situation, a triangular stiff domain can be applied because it has dual

tactic cues of usual durotaxis[36] and reverse durotaxis[26]. What behaviors of dynamics in ISD appear in the system? To investigate this issue, we analyzed traction forces on triangular patterned gels.

First, we measured cell trajectories to characterize migration (Figs 3a and b). Here, the cell trajectory is defined as the path of the geometric center of the cell shape projected on an x-y plane, which was superimposed on the elasticity distribution estimated from AFM measurement; background black/white shading denotes stiff and soft regions, respectively. On Triangle-150, MSCs tended to go along the sides of stiff triangles and nomadically moved between soft and stiff regions around the corners of triangles, suggesting the emergence of dual tactic behaviors of usual and reverse durotaxis. Such frequent shuttling of MSCs was not observed in the striped pattern with a single-cell size (see Fig. 2a). On the other hand, on Triangle-250, MSCs tended to stay around the corner and the side of the triangle. As a result, MSCs stayed almost equally in soft and stiff regions on Triangle-150, while they stayed in stiff regions longer on Triangle-250 (Fig. S6). To confirm whether reverse durotaxis occurred, we calculated the probability distributions of cell position in the unit triangle of patterned gels, which was determined by the steady state of cell migration (Figs. 3c and d). On Triangle-150 (Fig. 3c), cells were distributed around the corners of triangles and migrated across the soft region between the corners of adjacent stiff triangles. On Triangle-250 (Fig. 3d), cells were strongly trapped near corner regions inside stiff domains.

What behaviors in traction forces emerge around triangular stiff regions? Figures 3e and f show the measured deformation field and reconstructed traction field generated by a MSC on Triangle-150. Interestingly, large traction forces of MSCs did not necessarily appear in the stiffest region, but rather appeared around the corners of triangles (Fig. 3f). The calculated spatial variation of the traction stress of the force spots (Figs. 3g and h) increased around the soft region outside of the corners of stiff domains for both small and large triangular patterns, indicating that the convex shape of the stiff domain crucially enhanced the magnitude of the traction stress in the soft region around the corners (Figs. 3g and h, red arrows). We clarified that MSCs are attracted to the soft outside of corners of stiff triangles by the effect of enhanced traction stress of the pseudopodia. In addition, Fig. 3h shows the increase in traction stress around the center of Triangle-250, suggesting the stronger induction of usual durotaxis toward stiff domains. This could cause the suppression of reverse durotaxis and nomadic motion on Triangle-250 (Fig. 3d). Thus, the results suggest that the size of the triangle modulated the balance of the competing cellular taxis.

Figure 4. Time course of the traction stress on the patterned and homogeneous gels. (a - c) Example time course of the mean traction stress (blue) of a cell and mean elasticity (orange) under a cell on Stripe-100 (a), Triangle-150 (b), Plain-soft (c; dashed line), and Plain-stiff (c; solid line). **(d – f)** Time course of the mean traction stress of 10 cells on Stripe-100 (d), Triangle-150 (e), and Plain-stiff (f). Different colors indicate different cells. *N* denotes the cell number.

Temporal fluctuations of whole-cell traction stress affected by stiffness-heterogeneity

As clarified above, the spatial distribution and magnitude of traction forces in migrating cells are significantly modulated by the conditions of microscopic stiffness-heterogeneity, which, in principle, is a result of the characteristic dynamics in the remodeling of adhesion machinery and cytoskeleton on the matrix. Such dynamic remodeling of the intracellular architecture should cause modulations of ISD on long-term and whole-cell scales. To characterize the detailed features of the ISD, we analyzed temporal fluctuations of traction forces (Fig. 4).

For patterned gels, the time series of mean traction stress was found to largely fluctuate during cell movement between soft and stiff regions (Figs. 4a and b, blue lines) compared to the control (Fig. 4c, blue lines). This tendency was confirmed for 10 cells in each condition (Figs. 4d-f), suggesting that fluctuation of the mean traction stress was greatest on triangular gels and least on the homogeneous gel. In the case of striped gel (Fig. 4d), they seemed to be intermediate.

Figure 5. Quantification of fluctuation of mean traction stress and cell shapes. (a) Autocorrelation function of the time course of mean traction stress. Red: Stripe-100. Blue: Triangule-150. Orange: Plain-stiff. **(b)** Bar graph of correlation time of mean traction stress. Bar denotes a median value. Error bar connects the 0.25 and 0.75 quantiles. **(c)** Normalized standard deviation (SD) of the traction stress calculated from the time course of mean traction stress of a cell. Standard deviation of the traction stress was divided by the time-averaged traction stress. **(d - f)** Normalized SD of the mean deformation field of the gel just under a cell (d), aspect ratio (e), and cell area (f). Standard deviations of the parameters were divided by the time-averaged values. The Mann–Whitney U test was used to calculate the P value. * P < 0.05. ** P < 0.01. *** P < 0.001. Plain-soft: n = 39. Plain-stiff: n=28. Stripe-600: n = 25. Stripe-100: n = 32. Triangle-250: n = 23. Triangle-150: n = 46.

To characterize the typical time-scale of the observed fluctuations of traction stress, we calculated the population-averaged autocorrelation function of the time series of traction stress (Fig. 5a). The autocorrelation functions exponentially decayed to zero within $2-4$ hours without a clear peak, indicating that the fluctuation of the traction force was rather noisy. Through fitting of the autocorrelation function by an exponential $\exp(-\kappa t)$, the correlation time $T_f = \ln2/\kappa$ for each cell on a triangular patterned gel was found to be about 50 % smaller than that on homogeneous gels (Fig. 5 b). This result quantitatively

confirmed that the temporal fluctuation of traction stress is strongly enhanced on triangular patterned gel.

Regarding the magnitude of the temporal fluctuation of traction stress, the standard deviation of the time series of traction stress divided by the average traction stress of each cell (see Method) was about two times larger on triangular patterned gels than on homogeneous gels (Fig. 5 c). The fluctuation on Stripe-100 was intermediate between those on triangular and homogeneous gels. No significant difference was noted between Stripe- 600 and homogeneous gel. Similar to the fluctuation of the traction stress, the magnitude of the deformation strongly fluctuated on the triangular pattern gels (Fig. 5 d). The large fluctuation of the traction stress should couple with the fluctuation of cell-shaping in correlation with the cell polarization and adhesion. The measured fluctuation of both the cell aspect ratio and area was largest on the triangular patterned gel with small stiff regions (Figs. 5e and f, respectively).

As revealed above, on the matrix with cell-scale stiffness-heterogeneity, traction stress dynamics exhibit characteristic fluctuations depending on the microscopic patterns of stiffness, and especially oscillate between low and high values when the cell body repeatedly intersects the micro-pattern every few hours, as demonstrated around the triangular stiff domains. In conclusion, the matrix with dual cues for competing taxis on cell-scale stiffness-heterogeneity was confirmed to induce extraordinarily large and frequent fluctuation of ISD together with enhanced morphological fluctuations.

Discussion

In this study, we focused on the features of intracellular stress dynamics (ISD) in cells migrating on a matrix with cell-scale stiffness-heterogeneity. To address this issue, two model systems of microelastically patterned gels were used: stiff/soft stripe and stiff triangular patterns. These stripe and triangular patterns were designed to characterize the effects of a spatial constraint for cell-shaping and of different coexistent cues to induce competing cellular taxis (usual and reverse durotaxis) on the ISD, respectively. One of the most striking ISD responses in migrating cells was that the strength of long-term fluctuation of traction force on a whole-cell scale was markedly enhanced in the latter system of triangular patterns compared with a stiffness-homogeneous matrix, which made the cells far from tensional equilibrium. Based on this finding, we discuss the following issues: (1) why is the fluctuation of traction forces enhanced on the triangular patterned system?, and (2) what kind of functional effect would migrating cells receive by remaining far from tensional equilibrium?

First, why was the fluctuation of traction stress amplified, especially on triangular patterns? In principle, large variations in the development and decline of traction forces in an entire cell should involve a sufficient residence time of cells on the stiff and soft regions for the development and dissipation of forces. In addition, the residence times should be balanced between these regions through nomadic cell migration to attain the up-and-down cycles of traction force dynamics (see Fig. S6): i.e., nomadic migration on a matrix with stiffness-heterogeneity is the essential cause of the amplification of the fluctuation of traction force dynamics. A matrix with homogeneous stiffness cannot induce cyclic force development and dissipation. Even though the matrix has a heterogeneous stiffness distribution, a stiff region larger than a single-cell size should trap the cells and tensional equilibrium can be realized. Besides, also in the case of a nano-patterned substrate with stiffness-heterogeneity, focal adhesions of the cells are preferentially formed on the dot where focal adhesions are more stabilized in a microscopic scale[38, 39, 40], so the cells apparently sense such a substrate as an almost homogeneous field of stiffness, and finally reach tensional equilibrium[7, 41]. On the other hand, in the triangular patterns, the essential difference from these systems is that the cells actively remain away from tensional equilibrium in the process of nomadic migration among different regions of stiffness. The essential factor that makes this possible is the presence of dual competing taxis in the matrix. The system was arranged so that competing usual and reverse durotaxis can cause both the development and decrease of traction forces in an iterative manner. Therefore, fluctuations of the ISD can be amplified, which leads to the avoidance of tensional equilibrium.

Secondly, what kind of functional effects do migrating cells on a matrix with cell-scale stiffness-heterogeneity experience? The amplification of ISD fluctuations is linked to fluctuations in CSK tension and remodeling. This may have two major effects on cells. One effect is CSK-related mechanotransduction through signaling pathways including Rho-family GTPases[42], Lats1/2 [43, 44], angimotin[45, 46], and so on. Dynamic remodeling of CSK structures makes the intracellular localization of these factors strongly fluctuate, which causes frequent shuttling of nuclear translocation factors such as YAP/TAZ [47, 48] between the cytoplasm and nucleus. The other effect is the regulation of gene expression linked to nuclear deformation. It has been reported that intermingling of different chromosome territories mechanically occurs in response to cell shaping and nuclear deformation, and contributes to the regulation of gene expression[49]. The avoidance of tensional equilibrium should induce the shuttling of mechanosensitive nuclear translocating factors and the regulation of cellular function through ISD-dependent nuclear deformation. We will report complete set of our findings on functional

modulation of the MSCs that experienced the far-from tensional-equilibrium and the related mechanical-stimuli-dependent regulation of gene expressions in another article soon.

Does nomadic cell migration on a heterogeneous mechanical field exist in a living organism? Some types of cells should migrate on micromechanically heterogeneous milieu, such as typically seen in wound healing of disordered tissues[50, 51], in the biological development of immature organs[52, 53, 54], and in stem cell localization inside a specific niche[55, 56]. In particular, MSCs are delocalized in niches composed of hard bone, soft vessels, and very soft blood cell surroundings in bone marrow, and are nomadically delocalized in the niche with such stiffness-heterogeneity[56]. This in vivo situation regarding nomadic cell migration, as inferred from the model system in the present study, should also induce the avoidance of tensional equilibrium.

Conclusion

The present study revealed the principle conditions of cell-scale stiffness heterogeneity of ECM needed to enhance the fluctuations of ISD in cells migrating on it. The key factor for such enhancement is long-term continuous tactic cell movement, as exemplified in the coexistence of different cues of competing cellular taxis. Markedly enhanced ISD should lead to the avoidance of tensional equilibrium in an entire cell, which is expected to induce CSK-remodeling- and nuclear-deformation-linked functional regulation of migrating cells. This methodology should contribute to development of novel kind of sophisticated biomaterials which enable mechanobiology-based manipulation of cell functions.

Acknowledgments

Funding: This research was supported by AMED-CREST under Grant Number JP20gm0810002.

Author contributions: H. E. conducted all experiments, derivations, computations, and analyses. S. K. proposed the project, directed the research, and proposed the analyses. H. E. and S. K. discussed the results and wrote the paper.

Competing interests: The authors declare no competing interests.

Data and materials availability: All data needed to evaluate the conclusions in the paper are present in the paper and/or the Supplementary Materials. Additional data related to this paper may be requested from the authors.

References

1. J. Folkman, A. Moscona, Role of cell shape in growth control. *Nature* 273, 345-349 (1978).
2. C.S. Chen, M. Mrksich, S. Huang, G.M. Whitesides, D.E. Ingber, Geometric Control of Cell Life and Death. *Science* 276, 1425-1428 (1997).
3. S. Huang, C.S. Chen, D.E. Ingber, Control of cyclin D1, p27(Kip1), and cell cycle progression in human capillary endothelial cells by cell shape and cytoskeletal tension. *Mol. Biol. Cell* 9, 3179-3193 (1998).
4. S. Huang, D.E. Ingber, The structural and mechanical complexity of cell-growth control. *Nat. Cell Biol.* 1, E131-E138 (1999).
5. M.A. Wozniak, et al., ROCK-generated contractility regulates breast epithelial cell differentiation in response to the physical properties of a three-dimensional collagen matrix. *J. Cell Biol.* 163, 583-595 (2003).
6. R. McBeath, et al., Cell shape, cytoskeletal tension, and RhoA regulate stem cell lineage commitment. *Dev. Cell* 6, 483-495 (2004).
7. M.J. Paszek, et al., Tensional homeostasis and the malignant phenotype. *Cancer Cell* 8, 241-245 (2005).
8. A.J. Engler, S. Sen, H.L. Sweeney, D.E. Discher, Matrix elasticity directs stem cell lineage specification. *Cell* 126, 677-689 (2006).
9. A.J. Ridley, et al., Cell migration: integrating signals from front to back. *Science* 302, 1704-1709 (2003).
10. P.J. Van Haastert, P.N. Devreotes, Chemotaxis: signaling the way forward. *Nat. Rev. Mol. Cell Biol.* 5, 626-634 (2004).
11. E.R. Gomes, et al., Nuclear movement regulated by Cdc42, MRCK, myosin, and actin flow establishes MTOC polarization in migrating cells. *Cell* 121, 451-463 (2005).
12. N. Wang, et al., Cell prestress. I. Stiffness and prestress are closely associated in adherent contractile cells. *Am. J. Cell Physiol.* 282, C606-C616 (2002).
13. S. Féréol, et al., Prestress and adhesion site dynamics control cell sensitivity to extracellular stiffness. *Biophys. J.* 96, 2009-2022 (2009).
14. D. Stamenovic, N. Wang, Stress transmission within the cell. *Compr. Physiol.* 1, 499-524 (2011).

15. E.P. Canovic, et al., Biomechanical imaging of cell stiffness and prestress with subcellular resolution. *Biomech. Model Mechanobiol.* 13, 665-678 (2014).

16. K. Franze, et al., Spatial mapping of the mechanical properties of the living retina using scanning force microscopy. *Soft Matter* 7, 3147-3154 (2011).

17. D. Shahmirzadi, et al., Mapping the longitudinal wall stiffness heterogeneities within intact canine aortas using pulse wave imaging (PWI) ex vivo. *J. Biomech.* 46, 1866-1874 (2013).

18. M. Zhu, K. Zhang, H. Tao, S. Hopyan, Y. Sun, Magnetic micromanipulation for in vitro measurement of stiffness heterogeneity and anisotropy in the mouse mandibular arch. *AAAS Res.* 2020, 7914074 (2020).

19. M. Zhu, et al., Spatial mapping of tissue properties in vivo reveals a 3D stiffness gradient in the mouse limb bud. *PNAS* 117, 4781-4791 (2020).

20. M. Dembo, Y.-L. Wang, Stresses at the cell-to-substrate interface during locomotion of fibroblasts. *Biophys. J.* 76, 2307–2316 (1999).

21. J.P. Butler, I.M. Tolic-Norrelykke, B. Fabry, J.J. Fredberg, Traction fields, moments, and strain energy that cells exert on their surroundings. *Am. J. Physiol. Cell Physiol.* 282, C595–C605 (2002).

22. Z. Yang, J.S. Lin, J. Chen, J.H. Wang, Determining substrate displacement and cell traction fields—a new approach. *J. Theor. Biol.* 242, 607-616 (2006).

23. W.R. Legant, et al., Measurement of mechanical tractions exerted by cells in three-dimensional matrices. *Nature Methods* 7, 969–971 (2010).

24. R. Sunyer, et al., Collective cell durotaxis emerges from long-range intercellular force transmission. *Science* 353, 1157-1161 (2016).

25. S. Kidoaki, T. Matsuda, Microelastic gradient gelatinous gels to induce cellular mechanotaxis. *J. Biotechnol.* 133, 225-230 (2008).

26. A. Ueki, S. Kidoaki, Manipulation of cell mechanotaxis by designing curvature of the elasticity boundary on hydrogel matrix. *Biomaterials* 41, 45-52 (2015).

27. L.Trichet, et al., Evidence of a large-scale mechanosensing mechanism for cellular adaptation to substrate stiffness. *PNAS* 109, 6933–6938 (2012).

28. M.T. Breckenridge, R.A. Desai, M.T. Yang, J. Fu, C.S. Chen, Substrates with engineered step changes in rigidity induce traction force polarity and durotaxis. *Cell Mol. Bioeng.* 7, 26–34 (2013).

29. H. Ebata, K. Moriyama, T. Kuboki, S. Kidoaki, General cellular durotaxis induced with cell-scale heterogeneity of matrix-elasticity. *Biomaterials* 230, 119647 (2020).

30. L. Pieuchot, et al., Curvotaxis directs cell migration through cell-scale curvature

landscapes. *Nat. Commun.* 9, 3995 (2018).

31. B. Forster, D. Van De Ville, J. Berent, D. Sage, M. Unser, Complex Wavelets for Extended Depth-of-Field: A New Method for the Fusion of Multichannel Microscopy Images. *Microsc. Res. Tech.* 65(1-2), 33-42 (2004).

32. H. Ebata, et al., Persistent random deformation model of cells crawling on a gel surface. *Sci. Rep.* 8 (2018), p. 5153.

33. J. Steinwachs, et al., Three-dimensional force microscopy of cells in biopolymer networks. *Nat. Methods* 13, 171–176 (2016).

34. H. Tanimoto, M. Sano, A simple force-motion relation for migrating cells revealed by multipole analysis of traction stress. *Biophys. J.* 106, 16–25 (2014).

35. A. Marinkovic, J.D. Mih, J.A. Park, F. Liu, D.J. Tschumperlin, Improved throughput traction microscopy reveals pivotal role for matrix stiffness in fibroblast contractility and TGF-beta responsiveness. *Am. J. Physiol. Lung Cell Mol. Physiol.* 303, L169–L180 (2012).

36. C-M. Lo, H-B. Wang, M. Dembo, Y-l. Wang, Cell movement is guided by the rigidity of the substrate. *Biophys. J.* 79, 144 (2000).

37. J. Tse, A.J. Engler, Stiffness gradients mimicking in vivo tissue variation regulate mesenchymal stem cell fate. *PLoS ONE* 6, e15978 (2011).

38. N.Q. Balaban, et al., Force and focal adhesion assembly: a close relationship studied using elastic micropatterned substrates. *Nat. Cell Biol.* 3, 466-472 (2001).

39. F.-C. Chien, C.W. Kuo, Z.-H. Yang, D.-Y. Chueh, P. Chen, Exploring the formation of focal adhesions on patterned surfaces using super-resolution imaging. *Small* 7, 2906-2913 (2011).

40. S.R. Coyer, et al., Nanopatterning reveals an ECM area threshold for focal adhesion assembly and force transmission that is regulated by integrin activation and cytoskeleton tension. *J. Cell Sci.* 125, 5110-5123 (2012).

41. K.D. Webster, W.P. Ng, A. Fletcher, Tensional homeostasis in single fibroblasts. *Biophys. J.* 107, 146-155 (2014).

42. A.D. Bershadsky, N.Q. Balaban, B. Geiger, Adhesion-dependent cell mechanosensitivity. *Annu. Rev. Cell Dev. Biol.* 19, 677–695 (2003).

43. S. Visser-Grieve, et al., LATS1 tumor suppressor is a novel actin-binding protein and negative regulator of actin polymerization. *Cell Res.* 21, 1513-1516 (2011).

44. Y. Shao, J. Sang, J. Fu, On human pluripotent stem cell control: the rise 3D bioengineering and mechanobiology. *Biomaterials* 52, 26-43 (2015).

45. S.W. Chan, et al., Hippo pathway-independent restriction of TAZ and YAP by angiomotin. *J. Biol. Chem.* 286, 7018-7026 (2011).

46. B. Zhao, et al., Angiomotin is a novel Hippo pathway component that inhibits YAP oncoprotein. *Genes Dev.* 25, 51-63 (2011).

47. K. Wada, K. Itoga, T. Okano, S. Yonemura, H. Sasaki, Hippo pathway regulation by cell morphology and stress fibers. *Development* 138, 3907-3914 (2011).

48. S. Dupont, et al., Role of YAP/TAZ in mechanotransduction. *Nature* 474, 179-183 (2011).

49. Y. Wanga, M. Nagarajana, C. Uhlerb, G.V. Shivashankar, Orientation and repositioning of chromosomes correlate with cell geometry–dependent gene expression. *Mol. Biol. Cell* 28, 1997-2009 (2017).

50. SE. Mutsaers, J.E. Bishop, G. McGrouther, G.J. Laurent, Mechanisms of tissue repair: from wound healing to fibrosis. Int. *J. Biochem. Cell Biol.* 29, 5-17 (1997).

51. S. Ghatak, V.C. Hascall, R.M. Rodriguez, R.R. Markwald, S. Misra. "Inflammation, Wound Healing, and Fibrosis" in Wound Healing: Stem Cells Repair and Restorations, Basic and Clinical Aspects, First Edition. K. Turksen, Ed. (John Wiley & Sons, Inc., 2018).

52. M. Chuai, D. Hughes, C.J. Weijer, Collective epithelial and mesenchymal cell migration during gastrulation. *Curr. Genomics* 13, 267-277 (2012).

53. E. Scarpa, R. Mayor, Collective cell migration in development. *J. Cell Biol.* 212, 143–155 (2016).

54. K. Schilling, Moving into shape: cell migration during the development and histogenesis of the cerebellum. Histochem. *Cell Biol.* 150, 13–36 (2018).

55. B. de Lucas, L.M. Pérez, B.G. Gálvez, Importance and regulation of adult stem cell migration. *J. Cell. Mol. Med.* 22, 746-754 (2018).

56. K. Maeda, et al., Identification of Meflin as a Potential Marker for Mesenchymal Stromal Cells. *Sci. Rep.* 6, 22288 (2016).

Supplementary Information for

Avoiding tensional equilibrium in cells migrating on a matrix with cell-scale stiffness-heterogeneity

Hiroyuki Ebata, Satoru Kidoaki

Corresponding author: Satoru Kidoaki
Email: kidoaki@ms.ifoc.kyushu-u.ac.jp

This PDF file includes:

> Supplementary text
> Figs. S1 to S6
> References for SI reference citations

Flow chart of FEM-based traction force microscopy on microelastically patterned gels.

A flow chart of FEM-based traction force microscopy is shown in Fig. S1. The parameters and procedures that are not mentioned in the main text are as follows.

1. In the calculation of FEM, we used a hexahedron as a unit cell. The size of the hexahedron is 7.8 x 7.8 x 8.0 μm. The size of the imaginary gel used in the numerical calculation is 491.4 x 491.4 x 200 μm. The thickness of the microelastically patterned gel used in the experiment is around 200 μm.

2. To calculate the traction force from $M(x, x')$ and the measured displacement field, the origins of $M(x, x')$ and the displacement field should be matched. For this purpose, we calculated a height map of the fluorescent beads while making the full focus image, which reflected the topography of the surface. Because the topography and elasticity distribution had an almost inverse relation, we calculated the origin of the measured displacement field by pattern-matching between the inverse of height map and the distribution of elasticity used in the calculation of $M(x, x')$.

3. Since we only measured the displacement field of the gels in the x and y directions, we neglect the z-direction of the traction force and the topography of the gel surface as in usual 2-dimensional TFM.

Measurement of elasticity distribution by AFM (Nanowizard, JPK).	Measurement of fluorescent beads with and without the cells (Biorev, Keyence).

Approximation of elasticity distribution by sinusoidal functions (Matlab).	Full focus image was made of z-stack images (Image J).

Displacement $M(x, x')$ due to the test point force was calculated by using FEM (C++).	Displacement of the gel was calculated by using PIV (Flownizer 2D, Detect).

By using the height map of the gel calculated in the full focus image procedure, the origins of the displacement field and elasticity distribution were matched through pattern matching (Matlab).

By solving the inverse problem using $M(x, x')$, the traction force field around a cell was calculated (C++).

Fig. S1. Flow chart of FEM-based traction force microscopy.

Validity of FEM-based traction force microscopy.

To check the validity of FEM-based traction force microscopy (FEM-TFM), we first compared the estimated traction force field from FEM-TFM and Fourier transform traction cytometry (FTTC) on homogeneous gels. FTTC is one of the most widely used methods for estimating the traction force. Figures S2 (a) and (b) show the estimated traction field by FEM-TFM (a) and the estimated traction field by FTTC (b). For FTTC, we adopted a Gaussian filter with a cut-off frequency of 0.066 μm^{-1} for the deformation field. The two methods give a very similar estimated traction field. However, for FEM-TFM, a large traction force tends to be localized in a narrow region. This phenomenon

Fig. S2. Traction force microscopy on homogeneous gels.
(a) Field of the traction force reconstructed by FEM-TFM. (b) Field of the traction force reconstructed by FTTC. (a, b) Black line denotes the cell periphery. (c) Time course of mean traction stress under a cell. Blue: reconstruction by FEM-TFM. Red: reconstruction by FTTC. (a-c) Homogeneous soft gel. E = 5 kPa.

could be due to the regulation method we applied. Figure S2 (c) shows the time course of the mean traction stress under a cell. Blue and red lines represent the traction stress estimated by FEM-TFM and FTTC, respectively. The figure shows complete agreement between these two methods. For FTTC, the mean traction stress increases as the cut-off frequency of the Gaussian filter increases.

Next, through a numerical calculation, we checked the accuracy of the estimation method[1] of the traction force on the elastically patterned substrate. First, we provided an artificial force distribution that mimicked traction forces exerted by a polarized MSC (Fig. S3 (a)). By using FEM, we calculated the deformation field at the surface of the substrate. Next, we added Gaussian noise to the deformation field with a standard deviation of 0.1 μm, which was the typical value of the background noise observed in the experiment (Fig. S3 (b)). Finally, we reconstructed the force distribution from the disturbed deformation field. As shown in Fig. S3 (c), we successfully estimated the force distribution. Compared to the forces in the soft region, estimated forces in the stiff region tended to be noisy, because the signal-to-noise ratio was lower in the stiff region.

Fig. S3. Traction force microscopy on microelastically patterned gels.
(a – c) Test of force reconstruction by numerical calculation. (a) Test forces that mimic the forces from the polarized MSCs. (b) Calculated deformation field at the surface of the gel by using the finite element method. We added white Gaussian noise to the deformation field, where the standard deviation of the noise is 0.1 μm. (c) Estimated force distribution (red arrow) from the disturbed deformation field, Fig. 3 (b). White arrow represents the true forces. (d, e) Dependence of the magnitude of the unbalance of the forces on the mean traction stress of a cell (d) and the mean elasticity under a cell (e). (d) Blue: Triangular-150. Red: Plain-stiff. (e) Blue: Triangle-150. Red: Stripe-100.

Finally, we briefly examined the accuracy of FEM-TFM for cells on the microelastically patterned gels. It has been reported that the unbalance of the traction force vectors $\left|\sum F\right| / \sum |F|$ became nearly zero on homogeneous gels[2, 3], because the inertial force and viscous drag force are almost negligible for adhesive cells. Thus, a condition of zero-sum force should also be satisfied on elastically patterned gels. In general, $\left|\sum F\right| / \sum |F|$ has a finite value due to the error of the measurement of the displacement field and the procedure used for force reconstruction[2, 3]. Thus, the magnitude of unbalance of the forces, $\left|\sum F\right| / \sum |F|$, is a measure of the accuracy of TFM. For all experimental data, average $\left|\sum F\right| / \sum |F|$ are around 2.9 % and 5.7 % for homogeneous and patterned gels, respectively. As shown in Fig. S3 (d), for both homogeneous and patterned gels, unbalance of the forces is negatively correlated with the magnitude of the mean traction stress (correlation coefficient ~ -0.4 – -0.3). Especially, when the traction force is too small (~0.1 kPa), the force distribution was hardly estimated. On the other hand, the mean elasticity under the cell had almost no correlation with the unbalance of the forces (correlation coefficient ~ 0 – 0.1, Fig. S3 (e)). Thus, in our experiment, the accuracy of force reconstruction could not significantly depend on the spatial variation of elasticity.

Threshold of the force spot calculated from the cumulative distribution.
To identify the force spot, we calculated the threshold of the traction stress. To define this threshold, we used the complementary cumulative distribution (CFD, $C(\tau)$) of the traction stress. The derivative of CFD provides the probability distribution function. As shown in Fig. S4, CFD sharply decreased at a small traction stress, which comes from the background noise. CFD had exponential tails, as reported in the previous work on a homogeneous gel. Thus,

$$CFD(Tr) \sim \exp\left(-\frac{Tr}{P_0}\right)$$

is satisfied for large traction stress. The exponential tails should be due to the traction force exerted by a cell. Thus, we use typical stress P_0 as the threshold for the force spot.

Fig. S4. Complementary cumulative distribution of the traction stress of a cell at a certain time.

Magnitude of traction stress in force spots on homogeneous gels.

Figures S5 (a) and (b) show the time series of the field of traction force on Plain-soft and Plain-stiff. Cells on Plain-soft had a rather circular shape, while cells on Plain-stiff had an elongated shape. As shown in Fig. S5 (c), traction stress in the force spot on Plain-stiff was significantly greater than that on Plain-soft.

Fig. S5. Traction forces on the control homogeneous gels.

(a, b) Time series of the traction force field on Plain-soft (a) and Plain-stiff (b). (c) Bar graph of the magnitude of traction stress in force spots. Bar denotes the median value. Error bar connects the 0.25 and 0.75 quantiles. Plain-soft: n = 39. Plain-stiff: n=28.

Residence time in soft and stiff regions.

   We calculated the residence time, which is the amount of time a cell centroid remained in the soft and stiff regions (Fig. S6). Here, we defined the irradiated region of the photomask as a stiff region and the masked region as a soft region (Fig. 1 (c) and (d) inset). Residence times in soft and stiff regions were almost equal for wide stripes and a small triangular pattern. Otherwise, MSCs stayed in stiff regions longer. Compared to the residence time on stripe patterns, the residence time on triangular patterns was short, which indicates that the cell frequently moved between soft and stiff regions.

Fig. S6. Residence time of cells in the soft and stiff regions on each patterned gel.
Bar denotes the median value. Error bar connects the 0.25 and 0.75 quantiles. Stripe-600: striped patterned gel with L = 600 μm. Stripe-100: striped patterned gel with L = 100 μm. Triangle-250: triangular patterned gel with L = 250 μm. Triangle-150: triangular patterned gel with L = 150 μm. Stripe-600: n = 25. Stripe-100: n = 32. Triangle-250: n = 23. Triangle-150: n = 46.

References

1. U.S. Schwarz, *et al.*, Calculation of forces at focal adhesions from elastic substrate data: the effect of localized force and the need for regularization. *Biophys. J.* **83**, 1380-1394 (2002).

2. V. Maruthamuthu, B. Sabass, U.S. Schwarz, M.L. Gardel, Cell-ECM traction force modulates endogenous tension at cell–cell contacts. *Proc. Natl Acad. Sci. USA* **108**, 4708–4713 (2011).

3. H. Tanimoto, M. Sano, A simple force-motion relation for migrating cells revealed by multipole analysis of traction stress. *Biophys. J.* **106**, 16–25 (2014).