EGCG-modified bone graft to modulate the recruitment of M1 macrophage and alleviate the forming of fibrous capsule

Dengbo Yao[a][1], Shengan Rung[a,1], Chenyu Chu[a,b], Yi Man[a,b*], Yili Qu[a*]

[a]*Department of Oral Implantology, West China Hospital of Stomatology, Sichuan University, Chengdu, Sichuan 610041, China, China; Department of orthopedics, Search Sun Yat-sen University, Guangzhou, Guangdong 510275, China*

[b] *State Key Laboratory of Oral Diseases, West China Hospital of Stomatology, Sichuan University, Chengdu, Sichuan 610041*

1 These authors contributed equally to this work.

Corresponding author:

Yi Man, DDS, PhD

Professor and Chair

Department of Oral Implantology

State Key Laboratory of Oral Diseases, West China Hospital of Stomatology, Sichuan University, 14#, 3rd section, Renmin South Road

Chengdu 610041, China

Tel: 0086-28-85503571

Fax: 0086-28-85483678

E-mail: manyi780203@126.com

Yili Qu, DDS, PhD

Associate Professor

State Key Laboratory of Oral Diseases, West China Hospital of Stomatology, Sichuan University, 14#, 3rd section, Renmin South Road

Chengdu 610041, China

Tel: 0086-28-85503571

Email: qqyili@126.com

Abstract

Bone graft with hydroxyapatite, HA, as the main component, is commonly used for bone repair. It will stimulate the bone ECM, providing promising bone regeneration potential. However, due to its pro-fibrosis effect, implant failure of this osteoconductive material is common. To boost the success rate, pure HA is usually modified, or simply being as a part of a biomaterial to improve osteoinductivity. In this paper, we focus on M1 macrophages for its close relationship with fibrosis, acting as the important role during the immune response and the subsequent repairs with its various phenotypes in regulating inflammation. To reduce M1 macrophage recruitment in subcutaneous implantation, we attempt to immerse HA in an extraction of green tea, epigallocatechin-3-gallate (EGCG). The result showed that E-HA considerably compromised the forming of fibrous capsule in HE sections and cell viability was improved in the meanwhile, laying the foundation for future studies on guiding bone regeneration.

Keywords: hydroxyapatite; macrophage; fibrous capsule; EGCG

1   Introduction

One of the key principles of guided bone regeneration (GBR) is to avoid the damaged area being filled with soft tissue, leaving no space for deposition of bone tissue; this can be attained by removing non-osteogenic tissues from interfering bone regeneration while implanting biomaterials. The design of implanted bone substitutes should base on the certain characteristic of the defect, restoring the microenvironment of the tissue before being impaired and keeping from severe fibrosis to promote integration and recovery the function [1,2]. As a primary component of mineral bone, hydroxyapatite (HA) comprised in 60–70 % bone and 98 % dental enamel has been known to possess good bio-compatibility, high osteoconductivity and osteoinductivity [3], remaining in the implant site with slow absorption rate [4]. A 20 years follow-up in maxillary sinus floor elevation by means of commercial bovine- derived bone mineral, which is mainly composed of HA, revealed that new mineralized bone volume remained stable and increased from 16.96% to 22.05% in 20 years, while the volume of the implanted graft has fallen from 35.87% to about 4% [5]. However, in some cases, HA implantation resulted in disappointed healing outcome for thick fibrous

capsule restrained the bone-biomaterial integration.

Epigallocatechin-3-gallate (EGCG), the main catechins of tea, was then

regarding as a great substance for modifying HA, with its multiple

therapeutic effects against various human diseases through its

anti-inflammatory [6], anti- carcinogenic [7], anti-microbial and

anti-oxidative ability [8]. Apart from the above biological properties, in the

field of bone remodeling, EGCG can promote osteogenesis with the

increase the expression of BMP2, Runx2, alkaline phosphatase (ALP),

osteonectin and osteocalcin. A Better ALP activity and mineralization of

bone defect were then achieved [9] to prevent inflammatory bone loss

caused by inhibiting prostaglandin E synthesis [10]. Also, in our previous

study, we found that when adding EGCG to the designed material, EGCG

seemed to bring about a promising microenvironment for bone

regeneration underlining the recruitment and the phenotype of

macrophage [11]. Regarding on macrophage, the persistence of

inflammatory phenotype of it could contribute to fibrosis, which impacts

the bone growth at last. Although the mechanism of fibrosis which

features in implant biodegradation and the blocking of the interaction

between biomaterial and surrounding tissue is still needed to be studied to

further scrutiny; the process was confirmed to be associated with the

participation of certain phenotype of macrophage and various immune

cells. This fibrous response usually began with severe foreign body

reaction as cells being damaged, necrotic and stressed [12-14]. Nevertheless,

principal cells that prompt tissue repair are no different from those

leading to fibrosis capsule, except the long persistence and drastic

communication of the inflammatory cells and myo-fibroblasts [15]. In fact,

with different degree of fibrosis, the outcome of implantation could be

either advantageous to repair and prognosis (deposited provisional

extracellular matrix providing frame for angiogenesis) or harmful to the

host (impair the integration resulting in failure) [16]. Hence, the ideal

situation is to avoid serious foreign body reaction, and direct healing in

the meanwhile through controlling the infiltrated cells and their behavior

to modulate immune response. To sum up, immunoreaction plays a vital

role in the healing process and determines the final result; considering the

broad clinical application of HA material, it is of interest to understand

the immune response after the involvement of EGCG which is capable to

reduce the amount of M1 macrophage. The purpose of the presented

study was to evaluate whether binding EGCG to HA could mitigate

foreign body reaction with less fibrosis, even further enhance bone

regeneration (**Fig. 1**).

2 Materials and Methods

2.1 Materials

We purchased a commercial Heal-All® Bone Repair Material from

Zhenghai Biotechnology (Shandong, China), which mainly contains

hydroxyapatite and collagen, and retains its three-dimensional porous

structure. The EGCG is available from Jiang Xi Lv Kang Natural

Products (Jiang Xi, China). The solvents and chemicals used were all of

analytical grade which need no further purification. To fabricate the

EGCG-modified HA for the follow-up experiment, we dissolved EGCG

in aseptic double distilled water at the concentration of 0.64% (w/v) and

immersed HA in it for 24 h at 4□ in dark. E-HA is then washed with PBS

for three times and preserved in dark at 4°C before use. Optical density

(OD) value at 272 of the EGCG solution was obtain before and after

immersion to ensure E-HA manufactured successfully.

2.2 *In vitro* release profile of E-HA

E-HA was soaked in PBS in 48-well plate at 37°C, 5% CO_2 and

scanned by ultraviolet□visible spectrophotometry to obtain the release

profile. OD value at 272 was used to detect EGCG in solution. At 0 h, the

instrument was calibrated to zero, then, measured the OD value of the

media at 2, 6, 12, 24, 48, 96, 120, 144, 216 h by removing media (200 μl)

and replenishing with fresh buffer (200 μl) each time. The concentration

of the solution and weight of ECGC was transferred from OD value to

specific concentration by establishing standard curve with different

concentrations (7.8, 125, 15.625, 31.25, 62.5, 125, 250 and 500 µg/ml);

the vertical axis shows the absorbance value, and the horizontal axis

shows the concentration of EGCG solution. Linear regression analysis

was performed using the weighted least-square method (W=1/C2).

2.3 Surface morphology observation

Scanning electron microscope (SEM, s-800, HITACHI, Tokyo, Japan)

at 15 kV and digital camera (Canon EOS 6D Mark II) were used to

characterize the morphology of materials. The typical image of each was

captured.

2.4 Cell viability

Murine RAW264.7 cell line (RIKEN BioResource Center, Japan)

were used for quantitative and qualitative cell viability assay. The cells

were cultured in 48-well plates and seeded on the untreated and EGCG

treated HA at 10^4 cells/well cultured in 1640 medium supplemented with

10% fetal bovine serum (FBS). Immediately and after culture for 1, 3, 5

and 7 d, cell viability were evaluated using Cell Counting Kit-8 (CCK-8,

Dojindo Laboratories, Kumamoto, Japan) according to the

manufacturer's instructions. OD value at 450 nm was measured using

micro-plate reader (Multiskan, Thermo, USA).

2.5 Establishment of *in vivo* Model

This experimental protocol was approved by the Institutional Review

Board of West China Dental Hospital (No. WCHSIRB-D-2017-097). *In*

vivo experiments were performed with 6-8-week-old C57 mouse (Animal

Experimental Center of Sichuan University) weighing about 37.5 g. Two

parallel surgical sites were established on each mouse for pure HA and

E-HA, respectively (N≥3). To minimize the bias caused by the surgical

site, materials were implanted with different arrangements.

2.6 Surgical procedures

After anesthetized with 0.15ml 10% chloral hydrate, the skin on the

back of the mouse above the surgical area was shaved and followed the

aseptic process before implantation. Two sagittal incisions of about 10

mm were made on the dorsal skin to create subcutaneous pockets for

bone repair material. Pure bone repair material and the EGCG-modified

one were then implanted into the pockets. Subsequently, the incision was

sutured with horizontal mattress 3.0 Vicryl suture (Ethicon, CA, USA).

The animals were housed in a room specially designed for conducting an

animal experiment and fed on a standard laboratory diet. After 7 days of

recovery, the animals were sacrificed. Then, bone repair material and

whole skin samples around the surgical site were collected.

2.7   Hematoxylin-eosin (HE) staining

For HE staining, 8 μm sections were incubated at 65 $^\circ$ C for 4 h to

dewax. After ethanol dehydration, hematoxylin was stained for 5 min,

and 1% hydrochloric acid ethanol was differentiated for 2 h. Sections

were then incubated for 2 min in 0.2% ammonia water, followed by

staining with eosin for 1 min. After dehydration, the sections were

removed and fixed with neutral resin. The slides were viewed with a

microscope with 200 $\times$ oil immersion objective (Olympus Corporation,

Tokyo, Japan); scanned with a digital slide scanning system (PRECICE,

Beijing, China).

2.8   Immunofluorescent staining

The paraffin-embedded tissue was simply cut into 8 μm thick

sections. After dewaxing and hydrating, immunostaining was conducted.

Sections were pre-treated with 0.1% Triton X-100 in PBS with 1% bovine

serum albumin for 1 h, 1% t20 for 20 min, and PBS was washed for 20

minutes. Briefly, the sections were incubated for 30 min in the dark. The

excess dye was washed away with PBS. Sections were incubated isotype

with antibodies to exclude false positive staining. At least three parallel

sections from different implantation sites were observed under a

fluorescence microscope (Zeiss stereoscopic finding, V20, Germany).

Five fields were randomly selected for immunofluorescence

determination. Macrophages were magnified 400 times to exclude false

positive staining. Semi-quantitative analysis was then performed at a

magnification of 40 times. CaseViewer 2.1 and Image Pro Plus 7.0 (n = 5)

were used to measure the fluorescence intensity of 5 random spots.

Hoechst staining analysis was performed at the same time.

2.9   Statistical analysis

All quantitative data are presented as mean ± standard deviation.

Statistical calculations were performed using GraphPad Prism 5.0 (San

Diego, CA, USA). The semi-quantitative data of immunofluorescent

staining that did not conform to the normal distribution were further

analyzed by Mann-Whitney U test, as statistical significance between

groups was analyzed by analysis of variance (ANOVA) followed by

Tukey's multiple comparison tests. P <0.05 was considered statistically

significant. The standard curve of EGCG solution was established with

linear regression. Pearson's correlation analysis was used to analyze the

detected concentration.

3 Results

3.1 *In vitro* release profile of E-HA

After immersing HA into EGCG solution, the OD value of that

decreased, which represented that the concentration of which reduced,

and E-HA was fabricated successfully (**Fig. 3A**). The concentration was

calculated based on the standard curve of EGCG solution. To establish

the standard curve, EGCG solutions were detected by ultraviolet⬚visible

spectrophotometry, which revealed that EGCG at different concentrations

had a maximum absorption wavelength of 272 nm. Therefore, 272 nm

was selected for detection, and the absorbance value was set as the

vertical axis with the corresponding concentration setting as horizontal

axis. The regression equation was identified to be y=0.0067x-0.0327,

with R^2 =0.9998. The linear concentration range was identified to be

7.8-500 µg/ml for EGCG, presenting in **Fig. 3B**. Cumulative release

profile of E-HA was obtained by detecting the amount of EGCG released

to the buffer with time. The release profile demonstrated a minimal initial

release, with only approximately 10µg EGCG being released in the first 3

days, followed by a continuous release up to about 100µg the next 3 days.

Extra release about 75µg was measured at 216 h (**Fig. 3C**).

3.2   Surface morphology

The morphology of bone repair material is shown in **Fig. 2A**. It is

inconsistent in shape, different in size, and featuring in the porous

structure. After adding EGCG, the surface outlook of bone repair material

became directional, dense and uniform, which may be caused by the

hydrogen bond between EGCG and collagen fibers. From the SEM image,

it can also be seen that the surface roughness decreased (**Fig. 2B**).

3.3   Cell viability

RAW 264.7 were seeded on the material for 7 days; during all period

of time, cell viability of group HA stayed relatively constant, whereas the

effect of EGCG towards which increased when the co-culture time was

prolonged. On day 0 and day 1, there was no statistical significance

between group HA and E- HA, whereas on day 3 and day 5, cell viability

slightly improved with the involvement of EGCG, which thrived over

time and was highest on day 7 (**Fig. 4**). That is, the modification of

EGCG did not harm the cell viability of the RAW 264.7 and was even

conducive to the improvement of cell viability.

3.4　The severity of fibrosis after HA and E-HA implantation is

related to different phenotypes of infiltrated macrophages

In order to evaluate whether EGCG-modified bone repair materials

are able to mitigate fibrosis by modulating the immune microenvironment,

the selected materials were implanted subcutaneously (**Fig. 5A-F**), and

the reaction of immune cell towards EGCG modification was investigated

by HE staining (**Fig. 5G**). On day 7 after the bone repair material was

implanted, incisions of both groups healed well. And the nonvascular

tubular structure could be observed, whereas more abundant in group E-

HA. The fibrous encapsulation effect was much more intense in the group

HA, with a large amount of collagen fibers deposited on the surface of the

material. And the surrounding immune cells would migrate around the

bone repair material, forming an inflammatory cell infiltration zone. The

inflammation resulted from the implant of EGCG-load bone repair

material is lighter than pure bone repair material. We further explored the

phenotype of macrophage at the same time point. From the

immunofluorescence staining images of Hoechst, CD68 and iNOS (**Fig.**

5H), we could find that in group HA and E- HA recruited macrophages of

different phenotype. Although the detection of CD68 which serves as the

surface marker for macrophage could be seen in both groups, iNOS, a

representative for M1 phenotype macrophages, cannot be detected in the

E-HA group, whereas existed in group HA, reconfirming macrophage

infiltration and the effect of EGCG in anti-inflammation.

4　Discussion:

Serious defects in the hard tissue would cause self-healing to fail. At

the present, the application of biomaterial and GBR membrane are often

used in clinical practice to block the invasion of soft tissue in the growth

space of the hard tissue; this effect has been widely proved. Among them,

collagen membrane modified by EGCG had been thorough a deep

research, including biotoxicity [17], effects on osteoblasts [18], chemotaxis of

macrophages [19], phenotypic regulation [11], and Foreign Body Reaction

(FBR) [20].For the implanted biomaterial, the ideal therapeutic effect cannot

be achieved due to the absence of organic components and the lack of

biological signals in pure HA. When designing a biomaterial, HA is often

a part of it, such as BMP-2 immobilized PLGA/hydroxyapatite fibrous

scaffold [21]; or modified, such as loading Nerve Growth Factor [22].

Therefore, in order to better stimulate bone ECM and provide suitable

microenvironment for the regeneration of the hard tissue, we used a

bovine-derived decellularized bone graft which composed of HA and

collagen type I, which is similar to the composition of bone and the

current commercial dental bone substitute.

As a biomaterial is implanted, not only osteoblasts are involved in the

repair, but the interaction between the material and immune cells is the

key in the healing of tissue. The adsorption of proteins i is the beginning

of the acute inflammatory phase of FBR, and the inflammation will

gradually transit to tissue repair. Right after the surgery was performed,

macrophages quickly identified the implant, and were recruited to

biomaterial the forming specific immune microenvironment. Macrophage

is involved in the starting of inflammation and the following tissue

reconstruction with the secretion of cytokines. Macrophage phenotype

transformation for tissue from M1 to M2 is necessary in both hard and

soft tissue repair; long-term or severe inflammation usually contribute to

fibrous capsule formation by M2 macrophages, blocking material with

the surrounding and ending up with bone- biomaterial integration failure

[23]. The main cause of implant failure, aseptic loosening, is due to the

formation of wear particles from the implant under phagocytosis, which

promotes macrophages to secrete cytokines related to bone absorption.

HA-induced phagocytosis depended on IL-1β and TNF-α produced by

macrophages [24], which was closely related to M1 phenotype. In the

meanwhile, the presence of a long-term high M1/M2 phenotypic ratio

macrophages often indicated the failure of implantation. Thus, in addition

to manufacturing biomaterials close to the natural ECM, the phenotype of

macrophages should also be taken into consideration. Biodegradable

three-dimensional scaffold which was comprised of polymer matrix

(polylactic acid and polyethylene glycol), nano hydroxyapatite, and

dexamethasone utilizing 3D printing technology to precisely control

properties and shape, promoted macrophage polarization towards M2

phenotype and osteogenesis that downregulated IL-6 and iNOS

expression by M1 macrophage [25]. In fact, both M1 and M2 phenotypes

are indispensable for tissue healing, and M1 macrophage can even guide

the subsequent behavior of the M2. Only the existing time matters, as

fortunate repair can never be accompanied by excessive M1 polarization

[26]. CD68, which is widely acknowledged as a marker for macrophage,

was stained to identify the presence of it and confirmed the reduction of

M1 phenotype by adding EGCG can through iNOS.

Apart from absenting M1 macrophage, we also found that EGCG

made the difference to the surface morphology, shown under scanning

electron microscope, which has close relationship with FBR. Researchers

had speculated that the mechanism by which HA coating promotes

osteogenesis may take place on the basis of its surface morphology rather

than on stimulating macrophages to express BMP2, since HA could

significantly up-regulat proinflammatory factors, TNF-α, by M1

macrophages, further inhibited M2 macrophages from expressing BMP2

that featured in osteoconductive [27]. In other words, HA has a

proinflammatory tendency and is not conductive to the expression of

BMP2, both of which may be improved by the addition of EGCG [6,9].

However, whether EGCG can promote the polarization of macrophages

toward M2 and stimulate the secretion of desired cytokines, as our

previous studies on collagen membranes have shown, it needs further

investigation.

Cytotoxicity is another essential aspect to evaluate biocompatibility.

Karin H. Müller and Michael Motskin et al. found that HA nanoparticles

formed large agglomerates in the medium resulting in extensive particle

uptake in macrophage and sequestered in surface-connected compartment

[28], triggered dose-dependent cytotoxicity. To reduce cytotoxicity, particles

could be citrated or added dispersant Darvan 7 [29]. Our HA particle size is

between 1000-2000 μm, and cell viability even improved after adding

EGCG. We found that the effect of EGCG on cell viability was related to

its released amount from E-HA. The in vitro EGCG release rate assay

showed that more EGCG was released over time. The longer the culture

time, the more significant the effect EGCG puts on cell viability.

Therefore, it is considered that the addition of EGCG will not reduce, but

even increase, cell activity, which is beneficial for healing.

This article only mentioned a subcutaneous method to reduce M1

macrophage. As for the specific mechanism and phenotypic

transformation, including the ratio of M1/M2 macrophage at different

time points, will be discussed in the bone model in the future.

5 Conclusion:

To sum up, we have found a possible strategy to modify bone repair

material, which acquired anti-inflammatory effect for lowering the

accumulation of M1 macrophage and further regulated the fibrosis, while

the effect of EGCG on the surface morphology cannot be excluded. The

specific mechanism of reducing the fibrosis needs to be verified. The

results of this study will pave the way for subsequent experiments and

explore the osteogenesis effect of E-HA as this is surely the most

important effect for bone repair materials. At any circumstances，EGCG

do improve cell activity after being added to HA and no $CD68^+iNOS^+$

cells were detected in the immunofluorescence staining 7D post-surgery,

indicating that the addition of EGCG could bring hope for the following

regenerative cascade.

Grant

Statement Conflict of Interest

There are no conflicts of interest related to this manuscript

Reference

1.   Christman KL. Biomaterials for tissue repair. Science
        2019;363(6425):340–341.
2.   Sadtler K, Singh A, T. Wolf M, Wang X, Pardoll D, H. Elisseeff J.
        Design, clinical translation and immunological response of
        biomaterials in regenerative medicine. Nature reviews materials
        2016;1(7):1–17.

3.   Dutta SR, Passi D, Singh P, Bhuibhar A. Ceramic and non-ceramic
hydroxyapatite as a bone graft material: a brief review. Ir J Med Sci
2015;184(1):101–6.

4.   Ratnayake JTB, Mucalo M, Dias GJ. Substituted hydroxyapatites
for bone regeneration: A review of current trends. Journal of
biomedical materials research. Part B, Applied biomaterials
2017;105(5):1285–1299.

5.   Valentini P, Bosshardt DD. 20-Year Follow-up in Maxillary Sinus
Floor Elevation Using Bovine-Derived Bone Mineral: A Case
Report with Histologic and Histomorphometric Evaluation. The
International journal of oral & maxillofacial implants
2018;33(6):1345–1350.

6.   Ohishi T, Goto S, Monira P, Isemura M, Nakamura Y.
Anti-inflammatory Action of Green Tea. Antiinflamm Antiallergy
Agents Med Chem 2016;15(2):74–90.

7.   Negri A, Naponelli V, Rizzi F, Bettuzzi S. Molecular Targets of
Epigallocatechin-Gallate (EGCG): A Special Focus on Signal
Transduction and Cancer. Nutrients 2018;10(12):1936.

8.   Chakrawarti L, Agrawal R, Dang S, Gupta S, Gabrani R.
Therapeutic effects of EGCG: a patent review. Expert Opin Ther
Pat 2016;26(8):907–16.

9.   Lin SY, Kang L, Wang CZ, Huang HH, Cheng TL, Huang HT, Lee
MJ, Lin YS, Ho ML, Wang GJ and others.
(-)-Epigallocatechin-3-Gallate (EGCG) Enhances Osteogenic
Differentiation of Human Bone Marrow Mesenchymal Stem Cells.
Molecules 2018;23(12):3221

10.   Tominari T, Ichimaru R, Yoshinouchi S, Matsumoto C, Watanabe K,
Hirata M, Grundler FMW, Inada M, Miyaura C. Effects of
O-methylated (-)-epigallocatechin gallate (EGCG) on LPS-induced
osteoclastogenesis, bone resorption, and alveolar bone loss in mice.
FEBS Open Bio 2017;7(12):1972–1981.

11.   Chu C, Wang Y, Wang Y, Yang R, Liu L, Rung S, Xiang L, Wu Y,
Du S, Man Y and others. Evaluation of epigallocatechin-3-gallate

(EGCG) modified collagen in guided bone regeneration (GBR) surgery and modulation of macrophage phenotype. Materials Science and Engineering: C 2019;99:73–82.

12. Perciani CT, MacParland SA. Lifting the veil on macrophage diversity in tissue regeneration and fibrosis. Sci Immunol 2019;4(40):eaaz0749.

13. Shook BA, Wasko RR, Rivera-Gonzalez GC, Salazar-Gatzimas E, López-Giráldez F, Dash BC, Muñoz-Rojas AR, Aultman KD, Zwick RK, Lei V and others. Myofibroblast proliferation and heterogeneity are supported by macrophages during skin repair. Science 2018;362(6417):eaar2971.

14. Klopfleisch R, Jung F. The pathology of the foreign body reaction against biomaterials. J Biomed Mater Res A 2017;105(3):927–940.

15. Pakshir P, Hinz B. The big five in fibrosis: Macrophages, myofibroblasts, matrix, mechanics, and miscommunication. Matrix Biology 2018;68-69:81–93.

16. Tang L, Eaton JW. Inflammatory responses to biomaterials. Am J Clin Pathol 1995;103(4):466–471.

17. Chu C, Deng J, Hou Y, Xiang L, Wu Y, Qu Y, Man Y. Application of PEG and EGCG modified collagen-base membrane to promote osteoblasts proliferation. Materials Science and Engineering: C 2017;76:31–36.

18. Chu C, Deng J, Xiang L, Wu Y, Wei X, Qu Y, Man Y. Evaluation of epigallocatechin-3-gallate (EGCG) cross-linked collagen membranes and concerns on osteoblasts. Materials Science and Engineering: C 2016;67:386–394.

19. Chu C, Liu L, Wang Y, Yang R, Hu C, Rung S, Man Y, Qu Y. Evaluation of epigallocatechin-3-gallate (EGCG)-modified scaffold determines macrophage recruitment. Materials science & engineering. C, Materials for biological applications 2019;100:505–513.

20. Chu C, Liu L, Wang Y, Wei S, Wang Y, Man Y, Qu Y. Macrophage phenotype in the epigallocatechin-3-gallate (EGCG)-modified

439  collagen determines foreign body reaction. Journal of Tissue
440  Engineering and Regenerative Medicine 2018;12(6):1499–1507.

441 21. Zhao X, Han Y, Li J, Cai B, Gao H, Feng W, Li S, Liu J, Li D.
442  BMP-2 immobilized PLGA/hydroxyapatite fibrous scaffold via
443  polydopamine stimulates osteoblast growth. Materials science &
444  engineering. C, Materials for biological applications
445  2017;78:658–666.

446 22. Han X, Liu H, Kuang X, Wang Z, Wang X. Silk Fibroin Improves
447  the Release of Nerve Growth Factor from Hydroxyapatite Particles
448  Maintaining its Bioactivity. Current drug delivery
449  2018;15(6):879–886.

450 23. Chen Z, Klein T, Murray RZ, Crawford R, Chang J, Wu C, Xiao Y.
451  Osteoimmunomodulation for the development of advanced bone
452  biomaterials. Materials Today 2016;19(6):304–321.

453 24. Gopinath VK, Musa M, Samsudin AR, Sosroseno W. Role of
454  interleukin-1beta and tumour necrosis factor-alpha on
455  hydroxyapatite-induced phagocytosis by murine macrophages
456  (RAW264.7 cells). British journal of biomedical science
457  2006;63(4):176–178.

458 25. Ma Q-L, Zhao L-Z, Liu R-R, Jin B-Q, Song W, Wang Y, Zhang Y-S,
459  Chen L-H, Zhang Y-M. Improved implant osseointegration of a
460  nanostructured titanium surface via mediation of macrophage
461  polarization. Biomaterials 2014;35(37):9853–9867.

462 26. Chu C, Liu L, Rung S, Wang Y, Ma Y, Hu C, Zhao X, Man Y, Qu Y.
463  Modulation of foreign body reaction and macrophage phenotypes
464  concerning microenvironment. J Biomed Mater Res A
465  2020;108(1):127–135.

466 27. Jakobsen SS, Larsen A, Stoltenberg M, Bruun JM, Soballe K.
467  Hydroxyapatite Coatings Did not Increase TGF-β and BMP-2
468  Secretion in Murine J774A.1 Macrophages, but Induced a
469  Pro-inflammatory Cytokine Response. Journal of Biomaterials
470  Science, Polymer Edition 2009;20(4):455–465.

471 28. Motskin M, Müller KH, Genoud C, Monteith AG, Skepper JN. The

sequestration of hydroxyapatite nanoparticles by human
monocyte-macrophages in a compartment that allows free diffusion
with the extracellular environment. Biomaterials
2011;32(35):9470–9482.
29.   Müller KH, Motskin M, Philpott AJ, Routh AF, Shanahan CM,
Duer MJ, Skepper JN. The effect of particle agglomeration on the
formation of a surface-connected compartment induced by
hydroxyapatite nanoparticles in human monocyte-derived
macrophages. Biomaterials 2014;35(3):1074–1088.
481

Figure 1. Schematic illustration.

Diagram of in vivo experiments. (A) Showing the period to harvest and

the subsequently executed testing. (B) Cell viability, macrophage

polarization, and fibrosis outcome of EGCG modified bone graft,

compared with bone graft alone.

Figure 2. Representative image of HA and E-HA. (A) Surface

morphology of materials is clearly presented under digital camera and

(B) scanning electron microscope.

Figure 3. The establishment and release of EGCG on the bone graft.

(A) E-HA fabrication assessment by detecting the concentration of EGCG

solution before and after immersing HA. (B) The standard curve of

EGCG solution at the concentration between 7.8 and 500 μg/ml, (C)

obtained under OD value of 272. *In vitro* cumulative release profile of

E-HA.

Figure 4. Cell viability assay. Culturing RAW 264.7 on deproteinized

bone material with or without EGCG treatment, then the cell viability was

detected on day 0, 1, 3, 5 and 7. NS= no significance; *= $P<0.05$, **=

$P<0.01$, ***= $p<0.001$.

Figure 5. Evaluation of fibrosis and phenotype of infiltrating

macrophages after implantation. (A-C) Pictures of harvested tissue

encapsulated with (D-E) HA and E-HA. (G) HE staining result on day 7

post-surgery. (H) Immunofluorescent staining result on day 7 post-

surgery. Hoechst, blue; CD68, green; iNOS, red. (I) Semi-quantitative

analysis of immunofluorescent staining result. NS= no significance; **=

$P<0.01$.