Rapidly self-sterilizing PPE capable of 99% SARS-CoV-2 deactivation in 30 seconds.

Authors: Alfred A. Zinn[1], Mina Izadjoo[2], Hosan Kim[2], Kylene Kehn-Hall[3,4], Caitlin Woodson[3,4], Rachel L. Brody[1], Robert R. Roth[1], Agustin Vega[1], Khanh K. Nguyen[1], Nhi T. Ngo[1], Hannah T. Zinn[1], Lauren Panny[3,4], Rafaela Flor[4], Nicholas Antonopoulos[1], Randall M. Stoltenberg[1]

[1]Kuprion, Inc. San Jose, CA 95134, USA
[2]Integrated Pharma Services, Frederick, MD 21704, USA
[3]Department of Biomedical Sciences and Pathobiology, Virginia-Maryland College of Veterinary Medicine, Virginia Polytechnic Institute and State University, Blacksburg, VA 24061, USA
[4]National Center for Biodefense and Infectious Diseases, School of Systems Biology, George Mason University, Manassas, VA, USA

Abstract:

The Coronavirus disease 2019 (COVID-19) has created an acute worldwide demand for sustained broadband pathogen suppression in households, hospitals, and public spaces. Infections have surged past 160,000 daily new cases in the US, the highest rates yet seen during the pandemic. In response, we have created a rapid-acting, self-sterilizing PPE configurations capable of killing SARS-CoV-2 and other microbes in seconds. The highly active material destroys pathogens faster than any conventional copper configuration. The material maintains its antimicrobial efficacy over sustained use and is shelf stable. We have performed rigorous testing in accordance with guidelines from U.S. governing authorities and believe that the material could offer broad spectrum, non-selective defense against most microbes via integration into masks and other protective equipment.

Summary:

A novel configuration of copper offers continued fast-acting protection against viruses and bacteria, including SARS-CoV-2.

Main Text:

The rush on PPE from the pandemic's onset illustrated a fatal flaw in our approach to microbe management. The world relies on stockpiles of resources to create a clean field that is sullied

immediately upon contact. The sterility provided by widely used disinfectant options is all too fleeting. Demands imposed by COVID-19 turned inefficiencies into breaking points; there is simply not enough sterile equipment in the world to shield ourselves if materials do not offer lasting protection. The masks we are using, while effective, accumulate bacteria over the course of normal wear and are thus limited to a single use before they must be washed or discarded.[1] We need a material that keeps hands, surfaces, and tools free of pathogens over prolonged use.

Our copper configuration, termed ActiveCopper (aCu), was first produced as a novel all-copper alternative to tin-based solder. Catalysis taught us that a material's surface reactivity is contingent on its surface area and energy; the larger the surface area, the more reactive it will be.[2, 3] aCu owes its activity to a large interconnected meso-structured metal network consisting of polymeric gel-like copper material with meso-scale porosity and surface roughness. As COVID-19 overwhelmed the world in early 2020, we hypothesized that this unique structure and its surfactant shell should be highly antimicrobial. The literature is rife with examples of copper as an antimicrobial and the EPA has approved hundreds of copper alloys for their disinfectant properties.[4–6] However, they are slow-acting and require up to 4 hours to fully deactivate microbes. Because conventional copper surfaces disinfect more slowly, they still need to be disinfected regularly. Given the structural differences between aCu and previous copper iterations, it made sense to explore aCu's anti-COVID activity.

Fig. 1 Synthesis of aCu via reduction of CuCl₂. Anhydrous copper(II) chloride is reduced with sodium borohydride in the presence of amine surfactants to form the raw aCu material. The reaction takes place near room temperature. The borane generated during the reduction forms borane-amine complexes which are later hydrolyzed upon the addition of water to remove NaCl byproducts. The amines assist in dissolving the copper(II) chloride and mediate resultant particle sizes. This prevents the aCu particles from oxidizing and continuing to grow.

aCu is manufactured using a bottom-up synthesis approach via NaBH$_4$ reduction of CuCl$_2$ in solution (Fig. 1). The resultant copper material is rendered stable through the formation of a very sticky paste-like metallic gel. It behaves like a typical non-Newtonian "liquid" with high thixotropy (Fig. 5). The specially designed amine surfactant layer exerts strong cohesion via hydrophobic interactions and organic end-chain entanglement, which holds the dense metallic gel together with the aid of the high surface area and energy (Fig. 2) and does not dissolve in

water and most organic solvents. Its structure can be described as a dense but flowable metallic gel-like paste with an interconnected meso-scale network, porosity and surface roughness that enables safe handling and processing; it never turns into an airborne powder but rather hardens into a solid copper mass similar to a xerogel, allowing the material to retain the high activity of the unfused aCu.

Fig. 2: **High magnification scanning electron microscopy images of aCu on 45/55 cellulose/polyester fabric**. (**A**) fibers of the cellulose/polyester fabric coated with aCu. (**B**) 10,000x magnification of aCu on fabric, showing copper agglomerates in the 3-7 micrometer range.

We set out to quantify aCu's activity against a host of viruses and bacteria with the eventual goal of testing against the SARS-CoV-2 virus. We formulated water-based paints to coat fabrics and porous filter materials that could be used in face masks and air purification units such as HVAC systems in airplanes, hospitals or public transportation.

As an initial rapid efficacy pre-screen, we tested *Salmonella enterica*-specific bacteriophage Ø32 against aCu. Two aCu formulations, A and E, were applied to sections of a cellulose/polyester fabric blend (45/55% w/w) that is commonly used to make surgical masks. Both formulations were applied at a concentration of $2 \cdot 5$ mg/in^2; sample E included a small amount of CuCl$_2$ as an activator. The samples were inoculated with *Salmonella* bacteriophage and the resultant viral plaques were counted at 5, 30, and 60 min post-challenge. All active samples showed 100% viral kill rates after just 5 minutes; no plaques remained to be counted (Fig. 3A). To ensure that these dramatic results were accurate, this test was duplicated on a different rayon/polyester (70/30% w/w) fabric blend and yielded the same result (Fig. 3B).

To determine how quickly aCu acts against microbes, we opted to further decrease the testing time increments to as short as 30 sec and test the kill rate upon initial contact.

Cellulose/polyester (45/55) samples were sprayed with two variations of aCu paint: C4 contained paint alone, D4 included CuCl$_2$ as an activator. Viral challenges of *Salmonella* bacteriophage were administered to each of the samples. The remaining phages were measured at seven intervals (T0, T30s, T1, T2, T2.5, T3, T5 min). At T0, reductions of 15,000 PFU/ml (C4) and

62,000 PFU/ml (D4), 6% and 23% respectively, had already taken place (Fig. 3Ca, b). By T2, the D4 sample had achieved a 100% kill rate of both phage concentrations (Fig. 3Ca, b). Sample C4 achieved 100% kill rates of the $2 \cdot 7 \times 10^4$ PFU/ml concentration by T2 and the $2 \cdot 7 \times 10^5$ PFU/ml concentration by T3 (Fig. 3Ca, b). This compares very favorably to 70% ethanol, the disinfectant regarded as the standard, which achieved a 3 $\log_{10}$ reduction of SARS-CoV-2 after 30 seconds,[7] and a 2 $\log_{10}$ reduction of feline calicivirus after one minute.[8]

Metal	Unused, Purified Water	Untreated – Normal Flow	Untreated – Reverse Flow	Treated – Normal Flow	Treated – Reverse Flow
Cu	0·01 ppb	0·09 ppb	0·06 ppb	0·07 ppb	0·11 ppb
Fe	0·02 ppb	0·42 ppb	0·19 ppb	0·14 ppb	0·14 ppb
Ca	0·01 ppb	0·74 ppb	3·55 ppb	1·30 ppb	1·04 ppb

Fig. 3F

Metal	Unused Filter 1	Unused Filter 2	Untreated Normal Flow 1	Untreated Normal Flow 2	Untreated Reverse Flow	Treated Normal Flow 1	Treated Normal Flow 2	Treated Reverse Flow
Cu	4 ng	6 ng	11 ng	7 ng	5 ng	10 ng	204 ng	6 ng
Fe	193 ng	210 ng	396 ng	319 ng	280 ng	320 ng	337 ng	293 ng
Ca	323 ng	359 ng	337 ng	368 ng	309 ng	369 ng	566 ng	359 ng

Fig. 3G

Fig. 3: Results from antimicrobial tests of aCu. From left to right, **A** percentage of viral plaques remaining after 5 and 60 mins. exposure of bacteriophage to aCu – comparison between 4 active samples and 1 control per duration. **B** 100% kill rate of bacteriophage after 30 min on aCu-treat rayon/polyester fabric. **C (a&b)** deactivation of $2·7*10^4$ (a) and $2·7*10^5$ (b) PFU/ml viral titer by 2 formulations (C&D) of aCu. **D** Deactivation of bacteriophage on 2 year old aCu-coated aluminum substrate over short duration. **E** Deactivation of SARS-CoV-2 on aCu-coated fabric. **F** and **G** Filter metal testing from collected water (**F**) and ICP-MS (**G**) after shedding/particulate testing. Fe indicates traces of stainless steel – stainless steel sample holders were used. Ca indicates environmental contamination/sample hygiene. Spike of copper at treated normal flow 2 is commensurate with other increases, indicating environmental sample contamination.

Next, we measured performance over an extended period of use to address the durability requirements established by the Environmental Protection Agency (EPA) for the registration of copper alloys as antimicrobial agents. Regulations stipulate that compounds must be able to continuously reduce a recurrent bacterial load,[9] which would be expected in a hospital setting or on surfaces in public transportation.

Over 14 days, aCu's sustained antimicrobial efficacy was tested according to EPA protocol, which calls for repeated inoculations over the course of 21 hours.[9] We lengthened the timeline to better gauge the longevity we could expect from copper-coated fabrics (fig. S2) and applied a very large viral load of $2·7x10^7$ PFU/ml to simulate high touch-traffic scenarios. The first extended exposure test was planned for 10 days anticipating some performance degradation. aCu-coated cellulose/polyester (45/55) fabric was treated with a daily titer of *Salmonella* bacteriophage Ø32 ($2·7x10^7$ PFU/ml). After 10 days, antimicrobial capacity showed no degradation whatsoever. We opted to extend the test to 14 days. After 14 days the aCu-coated sample had maintained its antiviral capacity (fig. S2). The material was as active against phages

on day 14 as on day 1. The results of this test demonstrate the high efficacy of aCu even when subjected to the frequent and intense pathogen exposure that is a fixture of health care settings.

We wanted to understand what kind of durability and longevity we could expect from solid surfaces coated with a layer of aCu paint. To test this, we used a piece of aluminum (2x2 cm, 3 mm thick) that had been fully coated with aCu paint in 2018 (batch #K0604-56ABP) and stored indoors in ambient conditions with full exposure to seasonal temperature swings. It was challenged with *Salmonella* bacteriophage Ø32 and the antimicrobial response was measured at rapid intervals (T0, 15, 30, 60 seconds). By T15, 94% of the phages had been killed, by T30 97%, and by T60 fully 100% of the phages had been killed, leaving no viral plaques to count (Fig. 3D). SEM analysis revealed that the copper material had not changed its morphology over the two years, indicating excellent shelf-stability (fig. S4a). From these data we learned that aCu maintains vigorous antimicrobial activity independent of its substrate; textiles and hard surfaces are both viable mediums.

Fig. 4: SEM image of two-year-old copper coating layer on Al substrate. A after initial coating in 2018; **B** 2 years later. Both show very similar agglomerated particle morphology, shape and size (images have been sized to reflect identical scale).

Encouraged by aCu's durability and fast action, we conducted efficacy testing based on ISO test #18184:2019 – Determination of Antiviral Activity of Textile Products. aCu was applied to cellulose/polyester fabric with additional $CuCl_2$ as an activator. Samples were challenged with human influenza A (H1N1 & H3N2) and feline calicivirus VR-782. Viral suspensions were deposited onto the fabric samples and after two hours (shortest allowable with ISO) of incubation the aCu textile had reduced the concentrations of all three viruses by more than 99% (Table S6b). H1N1 was reduced by 99·93%, H3N2 by 99·77%, and feline calicivirus by 99·42%. It is encouraging to yield favorable results against both enveloped (influenza) and non-enveloped (calicivirus) viruses.

These preliminary investigations culminated in a test against the SARS-CoV-2 virus to determine the suitability of aCu treated face masks to prevent virus transmission. The cellulose/polyester (45/55) fabric was coated with aCu and adhesive. A viral load of

approximately 10^6 PFU/ml was applied to the fabric; after 30 seconds 99·9% of the virus had been killed (Fig. 3F, Table S5). This dramatic efficacy makes aCu a very promising candidate for the development of self-cleaning PPE.

Copper in medicine and mammalian compatibility

To ensure that no harmful respiratory exposure occurs from using an aCu-coated insert in a face mask, shedding tests were conducted under simulated breathing conditions. aCu-coated fabric and blank controls were individually loaded into a sample holder and a flow of nitrogen was administered at rates commensurate with breathing. Two different flow rates were tested, 4·1 slpm and 20 slpm, to simulate normal breathing and more intense breathing during physical activity. Optical particle monitoring, condensation particle counting, filter trapping, and water trapping were employed to assess the exhausted N_2 for shed particles (Fig. 3F, G). SEM/EDS analysis of the filter traps did not detect any copper (fig. S4). Metal levels in the water trapped from both treated and blank control materials were equivalent; no Cu was detected (Fig. 3F). Optical particle counter tests found total particle counts to be <0·1 ng in each 15-minute test window (fig. S3). These particles were organic in nature and looked like loose fabric material. Hypothetically, if all of the identified particles were copper, it would equate to a maximum shedding rate of 0·1 ng Cu per 15-minute period. This would translate to a maximal copper "dose" of approximately 2 ng/hour for a wearer. This would be significantly below OSHA's maximum Permissible Exposure Limit (PEL) of 1mg/m^3 for copper dust in the workplace.[10] The simulated breathing data offers reassurance that aCu-coated fabrics are safe for frequent human use and proximity to the respiratory system.

Our results far exceed the benchmarks established by the EPA for speed of action as well as material longevity and durability. The favorable results against multiple virus configurations (enveloped and non-enveloped) suggest that aCu is broadly lethal against pathogens and is therefore unaffected by the possibility of future mutations. Enveloped viruses, like coronaviruses and influenzas, are generally regarded as less hardy than non-enveloped viruses.[11] aCu's non-selectivity coupled with its rapid deactivation window suggests viability as an additive to healthcare tools like privacy curtains, door handles and guard rails.

As with any material that contacts skin or the respiratory system, safety is of utmost concern. A protective item must not introduce new health threats while protecting the user. To this end, it's pertinent to highlight copper's long and safe history in medical and industrial materials.[12, 13] Ancient civilizations recorded medical copper use as early as 2200 B.C., and a more scientific understanding was established when a doctor realized that copper miners and smelters enjoyed distinct immunity from Paris's 1832 cholera outbreak *4*. Reliance on copper continued to grow until it was displaced by penicillin in 1932. More recently, copper has been incorporated into medical devices,[14] dental cement,[15,16] and dilute $CuCl_2$ IV solutions to treat copper deficiencies in patients.[17] Copper's bioactivity is relevant in both the synthesis and maintenance of skin proteins; it is used in treating skin conditions.[18] Extended dermal exposure to copper has been shown to be well-tolerated.[19]

Copper plays an essential role in human health. It is involved in angiogenesis,[20] transcription factor regulation, bone development, and various other physiological processes.[21] Deficiencies in bodily copper can cause anemia, neutropenia, and neurological disorders.[21, 22] Because it is so well integrated into human biology, robust mechanisms exist to regulate copper levels in the body.[23] Homeostatic maintenance of copper occurs via intestinal absorption and release is mediated by the liver into bile.[24] Small stores of copper are kept in the body, approximately 0·5 mg per pound of body weight in the average adult.[25]

Discussion

When the EPA recognized the antimicrobial efficacy of copper alloys in February, 2008, copper's biocompatibility contributed to their determination that "these products pose no risks to public health; copper products have been in use for centuries, and we know of no harm from such use".[26] EPA recognition allows copper manufacturers to claim that approved copper products "kill 99·9% of bacteria within two hours".[26] The two-hour guarantee of bacterial deactivation is accompanied by an EPA mandate to maintain rigorous disinfecting regiments because copper that works on this timescale could still transmit pathogens. Over 500 copper alloys are registered with the EPA and deemed to have no "unreasonable adverse effects" under the U.S. Federal Insecticide, Fungicide, and Rodenticide Act.[26]

Because our testing indicated that aCu has the potential to function as personal protective equipment in a medical setting, it is necessary to consider the precedent set by other medical copper products prior to the development of aCu for safety and indicators of need within the field. We considered the guidance from the Food and Drug Administration (FDA). The FDA has listed fine copper powder (95% w/w Cu) as exempt from certification, deeming it safe for use as a color additive in cosmetics. This qualification was extended to products intended for use specifically in the eye area.[27] The FDA's relaxed position on copper provided further reassurance that our material would create no health issues for the people using it. FDA approval has been sought and granted for other medical copper products, establishing a precedent for copper's enduring modern utility. FDA approval was granted for a breathable face mask in 2016 *28* that protects against bacteria and influenza viruses. The mask material was proven to kill 99% of tested bacteria after one hour of contact and inactivate 99·9% of test influenza viruses after five minutes of contact.[28]

The antimicrobial technology at play applies fine zeolite infused with Ag^+ and Cu^+ ions to the non-woven polyester fibers of a mask. Their application method eliminated off-gassing or leaching of the antimicrobial agent, which we have accomplished with aCu (fig. S3, S4). To securely fix aCu paint to the intended material, we have adopted the practice of gluing (bonding) aCu to the core of the fabrics. aCu's protective lipid-type layer both protects and stabilizes the high surface area of aCu, further enabling strong cohesion of the micron-size agglomerates (Fig. 1). Our highly active copper material is differentiated from related precursors by its ability to kill viruses and bacteria in one minute or less.

Fig. 5 Image of aCu after being dispensed from a tube. The dense thixotropic copper gel is paste-like and stable. It behaves like a typical non-Newtonian "liquid". A layer of amine surfactants exerts strong cohesion via hydrophobic interactions and organic end-chain entanglement.

We have speculated on the mechanisms responsible for aCu's non-specific eradication of microbes and have been informed extensively by the work of other researchers. Research on inorganic aerogels, xerogels and the like has shown that they exhibit high surface areas due to their fine pore structure; they are strongly attracted to one another and other surfaces via hydrophobic interactions or hydrophilic hydrogen bonding and chain entanglement.[29] This can be enhanced by placing long-chain organic surfactants at their surfaces, forming a reverse micelle-type structure. We did exactly that with our aCu and designed a surfactant monolayer that maximizes attraction and mimics a lipid cell membrane. A virus's small size (20-300 nm) combined with its commensurate surface energy to aCu results in mutual attraction. When they stick together, the protective lipid envelope and the protein capsid of the virus is readily attacked by aCu. The copper oxidizes first to Cu^{+1} and then more rapidly to Cu^{+2} with the formation of very aggressive OH* radicals in the presence of moisture and air as well as fatty acid radicals from the oxidation of the protective lipid layer:

$$2\ aCu^0 + 2\ H_2O + O_2 \rightarrow\ 2\ CuOH + 2\ HO✹$$

$$2\ aCu^0 + 2\ FA\text{-}COOH + O_2 \rightarrow 2\ CuOH + 2\ FA\text{-}COO✹$$

This process causes the lipid layer to disintegrate and the protein capsid to break open .[30, 31] The destruction of the capsid was identified by Dr. Sarah Warnes, *et al.* in 2015 using transmission electron microscopy (TEM).[32] Viral replication is halted as Cu^{2+} ions, stabilized by their amine surfactants, cleave and cross-link RNA/DNA through their affinity for nucleotides.[33] This mechanism is analogous to the DNA binding exhibited by anti-tumor *cis*-platinum compounds.[34]

Both reactive oxygen species and ionic interactions have been shown to facilitate viral deactivation. Due to the unprecedented speed and activity of aCu, more testing is necessary to elucidate the exact order of operations.

Action against bacteria begins as their unique cell wall degrades.[35] Copper ions inhibit the transpeptidases responsible for cross-linking the peptidoglycan wall, compromising its structural integrity. Bacteriolysis is furthered by copper's interruption of the necessary balance between peptidoglycan-synthesizing enzymes and autolysin.[35] The destruction of such a fundamental piece of the bacterial framework in both Gram negative and positive strains indicates that aCu's efficacy would not be hindered by bacterial mutation. Additionally, antimicrobial copper experiments have been successfully conducted against a number of antibiotic-resistant strains. Reactive oxygen species generated by Cu^{2+}'s interactions with the cell wall and subsequent permeation into the membrane may harm bacteria via cytoplasmic toxicity.[36] aCu does not act as a mutagen, as antibiotics can,[37] indicating that it is not liable to produce mutant bacterial strains and contribute to antibiotic resistance.[38]

Around the world, people need to return to life, work, and family while protecting their health. A growing number of people who experienced flu-like Covid-19 and were believed to have recovered are reporting persistent fatigue, gastrointestinal, and cognitive issues that outlast their original symptoms.[39] In some cases, these long-term impacts manifest as cardiac dysfunction.[40] Trailing symptoms are not unprecedented with coronaviruses; a study conducted in 2009 on survivors of SARS determined that 40% of respondents struggled with chronic fatigue.[41] In addition to the detrimental follow-on effects of Covid-19, it is becoming apparent that reinfection may be possible.[42] The uncertainty that surrounds the long-term consequences of contracting Covid-19 puts additional pressure on people to mitigate their risk, no matter their age.

Under the most optimistic outlooks, vaccine development will be completed in the first few months of 2021.[43] If trials and approvals are successful along this never-before-seen timeline, major logistical hurdles will remain before a vaccine can be distributed to vast populations. At this moment, public distrust in medicine and governing authorities translates to considerable vaccine hesitancy in a multitude of countries.[44–46] This apprehension will likely hinder the compliance necessary to achieve broad inoculation and subsequent immunity.[47] A vaccine will be a significant triumph. However, a long-lasting protective mask offers individuals an immediate and reliable defense against COVID-19 while circumventing medical skepticism. It is both reversible and individually administered; a vaccine is not.

Remedies targeted specifically at SARS-CoV-2 are in dire need, but in the long term we need broad, non-selective protection against pathogens. In real time we have watched SARS-CoV-2 jump from humans to large populations of farmed mink in Denmark and now we are seeing a second episode of zoonosis as farm workers become sick with the mink-mutated strain.[48] Genomic sequencing confirmed that this strain was transmitted from humans to animals and back once more. When given the opportunity to move through a dense concentration of hosts, such as a farm, viruses can mutate into more virulent forms much more quickly than they would

in the wild.[49] A reassortant H1N1 influenza virus with pandemic potential has already been identified in China,[50] and we can continue to count on the appearance of seasonal illnesses. Due to the lag time in developing vaccines, a situation is conceivable where the distributed vaccine would miss the currently circulating coronavirus mutant. We posit that masks and other protective pieces that self-sterilize to destroy 100% of pathogens could aid in an expedited return to uninterrupted life.

Acknowledgments: We have been the very fortunate recipients of strong scientific collaboration focused on putting an end to Covid-19. We would like to thank Dr. Jelena Sepa, Ph.D of EMD Performance Materials Corp. for facilitating our particulate testing conducted by James Nehlsen at Versum/Merck. We would like to thank Gilman Louie of Alsop Louie as well as the Defense Innovation Unit (DIU) of the Department of Defense (DoD) for helping to facilitate the antimicrobial testing of aCu.

Funding: This work was funded exclusively by Kuprion Inc.

Author contributions: AAZ: originally conceived of and developed ActiveCopper, manages all projects related its use. **MI**, **HK** conducted foundational antimicrobial research **KKH, CW, LP, RF** conducted SARS-CoV-2 research **RLB** wrote the paper and compiled data **RR, AV, KKN, NTN, HTZ** produced and managed testing materials, formulated the copper paste, troubleshot technical materials issues **NA** supervised the project and handled administration and funding acquisition **RMS** handles the commercial manufacturing and scale up of the materials, developed methodologies and supervised the projects.

Competing interests: We own an extensive patent portfolio that protects the foundations of this technology platform. The authors declare that there exist no competing interests.

Data and materials availability: We are in pre-production phase currently manufacturing 40-50 kg of base ActiveCopper per month; the material is commercially available. Bacteria and viruses used in studies are available commercially, ascension numbers are included in Supplementary Materials.

References and Notes:

1. Yang Q, Li H, Shen S, *et al.* Study of the micro-climate and bacterial distribution in the deadspace of N95 filtering face respirators. *Sci Rep* **8,** 17382 (2018).
2. Nilsson A, Pettersson L, Norskov J, "Heterogeneous Catalysis" in *Chemical bonding at surfaces and interfaces*. (Elsevier, New York, 2008), pp. 255-321.
3. Hammond K, Conner Jr W. "Analysis of Catalyst Surface Structure by Physical Sorption" in *Advances in Catalysis*. (Elsevier, New York, vol. 56, 2013), pp.1-101.
4. Grass G, Rensing C, Solioz M. Metallic copper as an antimicrobial surface. *Appl. Environ. Microbiol*. **77,** 1541-1547 (2011).
5. Vincent M, Hartemann P, Engels-Deutsch M. Antimicrobial applications of copper. *Int. J Hyg. Environ. Health* 219, no. 7, 585-591 (2016).
6. United States Environmental Protection Agency, "*UNS Designations of Copper Alloys*" (2018).

7. Leslie R, Zhou S, Macinga D. Inactivation of SARS-CoV-2 by commercially available alcohol-based hand sanitizers. *Am. J Infect. Control* (2020).

8. Malik Y, Maherchandani S, Goyal S. Comparative efficacy of ethanol and isopropanol against feline calicivirus, a norovirus surrogate. *Am. J Infect. Control* 34, no. 1: 31-35: (2006).

9. Blackburn T, "*Test Method for Efficacy of Copper Alloy Surfaces as a Sanitizer*". (United States Environmental Protection Agency, 2008).

10. National Institute for Occupational Safety and Health, (NIOSH). "*Copper (dusts and mists, as Cu)*". (US Center for Disease Control NIOSH, 2016)

11. Kramer A, Schwebke I, Kampf G. How long do nosocomial pathogens persist on inanimate surfaces? A systematic review. *BMC Infect. Dis.* 6, no. 1, 130 (2006).

12. Hordyjewska A, Popiołek L, Kocot J. The many "faces" of copper in medicine and treatment. *Biometals*. 27(4):611-621 (2014).

13. Longano D, Ditaranto N, Sabbatini L, Torsi L, Cioffi N. Synthesis and Antimicrobial Activity of Copper Nanomaterials. *Nano-Antimicrobials*. 2011;85-117. (2011).

14. United States Food and Drug Administration, "*Metals Used in Medical Devices*" (2020).

15. Mahler D. The High-copper Dental Amalgam Alloys. *J. Dent. Res.* 76(1):537-541 (1997).

16. Glassman M, Miller I, Antibacterial properties of one conventional and three high-copper dental amalgams. *J. Prosthet. Dent.*, *52*(2), 199-203 (1984).

17. Griffith D, Liff D, Ziegler T, Esper G, Winton E. Acquired copper deficiency: a potentially serious and preventable complication following gastric bypass surgery. *Obesity* 17, no. 4: 827-831: (2009).

18. Borkow G. Using copper to improve the well-being of the skin. *Curr. Chem. Biol.*, *8*(2), 89-102 (2014).

19. Borkow G. Protection of Soldiers' feet by copper oxide impregnated socks. *Advances in Military Technology* 8.2: 101-108 (2013).

20. Gérard C, Bordeleau L, Barralet J, Doillon C. The stimulation of angiogenesis and collagen deposition by copper. *Biomaterials* 31, no. 5: 824-831 (2010).

21. Uauy R, Olivares M, Gonzalez M. Essentiality of copper in humans. *Am. J. Clin. Nutr.* 67, no. 5: 952S-959S (1998).

22. Desai V, Kaler S. Role of copper in human neurological disorders. *Am. J. Clin. Nutr.* 88, no. 3: 855S-858S (2008).

23. Turnlund J. Human whole-body copper metabolism. *Am. J. Clin. Nutr.* 67, no. 5: 960S-964S (1998).

24. Prohaska J. Role of copper transporters in copper homeostasis. *Am. J. Clin. Nutr.* 88, no. 3: 826S-829S (2008).

25. Erdman Jr J, MacDonald I, Zeisel S, eds. *Present knowledge in nutrition*. John Wiley & Sons. Chapter 35, page 540-44 (2012).

26. Swindell M. "*U.S. EPA Pesticide Product Label, Antimicrobial Copper Alloys Group V"*. (United States Environmental Protection Agency, 2008).

27. U.S. FDA. "*Color Additives Permitted for Use in Cosmetics"*. (U.S. Food and Drug Administration, 2017)

28. U.S. FDA. "*510(k) Premarket Notification – N95 Respirator with Antimicrobial/Antiviral Agent"*. U.S. Food and Drug Administration, 2009).

29. Liu S, Wang L, Li S, *et al*. Multidrug resistant tumors-aimed theranostics on the basis of strong electrostatic attraction between resistant cells and nanomaterials. *Biomat. Sci.* 7, no. 12: 4990-5001 (2012).

30. Warnes S, Keevil C. Inactivation of norovirus on dry copper alloy surfaces. *PloS one 8*, no. 9: e75017 (2013).

31. Abad F, Pinto R, Diez J, Bosch A. Disinfection of human enteric viruses in water by copper and silver in combination with low levels of chlorine. *Appl. Envir. Microbiol.* 60, no. 7: 2377-2383 (1994).

32. Warnes S, Summersgill E, Keevil C. Inactivation of murine norovirus on a range of copper alloy surfaces is accompanied by loss of capsid integrity. *Appl. Envir. Microbiol.* 81, no. 3: 1085-1091 (2015).

33. Ishida T. Antiviral Activities of Cu2+ Ions in Viral Prevention, Replication, RNA Degradation, and for Antiviral Efficacies of Lytic Virus, ROS-Mediated Virus, Copper Chelation. *World Scientific News* 99: 148-168 (2018).

34. Roberts J, Pascoe J. Cross-linking of complementary strands of DNA in mammalian cells by antitumour platinum compounds. *Nature* 235, no. 5336: 282-284 (1972).

35. Peters K, Pazos M, Edoo Z, *et al.* Copper inhibits peptidoglycan LD-transpeptidases suppressing β-lactam resistance due to bypass of penicillin-binding proteins. *Proc. Natl. Acad. Sci. U. S. A.* 115, no. 42: 10786-10791 (2018).

36. Solioz M, Abicht H, Mermod M, Mancini S. Response of Gram-positive bacteria to copper stress. *JBIC, J. Biol. Inorg. Chem.* 15, no. 1: 3 (2010).

37. Long H, Miller S, Strauss C, *et al*. Antibiotic treatment enhances the genome-wide mutation rate of target cells. *Proc. Natl. Acad. Sci. U. S. A.* 113, no. 18: E2498-E2505 (2016).

38. Santo C, Lam E, Elowsky C. Bacterial killing by dry metallic copper surfaces. *Appl. Envir. Microbiol.* 77, no. 3: 794-802 (2011).

39. Nabavi N. Long covid: How to define it and how to manage it. *Br. Med. J.* (2020).

40. Mahase E. Covid-19: What do we know about "long covid"?. *Br. Med. J.* 370 (2020).

41. Lam M, Wing Y, Yu M, *et al.* Mental morbidities and chronic fatigue in severe acute respiratory syndrome survivors: long-term follow-up. *Arch. Intern. Med.* 169, no. 22: 2142-2147 (2009).

42. Tillett R, Sevinsky J, Hartley P, *et al*. Genomic evidence for reinfection with SARS-CoV-2: a case study. *Lancet Infect. Dis.* (2020).

43. Le T, Andreadakis Z, Kumar A. The COVID-19 vaccine development landscape. *Nat Rev Drug Discov* 19, no. 5: 305-306 (2020).

44. Özceylan G, Toprak D, Esen E. Vaccine rejection and hesitation in Turkey. *Hum. Vaccines Immunother.*: 1-6 (2020).

45. Hornsey M, Lobera J, Díaz-Catalán C. Vaccine hesitancy is strongly associated with distrust of conventional medicine, and only weakly associated with trust in alternative medicine. *Soc. Sci. Med.*: 113019 (2020).

46. Thunstrom L, Ashworth M, Finnoff D, Newbold S. Hesitancy Towards a COVID-19 Vaccine and Prospects for Herd Immunity. *Available at SSRN 3593098* (2020).

47. Neumann-Böhme S, Varghese N, Sabat I, *et al.* Once we have it, will we use it? A European survey on willingness to be vaccinated against COVID-19. *Eur. J. Health Econ.*: 1-6 (2020).

48. Enserink M. Coronavirus rips through Dutch mink farms, triggering culls. *Science 368*: no. 6496: 1169-1169 (2020).

49. Boots M, Hudson P, Sasaki A. Large shifts in pathogen virulence relate to host population structure. *Science* 303, no. 5659: 842-844 (2004).

50. Sun H, Xiao Y, Liu J, *et al*. Prevalent Eurasian avian-like H1N1 swine influenza virus with 2009 pandemic viral genes facilitating human infection. *Proc. Natl. Acad. Sci. U. S. A.* 117, no. 29: 17204-17210 (2020).