High current production of *Shewanella oneidensis* with electrospun carbon nanofiber anodes is directly linked to biofilm formation

Johannes Erben[a], Xinyu Wang[a,b], Sven Kerzenmacher[a,*]

[a]*Center for Environmental Research and Sustainable Technology (UFT), University of Bremen, 28359 Bremen, Germany*
[b]*Laboratory for MEMS Applications, IMTEK – Department of Microsystems Engineering, University of Freiburg, Georges-Koehler-Allee 103, 79110 Freiburg, Germany*

Abstract

We study the current production of *Shewanella oneidensis* MR-1 with electrospun carbon fiber anode materials and analyze the effect of the anode morphology on the micro-, meso- and macroscale. The materials feature fiber diameters in the range between 108 nm and 623 nm, resulting in distinct macropore sizes and surface roughness factors. A maximum current density of $(255 \pm 71)\,\mu\text{A}\,\text{cm}^{-2}$ was obtained with 286 nm fiber diameter material. Additionally, micro- and mesoporosity were introduced by CO_2 and steam activation which did not improve the current production significantly. The current production is directly linked to the biofilm dry mass under anaerobic and micro-aerobic conditions. Our findings suggest that either the surface area or the pore size related to the fiber diameter determines the attractiveness of the anodes as habitat and therefore biofilm formation and current production. Reanalysis of previous works supports these findings.

Keywords: Electrospinning, *Shewanella oneidensis* MR-1, Bioelectrochemical systems, Macropore, Surface area, Morphology

1. Introduction

1.1. *Shewanella oneidensis MR-1 and its applications in Bioelectrochemical Systems*

Due to recent attempts to find alternatives for the fossil-based economy, Bioelectrochemical systems (BES) moved into the focus of scientific interest. In BES, oxidative and reductive reactions are catalyzed by, e.g., electroactive bacteria. Electrodes are used to establish an electrical connection between bacteria cells and an external electrical circuit. The most prominent applications

---

[*]Sven Kerzenmacher
Email address: `kerzenmacher@uni-bremen.de` (Sven Kerzenmacher)

of BES comprise electricity production with microbial fuel cells [1], microbial electrosynthesis [2] for carbon dioxide fixation, and more recently, electrode-assisted fermentation for the production of platform chemicals [3, 4, 5]. In this work, the interplay between the electroactive microbe Shewanella oneidensis MR-1 (MR-1), a naturally occurring facultative anaerobic bacterium, and electrospun carbon nanofiber electrodes is studied. MR-1 is not only a well establish model organism for microbial anodes, but due to its fully sequenced and annotated genome [6] and ease of cultivation, it is a well-suited chassis organism for the genetic engineering of production strains [3, 4]. The extracellular electron transfer (EET) to insoluble terminal electron acceptors of MR-1 is subject to extensive scientific investigation. Three distinct electron transfer mechanisms were proposed for MR-1: mediated electron transfer (MET) via soluble redox-active species, direct electron transfer (DET), and electron transport via pili [7]. The ability to export electrons across the cellular membrane stems from several multi-heme c-type cytochromes bridging the gap between the cytoplasm and cell surface [8]. It has been shown that self-secreted flavins, most of them being riboflavin (RF), increase the current production of MR-1 [9]. The current production increase was attributed to MET via redox-cycling of RF, using knock-out mutants and medium replacement experiments [7, 9]. Okamoto et al. [10, 11] suggested a different role of flavins in the extracellular electron transport: flavin mononucleotide and RF act as co-factor of the outer membrane cytochromes MtrC and OmcA respectively and enhance their extracellular electron transfer rates. This role may explain the observed current increase in the presence of low concentrations of flavins that hardly can be accounted for by diffusive MET [12].

1.2. Biofilm formation of Shewanella oneidensis MR-1

The achievable current density with MR-1 strongly depends on the number of cells attached to the electrode. The operation conditions within a bioelectrochemical reactor and the electrode's working potential affect the biofilm formation of MR-1 cells on electrodes [13]. The biofilm coverage on electrodes is not limited to single layers and can be stimulated by the presence of oxygen [14], possibly due to increased motility or motility elements that promote the development of three-dimensional biofilm structures [15]. In static multilayer biofilms, electron transport from cells that are not directly attached to the electrode is facilitated by the sequential redox cycling of outer membrane c-type cytochromes and/or MET [16]. In dynamic biofilms, motile cells could increase the apparent cell surface coverage [17], enabling more cells to participate in EET. Besides oxygen, RF in solution, RF covalently bound to magnetic beads, and polymerized RF on electrodes are known to stimulate biofilm growth on electrodes, and a positive correlation between biofilm formation and current production was observed [18, 19]. More positive anode working potentials have been shown to enhance biofilm formation and current output [13]. While increased current production is preferential for a high production rate, a lower coulombic efficiency (CE) decreases production yield.

1.3. Anode materials tailored for the operation with Shewanella oneidensis MR-1

Compared to *Geobacter sulfurreducens*, MR-1 produces lower current densities, but the current production can be improved by choosing a suitable anode material [20]. Numerous studies with mixed-community biofilms have been conducted on anode materials [21, 22, 23, 24], while little systematic work with MR-1 is reported in the literature. Kipf et al. [25] identified a commercial steam-activated knitted carbon fiber material with a current density of $24\,\mu A\,cm^{-2}$ at a potential of $-200\,mV$ (sat. Calomel; $41\,mV$vs NHE) as superior to other carbon-based materials. Patil et al. [26] studied the current production of electrospun carbon fiber materials partly modified with activated carbon and graphite particles. Increased current production was observed with increasing specific BET surface area. Pötschke et al. [27] investigated the carbon composition and fiber breaks. They identified a combination of highly conductive graphitic carbon, and free filament ends as key to high current densities. In the present study, we systematically investigate the effect of the electrode the surface area, and the pore size on the anodic current production and biofilm formation of MR-1 under anaerobic and micro-aerobic conditions. The controlled fabrication process of the materials allows us to separate effects of the macro, meso- and micro-scale morphology on the current production. The surface chemistry is presumably identical, allowing us to separate the effects of the material morphology and the surface chemistry on the current production.

We tested four materials with distinct fiber diameters that feature surface roughness factors (*SRF*s) between 286 and 1004 and mean macropore diameters between $0.4\,\mu m$ and $1.6\,\mu m$. Additionally, the electrospun carbon fiber surface was modified by steam and CO_2 activation to increase the surface area further and introduce micro- and mesopores, which have been hypothesized to enhance MET [25, 26]. We also reevaluate previous systematic anode material studies [25, 26, 27] based on the premise that mainly the macrostructure of the anode determines the current production and biofilm formation of MR-1. The commercial reference materials were investigated previously [28, 5, 25, 20] and serve as a benchmark in this work.

2. Materials and methods

2.1. Preparation of tailored electrospun and commercial reference anodes

Four electrospun carbon fiber mat materials with average fiber diameters of ~108 nm (ES100), ~286 nm (ES300), ~400 nm (ES400), and ~623 nm (ES600) were fabricated by electrospinning of PAN with concentrations between 6 wt% and 13 wt% in N,N-dimethylacetamide and subsequent carbonization at 1100 °C as previously reported [29]. Activation was conducted for 4 h with CO_2 at 832 °C and with steam at 757 °C. Two commercial carbon materials, knitted steam activated carbon C-Tex 13 (Mast Carbon International Ltd., United Kingdom) and graphite felt GFD 2 (SGL Carbon SE, Germany), were used as reference materials [28, 25, 20] for comparison. SEM photographs of these materials are provided in Fig. S1.1. The anodes were cut into pieces of $2\,cm^2 \times 2\,cm^2$ and

mounted in polycarbonate frames exposing $2.25\,\text{cm}^2$ to the growth medium (Fig. S1.2). To remove gas bubbles from the porous anode structures, the anode material was wetted with isopropyl alcohol, rinsed with DI water, and placed in vacuum for approximately 10 minutes before the experiments.

2.2. Anode material characterization

The electrochemically active surface ($ECAS$) of the anodes was determined via the measurement of the double-layer capacitance using a Solartron Analytical potentiostat (1470E, Farnborough, United Kingdom) as reported previously [29]. Nitrogen adsorption was conducted at $77\,\text{K}$ using a Belsorp-Max instrument (BEL Japan Inc., Japan) for the electrospun materials and a Sorptomatic 1990 (CE Instruments, Italy) for the commercial reference materials. Scanning electron microscopy (SEM) was performed using a DSM 962 (Carl Zeiss Microscopy GmbH, Germany) and an SX 100 (Cameca, France). The macropore sizes were estimated from SEM photographs using the software ImageJ and DiameterJ [30] as described in Section S4 in the supplementary information. The porosity φ was calculated based on the anode thickness in the mounting frames t according to $\varphi = 1 - \rho_\text{A} \cdot (t\rho)^{-1}$. Herein, ρ_A is the material's area density, and ρ is the density of PAN-derived carbon ($1.75\,\text{g cm}^{-3}$, [31]). The internal surface area was assessed by the $ECAS$ method [29]. From the weight-specific $ECAS$ and S_BET surface area, and the area density ρ_A, the Surface Roughness Factor (SRF) was calculated according to $SRF_\text{ECAS} = ECAS \cdot \rho_\text{A}$ and $SRF_\text{BET} = S_\text{BET} \cdot \rho_\text{A}$. The SRF, defined by the ratio of the internal surface area and the anode's projected surface area, allows the direct comparison of the materials with different area densities. Similarly, the absolute micro- and mesopore volume V_Micro and V_Meso, determined from N_2 adsorption isotherms (t-plot and BJH analysis respectively), was calculated from the weight-specific value ν for the projected anode area: $V = \nu \cdot \rho_\text{A} \cdot 2.25\,\text{cm}^2$. The macropores of the electrospun materials and GFD 2 were assessed by digital image processing and 3D modeling as described in Section S4 in the supplementary information. With this method, a 2D SEM image is analyzed for its apparent porosity and pore diameter. In a second step, the 2D apparent pore diameter is converted into a 3D pore diameter by comparison with a 3D model of the fiber material morphology. This unique method was chosen because mercury intrusion porosimetry underestimates the pore sizes of compressible materials [32, 33].

2.3. Bioelectrochemical characterization

MR-1 cells were prepared following the procedure described by Kipf et al. [25]. In short, MR-1 cells were first cultivated aerobically in Lysogeny broth (LB medium) and then transferred to a growth medium containing $50\,\text{mM}$ Na-D/L-lactate and $100\,\text{mM}$ fumarate. The cells were washed with washing buffer (growth medium lacking lactate and fumarate) thrice before inoculation of the bioelectrochemical reactor (Fig. S1.3). The amount of inoculum was adjusted to an initial optical density (OD_{600}) of $\sim$0.05. Before inoculation, the bioelectrochemical reactor was sterilized by steam autoclavation at $121\,°\text{C}$ for

20 min. The bioelectrochemical reactor contained 1 L anode medium with 50 mM initial concentration of Na-D/L-lactate as an electron donor and no electron
140 acceptor other than 6 anodes. The anodes were polarized at -41 mV against a sat. Calomel reference (SCE, KE11, Sensortechnik Meinsberg, Germany) using PGU-MOD 500 mA potentiostats (IPS Elektroniklabor GmbH & Co. KG, Münster, Germany). To minimize non-coulombic currents, the anodes were polarized at least 12 h before the inoculation. A platinum mesh acted as a counter electrode.
145 The current production was recorded for 14 days. In the present publication, potentials are additionally provided vs. Normal Hydrogen Electrode (NHE) at 25 °C for better comparison. This way, different temperature dependencies of the redox couples are accounted for. The reactor is operated at 30 °C and its headspace is continuously purged with humidified N_2 at 125 mL min^{-1} for
150 anaerobic conditions (<20 ppm). Trace amounts of O_2 (200 ppm - 400 ppm corresponding to 1.4 µg L^{-1} - 2.8 µg L^{-1} dissolved oxygen) were introduced into the reactor by guiding the gas flow through an O_2 permeable silicone tube. Oxygen concentrations were determined with a Fibox 3 LCD trace oxygen meter (PreSens Precision Sensing GmbH, Germany). The medium was stirred
155 at 300 rpm and sampled every other day to monitor pH, cell density, lactate consumption, and flavin concentration.

2.4. Medium monitoring

Flavin concentration in the medium was measured with a Nanodrop 3300 spectrometer (emission at 525 nm, excitation 470 nm) using riboflavin (RF) as
160 a standard. RF exhibits similar fluorescence signals as FMN and FAD [34]. Therefore, the flavin concentrations reported comprise FMN, FAD, and RF. The CE was calculated based on the lactate consumption under microaerobic conditions and based on the acetate accumulation under anaerobic conditions assuming partial oxidation of lactate to acetate with 4 electrons per molecule
165 [35]. The initial and final lactate and acetate concentrations were determined by high-performance liquid chromatography (Elite La Chrome, Hitachi, Japan) equipped with an Aminex HPX-87H column (Bio-Rad, Germany) and RI-detector (RefraktoMax 521, IDEX Health & Science, Japan). The planktonic dry weight m in the medium was determined by $\{m\}_{\mathrm{mg}} = 716 \cdot \{V\}_{\mathrm{Liter}} \cdot \{OD_{600}\}$. The
170 conversion factor was determined experimentally with the dry weight of a cell filter cake from medium with known volume and OD_{600}.

2.5. Biofilm analysis

The biofilm dry weight was quantified after 14 days of operation as follows. The anodes were placed in 1 mL of lysis buffer (20 mM Tris/HCl, 16.5 mM Triton
175 X-100, 137 mM NaCl, protease inhibitor cocktail for bacteria 25 µL mL^{-1}, Carl Roth, Germany) at 4 °C overnight. The lysate's protein content was then analyzed using a biuret test according to the instructions (Roti-quant universal, Carl Roth, Germany). Dry mass was calculated by comparison to cell lysate with known dry weight. For SEM imaging, the biofilm was fixated with 2.5 % glutaraldehyde in
180 anode medium lacking lactate for 24 h at 4 °C. The samples were then dehydrated

with a series of 10 %, 30 %, 50 %, 70 %, 80 %, 90 %, and 100 % ethanol in washing buffer for 10 min each and air-dried at room temperature.

3. Results and discussion

3.1. Anode material properties

¹⁸⁵ The pore sizes and surface area of the anode materials were characterized on the micro (<2 nm), meso (>2 nm to <50 nm), and macro (>50 nm) scale by nitrogen adsorption, electrochemically accessible surface ($ECAS$), and SEM imaging. Scanning electron microscopy photographs of the materials are provided in Fig. S1.1. The self-made electrospun materials ES100 to ES600 feature ultra-
¹⁹⁰ thin fibers with mean fiber diameters between $\sim$100 nm and $\sim$600 nm. The commercial reference materials GFD 2 and C-Tex 13 consist of PAN derived fibers with about 10 µm diameter. The individual activated C-Tex 13 fibers feature grooves of about 1 µm width along the fiber (see inset of Fig. S1.1 E). The fibers are loosely twisted in bundles that are knitted into a fabric.
¹⁹⁵ GFD 2 felt consists of mostly smooth graphite fibers. C-Tex 13 and the activated electrospun materials feature a hydrophilic surface. GFD 2 and the electrospun non-activated materials are hydrophobic. The carbonization process is the same for all electrospun materials. The electrospun materials and GFD 2 exhibit porosities from 94 % to 95 %. C-Tex 13 has a lower porosity of 81 %. The
²⁰⁰ morphological characteristics of all investigated materials are listed in Tab. 1 and are discussed in detail below.

Table 1: Properties of the commercial and electrospun anode materials. The complete material properties are listed in Tab. S3.1 in the supplementary material. The pore diameters are: Micro: < 2 nm, Meso: > 2 nm & < 50 nm, Macro: > 50 nm. The material thicknesses are given according to the manufacturer's data sheet and have not been verified by own measurements, except for the electrospun materials and GFD 2.

Material	Diameter d_F nm	Thickness mm	V_Micro 10^{-3} cm^3	V_Meso cm^3 10^{-3} cm^3	d_Macro µm	SRF_ECAS	SRF_BET
GFD 2	$\sim$10000	2	0.4	1.95	31	27	10075
C-Tex 13	$\sim$10000	0.5	15.3	3.39	-*	132000	132000
ES100	108	0.5	-	0.24	0.4	1004	770
ES300	286	0.5	-	0.21	0.78	726	697
ES400	400	0.5	-	0.16	0.97	856	413
ES600	623	0.5	-	0.13	1.6	286	166
ES300-CO$_2$	$\sim$286	0.5	0.6	0.98	0.78	18781	8308
ES300-H$_2$O	$\sim$286	0.5	1.3	0.99	0.78	34692	16453

[*] Macropores are present but cannot be quantified.

The steam activated C-Tex 13 exhibits the highest SRF_ECAS, SRF_BET, and micropore volume V_Micro among the investigated materials. Interestingly, the graphitic GFD 2 also features a substantial micropore volume but a lower
²⁰⁵ SRF_ECAS of 27. Graphite contains lesser oxygen-containing groups [36] that increase the double layer capacitance [37] and thus the $ECAS$. The high mesopore volumes V_Meso of 3.39×10^{-3} cm^3 (C-Tex 13) and 1.95×10^{-3} cm^3 (GFD 2) are mainly due to the higher area densities of $182\,\mathrm{g\,m^{-2}}$ and $165\,\mathrm{g\,m^{-2}}$. The mean

macropore diameter d_{Macro} of GFD 2, 31 µm, is about a factor of 20 higher than
the electrospun materials with similar morphology. The macropore structure of
C-Tex 13 can only be assessed semi-quantitatively due to its knitted structure:
The grooves along the fibers introduce porosity in the submicron range, and
interfiber distances vary from direct contact to several fiber diameters within
one fiber bundle. Maximum distances between the fiber bundles are in the range
of ~200 µm. The electrospun materials' $ECAS$ values do not monotonically
increase with decreasing fiber diameter, possibly due to the fiber cross-section's
deviation from a perfectly round shape [29] or differing surface roughness. The
same holds for the SRF_{ECAS} due to similar area densities. However, S_{BET} and
SRF_{BET} increase monotonically with decreasing fiber diameter. CO_2 and steam
activation increase the SRF_{ECAS} of ES300 by 30 and 55 and SRF_{BET} by a
factor of 12 and 24, respectively. The increased micro- and mesopore volume of
the activated electrospun materials show that the increased SRFs are linked to
micro- and mesopore formation during activation. Because of the low weight
loss during activation, the fiber diameter and macropores remain practically
unaffected by CO_2 and steam activation.

3.2. Electrical resistivity of the anode materials

The sheet resistances for the electrospun materials given in Erben et al. [29] allow the estimation of the ohmic potential drop across the electrode according to Madjarov et al. [38]. For the electrospun materials and GFD 2, with sheet resistances between $\sim1.8\,\Omega$ and $\sim2\,\Omega$, the ohmic drop for the current densities of MR-1 obtained in this work is estimated to be less than $1\,mV$. C-Tex 13 has a higher sheet resistance of $144\,\Omega$, resulting in an ohmic drop of less than $40\,mV$ at the maximum current densities measured with the materials. Therefore, we do not expect that the different electrical resistances affect the current production.

3.3. Current production under anaerobic and micro-aerobic conditions

Figure 1: A) The maximum current normalized to the projected surface area. The hatched filling indicates the commercial reference materials, and the dotted filling the additional technical and biological replicates with activated electrospun materials conducted in a separate set of experiments. The values for C-Tex 13 were multiplied by 100 and the values of ES300-CO_2 and ES300-H_2O by a factor of 10 for better visualization. All values represent arithmetic means and sample standard deviation and are calculated based on a quadruplicate. A) A trend to higher current densities with decreasing fiber diameter is apparent under anaerobic conditions. Welch corrected t-tests did not reveal a significant improvement of the current production of activated ES300 materials ES300-CO_2 ($p = .14$, Welch corrected t-test) and ES300-H_2O ($p = .15$) compared to the non-activated ES300 material (Fig. S2.5). Under micro-aerobic conditions, similar current productions of the electrospun materials and C-Tex 13 are observed. The current production of GFD 2 is increased 13-fold under micro-aerobic conditions compared to anaerobic conditions. B) The maximum current density normalized to $ECAS$ reveals that the current production is not directly linked to the internal surface area.

The six different anode materials were characterized in four technical replicates to account for the experimental conditions' variability. The values reported in this section are averages with sample standard deviation (n = 4). As one anode material of a kind was used for biofilm imaging by SEM, three values were considered in the biofilm dry weight analysis in Section 3.4. The maximum current densities presented in Fig. 1 A were extracted from chronoamperometry data recorded over the experimental period of 2 weeks (data not shown). Under anaerobic conditions (Fig. 1A, red), a maximum current density of $(255 \pm 71)\,\mu\mathrm{A\,cm^{-2}}$ was recorded with the ES300 material. This current density is about 1.4-fold higher than the highest value of $186\,\mu\mathrm{A\,cm^{-2}}$ reported up to now [27]. A trend towards higher current densities with decreasing fiber diameter is apparent (Fig. 1 A, red). Through the fiber diameter d_{F} and the porosity φ, SRF and macropore diameter d_{Macro} are inseparably linked in fibrous materials on the macroscale (a detailed derivation of the analytical model can be found in Section S4.1 of the supplementary information):

$$SRF \sim \frac{1-\varphi}{d_{\mathrm{F}}} \quad \& \quad d_{\mathrm{Macro}} \sim \frac{d_{\mathrm{F}}}{\sqrt{1-\varphi}}. \tag{1}$$

As predicted by the analytical model, SRF_{ECAS}, SRF_{BET}, and d_{Macro} intercorrelate strongly for the non-activated electrospun materials (absolute correlation coefficients between 0.82 and 0.96, Tab. S3.2). Additionally, we find that the mesopores volume V_{Meso} is correlated to the SRF and d_{Macro} (absolute corre-
lation coefficients between 0.79 and 0.96). As expected, the maximum current density can be correlated reasonably well with all of the above material properties (Fig. S2.4). Therefore, the increased current production of thin fiber material cannot be attributed to the increased SRF, reduced macropore diameter, or the increasing mesopore volume. Steam and CO_2 activation introduce micro-
and mesopores, while the macropore structure remains unchanged. The surface roughness factor increases due to the surface within the micro- and mesopores, but the additional surface does not significantly improve current production (Fig. S2.5). This allows us to rule out micro- and mesopore's positive effects on the current production and the related pore surface. We will further discuss the role
of macropore size and SRF for the current production again in Section 3.7. Under micro-aerobic conditions (Fig. 1 A, blue), the different non-activated electrospun anode materials show maximum current densities between $(234 \pm 16)\,\mu\mathrm{A\,cm^{-2}}$ and $(305 \pm 58)\,\mu\mathrm{A\,cm^{-2}}$. The presence of trace amounts of oxygen under micro-aerobic conditions masks thin fibers' positive effect on the current production.
Due to the strong variability of the obtained values, no significant difference in the current production can be observed. Although oxygen serves as a competing electron acceptor to the anode, it enhances current production [25] and bacterial growth and biofilm formation (see Section 3.4). Little systematic research on the influence of the anode macro morphology on the current production has been
conducted up to now. Diverse characterization techniques make it impossible to compare results directly between different studies. The current production of the commercial reference materials C-Tex 13 and GFD 2 was characterized previously using a quasi-galvanostatic protocol by Kipf et al. [25]. Analysis

of the experimental setup in retrospect revealed that trace amounts of oxygen
₂₆₅ were present in the reactor. Therefore, micro-aerobic conditions in this work
are comparable to the anaerobic conditions in Kipf et al. [25]. Interestingly,
the commercial reference materials C-Tex 13 and GFD 2 exhibit about 10-fold
higher current densities, with $(229 \pm 82)\,\mu\mathrm{A\,cm^{-2}}$ and $(112 \pm 36)\,\mu\mathrm{A\,cm^{-2}}$ re-
spectively, than previously reported [25]. The 10-fold higher current production
₂₇₀ is most likely a result of the different characterization methods. In the present
study, even e.g. trace amounts of oxygen change the difference in the refer-
ence materials' current production from 9-fold under micro-aerobic to 2-fold
under micro-aerobic conditions. This underlines the necessity of a systematic
and well-controlled approach to material characterization. In the following, we
₂₇₅ reevaluate data from previous publications based on the premise that the anode
materials' macrostructure determines its current production with MR-1 taking
into account the possible effects of oxygen contamination. Tab. S5.3 summarizes
the data of Kipf et al. [25] and includes additional morphological characteristics.
We find that knitted, and woven activated carbon fabrics' current production
₂₈₀ is significantly higher than the carbon felts and carbon paper (p ¡ .001, Welch
corrected t-test). The current production of felt materials, made of grooved
activated carbon fibers (V1-Felt) and smooth graphitized fibers (GFD 2), does
not differ significantly ($p = .13$). This confirms our finding that micro- and
mesopores do not enhance the current production considerably. Within the group
₂₈₅ of knitted and woven fabric anode materials, C-Tex 27 produces a significantly
lower current than C-Tex 13 ($p = .0018$). Judging from the SEM images, the
densely aligned fibers of C-Tex 27 and woven structure cause less accessible
pore space in and between the fiber bundles compared to C-Tex 13, consisting
of knitted twisted fiber bundles. C-Tex 20 features a higher area density and
₂₉₀ thickness than C-Tex 13, while the fiber diameter is the same. The higher
current production of C-Tex 20 compared to C-Tex 13 ($p = .069$) can therefore
be attributed to the increased area-specific volume due to the higher thickness
of the electrode material, similar to four layers of C-Tex 13 compared to a single
layer [25]. It is noteworthy that the current production does not scale linearly
₂₉₅ with the number of layers, possibly to mass transport limitations. Patil et al.
[26] investigated the current production of electrospun PAN-based carbon fibers
without (PAN) and with additional activated carbon (PAN-AC) and graphite
(PAN-GR) particles (SEM images and material properties see Tab. S5.4). The
higher current production of the materials with particles was attributed to their
₃₀₀ higher surface area. Besides higher BET surface area and micropore volume of
PAN-AC and PAN-GR, the materials with particles and a higher surface area also
exhibited smaller fiber diameters. Similar to our results, the increasing current
production with decreasing fiber diameter could result from the macrostructure
with a larger accessible surface area and smaller macropores. In a study by
₃₀₅ Pötschke et al. [27], the effect of the chemical carbon fiber composition and fiber
breaks on the current production was investigated. SEM images of fiber bundles
depicted in Tab. S5.5 reveal that the fibers of stretch broken (SB) fabrics are less
aligned than non-broken (CM) fibers with pores between the individual fibers.
However, the mean current production of SB fabrics compared to CM fabrics is

³¹⁰ not significantly higher ($p = .32$). However, planktonic cell growth (max. OD_{600} $\sim$0.4 to $\sim$0.9) and flavin accumulation ($\sim$0.4 µM to $\sim$0.8 µM) are indications of trace amounts of oxygen present in this study (see Section 3.6) that mask effects of the anode morphology on the current production. Besides oxygen, the higher anode potential of 200 mV (sat. Ag/AgCl, 400 mV vs. NHE) compared ³¹⁵ to the 0 mV (sat. Ag/AgCl, 200 mV mV vs. NHE) in our study might enable cell growth and flavin secretion.

3.4. Current production and biofilm formation

Figure 2: A) Biofilm dry mass found on the anodes after two weeks of operation. B) Final current after two weeks of operation normalized to the biofilm dry weight. The similar values of (65.2 ± 7.0) µA mg^{-1}, as indicated by the horizontal lines in green, found for the electrospun materials under anaerobic and micro-aerobic conditions indicate a proportional relationship between the biofilm found on the electrodes and the current production. The hatched filling indicates the commercial reference materials. All values represent arithmetic means and sample standard deviation and are calculated based on a triplicate.

The bacterial dry weight was quantified after two weeks of operation (Fig. 2 A). Under micro-aerobic conditions, a higher bacterial dry mass was found ³²⁰ for all anode materials compared to anaerobic conditions. Under micro-aerobic conditions, similar amounts of bacterial dry mass with large variability between 38 % and 73 % were found on the electrospun materials and the commercial reference materials. Under anaerobic conditions, however, increasing bacterial dry mass with decreasing fiber diameter can be observed for the electrospun ³²⁵ materials (Fig. 2 A, plain red). The similarity to the maximum current densities in Fig. 1 A is apparent. Therefore, the final current densities (after two weeks of operation) were normalized to the bacterial dry weight (Fig. 2 B). Most interestingly, the electrospun materials show similar values as would be expected

for a proportional relationship between the number of current producing cells
and current production for anaerobic and micro-aerobic conditions. The values of
C-Tex 13 under both operating conditions, and GFD 2 under micro-aerobic conditions, do not deviate significantly from the average value of $(65.2 \pm 7.0)\,\mu A\,mg^{-1}$
for the electrospun materials. $(65.2 \pm 7.0)\,\mu A\,mg^{-1}$ corresponds to about $47\,fA$
per cell (calculated using a dry weight of $716\,pg/cell$ determined with the dry
weight of an MR-1 filter cake from an anaerobic culture with known cell density). This value is well in line with values reported by Lu et al. [39] for MR-1
single-cell current production of $165\,fA$ under aerobic conditions to $36\,fA$ at
$0.42\,mg\,L^{-1}$ dissolved oxygen. In this study, the anode was poised at $\sim 200\,mV$
(sat. Ag/AgCl, $400\,mV$ vs. NHE), and the cells were quantified by confocal
laser scanning microscopy. With real single-cell probing using optical tweezers,
a current of $50\,fA$ at the same potential as this work ($200\,mV$ vs. NHE) was
determined [40]. The lower value of GFD 2 could be explained by interstitial
cells that populate the pore space [41] and do not contribute to the current
production due to lacking electrical contact to the anode. This effect would
be less pronounced under micro-aerobic conditions. Interestingly, the current
production of single *Geobacter sulfurreducens* cells of $(93 \pm 33)\,fA$ [42] is in the
same range as single MR-1 cells.

3.5. Morphology of the MR-1 biofilms

SEM images of the biofilm grown under anaerobic conditions on the electrospun anode materials (Fig. 3) reveal biofilm coverage independent of the
fiber diameter at the anode front and a trend towards higher biofilm coverage
with decreasing fiber diameter at the anode back. The biofilms reaching further
into the electrospun anode material and increased bacterial dry weight suggests
that thin fiber materials provide a more attractive habitat for MR-1 cells than
thick fiber materials. However, under micro-aerobic conditions, a different trend
is visible: Higher biofilm coverage on the anode front compared to the anode
back is observed. The likely explanation for this observation is oxygen tension
towards the anode front due to the abundance of trace amounts of oxygen in
the medium [43]. It is important to note that the SEM images do not show the
biofilm structure in operation. During sample preparation, the drying process
leads to a collapse of the porous biofilm onto the anode surface and shrinkage of
the cells themselves.

3.6. Total cell growth yield, flavin accumulation, and coulombic efficiency

The planktonic cell growth and flavin accumulation differ significantly under
anaerobic and micro-aerobic conditions, as shown in Fig. 5. The presence of
trace amounts of oxygen results in cell growth with OD_{600} values up to about
0.2. Under anaerobic conditions, the planktonic cell density remains stable, with
OD_{600} values between 0.03 and 0.05. The total dry mass equivalent of planktonic
cells and biofilm on the anodes is depicted in Fig. 4. Only little cell growth with
$55\,\%$ more bacterial dry mass (biofilm plus the equivalent of planktonic cells)
is observed after 14 days of operation. In the case of micro-aerobic operation,

Figure 3: SEM photographs of the biofilms on the electrospun materials and semi-quantitative analysis of the biofilm coverage. Note: the commercial reference materials have been excluded from the biofilm morphology analysis due to major differences in the material morphology. SEM images of the biofilm coverage on these materials are depicted in Fig. S2.6

about 380 % more dry mass equivalent accumulates in the reactor after 14 days. A higher fraction, (57 ± 11) %, of the dry weight, is found on the anode under anaerobic conditions compared to (34 ± 17) % under micro-aerobic conditions. The higher cell growth under micro-aerobic conditions is accompanied by flavin accumulation to a final concentration of $\sim 1\,\mu$M after 14 days. Under anaerobic conditions, only $\sim 0.1\,\mu$M is observed. Considering the similar current to biofilm dry weight ratios of $(65.2 \pm 7.0)\,\mu\text{A}\,\text{mg}^{-1}$ under micro- and anaerobic conditions (see Section 3.4), it is reasonable to assume that planktonic cells do not contribute considerably to the current production. Hence, mediated electron transfer (MET) by flavins does not significantly affect the overall EET. The low cell growth under anaerobic conditions is surprising because the anode potential in the present work ($200\,$mV vs. NHE) is high enough to drive the DET via OmcA at $-110\,$mV vs. NHE and MtrC at $-150\,$mV vs. NHE as well as MET via free flavins at $-250\,$mV vs. NHE (NHE) [44]. Higher anode potentials may be preferential for the cell growth energetics and flavin secretion.

For applications such as acetoin production by unbalanced fermentation [3], the coulomb efficiency (CE) is crucial for high product yields. Under anaerobic conditions, the CE reaches values close to unity with (96.6 ± 1.8) %. Under micro-aerobic conditions, the CE drops to (41.6 ± 4.2) % . While the latter value

Figure 4: Total cell growth yield under anaerobic and micro-aerobic conditions after 14 days of operation. The growth yield under anaerobic conditions is 55 % and under micro-aerobic conditions 381 %. About 57 % of the total dry mass is found in the biofilm under anaerobic conditions and 34 % under micro-aerobic conditions.

lies in the previously reported range from ∼15 % to ∼75 % [25, 35, 27, 45, 46] for MR-1, the former value exceeds the literature values considerably. Similar high values have only been reported for unbalanced fermentation with engineered *E. coli* and *Shewanella oneidensis* strains [4, 5]. We suspect that our high CE stems from the superior current production with the electrospun anode materials compared to the oxygen leakage into our bioelectrochemical reactor. The pH remained stable under micro- and anaerobic conditions in the range of 7.14 to 7.50 without adjustment.

Figure 5: Growth medium characteristics under anaerobic and micro-aerobic conditions. Strongly different behavior can be observed in the flavin accumulation and planktonic cell growth.

3.7. The role of pore size and surface for the current generation and biofilm formation

As described above, current production is directly linked to the bacterial dry weight attached to the anode. Under anaerobic conditions, the dry weight increases with decreasing fiber diameter of the non-activated electrospun materials. Steam and CO_2 activation, which introduce micro- and mesopores and increase the surface area, does not further increase biofilm attachment. Therefore, we conclude that the anode materials' macrostructure determines bacterial attachment to the anode and thus current production. However, as established in Section 3.3 SRF, porosity, macropore diameter, and fiber diameter are inseparably linked in fibrous materials on the macroscale. Thus, the higher current production of the electrospun materials with decreasing fiber diameter, which is directly related to the biomass attached to the anode, cannot be attributed directly to either the increased SRF or the reduced macropore size. The literature does not provide an in-depth analysis of macropore size and the related surface regarding current production and biofilm formation. In the following, we discuss microscopic processes within biofilms and electrodes that allow attributing the high current production of macroporous electrospun materials to either pore size or surface. Electrospun fiber materials provide high SRFs for electron discharge and mean pore diameters in the range of 0.4 µm to 1.6 µm (Tab. 1) allow the bacteria to penetrate the anode pore space and attach to the internal surface. Chong et al. [47] concluded that pore sizes in the order of a millimeter are preferential for the current production with bacteria that form dense biofilms such as the *Geobacter spp.* and sludge-derived mixed communities. Smaller pores lead to (partial) pore-clogging that hinders the mass transport of nutrients and metabolic products and eventually limits the achievable current densities. MR-1 forms loose biofilms that do not block the pores and do not cover the entire fiber surface (Fig. 3). Hence, the surface area is unlikely to limit bacterial attachment and current production. This raises the question of whether the confinement of cells in proximity to the anode surface or a more attractive chemical microenvironment within the anode pore space leads to increased biofilm formation with decreasing fiber diameter. A recent study by Pirbadian et al. [16] revealed that the cell membrane hyperpolarization, a measure for metabolic activity, decreases rapidly with the distance from the anode under anaerobic conditions. The membrane hyperpolarization drops within (8.9 ± 12.4) µm to $1/e$ of the value in contact with the electrode. Upon addition of 5 µM riboflavin, this value increases to (21.8 ± 4.3) µm. Biofilms that were grown on flat graphite reach a similar thickness [14]. Therefore, pores, larger than a few µm, will be occupied by the biofilm with partially reduced average metabolic activity and current production per cell (panel A in Fig. 6). The low current per dry weight values for GFD 2 under anaerobic conditions (little flavin accumulation) and the increase under micro-aerobic conditions (flavin accumulation in the range of 1 µM) can thus be attributed to the large pores of GFD 2. Three mechanisms could explain the decreasing metabolic activity with increasing distance from the anode surface: consecutive redox-cycling of adjacent cells [17], MET through self-secreted flavins [7, 9], and a dynamic biofilm structure caused by motile

cells that increase the apparent surface coverage with cells, enabling more cells to participate in EET [17]. Therefore, we cannot attribute the high current densities of electrospun materials to either of the above EET mechanisms. The mean pore diameters of the electrospun materials of $0.4\,\mu m$ to $1.6\,\mu m$ are in the same range as the MR-1 cell size ($2\,\mu m$ to $3\,\mu m$ in length and $0.4\,\mu m$ to $0.7\,\mu m$ in diameter, [48]). Therefore, it is not surprising that the current per dry weight for all electrospun materials is similar, considering that the cells must be in close contact with the anode surface in small pores. The average value of $47\,fA$ per cell, we determined in Section 3.4, may represent the metabolic limit of MR-1 cells under this study's experimental conditions. The total cell volume in the anode is about $8.5\,mm^3$ (estimated from the volume of a single cell $0.7\,\mu m^3$), the maximum current density ($255\,\mu A\,cm^{-2}$, and $47\,fA$). This is about 8% of the pore space of the electrospun materials. Therefore, the available pore space is not limiting biofilm formation. A possible explanation for the low cell density within the pore space could be a self-inhibiting effect caused by gradients of metabolic products: i.e., protons and the related local acidification inside the anode (panel B in Fig. 6). Presumably, redox-cycling of flavins occurs between the anode and the MR-1 cells (panel C in Fig. 6). Increasing numbers of MR-1 cells inside the anode shift the equilibrium of oxidized and reduced flavins towards the reduced form. Therefore, the positive chemotaxis of MR-1 cells to oxidized riboflavin [43] is decreased by the presence of MR-1 cells. In turn, both smaller pore diameter and larger surface area increase the regeneration of oxidized flavins. Thus, a gradient of oxidized flavins can be sustained with larger numbers of cells within the pore space. Small pore diameter (shorter diffusion distances) and the surface (more reaction sites) would enhance this mechanism. Okamoto et al. [44] proposed a different role of pores concerning flavins: dead-end pores fully covered by cells could lead to a local increase of flavin concentration in the dead-end pores, enhancing the MET (panel D in Fig. 6). Also, small pores would decrease diffusion distances. This proposed effect requires dead-end pores with sizes within close boundaries: The lower limit is set by the molecular size of flavins ($1.3\,nm^2$ to $1.5\,nm^2$, [49]), and the cell footprint gives the upper limit in the order of $1\,\mu m^2$. We cannot exclude this possibility, as the present study's activated materials mainly feature micropores and open macropores. In conclusion, we can categorize the above processes in surface-related processes (cellular attachment, DET, and oxidation of flavins) and transport processes (flavins, electrons in the biofilm, and bacteria). As MR-1 biofilms do not clog pores, transport processes can be expected to be accelerated by small macropores. Materials with small macropores also provide a larger surface close to the surrounding bulk medium and allow steeper gradients that enhance mass transport of nutrients, oxygen, and metabolic products.

3.8. Implications for further research

Our material ES300 with open $0.78\,\mu m$ macropores exhibits a maximum current density of $(255 \pm 71)\,\mu A\,cm^{-2}$, which corresponds to a 1.4-fold increase compared to the previous literature [27]. In addition, this extraordinarily high current density is accompanied by a coulombic efficiency (CE) of $(96.6 \pm 1.8)\,\%$

Figure 6: Illustration of microscopic processes in the biofilm and their dependence on pore size, surface area, and the number of cells inside the anode. A) Metabolic activity as a function of the distance to the closest anode surface (free adaption of Pirbadian et al. [16]. B) Acidification in the anode as a function of distance from the bulk medium and cell density. C) Flavin oxidation state as a function of pore size and cell density inside the anode. D) Flavin accumulation in dead-end pores, according to Okamoto et al. [44].

that exceeds the previously reported values considerably (see Section 3.6). Both, high CE and current density are required for commercial applications with a high product yield and production rate. As shown by our experimental results, the high current production is linearly related to the bacterial dry weight found on the anodes. The electrode surface is only partially covered with cells, suggesting that the surface area does not directly limit cell attachment. Also, the pore space of the electrospun material is only filled to about 8 % with cells. The underlying mechanisms, that determine the attractiveness of the anodic habitat for MR-1 are not fully understood, and require further research. Further efforts to improve current densities with MR-1 should therefore focus on enhanced biofilm formation. Possible strategies include the chemical modification of the carbon surface, tailoring of pore size and shape. We discussed processes that affect the chemical microenvironment inside the anode material and might cause the improved biofilm formation with decreasing fiber diameter:

- Cellular attachment, DET, and oxidation of flavins are enhanced by large anode surface areas.

- Mediator transport by diffusion and electron transport in the biofilm profit from small macropores.

- High porosity and interconnected pores are required for the transport of nutrient and metabolic products between the bulk medium and the anode's interior.

Besides the material development, the chemical microenvironment inside the anode could be improved through media optimization, e.g. increase in buffer capacity. Special care needs to be taken during material characterization to ensure anaerobic conditions. Even trace amounts of oxygen lower the CE

⁵¹⁵ considerably and (partially) mask the macrostructure's effect on the current production. Planktonic cell growth and flavin accumulation are indicators for oxygen contamination.

4. Conclusions

The current production of Shewanella oneidensis MR-1 with tailored elec-⁵²⁰ trospun anode materials with fiber diameters between $108\,\mathrm{nm}$ to $623\,\mathrm{nm}$ was characterized. Our highest current production of $(255 \pm 71)\,\mu\mathrm{A\,cm^{-2}}$ with the $286\,\mathrm{nm}$ fiber diameter material exceeds the highest value reported in the literature 1.4-fold. The high current density is accompanied by a coulombic efficiency of $(96.6 \pm 1.8)\,\%$. Additional activation did not improve the current production ⁵²⁵ significantly. We observe a linear relationship between current production and bacterial dry weight and increased penetration depth of the biofilm. We conclude that the anode material's attractiveness for MR-1 cells is most likely determined by both the macropore size and the accessible surface area.

5. Acknowledgements

⁵³⁰ We are grateful for the financial support from the German Ministry of Education and Research (BMBF) under the program 03SF0496A. We thank Dr. Guillaume Alexis Adrien Pillot for fruitful discussions and critical feedback during the writing process.

References

⁵³⁵ [1] B. E. Logan, B. Hamelers, R. Rozendal, U. Schröder, J. Keller, S. Freguia, P. Aelterman, W. Verstraete, K. Rabaey, Microbial fuel cells: Methodology and technology, Environmental Science and Technology 40 (2006) 5181–5192. doi:10.1021/es0605016.

[2] K. P. Nevin, T. L. Woodard, A. E. Franks, Z. M. Summers, D. R. Lovley, ⁵⁴⁰ Microbial electrosynthesis: feeding microbes electricity to convert carbon dioxide and water to multicarbon extracellular organic compounds., mBio 1 (2010) e00103–10. doi:10.1128/mBio.00103-10.

[3] T. Bursac, J. A. Gralnick, J. Gescher, Acetoin production via unbalanced fermentation in *Shewanella oneidensis*, Biotechnology and Bioengineering ⁵⁴⁵ 114 (2017) 1283–1289. doi:10.1002/bit.26243.

[4] J. M. Flynn, D. E. Ross, K. A. Hunt, D. R. Bond, J. A. Gralnick, Enabling unbalanced fermentations by using engineered electrode-interfaced bacteria., mBio 1 (2010) e00190–10. doi:10.1128/mBio.00190-10.

[5] A. H. Förster, S. Beblawy, F. Golitsch, J. Gescher, Electrode-assisted ⁵⁵⁰ acetoin production in a metabolically engineered Escherichia coli strain, Biotechnology for Biofuels 10 (2017) 65. doi:10.1186/s13068-017-0745-9.

[6] J. F. Heidelberg, I. T. Paulsen, K. E. Nelson, E. J. Gaidos, W. C. Nelson, T. D. Read, J. A. Eisen, R. Seshadri, N. Ward, B. Methe, R. A. Clayton, T. Meyer, A. Tsapin, J. Scott, M. Beanan, L. Brinkac, S. Daugherty, R. T. DeBoy, R. J. Dodson, A. S. Durkin, D. H. Haft, J. F. Kolonay, R. Madupu, J. D. Peterson, L. A. Umayam, O. White, A. M. Wolf, J. Vamathevan, J. Weidman, M. Impraim, K. Lee, K. Berry, C. Lee, J. Mueller, H. Khouri, J. Gill, T. R. Utterback, L. A. McDonald, T. V. Feldblyum, H. O. Smith, J. C. Venter, K. H. Nealson, C. M. Fraser, Genome sequence of the dissimilatory metal ion–reducing bacterium Shewanella oneidensis, Nature Biotechnology 20 (2002) 1118–1123. doi:10.1038/nbt749.

[7] A. A. Carmona-Martinez, F. Harnisch, L. A. Fitzgerald, J. C. Biffinger, B. R. Ringeisen, U. Schröder, Cyclic voltammetric analysis of the electron transfer of Shewanella oneidensis MR-1 and nanofilament and cytochrome knock-out mutants, Bioelectrochemistry 81 (2011) 74–80. doi:10.1016/j.bioelechem.2011.02.006.

[8] A. Okamoto, R. Nakamura, K. Hashimoto, In-vivo identification of direct electron transfer from Shewanella oneidensis MR-1 to electrodes via outer-membrane OmcA-MtrCAB protein complexes, Electrochimica Acta 56 (2011) 5526–5531. doi:10.1016/j.electacta.2011.03.076.

[9] E. Marsili, D. B. Baron, I. D. Shikhare, D. Coursolle, J. A. Gralnick, D. R. Bond, Shewanella secretes flavins that mediate extracellular electron transfer., Proceedings of the National Academy of Sciences of the United States of America 105 (2008) 3968–73. doi:10.1073/pnas.0710525105.

[10] A. Okamoto, K. Hashimoto, K. H. Nealson, R. Nakamura, Rate enhancement of bacterial extracellular electron transport involves bound flavin semiquinones, Proceedings of the National Academy of Sciences of the United States of America 110 (2013) 7856–7861. doi:10.1073/pnas.1220823110.

[11] A. Okamoto, S. Kalathil, X. Deng, K. Hashimoto, R. Nakamura, K. H. Nealson, Cell-secreted Flavins Bound to Membrane Cytochromes Dictate Electron Transfer Reactions to Surfaces with Diverse Charge and pH, Scientific Reports 4 (2015) 5628. doi:10.1038/srep05628.

[12] C. I. Torres, A. K. Marcus, H.-S. Lee, P. Parameswaran, R. Krajmalnik-Brown, B. E. Rittmann, A kinetic perspective on extracellular electron transfer by anode-respiring bacteria, FEMS Microbiology Reviews 34 (2010) 3–17. doi:10.1111/j.1574-6976.2009.00191.x.

[13] A. A. Carmona-Martínez, F. Harnisch, U. Kuhlicke, T. R. Neu, U. Schröder, Electron transfer and biofilm formation of Shewanella putrefaciens as function of anode potential, Bioelectrochemistry 93 (2013) 23–29. doi:10.1016/J.BIOELECHEM.2012.05.002.

[14] M. Kitayama, R. Koga, T. Kasai, A. Kouzuma, K. Watanabe, Structures, compositions, and activities of live Shewanella biofilms formed on

graphite electrodes in electrochemical flow cells, Applied and Environmental Microbiology 83 (2017). doi:`10.1128/AEM.00903-17`.

[15] K. M. Thormann, R. M. Saville, S. Shukla, D. A. Pelletier, A. M. Spormann, Initial phases of biofilm formation in Shewanella oneidensis MR-1, Journal of Bacteriology 186 (2004) 8096–8104. doi:`10.1128/JB.186.23.8096-8104.2004`.

[16] S. Pirbadian, M. S. Chavez, M. Y. El-Naggar, Spatiotemporal mapping of bacterial membrane potential responses to extracellular electron transfer, Proceedings of the National Academy of Sciences of the United States of America 117 (2020) 20171–20179. doi:`10.1073/PNAS.2000802117`.

[17] A. Okamoto, K. Hashimoto, R. Nakamura, Long-range electron conduction of Shewanella biofilms mediated by outer membrane C-type cytochromes, Bioelectrochemistry 85 (2012) 61–65. doi:`10.1016/j.bioelechem.2011.12.003`.

[18] T. Arinda, L.-A. A. Philipp, D. Rehnlund, M. Edel, J. Chodorski, M. Stöckl, D. Holtmann, R. Ulber, J. Gescher, K. Sturm-Richter, Addition of riboflavin-coupled magnetic beads increases current production in bioelectrochemical systems via the increased formation of anode-biofilms, Frontiers in Microbiology 10 (2019) 126. doi:`10.3389/fmicb.2019.00126`.

[19] L. Zou, X. Wu, Y. Huang, H. Ni, Z. E. Long, Promoting *Shewanella* bidirectional extracellular electron transfer for bioelectrocatalysis by electropolymerized riboflavin interface on carbon electrode, Frontiers in Microbiology 10 (2019) 3293. doi:`10.3389/fmicb.2018.03293`.

[20] E. Kipf, R. Zengerle, J. Gescher, S. Kerzenmacher, How Does the Choice of Anode Material Influence Electrical Performance? A Comparison of Two Microbial Fuel Cell Model Organisms, ChemElectroChem 1 (2014) 1849–1853. doi:`10.1002/celc.201402036`.

[21] S. Chen, H. Hou, F. Harnisch, S. A. Patil, A. A. Carmona-Martinez, S. Agarwal, Y. Zhang, S. Sinha-Ray, A. L. Yarin, A. Greiner, U. Schröder, Electrospun and solution blown three-dimensional carbon fiber nonwovens for application as electrodes in microbial fuel cells, Energy & Environmental Science 4 (2011) 1417. doi:`10.1039/c0ee00446d`.

[22] V. Flexer, J. Chen, B. C. Donose, P. Sherrell, G. G. Wallace, J. Keller, The nanostructure of three-dimensional scaffolds enhances the current density of microbial bioelectrochemical systems, Energy & Environmental Science 6 (2013) 1291. doi:`10.1039/c3ee00052d`.

[23] G. He, Y. Gu, S. He, U. Schröder, S. Chen, H. Hou, Effect of fiber diameter on the behavior of biofilm and anodic performance of fiber electrodes in microbial fuel cells, Bioresource Technology 102 (2011) 10763–10766. doi:`10.1016/j.biortech.2011.09.006`.

[24] M. Picot, L. Lapinsonnière, M. Rothballer, F. Barrière, Graphite anode surface modification with controlled reduction of specific aryl diazonium salts for improved microbial fuel cells power output, Biosensors and Bioelectronics 28 (2011) 181–188. doi:10.1016/J.BIOS.2011.07.017.

[25] E. Kipf, J. Koch, B. Geiger, J. Erben, K. Richter, J. Gescher, R. Zengerle, S. Kerzenmacher, Systematic screening of carbon-based anode materials for microbial fuel cells with Shewanella oneidensis MR-1, Bioresource Technology 146 (2013) 386–392. doi:10.1016/j.biortech.2013.07.076.

[26] S. A. Patil, S. Chigome, C. Hägerhäll, N. Torto, L. Gorton, Electrospun carbon nanofibers from polyacrylonitrile blended with activated or graphitized carbonaceous materials for improving anodic bioelectrocatalysis, Bioresource Technology 132 (2013) 121–126. doi:10.1016/j.biortech.2012.12.180.

[27] L. Pötschke, P. Huber, S. Schriever, V. Rizzotto, T. Gries, L. M. Blank, M. A. Rosenbaum, Rational Selection of Carbon Fiber Properties for High-Performance Textile Electrodes in Bioelectrochemical Systems, Frontiers in Energy Research 7 (2019) 100. doi:10.3389/fenrg.2019.00100.

[28] K. Dolch, J. Danzer, T. Kabbeck, B. Bierer, J. Erben, A. H. Förster, J. Maisch, P. Nick, S. Kerzenmacher, J. Gescher, Characterization of microbial current production as a function of microbe-electrode-interaction, Bioresource Technology 157 (2014) 284–292. doi:10.1016/j.biortech.2014.01.112.

[29] J. Erben, A. Heußner, S. Thiele, S. Kerzenmacher, Activation of electrospun carbon fiber mats: the effect of fiber diameter on CO_2 and steam reaction kinetics, Journal of Polymer Research (accepted for publication) (2021). doi:https://doi.org/10.1007/s10965-020-02386-w.

[30] N. A. Hotaling, K. Bharti, H. Kriel, C. G. Simon, DiameterJ: A validated open source nanofiber diameter measurement tool, Biomaterials 61 (2015) 327–338. doi:10.1016/j.biomaterials.2015.05.015.

[31] Z. Wangxi, L. Jie, W. Gang, Evolution of structure and properties of PAN precursors during their conversion to carbon fibers, Carbon 41 (2003) 2805–2812. doi:10.1016/S0008-6223(03)00391-9.

[32] H. Giesche, Mercury porosimetry: A general (practical) overview, in: Particle and Particle Systems Characterization, 2006, pp. 9–19. doi:10.1002/ppsc.200601009.

[33] G. C. Rutledge, J. L. Lowery, C. L. Pai, Characterization by mercury porosimetry of nonwoven fiber media with deformation, Journal of Engineered Fibers and Fabrics (2009). doi:10.1177/155892500900400301.

[34] L. Valle, F. E. Morán Vieyra, C. D. Borsarelli, Hydrogen-bonding modulation of excited-state properties of flavins in a model of aqueous confined

environment, Photochemical & Photobiological Sciences 11 (2012) 1051. doi:10.1039/c2pp05385c.

[35] M. Lanthier, K. B. Gregory, D. R. Lovley, Growth with high planktonic biomass in Shewanella oneidensis fuel cells, FEMS Microbiology Letters 278 (2008) 29–35. doi:10.1111/j.1574-6968.2007.00964.x.

[36] T. H. Ko, S. C. Liau, M. F. Lin, Preparation of graphite fibres from a modified PAN precursor, Journal of Materials Science (1992). doi:10.1007/BF01133752.

[37] M. J. Bleda-Martínez, J. A. Maciá-Agulló, D. Lozano-Castelló, E. Morallón, D. Cazorla-Amorós, A. Linares-Solano, Role of surface chemistry on electric double layer capacitance of carbon materials, Carbon 43 (2005) 2677–2684. doi:10.1016/j.carbon.2005.05.027.

[38] J. Madjarov, S. C. Popat, J. Erben, A. Götze, R. Zengerle, S. Kerzenmacher, Revisiting methods to characterize bioelectrochemical systems: The influence of uncompensated resistance (iRu-drop), double layer capacitance, and junction potential, Journal of Power Sources 356 (2017) 408–418. doi:10.1016/j.jpowsour.2017.03.033.

[39] M. Lu, S. Chan, S. Babanova, O. Bretschger, Effect of oxygen on the per-cell extracellular electron transfer rate of *Shewanella oneidensis* MR-1 explored in bioelectrochemical systems, Biotechnology and Bioengineering 114 (2017) 96–105. doi:10.1002/bit.26046.

[40] H. Liu, G. J. Newton, R. Nakamura, K. Hashimoto, S. Nakanishi, Electrochemical Characterization of a Single Electricity-Producing Bacterial Cell of Shewanella by Using Optical Tweezers, Angewandte Chemie International Edition 49 (2010) 6596–6599. doi:10.1002/anie.201000315.

[41] N. P. Shroff, S. Xu, J. Acevedo, M. Y. El-Naggar, S. E. Finkel, A Microenvironment for Shewanella oneidensis MR-1 Exists within Graphite Felt Electrodes, Journal of The Electrochemical Society 164 (2017) H3103–H3108. doi:10.1149/2.0161703jes.

[42] X. Jiang, J. Hu, E. R. Petersen, L. A. Fitzgerald, C. S. Jackan, A. M. Lieber, B. R. Ringeisen, C. M. Lieber, J. C. Biffinger, Probing single- to multi-cell level charge transport in Geobacter sulfurreducens DL-1, Nature Communications 4 (2013) 2751. doi:10.1038/ncomms3751.

[43] B. J. Kim, I. Chu, S. Jusuf, T. Kuo, M. A. TerAvest, L. T. Angenent, M. Wu, Oxygen Tension and Riboflavin Gradients Cooperatively Regulate the Migration of Shewanella oneidensis MR-1 Revealed by a Hydrogel-Based Microfluidic Device, Frontiers in Microbiology 7 (2016) 1438. doi:10.3389/fmicb.2016.01438.

[710] [44] A. Okamoto, R. Nakamura, K. H. Nealson, K. Hashimoto, Bound Flavin Model Suggests Similar Electron-Transfer Mechanisms in Shewanella and Geobacter, ChemElectroChem 1 (2014) 1808–1812. doi:10.1002/celc.201402151.

[45] M. A. TerAvest, L. T. Angenent, Oxidizing Electrode Potentials Decrease [715] Current Production and Coulombic Efficiency through Cytochrome c Inactivation in *Shewanella oneidensis* MR-1, ChemElectroChem 1 (2014) 2000–2006. doi:10.1002/celc.201402128.

[46] V. J. Watson, B. E. Logan, Power production in MFCs inoculated with Shewanella oneidensis MR-1 or mixed cultures, Biotechnology and Bioengi- [720] neering 105 (2010) 489–498. doi:10.1002/bit.22556.

[47] P. Chong, B. Erable, A. Bergel, Effect of pore size on the current produced by 3-dimensional porous microbial anodes: A critical review, 2019. doi:10.1016/j.biortech.2019.121641.

[48] K. Venkateswaran, D. P. Moser, M. E. Dollhopf, D. P. Lies, D. A. Saffarini, [725] B. J. MacGregor, D. B. Ringelberg, D. C. White, M. Nishijima, H. Sano, J. Burghardt, E. Stackebrandt, K. H. Nealson, Polyphasic taxonomy of the genus Shewanella and description of Shewanella oneidensis sp. nov., International Journal of Systematic Bacteriology 49 (1999) 705–724. doi:10.1099/00207713-49-2-705.

[730] [49] L. Zou, Y. Qiao, Z. Y. Wu, X. S. Wu, J. L. Xie, S. H. Yu, J. Guo, C. M. Li, Tailoring Unique Mesopores of Hierarchically Porous Structures for Fast Direct Electrochemistry in Microbial Fuel Cells, Advanced Energy Materials 6 (2016) 1501535. doi:10.1002/aenm.201501535.