Extracellular Matrix Hydrogels Promote Expression of Paxillin, a Muscle-Tendon Junction Marker

Lewis S. Gaffney[a] BS., Matthew B. Fisher[a,b] PhD. and Donald O. Freytes[a] PhD.

[a] Department of Biomedical Engineering, North Carolina State University, Raleigh, NC 27695, USA and University of North Carolina at Chapel Hill, Chapel Hill, NC 27599, USA
[b] Department of Orthopaedics, University of North Carolina School of Medicine, Chapel Hill, NC 25799, USA

Working Title: ECM Hydrogels Promote Expression of Paxillin

***Corresponding authors and author contact information:**
*Matthew B. Fisher, Ph.D.
Associate Professor, Department of Biomedical Engineering
North Carolina State University & University of North Carolina at Chapel Hill

4130 Engineering Building III
Raleigh, NC 27695-7115
Phone: 919-515-5242
Email: mbfisher@ncsu.edu

*Donald O. Freytes, Ph.D.
Assistant Professor, Department of Biomedical Engineering
North Carolina State University & University of North Carolina at Chapel Hill

4130 Engineering Building III
Raleigh, NC 27695-7115
Office: 919-513-7933
dofreyte@ncsu.edu
dfreytes@unc.edu

Lewis Gaffney, BS

4130 Engineering Building III
Raleigh, NC 27695-7115

lsgaffne@ncsu.edu
Phone:919-395-8690

Keywords: **Extracellular Matrix, Engineered Tissues, Myotendinous Junction, Paxillin**

Abstract:

Muscle and tendon injuries are prevalent and range from minor sprains and strains to traumatic, debilitating injuries. However, the interactions between these tissues during injury and recovery remain unclear. Three-dimensional tissue models that incorporate both tissues and a physiologically relevant junction between muscle and tendon may aide in understanding how the two tissues interact. Here, we use tissue specific extracellular matrix (ECM) derived from muscle and tendon to determine how cells of each tissue interact with the microenvironment of the opposite tissue resulting in junction specific features. ECM materials were derived from the achilles tendon and gastrocnemius muscle, decellularized, and processed to form tissue specific pre-hydrogel digests. C2C12 myoblasts and tendon fibroblasts were cultured in tissue-specific ECM conditioned media or encapsulated in tissue-specific ECM hydrogels to determine cell-matrix interactions and the effects on a muscle-tendon junction marker, paxillin. ECM conditioned media had only a minor effect on upregulation of paxillin in cells cultured in monolayer. However, cells cultured within ECM hydrogels had 50-70% higher paxillin expression than cells cultured in type I collagen hydrogels. Contraction of the ECM hydrogels varied by the type of ECM used. Subsequent experiments with varying density of type I collagen (and thus contraction) showed no correlation between paxillin expression and the amount of gel contraction, suggesting that a constituent of the ECM was the driver of paxillin expression in the ECM hydrogels. Using tissue specific ECM allowed for the de-construction of the cell-matrix interactions similar to muscle-tendon junctions to study the expression of MTJ specific proteins.

Impact Statement: The muscle-tendon junction is an important feature of muscle-tendon units; however, despite cross-talk between the two tissue types, it is overlooked in current research. Deconstructing the cell-matrix interactions will allow the opportunity to study significant junction specific features and markers that should be included in tissue models of the muscle-tendon unit, while gaining a deeper understanding of the natural junction. This research aims to inform future methods to engineer a more relevant multi-tissue platform to study the muscle-tendon unit.

1. Introduction:

Musculoskeletal injuries involving muscle and tendon are prevalent and range from minor sprains and strains to debilitating injuries from volumetric muscle loss or tendon rupture.[1] In addition to acute injuries, muscle and tendon disorders can be caused by aging, dystrophies and inflammation.[2] Muscle and tendon tissue are inherently capable of healing after minor injuries, but in the case of massive defects or disease, loss of function can occur. Regenerative medicine is a promising new area to combat loss of function, and greatly improve the quality of life for those affected. Currently researchers in regenerative medicine have made great improvements in single tissue engineering, but there are far fewer engineered tissue systems that incorporate interfaces, including the muscle-tendon junction.

A crucial part of the muscle-tendon unit is the myotendinous junction, which transmits the contractile force of the muscle through the tendon to the skeletal system (Figure 1). At the myotendinous junction, muscle cells anchor to tendon matrix through the integrin-mediated complex.[3] The integrin-mediated complex is made up of several intracellular proteins including: paxillin, vinculin and talin.[3] In tendon fibroblasts, paxillin is an important component of cell

adhesion, motility and is linked to focal adhesion turnover, all of which are important factors in regeneration of tendon.[4] As tendon fibroblasts mature, paxillin localization in the cell membrane decreases along with other focal adhesion proteins leading to decreased cell motility which has implications for healing in mature tendon.[5] Paxillin expression in muscle cells occurs at the junction, where the sarcolemma binds to tendon ECM forming numerous focal adhesion complexes in response to mechanical stimulation.[3, 6] The specialized attachment (not present throughout the rest of the muscle tissue) is an example of specific structural component for muscle cells present at the myotendinous junction that could play a vital role in the function of the muscle-tendon unit. Figure 1C and D show increased paxillin localization where muscle fibers meet tendon ECM indicated by the white dashed line and arrows. While there is some understanding of the cellular response to various disorders in muscle and tendon tissue individually, there is less understanding of how disorders in a single tissue may further inhibit reparative processes and decrease function of the muscle-tendon unit.[2]

Currently, there are a limited number of techniques that aim to re-capitulate the multi-phasic structure of the MTJ, including the native interface between the tissues. The first multi-phasic tissues to model the muscle-tendon unit were engineered by seeding muscle cells onto a fibroblast monolayer, creating an inner muscle tissue and outer tendon-like tissue which expressed MTJ specific integrins.[7] These constructs expressed paxillin, although the protein expression was not localized to the interface of the cells. More recently 3D printing with bio-inks and poly-caprolactone has been used to create an interface between fibroblasts and muscle cells.[8, 9] 3D printing was successful in spatially organizing the two cell types and allowing for differentiation of the cells to form multi-phasic muscle-tendon constructs. However,

these systems relied on cell-cell interactions to produce MTJ expression and did not incorporate the extracellular matrix (ECM) microenvironment that exists within the muscle-tendon unit, which prevented the ability to analyze how specific cells at the junction interact with the environment of the opposite tissue, resulting in junction specific phenotypes and proteins.

Controlling cell interactions with the ECM microenvironment of the MTJ may allow localization of protein expression and formation of native-like focal adhesion in cell construct models. Beyond mechanical cues, ECM materials derived from tissues contain tissue-specific factors after decellularization and processing, which can influence cell behaviors.[10, 11] ECM materials contain tissue specific composition of ECM proteins and growth factors contribute to inherent bioactivity.[12] This tissue specific composition has been known to influence cell phenotypes such that stem cells or progenitor cells differentiate along similar pathways to the source tissues.[12] Examples include decellularized bone[13], muscle[14-17] and tendon[18-20], where in each case, ECM increased expression of tissue specific cell phenotypes *in vitro* or functionality of the tissues after healing *in vivo*. More recently, decellularized muscle-tendon units were used *in vivo* and *in vitro* to increase myogenic expression in satellite cells and improve function in a muscle defect model compared to a collagen implant alone.[21] However, such models do not allow us to determine how cells interact with neighboring tissue ECM.

The objective of this research is to determine if tissue specific ECM can promote expression of MTJ integrin associated proteins in myoblast and fibroblast cells. Using ECM materials derived from muscle and tendon allows for the culture of muscle and tendon cells in a three-dimensional microenvironment similar to a muscle-tendon unit. ECM materials can provide an extra component of signaling to cells cultured within the tissues that goes beyond cell-cell

interactions. Incorporating a microenvironment similar to native tissue, where muscle cells are in contact with tendon ECM and tendon cells in contact with muscle ECM could add function to *in vitro* models that have muscle and tendon components. Here, we present methods to deconstruct the myotendinous junction by using tissue specific ECM with different cells to study how cells interact with the opposite tissue's microenvironment.

Figure 1: ECM interactions and paxillin expression at the myotendinous junction. A) Graphical description of ECM-cell interactions at the myotendinous junction. Where muscle and tendon meet, cells within one tissue interact with ECM of the other tissue. This interaction could be responsible for production of MTJ specific proteins such as paxillin, which is part of the integrin mediated complex attaching muscle cells to tendon ECM. B) A mouse muscle tendon unit (achilles tendon and gastrocnemius muscle) dissected from mouse hindlimb was sectioned for C) hematoxylin and eosin staining, the dashed line indicating the junction of muscle and

tendon, D) anti-paxillin immunohistochemical staining. Arrows in C and in D indicate the junction of tendon (bottom) and muscle (top). In D, at the junction there is localization of paxillin expression in the ends of large muscle fibers, where the sarcolemma interacts and binds to tendon ECM through the accumulation of focal adhesion complexes containing paxillin.

2. Methods:

2.1 Muscle and Tendon derived ECM Hydrogels

Extracellular matrix materials were derived from porcine tissue harvested from 3-18 month old pigs (NCSU Swine Education Unit, Raleigh, NC). To obtain specific tissues, gastrocnemius muscle and achilles tendon were excised as a muscle-tendon unit from the lower shank of the pigs. Achilles tendon was dissected distal to the myotendinous junction and cleaned of connective tissue. Gastrocnemius was separated from the tendon proximal to the myotendinous junction and cleaned of connective tissue. (Figure 2A, upper left) Both muscle and tendon tissues were then washed and sliced into patches less than 1mm thick and frozen at -80⁰C.

Tissues were decellularized with adaptations from a previously described method[17]. Muscle and tendon tissue were washed separately in 50ml conical tubes with the protocol detailed in Table 1. Decellularized tissues were then lyophilized then ground in a mill to yield a powder (Figure 2A, lower left). Tissue specific hydrogels for muscle and tendon (m-ECM and t-ECM) were produced from the powder by digesting with 20:1 weight ratio of pepsin from porcine submucosa (Sigma-Aldrich) in .01 M HCl at a concentration of 10mg/ml. ECM digests (Figure 2A, lower right) were neutralized and buffered, m-ECM and t-ECM self-assembled to form stable hydrogels after 45 minutes at 37⁰C.

Table 1- Muscle and Tendon Decellularization Protocol

Solution	Time
.2%Trypsin/EDTA	2 hrs.
DI Water	30 min.
2X PBS	30 min.
.5% Sodium Deoxycholate	5 hrs.
DI Water	30 min.
2X PBS	30 min.
.5% Sodium Deoxycholate	14-16 hrs.
1%Triton X-100	1 hr.
DI Water	30 min.
.1% Peracetic Acid/4% Ethanol	2 hrs.
1X PBS	30 min. (2X)
Di Water	30 min. (2X)

Table 1: Decellularization protocol details for muscle and tendon tissue based on protocol from Wolf et. al.[17] Tendon and muscle tissues were washed in separate 50 ml conical tubes in each of the solutions for the detailed amount of time.

2.2 Cell Isolation and Preparation

C2C12 mouse myoblast cells were obtained from ATCC (C2C12s). Mouse tendon fibroblasts (TFs) were isolated from mouse Achilles tendon. Both cell-lines were cultured in proliferation media: Dulbecco's Modified Eagle Media, DMEM (Thermofisher), 10% FBS (Genesee Scientific) and 1% Penicillin Streptomycin (Thermofisher). Cells were used for experiments between passage 3 and passage 10 (within previously used ranges for C2C12s and 3T3 fibroblast cells).[17]

2.3 Presence of MTJ Expression in Cells Cultured with ECM Conditioned Media

C2C12s were seeded on cell culture plates and allowed to attach overnight. 400ug/ml of either type I collagen, mECM or tECM was added to supplement media (Figure 3A). 400ug ECM/ml of media has been previously described to influence macrophage phenotypes[22] and was the limit of ECM concentration before gelation of media started to occur. Cells were lysed

on day 5 for gene expression analysis. 3 separate experimental replicates of 2 individual wells, combined after culture, were analyzed for gene expression analysis. RNA was isolated using EZNA RNA isolation kits (Omega Bio-Tek). PCR analysis was done using SYBR Green (ThermoFisher) and primers for GAPDH (forward: AGGTCGGTGTGAACGGATTTG, reverse: GGGGTCGTTGATGGCAACA) and Paxillin (forward: AACGGCCAGTGTTCTTGTCAG, reverse: CACCGCAATCTCCTGGTATGT). Paxillin gene expression was determined with q-PCR, and $\Delta\Delta$CT was normalized to housekeeping gene, GAPDH, then normalized to media supplemented with type I collagen.

2.4 Paxillin Expression in Cells seeded in Tissue Specific ECM Tissue

Custom PDMS wells (15 mm x 10 mm x 4 mm) with two posts 8 mm apart and 2 mm in diameter were used to support 3D culture as tissues would contract around the posts. C2C12s and TFs were detached and suspended in either 5mg/ml type I collagen, 5mg/ml mECM or 5mg/ml tECM at 1×10^6 cells/ml of gel. The cell-laden ECM was seeded into the custom inserts to allow for culture. Gels were allowed to self-assemble for 30 min at 37C to fully form. After which proliferation media was used to culture tissues (Figure 4A). Tissues were cultured for 5 days, and media was changed at D3. At the conclusion of culture, the tissues were fixed and sucrose treated to improve sectioning. Tissues were cryo-sectioned at 10 μm. Samples were permeabilized, blocked, then treated with rabbit anti-paxillin antibody (Millipore-Sigma) at 1:100 dilution, anti-rabbit donkey AlexaFluor 594 (Invitrogen) and sealed with Prolong Anti-Fade mountant with DAPI (Thermofisher). For image analysis, 6 measurements per sample were used, more detail is described in Supplemental Figure 1. The ratio of TXRed and DAPI positive areas was defined as the Expression Index (E.I.) (Supplemental Figure 1). Percent

contraction was determined using ImageJ to calculate the area of the tissue at the time of seeding and at 5 days, when the tissue had fully contracted (Supplemental Figure 2).

2.5 Paxillin Expression due to Contraction of ECM Tissue

Similar to ECM hydrogels for 3D culture, custom inserts were used to seed ECM hydrogels. C2C12s were seeded in 2mg/ml and 5mg/ml type I collagen (low-Col., high-Col. respectively) and 5mg/ml tECM at a cell density of $2x10^6$ cells/ml of gel. Tissue construct contraction was predicted in low-Col. and tECM (Figure 5A). Cells were cultured in proliferation media and analyzed in the same manner as ECM hydrogels for 3D culture.

2.6 Statistical Methods

To quantify decellularization, percent removal of DNA was calculated for decellularized tendon and muscle by normalizing amount of DNA in a sample prior and after decellularization. In ECM conditioned media experiments gene expression for Paxillin was measured with q-PCR in 3 different experimental samples per media condition. One-way ANOVA between media groups were paired by experimental replicates with Tukey post-hoc analysis. For 3D ECM tissues, n=3 biological samples were sectioned at 3 depths (TFs in type I collagen had n=2 biological samples, due to sample fracture during sectioning) and imaged in 2 areas (Supplemental Figure 1). Expression Index was measured 6 times for each biological sample (3 depths and 2 areas per depth) and averaged for n=3 biological replicates. One way ANOVA between tissue ECM was run using n=3 of biological replicate averages with Bonferroni's multiple comparisons tests. Analysis was done separately for C2C12s and TFs. Similar to 3D ECM Tissues, E.I. measurements of 3 sections and 2 areas per section for each biological replicate were averaged for each biological replicate. To determine statistical significance in contraction experiments, one way ANOVA compared percent contraction in each ECM group

which had a biological replicate of n=3. Similar to 3D ECM tissues, paxillin expression in contracted tissues was compared with one way ANOVA comparing the averages of n=3 biological replicates with Tukey's multiple comparisons tests.

3. Results

3.1 Muscle and tendon can be decellularized to yield tissue specific hydrogels

Porcine muscle and tendon tissue (Figure 2A) were decellularized using the same decellularization protocol, and both were successfully digested to form hydrogels. Removal of DNA was 98% for muscle tissue and 96% for tendon tissue, determined with PicoGreen DNA quantification assays (Figure 2B). Additionally, H & E staining of tissue showed removal of cell nuclei (Figure 2C) confirming DNA removal and retention of some ultrastructural features, like collagen crimp in decellularized tendon. The gross tissue structure of decellularized ECM is disrupted, likely due to freezing and thawing of tissue before decellularization. While this may be a concern in other applications, the ECM is digested completely for use in a hydrogel so native macrostructure does not need to be maintained. In addition, ECM tissues and type I collagen were stained for DAPI and anti-paxillin to verify removal of nuclear content and that there was no presence of the paxillin integrin within the matrix, all of the tissues were negative for those proteins.

Figure 2: Decellularization methods of separate muscle and tendon. A) Porcine muscle tendon unit was excised from hindlimb, upper left, (shown still connected, for separated materials, muscle and tendon were separated) and decellularized, upper right. Tissues were lyophilized and ground into powder, lower left, and digested with pepsin, lower right. B) Presence of DNA was measured with PicoGreen assays. DNA content in native tissue was used to normalize %DNA removal. Muscle and tendon had a mean of 98% and 96% less DNA than native tissue after decellularization, respectively (n=3, mean represented by bar). C) Hematoxylin and eosin stains before and after decellularization also confirms removal of nuclear material from muscle and tendon. Scale bars are 200 μm.

3.2 ECM conditioned media does not promote paxillin

To assess bioactivity of the digested ECM materials independent of any structural cues, C2C12s were cultured in media supplemented with digested tissue specific ECM (Figure 3A). Relative to controls, mean paxillin expression increased by 65% and 74% in mECM and tECM conditioned media, respectively (Figure 3B). Relative paxillin gene expression had high

variability between biological replicates in each of the ECM supplementation groups, and there was no statistically significant effect of media supplementation (p=0.19).

Figure 3: C2C12s cultured in ECM conditioned media did not have a noticeable effect on paxillin expression. A) C2C12s were seeded in cell culture plates, then cultured in proliferation media supplemented with type I collagen, mECM or tECM at a concentration of 400ug/ml of media. B) qPCR analysis did not show significant difference in paxillin expression between cells grown in ECM conditioned media and type I collagen conditioned media (p>0.05). ΔCT was normalized to housekeeping gene GAPDH, data is presented as fold change of ΔCT with the mean and individual data points of n=3 experimental replicates and colors representing paired replicates.

3.3 3D ECM hydrogels promoted paxillin expression

To create a more physiologic microenvironment, C2C12s and TFs were embedded within 3D hydrogels made from tissue specific ECMs (Figure 4A). Cells cultured in 3D tissues had different levels of gel contraction after 5 days of culture (Supplemental Figure 2) resulting from contractile forces of the cells in the matrix expelling water from the hydrogel. C2C12s and TFs in type I collagen contracted least of all the tissue groups with little to no noticeable decrease in surface area. mECM tissues had a more variable decrease in area, while tECM consistently contracted.

Via fluorescence imaging, C2C12s had the highest paxillin expression when cultured in the tendon ECM (Figure 4B). TFs also had higher expression in tissue derived ECM than when cultured in type I collagen. Cells in type I collagen did not seem to align within the matrix, while C2C12s in mECM and tECM, and TFs in tECM had more alignment. This is likely due to contraction within the gel providing some mechanical signaling. Furthermore, contraction seemed to increase cell density, which is expected contracted gels have reduced volume for the same number of seeded cells. Cell density was not quantified after culture, so it was not determined if cells in ECM tissues were also proliferating more compared to collagen. In type I collagen, rounded cells had some paxillin expression, whereas in other groups, especially C2C12s in tECM, paxillin expression seemed to be upregulated all around the cell and throughout the matrix. It was verified that paxillin was not present in any of the ECM materials used for the 3D tissues. Finally, in tissues with higher levels of paxillin expression, the highest level of positive staining seemed to occur in areas where more cells were in contact with each other.

Fluorescence images were quantified using a ratio of positive signal area of each channel that we define as E.I. (Supplemental Figure 1). Within each sample, measurements at

different depths and areas had similar ranges of values, showing that that staining wasn't concentrated in different parts of the ECM tissues. One way ANOVA was used to compare these differences across the 3 biological replicates. Similar to quantitative images, there is an increase in expression in ECM tissues compared to type I collagen (Figure 4C). The highest E.I. occurred in C2C12s in tECM, with a mean 68% higher than C2C12s cultured in type I collagen (p<0.05). C2C12s in mECM had a mean increase of 48% over those cultured in type I collagen (p>0.05). TFs exhibited similar expression patterns, with the mean E.I in mECM and tECM tissues being 75% and 71% higher, respectively, than in type I collagen In that comparison, both groups had a significant increase over type I collagen at p<0.05. In contrast to supplementing media with ECM, culturing C2C12s and TFs in tissue specific ECM caused an up regulation of paxillin expression in both cell types.

Figure 4: C2C12s and TFs seeded in 3D hydrogels had higher expression of paxillin in ECM tissues after being cultured for 5 days in proliferation media. A) C2C12s or TFs were suspended in type I collagen, mECM or tECM pre-gelation, then seeded in custom inserts for culture. Stable hydrogels were cultured in proliferation media for 5 days, before they were cryo-sectioned and stained. B) Representative fluorescent images of sections stained with anti-paxillin rabbit antibody and DAPI, showed that cells in ECM groups became more concentrated most likely due to contraction of the ECM tissue, where cells in type I collagen did not contract. Additionally, cells in ECM tissues had more positive staining for paxillin, shown in red here. Scale bars are 200 um. C) Paxillin protein expression was quantified using an expression index, which was defined as the positive area for TXRed channel normalized to the positive area for DAPI. Colors indicate measurements within the same tissue sample. Different colors represent different tissue samples. Mean values for each tissue sample are presented in the foreground with mean and SD for each condition. In C2C12s, tECM had the highest expression index, which was significantly different from type I collagen tissues. In TFs, both ECM tissues had significant increases compared to type I collagen tissues. Asterisks indicate a significant difference between ECM tissues and type I collagen (p<0.05), determined with one-way ANOVA (n=3 samples; 6 E.I. measurements per sample).

3.4 Contraction of tissues does not lead to paxillin expression

In previous experiments, tissue construct contraction was dependent on the ECM material (Supplemental Figure 2). Independent of what cells were used in the tissue constructs, tECM constructs had the most contraction, while type I collagen Constructs contracted least. To verify that varying levels of gel contraction did not have an effect on paxillin expression, C2C12s were cultured in 2 different concentrations of low-Col. and high-Col., yielding a non-

contracting tissue construct and a contracting tissue construct respectively as well as tECM, which also yielded a contracting tissue construct.

C2C12s were cultured for a period of 5 days in proliferation media in each of the three tissue environments. Representative images are shown at day 5 of culture in Figure 5B. There is a clear decrease in surface area in the low-Col. tissue and in the tECM tissue group while the high-Col. tissue does not seem to have any change from the initial area of the hydrogel at the time of seeding. This decrease was quantified using ImageJ, by measuring the outline of the tissue construct at the end of the 5 day culture period. Overall, the high-Col. tissues had a mean decrease in area of only 3%, while the contracted tissues low-Col. and tECM had decreases in area of 62% and 68%, respectively (Figure 5D). The contracted tissues were significantly more contracted than high-Col., with $p < 0.0001$.

Representative fluorescent images are shown in Figure 5C. Similar to previous findings, high-Col. did not have a lot of positive staining for paxillin, while the tECM had clear paxillin expression, corroborating the results from 3D ECM tissues, even with the increased cell density. Interestingly, low-Col. did not have an increase in positive staining compared to high-Col., even though the tissue contracted similarly to tECM. Paxillin expression was quantified with image quantification methods previously described. Overall tECM had double the expression of the type I collagen groups. One-way ANOVA was used for analysis of the 3 biological replicates (each with 6 measurements for EI), in which tECM had a statistically significant increase in E.I. of paxillin ($p < 0.01$).

Figure 5: Contraction of hydrogel tissues did not induce paxillin expression. A) C2C12s were encapsulated in 2 concentrations, 5mg/ml and 2mg/ml, of type I collagen, and in 5mg/ml tECM. The formed tissues were cultured for 5 days in proliferation media before cryosectioning and staining. B) Brightfield images of tissues after 5 days of culture showed that decreasing the concentration of type I collagen allowed the cells to contract the tissue similar to tECM. Scale bars are 5 mm. C) Fluorescent images showing paxillin (red) and DAPI (blue) seemed to follow trends from other 3D tissues in that type I collagen did not have high paxillin expression, while tECM had higher expression. Scale bars are 200 um. D) Contraction was quantified by normalizing area of the contracted gels to the area of the seeded tissue after gelation, the mean contraction of 3 individual samples is shown here. The lower concentration of type I collagen and tECM both had higher contraction than the high concentration of type I collagen. Colors represent different ECM tissues. Four asterisks indicate a significant difference between contracted tissue constructs and 5mg/ml type I collagen constructs (p<0.0001)

determined with one way ANOVA (n=3 samples). E) Paxillin expression was quantified with the expression index method previously mentioned. Both type I collagen groups had significantly lower expression of paxillin compared to tECM. While tissues made from at 2mg/ml type I collagen did contract, they did not have increased paxillin expression suggesting contraction does not increase this expression. Different colors represent different tissue samples, and E.I. measurements.   Mean values for each sample is presented in the foreground, with mean and SD for each condition.   Two asterisks indicate a significant difference between ECM tissues and type I collagen (p<0.01), determined with one-way ANOVA (n=3 samples; 6 E.I. measurements per sample).

4. Discussion

The myotendinous junction consists of unique ECM, structural features, cell-matrix and cell-cell interactions.[23] Understanding how the unique aspects of the junction are formed and how they are maintained are important to inform regenerative medicine strategies to alleviate loss of tissue function in the event of disorders or traumatic injury. In this study, we hypothesized that myoblasts and tenocytes would be influenced by a tissue-specific microenvironment, resulting in a junction-like cellular response. In the present study, we focused on the expression of junction-specific protein (paxillin) and the use of muscle and tendon derived extracellular matrix hydrogels to mimic the composition of the respective tissue microenvironments. Cells cultured in monolayer on tissue culture plastic with media supplemented with tissue-specific ECM did not show increased paxillin protein expression compared to type I collagen supplemented media. However, C2C12 and TF cells cultured within ECM hydrogels showed increased paxillin protein expression compared to type I collagen Even though these ECM constructs contracted over time, the contraction had no

effect on paxillin expression, supporting the hypothesis that ECM-specific components were the driving force behind the increase in paxillin expression. The *in vitro* system presented here offers a unique method to study cell-matrix interactions by de-constructing the junction to study how cells interact with opposite matrix and how that may drive junction specific cell attachment to the matrix.

Tissue specific ECMs have emerged as a unique biomaterial class that promotes regenerative phenotypes in immune cells and attracts stem cells as it is broken down.[12] Tissue specific ECM derived from muscle and tendon has been used in previous *in vitro* and *in vivo* studies[15-20] but junction specific interactions remains under-explored. Here we use the ECM from muscle and tendon together to determine the effects of tissue specific cell-matrix interactions to model the junction where cells of one tissue may be in contact with matrix of the other tissue. These materials were derived from porcine achilles tendon and gastrocnemius by excising muscle tendon units and then separating the two tissues. While many labs use tissue-specific decellularization protocols, this study used the same process for both musculoskeletal tissues allowing for direct comparison between the inherent signals present within each tissue-specific ECM. The protocol modified from Wolf et al[17] was effective for both tissues, with muscle and tendon ECM having about 3%-4% of the original DNA content remaining. This removal was confirmed with hematoxylin and eosin staining before and after the decellularization protocol. This unique approach to modelling the MTJ allowed for cells of one tissue to be in contact with matrix from the other tissue which could have clues to how matrix of opposite tissues influences development and maintenance of the junction.

Tissue specific ECM has been used in several forms including lyophilized sheets, powders to supplement media and in a hydrogel form.[24] Tissue specific ECM in solubilized

form as a media supplement can influence immune cells[22] and stem cells.[25] To determine if solubilized ECM affected C2C12s, solubilized mECM and tECM was added to proliferation media during monolayer culture on tissue culture plastic. The solubilized matrix did not change the expression of paxillin when compared to type I collagen supplementation. The lower overall concentration of tissue specific material in the supplemented media could be below a threshold needed to illicit a cell response. This was the upper limit for supplementing media with muscle and tendon ECM as higher concentrations resulted in gelation of the media. Additionally, myoblast cells may not express MTJ specific integrins attaching to tissue culture plastic in monolayer. This consistent with observations by Merceron et.al., where myoblasts and fibroblasts in contact with synthetic materials did not form native focal adhesions without being in contact with natural ECM.[8]

ECM hydrogels allow cells to be suspended in the matrix, which creates a more relevant microenvironment for the cells to attach and spread, compared to monolayer culture. The cell-laden hydrogels had varying levels of contraction with tECM tissues having the largest decrease in surface area. Paxillin was expressed more in myoblast cells seeded in tECM compared to type I collagen There was also more expression in cells seeded in mECM, albeit not as much of an increase than in tECM. Similarly, paxillin was expressed more in tenocytes when cultured in tissue specific matrix when compared to type I collagen While 3D culture of cells in hydrogel tissues may have upregulated paxillin expression, the increased expression was not as evident when cells were cultured in 3D type I collagen hydrogels. This suggests that cells cultured in tissue specific ECM interacted with the matrix differently than in type I collagen This finding also supports the notion that our model can produce integrin expression in myoblasts and tendon fibroblasts that is known to be expressed at the myotendinous

junction. Additionally, there was differential expression of the same cells in one matrix compared to another. This exemplifies an interesting characteristic of these tissue constructs, the ECM hydrogels promoted MTJ integrins and it can be determined which cell-matrix interaction had the greatest upregulation. This is useful information because we can begin to dissect specific interactions that may contribute to the development of the junction. It also supports inclusion of a native-like MTJ in 3D tissue models to study the function, development, and maintenance of muscle-tendon units.

The varying levels of contraction of the 3D engineered tissue presented a unique challenge. While seeding densities and concentrations of ECM were consistent at the time of producing the cell-laden constructs, these variables did not stay constant over the period of culture due to the change in construct volume. The E.I. method used to quantify paxillin expression was a ratio of the positive area of TxRed and the positive area of DAPI to normalize to the cell density within tissue constructs. To verify that paxillin expression was not a result of the mechanical properties changing in contracted tissues, the cell-laden hydrogels were adjusted to allow contraction of type I collagen tissues that resembled the contraction of tECM tissues. By lowering the concentration of type I collagen to 2mg/ml, the cell constructs had a similar decrease in surface area as the tECM constructs. However, expression of paxillin was similar to high-Col. constructs, that did not contract. So, while the contraction may have influenced cell density and the mechanical environment, up-regulation of paxillin was only evident in the tissue specific ECM.

This study is not without limitations. We focused on one marker known to be present at the myotendinous junction but is present in many other tissues and cell types and it is focused on cell types in isolation from each other, without any cell-cell interactions. Protein analysis of

the ECM of muscle-tendon units revealed that there are several proteins, specifically type V alpha3 collagen, and type XXII alpha 1 collagen, that occur primarily at the junction.[23, 26] Research into this specific protein synthesis could inform strategies for development of native-like muscle-tendon interfaces, increasing the function and efficacy of engineered muscle-tendon units. Future studies should include analysis of additional MTJ specific proteins like type XXII collagen along with cell signaling pathways leading to increased focal adhesion expression. De-construction of the muscle tendon unit may provide some insight to specific proteins and features of the MTJ; however, we are only examining individual cell types interacting with a single matrix. An accurate model of the muscle tendon unit should include incorporation of both cell types, interacting in their own environments as well as with the opposite environment. Incorporating the information obtained here in a multi-tissue model will allow for the study of the muscle tendon unit with a junction or interface component. This should be considered an important inclusion for muscle tendon unit models as proteins such as paxillin are upregulated natively with mechanical loading, and lack thereof negatively effects the integrity of the junction.[7] This research plays a vital role in determining composition of an interface region that can be used within a more complex multi-tissue model.

5. Conclusion

Overall, the objective of this study was to determine how cell-matrix interactions play a role in regulating paxillin expression by myoblast cells. Tissue specific materials did modulate the expression of paxillin when used to culture cells in 3D. This finding is useful information for the development of a muscle tendon unit *in vitro* model that incorporates the two tissue types and a junction between them. A model like this could be used to determine how the effects of

cross-talk between cell populations play a role in development and maintenance of the specialized interface.

Acknowledgements: The authors would like to acknowledge Amber Detwiler for her work on the contraction analysis of the tissues.

Author Contributions: LG wrote the manuscript, planned and executed the studies presented. MF and DF wrote the manuscript, planned experiments and oversaw execution of the studies presented.

Author Disclosure Statements: The Authors have no conflicts to disclose

Funding Statements: The Authors have no funding to state.

Citations:

1. Romitti, P.A., Zhu, Y., Puzhankara, S., James, K.A., Nabukera, S.K., Zamba, G.K., Ciafaloni, E., Cunniff, C., Druschel, C.M., Mathews, K.D., Matthews, D.J., Meaney, F.J., Andrews, J.G., Conway, K.M., Fox, D.J., Street, N., Adams, M.M., Bolen, J., andSTARnet, M.D. Prevalence of Duchenne and Becker muscular dystrophies in the United States. Pediatrics **135**, 513, 2015.

2. Balestri, W., Morris, R.H., Hunt, J.A., andReinwald, Y. Current Advances on the Regeneration of Musculoskeletal Interfaces. Tissue Eng Part B Rev 2021.

3. Jarvinen, T.A., Jarvinen, T.L., Kaariainen, M., Kalimo, H., andJarvinen, M. Muscle injuries: biology and treatment. The American journal of sports medicine **33**, 745, 2005.

4. Tsai, W.C., Hsu, C.C., Chen, C.P., Chen, M.J., Lin, M.S., andPang, J.H. Ibuprofen inhibition of tendon cell migration and down-regulation of paxillin expression. Journal of orthopaedic research : official publication of the Orthopaedic Research Society **24**, 551, 2006.

5. Arnesen, S.M., andLawson, M.A. Age-related changes in focal adhesions lead to altered cell behavior in tendon fibroblasts. Mech Ageing Dev **127**, 726, 2006.

6. Graham, Z.A., Gallagher, P.M., andCardozo, C.P. Focal adhesion kinase and its role in skeletal muscle. J Muscle Res Cell Motil **36**, 305, 2015.

7. Larkin, L.M., Calve, S., Kostrominova, T.Y., andArruda, E.M. Structure and functional evaluation of tendon-skeletal muscle constructs engineered in vitro. Tissue Eng **12**, 3149, 2006.

8. Merceron, T.K., Burt, M., Seol, Y.J., Kang, H.W., Lee, S.J., Yoo, J.J., andAtala, A. A 3D bioprinted complex structure for engineering the muscle-tendon unit. Biofabrication **7**, 035003, 2015.

9. Laternser, S., Keller, H., Leupin, O., Rausch, M., Graf-Hausner, U., andRimann, M. A Novel Microplate 3D Bioprinting Platform for the Engineering of Muscle and Tendon Tissues. SLAS Technol **23**, 599, 2018.

10. O'Neill, J.D., Freytes, D.O., Anandappa, A.J., Oliver, J.A., andVunjak-Novakovic, G.V. The regulation of growth and metabolism of kidney stem cells with regional specificity using extracellular matrix derived from kidney. Biomaterials **34**, 9830, 2013.

11. Duan, Y., Liu, Z., O'Neill, J., Wan, L.Q., Freytes, D.O., andVunjak-Novakovic, G. Hybrid gel composed of native heart matrix and collagen induces cardiac differentiation of human embryonic stem cells without supplemental growth factors. J Cardiovasc Transl Res **4**, 605, 2011.

12. Gaffney, L., Wrona, E.A., andFreytes, D.O. Potential Synergistic Effects of Stem Cells and Extracellular Matrix Scaffolds. ACS Biomaterials Science & Engineering **4**, 1208, 2018.

13. Alom, N., Peto, H., Kirkham, G.R., Shakesheff, K.M., andWhite, L.J. Bone extracellular matrix hydrogel enhances osteogenic differentiation of C2C12 myoblasts and mouse primary calvarial cells. J Biomed Mater Res B Appl Biomater 2017.

14. McClure, M.J., Cohen, D.J., Ramey, A.N., Bivens, C.B., Mallu, S., Isaacs, J.E., Imming, E., Huang, Y.C., Sunwoo, M., Schwartz, Z., andBoyan, B.D. Decellularized Muscle Supports New Muscle Fibers and Improves Function Following Volumetric Injury. Tissue Eng Part A **24**, 1228, 2018.

15. Perniconi, B., Coletti, D., Aulino, P., Costa, A., Aprile, P., Santacroce, L., Chiaravalloti, E., Coquelin, L., Chevallier, N., Teodori, L., Adamo, S., Marrelli, M., andTatullo, M. Muscle acellular scaffold as a biomaterial: effects on C2C12 cell differentiation and interaction with the murine host environment. Front Physiol **5**, 354, 2014.

16. Perniconi, B., Costa, A., Aulino, P., Teodori, L., Adamo, S., andColetti, D. The pro-myogenic environment provided by whole organ scale acellular scaffolds from skeletal muscle. Biomaterials **32**, 7870, 2011.

17. Wolf, M.T., Daly, K.A., Reing, J.E., andBadylak, S.F. Biologic scaffold composed of skeletal muscle extracellular matrix. Biomaterials **33**, 2916, 2012.

18. Yang, G., Rothrauff, B.B., Lin, H., Gottardi, R., Alexander, P.G., andTuan, R.S. Enhancement of tenogenic differentiation of human adipose stem cells by tendon-derived extracellular matrix. Biomaterials **34**, 9295, 2013.

19. Ning, L.J., Zhang, Y.J., Zhang, Y., Qing, Q., Jiang, Y.L., Yang, J.L., Luo, J.C., andQin, T.W. The utilization of decellularized tendon slices to provide an inductive microenvironment for the proliferation and tenogenic differentiation of stem cells. Biomaterials **52**, 539, 2015.

20. Liu, H., Yang, L., Zhang, E., Zhang, R., Cai, D., Zhu, S., Ran, J., Bunpetch, V., Cai, Y., Heng, B.C., Hu, Y., Dai, X., Chen, X., andOuyang, H. Biomimetic tendon extracellular matrix composite gradient scaffold enhances ligament-to-bone junction reconstruction. Acta Biomater **56**, 129, 2017.

21. Zhao, C., Wang, S., Wang, G., Su, M., Song, L., Chen, J., Fan, S., andLin, X. Preparation of decellularized biphasic hierarchical myotendinous junction extracellular matrix for muscle regeneration. Acta Biomater **68**, 15, 2018.

22. Sicari, B.M., Dziki, J.L., Siu, B.F., Medberry, C.J., Dearth, C.L., andBadylak, S.F. The promotion of a constructive macrophage phenotype by solubilized extracellular matrix. Biomaterials **35**, 8605, 2014.

23. Narayanan, N., andCalve, S. Extracellular matrix at the muscle - tendon interface: functional roles, techniques to explore and implications for regenerative medicine. Connective tissue research **62**, 53, 2021.

24. Faulk, D.M., Johnson, S.A., Zhang, L., andBadylak, S.F. Role of the extracellular matrix in whole organ engineering. J Cell Physiol **229**, 984, 2014.

25. Williams, C., Quinn, K.P., Georgakoudi, I., andBlack, L.D. Young developmental age cardiac extracellular matrix promotes the expansion of neonatal cardiomyocytes in vitro. Acta Biomaterialia **10**, 194, 2014.

26. Jacobson, K.R., Lipp, S., Acuna, A., Leng, Y., Bu, Y., andCalve, S. Comparative Analysis of the Extracellular Matrix Proteome across the Myotendinous Junction. J Proteome Res **19**, 3955, 2020.