Modular biosynthesis of plant hemicellulose and its impact on yeast cells

Madalen Robert[1], Julian Waldhauer[1], Fabian Stritt[2], Bo Yang[1], Markus Pauly[2], Cătălin Voiniciuc[1,*]

[1] Independent Junior Research Group–Designer Glycans, Leibniz Institute of Plant Biochemistry,

06120 Halle (Saale), Germany

[2] Institute for Plant Cell Biology and Biotechnology, Heinrich Heine University, Düsseldorf, Germany

*For correspondence (email: catalin.voiniciuc@ipb-halle.de).

Abstract

Background: The carbohydrate polymers that encapsulate plants cells have benefited humans for

centuries and have valuable biotechnological uses. In the past five years, exciting possibilities have

emerged in the engineering of polysaccharide-based biomaterials. Despite impressive advances on

bacterial cellulose-based hydrogels, comparatively little is known about how plant hemicelluloses can

be reconstituted and modulated in cells suitable for biotechnological purposes.

Results: Here, we assembled cellulose synthase-like A (CSLA) enzymes using an optimized *Pichia*

pastoris platform to produce tunable heteromannan (HM) polysaccharides in yeast. By swapping the

domains of plant mannan and glucomannan synthases, we engineered chimeric CSLA proteins that

made β-1,4-linked mannan in quantities surpassing those of the native enzymes while minimizing the

burden on yeast growth. Prolonged expression of a glucomannan synthase from *Amorphophallus*

konjac was toxic to yeast cells: reducing biomass accumulation and ultimately leading to

compromised cell viability. However, an engineered glucomannan synthase as well as CSLA pure

mannan synthases and a CSLC glucan synthase did not inhibit growth. Interestingly, *Pichia* cell size

could be increased or decreased depending on the composition of the CSLA protein sequence. HM

yield and glucose incorporation could be further increased by co-expressing chimeric CSLA proteins

with a MANNAN-SYNTHESIS-RELATED (MSR) co-factor from *Arabidopsis thaliana*.

Conclusion: The results provide novel routes for the engineering of polysaccharide-based

biomaterials that are needed for a sustainable bioeconomy. The characterization of chimeric cellulose

synthase-like enzymes in yeast offers an exciting avenue to produce plant polysaccharides in a

tunable manner. Furthermore, cells modified with non-toxic plant polysaccharides such as β-mannan

offer a modular chassis to produce and encapsulate sensitive cargo such as therapeutic proteins.

Keywords: Cell wall biosynthesis, Hemicellulose, Glycosyltransferase, Chimeric enzymes, Mannan, Glucomannan, Glucan, *Pichia pastoris,* Synthetic biology

Background

Enzymes from the cellulose synthase superfamily produce the most abundant polysaccharides on Earth, including cellulose and a variety of hemicelluloses. Greater interest in the engineering of polysaccharide-based biomaterials has emerged in recent years. Synthetic biology efforts in this area have been largely restricted to bacterial cellulose due to its well-characterized production [1,2]. Several microbial organisms have been identified as suitable hosts for orthogonal polysaccharide production [3]. Chief among them is the industrial yeast *Pichia pastoris*, which was recently engineered into an autotroph capable of growing on the greenhouse gas CO_2 [4]. Despite this, comparatively little is known about how the biosynthesis of plant hemicelluloses by glycosyltransferases (GTs) could be reconstituted and modulated in non-plant cell factories. Heterologous expression systems are also needed to characterize the activities of cell wall biosynthetic enzymes, since these membrane-bound proteins are particularly difficult to purify in sufficient quantities from native plant tissues [5]. GTs from the Cellulose Synthase-Like (CSL) superfamily produce the backbones of xyloglucans, heteromannans (HM), as well as β-1,3-1,4-linked-glucans [6,7], which can account for one-third or more of the cell wall biomass. Of these polymers, HMs have the simplest structures since they can be found as linear β-1,4-linked mannans (defined as containing >90% mannose, Man), or as glucomannans that also contain β-1,4-linked glucose (Glc) units [8]. (Gluco)mannans can be decorated with galactose side chains [9,10] or *O*-acetylated [11,12], which increases their solubility [13]. HM is abundant in the endosperms of most legume seeds [14], and to a lesser extent in cereal grains [15], which confer important physiological properties, such as stabilizing the extracellular matrix. Since HMs are excellent thickening and gelling agents, locust bean gum (extracted from *Ceratonia siliqua*, also known as carob) and guar gum (from *Cyamopsis tetragonoloba*) are commonly used hydrocolloids in the food (approved as E410 and E412 stabilizers within the European Union), cosmetic and pharmaceutical industries.

HM backbones are elongated in the Golgi apparatus by CSL clade A (CSLA) enzymes from GDP-Man and GDP-Glc precursors. CSLAs are expected to function together with GT34 enzymes and/or *O*-acetyltransferases to produce branched hemicelluloses, in order to avoid intracellular self-

aggregation in the Golgi and thus facilitate their extracellular secretion [7]. Despite resembling CSLAs,

CSL family C (CSLC) proteins required for xyloglucan synthesis [16] have distinct numbers of

transmembrane domains, which can lead to opposite topologies at the Golgi membrane [17].

Recently, (gluco)mannan biosynthesis was reconstituted in the yeast *Pichia pastoris* (also known as

Komagataella phaffi) by expressing plant CSLA enzymes with or without MANNAN-SYNTHESIS-

RELATED (MSR) co-factors [18]. MSRs are putative GT that likely modulate (gluco)mannan

elongation by interacting with CSLA enzymes or post-translationally modifying them. The structure

and composition of HM, which varies widely between plant tissues, could be generated by GT

specificity and/or sugar substrate availability. There is increasing evidence for the former hypothesis,

since the *Amorphphallus konjac* AkCSLA3 produced glucomannan in yeast cells, while *Arabidopsis*

thaliana AtCSLA2 alone only made relatively pure mannan [18]. Even though AtCSLA2 participates in

galactoglucomannan elongation for Arabidopsis seed mucilage [9,19], the enzyme alone has a low

preference for Glc incorporation *in vitro* [20] or in living yeast cells without the co-expression of the

AtMSR1 protein co-factor [18].

To date, no study has looked specifically at how different CSLA protein motifs influence

(gluco)mannan biosynthesis. Domain swap experiments can provide insight into the structures and

functions of related enzymes. Previously, two studies reported domain swap experiments for CSLF

proteins involved in mixed-linkage glucan synthesis [21,22]. The expression of chimeric CSLF6

enzymes from several monocot species in *Nicotiana benthamiana* leaves revealed protein regions

that modulate β-1,3-1,4-linked-glucan structure. Tailoring the production of hemicelluloses could lead

to the engineering of grains enriched in fibers that are beneficial to human health [23], or could be

applied to engineer living materials with precisely controlled morphology and novel properties [1].

This study aimed to modulate the production of plant HM in a biotechnologically important

yeast and to assess the engineered cells (Fig. 1a), since they could provide a valuable chassis for

future biomaterial and therapeutic applications. We optimized the cultivation of *Pichia pastoris* for the

orthogonal production of plant hemicelluloses, and enhanced HM biosynthesis by assembling modular

CSLA enzymes. *Pichia* cells were promising hosts to study CSLC and CSLA activities [3,18,24,25],

but the impact of the plant polymers was not previously investigated. Here, we extend their utility by

improving the speed of chimeric enzyme expression and the hemicellulose yields. Prolonged

expression of the AkCSLA3 glucomannan synthase was toxic to yeast cells, but this impairment was

rescued by swapping its C-terminal region with that of AtCSLA2. Two additional chimeric CSLAs

enzymes enhanced plant mannan production compared to the native AtCSLA2 enzyme with minimal

impact on growth and morphology. This synthetic biology strategy could also be applied to other CSL

enzymes to synthesize sustainable hemicellulose-based materials.

Results

Modular Engineering of Cellulose Synthase-Like Enzymes and Cell Walls

To create chimeric CSLA proteins that modulate (gluco)mannan production, we first

compared AkCSLA3 and AtCSLA2 sequences. TOPCONS [26], which integrates multiple algorithms,

predicts that both proteins have a consensus topology with five transmembrane domains and a

catalytic site facing the cytosol (Fig. 1b). We delimited the proteins into four regions sharing 38% to

73% amino acid similarity, demarcated by border regions that contain at least 6 identical residues

(Fig. 1b). The second region contains most of the conserved GT2 domain (Pfam PF13641), which is

involved in transferring glycosyl residues. Following sequence domestication of AkCSLA3 and

AtCSLA2 to remove unwanted type IIS recognition sites, we amplified and assembled chimeric

CSLAs sequences using the GoldenPiCs toolkit (Fig. 1c) that contains a library of exchangeable parts

for *Pichia* expression [27]. Reciprocal chimeric constructs were created for each (gluco)mannan

synthase, each containing one swapped domain from AtCSLA2 or AkCSLA3 (Fig. 1d). The chimeric

constructs were labelled according to the origin of the four domains (e.g. 2322 contains the second

domain of AkCSLA3 and the other regions of AtCSLA2). The GoldenPiCs toolkit, which is based on

Golden Gate cloning [28], enabled the seamless assembly of multiple CSLA fragments in the desired

order, without introducing any mutations (Additional file 1). Once the coding sequences were verified,

they were assembled into a *Pichia* GoldenPiCs expression vector together with the strong methanol

inducible promotor *pAOX1* and a transcriptional terminator (Fig. 1c). Linearized transcriptional units

were stably integrated in the *AOX1* region of the *Pichia* genome, and Zeocin-resistant colonies were

verified by PCR to unambiguously confirm the chimeras (Additional file 2).

To efficiently compare the products of different GTs, we sought to improve the throughput and

cost of the yeast screening platform. Fluorescent reporters can speed up colony screening, but an N-

terminal superfolder green fluorescent protein (sfGFP) fusion inhibited AkCSLA3 activity in *Pichia* [18].

We therefore assembled and evaluated the functionality of modular C-terminal sfGFP fusions. Multiple

colonies expressed consistent levels of AkCSLA3-sfGFP and AtCSLA2-sfGFP fluorescent proteins

after methanol induction (Fig. 2a), albeit at reduced levels compared to sfGFP alone. While the

AkCSLA3-sfGFP produced alkaline-insoluble polymers rich in Man, fluorescently tagged AtCSLA2 did

not increase the relative content of Man compared to sfGFP and empty vector controls (Fig. 2b).

Since AtCSLA2 lost its activity when fused to fluorescent tags, we resorted to studying untagged

native and chimeric enzymes using an improved yeast growth protocol. Typically, *Pichia* cells are pre-

cultured for 24 to 60 h in complex buffered media containing glycerol, which promotes yeast biomass

accumulation but represses methanol-inducible promoters [18,24]. To avoid washing or long

incubation steps, we developed a streamlined method that uses autoclavable 24 deep-well plates

containing YP-based media (yeast extract, peptone, and at least one carbon source). We found that

AtCSLA2 and AkCSLA3 produced of significant amounts of alkaline-insoluble Man, even when

growing cells directly in YPM (YP Methanol medium; Fig. 2c). The addition of a limited amount of

glycerol upfront (YPM+G) increased the yeast biomass and HM production by an average of 60%

after 48 h (Fig. 2d). While we focused only on the top HM-producing colony for each chimeric CSLA

variant (Fig. 2c,d), initial screening showed that independent transformants produced similar amounts

of HM polymers based on monosaccharide composition or β-mannanase digestion (Additional file 3).

Since co-feeding methanol and a smaller amount of glycerol led to consistent biomass yields

(Additional file 3), the polysaccharides made by chimeric enzymes were further studied using YPM+G

cultivation.

The selected CSLA domains were similar in length and predicted topology (Fig. 1), yet the

swaps of individual regions had significant, unidirectional consequences on HM biosynthesis.

Terminal domain swaps (3222 and 2223) for AtCSLA2, and N-terminal swap for AkCSLA3 (2333)

largely abolished mannan production (Fig. 2 and Additional file 3), reminiscent of the reduced CSLA

activity associated with adding fluorescent tags. Replacement of the second or third domain of

AkCSLA3 (3233 and 3323) led to the production of intermediate levels of HM compared to the

parental enzymes and the Venus negative control. While most of the domain swaps impaired

hemicellulose synthesis, three of the chimeric enzymes (2322, 2232 and 3332) produced up to 2-fold

more alkaline-insoluble Man than the parental controls (Fig. 2). To elucidate the glycan structures

produced in yeast, polymers were derivatized to partially methylated alditol acetates (PMAAs) [29]. By

separating and detecting PMAAs via gas chromatography-mass spectrometry (GC-MS), we identified

a total of 11 sugar linkages and quantified their relative abundance (Additional file 4). As previously

shown for control strains [18], more than 80% of PMAAs derivatized from Venus alkaline-insoluble

polymers could be assigned to yeast glucans with non-branched (3-Glc and 6-Glc) or singly branched

(2,3-Glc and 3,6-Glc) hexopyranosyl residues. While the Venus samples contained only trace

amounts (< 0.001%) of unbranched 4-Man, this HM-defining linkage increased to 27–33% of total

PMAAs for AtCSLA2 and AkCSLA3 (Additional file 4). Since these biomaterials were insoluble in hot 1

M NaOH, we divided the HM-specific linkage content (4-Man and 4,6-Man) by t-Man (terminal units of

HM backbones and yeast mannoproteins) to evaluate the effect of CSLA domain swaps on mannan

content and estimated length. All CSLA variants tested significantly increased the ratio of mannan/t-

Man linkages compared to the Venus control (Fig. 3a), but five of the chimeric enzymes produced

fewer and/or shorter mannan chains than the parental enzymes and the top three swaps (2322, 2232,

and 3332). Branched 4,6-Man was below 1% of linkage area for all samples, so the mannans made

by CSLAs were not substituted with side chains (Additional file 4). While the mannan/t-Man ratio of

the *Pichia* materials in Fig. 3a underestimates their degree of polymerization (DP), the molecular

weight of unsubstituted HM polymers cannot be measured without fragmenting them [18]. Since

insoluble mannan extracted from ivory nuts has an expected DP of 15–20 (Megazyme Knowledge

Base, Product P-MANIV), the top five CSLA strains showed plausible minimum values of mannan

length (13–22 units; Fig. 3a). Of these five samples, only AkCSLA3, 2232 and 3332 also increased 4-

Glc to ≥4.5% (Fig. 3b) from the small amounts (1.6–3.3%) that are natively part of yeast compounds

such as glycogen [3]. Glucomannan production by AkCSLA3 and 3332 was supported by both

glycosidic linkage (Fig. 3) and β-mannanase digestion analyses (Additional file 3). However,

carbohydrates released from 2232 were not enriched in Glc (Additional file 3), suggesting that the

exchanged domains did not enable AtCSLA2 to synthesize β-1,4-glucomannan in yeast.

Influence of Top Domain Swaps on (Gluco)mannan Production

179   Since some of the generated swaps displayed reduced HM synthesis, we focused our further

180   investigations on the top three (2322, 2232 and 3332) most promising CSLA swaps. We re-grew the

181   yeast to isolate engineered cell wall material for comprehensive analyses of HM polysaccharides (Fig.

182   4 and Additional file 5). Following endo-β-mannanase digestion, only the AkCSLA3 and 3332 *Pichia*

183   strains released carbohydrates composed of both Man and Glc (Fig. 4a). In contrast, digestion of

184 AtCSLA2, 2322 and 2232 proteins (containing regions of AkCSLA3) only released significantly more

185 Man-containing carbohydrates compared to the Venus control. For the 2232 swap, the amount of Man

186 incorporated in alkaline-insoluble polymers increased up to 1 mg per well, which was 2.4-fold higher

187 than AtCSLA2 and 1.6-fold higher than AkCSLA3 (Additional file 5). (Gluco)mannan was further

188 enriched by pooling three biological replicates and reducing the content of yeast glucans using

189 Zymolyase, yielding 0.7–2.5 mg of HM for each CSLA construct (Additional file 5). Glycosidic linkage

190 analysis confirmed that only AkCSLA3 and 3332 enriched polymers contained significantly more 4-Glc

191 compared to Venus and AtCSLA2 controls (Fig. 4b, Additional file 5). To provide quantify the level of

192 Glc incorporation, we used HPAEC-PAD to profile the (gluco)mannan oligosaccharides released by

193 partial endo-β-1,4-mannanase digestion from the yeast-enriched (Fig. 4c,d) and commercial HM

194 polysaccharides (Additional file 6). While ivory nut mannan was digested to small manno-

195 oligosaccharides (DP ≤ 4), konjac glucomannan showed additional peaks with a retention time above

196 the mannohexaose (DP 6) standard. These larger peaks, known to be diagnostic of glucomannan

197 [15], represented only 1% of ivory nut oligosaccharide area but 48% of konjac sample area (Fig. 4c).

198 Even when using ten times more ivory nut mannan, the digestion profiles did not resemble the

199 glucomannan peaks (Additional file 6). The *Pichia* AtCSLA2 and AkCSLA3 oligosaccharides

200 resembled the digested pure mannan and glucomannan standards, respectively (Fig. 4d). While

201 polymers made by the chimeric 2322 and 2232 proteins showed detectable glucomannan peaks (4–

202 7% of total oligosaccharide area; Fig. 4d), their proportion was not significantly different from that of

203 AtCSLA2 ($P > 0.05$). Among the *Pichia* samples, only the AkCSLA3 and 3332 digested material had

204 substantial amounts of glucomannan oligosaccharides (22 to 26% of total area), albeit at half the level

205 of the konjac glucomannan standard (Fig. 4c). Therefore, the second or third region of AkCSLA3,

206 which contain its GT domain, are not sufficient to alter the composition of AtCSLA2-made mannan.

208 **Impact of CSLA Expression on Cell Growth**

209  Next, we investigated how the linear (gluco)mannans produced by plant CSLA expression in

210 *Pichia* cells impact yeast growth and morphology. None of the native or chimeric CSLA strains

211 showed reduced growth compared to controls when cultivated in a non-inducible medium (Additional

212 file 7). However, cultivation of yeast in YPM (Additional file 7) or YPM+G (Additional file 3) significantly

213 reduced the biomass accumulation of the AkCSLA3 strain compared to the Venus control. The growth

inhibition was consistent in additional AkCSLA3 colonies, including those previously generated using

the *pPICZ B* vector [18], suggesting that linear glucomannan accumulation is toxic to the yeast cells.

Multiple efforts to isolate stable *Pichia* transformants expressing AkCSLA3 under the control of *pGAP*,

a strong constitutive promoter [27], were also unsuccessful. Strains expressing the 2322, 2232 or

3332 chimeric proteins showed similar growth curves as Venus and AtCSLA2 in YPM (Fig. 5a). While

cells expressing AkCSLA3 resembled the exponential growth of the other CSLA strains in the first 24

hours of cultivation, their optical density at 600 nm (OD600) started to saturate earlier and remained

at 30% lower values than the Venus control even after 60 h. Compared to OD600 curves, Venus

protein fluorescence increased slower and plateaued later (Fig. 5a), after 2 to 3 days of cultivation.

After 24 h of induction, Venus and all CSLA cells showed similar morphology and area

(Additional file 7) when stained with Trypan Blue (TB), which labels cell wall β-glucans [30]. Since the

growth curves showed the biggest difference after more than 2 days of cultivation (Fig. 5a), we then

examined how TB stains yeast cells after 72 h of growth in YPM+G. Surprisingly, at this timepoint, the

majority of AkCSLA3 cells not only showed TB-stained walls but also appeared to be internally

saturated with the fluorescent dye (Fig. 5b). In contrast, only 4–6% of Venus and AtCSLA2 cells

showed TB uptake (Additional file 7). Furthermore, prolonged expression of AkCSLA3 decreased the

median cell area by 12.9% ($P < 0.00001$, one-way ANOVA with Tukey's pairwise), while AtCSLA2

increased it by 4.5% relative to the Venus control (Fig. 5c). The 2322 and 2232 chimeric proteins led

to intermediate cell dimensions compared to AkCSLA3 and the Venus control. TB is typically excluded

by the plasma membrane, and we noticed that its uptake in a few Venus cells correlated with a loss of

yellow fluorescence (Additional file 7). When yeast cells were intentionally damaged by partially

digesting the wall with Zymolyase and β-mercaptoethanol, the yellow fluorescence was lost from the

cytoplasm of most Venus cells (Fig. 5d). Partially spheroplasted Venus and AtCSLA2 cells showed

elevated TB uptake akin to treated or untreated AkCSLA3 cells (Fig. 5d). Therefore, the intracellular

TB staining indicates that extended AkCSLA3 expression reduced the integrity of the yeast capsules,

which was partially restored by the chimeric 3332 glucomannan synthase.

To exclude that these histological defects are TB-specific and to further study the engineered

yeast morphology, cells were stained with additional dyes after 3 days of cultivation. We combined

calcofluor white with propidium iodide to simultaneously label yeast/plant β-glucans and nuclei,

respectively. While calcofluor is carbohydrate-specific, propidium iodide can penetrate cells with

impaired membranes to intercalate nucleic acids [31]. Confocal laser scanning microscopy revealed

differences in viability of the different hemicellulose-producing strains (Fig. 6). Compared to Venus,

AtCSLA2, and 2232 cells, which rarely displayed nuclear staining, prolonged AkCSLA3 expression

increased the frequency of propidium iodide-stained cells (relative to calcofluor-stained cells) by 27-

fold (Fig. 6c). Both 2322 and 3332 chimeric proteins, containing most of the AkCSLA3 GT domain,

showed intermediate levels of propidium iodide uptake, but only 3332 expression reduced the area of

calcofluor-stained cells akin to AkCSLA3 (Fig. 6b). These results were further supported by staining

with congo red, a β-glucan dye that has a higher affinity for HM polymers than calcofluor [32]. Congo

red-stained AkCSLA3 cells showed elevated dye uptake and reduced cell area (Additional file 8),

consistent with the TB results (Fig. 5). In summary, AtCSLA2 increased the size of yeast cells with all

wall stains tested (Figs. 5, 6, Additional file 8), while extended glucomannan accumulation reduced

cell size and viability. These effects were *Pichia*-specific because overexpression of AkCSLA3

proteins did not visibly alter plant cell size or viability. Fluorescent AkCSLA3-sYFP proteins were

transiently expressed in intracellular punctae in *Nicotiana benthamiana* leaves without showing any

signs of cell death (Additional file 9). By itself, prolonged expression of the AkCSLA3 enzyme was not

toxic in a heterologous plant host. In contrast to the relatively small amounts of Man present in *N.*

benthamiana leaves [33], *Pichia* cells have copious amounts of sugars available for mannan

production [3]. Therefore, the modular assembly of CSLA enzymes tailored the biosynthesis of

(gluco)mannans and their effects on important yeast properties (such as biomass yield, cell size and

integrity).

Approaches to Further Boost the HM Yield and Glc Content

In addition to being a suitable host for β-1,4-mannan production, *Pichia* was previously used

to make long or short β-1,4-glucans by expressing Arabidopsis CSLC4 with or without XXT1 (a

xyloglucan xylosyltransferase), respectively [24]. We therefore used our optimized cultivation method

to express two of the highest expressed GTs during nasturtium (*Tropaeolum majus*) seed

development [34]. TmCSLC4 alone produced 13% more Glc-containing alkaline-insoluble polymers

than the Venus control, and even more (23%) glucan when co-expressed with TmXXT2 (Additional

file 10). It is noteworthy that the CSLC strains did not show the reduced growth observed for

AkCSLA3 (Additional file 10), suggesting that its effects are glucomannan-specific. TmCSLC4,

AtCSLA2 and AkCSLA3 share similar motifs in their GT2 domains (Fig. 7a), including multiple amino

acids involved in glucan coordination by a plant cellulose synthase complex [35]. We therefore tested

if the second region of AtCSLA2 could be functionally exchanged with the corresponding GT2

sequence of TmCSLC4. Despite the 58% amino acid identity of the two regions, the 2422 construct

was unable to make mannan nor increase Glc content (Additional file 10). We also did not detect any

HM production by 2332 construct (Additional file 11), which combines the two AkCSLA3 regions found

in the high-yielding 2322 and 2232 chimeras (Fig. 4). In contrast, the isolation of new 2232

transformants in the same experiment confirmed that this construct produced at least as much

mannan as the native AtCSLA2 protein (Additional file 11). Since the introduction of a CSLC part and

the exchange of a larger CSLA region were detrimental to hemicellulose biosynthesis, functional CSL

combinations cannot be easily predicted.

The synthesis of glucomannan can be influenced by CSLAs themselves as well as additional

factors. Alignments of 14 active (gluco)mannan synthases (from angiosperms, gymnosperms, and a

bryophyte; Additional file 12) or of a selection of cellulose synthase-like proteins (CesA, CSLC, CSLD,

and CSLF; Additional file 13) did not pinpoint CSLA polymorphisms associated with Glc incorporation.

Therefore, as an alternative strategy to boost (gluco)mannan production, we applied the MANNAN-

SYNTHESIS RELATED (MSR) protein as a co-factor [18]. The top colonies for the AtCSLA2 and the

2322 and 2232 chimeric constructs were re-transformed with a methanol-inducible *AtMSR1* cassette,

containing a distinct set of modular parts to avoid disrupting the previously integrated *CSLA*.

AtMSR1's introduction elevated (gluco)mannan content to 1.5–3.0 times higher than the parental

CSLA-only colonies (Fig. 7b). Consistent results were obtained for independent transformants of each

two-gene combinations. In this sequential transformation strategy, β-mannanase digestion of the

alkaline-insoluble polymers released 1.9-fold more Man and 1.2-fold more Glc for the AtCSLA2 +

AtMSR1 strain compared to AtCSLA2 alone (Fig. 7c; $P < 0.05$), consistent with results obtained using

a two-gene plasmid with recurring regulatory elements [18]. Interestingly, the co-expression of

AtMSR1 with either 2322 or 2232 significantly increased HM production made, compared to original

strains as well as the AtCSLA2 + AtMSR1 combination (Fig. 7b and 7c). Glucomannan production

was most prominent for the 2322 + AtMSR1, which had a 1.5-fold increase in Glc and 3.1-fold

increase in Man compared to AtCSLA2 alone. Therefore, the AkCSLA3 GT domain portion can be

directly or indirectly enhanced by AtMSR1 to a greater extent than the native AtCSLA2 sequence.

Discussion

Plant cells are predominantly shaped and strengthened by a cellulose-hemicellulose network,

which is built of a heterogeneous set of cross-linked that feature β-1,4-glycosidic bonds. In addition to

these natural polysaccharides, which have been used by humans for centuries, microorganisms can

now be modified to produce engineered living materials with entirely new functions [1]. In a recent

landmark, cellulose functionalized with enzymes or optogenetic sensors was produced by the co-

culture of *Komagataeibacter rhaeticus* bacteria and engineered yeast [2]. In contrast to bacteria and

yeast, plants have long generation times and increased biological complexity that dramatically limit

the speed of design-build-test-learn cycles. In this study, we embarked on a quest to efficiently

produce tailor-made HM polysaccharides in yeast, by exploring how swapping the domains from two

CSLA enzymes from konjac (a monocot) and Arabidopsis (a dicot) modulate its yield and composition.

In the developing konjac corm [25], AkCSLA3 produces glucomannan that already has promising

health care applications, including for the treatment of life style diseases [36]. While AtCSLA2 is most

important for seed mucilage biosynthesis in Arabidopsis [9,19], novel links between seed HM

structure and salt tolerance provide an indication that fine-tuning HM structure could also be relevant

for engineering stress-resistant crops [37].

We also improved the speed of recombinant hemicellulose production in yeast relative to the

sequential use of buffered (BMGY and BMMY) cultivation media [18], which are the standard

conditions in *Pichia* studies. Our growth protocol yielded rapid HM synthesis along with a higher level

of yeast glucans (Fig. 2 and Fig. 7b). Despite the elevated content of background Glc in AKI,

glucomannan could be readily detected via β-mannanase release (Fig. 4 and Fig. 7c), linkage

analysis (Fig. 3), or following partial enzymatic removal of background yeast glucans. Glycosidic

linkage analysis of AtCSLA2/AkCSLA3 chimeras showed that all the single-domain swaps produced

at least some 4-linked Man, but five of the constructs had only a marginal increase compared to the

trace amounts found in native *Pichia* polymers (Fig. 2 and Additional file 3). Except for the 3332

combination, N- or C-terminal domain swaps were not tolerated by CSLA enzymes as they led to

significantly less HM compared to the parents. Although AtCSLA2 and AkCSLA3 are predicted to

have similar topologies, their termini are the regions with the most divergent sequences (Fig. 1b) and

may play outsized roles in the overall architecture of active (gluco)mannan synthases. Cellulose [35],

xyloglucan [17], and β-1,3-1,4-linked-glucan [21,22] synthases have been demonstrated or are

predicted to form transmembrane pores that are important for glucan structure and translocation. Yet,

the roles of the multiple transmembrane domains found in CSLAs remain to be elucidated, if their

catalytic sites were to face the Golgi lumen.

We were surprised to find that 2322 and 2232 chimeric proteins produced higher amounts of

mannan compared to AtCSLA2, without incorporating significant amounts of Glc like AkCSLA3 (Fig.

4). Therefore, AtCSLA2 has a strict requirement for AtMSR1 co-expression to produce glucomannan

in the surrogate host [18]. Indeed, the addition of AtMSR1 enhanced HM production by the chimeric

2322 and 2232 proteins (Fig. 7b,c). Therefore, we hypothesize that the MSR1 putative protein O-

fucosyltransferase may directly interact with the GT2 domain of CSLA enzymes and/or glycosylate it.

Larger AtCSLA2 domain swaps or the introduction of TmCSLC4 catalytic domain to boost Glc

incorporation were not functional. One reason could be that CSLA glucomannan synthases, requiring

GDP-Man and GDP-Glc donor sugars [20,25], have catalytic domains that are incompatible with

CesA, CSLC and CSLFs, which utilize UDP-Glc [6]. However, barley CSLF3 and CSLF10 enzymes

were recently discovered to make polysaccharides containing both 4-linked Glc and xylose units [38],

while a spinach CSL protein was shown to transfer glucuronic acid onto specialized metabolites [39].

Based on these unexpected findings, the sugar specificity of CSL enzymes is not as restrictive as

previously thought and further diversification may be possible. Here, we produced unbranched

(gluco)mannans at the mg scale using single *CSLA* transcriptional units and affordable carbon

sources (methanol and glycerol). Since linear β-1,4-linked polymers are insoluble without enzymatic

or chemical fragmentation [13], it is not possible to determine their intact molecular weight. To

increase solubility, HM galactosylation and/or acetylation could be engineered in the *Pichia* CSLA

strains by introducing additional transcriptional units. By discovering more efficient biocatalysts in

yeast, only the best combinations of carbohydrate-active enzymes would have to be stacked *in planta*

to modulate desired traits, such as the yield of fermentable sugars [40].

A key advantage of our hemicellulose production system is that plant GTs can be stably

integrated in the *Pichia* genome and expressed when desired using tightly controlled promoters. In

two previous studies of CSL chimeras, cereal CSLF6 proteins with swapped domains were transiently

expressed by infiltrating *N. benthamiana* leaves and produced variable amounts (0.5–5.0% w/w) of β-

1,3-1,4-linked-glucan [21,22]. Despite the variable yields, lichenase digestion of the mixed-linkage

glucans released reproducible DP3:DP4 oligosaccharides ratios, which were typically similar to one of

the parental enzymes or at an intermediate level [21,22]. If we similarly compared the relative Glc:Man

ratios in several types of analyses (Fig. 4), the top performing constructs could be divided into

mannan (AtCSLA2, 2322 and 2232) and glucomannan (AkCSLA3 and 3332) synthases. While all the

published CSLF6 chimeras were functional, five of our CSLA swaps showed significantly reduced

activity compared (Fig. 2). One possible explanation is that the cereal CSLF6s are closely related

orthologs, but there is a greater distance between the CSLAs we selected. AkCSLA3 is orthologous to

AtCSLA3 [25], not AtCSLA2. Nevertheless, we could not pinpoint amino acids that are associated with

glucomannan synthase activity (Additional file 12). Given the significant boost after MSR1 protein co-

expression (Fig. 7), the Glc:Man ratio is clearly influenced by multiple factors. In the future, promising

amino acid changes to enhance Glc incorporation could be predicted via *de novo* CSLA modelling,

based on the structure of plant CesA [35], and *in silico* sugar binding simulations.

Yeast cell growth was reduced following glucomannan production by AkCSLA3. While

constitutive yeast promoters are available [27], we were not able to isolate stable colonies that

constitutively express AkCSLA3. In contrast, AtCSLA2 and the chimeric enzymes producing relatively

pure mannan showed no reductions in growth rates (Fig. 5a). Despite the reduced biomass, AkCSLA3

cells were histologically indistinguishable from the controls after 24 h of induction. An overwhelming

loss of viability (demonstrated by the uptake of TB, propidium iodide and congo red) became evident

for AkCSLA3 cells after three days of cultivation. However, the chimeric 3332 enzyme partially

rescued these defects (Fig. 5 and Fig. 6), despite only a small reduction in the Glc:Man ratio of its HM

product (Fig. 4). Furthermore, biomass accumulation was not reduced for the glucan synthase strains

expressing CSLC4 (Additional file 10), we therefore hypothesize that the competition for GDP-Glc

and/or glucomannan accumulation may explain this defect. The screening of natural or engineered

CSLA variants that produce higher levels of glucomannan than AkCSLA3 could be used to test this

hypothesis. Additional non-invasive tools will have to be developed to rapidly detect HM-producing

colonies, because the dyes used to monitor yeast walls can bind cellulose, hemicelluloses, yeast β-

glucans and chitin.

In conclusion, most of our HM-producing yeast strains grew well and showed a CSLA-

dependent increase or decrease in cell size distribution. Therefore, they could be viewed as modular

biological capsules for further engineering of polysaccharide-related pathways and/or biotechnological

products. Sensitive macromolecules such as therapeutic proteins can be protected by encapsulation

in non-toxic plant polysaccharides [41]. While plant biotechnology can offer low-cost solutions for drug

production [42], *Pichia* cells are also attractive hosts for recombinant protein production and have

been engineered to have a humanized glycosylation pathway [43]. Proteins produced in *Pichia* cells

with wild-type walls have been mixed with food and were effective at reducing gastrointestinal

bacterial infections in pigs [44], and face a simpler path to regulatory approval than genetically

engineered plants. Therefore, we anticipate that yeast modification with plant GTs will provide a

modular chassis for engineered biomaterials production and to encapsulate valuable cargo.

Methods

Modular assembly, verification and transformation

Plant genes and swaps were cloned using the modular GoldenPiCs cloning system [27]. The

GoldenPiCS Kit was a gift from the Gasser/Mattanovich/Sauer group (Addgene kit #1000000133). All

coding sequences were amplified with high-fidelity Phusion DNA Polymerase (Thermo Fisher

Scientific) using the primers listed in Additional file 14. First, fragments were domesticated for Golden

Gate assembly by introducing non-synonymous one or two base pair changes in custom fusion sites.

One unwanted site in AtCSLA2 was domesticated by amplifying two fragments with 1F + dom1R and

dom2F + 4R. Three unwanted AkCSLA3 sites were domesticated by amplifying and fusing four

fragments: 1F + dom1R, dom2F + dom2R, dom3F + dom3R, and dom4F + 4R. All Golden Gate

assemblies were performed based to the GoldenPiCs methods [27], but using FastDigest restriction

enzymes and T4 DNA ligase from Thermo Fisher Scientific. For each assembly, 10 µL reactions

containing 25 ng of each DNA part were incubated for at least 5 cycles of digestion (5 min at 37 °C)

and ligation (10 min at 22 °C), followed by final digestion and enzyme inactivation (10 min at 75 °C)

steps. DNA was transformed in *E. coli TOP10F'* via the heat-shock method. Antibiotic-resistant

colonies were first verified by colony PCR using gene- and/or vector-specific genotyping primers in

Additional file 14. DNA was isolated using the GeneJET Plasmid Miniprep Kit (ThermoFisher

Scientific), and all BB1 coding sequences were verified by Sanger Sequencing with M13 primers

and/or gene-specific primers. *pAOX1*:*CSL:RPP1Btt* transcriptional units were assembled in the

BB3aZ_14 backbone. The *pDAS2*:*AtMSR1*:*RPBS2tt* transcriptional unit was first assembled in the

BB2_BC vector, and then fused with an empty *AB* cassette in *BB3rN_AC*, which is Nourseothricin-

resistant and integrates in the *RGI2* locus. For each BB3 plasmid, 150 ng of linearized DNA was

transformed into *Pichia pastoris X-33* via the condensed electroporation method [45]. After three days

of cultivation, antibiotic-resistant colonies were re-streaked and verified by colony PCR using specific

primers and Red Taq DNA polymerase master mix (VWR International).

Pichia growth

Unless otherwise indicated, cells from at least three independent *Pichia* transformants per

construct were grown for 48h in 2 mL Yeast-Peptone (YP) medium supplemented with methanol (M,

1.5% v/v), dextrose (D, 2% w/v) or glycerol (G, 0.5% w/v) for biomass accumulation and induction.

Polypropylene square 24-deepwell microplates (Enzyscreen CR1424a) with matching metal covers

(CR1224b) served as re-usable cultivation vessels, which were washed and sterilized by autoclaving.

Plates, sealed with micropore tape, were incubated at 30 °C and 250 rpm in a shaking incubator

(Thermo Scientific MaxQ 6000). After incubation, cultures were transferred to 2 mL tubes and the

cells were collected by centrifugation for 5 min at 2000 *g*.

To measure growth curves, two biological replicates of each genotype were pre-cultured in 2

mL YPD medium in 14 mL sterile glass culture tubes with aluminum caps. Cultures were incubated for

24 hours at 30 °C and 250 rpm in a shaking incubator (Thermo Scientific MaxQ 6000). After

incubation, each pre-culture was diluted 1:10 and the OD600 was measured with the BioSpectrometer

(Eppendorf). The OD was then adjusted to 0.1 in YPM medium and three replicates with 300 µL of

each pre-culture were transferred to a 48-sterile well plate and mixed (360 rpm, 1.5 mm orbital

amplitude) inside a fluorescent plate reader (Tecan Spark 10M) at 29 °C. After every 30 min of mixing,

absorbance at 600 nm and fluorescence (excitation 485 ± 10 nm, emission at 530 ± 12.5 nm, manual

gain = 50) were recorded multiple times per well (5 x 5, filled circle pattern, 700 µm border).

Isolation of Carbohydrate Polymers

Alkaline-insoluble (AKI) polymers were obtained as previously described [18], but using cell

pellets as starting material and a thermomixer from a different supplier (neoMix 7-921). After

neutralization and washing, AKI polymers were homogenized in 600 µL of water using a ball mill, and

aliquots of the material were analyzed immediately or were stored as described below. To further

enrich (gluco)mannan, AKI samples were pooled from three biological replicates, pelleted by

centrifugation, and re-suspended in 300 µL of 0.2 M potassium phosphate buffer (pH 7.0). After re-

suspension, β-1,3-glucans were digested by adding 300 µL of water containing 125 µg of Zymolyase

20 T (from *Arthrobacter lutes*; USBiological) and 10 µg sodium azide. The samples were mixed for 48

h at 37 °C and 250 rpm in an incubator (Thermo Scientific MaxQ 6000). After centrifugation for 5 min

at 16,000 *g*, the remaining pellet was washed twice with 1 mL of water before carefully mixing it with

300 µL of acetone and gently dried to avoid material loss. Enriched (gluco)mannan (EM) polymers

were homogenized in 1000 µL of water using a ball mill. All carbohydrate samples and standards

were analyzed immediately or were stored at 4 °C (several days) or at -20 °C (long-term).

Monosaccharide and oligosaccharide quantification

For total monosaccharide quantification, 50 µL of *Pichia* AKI material or standards were

mixed with 800 µL of 30 µg/mL Ribose solution (internal standard). Blank and sugar standards

containing galactose, Man and Glc were prepared similarly. All samples and standards were

hydrolyzed by adding 30 µL of 72% (w/w) sulfuric acid, mixing and then incubating for 60 min at 120

°C in heat blocks. After cooling to room temperature, all tubes were centrifuged for 15 min at 20,000 *g*

to pellet any particles that remained insoluble, and 10 µL of the supernatant was injected for HPAEC-

PAD analysis. Carbohydrates were separated using a Metrohm 940 Professional IC Vario system

equipped with Metrosep Carb 2-250/4.0 analytical and guard columns. A short 30 min protocol

suitable for separation of the three HM sugar components (galactose, Glc and Man) included a 20 min

isocratic 2 mM sodium hydroxide (NaOH) + 3.4 mM sodium acetate (NaAce) separation step, followed

by 3 min rinse with 80 mM NaOH + 136 mM NaAce, before 4 min re-equilibration with the starting

eluents. Trace amounts of glucosamine were detected but were not quantified. Peaks were

automatically integrated and calibrated, with manual correction when necessary, using the MagIC Net

3.2 software (Metrohm).

For the digestion followed by monosaccharide analysis, 50 µL of *Pichia* AKI suspension were

incubated for 30 min at 40 °C and 1000 rpm in a thermomixer (neoMix 7-921) in 100 µL of 0.2 M

potassium phosphate buffer (pH 7.0) containing 1 U of endo-1,4-β-Mannanase (Megazyme, E-

BMABC). After incubation, samples were centrifuged for 2 min at 20,000 *g* and 100 µL of the

supernatant was dried under pressurized air using a heat block concentrator (Techne Dri Block

DB200/3). Dry samples and standards were hydrolyzed with 150 µL of 2 M trifluoroacetic acid (TFA)

for 90 min at 120°C. After cooling to room temperature, hydrolyzed samples were briefly centrifuged

and dried once again. Residual TFA was removed by washing with 300 µL of isopropanol and dried

as above. Samples were then eluted in 400 µL of 30 µg/mL Ribose solution (internal standard) and

were centrifuged for 2 min at 20,000 g prior to transferring 100 µL of supernatant to IC vials.

For oligosaccharide profiling, 100 µL of potassium phosphate buffer (pH 7.0) containing 0.1 U

of E-BMABC enzyme were added to 100 µL of EM or polysaccharide standards (from Megazyme)

and incubated for 30 min at 40 °C and 1500 rpm in a thermomixer. Enzyme was then heat-inactivated

for 10 min at 90 °C and 1500 rpm. Samples were centrifuged for 2 min at 20,000 g and 10 µL of the

supernatant were injected for HPAEC-PAD profiling of oligosaccharides. The instrument and column

setup were the same as for monosaccharide analysis but utilized a different eluent gradient. Starting

with 15.6 mM NaOH, the gradient was increased to 78 mM NaOH over 5 min, followed by a linear

increase to 78 mM NaOH + 50 mM NaAce for 25 min. The column was re-equilibrated for 15 min with

15.6 mM NaOH, before the next sample was injected.

Glycosidic linkage analysis

To determine the glycosidic linkages, yeast samples and commercial polysaccharides were

subjected to methylation [46], TFA hydrolysis, reduction and acetylation to generate PMAAs, similar to

a previously described method [29] with the following modifications. To start, 100 µL of AKI/EM

solutions or 1 mg/mL polysaccharide standards were dried in a glass tube and mixed overnight in 200

µL DMSO, pre-dried using molecular sieves. Solubilized polymers were methylated by using 200 µL

of a NaOH/DMSO slurry and 100 µL of methyl iodide, under N_2 atmosphere for 2 to 3 h. Reactions

were quenched by adding 2 mL of water, and N_2 was gently bubbled into each tube until the solution

became clear. After adding 2 mL of dichloromethane, ~1.5 mL of the organic phase was transferred to

a new tube, dried and the methylated polymers were hydrolyzed into monomers using 2 M TFA. Dried

monosaccharides, with *myo*-inositol added as internal standard, were reduced using 200 µL of fresh

10 mg/mL sodium borodeuteride in 1 M ammonium hydroxide for 60 min at room temperature. After

neutralization with acetic acid and extensive methanol washes, samples were dried and acetylated

with 50 µL acetic anhydride and 50 µL pyridine for 20 min at 120°C. The resulting PMAAs were then

dried, washed twice with 200 µL of toluene, and finally cleaned using 1.2 mL ethyl acetate and 5 mL

of water. The organic molecules were dried in new tubes, resuspended in 300 µL acetone, and 2 µL

of each PMAA sample was automatically injected for GC-MS using an Agilent Technologies 6890N

GC system equipped with a Supelco SP-2380 column (30 m x 0,25 mm x 0,2 μm) and coupled to an

Agilent 5975 quadrupole EI detector. The GC oven started at 80 °C for 3 min, increased to 170 °C (at

a rate of 30 °C/min), followed by second ramp to 240°C (rate of 4 °C/min) and a 15 min hold time per

run. PMAAs were semi-automatically quantified in Agilent MSD Chemstation Classic Data Analysis

(G1701FA) based on the retention time of the glycosidic linkage peaks from polysaccharide

standards, and their relative ion spectra or available data in the CCRC Spectral Database for PMAAs

(https://www.ccrc.uga.edu/specdb/ms/pmaa/pframe.html).

Fluorescence microscopy

For microscopy, cell cultures diluted in water or phosphate-buffered saline (PBS) solution, pH

7.0, and mixed with an equal volume of 0.01% (w/v) solution of one or more dyes (all from Sigma

Aldrich, except calcofluor white from Megazyme). Cells were imaged with a 40x or 60x objectives on a

laser scanning confocal microscope (Carl Zeiss, LSM 700), beam splitter (MBS 405/488/555/639),

and multiple laser/filter combinations. Separate acquisition tracks with the following excitation and

emission wavelengths were used to acquire Venus fluorescence (488 nm and BP 450-550), calcofluor

(405 nm and BP 420-550), TB, propidium iodide, and congo red (639 nm and LP 640). Images were

acquired using the ZEN 2011 (black edition) from Carl Zeiss and then processed uniformly in ImageJ

[47]. To quantify cell numbers and sizes, the microscopy images were segmented using the web

version (http://yeastspotter.csb.utoronto.ca) of the YeastSpotter tool [48], and particles were then

measured in ImageJ with the Analyze Particles (size=3-40, circularity=0.80-1.00) command.

Transient expression in *N. benthamiana* leaves

For plant expression, the coding sequences were synthesized and were cloned in the

previously described *pCV01* vector [9], using the LIC primers listed in Additional file 14 and ligation

independent cloning [49]. Constructs were verified via Sanger sequencing. Transient expression was

performed in *N. benthamiana* leaves as previously described [50]. *Agrobacterium tumefaciens* strains

containing the desired gene of interest were mixed with the P19 viral suppressor (each with an OD600

of 0.7). *Agrobacterium* mixtures were infiltrated in the lower side of the leaf of 5-week-old plants. A

total of eight replicate infiltration spots for each gene were distributed randomly in leaves from four

different plants to avoid positional bias. The subcellular yellow fluorescence was analyzed after 4 days

using similar confocal microscope setup to the described yeast Venus imaging. Whole leaves were

imaged at 6-days post-infiltration using a hand-held camera as well as a gel documentation system

(Analytik Jena, UVP Gelstudio Plus) equipped with an overhead blue LED and a GFP Emission Filter

(#849-00405-0).

Declarations

Ethics approval and consent to participate
Not applicable.

Consent for publication
Not applicable.

Availability of data and materials
The datasets and materials used and/or analysed during the current study are available from the
corresponding author on reasonable request.

Competing interests
The authors declare that they have no competing interests.

Funding
The work in the Designer Glycans group was funded by the Leibniz Institute of Plant Biochemistry and
the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation grant 414353267 to
CV). Additional funding was provided by the DFG under Germany's Excellence Strategy—EXC
2048/1—Project ID: 390686111 to MP.

Authors' contributions
MP proposed the domain swap strategy. CV designed and coordinated all experiments. JW and FS
assembled the AtCSLA2/AkCSLA3 single domain swaps and carried out the initial activity screen. MR
performed all the presented experiments with help from CV, except that the work in Additional file 9
was done by BY. CV and MR wrote the paper with input from all authors.

Acknowledgements
Mehdi Ben Targem assisted with CSLA sequence domestication and Annika Grieß-Osowski prepared
the *Agrobacterium AkCSLA3* strain. Balakumaran Chandrasekar and Niklas Gawenda (Institute for
Plant Cell Biology and Biotechnology) kindly provided the two glucan-producing *Pichia* control strains.
We gratefully acknowledge the following individuals and groups at the Leibniz Institute of Plant
Biochemistry (IPB) for instrument access: GC-MS (Karin Gorzolka, Department of Biochemistry of
Plant Interactions), confocal microscope (Bettina Hause, Imaging Unit of the IPB), and plate readers
(Martin Weissenborn, Bioorganic Chemistry group and Steffen Abel, Department of Molecular Signal
Processing). Pascal Püllmann provided useful tips on high-throughput yeast growth, and IPB
gardeners for assistance with the tobacco cultivation.

Fig. Legends

Fig. 1 Modular engineering of hemicellulose synthesis. **a** Model of the potential cell phenotypes and
future applications, such as biological capsules for therapeutic proteins, of yeast engineered to
produce plant matrix polysaccharides. **b** Topology of AtCSLA2 and AkCSLA3 enzymes visualized with
TOPCONS 2.0. Transmembrane domains (pink boxes), and regions inside (red) and outside (blue)
the membrane. The GT2 domain denotes the conserved GT2 domain (Pfam PF13641). Three regions
(dashed lines) with 100% amino acid identity were selected as borders for CSLA domain swapping. **c**

Workflow for the assembly of chimeric DNA using the GoldenPICS cloning system. CSL domains are
fused seamlessly in a level 1 vector, and then assembled with a yeast promoter and a transcriptional
terminator into a level 2 vector for stable yeast transformation. Selected yeast colonies were induced
to express the CSL enzymes using methanol and were subjected to cell wall analyses. **d** Matrix and
labeling of AtCSLA2/AkCSLA3 single domain swaps assembled in this study.

Fig. 2 Abundance and composition of engineered wall polymers. **a** Relative green fluorescence of
independent *Pichia* colonies (except that sfGFP controls are biological replicates). **b** Mannose (Man)
content as a percent of the total sugars detected for the alkaline-insoluble polymers (made by the
cells from panel **a**). **c, d** Absolute monosaccharide composition of alkaline-insoluble polymers after
cultivation of engineered yeast strains in two media: **c** YPM (containing 1.5% w/w Methanol as sole
carbon source) or **d** YPM + G (plus 0.5% v/v Glycerol to boost biomass accumulation.
Polysaccharides were hydrolyzed using sulfuric acid. In panels **c** and **d**, dots show the values of two
biological replicates, and significant differences between samples are marked by different letters (one-
way ANOVA with Tukey test, $P < 0.05$). All samples in panel **d** had similar Glc levels.

Fig. 3 Effects of AtCSLA2 and AkCSLA3 domain swaps on (gluco)mannan linkages. **a** Relative
content of plant mannan (sum of 4-Man and 4,6-Man) to terminal-Man (t-Man) in alkaline-insoluble
polymers after derivatization to partially methylated alditol acetates. **b** Percentage of 1,4-linked Glc
relative to the total area of glycosidic linkages. The 4-Glc background level is derived from native
yeast polymers such as glycogen. Jitter plots show three biological replicates. Boxes show the 25–
75% quartiles, the median value (inner horizontal line), and whiskers extending to the largest/smallest
values. Significant differences between samples are marked by different letters (one-way ANOVA with
Tukey test) in panels **a** ($P < 0.001$) and **b** ($P < 0.05$).

Fig. 4 Structure of (gluco)mannans produced by the top chimeric CSLAs. **a** Carbohydrates released
by endo-β-1,4-mannanase digestion of alkaline-insoluble polymers. Solubilized carbohydrates were
subjected to TFA-hydrolysis prior to HPEAC-PAD analysis. Data show the mean + SD of three
biological replicates, re-grown based on the most promising *Pichia* strains from Figs. 2 and 3. **b**
Relative abundance of glucomannan glycosidic linkages in enriched mannan (EM) samples after
Zymolyase treatment. Data show the mean + SD of three measurements for each sample. **c** Relative
peak area of mannan (Man$_{1-5}$) and glucomannan (GlcMan) oligosaccharides released from *Pichia* EM
by mannanase relative to ivory nut mannan (INM) and konjac glucomannan (KGM) standards. Data
show the mean + SD of two measurements. In panels **a** to **c**, significant differences between samples
are marked by different letters (one-way ANOVA with Tukey test, $P < 0.05$). **d** HPAEC-PAD
oligosaccharide profiles of mannanase-treated samples quantified in panel **c**. GlcMan diagnostic
peaks, based on the controls in Additional file 6, are marked by asterisks.

Fig. 5 CSLA expression influences yeast growth and cell wall morphology. **a** Growth curve of CSLA
parents and top swaps after transfer to YPM in a 48-well plate. Optical density at 600 nm (OD600)
and yellow relative fluorescence units (RFU) were monitored with a plate reader after every 30 min of
shaking. Data show the mean ± SD of at least 3 biological replicates. The error bars are only shown
for Venus and AkCSLA3 due to space constraints, but data points had a coefficient of variance below
5% after 32 h. **b** Morphology of yeast cells stained with Trypan Blue (TB) after 72 h of cultivation in
YPM + G. **c** Yeast cell area (μm²) of CSLA parents and top swaps. Violin plot shows the size
distribution of at least 350 cells per genotype, and significant differences between samples are
marked by different letters (one-way ANOVA with Tukey test, $P < 0.0001$). **d** Zymolyase and β-
mercaptoethanol treatment spheroplasted Venus cells based on Transmitted Light (TL) and yellow
protein fluorescence (YFP) imaging. Scale bars = 5 μm in **b**, 10 μm in **d**. Arrows indicate TB uptake.

Fig. 6 Glucomannan synthesis by AkCSLA3 is toxic to yeast cells. **a** Transmitted light (TL),
calcofluor white (CF), and propidium iodide (PI) staining of cells after 72 h of cultivation in YPM + G.
Scale bars = 5 μm. **b** Yeast cell area (μm²) of CSLA parents and top swaps. Violin plot shows the size
distribution of at least 1200 cells per genotype (combining four biological replicates). Different letters
denote significant changes (one-way ANOVA with Tukey test, $P < 0.001$). **c** The ratio of cells stained
with PI relative to those stained with CF, segment using Yeastspotter and counted with ImageJ. Dots
show four biological replicates. Boxes show the 25–75% quartiles, the median value (inner horizontal
line), and whiskers extending to the largest/smallest values. In panels **b** and **c**, significant differences
between samples are marked by different letters (one-way ANOVA with Tukey test, $P < 0.05$).

656
Fig. 7 CSL enzyme features and further enhancement of hemicellulose synthesis. **a** Multiple
sequence alignment, showing the selected borders for the chimeric proteins (dashed lines) and
additional conserved motifs among active CSLAs (green lines). Arrowheads mark residues involved in
glucan coordination by the structural studies of the PttCesA8 enzyme in *Pichia*. The shading is
proportional to the amino acid similarity. TM, transmembrane domains. **b** Swapped CSLA domains
are particularly boosted by catalytic domain by AtMSR1 to surpass parental yields, based on absolute
monosaccharide composition. **c** Monosaccharide composition of carbohydrates released from AKI by
β-mannanase digestion. In **b** and **c**, dots show two technical replicates (each measured in duplicate)
and significant differences between samples are marked by different letters (one-way ANOVA with
Tukey test, $P < 0.05$).
667
Additional files

Additional file 1. Sanger sequencing alignments of assembled *CSL* constructs.
Additional file 2. Genotyping of domain-swapped AtCSLA2/AkCSLA3 yeast colonies.
Additional file 3. Screening of *Pichia* colonies expressing recombinant proteins.
Additional file 4. Complete glycosidic linkage table for alkaline-insoluble polymers.
Additional file 5. Enrichment and composition of (gluco)mannan for the top CSLA strains.
Additional file 6. Oligosaccharide profiling of commercial (gluco)mannan polysaccharides.
Additional file 7. Yeast cell density and area after CSLA expression.
Additional file 8. Imaging and quantification of yeast cells stained with Congo Red.
Additional file 9. Expression of AkCSLA3 in *Nicotiana beanthamiana* leaves.
Additional file 10. Replacement of a CSLA catalytic domain with that of a CSLC.
Additional file 11. Combinatorial effect of AkCSLA3/AtCSLA2 domain swaps.
Additional file 12. Alignment of active mannan and/or glucomannan synthases.
Additional file 13. Alignment of CesAs and CSL representatives.
Additional file 14. Primer sequences used in this study.

683
References

1. Gilbert C, Ellis T. Biological Engineered Living Materials: Growing Functional Materials with
Genetically Programmable Properties. ACS Synth Biol. American Chemical Society; 2019;8:1–15.

2. Gilbert C, Tang T-C, Ott W, Dorr BA, Shaw WM, Sun GL, et al. Living materials with programmable
functionalities grown from engineered microbial co-cultures. Nat Mater. 2021;20:691–700.

3. Pauly M, Gawenda N, Wagner C, Fischbach P, Ramírez V, Axmann IM, et al. The Suitability of
Orthogonal Hosts to Study Plant Cell Wall Biosynthesis. Plants. 2019;8:516.

4. Gassler T, Sauer M, Gasser B, Egermeier M, Troyer C, Causon T, et al. The industrial yeast Pichia
pastoris is converted from a heterotroph into an autotroph capable of growth on CO2. Nat Biotechnol.
2020;38:210–6.

5. Amos RA, Mohnen D. Critical Review of Plant Cell Wall Matrix Polysaccharide Glycosyltransferase
Activities Verified by Heterologous Protein Expression. Front Plant Sci. 2019;10:915.

6. Pauly M, Gille S, Liu L, Mansoori N, de Souza A, Schultink A, et al. Hemicellulose biosynthesis.
Planta. 2013;238:627–42.

7. Scheller HV, Ulvskov P. Hemicelluloses. Annu Rev Plant Biol. 2010;61:263–89.

8. Buckeridge MS. Seed cell wall storage polysaccharides: models to understand cell wall
biosynthesis and degradation. Plant Physiol. 2010;154:1017–23.

9. Voiniciuc C, Schmidt MH-W, Berger A, Yang B, Ebert B, Scheller HV, et al. MUCILAGE-
RELATED10 Produces Galactoglucomannan That Maintains Pectin and Cellulose Architecture in
Arabidopsis Seed Mucilage. Plant Physiol. 2015;169:403–20.

10. Yu L, Lyczakowski JJ, Pereira CS, Kotake T, Yu X, Li A, et al. The Patterned Structure of
Galactoglucomannan Suggests It May Bind to Cellulose in Seed Mucilage. Plant Physiol.
2018;178:1011–26.

11. Zhong R, Cui D, Ye Z-H. Members of the DUF231 Family are O-Acetyltransferases Catalyzing 2-
O- and 3-O-Acetylation of Mannan. Plant Cell Physiol. 2018;59:2339–49.

12. Zhong R, Cui D, Ye Z. Evolutionary origin of O-acetyltransferases responsible for glucomannan
acetylation in land plants. New Phytol. 2019;224:466–79.

13. Berglund J, Kishani S, Morais de Carvalho D, Lawoko M, Wohlert J, Henriksson G, et al.
Acetylation and Sugar Composition Influence the (In)Solubility of Plant β-Mannans and Their
Interaction with Cellulose Surfaces. ACS Sustain Chem Eng. 2020;8:10027–40.

14. Bewley JD, Bradford KJ, Hilhorst HWM, Nonogaki H. Structure and Composition. In: Seeds. New
York, NY: Springer New York; 2013. p. 1–25.

15. Verhertbruggen Y, Bouder A, Vigouroux J, Alvarado C, Geairon A, Guillon F, et al. The TaCslA12
gene expressed in the wheat grain endosperm synthesizes wheat-like mannan when expressed in
yeast and Arabidopsis. Plant Sci. 2021;302:110693.

16. Kim S-J, Chandrasekar B, Rea AC, Danhof L, Zemelis-Durfee S, Thrower N, et al. The synthesis
of xyloglucan, an abundant plant cell wall polysaccharide, requires CSLC function. Proc Natl Acad
Sci. 2020;117:20316–24.

17. Davis J, Brandizzi F, Liepman AH, Keegstra K. Arabidopsis mannan synthase CSLA9 and glucan
synthase CSLC4 have opposite orientations in the Golgi membrane. Plant J Cell Mol Biol.
2010;64:1028–37.

18. Voiniciuc C, Dama M, Gawenda N, Stritt F, Pauly M. Mechanistic insights from plant
heteromannan synthesis in yeast. Proc Natl Acad Sci. 2019;116:522–7.

19. Yu L, Shi D, Li J, Kong Y, Yu Y, Chai G, et al. CELLULOSE SYNTHASE-LIKE A2, a glucomannan
synthase, is involved in maintaining adherent mucilage structure in arabidopsis seed. Plant Physiol.
2014;164:1842–56.

20. Liepman AH, Wilkerson CG, Keegstra K. Expression of cellulose synthase-like (Csl) genes in
insect cells reveals that CslA family members encode mannan synthases. Proc Natl Acad Sci.
2005;102:2221–6.

21. Jobling SA. Membrane pore architecture of the CslF6 protein controls (1-3,1-4)-β-glucan structure.
Sci Adv. 2015;1:e1500069.

22. Dimitroff G, Little A, Lahnstein J, Schwerdt JG, Srivastava V, Bulone V, et al. (1,3;1,4)-β-Glucan
Biosynthesis by the CSLF6 Enzyme: Position and Flexibility of Catalytic Residues Influence Product
Fine Structure. Biochemistry. 2016;55:2054–61.

23. Collins HM, Burton RA, Topping DL, Liao M, Bacic A, Fincher GB. REVIEW: Variability in Fine
Structures of Noncellulosic Cell Wall Polysaccharides from Cereal Grains: Potential Importance in
Human Health and Nutrition. Cereal Chem. 2010;87:272–82.

24. Cocuron J-C, Lerouxel O, Drakakaki G, Alonso AP, Liepman AH, Keegstra K, et al. A gene from
the cellulose synthase-like C family encodes a -1,4 glucan synthase. Proc Natl Acad Sci.
2007;104:8550–5.

25. Gille S, Cheng K, Skinner ME, Liepman AH, Wilkerson CG, Pauly M. Deep sequencing of voodoo
lily (Amorphophallus konjac): An approach to identify relevant genes involved in the synthesis of the
hemicellulose glucomannan. Planta. 2011;234:515–26.

26. Tsirigos KD, Peters C, Shu N, Käll L, Elofsson A. The TOPCONS web server for consensus
prediction of membrane protein topology and signal peptides. Nucleic Acids Res. 2015;43:W401-407.

27. Prielhofer R, Barrero JJ, Steuer S, Gassler T, Zahrl R, Baumann K, et al. GoldenPiCS: a Golden
Gate-derived modular cloning system for applied synthetic biology in the yeast Pichia pastoris. BMC
Syst Biol. BMC Systems Biology; 2017;11:123.

28. Engler C, Kandzia R, Marillonnet S. A One Pot, One Step, Precision Cloning Method with High
Throughput Capability. PLoS ONE. 2008;3:e3647.

29. Pettolino FA, Walsh C, Fincher GB, Bacic A. Determining the polysaccharide composition of plant
cell walls. Nat Protoc. 2012;7:1590–607.

30. Liesche J, Marek M, Günther-Pomorski T. Cell wall staining with Trypan blue enables quantitative
analysis of morphological changes in yeast cells. Front Microbiol. 2015;6:107.

31. Suzuki T, Fujikura K, Higashiyama T, Takata K. DNA Staining for Fluorescence and Laser
Confocal Microscopy. J Histochem Cytochem. 1997;45:49–53.

32. Wood PJ. Specificity in the interaction of direct dyes with polysaccharides. Carbohydr Res.
1980;85:271–87.

33. Le Mauff F, Loutelier-Bourhis C, Bardor M, Berard C, Doucet A, D'Aoust M-A, et al. Cell wall
biochemical alterations during Agrobacterium-mediated expression of haemagglutinin-based influenza
virus-like vaccine particles in tobacco. Plant Biotechnol J. 2017;15:285–96.

34. Jensen JK, Schultink A, Keegstra K, Wilkerson CG, Pauly M. RNA-Seq Analysis of Developing
Nasturtium Seeds (Tropaeolum majus): Identification and Characterization of an Additional
Galactosyltransferase Involved in Xyloglucan Biosynthesis. Mol Plant. 2012;5:984–92.

35. Purushotham P, Ho R, Zimmer J. Architecture of a catalytically active homotrimeric plant cellulose
synthase complex. Science. 2020;369:1089–94.

36. Behera SS, Ray RC. Konjac glucomannan, a promising polysaccharide of Amorphophallus konjac
K. Koch in health care. Int J Biol Macromol. 2016;92:942–56.

37. Yang B, Hofmann F, Usadel B, Voiniciuc C. Seed hemicelluloses tailor mucilage properties and
salt tolerance. New Phytol. 2020;229:1946–54.

38. Little A, Lahnstein J, Jeffery DW, Khor SF, Schwerdt JG, Shirley NJ, et al. A Novel (1,4)-β-Linked
Glucoxylan Is Synthesized by Members of the *Cellulose Synthase-Like F* Gene Family in Land Plants.
ACS Cent Sci. 2019;5:73–84.

39. Jozwiak A, Sonawane PD, Panda S, Garagounis C, Papadopoulou KK, Abebie B, et al. Plant
terpenoid metabolism co-opts a component of the cell wall biosynthesis machinery. Nat Chem Biol.
2020;16:740–8.

40. Aznar A, Chalvin C, Shih PM, Maimann M, Ebert B, Birdseye DS, et al. Gene stacking of multiple
traits for high yield of fermentable sugars in plant biomass. Biotechnol Biofuels. 2018;11:2.

41. Vela Ramirez JE, Sharpe LA, Peppas NA. Current state and challenges in developing oral
vaccines. Adv Drug Deliv Rev. 2017;114:116–31.

42. Kwon K-C, Daniell H. Low-cost oral delivery of protein drugs bioencapsulated in plant cells. Plant
Biotechnol J. 2015;13:1017–22.

43. Jacobs PP, Geysens S, Vervecken W, Contreras R, Callewaert N. Engineering complex-type N-
glycosylation in Pichia pastoris using GlycoSwitch technology. Nat Protoc. 2009;4:58–70.

44. Virdi V, Palaci J, Laukens B, Ryckaert S, Cox E, Vanderbeke E, et al. Yeast-secreted, dried and
food-admixed monomeric IgA prevents gastrointestinal infection in a piglet model. Nat Biotechnol.
2019;37:527–30.

45. Lin-Cereghino J, Wong WW, Xiong S, Giang W, Luong LT, Vu J, et al. Condensed protocol for
competent cell preparation and transformation of the methylotrophic yeast Pichia pastoris.
BioTechniques. 2005;38:44, 46, 48.

46. Ciucanu I, Kerek F. A simple and rapid method for the permethylation of carbohydrates.
Carbohydr Res. 1984;131:209–17.

47. Schindelin J, Arganda-Carreras I, Frise E, Kaynig V, Longair M, Pietzsch T, et al. Fiji: an open-
source platform for biological-image analysis. Nat Methods. 2012;9:676–82.

48. Lu AX, Zarin T, Hsu IS, Moses AM. YeastSpotter: accurate and parameter-free web segmentation
for microscopy images of yeast cells. Bioinformatics. 2019;35:4525–7.

49. De Rybel B, van den Berg W, Lokerse A, Liao C-Y, van Mourik H, Möller B, et al. A Versatile Set
of Ligation-Independent Cloning Vectors for Functional Studies in Plants. Plant Physiol.
2011;156:1292–9.

50. Grefen C, Donald N, Hashimoto K, Kudla J, Schumacher K, Blatt MR. A ubiquitin-10 promoter-
based vector set for fluorescent protein tagging facilitates temporal stability and native protein
distribution in transient and stable expression studies. Plant J. 2010;64:355–65.

a Plant GTs + Yeast Cells → Matrix Design → Modular Capsules | Tailor-Made Biomaterials

b

VLVQIPM   QQHRWSCGPANL   NEWVVT

AtCSLA2 — GT2

43.2%   72.6%   58.0%   38.3%

AkCSLA3 — GT2

100 aa

Border A   Border B   Border C

c PCR fragments

1st Assembly

BB1_23 CSL

pAOX1   Golden Gate Cloning   RPP1Btt

2nd Assembly   1 2   3 4

BB3_aZ → *Pichia pastoris* → Engineered Polysaccharides

d

AtCSLA2
AkCSLA3

a

Mannan/t-Man

Venus · AtCSLA2 · AkCSLA3 · 3222 · 2322 · 2232 · 2223 · 2333 · 3233 · 3323 · 3332

a · b · b,c · d · b · c · d · d · d · d · b

b

Linkage (%)

6
4
2
0

4-Glc

Venus · AtCSLA2 · AkCSLA3 · 3222 · 2322 · 2232 · 2223 · 2333 · 3233 · 3323 · 3332

a · b · c · a,b · a,b · c · b · a,b · b · b · c