Development of lipidoid nanoparticles for siRNA delivery to neural cells

Purva Khare,[1] Kandarp M. Dave,[1] Yashika S. Kamte,[1] Muthiah A. Manoharan,[2] Lauren A. O'Donnell,[1] Devika S Manickam[1][†]

[1]Graduate School of Pharmaceutical Sciences, Duquesne University, Pittsburgh, PA, USA.

[2]Alnylam Pharmaceuticals, Cambridge, MA, USA.

[†]**Corresponding author**: Devika S Manickam
453 Mellon Hall, 600 Forbes Avenue,
Pittsburgh, PA 15282.
Email: soundaramanickd@duq.edu
Twitter @manickam_lab
Phone: +1 (412) 396-4722, Fax +1 (412) 396-2501

Abstract

Lipidoid nanoparticles (LNPs) are the delivery platform in Onpattro, the first FDA-approved

siRNA drug. LNPs are also the carriers in the Pfizer-BioNTech and Moderna COVID-19 mRNA

vaccines. While these applications have demonstrated that LNPs effectively deliver nucleic acids

to hepatic and muscle cells, it is unclear if LNPs could be used for delivery of siRNA to neural

cells, which are notoriously challenging delivery targets. Therefore, the purpose of this study was

to determine if LNPs could efficiently deliver siRNA to neurons. Because of their potential utility

in either applications in the central nervous system and the peripheral nervous system, we used

both cortical neurons and sensory neurons. We prepared siRNA-LNPs using C12-200, a

benchmark ionizable cationic lipidoid along with helper lipids. We demonstrated using dynamic

light scattering that the inclusion of both siRNA and PEG-lipid provided a stabilizing effect to the

LNP particle diameters and polydispersity indices by minimizing aggregation. We found that

siRNA-LNPs were safely tolerated by primary dorsal root ganglion neurons. Flow cytometry

analysis revealed that Cy5 siRNA delivered via LNPs into rat primary cortical neurons showed

uptake levels similar to Lipofectamine RNAiMAX—the gold standard commercial transfection

agent. However, LNPs demonstrated a superior safety profile whereas the Lipofectamine-mediated

uptake was concomitant with significant toxicity. Fluorescence microscopy demonstrated a time-

dependent increase in the uptake of LNP-delivered Cy5 siRNA in a human cortical neuron cell

line. Overall, our results suggest that LNPs are a viable platform that can be optimized for delivery

of therapeutic siRNAs to neural cells.

Keywords

Lipidoid nanoparticle, C12-200, siRNA, neural cell, transfection

Introduction

Delivery of small interfering RNA (siRNA) is a promising strategy to treat pathologies as it allows genetic manipulation with a greater degree of target specificity with fewer off-target effects (1, 2). Lipidoid nanoparticles (LNPs) are the carriers in Onpattro, the first LNP-based RNAi drug to gain FDA approval for the treatment of polyneuropathies caused by a rare and life-threatening disorder, hereditary transthyretin-mediated amyloidosis (3). The clinical utility of LNPs is further reiterated by the recent full and emergency FDA approvals of the Pfizer-BioNTech (Comirnaty) and Moderna COVID-19 mRNA vaccines, respectively (4, 5). Based on the clinical success of LNPs in delivering siRNAs to hepatic and non-hepatic targets (7–9), we explored if LNPs could effectively deliver siRNA to neural cells. Neural cells are targets for drug delivery in multiple CNS disorders such as Alzheimer's disease, Parkinson's disease, ischemic stroke, peripheral nerve injuries, neuropathic and inflammatory pain (9–13). The key challenge associated with the delivery of siRNA to neural cells are its poor accumulation and short duration of action inside cells.

The potent delivery characteristics of LNPs may allow them to be optimized for neural cell delivery. LNPs are primarily composed of an ionizable cationic lipidoid along with helper lipids like distearylphosphatidylcholine (DSPC), polyethylene glycol-dimyristoyl glycerol (PEG-DMG) and cholesterol (13, 14). Ionizable cationic lipidoids allow higher encapsulation efficiencies and greater intracellular release via effective endosomal escape (16). Ionizable cationic lipidoids with pKa values between 6-7 acquire a positive charge at acidic pH and result in electrostatic interactions with the negatively charged siRNA molecules leading to the spontaneous formation of LNPs. At physiological pH of 7-7.4, these obtain a neutral charge and thereby largely eliminate

the toxicity associated with cationic lipids such as lipofectamine (17). This key feature renders the

LNPs a superior safety profile compared to cationic transfection agents. The acidic

microenvironment of endosomes lend the LNPs a positive charge because of which they associate

with negative anionic endosomal lipids leading to endosomal destabilization and improved siRNA

release into the cytoplasm (17, 18).

Seminal studies by Langer, Anderson and colleagues developed high throughput lipidoid

libraries consisting of thousands of ionizable cationic lipidoids and identified lead lipidoids based

on their *in vitro* and *in vivo* delivery efficacies in rodents as well as non-human primates. Amongst

those, C12-200 lipidoid demonstrated the highest knockdown and uptake *in vitro* (7, 19, 20).

Therefore, we chose C12-200 lipidoid as the ionizable cationic lipidoid component of LNPs. LNP-

based siRNA delivery harnesses several key advantages of LNP chemistry such as high

transfection efficiency, low toxicity and immunogenicity, protection of the payload from

physiological enzymes to increase their metabolic stability, ability for ligand conjugation and

enhancing the overall pharmacokinetics of the delivered cargo (22–24). The novelty of our work

lies in exploiting some of these cardinal features of LNPs to maximize siRNA uptake into neural

cells, a notoriously challenging delivery target.

In this pilot study, we formulated siRNA-LNPs using C12-200 lipidoid and characterized their

colloidal stability using dynamic light scattering. We characterized their cytocompatibility with a

panel of breast cancer cell lines and a model of sensory neurons, primary dorsal root ganglion

cultures. We studied the qualitative and quantitative uptake of siRNA delivered via LNPs into

neurons using fluorescence microcopy and flow cytometry, respectively. Despite mediating

similar levels of siRNA uptake, we found that LNPs are a safe carrier and show no signs of toxicity

in the neuronal models compared to the commercially available cationic lipid, Lipofectamine.

These findings encourage the further optimization of LNPs for knockdown of therapeutically-

relevant neuronal targets.

Experimental section

Materials

1,2-distearoyl-sn-glycero-3-phosphocholine (DSPC) (850365P) and 1,2-Dimyristoyl-rac–glycero-

3-methoxypolyethylene glycol-2000 (PEG-DMG) (8801518) were obtained from Avanti Polar

Lipids (Alabaster, AL). Cholesterol (8667) and Cy5-labeled siRNA were procured from Sigma-

Aldrich (St. Louis, MO). 1,1'-((2-(4-(2-((2-(bis (2 hydroxy dodecyl) amino) ethyl)

(2hydroxydodecyl) amino) ethyl) piperazin1yl) ethyl) azanediyl) bis(dodecan-2-ol) (C12-200), an

ionizable cationic lipidoid was a generous gift from Alnylam Pharmaceuticals (Cambridge, MA).

Quant-iT Ribogreen RNA Assay Kit (R11490) was purchased from Life Technologies (Carlsbad,

CA). Triton X-100 was procured from Acros organics (Morris Plains, NJ). Heat-inactivated fetal

bovine serum (FBS) and phosphate buffered saline (PBS) were purchased from Hyclone

Laboratories (Logan, UT). TrypLE express, RPMI + GlutaMAX-I (1X) and DMEM/F-12 were

purchased from Life Technologies Corporation (Grand Island, NY). MCF-7, MDA-MB-231 and

BT-549 cell lines were generously provided by Dr. Jane Cavanaugh (Duquesne University).

Human cortical neuron cell line (HCN-2) (CRL-10742) and primary rat cortical neurons (RCN)

(A10840-02) were purchased from ATCC (Manassas, VA) and Thermo Fisher Scientific

(Frederick, MD) respectively. siGFP (AM4626), siGAPDH (Silencer Select GAPDH siRNA)

(4390849),   siTRPV1   (5'   GCGCAUCUUCUACUUCAACTT 3',   3'

TTCGCGUAGAAGAUGAAGUUG 5') [4390828 (Assay ID 554887)] and control, inverted

siTRPV1 (5' CAACUUCAUCUUCUACGCGTT 3', 3' TTGUUGAAGUAGAAGAUGCGC 5')

[4390828 (Assay ID 554886)] were procured from Thermo Fisher Scientific (Austin, TX). RNeasy

Mini Kit (74104) and QIAshredder (79654) were procured from Qiagen (Qiagen, Germantown,

MD). High-capacity cDNA Reverse Transcription Kit (4368813) was purchased from Thermo

Fisher Scientific (ThermoFisher, Waltham, MA). Forward (AAGGATGGAACAACGGGCTAG)

and reverse primers (TCCTGGTAGTGAAGATGTGGG) (299688565) for TRPV1 were procured

from Integrated DNA Technologies (Coralville, Iowa). All reagents were used as received unless

stated otherwise.

Preparation of siRNA-loaded LNPs (siRNA-LNPs)

LNPs were prepared using previously reported methods (8). Briefly, the ionizable cationic lipidoid

C12-200, DSPC, cholesterol and PEG-DMG were dissolved in ethanol at a molar ratio of

50/10/38.5/1.5. The concentrations and volumes used for LNP preparation are shown in **Table 1**.

A one mg/mL solution of siRNA was prepared in 10 mM citrate buffer, pH 4.0. The 'slow mixing'

and 'fast mixing' protocols are defined based on the speed used during the addition of the

lipid/ethanolic phase to the aqueous phase. For the 'slow mixing' method, the entire volume of the

lipid phase was added to the aqueous phase instantaneously (in a single shot) followed by vortexing

the mixture for 30 seconds while maintaining the Fisher benchtop vortexer knob at position '7'.

For the 'fast mixing' protocol, the lipid phase was added dropwise to the aqueous phase under

continuous vortexing for 30 seconds while maintaining the Fisher benchtop vortexer knob at

position '7'. A precalculated volume of $1X$ PBS pH 7.4 was then added to the LNPs to adjust the

final siRNA concentration to 400 nM. All the formulations were made at a final siRNA

concentration of 400 nM and cationic ionizable lipidoid/siRNA w/w ratio was maintained at 5:1,

unless stated otherwise.

Table 1. Representative formulation scheme for LNPs

Component	w/w% in final LNP mixture	Stock concentration (mg/mL)	Volume of the stock solution required (µL)
Ethanolic phase			
C12-200	50	1	12.5
Cholesterol	38.5	1	3.1
PEG-DMG	1.5	0.5	13.6
DSPC	10	0.5	16.9
Ethanol	-	-	78.9
	Total ethanolic phase volume		125
Aqueous phase			
siRNA	400 nM	1	2.5
10 nM citrate buffer	-	-	122.5
PBS	-	-	250
	Total aqueous phase volume		375
Final volume of LNPs prepared (µL)			500

Agarose gel electrophoresis

Agarose gel electrophoresis was performed to qualitatively confirm the encapsulation of siRNA

in LNPs. Briefly, a 2% agarose gel was prepared in 1X Tris-borate buffer composed of 108 g Tris

and 55 g Boric acid dissolved in 900 ml distilled water with 40 ml of 0.5 M Na_2EDTA and 0.05%

Ethidium bromide. Samples pre-mixed with 1X RNA loading buffer were electrophoresed in an

Owl EasyCast B2 Mini Gel Electrophoresis System (Thermo Fisher Scientific, St. Louis, MO) for

90 min. The gel was imaged under UV light using a Gel Doc system (ProteinSimple, San Jose,

CA).

Determination of the extent of siRNA loading using the RiboGreen assay

The extent of siRNA loading in the prepared LNPs was measured using the Quant-iT Ribogreen RNA Assay Kit by following the manufacturer's instructions. RiboGreen is a fluorescent dye, which, in its free form exhibits minimal fluorescence but when bound to a nucleic acid, it fluoresces with an exceptionally high intensity that is directly proportional to the amount of nucleic acid (25). Total siRNA content is defined as the amount of encapsulated and non-encapsulated/free siRNA in the LNPs. The difference between the total and free siRNA was used to calculate the amount of siRNA encapsulated within the LNPs. A fresh sample of two µg/mL dsRNA stock solution was prepared each time with $1X$ Tris-EDTA (TE) and the standard curve was generated at concentrations ranging from 0-1000 ng/mL. A free siRNA sample was prepared with $1X$ TE and LNPs were lysed with 2% Triton X-100 in $1X$ TE to measure the "total" siRNA content. The fluorescence intensities were measured on a SYNERGY HTX multi-mode reader (Winooski, VT) at an excitation wavelength of 485 nm and an emission wavelength of 528 nm. The % encapsulation efficiency was calculated using the **Eq. 1**.

$\% \; siRNA \; encapsulation \; efficiency =$

$$\frac{(Amount \; of \; total \; siRNA \; in \; the \; sample - \; Amount \; of \; free \; siRNA \; in \; the \; sample)}{Amount \; of \; total \; siRNA \; in \; the \; sample} \times 100\% \quad \textbf{Equation 1}$$

Dynamic Light Scattering

To determine the physical stability of LNPs, the average particle diameters, polydispersity indices and zeta potentials of the blank and siGFP-loaded LNPs were measured by dynamic light scattering (DLS) using a Malvern Zetasizer Pro (Malvern Panalytical Inc., Westborough, PA) over a period of seven days with intermittent storage at 2-8°C and upon storage at 37°C for 24 h. We also performed the colloidal stability analysis of LNPs 24 h post-preparation in $1X$ PBS and in

samples supplemented with FBS (10%) to determine its serum stability. The prepared LNPs were

diluted to a siRNA concentration of 40 nM using 10 mM $1X$ PBS pH 7.4 for particle size

measurements and using deionized water for zeta potential measurements. All measurements were

carried out in triplicate and the data are presented as average + standard deviation (SD) and are

representative of at least five-six independent experiments (measurement errors <5%).

Cell culture

MCF-7 and BT-549 cells were maintained in RPMI + GlutaMAX ($1X$) supplemented with 10%

FBS. MDA-MB-231 cells were maintained in DMEM/F-12 1:1 medium supplemented with 2.5

mM L-Glutamine + 15 mM HEPES Buffer + 110 mg/L Sodium Pyruvate + 10% FBS. The growth

medium was changed every 48 hours. Primary rat dorsal root ganglion (DRG) cultures were

isolated using previously reported methods (26). DRG cultures were maintained in DMEM/high

glucose (4.5 g/L glucose) media supplemented with 2.5 mM L-Glutamine + 15 mM HEPES Buffer

+ 110 mg/L Sodium Pyruvate + 10 % FBS. Human cortical neuron cell line was maintained in

DMEM/high Glucose (4.5 g/L glucose) medium supplemented with 10 % FBS. Primary rat cortical

neurons were maintained in Neurobasal Plus medium supplemented with 200 mM GlutaMAX I

and B-27 Plus supplement. All cultures were maintained in a humidified incubator at 37 °C and

5% CO_2.

Cytocompatibility of LNPs

MCF-7, MDA-MB-231, BT-549 cells and primary rat DRG neurons were seeded in a clear, flat

bottom Poly-D-Lysine coated 96-well plate (Azer Scientific, Morgantown, PA) for the

cytocompatibility studies. MCF-7, MDA-MB-231, BT-549 cells were seeded at a density of 5,000

cells/well and DRG neurons were seeded at a density of 1,500 cells/well. Untreated cells were

used as a control in all studies. Cells were transfected for 4 h with LNPs containing 50 nM of

siRNA in complete growth medium in a volume of 50 µL/well. We also treated cells with

increasing doses of siRNA-LNPs (10, 25, 50, 75 and 100 nM siGFP-loaded LNPs) to determine

any possible effects of dose escalation on cytocompatibility. Post-transfection, the transfection

mixture was replaced with 200 µL of fresh complete growth medium/well followed by a 24-hour

incubation at 37°C and 5% CO_2. The relative intracellular ATP levels were measured using the

Cell Titer-Glo luminescence assay (ATP assay) 24 h-post transfection using previously described

methods (27–29). The levels of ATP directly correlate with the cell numbers used here as a

measure of cell viability. The ATP levels of the treatment groups were measured against those of

the untreated or control cells. Briefly, 60 µL of the complete growth media and 60 µL of Cell Titer

Glo 2.0 reagent were added to each well of the 96-well plate. The plate was incubated for 15

minutes in dark at room temperature in an incubator-shaker (Thermo Fisher Scientific, Waltham,

MA). Following incubation, 60 µL of the mixture from each well was transferred to a flat-bottom,

white opaque 96-well plate (Azer Scientific, Morgantown, PA). The luminescence was measured

using SYNERGY HTX multi-mode reader (BioTek Instruments, Winooski, VT). Relative ATP

levels (%) were calculated for the transfection groups by normalizing them to the luminescence of

the untreated cells as shown in **Eq.2**.

Relative ATP levels (%) = $\frac{Luminescence\ from\ cells\ treated\ with\ samples}{Luminescence\ from\ untreated\ cells} \times 100$ **Equation 2**

Cy5 siRNA uptake into primary rat cortical neurons using flow cytometry

Neurons were plated in a clear, flat-bottom Poly-D-Lysine coated 24-well plate (Genesee

Scientific, San Diego, CA) at a density of 50,000 neurons/well in Complete Neurobasal Plus media

and were allowed to acclimatize at 37°C and 5 % CO_2 for 4-5 days. Cy5 siRNA containing LNPs

were prepared as described earlier and diluted with the Complete Neurobasal Plus to a final Cy5

siRNA concentration of 50 nM. The neurons were incubated with the transfection mixture for 24

h. The transfection mixture contained either naked Cy5 siRNA or Cy5 siRNA-LNPs with PEG-

DMG (+ PEG-DMG) or Cy5 siRNA-LNPs without PEG-DMG (- PEG-DMG) or Cy5 siRNA-

Lipofectamine RNAiMAX complexes. Post-exposure, cells were gently removed from the wells

and collected in microcentrifuge tubes. The cell suspension was centrifuged at 300 g for 5 minutes

and the pellet was resuspended in 500 µL *1X* PBS. Cells were then analyzed using Attune NxT

Acoustic Focusing Cytometer (Singapore) equipped with Attune NxT software. The fluorescence

intensity of Cy5 siRNA was detected at an excitation wavelength of 638 nm and an emission

wavelength of 720/30 nm. A total of 30,000 events were recorded for each sample. Histogram

plots were obtained from the Attune NxT software. Cells were gated using forward vs. side scatter

plots to exclude dead cells and cell debris. Untreated cells were used as negative-staining controls

to set a gate for Cy5-negative and Cy5-positive populations. Data are presented as a percentage of

Cy5-positive (Cy5 (+)) events.

Cy5 siRNA uptake by fluorescence microscopy in a human cortical neuron cell line

We used fluorescence microscopy to determine the Cy5 siRNA uptake into a neuronal cell line.

Human cortical neurons (HCN-2) were seeded in a clear, flat-bottom, Poly-D-Lysine coated 48-

well plate (Genesee Scientific, San Diego, CA) at a density of 7,000 cells/well. The cells were

cultured in complete growth medium in a humidified incubator at 37°C and 5 % CO_2 for 1-2 weeks

while replenishing the growth medium every other day. After 4-5 days of culturing, the media was

replaced with 175 µL of the transfection mixture. The transfection mixture consisted of either Cy5

siRNA-LNPs or Cy5 siRNA-Lipofectamine RNAiMAX complexes containing 50 nM or 100 nM

of Cy5 siRNA or naked Cy5 siRNA diluted in complete growth media. Cells were incubated with

the transfection mixture for two, four and 24 hours at 37°C and 5% CO_2. After the respective time

points, the cells were washed once using pre-warmed PBS before adding 0.5 mL of the complete,

phenol red-free growth medium/well. Untreated cells and cells treated with Cy5 siRNA-

Lipofectamine RNAiMAX complexes were used as negative and positive controls, respectively.

Cells were imaged using an Olympus IX 73 epifluorescent inverted microscope (Olympus, Center

Valley, PA) to detect Cy5 signals at excitation and emission wavelengths of 651 nm and 670 nm,

respectively.

Transfection of siTRPV1-LNPs in primary rat DRG neurons

Primary rat DRG neurons were seeded in a clear, flat bottom Poly-D-Lysine coated 48-well plate

(Azer Scientific, Morgantown, PA) at a density of 2,500 cells/well in triplicates. The cells were

cultured in complete growth medium in a humidified incubator at 37°C and 5 % CO_2 for 48 hours.

Forty-eight hours post-seeding, the medium was replaced with 200 μL of the transfection mixture.

Cells were transfected with either 50 nM naked siTRPV1, LNPs containing 50 nM of siTRPV1 or

inverted siTRPV1 diluted in complete growth medium. Untreated cells and cells treated with

RNAiMAX lipofectamine/siTRPV1 complexes were used as negative and positive controls,

respectively. Cells were incubated with the transfection mixture for about eight-nine hours at 37°C

and 5 % CO_2. Post eight-nine hours of transfection, growth medium was added to bring up the

volume 0.5 mL/well followed by a 24-hour incubation.

Quantitative reverse transcription PCR

Twenty-four hours-post transfection, the medium was removed, and cells were washed with $1X$

PBS and detached with TrypLE express. Detached cells were collected in microcentrifuge tubes

and washed with $1X$ PBS. Total RNA extraction and purification from the cells was done using

RNeasy Mini Kit and QIAshredder according to the manufacturer's instructions. The isolated RNA

was eluted in 30 µl of RNase-free water and stored at -80°C. The concentration of RNA was

measured using NanoDrop ND-1000 spectrophotometer (Waltham, MA). Briefly, 1.5 µl of the

sample was placed on the sample holder. The concentration (ng/µl) and the absorbance ratio of

260/280 were representative of the quantity and quality of the RNA, respectively. A 260/280 ratio

of ~2.0 was considered as "pure" for RNA. For mRNA detection, 2 µg of the RNA samples was

reverse transcribed into cDNA in technical triplicates using a high-capacity cDNA Reverse

Transcription Kit. All steps were done on ice to maintain integrity of the samples. Reverse

transcription was done by a two-step protocol according to the manufacturer's instructions. A

DNA Thermal Cycler (Perkin Elmer Cetus) was used to incubate the samples. The resulting cDNA

was diluted $10X$ with DEPC-treated water and stored at -20°C. Concentration of the cDNA was

measured using NanoDrop ND-1000. One µg cDNA was used to perform RT-qPCR using TaqMan

Gene Expression Master Mix and TaqMan Assays. An appropriate volume of the Gene Expression

Master Mix and TaqMan primers were added to get a total volume of 20 µL. Reactions were

performed in three technical replicates. The plate was covered with Microamp optical adhesive

film and RT-qPCR was done using a Stratagene Mx3000P.

Statistical analysis

The data is expressed as mean ± standard deviation (SD), wherever applicable. Comparative

statistical analyses were performed using either one-way, two-way ANOVA or One sample t and

271   **Results**

272   **Determination of the extent of siRNA loading using the**

273   **RiboGreen assay**

Figure 1. **Extent of siRNA encapsulation in LNPs prepared at different mixing speeds determined by the Ribogreen assay**. The extent of siRNA encapsulation in LNPs (+/- PEG-DMG) was calculated using the following equation

$$\left(\frac{\textit{Amount of total siRNA in the sample} - \textit{Amount of free siRNA in the sample}}{\textit{Amount of total siRNA in the sample}}\right) \times$$

100%). SiRNA-LNPs were initially prepared in 10 mM citrate buffer and further diluted to a final siRNA concentration of 50 nM using 1x PBS. Data are presented as mean ± SD of n=3 samples. Statistical comparisons were made using two-way ANOVA. *$p <$ 0.05 and ns: non-significant.

We used the Ribogreen assay as a quantitative measure to determine the extent of siRNA

encapsulation within the LNPs *(Figure 1)* and used agarose gel electrophoresis as a qualitative

tool to confirm the absence of 'free' or unentrapped siRNA (**Supplementary Figure 1**). Triton X-

100 was used to lyse the LNPs resulting in the extraction of the entrapped siRNA to measure the

'total' siRNA (Total siRNA = entrapped siRNA + free siRNA). Fluorescence readout from LNPs

not treated with Triton X-100 is indicative of the amount of free siRNA. Two different mixing

speeds used during LNP formulation, slow *vs*. fast, were compared for determining their effects

on % siRNA encapsulation. The values increased from 74.4% at slow mixing to 83.8% at faster

mixing speeds for LNPs prepared without the inclusion of PEG-DMG, whereas we did not observe

a significant increase in siRNA loading for LNPs prepared with PEG-DMG at the different mixing

speeds.

Colloidal stability of siRNA-loaded LNPs

288
Physicochemical characteristics of nanocarriers such as particle diameter, polydispersity index

(PDI) and surface charge (zeta potential) are influential determinants of their biological activity

(30–32). Published studies have reported significant effects of physicochemical characteristics of

nano-sized systems on the overall delivery efficacy (33–36). Particle characteristics of self-

assembled systems such as LNPs can vary over time during storage potentially affecting their

biological activity. We also anticipated that neural cells may show a slower rate of particle uptake

compared to non-neuronal cells owing to limited endocytosis/other uptake pathways. We therefore

measured the changes in particle diameters and zeta potentials of the LNPs over a period of seven

days where the samples were refrigerated interim. Surface coating of nanoparticles using PEG-

DMG has been reported to improve their pharmacokinetic profile by reducing the recognition by

the mononuclear phagocyte system (37–39). We studied the effect of PEG-DMG in stabilizing

LNPs by comparing LNPs prepared in the presence (+) and absence (-) of PEG-DMG. We

compared the particle parameters of blank LNPs and siRNA-loaded LNPs to study the effect of

siRNA encapsulation on the resulting particle characteristics.

Figure 2. Colloidal stability of blank or siGFP-loaded LNPs measured using dynamic light scattering. SiGFP-LNPs were initially prepared in 10 mM citrate buffer and further diluted to a final siRNA concentration of 50 nM using 1x PBS (pH 7.4). The samples were stored at 2-8 $^{\circ}$C while not in use. Z-average particle diameters (a), dispersity indices (b) and zeta potentials (c) were measured on a Malvern Zetasizer Pro. Data are presented as mean ± SD of n=3 measurements. Statistical comparisons were made using one-way ANOVA or One sample t and Wilcoxon tests. *$p < 0.05$, **$p < 0.01$, ***$p < 0.001$ and ****$p < 0.0001$.

Blank LNPs (+PEG-DMG) showed average particle diameters of about 250 nm which

increased to about 350 nm on day seven. In contrast, the diameters of LNPs (-PEG-DMG) were

about 900 nm post-preparation and increased to 4 μm after seven days *(Figure 2a)*. A similar trend

was observed for the PDI values of blank LNPs i.e., an initial PDI of 0.32 increased to 0.4 after

seven days for LNPs (+PEG-DMG) and an initial PDI of 0.5 increased to 1.8 after seven days for

LNPs (-PEG-DMG) *(Figure 2b)*. We observed a few statistically significant changes in the particle

diameters, PDI values and zeta potential of the prepared LNPs over the period of 7-days

(Supplementary Table 1). The narrow polydispersity indices and smaller average particle

diameters demonstrate the stabilizing effect of PEG-DMG in the LNPs. siGFP-loaded LNPs (with

PEG-DMG) showed average particle diameters of about 120 nm which increased to about 200 nm

on day seven *(Figure 2a)*. Their initial PDI values of ca. 0.2 increased to about 0.3 after seven

days *(Figure 2b)*. From this observation we can infer that siRNA loading in the LNPs results in

an additional stabilizing effect to the respective blank LNP counterparts resulting in narrow and

consistent PDI values and particle diameters.

The cationic lipidoid, C12-200, in the LNPs resulted in a net positive charge to the blank LNPs.

Blank LNPs containing PEG-DMG showed slightly lower zeta values (6-10 mV) compared to

blank LNPs without PEG-DMG (9-12 mV) *(Figure 2c)* that is likely explained by the insertion of

PEG chains in between the C12-200 lipidoids or due to formation of a PEG monolayer around

C12-200 (40). As seen from *Figure 2c*, siGFP-loaded LNPs showed a negative zeta potential

compared to their blank LNP counterparts. Although the changes were not statistically significant,

the zeta potentials of the siGFP-loaded LNPs decreased over the seven-day period from -5.91 mV

to -19.12 mV. Overall, the average particle diameters and polydispersity indices do not vary

significantly over a period of seven days. However, zeta potential values of siGFP-LNPs decreased

over a period of seven days. Despite the apparent numerical differences in the zeta potentials, a

one-way ANOVA analysis revealed that the differences were not significant.

*< 0.05, ***< 0.001, ****< 0.0001

Figure 3. Colloidal stability of blank- or siGFP-loaded LNPs immediately after preparation (0 h) and upon storage at 37°C for 24 h measured using dynamic light scattering. SiGFP-LNPs were initially prepared in 10 mM citrate buffer and further diluted to a final siRNA concentration of 50 nM using 1x PBS at a final pH of 7.4 for particle size and PDI measurements and using de-ionized water for zeta potential measurements. The samples were stored at 37°C for 24 h. Z-average particle diameters (a), polydispersity indices (b) and zeta potentials (c) were measured on a Malvern Zetasizer Pro. Data are presented as mean ± SD of n=3 measurements. Tukey's and Šídák's multiple comparisons tests for statistical comparisons were performed using two-way ANOVA. *p < 0.05, ***p < 0.001, ****p < 0.0001 and ns: non-significant.

The colloidal stability of siGFP loaded- and blank LNPs was measured using dynamic light scattering at 0 (immediately after preparation) and 24 h post-preparation upon storage at 37°C (*Figure 3*). We also studied the effect of PEG-DMG in stabilizing LNPs by preparing LNPs with (+) and without (-) PEG-DMG. Blank LNPs (+PEG-DMG) showed an average particle diameter of about 167.8 nm that shifted to about 159.8 nm 24 h-post storage at 37°C. In contrast, the diameters of LNPs (-PEG-DMG) were about 345.5 nm post-preparation and increased to 471.1 nm post 24 h storage at 37°C (*Figure 3a*). A similar trend was observed for the PDI values of blank LNPs i.e., an initial PDI of 0.09 decreased to 0.06 for LNPs (+PEG-DMG) and an initial PDI of 0.3 increased to 0.4 for LNPs (-PEG-DMG) 24 h-post storage at 37°C (*Figure 3b*). We found a similar trend for the particle diameters and dispersity indices of siGFP-loaded LNPs, both (+) and (-) PEG-DMG, 24 h-post storage at 37°C (*Figure 3a and b*). siGFP-loaded LNPs (+PEG-DMG) showed an average particle diameter of about 163.2 nm that shifted to about 157.2 nm 24 h-post storage at 37°C. In contrast, the diameters of LNPs (-PEG-DMG) were about 442.2 nm post-preparation and decreased to 390.7 nm 24 h-post storage at 37°C (*Figure 3a*). For the dispersity indices, an initial value of 0.09 decreased to 0.06 for siGFP-loaded LNPs (+PEG-DMG) and an initial value of 0.31 shifted to 0.32 for LNPs (-PEG-DMG) 24 h-post storage at 37°C (*Figure 3b*). Nevertheless, the observed changes in particle diameters and dispersity indices of blank LNPs (+ PEG-DMG) and siGFP-loaded LNPs (+ and – PEG-DMG) 24 h-post storage at 37°C were statistically insignificant. However, we noted a significant increase in the particle diameters (*$p < 0.05$) and dispersity indices (****$p < 0.0001$) of blank LNPs (-PEG-DMG) likely due to the absence of PEG-DMG and the siGFP cargo—that are known to provide a stabilizing effect by inhibiting particle-particle aggregation and via complexation of the negatively charged

siRNA with the positively-charged C12-200, respectively. Noteworthy, we noted a similar trend

of the stabilizing effects of PEG-DMG and the siGFP cargo in *Figure 2*.

Blank LNPs containing PEG-DMG showed slightly negative zeta potentials (-5 to -7 mV)

that shifted to slightly cationic values (3 to 4 mV) whereas the zeta potentials of blank LNPs

without PEG-DMG were about -13 mV that increased to about -2 mV 24 h-post storage at 37°C

(*Figure 3c*). siGFP-loaded LNPs (+ PEG-DMG) showed a zeta potential of -1.2 mV that increased

to about 4.6 mV whereas the LNPs (- PEG-DMG) counterparts showed a zeta potential of -9.8 mV

that increased to about -9.1 mV 24 h-post storage at 37°C (*Figure 3c*). Despite the apparent

numerical differences, it should be noted that the measured zeta potentials reflect electrostatically-

neutral samples and a two-way ANOVA analysis revealed that the differences were not significant.

Figure 4. Intensity size distribution plots demonstrating the colloidal stability of siGFP-loaded LNPs (+PEG-DMG) supplemented with 10% FBS. (a) A blank sample consisting of 10% FBS in 1x PBS was used to understand the serum protein-mediated scattering. (b) SiGFP-LNPs (+PEG-DMG) were initially prepared in 10 mM citrate buffer and further diluted to a final siRNA concentration of 50 nM using 1x PBS. LNPs supplemented with 10% FBS were measured to determine their serum stability. (d) An overlay depicts the pattern of the size distribution obtained for all the LNP samples.

The particle diameters of siGFP-LNPs (+PEG-DMG) containing 10% FBS was measured using

dynamic light scattering to determine the effect of serum proteins on the colloidal stability of

LNPs. We specifically chose siGFP-LNPs (+PEG-DMG) to study the effect of serum since the

presence of siRNA and PEG-DMG resulted in the maximum stability of LNPs with respect to

particle diameters and dispersity indices **(Figure 2*a and b*)**. We first measured the particle

diameter of a control sample containing 10% FBS in PBS (***Figure 4a***) that showed an average

particle diameter of 19.6 nm whereas siGFP-LNPs (+PEG-DMG) in PBS showed an average

particle diameter of about 170 nm ***(Figure 4b)***. We observed distinct size distribution by intensity

peaks for the blank 10% FBS as well as LNP samples ***(Figure 4a and b)***. We then measured the

particle diameter of siGFP-LNPs (+PEG-DMG) that was supplemented with 10% FBS. ***Figure 4*c**

has two distinct peaks denoting peaks corresponding to 10% FBS and the siGFP-LNPs (+PEG-

DMG) at 20.2 nm and 80.5 nm respectively. The overlay size distribution plot demonstrated a

"shift" in the siGFP-LNPs (+PEG-DMG) peak towards the left (lower particle diameters) when

the LNPs were supplemented with 10% FBS as opposed to those in PBS (80.5 nm vs 170 nm)

(Figure 4d). We speculate that the observed decrease in diameter is suggestive of the additional

stabilizing effects of serum (10% FBS) on the LNP diameters. This, in fact, may be

beneficial/favorable for LNP uptake ***(Figure 7 and Figure 8)*** as neurons may preferentially

internalize smaller compared to larger LNPs.

Figure 5. Representative correlogram and intensity size distribution plots of siGFP-loaded LNPs (+PEG-DMG). siGFP-LNPs were initially prepared in 10 mM citrate buffer and further diluted to a final siRNA concentration of 50 nM using 1*x* PBS at a final pH of 7.4 prior to particle size measurements on a Malvern Zetasizer Pro.

Table 2. Comparison of the Y-intercept in the autocorrelograms from the colloidal stability data (Figure 2) at different time points.

Groups	Y-intercept				
	Day 0	Day 1	Day 3	Day 5	Day 7
Blank LNPs (with PEG-DMG)	0.98	0.98	0.94	0.89	0.8
Blank LNPs (without PEG-DMG)	0.99	1.3	1	1	0.9
siGFP LNPs (with PEG-DMG)	0.96	0.93	0.9	0.86	0.87
siGFP LNPs (without PEG-DMG)	1	1.1	1.1	0.96	0.88

The correlation function is a statistical analysis tool for measuring the non-randomness in a data set that is depicted here as a correlogram. A correlogram is a plot of the correlation coefficient G (τ) vs time (μs) **(Figure 5)**. The Y-intercept of the correlogram is indicative of the signal to noise ratio and presence/absence of multiple scattering. A Y-intercept of ~0.9-1.15 indicates a good

 signal in the absence of multiple scattering. Samples with multiple scattering show a Y-intercept

 of ~0.6-0.8 and samples with number fluctuations show a Y-intercept of ~1.15-1.4 (41). As

 observed from **Table 2**, the Y-intercept values for all the LNP groups over a period of seven days

 ranged from 0.8-1.1 that is indicative of a good signal-to-noise ratio in the absence of multiple

 scattering and number fluctuations.

Cytocompatibility of C12-200-LNPs

Figure 6. C12-200 LNPs are cytocompatible with TRPV1-expressing breast cancer cell line panel (a), rat primary DRG neurons (b) and MDA-MB-231 cells (c). Cells were incubated with LNPs containing 50 nM siGAPDH (a), 50 nM siTRPV1 (b) and the indicated concentrations of siGFP-LNPs (c) for four hours. Untreated cells and cells treated with PEI (50 µg/mL) were used as negative and positive controls, respectively. Cell viability was determined 24 h-post transfection using a CellGlo luminescence viability assay and the data were normalized to untreated cells. Data represents mean + SD (n=6).

We studied the cytocompatibility of the prepared C12-200/siGAPDH LNPs with MCF-7,

MDA-MB-231 and BT-549 cells as these cell models are known to overexpress TRPV1, a

neuronal target for siRNA delivery *(Figure 6a)* (42). We also studied the compatibility of C12-

200/siTRPV1 LNPs with primary rat dorsal root ganglion (DRG) neurons *(Figure 6b)*. We

specifically chose primary rat DRG neurons due to their high expression of TRPV1 (41, 42).

TRPV1 is reported to be expressed in 60% of the peripheral nociceptors present in the DRG (45)

and is a potential neuronal target for gene knockdown. Cell Titer Glo assay (referred henceforth

as the ATP assay) was used the study cytocompatibility of LNPs. The ATP assay is a simple and

straightforward technique wherein the readout in relative luminescence units (RLU) can be directly

correlated with the ATP levels in the cells. RLU of the untreated cells were normalized to 100%

cell viability. Untreated cells and cells treated with a synthetic polycation, polyethyleneimine (PEI)

served as the negative and positive controls, respectively. As we expected, MCF-7, MDA-MB-

231, BT-549 cells and primary DRG neurons treated with PEI (50 µg/mL), a synthetic polycation

known to induce apoptosis showed a 50-60% reduction in cell viability (46). However, MCF-7,

MDA-MB-231 and BT-549 incubated with C12-200/siGAPDH LNPs showed very little evidence

of cell death, with cell viabilities >95% 24 h-post transfection *(Figure 6a)*. Similarly, siTRPV1-

loaded C12-200 LNPs were well tolerated (cell viabilities of ca. 100%) by primary DRG neurons

(Figure 6b). We tested the effect of siRNA dose escalation by incubating MDA-MB-231 cells

with increasing concentrations of siRNA-LNPs (10, 25, 50, 75 and 100 nM siGFP-loaded LNPs).

We noticed cell viabilities >85% 24 h-post transfection (*Figure 6c*) suggesting that higher siRNA

and concomitant lipid doses were well-tolerated by the cells. There was a significant difference

($p<0.0001$) in the % cell viabilities of cells treated with siRNA-LNPs compared to those treated

with the positive control, PEI (20% cell viability).

Flow cytometry analysis of Cy5 siRNA uptake into primary rat cortical neurons

After confirming that LNPs had little-to-no effect on cell viability, we next wanted to determine if LNPs were taken up by neurons. Because of their commercial availability as well as their non-mitotic nature similar to that of the primary rat DRG neurons, primary rat cortical neurons were used to quantify the uptake levels of Cy5 siRNA using flow cytometry. Lipofectamine RNAiMAX, a cationic lipid, was used as a positive control. Flow cytometry is a quantitative tool for single-cell analysis to measure the light scattered and the fluorescence emitted form a single cell (47). The dead cells/debris were likely removed at the centrifugation step during the sample processing and as a result, we did not observe any dead cells or debris *(Figure 7a, left)* that are typically found at the bottom left corner of the SSC-A vs. FSC-A plot (48). We then analyzed whether the cells were present in a monodisperse cell suspension to allow for single cell analysis. The forward scatter distributions for height *vs*. area (FSC-A v/s FSC-H) showed a linear profile for about 92% of the recorded events which indicated a single-cell suspension *(Figure 7a, right)*. We analyzed untreated cells and gated out the auto fluorescence *(Figure 7b, left)*. Thus, a shift of signal to the right of the histogram gate (R1 region) was considered to signify that the cell was Cy5-positive (+). The proportion of Cy5 (+) cells directly correspond to the % uptake of Cy5 siRNA in the neurons as represented by the individual histogram plots for the different groups *(Figure 7c)*.

Figure 7. Uptake of LNPs into rat primary cortical neurons determined using flow cytometry analysis. Cells were transfected for 24 h with the indicated samples in a 24-well plate. Cy5 siRNA-Lipofectamine RNAiMAX complexes and untreated cells were used as positive and negative controls, respectively. Data are presented as percentages of positive cells for Cy5 (Cy5 (+)). SSC-A vs. FSC-A and FSC-H vs. FSC-A plots of untreated cells demonstrating monodispersed cells. (a), Untreated and Cy5 siRNA/Lipofectamine RNAiMAX-treated cells (b), Cells treated with the indicated samples (c), Overlay histograms comparing Cy5 (+) cells in each treatment group in comparison to the controls (d), Overlay histograms (e) and % Cy5 siRNA uptake by the neurons for the respective groups (f). The histograms are representative of quadruplicate samples. Statistical comparisons were made using one-way ANOVA. ****$p < 0.0001$.

We then analyzed the % uptake of Cy5 siRNA encapsulated in LNPs prepared with (+) and without (-) the inclusion of PEG-DMG. Around 92-94% *(Figure 7c (yellow))* and 81-83% *(Figure 7c (brown))* cells were Cy5 (+) when transfected with Cy5 siRNA-LNPs prepared with and without the inclusion of PEG-DMG, respectively. *Figure 7d* shows the relative Cy5+ cells in each of the indicated groups in reference to the untreated (blue) and positive control-treated (green)

groups. The rightward shift in intensities of Cy5 (+) cells for all the groups in comparison with the

controls are demonstrated in the overlay histogram plot in *Figure 7*e. As expected, the % uptake

of Cy5 siRNA was least in cells treated with free Cy5 siRNA and greatest in cells treated with

LNPs (+PEG-DEMG) and Cy5 siRNA/Lipofectamine RNAiMAX complexes *(Figure 7e and f)*.

Furthermore, as seen in *Figure 7*e, we saw a greater uptake of LNPs with PEG-DMG as compared

to those without PEG-DMG. Particle sizes of LNPs play one of the major roles in determining

uptake levels and therefore, lower diameter particles may allow efficient cellular internalization.

Furthermore, a significant difference in the uptake of Cy5 siRNA was observed when transfected

with naked Cy5 siRNA and Cy5 siRNA-LNPs (+/- PEG-DMG) *(Figure 7e and f)*. This reiterates

the need for a safe and efficient transfection agent to maximize the uptake of siRNA in neurons, a

hard-to-transfect cell type.

Around 94-96% of the cells were Cy5 (+) for the Lipofectamine RNAiMAX group indicating

efficient uptake *(Figure 7b right and f)*. Charge-based interactions of cationic lipids with

negatively-charged cells allows for higher uptake as compared to neutral or negatively-charged

particles. About 44-46% of the cells were Cy5 (+) for the naked Cy5 siRNA transfection group

(Figure 7c (red)). The difference between the uptake mediated by LNPs (+ PEG-DMG) and

Lipofectamine RNAiMAX was statistically non-significant *(Figure 7f)*. Despite the similar levels

of uptake among the LNP(+PEG-DMG) and lipofectamine groups, it must also be pointed out that

the uptake mediated by Lipofectamine RNAiMAX was accompanied with noticeable cell

stress/toxicity upon visual observation under a microscope whereas LNPs showed a superior safety

profile.

Cy5 siRNA uptake by fluorescent microscopy in a human cortical neuron cell line

We studied the effect of exposure time on the uptake of LNPs by incubating the cells for two, four or 24 hours. PEGylation is known to regulate the uptake kinetics of LNPs into cells (49). We compared the differences in uptake for LNPs prepared with/without PEG-DMG. Although Lipofectamine RNAiMAX is a gold standard transfection agent for RNA molecules, it is also quite toxic to cells owing to its strong cationic nature. Therefore, it was unsurprising when we saw changes in morphology indicating cell death, just 2 h after Lipofectamine RNAiMAX was added to cortical neurons, while untreated cells continued to appear spindle-shaped and healthy *(Figure 8a)*.

For this experiment, cells were incubated either with naked Cy5 siRNA, Cy5 siRNA LNP with PEG-DMG, with Cy5 siRNA LNP without PEG-DMG, with Lipofectamine RNAiMAX Cy5 siRNA, or were left untreated. We qualitatively compared the fluorescence intensity among the cells treated with the above samples. Cells treated with naked Cy5 siRNA showed less intense fluorescent signals as compared to cells treated with Cy5 siRNA-LNPs (+/- PEG-DMG) for the two- and four-hour incubation time points *(Figure 8a, b)*. However, we saw a noticeable increase in siRNA uptake 24 h-post transfection **(*Figure 8c*)**. The next pivotal observation was the difference in uptake from the LNPs (+/- PEG-DMG) groups. As mentioned earlier, PEG-DMG plays a key role in determining the physical stability of LNPs as it allows to maintain lower particle diameters by inhibiting particle aggregation (38). We also noted time-dependent differences in Cy5 siRNA uptake for the LNPs formulated with and without PEG-DMG. LNPs formulated with PEG-DMG showed a time-dependent increase in the uptake of Cy5 siRNA as opposed to LNPs

without PEG-DMG where the extent of uptake was not time-dependent. We observed that only a

few cells did not show Cy5 siRNA signals when treated with Cy5 siRNA-LNPs (+ PEG-DMG)

two- and four-hours post-transfection whereas 24 h post-treatment almost all the cells showed

signals corresponding to Cy5 siRNA. Conversely, cells treated with Cy5 siRNA-LNPs (- PEG-

DMG) showed efficient uptake of Cy5 siRNA post two- and four hours transfection. A zoomed-

in image of cells treated with LNPs containing 50 nM Cy5 siRNA is presented in *Figure 8*d to

show image resolution. This particularly depicts the uptake of Cy5 siRNA LNPs associated with

diffuse cytoplasmic fluorescence.

a. <u>2h exposure</u>

LNPs (- PEG-DMG) | LNPs (+ PEG-DMG) | Naked | RNAiMAX complexes | Untreated cells

Bright field

Cy5

b. <u>4h exposure</u>

LNPs (- PEG-DMG) | LNPs (+ PEG-DMG) | Naked | RNAiMAX complexes | Untreated cells

Bright field

Cy5

<u>24h exposure</u>

c.

LNPs (- PEG-DMG) | LNPs (+ PEG-DMG) | Naked | RNAiMAX complexes | Untreated cells

Bright field

Cy5

d.

**Zoomed-in image of cells treated with
Cy5 siRNA LNPs (+PEG-DMG) 24 h post-exposure**

Figure 8. Cellular uptake of Cy5 siRNA determined using fluorescent microscopy. HCN-2 cells (human cortical neuron cell line) were incubated for 2 hours (a) 4 hours (b) and 24 hours (c) with the indicated samples containing 50 nM Cy5 siRNA. Panel (d) represents the zoomed-in image depicting HCN-2 cells incubated with LNPs with PEG-DMG. Scale bar = 50 μm. Cells were imaged using an Olympus IX 73 epifluorescent inverted microscope to detect Cy5 signals at excitation and emission wavelengths of 651 nm and 670 nm, respectively. Images are representative of n=3 independent wells.

Discussion

The goal of this pilot study was to determine if LNPs based on the benchmark C12-200 lipidoid can be used for siRNA transfection into neurons, a notoriously challenging yet clinically unmet/interesting delivery target. We propose that the well-documented delivery advantages of LNPs including their high levels of siRNA encapsulation, favorable pharmacokinetics, limited immune activation, uptake into target cells and efficient endosomal escape for siRNA into the cytoplasm (14, 47, 48) make them interesting candidates for neural delivery applications.

In this pilot study, we prepared and characterized C12-200 LNPs using DLS. The RiboGreen assay is a well-validated quantitative method to determine the % siRNA loading in LNPs (49, 50). Encapsulation of siRNA in the LNPs for the slow and fast mixing (without PEG-DMG) speeds were about 74.4% and 83.8%, respectively. LNPs with and without PEG-DMG (for fast mixing speed) showed encapsulation efficiencies of about 71.4 % and 83.8 %, respectively *(Figure 1)* which were comparable to the entrapment of siRNA reported for some of the top LNP candidates (54). Although we did not find a significant difference in the encapsulation efficiencies of LNPs prepared with and without PEG-DMG, the inclusion of PEG-DMG serves other vital roles *i.e.,* maintaining lower particle diameters by inhibiting particle aggregation and providing a stealth effect for longer circulation times *in vivo* (37, 38). We further studied the physicochemical stability

of the prepared LNPs and compared the stabilizing effect provided by the inclusion of PEG-DMG

and siRNA in the LNPs. We utilized siGFP as the model siRNA to compare the siRNA-loaded

and blank LNP counterparts prepared both with and without PEG-DMG. We observed a non-

significant increase or change in the particle diameters, polydispersity indices and zeta potential

over a one-week storage period at 2-8 °C for all the samples *(Figure 2)*. Nevertheless, the particle

diameters differed significantly for blank *vs*. siRNA-loaded LNPs and LNPs with *vs*. LNPs without

PEG-DMG *(Figure 2a)*. A similar trend was also observed for the polydispersity indices of blank

and siRNA-loaded LNPs; both with and without PEG-DMG *(Figure 2b)*. Our data demonstrated

that both siRNA loading and PEG-DMG provided a stabilizing effect to the LNPs by maintaining

lower particle diameters and uniform dispersity indices over a period of seven-days. The

stabilizing effects of siRNA and PEG-DMG on the resulting particle diameters and dispersity

indices were noted when the LNPs were stored for 24 h at 37°C (***Figure 3***). LNPs showed further

lower particle diameters (ca. 80.5 nm) when sizes were measured in the presence of serum (10%

FBS) suggestive of the additional serum-mediated stabilization (***Figure 4***).

Although LNPs are deemed to be safe and are well-tolerated by most of the cells, determining

their safety and tolerability in neural cells was our primary aim. As shown in ***Figure 6***, LNPs

were deemed to be well-tolerated by primary DRG neurons as evident by >95% cell viabilities.

Increasing the dose of siRNA (and concomitantly the dose of the lipids) did not alter the safety

profile of LNPs *(Figure 6c)*. Establishing the safety profile of LNPs with neural cells allowed

further evaluation of their uptake in neural cell lines. We studied the uptake of Cy5 siRNA-loaded

LNPs in primary rat cortical neurons and a human neuronal cell line using flow cytometry and

fluorescence microscopy, respectively. Previously, Howard *et al* and Thiramanas *et al.* studied the

cellular uptake of Cy5 siRNA using flow cytometry (52, 53). As PEG-DMG is known to stabilize

the LNPs with resulting lower particle diameters and thus have an impact on their cellular uptake,

we compared LNPs prepared with (+) and without (-) PEG-DMG. We used the siRNA complexes

of the cationic transfection agent, Lipofectamine RNAiMAX, as a positive control. The cell-

associated fluorescence (Cy5 (+) neurons) for the Cy5 siRNA-LNPs (+ PEG-DMG) group was

about 94%—2-fold greater than the neurons transfected with naked Cy5 siRNA group *(Figure 7c,*

e, and f). As expected, despite its transfection-induced toxicity, Cy5 siRNA-Lipofectamine

RNAiMAX-treated cells demonstrated the highest proportion of Cy5 (+) cells *(Figure 7c, e, and*

f). On the other hand, cells treated with LNPs appeared healthy and showed no visible signs of

toxicity, highlighting the safety of LNPs over cationic transfection agents like Lipofectamine

RNAiMAX. There was a significant difference in the uptake of neurons transfected with naked

Cy5 siRNA as compared to the neurons transfected with the LNPs (both with and without PEG-

DMG) emphasizing the need for an effective transfection agent for neural cell uptake *(Figure 7f)*.

We also performed fluorescence microscopy to qualitatively study the uptake of Cy5 siRNA

into neural cells. A technical caveat of such qualitative assessments is rooted in the fact that the

observed/apparent fluorescent intensities are not normalized to cell number. The cells appeared to

be healthy, and spindle-shaped in all the treatment groups except for the Lipofectamine

RNAiMAX group where cells appeared stressed and rounded as early as at the 2 h timepoint

(Figure 8a). As described earlier, we speculate that this is due strong cationic nature of

Lipofectamine RNAiMAX. We did not observe a greater uptake for cells treated with LNPs at 100

nM siRNA concentration *(Supplementary Figure 2)*. Nearly all the cells in the field showed Cy5

fluorescent signals 24 h-post exposure *(Figure 8c)* compared to the 2 and 4 h time points *(Figure*

8a and b), suggesting that neural cells require a longer transfection time compared to non-neural

cells. LNPs formulated with PEG-DMG showed a time-dependent increase in the uptake of Cy5

siRNA as opposed to LNPs without PEG-DMG. The time dependent uptake of LNPs formulated

with PEG-DMG was in agreement with the PEG-DMG dissociation kinetics as predicted by Mui

et al. (57). The PEG-lipid component of the LNPs undergoes desorption from the surface of LNPs

which results in efficient uptake of the cargo into the cells (58). Studies have reported desorption

rates of PEG-DMG from the LNPs at a rate of 45%/h only after which LNPs were taken up by

cells (57). We observed a similar trend of Cy5 siRNA uptake when neurons were transfected with

LNPs (+ PEG-DMG). At the 2 and 4 h time points, most (but not all) of the cells had efficiently

taken up the LNPs. However, 24 h post-treatment, almost all the cells in the field of view showed

fluorescent puncta corresponding to Cy5 siRNA. In contrast, in cells transfected with Cy5 siRNA-

LNPs (- PEG-DMG), all the cells demonstrated complete and uniform uptake irrespective of the

incubation period. The effects of RNAiMAX-mediated toxicity were evident via altered cell

morphology seen in the phase contrast images.

Overall, both flow cytometry and fluorescent microscopy analysis in cortical neurons

demonstrated efficient uptake of siRNA delivered using LNPs in the absence of noticeable toxicity

while the cationic Lipofectamine RNAiMAX-mediated uptake was concomitant with significant

cellular toxicity. Based on these findings, we conclude that LNPs are a safe carrier for siRNA

delivery to neural cells. We are currently screening a pre-existing LNP library prepared using

different lipidoid chemistries to identify LNP candidates for safe and efficient neuronal gene

knockdown. We anticipate that the results of these studies will set the foundation for using LNPs

for neural cell transfection in a variety of CNS diseases. While our approach validates using LNPs

for uptake of siRNA into neural cells, their knockdown efficacy and therapeutic index remain an

open question which we are currently investigating.

Conclusion

SiRNA-loaded LNPs remained stable over a period of seven days and were well-tolerated by

neural cell models, allowing their further exploration for gene silencing. Although the LNPs are

comparable to Lipofectamine RNAiMAX in facilitating siRNA uptake into cortical neurons, the

ionizable cationic LNPs are safer and well-tolerated compared to the cationic Lipofectamine

RNAiMAX. PEG-DMG served a crucial role in maintaining lower particle diameters that likely

resulted in efficient uptake into primary rat cortical neurons. Our findings suggest that LNPs hold

promise for further silencing of therapeutically-relevant neuronal targets like TRPV1.

Acknowledgements

This work was supported via start-up funds for the Manickam laboratory from Duquesne

University (DU), a 2021 Faculty Development Fund (Office of Research, DU) and a 2021 Charles

Henry Leach II Fund to the PI (Duquesne University). We are grateful to Dr. Kathryn A.

Whitehead (Carnegie Mellon University) and her group for their support. We are grateful to Drs.

Jane E. Hartung and Michael S. Gold (University of Pittsburgh) for providing the DRG cultures.

We are also thankful to Dr. Wilson Meng and express our special appreciation to Mr. Nevil

Abraham (Duquesne University) for his help with the qPCR experiments. We express our

appreciation to Mr. Duncan Dobbins (Duquesne University) for his assistance with the graphical

abstract.

References

1. Wu SY, McMillan NAJ. Lipidic systems for in vivo siRNA delivery. AAPS J. 2009;11(4):639–52.
2. Wang J, Lu Z, Wientjes MG, Au JLS. Delivery of siRNA therapeutics: Barriers and carriers. AAPS J. 2010;12(4):492–503.
3. Akinc A, Maier M, Manoharan M, Fitzgerald K, Jayaraman M, Barros S, et al. The Onpattro story and the clinical translation of nanomedicines containing nucleic acid-based drugs. Nat Nanotechnol. 2019 Dec 1;14:1084–7.
4. FDA. FDA Approves First COVID-19 Vaccine. FDA News Release [Internet]. 2021; Available from: https://www.fda.gov/news-events/press-announcements/fda-approves-first-covid-19-vaccine
5. Ryan Cross. Without these lipid shells, there would be no mRNA vaccines for COVID-19. Chem Eng News. 2021;16–9.
6. Katakowski JA, Mukherjee G, Wilner SE, Maier KE, Harrison MT, Di Lorenzo TP, et al. Delivery of siRNAs to dendritic cells using DEC205-targeted lipid nanoparticles to inhibit immune responses. Mol Ther. 2016;24(1):146–55.
7. Uemura Y, Naoi T, Kanai Y, Kobayashi K. The efficiency of lipid nanoparticles with an original cationic lipid as a siRNA delivery system for macrophages and dendritic cells. Pharm Dev Technol. 2018 Apr 24;24:1–22.
8. Whitehead KA, Dorkin JR, Vegas AJ, Chang PH, Veiseh O, Matthews J, et al. Degradable lipid nanoparticles with predictable in vivo siRNA delivery activity. Nat Commun. 2014;5.
9. Lopes CDF, Gonçalves NP, Gomes CP, Saraiva MJ, Pêgo AP. BDNF gene delivery mediated by neuron-targeted nanoparticles is neuroprotective in peripheral nerve injury. Biomaterials. 2017;121:83–96.
10. Haney MJ, Klyachko NL, Zhao Y, Gupta R, Plotnikova EG, He Z, et al. Exosomes as drug delivery vehicles for Parkinson's disease therapy. J Control Release [Internet]. 2015;207:18–30. Available from: http://dx.doi.org/10.1016/j.jconrel.2015.03.033
11. Wolfe D, Mata M, Fink DJ. Targeted drug delivery to the peripheral nervous system using gene therapy. Neurosci Lett [Internet]. 2012;527(2):85–9. Available from: http://dx.doi.org/10.1016/j.neulet.2012.04.047
12. H. Ferreira-Vieira T, M. Guimaraes I, R. Silva F, M. Ribeiro F. Alzheimer's disease: Targeting the Cholinergic System. Curr Neuropharmacol. 2016;14(1):101–15.
13. Yang L, Han B, Zhang Z, Wang S, Bai Y, Zhang Y, et al. Extracellular vesicle-mediated delivery of circular RNA SCMH1 promotes functional recovery in rodent and nonhuman primate ischemic stroke models. Circulation. 2020;142(6):556–74.
14. Kim J, Jozic A, Sahay G. Naturally Derived Membrane Lipids Impact Nanoparticle-Based Messenger RNA Delivery. Cell Mol Bioeng. 2020;13(5):463–74.
15. Kulkarni JA, Witzigmann D, Chen S, Cullis PR, Van Der Meel R. Lipid Nanoparticle Technology for Clinical Translation of siRNA Therapeutics. Acc Chem Res. 2019;52(9):2435–44.
16. Rehman ZU, Zuhorn IS, Hoekstra D. How cationic lipids transfer nucleic acids into cells and across cellular membranes: Recent advances. J Control Release [Internet]. 2013;166(1):46–56. Available from: http://dx.doi.org/10.1016/j.jconrel.2012.12.014
17. Soenen SJH, Brisson AR, De Cuyper M. Addressing the problem of cationic lipid-

mediated toxicity: The magnetoliposome model. Biomaterials [Internet].
2009;30(22):3691–701. Available from:
http://dx.doi.org/10.1016/j.biomaterials.2009.03.040
18. Dahlman J, Kauffman K, Langer R, Anderson D. Nanotechnology for In vivo Targeted
siRNA Delivery. Adv Genet. 2014 Nov 21;88:37–69.
19. Wan C, Allen T, Cullis P. Lipid nanoparticle delivery systems for siRNA-based
therapeutics. Drug Deliv Transl Res. 2014 Feb 1;4.
20. Love KT, Mahon KP, Levins CG, Whitehead KA, Querbes W, Dorkin JR, et al. Lipid-like
materials for low-dose, in vivo gene silencing. Proc Natl Acad Sci U S A.
2010;107(5):1864–9.
21. Novobrantseva TI, Borodovsky A, Wong J, Klebanov B, Zafari M, Yucius K, et al.
Systemic RNAi-mediated gene silencing in nonhuman primate and rodent myeloid cells.
Mol Ther - Nucleic Acids. 2012;1(1):e4.
22. Blakney AK, McKay PF, Yus BI, Aldon Y, Shattock RJ. Inside out: optimization of lipid
nanoparticle formulations for exterior complexation and in vivo delivery of saRNA. Gene
Ther [Internet]. 2019;26(9):363–72. Available from: http://dx.doi.org/10.1038/s41434-
019-0095-2
23. Naseri N, Valizadeh H, Zakeri-Milani P. Solid lipid nanoparticles and nanostructured lipid
carriers: Structure preparation and application. Adv Pharm Bull [Internet]. 2015;5(3):305–
13. Available from: http://dx.doi.org/10.15171/apb.2015.043
24. Cullis PR, Hope MJ. Lipid Nanoparticle Systems for Enabling Gene Therapies. Mol Ther
[Internet]. 2017;25(7):1467–75. Available from:
http://dx.doi.org/10.1016/j.ymthe.2017.03.013
25. J. Jones L, T. Yue S, Cheung Ching-Ying, L. Singer V. RNA Quantitation by
Fluorescence-Based Solution Assay- RiboGreen Reagent Characterization.pdf. Anal
Biochem [Internet]. 1998;374(265):368–74. Available from: http://files/191/J. Jones et al.
- 1998 - RNA Quantitation by Fluorescence-Based Solution As.pdf
26. Hartung JE, Gold MS. GCaMP as an indirect measure of electrical activity in rat
trigeminal ganglion neurons. Cell Calcium [Internet]. 2020;89(April):102225. Available
from: https://doi.org/10.1016/j.ceca.2020.102225
27. Dave KM, Ali L, Manickam DS. Characterization of the SIM-A9 cell line as a model of
activated microglia in the context of neuropathic pain. PLoS One [Internet]. 2020;15(4):1–
28. Available from: http://dx.doi.org/10.1371/journal.pone.0231597
28. Dave KM, Han L, Jackson MA, Kadlecik L, Duvall CL, S Manickam D. DNA Polyplexes
of a Phosphorylcholine-Based Zwitterionic Polymer for Gene Delivery. Pharm Res.
2020;37(9).
29. Dave KM, Zhao W, Hoover C, D'Souza A, S Manickam D. Extracellular Vesicles
Derived from a Human Brain Endothelial Cell Line Increase Cellular ATP Levels. AAPS
PharmSciTech. 2021;22(1).
30. Honary S, Zahir F. Effect of zeta potential on the properties of nano-drug delivery systems
- A review (Part 1). Trop J Pharm Res. 2013;12(2):255–64.
31. Ing LY, Zin NM, Sarwar A, Katas H. Antifungal activity of chitosan nanoparticles and
correlation with their physical properties. Int J Biomater. 2012;2012.
32. Li X, Sloat BR, Yanasarn N, Cui Z. Relationship between the size of nanoparticles and
their adjuvant activity: Data from a study with an improved experimental design. Eur J
Pharm Biopharm. 2011;78(1):107–16.

33.   Breznan D, Das DD, Mackinnon-Roy C, Bernatchez S, Sayari A, Hill M, et al.
795   Physicochemical Properties Can Be Key Determinants of Mesoporous Silica Nanoparticle
796   Potency in Vitro. ACS Nano. 2018;12(12):12062–79.
797   34.   Shin SW, Song IH, Um SH. Role of physicochemical properties in nanoparticle toxicity.
798   Nanomaterials. 2015;5(3):1351–65.
799   35.   Navya PN, Daima HK. Rational engineering of physicochemical properties of
800   nanomaterials for biomedical applications with nanotoxicological perspectives. Nano
801   Converg. 2016;3(1):1–14.
802   36.   Braakhuis HM, Park MVDZ, Gosens I, De Jong WH, Cassee FR. Physicochemical
803   characteristics of nanomaterials that affect pulmonary inflammation. Part Fibre Toxicol.
804   2014;11(1).
805   37.   Witzigmann D, Kulkarni JA, Leung J, Chen S, Cullis PR, Meel R Van Der. Since January
806   2020 Elsevier has created a COVID-19 resource centre with free information in English
807   and Mandarin on the novel coronavirus COVID- 19 . The COVID-19 resource centre is
808   hosted on Elsevier Connect , the company ' s public news and information .
809   2020;(January).
810   38.   Chen S, Tam YYC, Lin PJC, Leung AKK, Tam YK, Cullis PR. Development of lipid
811   nanoparticle formulations of siRNA for hepatocyte gene silencing following subcutaneous
812   administration. J Control Release [Internet]. 2014;196:106–12. Available from:
813   http://dx.doi.org/10.1016/j.jconrel.2014.09.025
814   39.   Romberg B, Hennink WE, Storm G. Sheddable coatings for long-circulating
815   nanoparticles. Pharm Res. 2008;25(1):55–71.
816   40.   Kulkarni JA, Darjuan MM, Mercer JE, Chen S, Van Der Meel R, Thewalt JL, et al. On the
817   Formation and Morphology of Lipid Nanoparticles Containing Ionizable Cationic Lipids
818   and siRNA. ACS Nano. 2018;12(5):4787–95.
819   41.   Malvern Panalytical. CORRELATION INTERCEPT – WHAT IS IT AND WHAT DOES
820   IT MEAN? [Internet]. Available from: https://www.materials-
821   talks.com/blog/2020/03/10/correlation-intercept-what-is-it-and-what-does-it-mean/
822   42.   Pecze L, Jósvay K, Blum W, Petrovics G, Vizler C, Oláh Z, et al. Activation of
823   endogenous TRPV1 fails to induce overstimulation-based cytotoxicity in breast and
824   prostate cancer cells but not in pain-sensing neurons. Biochim Biophys Acta - Mol Cell
825   Res [Internet]. 2016;1863(8):2054–64. Available from:
826   http://dx.doi.org/10.1016/j.bbamcr.2016.05.007
827   43.   Esposito MF, Malayil R, Hanes M, Deer T. Unique Characteristics of the Dorsal Root
828   Ganglion as a Target for Neuromodulation. Pain Med (United States). 2019;20:S23–30.
829   44.   Yu X, Liu H, Hamel KA, Morvan MG, Yu S, Leff J, et al. Dorsal root ganglion
830   macrophages contribute to both the initiation and persistence of neuropathic pain. Nat
831   Commun [Internet]. 2020;11(1):1–12. Available from: http://dx.doi.org/10.1038/s41467-
832   019-13839-2
833   45.   Xu Q, Zhang XM, Duan KZ, Gu XY, Han M, Liu BL, et al. Peripheral tgf-β1 signaling is
834   a critical event in bone cancer-induced hyperalgesia in rodents. J Neurosci.
835   2013;33(49):19099–111.
836   46.   Moghimi SM, Symonds P, Murray JC, Hunter AC, Debska G, Szewczyk A. A two-stage
837   poly(ethylenimine)-mediated cytotoxicity: Implications for gene transfer/therapy. Mol
838   Ther. 2005;11(6):990–5.
839   47.   Davey HM, Kell DB. Flow cytometry and cell sorting of heterogeneous microbial

840   populations: The importance of single-cell analyses. Microbiol Rev. 1996;60(4):641–96.

841   48.   BIO-RAD. Flow Cytometry Data Analysis [Internet]. Available from: https://www.bio-
842   rad-antibodies.com/flow-cytometry-gating-
843   strategies.html?JSESSIONID_STERLING=1C53AF8B8470DB1019FE94619BC4BF4F.e
844   commerce1&evCntryLang=US-
845   en&cntry=US&thirdPartyCookieEnabled=true&wdLOR=cBC762A28-80AB-9C4A-
846   8B9C-0FF8F79509C6

847   49.   Ryals RC, Patel S, Acosta C, McKinney M, Pennesi ME, Sahay G. The effects of
848   PEGylation on LNP based mRNA delivery to the eye. PLoS One [Internet]. 2020;15(10
849   October):1–17. Available from: http://dx.doi.org/10.1371/journal.pone.0241006

850   50.   Chen S, Tam YYC, Lin PJC, Sung MMH, Tam YK, Cullis PR. Influence of particle size
851   on the in vivo potency of lipid nanoparticle formulations of siRNA. J Control Release
852   [Internet]. 2016;235:236–44. Available from:
853   http://dx.doi.org/10.1016/j.jconrel.2016.05.059

854   51.   van der Meel R, Chen S, Zaifman J, Kulkarni J, Zhang XR, Tam Y, et al. Modular lipid
855   nanoparticle platform technology for siRNA and lipophilic prodrug delivery. bioRxiv.
856   2020;(2020).

857   52.   Buyens K, Lucas B, Raemdonck K, Braeckmans K, Vercammen J, Hendrix J, et al. A fast
858   and sensitive method for measuring the integrity of siRNA-carrier complexes in full
859   human serum. J Control Release. 2008;126(1):67–76.

860   53.   Walsh C, Ou K, Belliveau N, Leaver T, Wild A, Huft J, et al. Microfluidic-Based
861   Manufacture of siRNA-Lipid Nanoparticles for Therapeutic Applications. Methods Mol
862   Biol. 2014 Feb 25;1141:109–20.

863   54.   Ball R, Bajaj P, Whitehead KA. Achieving long-term stability of lipid nanoparticles:
864   Examining the effect of pH, temperature, and lyophilization. Int J Nanomedicine.
865   2017;12:305–15.

866   55.   Howard KA, Rahbek UL, Liu X, Damgaard CK, Glud SZ, Andersen M, et al. RNA
867   Interference in Vitro and in Vivo Using a Novel Chitosan/siRNA Nanoparticle System.
868   Mol Ther [Internet]. 2006;14(4):476–84. Available from:
869   http://dx.doi.org/10.1016/j.ymthe.2006.04.010

870   56.   Thiramanas R, Li M, Jiang S, Landfester K, Mailänder V. Cellular Uptake of siRNA-
871   Loaded Nanocarriers to Knockdown PD-L1: Strategies to Improve T-cell Functions. Cells.
872   2020;9(9):1–12.

873   57.   Mui1 BL, , Ying K Tam1 , Muthusamy Jayaraman2 , Steven M Ansell1 , Xinyao Du1 ,
874   Yuen Yi C Tam3 PJL, Chen3 S, Narayanannair2 JK, , Kallanthottathil G Rajeev2 ,
875   Muthiah Manoharan2 , Akin Akinc2 , Martin A Maier2 PC, Madden1 TD, et al. Influence
876   of Polyethylene Glycol Lipid Desorption Rates on Pharmacokinetics and
877   Pharmacodynamics of siRNA Lipid Nanoparticles. Mol Ther - Nucleic Acids.
878   2013;2(12):1–8.

879   58.   Kulkarni JA, Cullis PR, Van Der Meel R. Lipid Nanoparticles Enabling Gene Therapies:
880   From Concepts to Clinical Utility. Nucleic Acid Ther. 2018;28(3):146–57.

Response to reviewers

We thank the reviewers for their insightful comments and helpful suggestions. We have addressed the comments and the individual responses to the questions are presented below. All new text (and figure titles) added in the revised manuscript in response to the reviewer's comments are highlighted in blue font.

Reviewer #1: The authors give a specific neural application of LNPs which is a hot topic during the COVID-19 pandemic. There are some points to clarify before publication:

1. Although a reference is cited in the section "Preparation of siRNA-loaded LNPs", this section can be described in more detail for the ease of understanding of readers out of the field. These parameters could be detailed: i) precise volume of ethanolic phase and aqueous phase used for the fabrication of LNPs should be cleared, ii) the 'slow mixing' and for the 'fast mixing' protocols should be explained in detail, iii) how the ethanol is removed from LNPs before application on the cells.

The precise volumes of the aqueous and ethanolic phases have been added to the revised manuscript in **Table 1**. We have also appended the protocols to include details of the 'slow' and 'fast' mixing in the methods section under '**Preparation of siRNA-loaded LNPs (siRNA-LNPs)**'. We treated cells with non-dialyzed LNPs and the concentration of ethanol in the transfection/treatment mixture was ca. 2% v/v. In our personal correspondence with Dr. Kathryn Whitehead (Carnegie Mellon University) ca. 2018, one of the pioneers in the development of siRNA-loaded LNPs, she indicated that non-dialyzed LNPs could be safely used on cells as long as the cells tolerated the formulations with no significant toxicity. We observed ~100% cell viabilities when cancer cell lines (MCF-7, MDA-MB-231 and BT-549) and primary DRG neurons were exposed to LNPs (**Figure 6**) and conclude that the non-dialyzed LNPs are safely tolerated by the cell models used in this study.

2. The colloidal stability of nanoparticles should be also checked at 37 C for 24 h since the cells were exposed to nanoparticles for 24 hours in 37 C. Testing the stability at 37 C reveals if the nanoparticles remain stable during this experiment. Additionally, it would be nice to have the results of the serum stability test results of LNPs to see if the developed LNPs are stable in this medium.

The colloidal stability of LNPs at 37°C for 24 h and in the presence of serum was studied and the results are presented in the revised manuscript as **Figures 3** and **4**. Our data showed that the LNP diameters and zeta potentials did no change appreciably 24 h post-preparation at 37 °C and LNP particle diameters were additionally stabilized in the presence of 10% FBS—suggesting that both these conditions did not affect their colloidal stability.

3. TEM imaging before and after incubation at 37 C for 24 h could be presented to prove the stability of LNPs.

As discussed above, we have used DLS measurements as a quantitative tool to demonstrate the stability of LNPs. We thank the reviewer for this important suggestion and are now establishing collaborative arrangements with the University of Pittsburgh to carry out cryo-TEM studies of LNPs and the results of these studies will be reported in a forthcoming manuscript.

4. In figure4, some of the graphs and the letters on these graphs are presented with the same color which makes it harder to follow and understand. This figure could be rebuilt with more clear structuring and coloring. Specifically, the graph lines with green color seem pixelized.

This figure has been re-worked to improve clarity in the revised manuscript (**Figure 7**). We would like to highlight a few things to explain the pixelization of the histogram. The green-colored histogram in **Figure 7** shows the percentage of positive cells for Cy5 (Cy5 (+)) when the neurons were treated with Cy5 siRNA/Lipofectamine RNAiMAX complexes. As expected, Lipofectamine RNAiMAX showed the highest (94.9 %) percentage of Cy5 (+) cells. As a result, neurons treated with Lipofectamine RNAiMAX showed the greatest shift towards the right. Interestingly, we also observed two distinct peaks (a "bimodal" histogram) for this group with varying Cy5 intensities as compared to a "unimodal" histogram for neurons treated with LNPs (**Figure 7c (yellow and brown)**). As RNAiMAX is toxic to cells, it is likely that the first peak corresponds to Cy5 siRNA taken up by distressed cells (resulting in lower Cy5 intensities). The second peak showed a greater percentage Cy5 (+) cells demonstrating the increased uptake of Cy5 siRNA by the viable cells. The histogram corresponding the Lipofectamine groups appears to be pixelized as the histogram width is also broader for this treatment group compared to the LNP-treated neurons. Moreover, the histograms depicted in **Figure 7** are autogenerated by the Attune NxT software of the Attune NxT Flow Cytometer. It should be pointed out that histograms reported in literature as well as those in the training and user guides of the Attune NxT Cytometer show a similar pattern of pixelization (1–4).

5. The fluorescent microscopy images presented in Figure5 seem blurry, they could be enhanced. Additionally, in Figure5b the cell morphology seems different than other cells specifically in the image of cells exposed to RNAİMAX complex (Cells treated with this complex are presented as viable after 4 h, it would be necessary to detail this finding).

The 'blurriness' of the fluorescent microscopy image presented in **Figure 8** (in the revised manuscript) is likely a result of the 'zoomed-out' micrographs presented in the figures. We have revised **Figure 8** by including a 'zoomed-in' version of one the LNP groups (cells treated with 50 nM Cy5 siRNA-LNPs+PEG-DMG in **panel d**. This image depicts a clearer view of the cells wherein the Cy5 siRNA LNPs show diffuse fluorescence in the cytoplasm. The reviewer has rightly pointed out the difference in morphology of cells exposed to Lipofectamine RNAiMAX in **panels b and c** in **Figure 8**. Lipofectamine RNAiMAX is a highly cationic lipid and a benchmark transfection agent for RNA molecules. Although a strong cationic charge serves to enhance the uptake of carrier molecules in cells, it concurrently mediates cell stress (5). The observed changes in morphology of cells is a result of this Lipofectamine-mediated stress in this particular cell model, human cortical neurons.

Reviewer #2: The author herein demonstrate performance of LNPs for siRNA delivery to neural cell. The study is interesting and deemed fit for publication in this journal. However, there are several limitations that must be addressed and discussed.

1. The author must perform a reporter assay. Only uptake does not guarantee successful siRNA delivery.

The reviewer makes an important comment here and we have indeed performed pilot experiments to study the knockdown of a therapeutic/neuron-relevant knockdown target. We had chosen not to include this data in the original submission due to the reasons discussed in the supplementary information, but this data is now included in the revised manuscript (**Supplementary Figure 3**). Primary dorsal root ganglion (DRG) neurons isolated from rat trigeminal ganglia were used to study the knockdown of transient receptor potential cation channel subfamily V member 1 (TRPV1), a neuron-relevant knockdown target. SiRNA against TRPV1 (siTRPV1) was chosen as a proof-of-concept drug because it has been reported that TPRV1 becomes hyperactive in response to chronic inflammatory pain that reduces their threshold for activation and increases sodium, calcium and chloride fluxes (7, 8). TRPV1 is a non-selective cation channel exhibiting high calcium permeability and is expressed in peripheral, central axon terminals in the spinal cord, C fibers and/or Aδ fibers (8). Nearly 60% of the peptidergic primary nociceptors in the dorsal root ganglia and trigeminal ganglia express TRPV1 (8). Primary DRG cultures were isolated using previously reported methods (9). The inherent technical challenges associated with isolating DRG neurons/cultures resulted in low numbers of isolated cells but we still proceeded with the transfection study to determine if this TRPV1 target can be silenced using siTRPV1 delivered via LNPs (10–12).

<u>**A key limitation of this study is that the low numbers of neurons (2,500 cells/well) used will naturally have a low (or rather a very low) baseline expression of TRPV1 and therefore, this current setting does not allow us to optimally determine the effectiveness of siTRPV1 delivery via LNPs**</u>. Proceeding with this caveat, we cautiously discuss here the findings from this experiment. siTRPV1-LNPs (+PEG-DMG) were formulated using C12-200, an ionizable cationic lipid and helper lipids. The resulting mRNA levels post-transfection were determined using quantitative reverse transcription PCR. Our data showed a low 9% knockdown of TRPV1 when primary DRG cultures were treated with siTRPV1-LNPs that was similar to cells treated with the positive control, siTRPV1-Lipofectamine RNAiMAX complexes. Cells treated with naked siTRPV1-LNPs showed around 2.6% knockdown of TRPV1 whereas inverted (inv.) siTRPV1-LNPs showed about 3.2% TRPV1 knockdown. Despite the low levels of knockdown, the observed differences in % knockdown were significant (****$p < 0.0001$). As stated earlier in this section, this pilot study must be carefully interpreted due to the caveats associated with the low cell numbers and therefore, a lower baseline TRPV1 expression. Nevertheless, this data points out the safety and the potential of LNPs as delivery agents to silence therapeutically-relevant neuronal targets. Current efforts are underway in the laboratory to establish primary neuronal cultures with a higher yield and results of those studies will be reported in a forthcoming manuscript.

2. The authors just selected one concentration to show cytocompatibility. The cytocompatibility of the LNPs and control lipids must be performed in a dose escalation setting for better comparison.

The cytocompatibility data of LNPs tested at increasing doses of siGFP LNPs is now included in the revised manuscript (**Figure 6c**).

3. The intensity and autocorrelation function of DLS measurement must be included. This reviewer strongly recommends comparing autocorrelation function at different time point to get insights into their stability.

The intensity and autocorrelation function of DLS measurement is now included in the revised manuscript in **Figure 4**. We have also compared the autocorrelation function at different time points and is now included in the revised manuscript as **Table 2**.

4. The author must stain the live cells. Besides, the microscopy pictures are of poor resolution.

The 'blurriness' of the fluorescent microscopy image presented in **Figure 8** (in the revised manuscript) is likely a result of the 'zoomed-out' micrographs presented in the figures. We have revised **Figure 8** by including a 'zoomed-in' version of one the LNP groups (cells treated with 50 nM Cy5 siRNA-LNPs+PEG-DMG) in **panel d**. This image depicts a clearer view of the cells wherein the LNP-delivered siRNA shows diffuse fluorescence in the cytoplasm.

5. The LNP preparation methods need clarification. How much volume of 1 mg/mL siRNA solution was prepared? The author must mention the cat# for each siRNA used.

The precise volumes of the aqueous and ethanolic phases have been added to the revised manuscript in **Table 1**. We have also appended the protocols for 'slow' and 'fast' mixing in the methods section under '**Preparation of siRNA-loaded LNPs (siRNA-LNPs)'**. The catalog numbers of the siRNAs are now included in the **'Materials'** section of the revised manuscript.

6. In LNP preparation, why the author chose to dilute instead of dialysis/similar technique to replace the citrate buffer with PBS? What's the final pH of the solution? This is important to report the zetapotential, as it is highly pH dependent. Depending on volume of citrate and PBS used for LNP preparation for different experiment their charge and size may get affected.

In our personal correspondence with Dr. Kathryn Whitehead (Carnegie Mellon University) ca. 2018, one of the pioneers in the development of siRNA-loaded LNPs, she indicated that non-dialyzed LNPs could be safely used on cells as long as the cells tolerated the formulations with no significant toxicity. We observed ~100% cell viabilities when cancer cell lines (MCF-7, MDA-

MB-231 and BT-549) and primary DRG neurons were exposed to LNPs (**Figure 6**) and conclude that the non-dialyzed LNPs are safely tolerated by the cell models used in this study.

The final pH of the solution is 7.4 (now included in the legend for **Figure 2** in the revised manuscript).

7. The method section must include statistical analysis. Two-way ANOVA and not one-way should be performed whenever applicable.

We have now added statistical analysis in the **'Methods'** section of the revised manuscript. We used either one-way ANOVA or two-way ANOVA along with One-Sample T- and Wilcoxon tests based on the recommendations from GraphPad Prism software.

References

1.	ThermoFisher. Imaging-enhanced flow cytometry [Internet]. Available from: https://www.thermofisher.com/us/en/home/life-science/cell-analysis/flow-cytometry/flow-cytometers/attune-nxt-flow-cytometer/sample-data.html

2.	Life Technologies. Attune ® acoustic focusing cytometer training guide. 2010;(MAN0002736):2–6.

3.	ThermoFisher Scientific. Attune ™ NxT Software User Guide. 2019;(100024236).

4.	Flegel K, Sun D, Grushko O, Ma Y, Buttitta L. Live cell cycle analysis of Drosophila tissues using the attune acoustic focusing cytometer and vybrant dyecycle violet DNA stain. J Vis Exp. 2013;(75):1–7.

5.	Soenen SJH, Brisson AR, De Cuyper M. Addressing the problem of cationic lipid-mediated toxicity: The magnetoliposome model. Biomaterials [Internet]. 2009;30(22):3691–701. Available from: http://dx.doi.org/10.1016/j.biomaterials.2009.03.040

6.	Huang J, Zhang X, McNaughton P. Inflammatory Pain: The Cellular Basis of Heat Hyperalgesia. Curr Neuropharmacol. 2006;4(3):197–206.

7.	Tominaga M, Wada M, Masu M. Potentiation of capsaicin receptor activity by metabotropic ATP receptors as a possible mechanism for ATP-evoked pain and hyperalgesia. Proc Natl Acad Sci U S A. 2001;98(12):6951–6.

8.	Finnerup NB, Attal N, Haroutounian S, McNicol E, Baron R, Dworkin RH, et al. Pharmacotherapy for neuropathic pain in adults: Systematic review, meta-analysis and updated NeuPSig recommendations. Lancet Neurol. 2015;14(2):162–73.

9.	Hartung JE, Gold MS. GCaMP as an indirect measure of electrical activity in rat trigeminal ganglion neurons. Cell Calcium [Internet]. 2020;89(April):102225. Available from: https://doi.org/10.1016/j.ceca.2020.102225

10.	Shen H, Gan M, Yang H, Zou J. An integrated cell isolation and purification method for rat dorsal root ganglion neurons. J Int Med Res [Internet]. 2019;47(7):3253–60. Available from: https://doi.org/10.1177/0300060519855585

11.   Jennifer Gordon, Shohreh Amini and MKW. General overview of neuronal cell culture. Methods Mol Biol [Internet]. 2013;1078:35–44. Available from: http://link.springer.com/10.1007/978-1-62703-640-5

12.   Klimovich P, Rubina K, Sysoeva V, Semina E. Three-dimensional model of dorsal root ganglion explant as a method of studying neurotrophic factors in regenerative medicine. Biomedicines. 2020;8(3).

Figure 1

a. Particle diameters

*< 0.05,
**< 0.01,
***< 0.001
****< 0.0001

Day 0   Day 1   Day 3   Day 5   Day 7

b. Dispersity indices

c. Zeta Potential

Zoomed-in image of cells treated with
Cy5 siRNA LNPs (+PEG-DMG) 24 h post-exposure

Author Supplementary Files (excel worksheets, video in mpeg-1
format only , etc)

Click here to access/download
Author Supplementary Files (excel worksheets, video in
mpeg-1 format only , etc)
Revision_Supplementary Information.pdf