The physical properties of the stick insect pad secretion are independent of body size

Domna-Maria Kaimaki,[*] Charlotte N. S. Andrew, Andrea E. L. Attipoe, and David Labonte[*]

Many insects use adhesive organs to climb. The ability to cling to surfaces is advantageous but is increasingly challenged as animals grow, due to the associated reduction in surface-to-volume ratio. Previous work has demonstrated that some climbing animals overcome this scaling problem by systematically altering the maximum force per area their adhesive pads can sustain; their adhesive organs become more efficient as they grow, an observation which is also of substantial relevance for the design of bio-inspired adhesives. What is the origin of this change in efficiency? In insects, adhesive contact is mediated by a thin film of a liquid, thought to increase adhesive performance via capillary and viscous forces. Here, we use interference reflection microscopy and dewetting experiments to measure the contact angle and dewetting speed of the pad secretion of Indian stick insects varying in mass by over two orders of magnitude. Neither contact angle nor dewetting speed change significantly with body mass, suggesting that the key physical properties of the pad secretion – its surface tension and viscosity – are size-invariant. Thus, the observed change in pad efficiency is unlikely to arise from systematic changes of the physical properties of the pad secretion; the functional role of the secretion remains unclear.

1 Introduction

Bio-inspired adhesives are an important area of biomimetic innovation[1]. However, despite significant progress[2–4], key challenges remain. Technical adhesives often need to cover large areas and carry heavy loads, resulting in a classic scaling problem: large contacts suffer reduced strength due to stress concentrations, and heavy weights lead to poorer relative performance due to changes in the support-surface-to-volume ratio[4,5]. A similar problem arises for climbing animals of various sizes[6]. How do they resolve this problem?

Previous work has revealed that some climbing animals are able to systematically alter the sustainable force per area – the efficiency of their adhesive pads - as they increase in size[6–10]. In insects[11], tree frogs[7,8] and arachnids[12,13], adhesive surface contacts are mediated via thin films of a liquid secretion, and it has been speculated that systematic changes to the physical properties of this secretion represent a possible strategy to alter pad efficiency with size[6]. The basis of this hypothesis is the long-standing assumption that the secretion's functional significance is to promote attachment via capillary and viscous forces[14–19]. Here, we test experimentally whether Indian stick insects alter the physical properties of their pad secretion as they grow, in order to increase pad efficiency and overcome the scaling problem.

2 Materials & methods

2.1 Study animals

Stick insects (*Carausius morosus*, Phasmatidae, Sinéty 1901) were taken from a laboratory colony, fed with bramble and water *ad libitum*, and kept in a climate chamber at 60%RH/25°C with a 12/12 h light cycle. We randomly collected 54 individuals to cover a body mass range of $2.57 - 892.03$ mg, close to the maximum mass range of the colony (Fig.1A).

Department of Bioengineering, Imperial College London, SW7 2AZ, UK. E-mail: domna-maria.kaimaki@imperial.ac.uk, d.labonte@imperial.ac.uk

2.2 Contact angle and dewetting speed measurements

We estimated the physical properties of the secretion - its surface tension and viscosity - by Interference Reflection Microscopy (IRM) and dewetting experiments, performed with a five-component setup: (i) an insect mounting apparatus as described in Labonte *et al*[20]; (ii) a borosilicate glass coverslip coated with conducting Indium-Tin-Oxide on one side (18 x 18mm, #1.5 thickness and $8 - 12\Omega$ resistivity, SPI Supplies, USA) cleaned by an ultrasonic bath in acetone and isopropanol for 10 mins each and blow-dried with compressed air; (iii) a surface holder to secure the coverslip in place and to connect it to a temperature control unit; (iv) a K-thermocouple (TP870, Extech, USA) connected to a custom-built Arduino temperature controller to maintain a constant surface temperature of 30°C during all experiments; and (v) an inverted microscope (DMi8, Leica Microsystems, Germany) connected to a high-speed camera (Blackfly S USB3, BFS-U3-16S2C-CS, FLIR, USA; Fig.1B).

In order to assess whether the secretion's surface tension changes with size, we measured contact angles of droplets deposited on glass using IRM, following earlier work[21,22]. In brief, droplets of the pad secretion were deposited on the glass coverslips using a micromanipulator (M3301R, World Precision Instruments, UK). Secretion droplets were then imaged at 63x magnification, an illuminating numerical aperture of 0.8, and with a wavelength of 445nm from a pE-300 ultra LED (filter with 10nm bandwidth, CoolLED, UK; Fig.1C). We approximated the contact angle as the slope calculated from the first two height increments, to minimise a bias introduced by the curvature of the droplets. We measured contact angles from three droplets per individual and 23 individuals across the size range (n=23, N=69). The relationship between contact angle and surface tension is complex[23], but simplifies for a dominantly dispersive fluid such as the insect pad secretion (see SI).

In order to estimate the viscosity of the secretion, we quantified its dewetting speed[22]. Hydrodynamic theory predicts that surface

Fig. 1 A. *Carausius morosus* stick insects vary by over two orders of magnitude in weight between first instars and adults. B. The physical properties of the secretion were determined with a custom-made setup. C. Interference Reflection Microscopy image of a droplet of the pad secretion deposited on glass, recorded at 30°C. Interference fringes indicate fixed height increments and can thus be used to estimate the contact angle of the pad secretion and hence its surface tension. D. When a contacting pad is slid to expose the secretion film, thermodynamic instabilities lead to dewetting; dry patches nucleate within the thin continuous film (dotted circle), then grow (dashed circle) and finally merge (full circle). The speed of dry patch growth is inversely proportional to the secretion's viscosity.

tension, γ, and dewetting speed, v_{d}, are related to viscosity, η, via:

$$\eta \propto \theta^3 \frac{\gamma}{v_{\mathrm{d}}}, \qquad (1)$$

where θ is the contact angle[24–26] (Fig.1D). In order to measure dewetting speed, we connected the micromanipulator to a hydraulic drum controller (MHW-3, Narishige, Japan), to rapidly slide pads in surface contact in parallel to the coverslip. The subsequent dewetting of the thin film left behind was recorded at 20x magnification and 226fps (Fig. 1D). We recorded a minimum of three dewetting videos per stick insect. Every dewetting experiment was conducted on a clean part of the glass coverslip. A period of at least 10min separated consecutive experiments with the same individual in order to provide time for recovery of a sufficient footprint volume[17]. The rate of growth of dry patches, the dewetting speed ($v_{\mathrm{d}} = \frac{dR}{dt}$), was extracted with a custom-written ImageJ macro[27]. A minimum of three dry patches tracked for at least four frames were analysed for each stick insect (n=54, N=354).

3   Results & discussion

The contact angle of the pad secretion does not vary significantly with size (log-log slope obtained via ordinary least-squares regression=-0.095 (95% CI (-0.239 | 0.048)), $F_{1,21}$=1.912, p=0.181, n=23; Fig.2A). The mean contact angle of $17 \pm 9°$ (mean $\pm$ std), is in excellent agreement with previous measurements in ants, stick insects and cockroaches ($18 \pm 7°$, $18 \pm 1°$ and $17 \pm 1°$ respectively,[17,22,28]. As the secretion is immiscible in water and almost entirely dispersive[29,30], this result strongly suggests a size-invariant surface tension (see SI for a detailed quantitative argument).

The dewetting speed showed a small but insignificant trend to decrease with size (log-log slope=-0.080 (95% CI (-0.172 | 0.013)), $F_{1,52}$=2.993, p=0.090, n=54). The mean dewetting speed was $69 \pm 39 \mu\mathrm{ms}^{-1}$ (mean $\pm$ std, Fig.2B), comparable to preliminary results reported for ants ($v_{\mathrm{d}} = 60 \pm 5$ $\mu\mathrm{ms}^{-1}$)[22]. As both contact angle and dewetting speed do not vary significantly with size, neither does viscosity (assessed via eq.1 with $\gamma = 37\mathrm{mNm}^{-1}$ (see SI) and θ as measured for paired or as mean for unpaired measurements, respectively; log-log slope=-0.042 (95% CI (-0.215 | 0.131), $F_{1,52}$=0.233 p=0.631). Any change in pad efficiency is thus unlikely to arise from changes of the physical properties of the pad secretion.

Although the dewetting speed is size-invariant, it scatters notably around the mean (56% coefficient of variation). A linear mixed model with random intercept for the individuals for which both contact angle and dewetting measurements exist suggested that this variation arises largely from inter-individual variation (moderate Intraclass Correlation Coefficient (ICC) of 0.56). Indeed, when the variation of the contact angle is taken into account via eq.1, the ICC increases to 0.90, suggesting that a

Fig. 2 Neither contact angle (A) nor dewetting speed (B) of the stick insect pad secretion change significantly with size, indicating that both surface tension and viscosity are size-invariant ($n_\theta = 23$ individuals, $n_d = 54$ individuals).

large part of the variation results from the strong non-linear dependence of dewetting speed on contact angle, and that the dewetting measurements are robust.

The insect pad secretion is a multi-phasic emulsion, consisting of aqueous droplets dispersed in an oily continuous phase[22]. IRM imaging of the pad contact area across size revealed a qualitatively similar appearance and a similar amount and size of aqueous phase droplets (Fig.S1). In combination with the size-invariance of the contact angle and dewetting speed, this finding strongly suggests that the chemical composition of the pad secretion may also vary little with size.

4 Conclusion

Our results demonstrate that stick insects do not systematically alter the physical properties of their pad secretion to avoid a size-related reduction in safety factors. Indeed, a size-specific change in efficiency is only observed in the presence of shear forces[10], and is thus likely explained by the shear-sensitivity of biological adhesive pads[9,31,32]. Potential changes in the physical properties of the pad secretion will only affect adhesive performance if attachment is dominated by capillary or viscous forces. Although this has been a long-standing assumption[15–19], strong direct evidence in support of it is absent, and recent research has put forward alternative functional interpretations[33–35]. Systematic changes in adhesive performance may also arise from a size-specific variation of the pad's viscoelastic properties, which thus need to be investigated in future work.

Competing interests

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Funding

Funding for this study was provided by the Biotechnology and Biological Sciences Research Council to DL (BBSRC grant no. BMPF-P72408).

Contributions

D-M.K.: methodology, investigation, supervision, formal analysis, visualisation and writing - original draft, C.N.A.: investigation, formal analysis and writing—review and editing, A.E.L.A.: methodology, formal analysis and writing—review and editing, D.L.: conceptualisation, funding acquisition, supervision, formal analysis and writing—review and editing.

Acknowledgements

The authors would like to thank Myrta N. Stoukidi and Eleni Papafilippou for their respective contributions to the design of the surface temperature controller and the ImageJ dewetting analysis macro, and Fabian Plum for the 3D scan of the stick insect leg appearing in Fig.1.

References

Favi PM, Yi S, Lenaghan SC, Xia L, Zhang M. Inspiration from the natural world: From bio-adhesives to bio-inspired adhesives. J Adhes Sci Technol. 2014;28(3-4):290-319.

Sameoto D, Menon C. Recent advances in the fabrication and adhesion testing of biomimetic dry adhesives. Smart Mater Struct. 2010;19(10).

Jagota A, Hui CY. Adhesion, friction, and compliance of bio-mimetic and bio-inspired structured interfaces. Mater Sci Eng R Reports. 2011;72(12):253-92.

Arzt E, Quan H, McMeeking RM, Hensel R. Functional surface microstructures inspired by nature – From adhesion and wetting principles to sustainable new devices. Prog Mater Sci. 2021;120(October 2020):100823.

Bartlett MD, Croll AB, King DR, Paret BM, Irschick DJ, Crosby AJ. Looking beyond fibrillar features to scale gecko-like adhesion. Adv Mater. 2012;24(8):1078-83.

Labonte D, Federle W. Scaling and biomechanics of surface attachment in climbing animals. Philos Trans R Soc B Biol Sci. 2015;370:20140027.

Barnes WJP, Oines C, Smith JM. Whole animal measurements of shear and adhesive forces in adult tree frogs: Insights into underlying mechanisms of adhesion obtained from studying the effects of size and

scale. J Comp Physiol A Neuroethol Sensory, Neural, Behav Physiol. 2006;192(11):1179-91.

Smith JM, Barnes WJP, Downie JR, Ruxton GD. Structural correlates of increased adhesive efficiency with adult size in the toe pads of hylid tree frogs. J Comp Physiol A Neuroethol Sensory, Neural, Behav Physiol. 2006;192(11):1193-204.

Labonte D, Federle W. Biomechanics of shear-sensitive adhesion in climbing animals: Peeling, pre-tension and sliding-induced changes in interface strength. J R Soc Interface. 2016;13(122):20160373.

Labonte D, Struecker MY, Birn-Jeffery AV, Federle W. Shear-sensitive adhesion enables size-independent adhesive performance in stick insects. Proc R Soc B Biol Sci. 2019;286:20191327.

Walker G, Yulf AB, Ratcliffe J. The adhesive organ of the blowfly, Calliphora vomitoria: a functional approach (Diptera: Calliphoridae). J Zool. 1985;205:297-307.

Peattie AM, Dirks JH, Henriques S, Federle W. Arachnids secrete a fluid over their adhesive pads. PLoS One. 2011;6(5):2-7.

Wolff JO, Gorb SN. Attachment Structures and Adhesive Secretions in Arachnids. Springer International Publishing; 2016.

Stork NE. Experimental Analysis of Adhesion of Chrysolina Polita (Chrysomelidae: Coleoptera) on a Variety of Surfaces. J Exp Biol. 1980;88(1):91-108.

Vötsch W, Nicholson G, Müller R, Stierhof YD, Gorb S, Schwarz U. Chemical composition of the attachment pad secretion of the locust Locusta migratoria. Insect Biochem Mol Biol. 2002;32:1605-13.

Abou B, Gay C, Laurent B, Cardoso O, Voigt D, Peisker H, et al. Extensive collection of femtolitre pad secretion droplets in the beetle Leptinotarsa decemlineata allows nanolitre microrheology. J R Soc Interface. 2010;7(53):1745-52.

Dirks JH, Federle W. Fluid-based adhesion in insects - Principles and challenges. Soft Matter. 2011;7(23):11047-53.

Peisker H, Heepe L, Kovalev AE, Gorb SN. Comparative study of the fluid viscosity in tarsal hairy attachment systems of flies and beetles. J R Soc Interface. 2014;11:20140752.

Stark AY, Arstingstall K, Yanoviak SP. Adhesive performance of tropical arboreal ants varies with substrate temperature. J Exp Biol. 2018;221(1):jeb171843.

Labonte D, Federle W. Functionally different pads on the same foot allow control of attachment: Stick insects have load-sensitive "heel" pads for friction and shear-sensitive "toe" pads for adhesion. PLoS One. 2013;8(12):e81943.

Wiegand G, Jaworek T, Wegner G, Sackmann E. Studies of structure and local wetting properties on heterogeneous, micropatterned solid surfaces by microinterferometry. J Colloid Interface Sci. 1997;196(2):299-312.

Federle W, Riehle M, Curtis ASG, Full RJ. An Integrative Study of Insect Adhesion: Mechanics and Wet Adhesion of Pretarsal Pads in Ants. Integr Comp Biol. 2002;42(6):1100-6.

Owens DK, Wendt RC. Estimation of the Surface Free Energy of Polymers. J Appl Polym Sci. 1969;13:1741-7.

Tanner LH. The spreading of silicone oil drops on horizontal surfaces. J Phys D Appl Phys. 1979;12:1473.

Redon C, Brochard-Wyart F, Rondelez F. Dynamics of Dewetting. Phys Rev Lett. 1991;66(6):715-8.

Martin P, Brochard-Wyart F. Dewetting At Soft Interfaces. Phys Rev Lett. 1998;80(15):3296-9.

Schindelin J, Arganda-Carreras I, Frise E, Kaynig V, Longair M, Pietzsch T, et al. Fiji: An open-source platform for biological-image analysis. Nat Methods. 2012;9(7):676-82.

Dirks JH, Clemente CJ, Federle W. Insect tricks: Two-phasic foot pad secretion prevents slipping. J R Soc Interface. 2010;7(45):587-93.

Hasenfuss I. The adhesive devices in larvae of Lepidoptera (Insecta, Pterygota). Zoomorphology. 1999;119(3):143-62.

Labonte D. Biomechanics of attachment in insects - the influence of surface energy. University of Applied Sciences, Bremen; 2010.

Autumn K, Dittmore A, Santos D, Spenko M, Cutkosky M. Frictional adhesion: A new angle on gecko attachment. J Exp Biol. 2006;209(18):3569-79.

Federle W, Labonte D. Dynamic biological adhesion: Mechanisms for controlling attachment during locomotion. Philos Trans R Soc B Biol Sci. 2019;374:20190199.

Betz O. Adhesive Exocrine Glands in Insects : Morphology, Ultrastructure, and Adhesive Secretion. In: von Byern J, Grunwald I, editors. Biol. Adhes. Syst. Vienna: Springer; 2010. p. 111-52.

Labonte D, Federle W. Rate-dependence of 'wet' biological adhesives and the function of the pad secretion in insects. Soft Matter. 2015;11(44):8661-73.

Hosoda N, Nakamoto M, Suga T, Gorb SN. Evidence for intermolecular forces involved in ladybird beetle tarsal setae adhesion. Sci Rep. 2021;11(1):1-9.