**Fungi with history: Unveiling the mycobiota of historic documents of Costa Rica**

Efraín Escudero-Leyva[1,2], Sofía Vieto[1], Roberto Avendaño[1], Diego Rojas-Gätjens[1], Paola Agüero[3], Carlos Pacheco[4], Mavis L. Montero[3,5], Priscila Chaverri[2,6]* & Max Chavarría[1,2,3]*

[1]Centro Nacional de Innovaciones Biotecnológicas (CENIBiot), CeNAT-CONARE, 1174-1200 San José, Costa Rica. [2]Centro de Investigaciones en Productos Naturales (CIPRONA), Universidad de Costa Rica, 11501-2060 San José, Costa Rica. [3]Escuela de Química, Universidad de Costa Rica, 11501-2060 San José, Costa Rica. [4]Archivo Nacional de Costa Rica, San José, Costa Rica. [5]Centro de Investigación en Ciencia e Ingeniería de Materiales (CICIMA), Universidad de Costa Rica, 2060 San Pedro, San José, Costa Rica. [6]Escuela de Biología, Universidad de Costa Rica, 11501-2060 San José, Costa Rica.

*Corresponding authors:

Priscila Chaverri (priscila.chaverriechandi@ucr.ac.cr)

Escuela de Biología and Centro de Investigaciones en Productos Naturales, Universidad de Costa Rica, 11501-2060 San José, Costa Rica.

Max Chavarría (max.chavarria@ucr.ac.cr)

Escuela de Química and Centro de Investigaciones en Productos Naturales, Universidad de Costa Rica, 11501-2060 San José, Costa Rica.

**Abstract**

Through nondestructive techniques, we studied the physicochemical characteristics and mycobiota of five key historic documents from Costa Rica, including the Independence Act of Costa Rica from 1821. We determined that for documents dated between 1500 and 1900 (i.e., the Cloudy Days Act, the Independence Act, and two documents from the Guatemalan Series from 1539 and 1549), the paper composition was cotton, whereas the 1991 replicate of the Political Constitution from 1949 was made of wood cellulose with an increased lignin content. We also determined that the ink employed in 1821 documents is ferrogallic, i.e., formed by iron sulfate salts in combination with gallic and tannic acids. In total, 22 fungal isolates were obtained: 15 from the wood-cellulose-based Political Constitution and seven from the other three cotton-based documents. These results suggest that cotton-based paper is the most resistant to microbial colonization. Molecular identifications using three DNA markers (i.e., ITS nrDNA, beta-tubulin, and translation elongation factor 1-alpha) classified the isolates in eight orders and ten genera. The most frequent genera were *Cladosporium*, *Penicillium*, and *Purpureocillium*. Of the isolates, 95% presented cellulolytic activity correlated to their ability to cause deterioration of the paper. This work increases the knowledge of the fungal diversity that inhabits historic documents and its relationship with paper composition and provides valuable information to develop strategies to conserve and restore these invaluable documents.

**Keywords**

Biodeterioration; historic documents of Costa Rica, Independence Act of Costa Rica, *Cladosporium*, *Penicillium*, *Purpureocillium*, cellulolytic activity.

## Introduction

Because biodeterioration can lead to the damage of historic documents, artwork, monuments, or buildings, its study is fundamental for the conservation of cultural heritage (Sterflinger and Pinar 2012; Palla and Barresi 2017; Vieto *et al.* 2021; Ranalli and Zanardini 2021; Ranalli *et al.* 2005). The prevention of biodeterioration and development of adequate conservation and restoration strategies cannot be an unscripted process; it is necessary to undertake diagnoses of these valuable pieces of our history and art, which include chemical characterization and the study of microbial diversity together with the physiological characteristics of biodeteriogens (Palla and Barresi 2017; Negi and Sarethy 2019).

Valuable cultural and historic objects, such as relevant paintings, ancient sculptures, and historic documents, can be seen as substrates on which microorganisms can thrive and cause damage. Specifically, paper-based documents contain biodegradable organic constituents that fungi can use as a substrate (Jia *et al.* 2020; Pyzik *et al.* 2021). The term "paper" is a general concept that encompasses all thinly laminated material that is produced with vegetable fiber pulp or other materials ground and mixed with water, dried, and hardened. Historically, vegetable fibers have been extracted from natural sources, such as straw, silk, hemp, flax, cotton, and the bark of different trees, among others. The content of cellulose and other components of paper can vary depending on its origin, generating papers that are more or less resistant to biodegradation as a consequence. For example, it is well known that cellulose fibers have high purity in cotton and linen papers, which results in papers with greater durability and resistance to biodeterioration (Negulescu *et al.* 1998; Daria *et al.* 2020).

Damage produced by fungi that is normally present on paper —including staining,

material weakening, and partial or complete destruction of documents— can occur in the long term

(Sequeira *et al.* 2019). Besides the alterations caused to the documents, the health of curators and

people involved in archives or museums can also be threatened if the spore production is elevated

or mycotoxins are produced (Sterflinger and Pinzari 2012). The study of fungi responsible for the

biodegradation of paper began in 1818 with the pioneering work of Christian Gottfried Ehrenberg

(Sterflinger and Pinzari 2012). To date, diverse fungi have been identified in old paperwork, such

as *Aspergillus*, *Chaetomium*, *Cladosporium*, *Penicillium,* and *Trichoderma*; occasionally, new

species can even be found (Coronado-Ruiz *et al.* 2018; Sequeira *et al.* 2019). Mesquita *et al.* (2009)

isolated, identified, and characterized the microbiota from historic documents dated between

1860–1939 in the archive of the University of Coimbra and found fourteen fungal genera, of which

*Aspergillus*, *Cladosporium,* and *Penicillium* were the most common. Our research group recently

isolated nineteen fungi from a nineteenth-century French collection of drawings and lithographs

in the custody of Universidad de Costa Rica (Coronado-Ruíz *et al.* 2018). The fungi were

molecularly identified as *Arthrinium, Aspergillus*, *Chaetomium*, *Cladosporium*, *Colletotrichum*,

*Penicillium*, and *Trichoderma*; a great majority of them showed cellulolytic activity. Many fungal

species found in historic paper-based documents contain enzymatic activity related to

biodeterioration, which allows fungi to use these surfaces as a source of carbon (Coronado-Ruíz

*et al.* 2018; Pinheiro *et al.* 2019; Vieto *et al.* 2022). The enzymatic machinery to take advantage

of paper as a source of carbon has been reported in fungi isolated from historic documents and

includes the presence of exoenzymes with cellulase activity (Puškárová *et al.* 2019; El Begardi *et*

*al.* 2014), lignocellulolytic (Mazzoli *et al.* 2018) glucanase, and laccase (Sterflinger and Pinzari

2012).

The National Archive of Costa Rica (NACR) —called Archivos Nacionales (National

Archives) before 1948— is where the most treasured documents in Costa Rica are preserved; these

include the Cloudy Days Act (Acta de los Nublados, September 28, 1821), in which authorities of

the Municipality of León, in the Captaincy General of Guatemala, expressed their position on

Central American Independence; the Political Constitution with all historic changes, including the

abolition of the Costa Rican army (Jaén García 2019; Chacón León 2021); and perhaps the most

important historic document in the country: the Costa Rican Independence Act (Acta de

Independencia, October 29, 1821). These invaluable documents are in addition to more than

20,000 linear meters of other paper-based documents that contain the history of Costa Rica and

that are in the custody of NACR. Due to the tropical peculiarities of the country —such as high

humidity, heat, long rainy seasons, and sometimes inadequate storage conditions— documents and

artworks are constantly threatened and come under continuous biodeterioration, making the

conservation of the country's cultural heritage a challenge (Silva, 2011).

The aim of this work was to characterize the paper composition and evaluate the presence

and cellulolytic activity of culturable fungi in historic documents from the National Archive of

Costa Rica, including invaluable documents such as the Independence Act of Costa Rica. This

information enables restorers to establish guidelines for the preservation and restoration of paper-

based historic documents.

**Materials and Methods**

*Sampling of documents*

Permits to sample the historic documents were obtained from the Institutional Commission

of Biodiversity of the University of Costa Rica (resolution Nº 186) and authorities of the NACR.

Historic documents stored at NACR were sampled between March and September 2019. The

documents were: (i) Political Constitution redacted in 1949 (1991 replicate), (ii) Cloudy Days Act

from 1821 (Acta de los Nublados), (iii) Independence Act of Costa Rica from 1821, and (iv) two

documents from the Guatemalan Series from 1539 and 1549 (Fig. 1). For fungal isolation, careful

rubbing with sterile cotton swabs over the surface of the documents was performed, especially

seeking signs of biodeterioration such as dark spots. The swabs were then saved inside Falcon

tubes for transport to the laboratory.

*Material characterization by attenuated-total-reflection Fourier-transform infrared spectra (ATR-*

*FTIR).*

ATR-FTIR was used to determine functional groups and distinguish cellulosic materials.

These ATR-FTIR spectra were recorded using a portable spectrophotometer (Bruker Alpha II,

Canada) with platinum ATR mode and monolithic diamond crystal. The spectral resolution was 4

$cm^{-1}$, in wavenumber range 400–4,000 $cm^{-1}$ with 99 scans. To carry out the identification, the

"Database of ATR-FT-IR spectra of various materials" (Vahur *et al.* 2016) was used.

*Material characterization by X-ray fluorescence (XRF).*

X-ray fluorescence (XRF) was used to determine the elemental composition of the

material, especially the presence of metallic ions, such as iron and calcium, among others. This

technique is especially important in the characterization of inks. The XRF spectra were recorded

with a portable XRF spectrophotometer (Elio, XGLab; Bruker, Italy) measured at the Kα line of

manganese (resolution 140 eV), a SDD detector (active area 25 mm$^2$, fluorescence angle 63°,

incident angle 90°) and a distance of 14 mm from the detector to the sample. The electric current

was adjusted to 80 µA, with a voltage of 50 kV and a measuring duration of 300 s. Software XRS-

FP2 (CrossRoads Scientific, USA) was used for data analysis, maintaining a noise signal of 0.5.

*Fungal cultivation strategy*

Samples were processed in the laboratory 2-4 hours after sampling. Cotton swabs were

immersed into sterile phosphate-buffered saline solution (PBS; 400 µL, 1X; Thermo Fisher

Scientific, USA) and homogenized using a vortex (40 s). Each sample (100 µL) was then cultured

in plates of potato dextrose agar (1% Difco PDA; BD company, France) and carboxymethyl

cellulose (1% CMC; Sigma Aldrich, USA, with 0.8 % agar; BD company, France) with kanamycin

(50 µg/mL; Sigma-Aldrich, USA) and incubated (25 °C) until growth was observed. Colonies

exhibiting varied morphologies were purified and transferred onto PDA plates; photographs were

taken after incubation (15 days, 30 °C).

*Molecular identification of the isolated fungi*

Genomic DNA was extracted from the isolated fungi using the method described by Lodhi

*et al.* (1994) with modifications. First, two agar disks (diameter 8 mm) from each fungus were

added to a centrifuge tube (2 mL) and were ground with sterile micro-pestles. Extraction buffer

(750 µL, sodium EDTA 20 mM, tris-HCl 100 mM, NaCl 1.4 M, CTAB 2 % [w/v], PVP 2% [w/v]

and ß-mercaptoethanol 0.2%) was added; the tubes were vortexed and incubated (20 min, 65 °C).

For DNA separation, trichloromethane-octanol (750 µL, 24:1) was added to the mixture and

centrifuged (25 °C, 14,000 rpm). DNA from the top aqueous phase (600 µL) was precipitated on

an addition of 2-propanol (600 µL; Sigma-Aldrich, USA). Then, ethanol (70 %, 500 µL; Sigma-

Aldrich, USA) was used to wash the precipitated DNA. Finally, DNA was resuspended in Tris-

EDTA buffer (50 µL) with RNAse (1 µL, 10 mg/mL; Thermo Fisher Scientific, USA).

To obtain a preliminary identification of the isolates, the nrDNA internal transcribed

spacers (ITS) were amplified with primers ITS4 (TCCTCCGCTTATTGATATGC) and ITS5

(GGAAGTAAAAGTCGTAACAAGG) (White *et al.*1990). Depending on the results from ITS,

secondary markers were used to refine the identifications for some isolates, i.e., portions of the

translation elongation factor 1-alpha (TEF1; primers CATCGAGAAGTTCGAGAAGG and

TACTTGAAGGAACCCTTACC) (Carbone and Kohn 1999) and beta-tubulin (TUB2; primers

AACATGCGTGAGATTGTAAGT  and  TAGTGACCCTTGGCCCAGTTG) (O'Donnell and

Cigelnik  1997) genes. Each reaction (total volume 20 µL) consisted of Master Mix (10 µL, 2X;

Thermo Fisher Scientific, USA), bovine serum albumin (BSA, 0.5 µL, 20 mg/mL; Sigma Aldrich,

USA), dimethyl sulfoxide (DMSO, 1.5 µL; Sigma Aldrich, USA), and primers (0.5 µL each, 10

µM) and DNA (2 µL, 50 ng/µL). PCR reactions were implemented in a thermal cycler (9902

Veriti, Applied Biosystem, Norwalk, USA), according to conditions described by Schoch *et al.*

(2012) for ITS, Carbone and Kohn (1999) for TEF1 and O'Donnell and Cigelnik (1997) for TUB2.

Sanger sequencing of PCR products was performed with Psomagen (USA); the raw sequences

were edited and assembled in Bioedit v.7.2. Isolate identification was performed by comparing the

consensus sequences against the GenBank database using the BLAST search tool. Then, a

cladogram was constructed using the ITS sequences. For this, the two closest matches, with type

material prioritized, were retrieved/downloaded from the BLAST analysis and aligned using

MUSCLE (Edgar 2004). The resulting alignment in Phylip format was submitted to Bayesian

Inference analysis with Exabayes (Aberer *et al.* 2014). MCMC was run in parallel and 15 million

generations were done with 25% burn-in. All analyses were run in the Kabré supercomputer

(CNCA-CONARE, Costa Rica). A consensus tree was visualized and edited with FigTree v.1.4.3

(Rambaut 2010). Newly generated sequences were deposited in GenBank under accession

numbers ON479855-ON479876 (ITS), ON720280-ON720285 (TEF1), and ON734081–

ON734096 (TUB2).

*Screening of cellulolytic activity*

The screening of cellulase-producing fungi was undertaken on carboxymethyl

cellulose plates (CMC, 1 %; Sigma Aldrich, USA) as the sole carbon source, supplemented with

agar (0.8 %, Sigma Aldrich, USA; Johnsen and Krause 2014; Gohel *et al.* 2014). For this purpose,

agar disks (diameter ~0.8 mm) of each fungus were placed in the center of CMC plates and

incubated (7 days, 30 °C). After incubation, each plate was flooded with Gram's iodine stain (10

mL; Sigma-Aldrich, USA; Kasana *et al.* 2008; Gohel *et al.* 2014) and washed with water for 10

min. Because Gram's iodine dye is held only by integral cellulose polymers, cellulase activity is

revealed by the clear zones appearing as pale halos (Florencio *et al.* 2012). Photographs were taken

before and after staining the plates; software ImageJ v.1.52k (Bourne 2010) was used to measure

fungal growth (as the diameter of the colony) and the halo diameter for a subsequent calculation

of the enzymatic index (EI), a semiquantitative estimate of enzyme activity according to the

following formula (Florencio *et al.* 2012):

209
$$EI = \frac{\text{Diameter of hydrolysis zone}}{\text{Diameter of colony}}$$

The experiments were performed in triplicate; *Pleurotus ostreatus* served as a positive control

(Garzlllo *et al.* 1994; Valášková and Baldrian 2006).

**Results**

*Material characterization by infrared spectra (ATR-FTIR) and X-ray fluorescence (XRF)*

Macroscopically all documents analyzed showed detailed damage as observed in Fig. 1, in

which signs of humidity and possible leakage are visible in several areas. Particularly, in the

Independence Act surface, orangish spots were present. When observed under UV light, those

areas are fluorescent and appear as dark spots in UV reflectance photographs (Supplementary Fig.

S1).

The chemical composition of historic documents (both inks and paper) was studied through

nondestructive and portable techniques (See Materials and Methods). The composition of each

document is shown in Table 1. The composition of the organic substrate was determined by

comparing the IR spectra with databases; the elements present in the ink and additives were

resolved with X-ray fluorescence. The results showed that the paper in the documents from 1500–

1900 was handmade mainly from cotton with watermark presence (excepting the second page from

the Cloudy Days Act, which was cellulose-based). In the Political Constitution (1991 replicate),

modern paper was used, characterized by shorter fibers and greater lignin content; this indicates

that this paper was made from wood cellulose. The results showed that the ink employed in the

documents from 1821 was ferrogallic, formed by iron sulfate salts in combination with gallic and

tannic acids (Table 1 and Supplementary Fig. S1).

*Isolation and identification of fungi*

In total, 22 fungal isolates (Supplementary Fig. S2) were recovered from the Costa Rican

historic documents, being the Political Constitution (1991 replicate) that with the most isolates (15

in total). The taxonomic identification provided by BLAST and ITS phylogenetic analyses are

shown in Table 2 and Fig. 2, respectively. The fungi recovered belong to 14 genera and eight

orders. Two taxa were obtained from the Independence Act, two from the Cloudy Days Act, two

from the document from 1549, and only one fungal isolate from the oldest document (Guatemalan

Series 1539). The phylogenetic placement of the isolates corresponded to eight orders, as shown

in the ITS cladogram (Fig. 2). The phylogenetic analysis supports the identifications performed

with the BLAST tool, at least at the genus level. TEF1 and TUB2 sequences refined the

identification for some of the isolates (Table 2).

Most of the fungi found belong in the Ascomycota (86%), followed by Basidiomycota

(14%). Among the resulting orders, the majority belong in Hypocreales (23%; *Acremonium,*

*Beauveria*, and *Purpureocillium*), Eurotiales (18%; *Aspergillus* and *Penicillium*), and Capnodiales

(18%; *Cladosporium*). The Basidiomycota was represented by *Coprinellus, Trametes* and an

unidentified species of Psathyrellaceae.

*Cellulolytic activity*

The results from cellulolytic activity are shown in Table 3. For the 22 isolates tested, the

Enzymatic Index (EI) average was 2.45, with *Cyphellophora* aff. *pluriseptata* CP2-A4P isolated

from the Political Constitution being the fungus with the greatest cellulolytic activity (4.0 ± 0.3),

followed by *Penicillium steckii* ND1-A1P (3.3 ± 0.3), and *Cladosporium* sp. CP1-A2P (3.3 ± 0.1).

In contrast, *Purpureocillium lilacinum* 1539-A1P —from the 1539 Guatemalan Series— was the

only isolate without cellulolytic activity. The other fungal isolates showed cellulolytic activity

above the levels of the control (*Pleurotus ostreatus*), except for *Trametes* CP1-A3C.

**Discussion**

In this work we determined the chemical and microbiological composition of five

important historic documents of Costa Rica, including the Independence Act of 1821. Through

spectral techniques, we determined that for the documents dated between 1500 and 1900 (i.e., the

Cloudy Days Act, the Independence Act of Costa Rica of 1821, and two documents from the

Guatemalan Series of 1539 and 1549), the composition of the paper was cotton (i.e., approximately

90% cellulose (Felgueiras *et al.* 2021), except the second page of the Cloudy Days Act, which is

composed of cellulose acetate. The 1991 replicate of the Political Constitution of 1949 was made

of cellulose and lignin; this paper presented the greatest amount of lignin, which indicates a modern

paper made from wood (hereafter referred to as wood cellulose-based paper).

Despite that modern paper is relatively stable, deterioration is common with increased

levels of humidity and acidification produced by oxidation and the presence of microorganisms

(Proniewicz *et al.* 2001). Although the 1991 replicate of the Political Constitution from 1949 is

the most recent, 15 fungal isolates were obtained, whereas from all the oldest documents (made

mainly of cotton), seven in total were obtained. These data suggest that wood-cellulose-based

paper possesses characteristics that are more suitable for fungal colonization than cotton-based

documents. These observations make sense if we consider the differences between the chemical

composition of cotton and paper obtained from other plant fibers such as wood. Cotton contains

approximately 90% cellulose (hence it is sometimes referred to as highly pure cellulose), whereas

other natural fibers, such as wood, contain 40–55% cellulose combined with other constituents

such as lignin and hemicelluloses (Felgueiras *et al.* 2021). Cellulose is considered a two-phase

material, having both crystalline and amorphous phases (Ling *et al.* 2019). Cotton cellulose fibers

are reported to have a greater degree of polymerization and crystallinity, which generates stronger

fibers and greater resistance to hydrolysis and biodegradation. (Itävaara *et al.* 1999). Therefore,

these two characteristics (higher cellulose content and higher crystallinity) make cotton a substrate

that is less prone to microbial colonization than a material such as wood-based paper, which is the

case of the paper of the 1991 replicate of the Political Constitution of 1949. Enzymatically, the

reduced ability for microbial colonization of cotton-based papers is related to the more limited

access of the cellulase enzyme complex to the substrate due to the orderly and compact architecture

of the crystalline cellulose present in cotton (Arantes and Saddler 2010).

In Fig. 1C, the orangish spots over the Independence Act surface indicate oxidation from

cellulose and iron, probably caused by both abiotic and biotic factors (Choi 2007). Those areas are

fluorescent under UV light and appear as dark spots in UV reflectance photographs

(Supplementary Fig. S1). Although excessive humidity can itself trigger oxidation, contributing to

the damage of important documents, the inks used can also be affected by this abiotic factor,

producing the migration of metal ions of common ink components such as iron and copper,

compromising the preservation of historic and cultural heritage due to weakened paper (Henniges

*et al.* 2006). Our work determined that the ink employed in the documents from 1821 was

ferrogallic, formed by iron sulfate salts in combination with gallic and tannic acids. The last was

confirmed from the XRF and multispectral photography (see Supplementary Fig. S1). Ink of this

kind is visible under infrared and, in darkness, under UV light (Havermans *et al.* 2003). The

implementation of optical spectroscopy techniques, such as those used in this work, have been

shown to help identify the early stages of document damage by microorganisms such as fungi,

relating changes in the spectral composition to the active presence of fungi (Povolotckaia *et al.*

2019).

In the historic documents, we obtained a total of 22 fungi belonging to 14 genera, of which

five (35%) were previously identified in paper-based historic documents (Bensch *et al.* 2018;

Pinheiro *et al.* 2019; Romero *et al.* 2021; Trovão and Portugal 2021). The presence of two

Chaetothyriales members (isolates 1549-4A1C and CP2-A4P) is interesting because they are

inhabitants of environments with limited resources, such as rocks, insects, and ant nests; some

species in the order can even become pathogenic for humans, especially in tropical regions ( Attili-

Angelis *et al.* 2014; Ahmed *et al.* 2021). *Cyphellophora,* also Chaetothyriales, is closely related to

*Phialophora* (Feng *et al.* 2014), which includes species that grow in extremely acidic conditions

and have been reported to produce ß-mannanase and ß -glucanase enzymes (Zhao *et al.* 2010; Zhao

*et al.* 2012). Our isolate CP2-A4P had the greatest enzymatic index value (4.0 ± 0.3), for which

further analysis involving enzyme identification could yield intriguing results. Isolate *Penicillium*

*steckii* ND1-A1P originated from a cotton-based substrate and presented an enzymatic index of

3.3 ± 0.3. This corresponds to what is commonly observed because *Aspergillus* and *Penicillium*

species are registered continuously in paper biodeterioration and are known to break the hydrogen

bonds, which translates into a weakening of the documents, regardless of their composition

(Povolotckaia *et al.* 2019). In total, three isolates corresponding to *Penicillium* were obtained from

the Cloudy Days Act, the Political Constitution, and the 1549 Guatemalan Series. We registered

only a single isolate corresponding to *Aspergillus hiratsukae* (AI3-A1P), which was recovered

from the Independence Act of 1821. This was unexpected because *Aspergillus* spp. are frequent

biodeteriogens in cultural heritage objects and spaces in which historic documents are preserved,

such as the National Archive of Cuba, in which *Aspergillus*, *Cladosporium,* and *Penicillium* were

the most frequent airborne genera reported (Borrego and Perdomo 2016). In this work,

*Cladosporium* isolates were present in the Cloudy Days Act (isolate ND2-A1P), the Independence

Act (isolate AI1-A1C), and the Political Constitution (isolates CP1-A1P and CP1-A2P),

corresponding to cellulose acetate, cotton, and wood cellulose substrates. *Cladosporium* spp. are

reported as colonizers in agricultural waste (Herculano *et al.* 2011), artworks (Coronado-Ruiz *et*

*al.* 2018), repositories of historic documents (Borrego and Perdomo 2016), and as extremophiles

in high-altitude tropical glaciers (Calvillo-Medina *et al.* 2020).

*Neopestalotiopsis clavispora* (CP1-A2C) and *Pestalotiopsis kenyana* (CP2-A2C)

(Xylariales), both obtained from the Political Constitution, belong to a genus known as a common

endophyte, saprotroph, and phytopathogen in diverse plants and climates (Reddy *et al.* 2016).

Because of the various ecological relationships this genus has with plants, it has attracted attention

for its cellulolytic abilities, with over 400 possible enzymes found through the study of a

*Pestalotiopsis* isolated from a mangrove (Arfi *et al.* 2013). So far, there are some cellulolytic

enzymes known from this genus that have been studied, such as the xylanase (Koh *et al.* 2021) or

the cellulases (Goukanapalle *et al.* 2020). Another single isolate obtained from the Political

Constitution was *Periconia* CP1-A1C, which belongs to the dark septate fungi Pleosporales, with

some isolates reported with thermostable β-Glucosidases suitable for biotechnological processes

(Harnpicharnchai *et al.* 2009). *Periconia* species have been encountered in extreme environments,

such as deserts, seas, tropical glaciers (Calvillo-Medina *et al.* 2020), and even a new species

growing over lithographs from the 19th century (Coronado-Ruiz *et al.* 2018), among others.

Hypocreales isolates were only found in the Political Constitution. Intriguing were two

isolates known as insect pathogens, i.e., *Beauveria* (CP2-A3P) and *Purpureocillium* (1539-A1P

and CP2-A1P; Shrestha *et al.* 2019). The cellulolytic activity recorded for our *Beauveria* isolate

was $3.1 \pm 0.3$, which is consistent with reports of cellulolytic activity driven by a thermally stable

β-Glucosidase in *Beauveria bassiana* (Borgi and Gargouri 2016). Screening for cellulolytic

activity in this entomopathogenic species is not commonly done because it is mainly studied for

its biological control abilities in multiple agricultural crops (Posada and Vega 2006; Sanjuan *et al.*

2014; Mwamburi 2021). *Beauveria* has also been found as an endophyte, along with

*Purpureocillium* (Kepler *et al.* 2013). An isolate of *Purpureocillium lilacinum* has been reported

as a biodeteriogen of indoor materials able to grow in alkaline materials, producing damage in

limestones and plasters of cultural heritage in Russia (Ponizovskaya *et al.* 2019). The tolerance to

extreme conditions by some *Purpureocillium* spp. results in the ability to become pathogenic to

humans and resistant to fungicides (Calvillo-Medina *et al.* 2020). Although one isolate recovered

from the 1539 Guatemalan Series (cotton-based) was unable to grow in the carboxymethyl

cellulose media, isolate CP2-A1P from the Political Constitution (wood cellulose-based) attained

EI of 3.2. *Acremonium* isolates CP2-A3C and ND2-A1P registered enzymatic indexes < 3.

Previous researchers reported a xylanase produced by *Acremonium cellulolyticus* (Watanabe *et al.*

2014); another group subsequently revised the taxonomy and concluded a misidentification of an

*Acremonium* species, reidentifying isolate Y-94 from Japan as *Talaromyces* (Eurotiales) (Fujii *et*

*al.* 2014). Apart from the latter, only a xylanase has been reported for *A. alcalophilum* (Šuchová

*et al.* 2020).

Small enzymatic indexes also occurred for three basidiomycetes recovered from the

Political Constitution (CP1-A3C, CP1-A3P, and CP2-A2P). These were identified as belonging to

Psathyrellaceae, including *Coprinellus* (CP2-A2P). From these, only one report exists of a

xylanase produced by *Coprinellus disseminatus,* which was tolerant to varied pH and temperatures

(Agnihotri *et al.* 2010). Isolate *Trametes* CP1-A3C registered an EI less than the control (*Pleurotus*

*ostreatus*). Species with tough fruiting bodies, such as *Trametes maxima,* are reported to possess

laccase activity, even when exposed to herbicides (Cupul *et al.* 2014); an isolate of *T. versicolor*

is reported to cause the effective degradation of fungicides (Rodríguez-Rodríguez *et al.* 2012).

**Conclusions**

Regardless of the material of a document of origin —cotton or wood cellulose— most

recovered fungal isolates presented cellulolytic activity. From the historic documents sampled, the

Political Constitution had the greatest number of isolates, which suggests that wood cellulose-

based paper possesses characteristics more suitable for fungal colonization than the oldest cotton-

based documents (i.e., documents from 1500–1900). Cotton contains 90% cellulose and has great

crystallinity, which makes it more difficult for the enzymatic machinery of microorganisms to

degrade these polymers and use them for their nutritional requirements. Even though the oldest

documents (e.g., Independence Act and the Cloudy Days Act) yielded few isolates, restoration and

improvement of the conditions they are stored in should be implemented to avoid oxidation and

weakening of their fibers which could then increase microbiological contamination. The results of

our work provide valuable information for establishing the appropriate protocols to undertake that

restoration and conservation. Determining the chemical composition of the paper and the

composition of the inks, as well as the microbiological load, allows for identification of the most

appropriate strategies and treatments to restore documents as important to Costa Rica as the Act

of Independence itself. Because historic documents can be considered microhabitats with limited

resources, the screening of species with novel biotechnological applications in such environments

is a promising and fascinating field. The study of how best to conserve historic documents is vital

to preserve, in a satisfactory condition, important sources and records of human history.

Multidisciplinary approaches such as the present work can help curators make the best choice of

restoration techniques and eventually fulfill the Korean phrase: "Silk can stand five hundred years,

but paper can stand one thousand" (Jeong et al., 2014).

**References**

Aberer, A.J., Kobert, K. and Stamatakis, A. (2014) ExaBayes: massively parallel Bayesian tree
inference for the whole-genome era. *Mol Biol Evol* **31**, 2553–2556.

Agnihotri, S., Dutt, D., Tyagi, C.H., Kumar, A. and Upadhyaya, J.S. (2010) Production and
biochemical characterization of a novel cellulase-poor alkali-thermo-tolerant xylanase from
*Coprinellus disseminatus* SW-1 NTCC 1165. *World J Microbiol Biotechnol* **26**, 1349–1359.

Ahmed, S.A., Bonifaz, A., González, G.M., Moreno, L.F., Menezes da Silva, N., Vicente, V.A.,
Li, R. and de Hoog, S. (2021) Chromoblastomycosis caused by *Phialophora*-proven cases from
Mexico. *J Fungi* **7**, e95.

Arantes, V. and Saddler, J.N. (2010) Access to cellulose limits the efficiency of enzymatic
hydrolysis: the role of amorphogenesis. *Biotechnol Biofuels* **3**, e4.

Arfi, Y., Chevret, D., Henrissat, B., Berrin, J.G., Levasseur, A. and Record, E. (2013)
Characterization of salt-adapted secreted lignocellulolytic enzymes from the mangrove fungus
*Pestalotiopsis* sp. *Nat Commun* **4**, 1810–1819.

Attili-Angelis, D., Duarte, A.P.M., Pagnocca, F.C., Nagamoto, N.S., De Vries, M., Stielow, J.B.
and De Hoog, G.S. (2014) Novel *Phialophora* species from leaf-cutting ants (tribe Attini). *Fungal*
*Divers* **65**, 65–75.

Bensch, K., Groenewald, J. Z., Meijer, M., Dijksterhuis, J., Jurjević, Ž., Andersen, B., Houbraken,
J., Crous, P.W. and Samson, R.A. (2018) *Cladosporium* species in indoor environments. *Stud*
*Mycol* **89**, 177–301.

Borgi, I. and Gargouri, A. (2016) A novel high molecular weight thermo-acidoactive β-glucosidase
from *Beauveria bassiana*. Appl Biochem Microbiol **52**, 602–607.

Borrego, S. and Perdomo, I. (2016) Airborne microorganisms cultivable on naturally ventilated
document repositories of the National Archive of Cuba. *Environ Sci Pollut Res*, **23**, 3747–3757.

Bourne, R. (2010). ImageJ. In: Fundamentals of digital imaging in medicine. Springer, London.

Calvillo-Medina, R.P., Gunde-Cimerman, N., Escudero-Leyva, E., Barba-Escoto, L., Fernández-
Tellez, E.I., Medina-Tellez, A.A., Bautista-de Lucio, V., Ramos-López, M.Á., and Campos-
Guillén, J. (2020) Richness and metallo-tolerance of cultivable fungi recovered from three high
altitude glaciers from Citlaltépetl and Iztaccíhuatl volcanoes (Mexico). *Extremophiles* **24**, 625–
636.

Carbone, I. and Kohn, L.M. (1999) A method for designing primer sets for speciation studies in

filamentous ascomycetes. *Mycologia* **91**, 553-556.

Chacón León, L.A. (2021) El bicentenario de la independencia de Costa Rica. *Revista del Archivo*

*Nacional de Costa Rica* **85**, 1–13.

Choi, S. (2007) Foxing on paper: a literature review. *J Am Inst Conserv* **46**, 137-152.

Coronado-Ruiz, C., Avendaño, R., Escudero-Leyva, E., Conejo-Barboza, G., Chaverri, P. and

Chavarría, M. (2018) Two new cellulolytic fungal species isolated from a 19th-century art

collection. *Sci Rep* **10**, e7492.

Cupul, W.C., Abarca, G.H., Vázquez, R.R., Salmones, D., Hernández, R.G. and Gutiérrez, E.A.

(2014) Response of ligninolytic macrofungi to the herbicide atrazine: dose-response bioassays.

*Revista Argentina de Microbiologia* **46**, 348–357.

Daria, M., Krzysztof, L. and Jakub, M. (2020) Characteristics of biodegradable textiles used in

environmental engineering: A comprehensive review. *J Clean Prod* **268**, e122129.

Edgar, R.C. (2004) MUSCLE: a multiple sequence alignment method with reduced time and space

complexity. *BMC Bioinform* **5**, 1-19.

El Bergadi, F., Laachari, F., Elabed, S., Mohammed, I.H. and Ibnsouda, S.K. (2014) Cellulolytic

potential and filter paper activity of fungi isolated from ancients manuscripts from the Medina of

Fez. *Ann Microbiol* **64**, 815–822.

Felgueiras, C., Azoia, N.G., Gonçalves, C., Gama, M. and Dourado, F. (2021) Trends on the

cellulose-based textiles: raw materials and technologies. *Front Bioeng Biotechnol* **9**, 608826.

Feng, P., Lu, Q., Najafzadeh, M.J., van den Ende, A.H.G.G., Sun, J., Li, R., Xi, L., Vicente, V.A.,
Lai, W., Lu, C. and de Hoog, G.S. (2014) *Cyphellophora* and its relatives in *Phialophora*:
biodiversity and possible role in human infection. *Fungal Divers* **65**, 17–45.

Florencio, C., Couri, S. and Farinas, C.S. (2012) Correlation between agar plate screening and
solid-state fermentation for the prediction of cellulase production by *Trichoderma* strains. *Enzyme*
*Res* **2012**, e793708.

Fujii, T., Hoshino, T., Inoue, H. and Yano, S. (2014) Taxonomic revision of the cellulose-
degrading fungus *Acremonium cellulolyticus* nomen nudum to *Talaromyces* based on phylogenetic
analysis. *FEMS Microbiol Lett* **351**, 32–41.

Garzlllo, A.M.V., Di Paolo, S., Ruzzi, M. and Buonocore, V. (1994) Hydrolytic properties of
extracellular cellulases from *Pleurotus ostreatus*. *Appl Microbiol Biotechnol* **42**, 476–481.

Gohel, H.R., Contractor, C.N., Ghosh, S. K. and Braganza, V.J. (2014) A comparative study of
various staining techniques for determination of extra cellular cellulase activity on Carboxy
Methyl Cellulose (CMC) agar plates. *Int J Curr Microbiol Appl Sci* **3**, 261–266.

Goukanapalle, P.K.R., Kanderi, D.K., Rajoji, G., Shanthi Kumari, B.S. and Bontha, R.R. (2020)
Optimization of cellulase production by a novel endophytic fungus *Pestalotiopsis microspora*
TKBRR isolated from Thalakona forest. *Cellulose* **27**, 6299–6316.

Harnpicharnchai, P., Champreda, V., Sornlake, W. and Eurwilaichitr, L. (2009) A thermotolerant
β-glucosidase isolated from an endophytic fungi, *Periconia* sp., with a possible use for biomass
conversion to sugars. *Protein Expr Purif* **67**, 61–69.

Havermans, J., Aziz, H.A. and Scholten, H. (2003) Non destructive detection of iron gall inks by
means of multispectral imaging part 1: Development of the detection system. *Restaurator* **24**, 55-
60.

Henniges, U., Prohaska, T., Banik, G. and Potthast, A. (2006) A fluorescence labeling approach
to assess the deterioration state of aged papers. *Cellulose* **13**, 421–428.

Herculano, P.N., Lima, D.M.M., Fernandes, M.J.S., Neves, R.P., Souza-Motta, C.M. and Porto,
A.L.F. (2011) Isolation of cellulolytic fungi from waste of castor (*Ricinus communis* L.). *Curr*
*Microbiol* **62**, 1416–1422.

Itävaara, M., Siika-aho, M. and Viikari, L. (1999) Enzymatic degradation of cellulose-based
materials. *J Polym Environ* **7**, 67–73.

Jaén García, L.F. (2019) José Luis Coto Conde y la transformación del Archivo Nacional de Costa
Rica. *Revista del Archivo Nacional de Costa Rica* **83**, 54–72.

Jeong, M.J., Kang, K.Y., Bacher, M., Kim, H.J., Jo, B.M. and Potthast, A. (2014) Deterioration of
ancient cellulose paper, Hanji: evaluation of paper permanence. *Cellulose*, **21**, 4621–4632.

Jia, Y., Yin, L., Zhang, F., Wang, M., Sun, M., Hu, C., Liu, Z., Chen, Y., Lui, J. and Pan, J. (2020)
Fungal community analysis and biodeterioration of waterlogged wooden lacquerware from the
Nanhai no. 1 shipwreck. *Appl Sci* **10**, e3797.

Johnsen, H.R. and Krause, K. (2014) Cellulase activity screening using pure
carboxymethylcellulose: Application to soluble cellulolytic samples and to plant tissue prints. *Int*
*J Mol Sci* **15**, 830–838.

Kasana, R.C., Salwan, R., Dhar, H., Dutt, S. and Gulati, A. (2008) A rapid and easy method for
the detection of microbial cellulases on agar plates using Gram's iodine. *Curr Microbiol* **57**, 503–
507.

Kepler, R., Ban, S., Nakagiri, A., Bischoff, J., Hywel-Jones, N., Owensby, C.A. and Spatafora,
J.W. (2013) The phylogenetic placement of hypocrealean insect pathogens in the genus
*Polycephalomyces*: An application of One Fungus One Name. *Fungal Biol* **117**, 611–622.

Koh, S., Mizuno, M., Izuoka, Y., Fujino, N., Hamada-Sato, N. and Amano, Y. (2021) Xylanase

from marine filamentous fungus *Pestalotiopsis* sp. AN-7 was activated with diluted salt solution

like brackish water. *J Appl Glycosci*, **68**, 11–18.

Ling, Z., Wang, T., Makarem, M., Cheng, H.N., Kang, X., Bacher, M., Potthast, A., Rosenau, T.,

King, H., Delhom. C.D., Nam, S., Edwards, J.V., Kim, S.H., Xu, F. and French, A.D. (2019)

Effects of ball milling on the structure of cotton cellulose. *Cellulose* **26**, 305–328

Lodhi, M.A., Ye, G.N., Weeden, N.F. and Reisch, B.I. (1994) A simple and efficient method for

DNA extraction from grapevine cultivars and *Vitis* species. *Plant Mol Biol* Rep **12**, 6-13.

Mazzoli, R., Giuffrida, M.G. and Pessione, E. (2018) Back to the past: "find the guilty bug—

microorganisms involved in the biodeterioration of archeological and historical artifacts". *Appl*

*Microbiol Biotechnol* **102**, 6393–6407.

Mesquita, N., Portugal, A., Videira, S., Rodríguez-Echeverría, S., Bandeira, A.M.L., Santos,

M.J.A. and Freitas, H. (2009) Fungal diversity in ancient documents. A case study on the Archive

of the University of Coimbra. *Int Biodeterior Biodegradation* **63**, 626-629.

Mwamburi, L.A. (2021) Endophytic fungi, *Beauveria bassiana* and *Metarhizium anisopliae*,

confer control of the fall armyworm, *Spodoptera frugiperda* (J. E. Smith) (Lepidoptera:

Noctuidae), in two tomato varieties. *Egypt J Biol Pest Control* **31**, e7.

Negi, A. and Sarethy, I. P. (2019) Microbial biodeterioration of cultural heritage: events,

colonization, and analyses. *Microb Ecol* **78**, 1014–1029.

Negulescu, I., Hyojung, K., Collier, B.J. Collier, J.R. and Pends, A. (1998) Recycling cotton from

cotton/ polyester fabrics. *Text Chem Color* **30**, 31–35.

O'Donnell, K. and Cigelnik, E. (1997) Two divergent intragenomic rDNA ITS2 types within a
monophyletic lineage of the Fungus *Fusarium* are nonorthologous. *Mol Phylogenetics Evol* **7**, 103-
116.

Palla, F., Barresi, G. (2017) Biotechnology and conservation of cultural heritage. Springer, Cham.
Pinheiro, A.C., Sequeira, S.O. and Macedo, M.F. (2019) Fungi in archives, libraries, and museums:
a review on paper conservation and human health. *Crit Rev Microbiol* **45**, 686–700.

Ponizovskaya, V.B., Rebrikova, N.L., Kachalkin, A.V., Antropova, A.B., Bilanenko, E.N. and
Mokeeva, V.L. (2019) Micromycetes as colonizers of mineral building materials in historic
monuments and museums. *Fungal Biol* **123**, 290–306.

Posada, F. and Vega, F.E. (2006) Inoculation and colonization of coffee seedlings (*Coffea arabica*
L.) with the fungal entomopathogen *Beauveria bassiana* (Ascomycota: Hypocreales).
*Mycoscience* **47**, 284–289.

Povolotckaia, A.V., Pankin, D.V., Sazanova, K.V., Petrov, Y.V., Kurganov, N.S., Mikhailova, A.
A., Povolotckiy, A.V., Kurochkin, A.V., Vlasov, A.D., Gonobobleva, S.L., Galushkin, A.A. and
Hosid, E.G. (2019) Biodamage to paper by micromycetes under experimental conditions: a study
by vibrational spectroscopy methods. *Opt Spectrosc* **126**, 354–359.

Proniewicz, L.M., Paluszkiewicz, C., Wesełucha-Birczyńska, A., Majcherczyk, H., Barański, A.
and Konieczna, A. (2001) FT-IR and FT-Raman study of hydrothermally degradated cellulose. *J*
*Mol Struct* **596**, 163–169.

Puškárová, A., Bučková, M., Habalová, B., Kraková, L., Maková, A. and Pangallo, D. (2016)
Microbial communities affecting albumen photography heritage: a methodological survey. *Sci Rep*
**6**, e20810.

Pyzik, A., Ciuchcinski, K., Dziurzynski, M. and Dziewit, L. (2021) The bad and the good-
microorganisms in cultural heritage environments-an update on biodeterioration and biotreatment
approaches. *Materials* **14**, 1–15.

Rambaut, A. (2010) FigTree v1.3.1. Institute of Evolutionary Biology, University of Edinburgh,
Edinburgh. http://tree.bio.ed.ac.uk/software/figtree/

Ranalli, G. and Zanardini E. (2021) Biocleaning on cultural heritage: new frontiers of microbial
biotechnologies. *J. Appl. Microbiol* **131**, 583-603.

Ranalli, G., Alfano, G., Belli, C., Lustrato, G., Colombini, M.P., Bonaduce, I., Zanardini, E.,
Abbruscato, P., Cappitelli, F., Sorlini, C. (2005) Biotechnology applied to cultural heritage:
biorestoration of frescoes using viable bacterial cells and enzymes. *J. Appl. Microbiol* **98**, 73-83.

Reddy, M.S., Murali, T.S., Suryanarayanan, T.S., Govinda Rajulu, M.B. and Thirunavukkarasu,
N. (2016) *Pestalotiopsis* species occur as generalist endophytes in trees of Western Ghats forests
of southern India. *Fungal Ecol* **24**, 70–75.

Rodríguez-Rodríguez, C. E., Jesús García-Galán, M., Blánquez, P., Díaz-Cruz, M. S., Barceló, D.,
Caminal, G., and Vicent, T. (2012) Continuous degradation of a mixture of sulfonamides by
*Trametes versicolor* and identification of metabolites from sulfapyridine and sulfathiazole. *J*
*Hazard Mater* **213–214**, 347–354.

Romero, S.M., Giudicessi, S.L. and Vitale, R.G. (2021) Is the fungus *Aspergillus* a threat to
cultural heritage? *J Cult Her* **51**, 107−124.

Sanjuan, T., Tabima, J., Restrepo, S., Læssøe, T., Spatafora, J.W. and Franco-Molano, A.E. (2014)
Entomopathogens of Amazonian stick insects and locusts are members of the *Beauveria* species
complex (Cordyceps sensu stricto). *Mycologia* **106**, 260–275.

Sequeira, S.O., De Carvalho, H.P., Mesquita, N., Portugal, A. and Macedo, M.F. (2019) Fungal
stains on paper: Is what you see what you get? *Conservar Patrimonio* **32**, 18–27.

Shrestha, B., Kubátová, A., Tanaka, E., Oh, J., Yoon, D.H., Sung, J.M. and Sung, G.H. (2019)
Spider-pathogenic fungi within Hypocreales (Ascomycota): their current nomenclature, diversity,
and distribution. *Mycol Prog* **18**, 983–1003.

Silva, A.G. (2011) The difficulty for conserving cultural heritage in tropical countries: the
experience of Rio de Janeiro City. *Int Preserv News* **54**, 40–43.

Sterflinger, K. and Pinzari, F. (2012) The revenge of time: Fungal deterioration of cultural heritage
with particular reference to books, paper and parchment. *Environ Microbiol* **14**, 559–566.

Šuchová, K., Puchart, V., Spodsberg, N., Mørkeberg Krogh, K. B. R. and Biely, P. (2020) A novel
GH30 xylobiohydrolase from *Acremonium alcalophilum* releasing xylobiose from the non-
reducing end. *Enzyme Microb Technol* **134**, e109484.

Trovão, J. and Portugal, A. (2021) Current knowledge on the fungal degradation abilities profiled
through biodeteriorative plate essays. Appl Sci **11**, e4196.

Vahur, S., Teearu, A., Peets, P., Joosu, L. and Leito, I. (2016) ATR-FT-IR spectral collection of
conservation materials in the extended region of 4000-80 cm$^{-1}$. *Anal Bioanal Chem* **408**, 3373–
3379.

Valášková, V. and Baldrian, P. (2006). Estimation of bound and free fractions of lignocellulose-
degrading enzymes of wood-rotting fungi *Pleurotus ostreatus*, *Trametes versicolor* and
*Piptoporus betulinus*. *Res Microbiol* **157**, 119–124.

Vieto, S., Escudero-Leyva, E., Avendaño, R., Rechnitzer, N., Barrantes-Madrigal, M.D., Conejo-
Barboza, G., Herrera-Sancho, O. A., Chaverri, P. and Chavarría, M. (2022) Biodeterioration and

cellulolytic activity by fungi isolated from a nineteenth-century painting at the National Theatre

of Costa Rica. *Fungal Biol* **126**, 101–112.

Watanabe, M., Inoue, H., Inoue, B., Yoshimi, M., Fujii, T. and Ishikawa, K. (2014) Xylanase

(GH11) from *Acremonium cellulolyticus*: Homologous expression and characterization. *AMB*

*Express* **4**, 1–8.

White, T.J., Bruns, T., Lee, S. and Taylor, J. (1990) Amplification and direct sequencing of fungal

ribosomal RNA genes for phylogenetics, PCR Protocols. Academic Press, Inc.

Zhao, J., Shi, P., Huang, H., Li, Z., Yuan, T., Yang, P., Luo, H., Bai, Y., Yao, B. (2012) A novel

thermoacidophilic and thermostable endo-β-1,4-glucanase from *Phialophora* sp. G5: Its

thermostability influenced by a distinct β-sheet and the carbohydrate-binding module. *Appl*

*Microbiol Biotechnol* **95**, 947–955.

Zhao, J., Shi, P., Luo, H., Yang, P., Zhao, H., Bai, Y., Huang, H., Wang, H. and Yao, B. (2010)

An acidophilic and acid-stable β-mannanase from *Phialophora* sp. P13 with high mannan

hydrolysis activity under simulated gastric conditions. *J Agric Food Chem* **58**, 3184–3190.

683     **Tables**

685     **Table 1. Chemical, substrate, and ink characterization of the historic documents from Costa**

686     **Rica.**

| Document | Sections analyzed for chemical characterization | Sections analyzed for fungal isolation | Paper composition | Ink chemical elements detected |
|---|---|---|---|---|
| Independence Act, 1821 | Pages 1-3 | Pages 1-3 | Cotton | Fe, Ca, Zn, K |
| Cloudy Days Act, 1821 | Page 1 | Full document | Cotton | Fe, Ca, Zn, K, S, Cl, Pb |
|  | Page 2 |  | Cellulose acetate | Fe, Ca, Zn |
| Political Constitution, 1949 (1991 reproduction) | Full document | Cover and Slavery Abolition page | Wood cellulose | Not determined |
| Guatemalan Series 1539 | Full document | Pages 1,8,3,17 | Cotton | Not determined |
| Guatemalan Series 1549 | Full document | Pages 2,5,9,10 | Cotton | Not determined |

687
688

689 **Table 2.** Identification (ID); BLAST results using ITS, TEF1 and TUB2; and origin of documents. Names in bold indicate the
690 assigned classification.
691

| Isolate number | Origin | Closest match and accession number / % similarity * | | |
|---|---|---|---|---|
| | | ID with ITS | ID with TEF1 | ID with TUB2 |
| 1539-A1P | Guatemalan series, 1539 | *Purpureocillium lilacinum* MZ359582 / 99.3 | *Purpureocillium lilacinum* MH613753 / 100 | *Purpureocillium lilacinum* JQ965112 / 99.8 |
| 1549-1A1P | Guatemalan series, 1549 | *Penicillium* **sp**. FJ752622 / 99.81 | - | *Penicillium compactum* KM973202 / 98.6 |
| 1549-4A1C | | **Unidentified Herpotrichiellaceae** KJ612089 / 90.48 | no match | no match |
| AI1-A1C | Independence Act, 1821 | *Cladosporium* **sp**. OK274323 / 100 | - | *Cladosporium oxysporum* EF101455 / 95.5 |
| AI3-A1P | | *Aspergillus hiratsukae* MN347034 / 100 | - | *Aspergillus hiratsukae* MH644026 / 100 |
| CP1-A1C | Political Constitution, 1949 (1991 reproduction) | *Periconia* **sp**. KP128003 / 99.80 | no match | no match |
| CP1-A1P | | *Cladosporium* **sp.** OK274323 / 92.48 | - | *Cladosporium* **sp.** JQ217373 / 97 |
| CP1-A2C | | *Pestalotiopsis microspora* OK254042 / 100 | - | *Neopestalotiopsis clavispora* OM328818 / 98.2 |
| CP1-A2P | | *Cladosporium* **sp.** EF504401 / 100 | - | - |
| CP1-A3C | | *Trametes hirsuta* GQ280373 / 100 | - | - |
| CP1-A3P | | **Unidentified Psathyrellaceae** JQ922137 / 100 | - | no match |
| CP2-A1C | | **Unidentified Pleosporales** KP263091 / 92.42 | - | *Biatriospora* **sp**. MF588919 / 86 |

| | | | | |
|---|---|---|---|---|
| CP2-A1P | | *Purpureocillium lilacinum* MZ359582 / 99.88 | - | *Purpureocillium lilacinum* GU968702 / 100% |
| CP2-A2C | | *Pestalotiopsis trachycarpicola* MZ453106 / 99.82 | *Neopestalotiopsis* **sp.** KR493607 / 100 | *Pestalotiopsis kenyana* KX895360 / 100 |
| CP2-A2P | | *Coprinellus* **sp.** MK307658 / 99.84 | - | - |
| CP2-A3C | | *Acremonium persicinum* JQ599382 / 99.42 | - | - |
| CP2-A3P | | *Beauveria* **aff.** *bassiana* MZ618707 / 100 | - | *Xenoacremonium recifei* KM232105 / 89 |
| CP2-A4C | | *Acremonium persicinum* JQ599382 / 100 | - | - |
| CP2-A4P | | *Cyphellophora* **aff.** *pluriseptata* MH063042.1 / 91.7 | - | *Cyphellophora* **sp.** LR814116 / 80% |
| CP2-A5C | | *Penicillium* **aff.** *sumatraense* MH864547 / 100 | - | - |
| ND1-A1P | | *Penicillium steckii* MZ568311 / 100 | - | *Penicillium steckii* MW196656 / 100 |
| ND2-A1P | Cloudy Days Act, 1821 | *Cladosporium* **sp.** OK242741 / 100 | - | *Cladosporium* **aff.** oxysporum KU216745 / 99.7 |

692  *If the percent identity is less than 80% and query coverage less than 50%, then the result is indicated as "no match."
693

694  **Table 3.** Enzymatic index (EI) registered by fungal isolates (± indicates standard deviation based

695  on three replicates).

| Isolate code | Taxonomy | Enzymatic Index (EI) |
|---|---|---|
| CP2-A4P | *Cyphellophora* aff. *pluriseptata* | 4.0 ± 0.3 |
| ND1-A1P | *Penicillium steckii* | 3.3 ± 0.3 |
| CP1-A2P | *Cladosporium* sp. | 3.3 ± 0.1 |
| CP2-A1P | *Purpureocillium lilacinum* | 3.2 ± 0.0 |
| 1549-4A1C | Herpotrichiellaceae | 3.1 ± 0.4 |
| CP2-A2C | *Pestalotiopsis kenyana* | 3.1 ± 0.5 |
| CP2-A3P | *Beauveria* aff. *bassiana* | 3.1 ± 0.3 |
| CP1-A1P | *Cladosporium* sp. | 3.0 ± 0.1 |
| CP2-A5C | *Penicillium* aff. *sumatraense* | 2.9 ± 0.7 |
| CP2-A1C | Pleosporales | 2.8 ± 0.2 |
| AI3-A1P | *Aspergillus hiratsukae* | 2.8 ± 0.0 |
| 1549-1A1P | *Penicillium compactum* | 2.6 ± 0.9 |
| AI1-A1C | *Cladosporium* sp. | 2.6 ± 0.1 |
| CP1-A1C | *Periconia* sp. | 2.5 ± 0.3 |
| ND2-A1P | *Cladosporium* aff. *oxysporum* | 2.5 ± 0.2 |
| CP1-A3P | Psathyrellaceae | 2.2 ± 0.2 |
| CP2-A2P | *Coprinellus* sp. | 2.0 ± 0.3 |
| CP2-A4C | *Acremonium persicinum* | 1.8 ± 0.1 |
| CP1-A2C | *Neopestalotiopsis clavispora* | 1.7 ± 0.1 |
| CP2-A3C | *Acremonium persicinum* | 1.6 ± 0.2 |
| Control | *Pleurotus ostreatus* | 1.3 ± 0.1 |
| CP1-A3C | *Trametes hirsuta* | 1.1 ± 0.0 |
| 1539-A1P | *Purpureocillium lilacinum* | 0 |

**Figure captions**

**Figure 1.** Historic documents from Costa Rica analyzed for chemical and substrate characterization. **A,B**. Independence Act. **C**. Signs of deterioration on the Independence Act, including yellow spots around the letters. **D**. Cloudy Days Act. **E**. Humidity mark on Cloudy Days Act. **F**. Oxidation signs around the ink from Cloudy Days Act. **G**. 1949 Political Constitution

(1991 reproduction). **H**. Signs of microbiological contamination on 1949 Political Constitution (1991 reproduction). **I**. Yellow spots on 1949 Political Constitution (1991 reproduction). **J**. Fragment of the 1539 Guatemalan Series. **K**. Fragment of the 1549 Guatemalan Series. **L,M**. Signs of leakage and humidity on 1539-1549 Guatemalan Series.

**Figure 2.** Bayesian Inference consensus cladogram based on nrDNA ITS sequences. Posterior probabilities are indicated at branches. LnL = -13564.21

Independence Letter 1821

Cloudy Days Letter 1821

Political Constitution 1991 reproduction

Guatemalan Series 1539 and 1549