Dynamic matrices with DNA-encoded viscoelasticity for advanced cell and organoid culture

Y.-H. Peng[1,2], K. Gupta[1,2,‡], S. K. Hsiao[1,2,‡], A. Ruland[1], G. K. Auernhammer[1], M. F. Maitz[1], S. Boye[4], C. Gerri[3], A. Honigmann[3], C. Werner[1,2] , E. Krieg[1,2,*]

[1]Institute for Biofunctional Polymer Materials, Leibniz Institute of Polymer Research Dresden, Germany; [2]Center for Regenerative Therapies Dresden, Cluster of Excellence Physics of Life and Faculty of Chemistry and Food Chemistry, Technische Universität Dresden, Germany; [3]Max-Planck Institute for Cell Biology and Genetics, Dresden, Germany. [4]Institute for Macromolecular Chemistry, Leibniz Institute of Polymer Research Dresden, Germany.

‡ These authors contributed equally.   * To whom correspondence should be addressed: krieg@ipfdd.de

Keywords: DNA nanotechnology, supramolecular hydrogels, ECM, 3D cell culture, tissue engineering, organoids

Abstract

3D cell and organoid cultures, which allow in vitro studies of organogenesis and carcinogenesis, rely on the mechanical support of viscoelastic matrices. However, commonly used matrix materials lack rational design and control over key cell-instructive properties. Herein, we report a class of fully synthetic hydrogels based on novel DNA libraries that self-assemble with ultra-high molecular weight polymers, forming a dynamic DNA-crosslinked matrix (DyNAtrix). DyNAtrix enables, for the first time, computationally predictable, systematic, and independent control over critical viscoelasticity parameters by merely changing DNA sequence information without affecting the compositional features of the system. This approach enables: (1) thermodynamic and kinetic control over network formation; (2) adjustable heat-activation for the homogeneous embedding of mammalian cells; and (3) dynamic tuning of stress relaxation times over three orders of magnitude, recapitulating the mechanical characteristics of living tissues. DyNAtrix is self-healing, printable, exhibits high stability, cyto- and hemocompatibility, and controllable degradation. DyNAtrix-based 3D cultures of human mesenchymal stromal cells, pluripotent stem cells, canine kidney cysts, and human placental organoids exhibit high viability (on par or superior to reference matrices), proliferation, and morphogenesis over several days to weeks. DyNAtrix thus represents a programmable and versatile precision matrix, paving the way for advanced approaches to biomechanics, biophysics, and tissue engineering.

DyNAtrix: a fully synthetic cell-instructive matrix with programmable mechanical properties

Introduction

Supramolecular hydrogels are water-swollen three-dimensional (3D) networks of molecules, linked together by non-covalent bonds[1,2]. The dynamic nature of these bonds gives access to unique properties, such as stimuli-responsiveness and self-healing[3,4]. Hydrogels that contain self-assembling DNA are particularly interesting, as the *sequence-selective* recognition of complementary DNA strands enables modular construction and de-construction of complex functional materials[5–7]. With the help of DNA nanotechnology, the properties of these systems can be adjusted and dynamically changed *in situ*[8,9]. DNA-based materials can thus be adapted to respond to biomolecules and cells to sense[10–13], actuate[14,15], and release[16,17]. Amongst their many applications, DNA-based hydrogels could support 3D cell cultures, for instance, to mechanistically study cell and developmental biology, recapitulate pathologies, and develop (personalized) therapies[17–20].

The (micro)environment of cells in the extracellular matrix (ECM) is one of the key determinants for cell fate decisions[21]. In particular, the stiffness of ECM and ECM-mimicking materials can affect cell proliferation and morphology in 3D organoid cultures via mechanosensitive transcriptional regulators[22,23]. Beyond stiffness, it has recently been recognized that matrix viscoelasticity entails other critical parameters[24,25]. Specifically, the *stress relaxation* behavior describes the time-dependent change of mechanical stress in the material following a deformation. Faster stress relaxation can promote cell spreading[26], migration[27], and differentiation[28]. However, the most widely used hydrogel systems for 3D cell culture are naturally-derived basement membrane matrices, such as *Matrigel*, which do not allow precise tuning of critical material properties, including stress relaxation. They also exhibit significant batch-to-batch compositional variation and are prone to cause unexpected stimulation of cells[29]. More advanced materials that do offer viscoelastic tunability require significant modifications to the chemical composition of the system, whose influence on cells is fundamentally challenging to disentangle from mechanical effects. An ideal cell-instructive substitute material should be chemically defined and adapt its mechanical properties in a programmable manner[21,30]. Moreover, it should be printable under mild cytocompatible conditions to enable top-down fabrication of complex 3D tissue templates[31–33].

Synthetic DNA-crosslinked hydrogels appear uniquely suitable for addressing the need for a highly adaptive tissue culture platform. However, DNA oligonucleotides are typically required at very high concentrations (5 to 50 g/L). The high cost of oligonucleotide synthesis often makes these materials prohibitively expensive to be deployed at scale. Furthermore, large DNA concentrations can also induce undesired effects when in contact with living cells and tissues. For instance, DNA can electrostatically scavenge positively charged biomolecules[34] or stimulate inflammatory response pathways[35,36]. Thus, there has been significant interest in either reducing the cost of DNA material synthesis[37] or supporting the network with secondary non-DNA crosslinks[14].

We herein report a novel approach to a programmable dynamic DNA-crosslinked matrix platform (DyNAtrix). DyNAtrix is based on a diverse set of DNA modules that self-assemble with a biocompatible DNA-grafted ultra-high molecular weight (UHMW) poly(acrylamide-co-acrylic acid) backbone. By using novel crosslinker libraries—rather than single crosslinker splints—the formation of the supramolecular network and its mechanics can be uniquely controlled without changing crosslinker concentrations or other chemical components of the system. As a result, gelation occurs at very low DNA concentrations, where crosslink efficiencies approach the theoretical limit for affine molecular networks. Importantly, the DNA libraries provide dynamic control over viscoelasticity and plasticity, tunable crosslinking kinetics and mixing behavior, as well as adjustable degradability. These features demonstrate the unique programmability of soft materials powered by DNA nanotechnology as 3D cell culture matrices and printable bio-inks.

Results

Material concept and design

To create a programmable yet inexpensive and cytocompatible hydrogel, we first synthesized two derivatives of a UHMW poly(acrylamide-co-acrylic acid)-graft-DNA[38,39] copolymer (Figure 1a). We chose this backbone due to its high molecular weight, anticipated biocompatibility, and methanol responsiveness. The latter enables efficient removal of unreacted DNA and cytotoxic acrylamide monomers. We hypothesized that the UHMW backbone could serve as the majority structural component, while a relatively small amount of DNA would suffice to induce network formation and dictate material properties. The two polymer derivatives, MeRPy-7 and MeRPy-37, have an average number of ~7 and ~37 DNA strands per polymer backbone, respectively, and a molecular weight of 3-4 megadalton (MDa), as

determined by asymmetrical flow field-flow fractionation with light scattering detection, gel electrophoresis, and NMR (Supplementary Information, Figures S1-S3). The covalently linked DNA strands serve as universal *anchor* sites for self-assembly with DNA crosslinkers. Moreover, they allow modular noncovalent extension of the material with other functional DNA constructs. A single polymer batch can thus be used to assemble materials with vastly diverse properties. For studies involving cell culture, synthetic peptide side chains were included in the synthesis. The peptides contain the RGD motif that facilitates cell adhesion. The peptide-grafted polymer is termed MeRPy-37-1k, carrying an average number of ~37 DNA strands and approximately 1000 RGD peptides per polymer molecule.

To our surprise, initial attempts to crosslink MeRPy at low concentration with simple crosslinker splints failed to produce a stable hydrogel. As the mechanical strength of a hydrogel is directly proportional to the number of effective crosslinks (Supplementary Information 2.18), we hypothesized that polymer self-binding (i.e. ineffective *intra*-molecular bonds) dominated over network-forming (i.e. *inter*-molecular) crosslinks (Figure 1b). The predominance of undesirable intramolecular bonding is not specific to DNA gels, but a general phenomenon in crosslinked polymer gels, typically reducing crosslink efficiency to 20% or less[40,41].

The sequence-selectivity of DNA hybridization offered a unique solution to this problem: instead of using a single splint type, we constructed complex libraries based on a dual splint design (Figure 1c,d). All library members have an identical *anchor* domain that binds to MeRPy below a specific melting temperature, T_1. Additionally, each splint has an *overlap domain* that is designed to pair with only one other splint below a second melting temperature, T_2. The melting temperature is predictable with high accuracy based on nearest-neighbor thermodynamic models[42]. We designed anchor- and overlap domains to have sufficiently separated melting temperatures, ensuring that upon slow cooling from 95°C anchor domains would bind prior to overlap domains (Figure S4).

Figure 1. Basic concept and crosslinker design for DyNAtrix. *(a) Synthesis of MeRPy derivatives via free radical polymerization of acrylamide, sodium acrylate, and acryloyl-based monomers modified with anchor strand DNA (red). For cell culture, acrylamide-labelled cell adhesion peptides with RGD motif (green) were co-polymerized. (b) Scheme of intramolecular crosslinks predominant in high-molecular weight polymers at low concentrations, resulting in low crosslinking efficiency and poor mechanical strength. (c) Scheme of polymer crosslinking via combinatorial crosslinker library (CCL) splints to suppress the formation of intramolecular bonds and promote effective intermolecular crosslinks. (d) CCLs are generated by introducing ambiguous bases (N) in the overlap domain.*

In principle, overlap domains can be designed with perfectly orthogonal sequences. However, this would require costly synthesis of many different oligonucleotides. Instead, we chose a combinatorial approach where overlap domains are diversified by introducing ambiguous bases (N) at specific positions (Figure 1d). N indicates a sequence position at which an equal mixture of A, T, C, and G nucleotides is used during oligonucleotide synthesis. The complexity (i.e., the number of distinct splint pairs) of this *combinatorial crosslinker library* (CCL) equals 4^n, where n is the number of ambiguous bases in the sequence. As the DNA duplex is strongly destabilized even by a single base mismatch[43], equilibrium binding strongly favors perfectly complementary binding partners. We carried out thermodynamic predictions for all possible splint combinations in libraries ranging from 1 (n=0) to 256 (n=4) splint pairs, confirming that highly selective splint pairing (>95%) is expected at equilibrium in all crosslinker libraries (Figure 2b, Figure S5, Table S1).

CCL complexity uniquely controls network formation and matrix stiffness, allowing gelation at exceptionally low DNA content

According to statistical simulations, the suppression of undesired intra-molecular crosslinks strongly depends on the complexity of the CCL, as well as the number of anchor strands per polymer backbone (Figure 2a). For instance, MeRPy-37 was predicted to require approximately 75 splint pairs to suppress 80% of intramolecular crosslinks, while MeRPy-7 would require approximately 10 splint pairs. We first studied the mechanical properties of CCL-crosslinked MeRPy-37 at 1% (w/v) polymer concentration by oscillatory rheology. The polymer was annealed with five CCL versions comprising 1, 4, 16, 64, and 256 splint pairs (*CCL-1* to *CCL-256*), and each sample contained an equal DNA concentration of 1.3 g/L. In all cases, the elastic moduli, G', significantly exceeded the loss moduli, G'', over a wide range of frequencies and strains, confirming that the combination of dual splint CCLs with the UHMW polymers generates

stable gels (Figure S6). Expectably, due to the temperature-responsive melting of DNA, all MeRPy-CCL gels undergo a reversible sol-gel transition at temperatures between 50–65°C (Figure 3a, Figure S8).

Increasing CCL complexity improved crosslinking efficiency from approximately 28% in *CCL-1* to 76% in *CCL-64* (Figure 2c, Supplementary Information 2.18), which is in excellent agreement with the statistical prediction (Figure 2a). Increasing library complexity from 64 to 256 members did not further increase stiffness; the marginal benefit of using the more complex library is likely offset by slower binding kinetics, since overlap domains become increasingly unlikely to capture their zero-mismatch binding partners in very large libraries. Overall, G' values are in the range of 50 to 140 Pa, which is comparable to *Matrigel*, the most widely used cultural matrix for organoids. We note that adjusting CCL complexity is a novel approach to tune the elasticity of a gel without changing its crosslinker concentration.

The high crosslinking efficiency and low mass fraction of DNA in the polymer chains enable the formation of stable gels at extraordinary low DNA content, up to two orders of magnitude lower than previously reported synthetic DNA-crosslinked hydrogels with well-characterized rheological properties[14,19,44–47] (Figure 2d). CCL-64 crosslinked MeRPy-7 and MeRPy-37 gels showed critical gelation concentrations (CGC) of ~0.2% (w/v), corresponding to a total DNA content of 0.05 and 0.26 g/L, respectively. Even lower DNA contents (down to 0.017 g/L) were achieved when—instead of anchor strands—the CCL-64 overlap domain was directly grafted onto the polymer backbone (Supplementary Figure S10; Figure 2d, samples (6) & (7)). The directly grafted crosslinker libraries thus offered a more efficient use of synthetic DNA, however, at the expense of "hard-coding" the crosslinking properties into the polymer. Further experiments were performed with crosslinker splints, as they enable rapid modular adaptation of the material properties without time-consuming polymer synthesis.

Figure 2. Theoretical prediction and rheological validation of DyNAtrix crosslinked via combinatorial crosslinker libraries (CCL). *(a) Statistical simulation of the maximum percentage of intramolecular crosslinks as a function of CCL complexity and the number of anchor strands per polymer backbone. (b) The predicted minimum free energy (top) and the predicted hybridization interactions (normalized Boltzmann distribution, bottom) of crosslinker libraries CCL-4 and CCL-256 at equilibrium. High-resolution matrices for all crosslinker libraries are shown in Supplementary Files 1-10. (c) Top: Photographs of DyNAtrix, stained with SYBR-Gold. Bottom: Average stiffness of DyNAtrix crosslinked via 1, 4, 16, 64, 256-splint library at 20°C. All samples have a total DNA content of 1.3 g/L. Error bars represent the standard deviation from three independent experiments. (d) Different DNA hydrogel designs give access to different concentration and stiffness regimes: comparison between previously reported synthetic DNA-crosslinked hydrogels[14,19,44–47] and several DyNAtrix gels (this study, red). DyNAtrix samples (1)-(5) were crosslinked with CCL-64 splints, while samples (6) and (7) had CCL-64 directly grafted onto the polymer backbone (cf. Figure 1c, Supplementary Figure S10). (1) 1.65% (w/v) MeRPy-37, (2) 1% (w/v) MeRPy-37, (3) 1% (w/v) MeRPy-7, (4) 0.2% (w/v) MeRPy-37, (5) 0.2% (w/v) MeRPy-7, (6) 1% (w/v) MeRPy-7, (7) 0.2% (w/v) MeRPy-7.*

Rapid self-healing allows printing of complex patterns under cytocompatible conditions

Extrusion bioprinters require self-healing hydrogels that can be easily liquefied under mechanical forces and rapidly recover their viscoelasticity. Such properties allow the material to pass through the nozzle as a fluid, protect the cells from damaging forces, and quickly reform the network after extrusion. To explore the compatibility of DyNAtrix for extrusion bioprinting, we first tested its self-healing properties by oscillatory rheology (Figure 3b, Figures S9). When a large strain (1000%) is applied, the supramolecular network breaks apart and transitions into a liquid state, as revealed by a drastic drop of its stiffness (G' << G") and increase of the phase angle from 3°±1° to 74°±1°. When reducing the strain, the gel state is immediately restored. After being subjected to 10 consecutive breakage cycles, the storage modulus recovered to over 95% of its original value, revealing that breakage occurs predominantly at the reversible DNA crosslinks rather than the covalent polymer backbone. Due to this rapid self-healing, DyNAtrix quickly solidifies when extruded through a positive displacement pipette (Figure 3c, Supplementary Video 1). This feature allowed extrusion printing of various patterns on a commercial *BioScaffolder* under mild cell-compatible conditions, giving access to the application as *bio-ink* for fabricating complex two and three-dimensional tissue structures (Figure 3d).

Figure 3. Thermoreversibility, self-healing, bioprinting, and tunable stress-relaxation of DyNAtrix. *(a) Crosslinking efficiency of DyNAtrix (1% (w/v) MeRPy-37) as a function of temperature. Error bars represent the standard deviation from three independent experiments. (b) Self-healing of DyNAtrix (1% (w/v) MeRPy-37 crosslinked with CCL-4) was confirmed by repetitive strain recovery tests alternating between 1000% and 10% strain. The gel showed over 95% of recovery after 10 consecutive breakage-recovery cycles. (c) Scheme of extrusion printing (left) and photographs of DyNAtrix being extruded from a narrow tip (right, cf. Supplementary Video 1). The gels were prepared with 1% (w/v) MeRPy-37 crosslinked with CCL-64. (d) A grid printed on a BioScaffolder with a total height of ~500 μm. The material was stained with SYBR-Gold for imaging purposes. (e) Scheme of stress-relaxation crosslinkers (SRCs) with variable overlap domains (green). The corresponding DNA sequences are shown in Supplementary Table S1. (f) Normalized stress relaxation curves of DyNAtrix crosslinked via different SRCs (green traces) covering the typical range of biological tissues[25] (yellow background). Stress relaxation times (τ) were determined by the simple Maxwell model, where σ(τ) = σ₀/e. The measurements were carried out at 37 °C with 15% strain.*

Nanomechanical crosslinker stability encodes macroscopic stress-relaxation behavior

As demonstrated by Mooney, Chaudhuri and colleagues, matrix plasticity influences cell development.[28,48] Previously described approaches to alter plasticity require significant changes to the chemical composition or temperature—parameters that can influence cell development even without stress-relaxation effects. DNA crosslinkers can uniquely address this challenge, as the sequence and length of DNA duplexes dictate their stability under nanomechanical shear forces. For short DNA (<20nt), the force required to break the duplex into two separate strands grows linearly with the number of complementary bases[49]. Exploiting this phenomenon, we developed stress-relaxation crosslinkers (SRCs) by systematically changing only a few bases in the overlap domain sequence (Figure 3e, Supplementary Table S1). As the overlap domains are the weakest connection points in the supramolecular network, their rupture force was predicted to dictate the material's stress relaxation behavior. Indeed, SRCs with overlap domains ranging between 6 to 14 nucleotides allowed the adjustment of the stress-relaxation time (τ) from less than 1 s to more than 1000 s. Frequency-dependent rheological measurements confirm that—despite the vastly different stress relaxation times—all SCR-crosslinked gels using 8-14nt overlap domains exhibit similar plateau stiffnesses (Supplementary Figure S7). Due to its sub-second relaxation time, gels crosslinked by 6-nt SRCs are only solid at high deformation frequencies. Overall, SRCs allow precise mimicking of the typical stress relaxation times that are found across diverse animal tissues[28] (Figure 3f).

Heat-activated crosslinkers enable homogeneous encapsulation of mammalian cells

The previous sections described how CCLs and SRCs permit predictable engineering of network formation, thermodynamic stability, and (nano)mechanical properties. We next exploited the tunable binding kinetics of DNA in order to make MeRPy-CCL gels compatible with existing cell encapsulation workflows. In commercially available cell culture matrices, cells are typically first dispersed within a liquid precursor

solution. Subsequently, gelation is induced to encapsulate the cells. For instance, *Matrigel* precursor solution is typically mixed with cells at 4°C, followed by incubation at ~37°C. The heating step conveniently triggers gelation at the ideal temperature for mammalian cell culture. In contrast, DNA-crosslinked hydrogels typically require heating above the crosslinker melting temperature to become liquid (>50°C), which is incompatible with cell culture. As an alternative to thermal annealing, we first attempted to encapsulate cells by rapidly mixing two pre-annealed MeRPy precursor solutions (Figure 4b, left). However, the fast hybridization kinetics of DNA leads to crosslink formation before a homogeneous mixture can be achieved. The resulting supramolecular networks were highly inhomogeneous (Figure 4d, left) and exhibited poor mechanical stiffness (Figure 4c, green trace).

As a solution, we aimed to mimic the convenient thermoresponsive profile of Matrigel by altering the DNA crosslinking kinetics. We designed heat-activated crosslinkers (HACs) by upgrading the CCL design with blocking strands (Figure 4a). The blocking strands serve as protection groups that bind to the overlap domain at low temperatures to prevent their premature crosslinking. The blocking strands were designed to spontaneously dissociate from the overlap domains at 37°C, thereby activating the crosslinker for binding. A mixture of two polymer precursor solutions is thus trapped in an off-equilibrium (metastable) liquid state at 4°C, such that the mixing with cells and medium can proceed to completion. In agreement with this design, heating to 37°C leads to rapid formation of a homogeneous gel (Figure 4d, right) with highly superior mechanical stiffness (Figure 4c). HACs with 64-splint complexity were subsequently used in all cell culture experiments (see below).

Figure 4. Heat-activated crosslinkers (HACs) enable controlled gelation of DyNAtrix under cell-compatible conditions. (a) Scheme of heat-activated crosslinkers (HACs) and their binding mechanism. (b) Scheme of liquid precursor mixing with vs. without blocking strands. (c) Storage modulus G' of the incubated gel components, directly after mixing, with (blue) and without (green) blocking strands. (d) Confocal microscopy images (cross section) of MeRPy gels formed with and without blocking strands. One polymer component was stained with a fluorescein-labeled DNA strand (green fluorescence), while the other polymer component was unlabeled. Left: poor mixing is typically observed in the absence of blocking strands. Right: Highly homogeneous molecular networks are observed with HACs (+blocking strands). The black circle is an air bubble.

Matrix stability in cell culture, cytocompatibility, and tunable degradation

An immediate challenge for applying DNA-based materials in cell culture relates to their stability, as DNA is readily degraded by nucleases. DNase I, in particular, is present in fetal bovine serum (FBS) that is commonly added to culture media. It is thus necessary to protect DNA crosslinkers from DNase I activity, yet, on the flip side, a certain degree of enzymatic reconfigurability can be desirable. We therefore sought to identify conditions under which the enzymatic digestion of DNA-based gels can be either promoted or inhibited.

First, we tested the stability of unprotected gels in the presence of culture medium that was supplemented with 10% FBS. Gels were largely degraded within 48 hours (Supplementary Video 2). We then tested the effect of actin, which is a natural inhibitor of DNase I[50]. Using a fluorescently labeled DNA mock target, we showed that the rate of digestion by DNase I can be gradually tuned with different actin concentrations (Figure 5a). A concentration of 50 µg/mL was sufficient to suppress gel degradation for at least 48 hours (Figure 5b, Supplementary Video 3). 80 µg/mL actin reduced the rate of digestion by 97.5% (Figure S18), preserving DyNAtrix in cell culture experiments for at least 2 weeks. A similarly effective protection can be achieved by the addition of citrate (10 mM), which chelates divalent cations that are required by DNase I. As the chelation of calcium ions was suspected to affect cell development, we chose actin as our default protection strategy. Supplementing both actin and DNase I to the culture provides external control over the material's stability. This enables, for instance, gradual softening of the material or triggered release of cells at a chosen time point (see below).

To examine the cytocompatibility of the material, we first cultured mesenchymal stem cells (MSCs) in HAC-crosslinked and actin-protected MeRPy-37-1k in DMEM + 10% FBS, and cell viability was probed by live/dead staining for up to one week. MSCs showed excellent viability (91±7% on day 7), significantly higher than on a reference 2D surface, and even outperforming Matrigel in most experiments (Figure 5c, Supplementary Figure S12). To demonstrate triggered release of live cells, 1 µL of recombinant DNase I solution (2 units / µL) was added onto the gel on day 9. The gel was promptly deconstructed within 2 hours, and live cells settled to the bottom of the culture plate (Figure 5e, Supplementary Video 4).

Figure 5. DyNAtrix exhibits tunable stability against degradation in cell culture, high biocompatibility, and DNase-I-mediated release of live cells. *(a) Digestion experiment. A digestion probe containing a fluorophore (Cy5) and a fluorescence quencher (Q) was incubated in medium containing DNase-I and different concentrations of actin. Duplex digestion leads to dissociation of the strands, resulting in increased Cy5 emission. (b) Normalized volume of DyNAtrix in FBS-supplemented medium over time. The samples were incubated in buffer (negative control, black) or serum-containing medium without protection (red). The addition of actin (50 µg/mL, blue) or citrate (10 mM, green) effectively protected the gels from digestion. Error bars indicate the standard deviation from 4 independent experiments. (c) Viability of MSCs cultured in actin-protected DyNAtrix compared to Matrigel and a 2D culture plate. Error bars represents the standard deviation of 3 independent experiments. (d) Live/Dead staining of MSCs in*

DyNAtrix after 7 days in culture. Live cells were stained with calcein-AM (green) and dead cells were stained with propidium iodide (red). (e) Release of live MSCs from DyNAtrix by addition of DNase I on day 9. (f) Quantification of DyNAtrix-triggered immune response and hemocompatibility. Activation of monocytes in human whole blood (top) was measured by flow cytometric quantification of CD11b expression. Platelet activation (bottom) was assessed by quantification of the hemostasis marker platelet factor 4 (PF4). CCL-64-crosslinked MeRPy-37 and MeRPy-37-1k were compared with 3 reference substrates: glass, PTFE (Teflon AF), and covalently crosslinked acrylamide (AA) gel. Data were collected with a triplicate set of samples (n=3).

Innate immune response and hemocompatibility

To further evaluate the properties of DyNAtrix as a biomaterial, we incubated CCL-64-crosslinked MeRPy-37 and MeRPy-37-1k (1%, w/v) with fresh human whole blood and tested for various markers of inflammation and hemostasis. We compared these two gels to three reference substrates: (I) reactively cleaned glass, (II) Teflon™ AF (a benchmark material for medical devices), and (III) covalently crosslinked polyacrylamide (AA) gel. DyNAtrix exhibited low activation of monocytes (Figure 5f) and granulocytes (Supplementary Figure S11b,c), as indicated by low levels of CD11b expression. Similarly, we measured low levels of C5a, which is a marker for the activation of the complement system (Supplementary Figure S11a). Thus, DyNAtrix did not induce a significant innate immune response in vitro. Moreover, both gels showed very low release of platelet factor 4 (PF4, Figure 5f) and prothrombin fragment 1+2 (F1+2, Supplementary Figure S11d). The results indicate significantly reduced blood coagulation and platelet activation with respect to glass and even Teflon™ AF, and similar to the AA gel reference. These results suggest potential suitability for in vivo studies and medical applications. No statistically significant differences were observed between gels constructed from MeRPy-37 and MeRPy-37-1k.

DyNAtrix supports proliferation and guides morphogenesis of diverse cell types and organoids

We finally sought to validate the suitability of DyNAtrix for advanced cell culture and organoid research. To this end, three different cell types were embedded in DyNAtrix [+RGD] (1% (w/v) MeRPy-37-1k +HACs)

and DyNAtrix [−RGD] (1% (w/v) MeRPy-37 +HACs): (1) human induced pluripotent stem cells (hiPSCs), which offer patient-specific platforms for *in-vitro* disease modeling at the cellular level (Figure 6a,d,e), (2) Madin-Darby canine kidney (MDCK) cells, which serve as a model for developing epithelial tissues (Figure 6b), and (3) human trophoblasts that develop into placenta organoids, which allow in-vitro studies of human placental development and pregnancy-related disorders (Figure 6c,f,g). We assessed the proliferation and self-organization of the cells into multicellular structures and tested the effect of RGD adhesion sites on development and morphogenesis.

hiPSCs were cultured in DyNAtrix that was crosslinked in *mTeSR™1*, a chemically defined, serum-free medium optimized to maintain and expand hiPSCs. Notably, DyNAtrix did not require actin supplementation but stayed intact for the full culture duration (7 days). Similar results were obtained in other serum-free media with MDCK and trophoblast cultures (see below), indicating that the major source of nuclease is added serum, rather than secretion by cells. During the culture for one week, hiPSCs sustained continuous proliferation, formed hollow cysts that remained round-shaped, and continued expanding (Figure 6d). The size, morphology, and number of cysts appeared identical to those formed in a Matrigel reference culture. Confocal microscopy showed that the cysts strongly expressed pluripotency marker Oct4, further corroborating that the material is effectively supportive (Figure 6e). RGD peptides proved critical, as the number of observed cysts and their lumen size were greatly reduced in RGD-free DyNAtrix (Supplementary Figure S13), underlining the importance of mechanical hiPSC-matrix interactions.

We were initially skeptical whether it would be possible to stain the nuclear DNA of cells in DyNAtrix, as the presence of DNA crosslinkers could give rise to unacceptably high background fluorescence. However, due to the low DNA content in the gels (≤1.3g/L), cell nuclei were readily stained with DAPI (4′,6-diamidino-2-phenylindole) in all experiments (Figure 6a,e,g). We note that DAPI did produce background

effects when we explored DNA crosslinker concentrations beyond typically used values (Supplementary Figure S14).

The culture of MDCK cysts largely mirrored the results from hiPSC culture. MDCK cells were genetically modified to express fluorescently labeled E-cadherin and podocalyxin as markers for cell polarity and adhesion junctions. In initial experiments, cells were embedded in actin-protected DyNAtrix that was supplemented with 10% FBS. In order to remove any naturally-derived components, we also prepared DyNAtrix in a serum-free medium (UltraMDCK™), which led to identical results. In this environment, DyNAtrix remained stable for at least two weeks without nuclease protection. Confocal microscopy images showed that MDCK cells proliferate and form hollow cysts (Figure 6b). As in hiPSCs, cyst morphologies strongly depend on the presentation of extracellular adhesion signals. Even though numerous cysts formed in DyNAtrix [−RGD], only 2.2% (±1.0%) of those cysts showed an apical-in polarity, while the majority exhibited an inverted or undetermined polarity (Supplementary Figure S15). In DyNAtrix [+RGD], cyst development increased to 20% (±1%) apical-in morphologies. While RGD modification increased the fraction of apical-in cysts, additional synthetic adhesion signals may be required to reach levels comparable to Matrigel (>90%).

We finally explored the development of human trophoblasts in serum-free DyNAtrix. We chose this particular organoid model as the independently adjustable viscoelastic and biochemical cues could solve current challenges surrounding organoid polarity to more faithfully reproduce in-vivo morphologies[51]. In DyNAtrix [−RGD], trophoblast proliferation was low, and no organoids were observed (Figure 6f). In contrast, trophoblasts in DyNAtrix [+RGD] proliferated rapidly and had developed numerous placenta organoids within a week. The number, size, and shape of the organoids closely matched those grown in Matrigel at the same time point (Supplementary Figure S16). The organoid morphology in DyNAtrix [+RGD] and Matrigel was further investigated in immunofluorescence images obtained from confocal microscopy (Figure 6c,g, Supplementary Figure S17). We found strong expression GATA3, a trophoblast-specific

transcription factor typically found in all cells of placenta organoids (Figure 6g). Moreover, we confirmed the expression of syndecan and E-cadherin, which are important markers for cell differentiation and organoid development. Overall, confocal imaging did not reveal any morphological or developmental differences of placenta organoids in DyNAtrix when compared to Matrigel. To the best of our knowledge, this is the first report describing the successful growth of human placenta organoids in a fully synthetic 3D matrix environment. Beyond the scope of this article, future studies will focus on utilizing the independently tunable stress-relaxation, elasticity, and adhesion signals in DyNAtrix to improve the physiological relevance of this organoid model for in-vivo placental development.

Figure 6. DyNAtrix is compatible with a variety of 3D cell and organoid cultures. *Confocal images of (a) hiPSCs cysts embedded in DyNAtrix [+RGD]. Cells were stained for Oct4 (pluripotency), phalloidin (actin), and DAPI (nuclei), (b) MDCK cysts grown in DyNAtrix [+RGD]. The cells were modified to express mNeonGreen-labelled E-cadherin and mScarlet-labelled Podocalyxin, and (c) Trophoblast culture in DyNAtrix [+RGD]. Cells were immunofluorescently stained for GATA3, E-cadherin, and syndecan. (d) Representative microcopy images of hiPSC cysts grown in DyNAtrix [+RGD] in comparison with Matrigel. A comparison with DyNAtrix [−RGD] is shown in Supplementary Figure S13. (e) Representative confocal microcopy images of hiPSC cysts grown in DyNAtrix [+RGD] in comparison with Matrigel. Top: cross sections. Bottom: projection image of a cysts in DyNAtrix [+RGD]. (f) Representative brightfield images of trophoblasts grown in DyNAtrix [+RGD]/[−RGD] vs. Matrigel. Red arrows mark early organoids. (g) Brightfield (BF) and confocal microscopy images of an organoid in DyNAtrix [+RGD]. A comparison with organoids in Matrigel is shown in Supplementary Figure S17.*

Discussion

In this report, we have illustrated the power of DNA nanotechnology for soft materials engineering toward programmable and adaptive 3D cell culture matrices. The key feature of DNA is its unique potential for rational material design, allowing researchers to directly translate computationally predictable molecular properties into macroscopic material features: we show that the sequence and complexity of combinatorial crosslinker libraries (CCLs) determine network formation (Figure 2), thermodynamic stability (Figure 2b, Figure 3a), and elasticity (Figure 2c); stress relaxation crosslinkers (SRCs) control the (nano)mechanical stability (Figure 3); heat-activated crosslinkers (HACs) demonstrate customizable binding kinetics, which is critical for homogeneous cell encapsulation under optimal culture conditions (Figure 4). The concepts of CCLs, SRCs, and HACs can be combined, and the materials' modularity allows future upgrades with supplementary DNA components that either tweak mechanical properties or introduce entirely new features. Achieving this level of control helps mimic many of the properties of biological tissues and naturally-derived matrices, but in a fully synthetic and compositionally defined material. This improves reproducibility and reduces biological complications and regulatory hurdles in the field of regenerative medicine. DyNAtrix exhibits high cyto- and hemocompatibility, is self-healing, and suitable for injection and 3D extrusion printing. All of its components can be easily sterilized by filtration or alcohol treatment and stored (ready-to-use) for years.

DNA-based soft materials with remarkable adaptive properties had been previously reported[5,8,52]. However, surprisingly few studies had explored their use in 3D cell and tissue culture[53–55]. Problems relating to high required DNA content, premature gel degradation, and seamless integration with existing cell culture workflows had remained largely unsolved. In the present study we show that the combination of UHMW polymer backbone with CCLs enables very low DNA concentrations—up to 2 orders of magnitude lower than previously reported synthetic DNA-crosslinked gels. This approach gives access to

soft gels with elastic moduli in the range of 1–500 Pa, which are suitable for the study of many mechano-sensitive stem cell and organoid systems[56]. The lower end of the stiffness regime is particularly relevant for systems that benefit from ultra-soft environments, such as placenta organoids (as shown in this study) and stem cell models for embryo development. Due to the low DNA content, DyNAtrix is non-immunogenic, making it potentially suitable for medical applications, such as injectable cell-laden gels, drug release systems, or coatings for medical devices. The low DNA content also enables scalable high-throughput applications at relatively low material cost (Supplementary Table S2).

The construction of biocompatible hydrogels that combine dynamic viscoelastic properties with long-term stability in cell culture has been a major challenge[21]. Importantly, the degradation of DyNAtrix under mild cell-compatible conditions can be either inhibited (by supplementing actin) or promoted (by supplementing DNase I). Actin protection—or the use of serum-free media—allows cell culture for at least two weeks, which is a new record for DNA-crosslinked ECM mimics. Such long culture times are critical for future studies on human organoid systems. The nuclease/actin-regulated deconstruction of DyNAtrix represents an externally controllable alternative to the commonly relied-upon matrix degradation by cell-secreted matrix-metalloproteinases.

Previous studies had demonstrated control over stress relaxation via chemical modifications to the polymer scaffold or side groups[26,57–60]. Moreover, a DNA-crosslinked hydrogel had been shown to exhibit temperature-dependent stress-relaxation. In cell culture, however, temperature cannot be altered at will, and the effects of chemical matrix modifications on cell development can be difficult to disentangle from pure stress relaxation effects[61]. With the help of SRCs, for the first time the stress relaxation of a material can be adjusted systematically over 3 orders of magnitude by altering merely a few nucleobases on the DNA crosslinker sequence. The effects of different stress-relaxation times on the development of various cell and organoid models is subject of ongoing studies in our lab.

In summary, DyNAtrix allows a simple yet fully controlled noncovalent mix-and-match approach to matrix engineering. DNA modules and polymer backbones with different properties can be deployed in various combinations. For example, a HAC-crosslinked MeRPy gel can be further upgraded with fluorescent DNA stress sensors[62,63] to shed light onto the mechanical interactions of cells with their environment. DNA aptamers can be integrated to scavenge (or gradually release) specific biomolecules. Such modules can be activated on demand (e.g., by temperature), modified (e.g., by hybridization), and subsequently released off the polymer scaffold (e.g., by restriction enzymes). In the future, DyNAtrix could be autonomously controlled by molecular logic gates and synthetic regulatory circuits based on DNA strand displacement cascades[64,65]. We therefore envision this novel class of bioengineered materials to create unprecedented options for 3D cell and organoid culture and a range of other biomedical applications.

Acknowledgements

E.K. acknowledges funding by the Federal Ministry of Education and Research of Germany (BMBF) in the program NanoMatFutur (grant no. 13XP5098). The authors thank the medical faculty at the University Hospital Dresden for providing MSCs, and CRTD Stem Cell Engineering Facility for providing hiPSCs. We thank Aukha Stoppa, Dr. Yanuar Dwi Putra Limasale, Prannoy Seth, and Dr. Valentina Magno for helpful discussions. We also thank Dr. Ron Orbach, Dr. Agnes Kriegne Toth-Petroczy, Dr. Michele Marass, and Prof. Boris Rybtchinski for giving valuable feedback on the paper draft.

Author contributions

E.K. conceived the project. Y.-H.P., K.G., S.K.H., and E.K. designed the experiments. Y.-H.P. carried out sequence design, rheological experiments, gelation, MSC and hiPSC culture. S.K.H. carried out polymer synthesis and characterization, as well as MDCK culture and imaging. K.G. carried out DNA sequence design, thermodynamic predictions and early gelation experiments. A.R. performed peptide synthesis and characterization. G.K.A. helped plan and interpret rheological experiments. M.M. and S.K.H. carried out and analyzed blood incubation experiments. S.K.H., Y.-H.P. and C.G. helped plan, carry out and interpret trophoblast culture experiments. S.B. carried out and analyzed asymmetrical flow field-flow fractionation experiments. A.H. developed the genetically modified MDCK cells and helped with data analysis. C.W.

helped plan and interpret matrix engineering and cell culture experiments. Y.-H.P. and E.K. wrote the initial manuscript draft. All authors discussed the results and helped revise the manuscript.

Competing interests

E.K., Y.-H.P., K.G., and S.K.H. have filed a patent application for various aspects of this work.

References

1.	Du, X., Zhou, J., Shi, J. & Xu, B. Supramolecular Hydrogelators and Hydrogels: From Soft Matter to Molecular Biomaterials. *Chem Rev* **115**, 13165–13307 (2015).

2.	Voorhaar, L. & Hoogenboom, R. Supramolecular polymer networks: hydrogels and bulk materials. *Chem Soc Rev* **45**, 4013–4031 (2016).

3.	Krieg, E., Bastings, M. M. C., Besenius, P. & Rybtchinski, B. Supramolecular Polymers in Aqueous Media. *Chem Rev* **116**, 2414–2477 (2016).

4.	Goor, O. J. G. M., Hendrikse, S. I. S., Dankers, P. Y. W. & Meijer, E. W. From supramolecular polymers to multi-component biomaterials. *Chem Soc Rev* **46**, 6621–6637 (2017).

5.	Gačanin, J., Synatschke, C. v & Weil, T. Biomedical Applications of DNA-Based Hydrogels. *Adv Funct Mater* **30**, 1906253 (2020).

6.	Simmel, F. C. & Schulman, R. Self-organizing materials built with DNA. *MRS Bull* **42**, 913–919 (2017).

7.	Jiang, F. X., Yurke, B., Firestein, B. L. & Langrana, N. A. Neurite Outgrowth on a DNA Crosslinked Hydrogel with Tunable Stiffnesses. *Ann Biomed Eng* **36**, 1565 (2008).

8.	Kahn, J. S., Hu, Y. & Willner, I. Stimuli-Responsive DNA-Based Hydrogels: From Basic Principles to Applications. *Acc Chem Res* **50**, 680–690 (2017).

9.	Previtera, M. L., Chippada, U., Schloss, R. S., Yurke, B. & Langrana, N. A. Mechanical Properties of DNA-Crosslinked Polyacrylamide Hydrogels with Increasing Crosslinker Density. *Biores Open Access* **1**, 256–259 (2012).

10.	Guo, W. *et al.* pH-Stimulated DNA Hydrogels Exhibiting Shape-Memory Properties. *Advanced Materials* **27**, 73–78 (2015).

11.	Xing, Y. *et al.* Self-Assembled DNA Hydrogels with Designable Thermal and Enzymatic Responsiveness. *Advanced Materials* **23**, 1117–1121 (2011).

12.	Guo, W. *et al.* Switchable Bifunctional Stimuli-Triggered Poly-N-Isopropylacrylamide/DNA Hydrogels. *Angewandte Chemie International Edition* **53**, 10134–10138 (2014).

13.	Fang, X. & Tan, W. Aptamers Generated from Cell-SELEX for Molecular Medicine: A Chemical Biology Approach. *Acc Chem Res* **43**, 48–57 (2010).

14. Cangialosi, A. *et al.* DNA sequence–directed shape change of photopatterned hydrogels via high-degree swelling. *Science (1979)* **357**, 1126–1130 (2017).

15. Lu, C.-H., Guo, W., Hu, Y., Qi, X.-J. & Willner, I. Multitriggered Shape-Memory Acrylamide–DNA Hydrogels. *J Am Chem Soc* **137**, 15723–15731 (2015).

16. Xing, Y. *et al.* Self-Assembled DNA Hydrogels with Designable Thermal and Enzymatic Responsiveness. *Advanced Materials* **23**, 1117–1121 (2011).

17. Song, P. *et al.* DNA Hydrogel with Aptamer-Toehold-Based Recognition, Cloaking, and Decloaking of Circulating Tumor Cells for Live Cell Analysis. *Nano Lett* **17**, 5193–5198 (2017).

18. Freeman, R. *et al.* Instructing cells with programmable peptide DNA hybrids. *Nat Commun* **8**, 15982 (2017).

19. Li, C. *et al.* A Writable Polypeptide–DNA Hydrogel with Rationally Designed Multi-modification Sites. *Small* **11**, 1138–1143 (2015).

20. Wei, Y. *et al.* Programmable DNA Hydrogels as Artificial Extracellular Matrix. *Small* **18**, 2107640 (2022).

21. Qazi, T. H. *et al.* Programming hydrogels to probe spatiotemporal cell biology. *Cell Stem Cell* **29**, 678–691 (2022).

22. Gjorevski, N. *et al.* Designer matrices for intestinal stem cell and organoid culture. *Nature* **539**, 560–564 (2016).

23. Magno, V., Meinhardt, A. & Werner, C. Polymer Hydrogels to Guide Organotypic and Organoid Cultures. *Adv Funct Mater* **30**, 2000097 (2020).

24. Chaudhuri, O. Viscoelastic hydrogels for 3D cell culture. *Biomater Sci* **5**, 1480–1490 (2017).

25. Chaudhuri, O., Cooper-White, J., Janmey, P. A., Mooney, D. J. & Shenoy, V. B. Effects of extracellular matrix viscoelasticity on cellular behaviour. *Nature* **584**, 535–546 (2020).

26. Lou, J., Stowers, R., Nam, S., Xia, Y. & Chaudhuri, O. Stress relaxing hyaluronic acid-collagen hydrogels promote cell spreading, fiber remodeling, and focal adhesion formation in 3D cell culture. *Biomaterials* **154**, 213–222 (2018).

27. Adebowale, K. *et al.* Enhanced substrate stress relaxation promotes filopodia-mediated cell migration. *Nat Mater* **20**, 1290–1299 (2021).

28. Chaudhuri, O. *et al.* Hydrogels with tunable stress relaxation regulate stem cell fate and activity. *Nat Mater* **15**, 326–334 (2016).

29. Aisenbrey, E. A. & Murphy, W. L. Synthetic alternatives to Matrigel. *Nat Rev Mater* **5**, 539–551 (2020).

30. Wang, H. & Heilshorn, S. C. Adaptable Hydrogel Networks with Reversible Linkages for Tissue Engineering. *Advanced Materials* **27**, 3717–3736 (2015).

31. Loebel, C., Rodell, C. B., Chen, M. H. & Burdick, J. A. Shear-thinning and self-healing hydrogels as injectable therapeutics and for 3D-printing. *Nat Protoc* **12**, 1521–1541 (2017).

32. Gaharwar, A. K. *et al.* Shear-Thinning Nanocomposite Hydrogels for the Treatment of Hemorrhage. *ACS Nano* **8**, 9833–9842 (2014).

33. Zhang, S. *et al.* A self-assembly pathway to aligned monodomain gels. *Nat Mater* **9**, 594–601 (2010).

34. Helena Andrade, Weilin Lin & Yixin Zhang. Specificity from nonspecific interaction: regulation of tumor necrosis factor-α activity by DNA. *J Biol Chem .* (2019).

35. Surana, S., Shenoy, A. R. & Krishnan, Y. Designing DNA nanodevices for compatibility with the immune system of higher organisms. *Nat Nanotechnol* **10**, 741–747 (2015).

36. Volpi, C. *et al.* High doses of CpG oligodeoxynucleotides stimulate a tolerogenic TLR9–TRIF pathway. *Nat Commun* **4**, 1852 (2013).

37. Akintayo, C. O., Creusen, G., Straub, P. & Walther, A. Tunable and Large-Scale Model Network StarPEG-DNA Hydrogels. *Macromolecules* **54**, 7125–7133 (2021).

38. Krieg, E. & Shih, W. M. Selective Nascent Polymer Catch-and-Release Enables Scalable Isolation of Multi-Kilobase Single-Stranded DNA. *Angewandte Chemie International Edition* **57**, 714–718 (2018).

39. Krieg, E. *et al.* A smart polymer for sequence-selective binding, pulldown, and release of DNA targets. *Commun Biol* **3**, (2020).

40. Aharoni, S. Intramolecular crosslinking. *Die Angewandte Makromolekulare Chemie* **62**, (1977).

41. Tobita, H. & Hamielec, A. E. Crosslinking kinetics in polyacrylamide networks. *Polymer (Guildf)* **31**, 1546–1552 (1990).

42. John, S. A unified view of polymer, dumbbell, and oligonucleotide DNA nearest-neighbor thermodynamics. *Proceedings of the National Academy of Sciences* **95**, 1460–1465 (1998).

43. Wallace, R. B. *et al.* Hybridization of synthetic oligodeoxyribonucleotides to Φ X 174 DNA: the effect of single base pair mismatch . *Nucleic Acids Res* **6**, 3543–3558 (1979).

44. Lin, D. C., Yurke, B. & Langrana, N. A. Mechanical Properties of a Reversible, DNA-Crosslinked Polyacrylamide Hydrogel . *J Biomech Eng* **126**, 104–110 (2004).

45. Xing, Z. *et al.* Microrheology of DNA hydrogels. *Proceedings of the National Academy of Sciences* **115**, 8137–8142 (2018).

46. Yue, L., Wang, S., Wulf, V. & Willner, I. Stiffness-switchable DNA-based constitutional dynamic network hydrogels for self-healing and matrix-guided controlled chemical processes. *Nat Commun* **10**, 4774 (2019).

47. Du, C. & Hill, R. J. Complementary-DNA-Strand Cross-Linked Polyacrylamide Hydrogels. *Macromolecules* **52**, 6683–6697 (2019).

48. Indana, D., Agarwal, P., Bhutani, N. & Chaudhuri, O. Viscoelasticity and Adhesion Signaling in Biomaterials Control Human Pluripotent Stem Cell Morphogenesis in 3D Culture. *Advanced Materials* **33**, 2101966 (2021).

49. Hatch, K., Danilowicz, C., Coljee, V. & Prentiss, M. Demonstration that the shear force required to separate short double-stranded DNA does not increase significantly with sequence length for sequences longer than 25 base pairs. *Phys Rev E* **78**, (2008).

50. Lazarides, E. & Lindberg, U. Actin Is the Naturally Occurring Inhibitor of Deoxyribonuclease I. *Proceedings of the National Academy of Sciences* **71**, 4742–4746 (1974).

51. Sheridan, M. A. *et al.* Establishment and differentiation of long-term trophoblast organoid cultures from the human placenta. *Nat Protoc* **15**, 3441–3463 (2020).

52. Li, J. *et al.* Functional nucleic acid-based hydrogels for bioanalytical and biomedical applications. *1410 | Chem. Soc. Rev* **45**, 1410 (2016).

53. Um, S. H. *et al.* Enzyme-catalysed assembly of DNA hydrogel. *Nat Mater* **5**, 797–801 (2006).

54. Li, C. *et al.* Rapid Formation of a Supramolecular Polypeptide–DNA Hydrogel for In Situ Three-Dimensional Multilayer Bioprinting. *Angewandte Chemie International Edition* **54**, 3957–3961 (2015).

55. Shao, Y., Jia, H., Cao, T. & Liu, D. Supramolecular Hydrogels Based on DNA Self-Assembly. *Acc Chem Res* **50**, 659–668 (2017).

56. Chowdhury, F. *et al.* Material properties of the cell dictate stress-induced spreading and differentiation in embryonic stem cells. *Nat Mater* **9**, 82–88 (2010).

57. McKinnon, D. D., Domaille, D. W., Cha, J. N. & Anseth, K. S. Biophysically Defined and Cytocompatible Covalently Adaptable Networks as Viscoelastic 3D Cell Culture Systems. *Advanced Materials* **26**, 865–872 (2014).

58. Diba, M. *et al.* Engineering the Dynamics of Cell Adhesion Cues in Supramolecular Hydrogels for Facile Control over Cell Encapsulation and Behavior. *Advanced Materials* **33**, 2008111 (2021).

59. Chaudhuri, O. *et al.* Substrate stress relaxation regulates cell spreading. *Nat Commun* **6**, 6365 (2015).

60. Lorenz, J. S. *et al.* Synthetic Transient Crosslinks Program the Mechanics of Soft, Biopolymer-Based Materials. *Advanced Materials* **30**, 1706092 (2018).

61. Ohira, M. *et al.* Star-Polymer–DNA Gels Showing Highly Predictable and Tunable Mechanical Responses. *Advanced Materials* **34**, 2108818 (2022).

62. Merindol, R., Delechiave, G., Heinen, L., Catalani, L. H. & Walther, A. Modular Design of Programmable Mechanofluorescent DNA Hydrogels. *Nat Commun* **10**, 528 (2019).

63. Zhang, Y., Ge, C., Zhu, C. & Salaita, K. DNA-based digital tension probes reveal integrin forces during early cell adhesion. *Nat Commun* **5**, 5167 (2014).

64. Cangialosi, A. *et al.* DNA sequence–directed shape change of photopatterned hydrogels via high-degree swelling. *Science (1979)* **357**, 1126–1130 (2017).

65. Seelig, G., Soloveichik, D., Zhang, D. Y. & Winfree, E. Enzyme-Free Nucleic Acid Logic Circuits. *Science (1979)* **314**, 1585–1588 (2006).