The Structural Layers of the Porcine Iris Exhibit Inherently Different Biomechanical Properties

Royston K. Y. Tan[1,2,3], Satish K. Panda[1,4], Fabian A. Braeu[1,2,3,5], Arumugam R. Muralidharan[2,3], Monisha E. Nongpiur[2,3], Anita S. Y. Chan[2,3], Tin Aung[2,3,6], Raymond P. Najjar[2,3,6,7], Michaël J.A. Girard[1,2,3,8]

1. Ophthalmic Engineering & Innovation Laboratory, Singapore Eye Research Institute, Singapore National Eye Centre, Singapore
2. Singapore Eye Research Institute, Singapore National Eye Centre, Singapore
3. Duke-NUS Medical School, Singapore
4. Department of Mechanical Engineering, Indian Institute of Technology, Bhubaneswar, India
5. Critical Analytics for Manufacturing Personalized-Medicine, Singapore-MIT Alliance for Research and Technology, Singapore
6. Department of Ophthalmology, Yong Loo Lin School of Medicine, National University of Singapore and National University Health System, Singapore
7. Centre for Innovation & Precision Eye Health, Yong Loo Lin School of Medicine, National University of Singapore, Singapore
8. Institute of Molecular and Clinical Ophthalmology, Basel, Switzerland

Keywords:	Permeability, stress relaxation, angle closure, iris stroma, dilator muscle
Word Count:	3959 (Manuscript text) 250 (Abstract text)
Tables:	1
Figures:	4
Corresponding Author:	Michaël J.A. Girard Ophthalmic Engineering & Innovation Laboratory Singapore Eye Research Institute The Academia 20 College Road, Discovery Tower Level 6 Singapore 169856 mgirard@ophthalmic.engineering

The authors have no proprietary or commercial interest in any materials discussed in this article.

Abstract

Purpose: To isolate the structural components of the *ex vivo* porcine iris tissue and to determine their biomechanical properties.

Methods: The porcine stroma and dilator tissues were separated, and their dimensions were assessed using optical coherence tomography (OCT). The stroma underwent flow test ($n = 32$) to evaluate for permeability using Darcy's Law ($\Delta P = 2000$ Pa, $A = 0.0391$ mm^2), and both tissues underwent stress relaxation experiments ($\varepsilon = 0.5$ with initial ramp of $\delta\varepsilon = 0.1$) to evaluate for their viscoelastic behaviours ($n = 28$). Viscoelasticity was characterised by the parameters β (half width of the Gaussian distribution), τ_m (mean relaxation time constant), E_0 (instantaneous modulus) and E_∞ (equilibrium modulus).

Results: For the stroma, the hydraulic permeability was $9.49 \pm 3.05 \times 10^{-5}$ mm^2/Pa·s, and the viscoelastic parameters were $\beta = 2.50 \pm 1.40$, and $\tau_m = 7.43 \pm 4.96$ s, with the two moduli calculated to be $E_0 = 14.14 \pm 6.44$ kPa and $E_\infty = 6.08 \pm 2.74$ kPa. For the dilator tissue, the viscoelastic parameters were $\beta = 2.06 \pm 1.33$ and $\tau_m = 1.28 \pm 1.27$ s, with the two moduli calculated to be $E_0 = 9.16 \pm 3.03$ kPa and $E_\infty = 5.54 \pm 1.98$ kPa.

Conclusion: We have established a new protocol to evaluate the biomechanical properties of the structural layers of the iris. Overall, the stroma was permeable and exhibited smaller moduli than those of the dilator muscle. An improved characterization of iris biomechanics may form the basis to further our understanding of angle closure glaucoma.

Introduction

Research in angle closure glaucoma explores a myriad of possible risk factors and characteristics that are associated with the disease, ranging from genetic studies[1-5] to anatomical measurements[6-10] and computational studies[11-15]. Being able to predict whether a patient will be afflicted with angle closure is paramount, so that preventive measures can be undertaken.[16, 17]. Similarly, clinical examinations can identify patients with a higher risk of developing angle closure so that laser iridotomy can be done to widen the drainage angle, lowering the chance of glaucoma development in many instances.

Whilst clinical examinations are crucial to aid early angle closure detection[18, 19], the main pathology of angle closure disease is apposition of the peripheral iris to the trabecular meshwork impeding aqueous outflow. It is believed that dynamic movement of the iris, primarily the way the iris dilates, plays a role in angle closure pathogenesis[20-22]. Modern technology can also play its part to study the iris using computational simulations in the form of biomechanical analyses. An example would be to input ocular parameters from a patient's optical coherence tomography (OCT) scan to evaluate how hypothetical changes in iris stiffness could influence angle closure development. These biomechanical models could evaluate the physics and predict the behaviour of the eye in any prescribed scenarios that would otherwise be difficult to analyse *in vivo*.

For example, Wang et al.[23] explored aqueous humour dynamics to investigate its influence on the iris and pupillary block in angle closure. This was done using a physical model of the anterior chamber and tracer particles together with computational simulations. Huang et al.[24] and Heys et al.[25] modelled the iris-lens interactions to determine the influence of different morphological parameters (i.e. iris thickness, pupil size, anterior chamber depth, lens diameter, etc.) affecting pupillary block that would otherwise be impossible to determine experimentally. Models could also be invaluable to interpret clinical data; from dynamic OCT images, one could extract parameters such as iris stiffness and permeability[11, 12] in addition to

more traditional morphologic parameters in order to better describe the structural and biomechanical phenotype of angle closure.

However, current computational models[26-29] of the iris are still limited in describing the physiological behaviour *in vivo*, particularly outflow of aqueous during pupil constriction and dilation. The inability to model volume changes of the iris severely limits research capabilities in angle closure, since the primary mechanism is pupillary block by the iris tissue. Our group had also previously attempted to describe the iris as a biphasic tissue; with a permeable stroma to allow for fluid exchange, and a non-linear hyperelastic model to describe both the solid phases of the stroma and the iris muscles[11, 30, 31] However, to date, no attempts were made to isolate these tissues experimentally to describe their individual biomechanical behaviours, partly due to the difficulty in separating them *ex vivo*.

The aim of this study was to characterise the biomechanics of the main structural components of the iris (stroma and dilator muscle) experimentally. Specifically, we aimed to determine (1) the permeability of the iris stroma using a refined experimental set-up, and (2) the viscoelastic properties of both the stroma and dilator muscle through stress relaxation testing.

Methods

For this study, we isolated two of the primary load bearing components of the iris: the stroma and the dilator muscle. The iris stroma is composed of a sponge-like meshwork[32], porous in the middle to allow fluid movements within the anterior volume. It is also composed of fibroblasts and melanocytes that form a cellular matrix, along with vasculature, neural elements and a connective tissue extracellular matrix[33]. We isolated the stroma tissue to determine its fluid permeability, as well as the viscoelastic properties of the solid matrix.

On the other hand, the dilator muscle is made of smooth muscle cells, arranged in bundles separated by tissue septae. These interdigital systems of muscle fibres are innervated from autonomic nerve fibres within these tissue septae, communicating through other muscle

fibres through large gap junctions. The surrounding cytoplasm contains a uniform distribution of myofilaments that contribute to the mechanical strength of the muscle. As the dilator muscle is impermeable due to the presence of tissue septae and gap junctions, only its viscoelastic properties would be investigated. As the iris posterior pigmented epithelium is a component of the blood aqueous barrier, it was removed to study the stromal permeability.

Tissue separation

Sixty freshly enucleated porcine eyes were purchased from a local porcine abattoir. (Singapore Food Industries Pte Ltd., Singapore). The fresh porcine eyes were transported back to the laboratory where experiments were completed within 24 hours post-mortem.

The procedure to separate the stroma and dilator tissues were as follows. First, for each eye, the entire iris was isolated from the porcine globe, and the iris pigmented epithelium gently scraped off. Next, a discontinuous cut was made to the iris. Using a mixture of tying forceps (2-500-2E, Duckworth & Kent, Hertfordshire, UK), jewellers forceps (2-900E, Duckworth & Kent, Hertfordshire, UK) and Chihara conjunctival forceps (2-500-4E, Duckworth & Kent, Hertfordshire, UK), the dilator muscle was gently lifted and peeled away from the stroma inward radially up to the sphincter, where the piece of tissue was cut off using a pair of vannas scissors (1-111, Duckworth & Kent, Hertfordshire, UK). When isolating the stroma, the dilator was removed in pieces to retain as much stroma tissue as possible, whereas when isolating the dilator muscle, care was taken to ensure no holes were present in the isolated sample, even though small amounts of stroma tissue may still be present. The samples were processed and stored using phosphate buffer saline without calcium or magnesium, diluted from 10× stock solution (17-517Q, Lonza Pharma & Biotech, Maryland, USA).

Stroma permeability study

Isolated stroma samples ($n = 32$) underwent a flow experiment to assess their permeability. The principle of the permeability experiment was similar to that described in our

previous study, whereby homogenization of the Navier-Stokes equation[34, 35] will yield Darcy's law[36, 37] :

$$Q = \frac{\kappa A \Delta P}{\mu \Delta x} \ (\text{mm}^3/s) \tag{1}$$

where Q is the flow rate (mm³/s), κ is the permeability (mm²), A is the surface area of flow (mm²), ΔP is the pressure difference across the tissue (Pa), μ is the dynamic viscosity of the fluid (Pa·s) and Δx is the thickness of the tissue (mm). Our measurement parameter is the hydraulic permeability, used in similar biphasic biological tissue experimentation such as the meniscus[38]. It is defined by the permeability of the tissue divided by the viscosity of the fluid (here: phosphate buffered saline or PBS):

$$\text{Hydraulic Permeability} = \frac{\kappa}{\mu} = \frac{Q \Delta x}{A \Delta P} \ (\text{mm}^2/[\text{Pa} \cdot s]) \tag{2}$$

Using Darcy's law, it was possible to obtain the hydraulic permeability of the iris stroma by setting a specific pressure difference and measuring the resulting flow rate. We designed an experimental setup consisting of a PBS column (30 mL syringe reservoir), itself connected by a tube (internal diameter (ID) = 1.00 mm) to a custom 3D-printed holder where the stroma tissue was positioned (**Figure 1**). The cross-sectional area for flow was measured using optical coherence tomography (OCT) and estimated as an ellipse (**Figure 1B and 2A**). The syringe reservoir was sufficiently large to prevent any noticeable drops in fluid level (< 1 mm) from direct flow or evaporation. The vertical height between the stroma tissue and the fluid level was approximately 204 mm to provide a pressure difference of approximately 2,000 Pa, or 15 mmHg. Outflow from the holder was through the large tube (ID = 1.00 mm), followed by a much smaller tube (ID = 0.397 mm) on the horizontal plane for the measurement of flow rate (**Figure 1C**).

The tubes of different inner diameters were selected for the following reasons: 1) The larger tube (ID = 1.00 mm) was sufficiently large that the tube resistance was negligible; 2)

The smaller tube allowed for accurate measurement of flow rate, which was measured by the time taken for 1.237 mm^3 of fluid to flow through the stroma tissue (10 mm of the tube). A smaller tube also created outflow resistance (positive pressure), which was taken into account during the calculations. The hydraulic permeability values were reported as the mean ± standard deviation, with outliers excluded beyond 3 standard deviations.

Stress relaxation study

Iris stroma ($n = 28$) and dilator muscles ($n = 28$) underwent stress relaxation tests (i.e. stress response over time over a constant strain) using a uniaxial testing machine (5542A, Instron Corp, Norwood, MA, USA). The tested length (in the direction of the uniaxial stretch) was 1.5 mm for all stroma and dilator muscle samples, with the cross-sectional areas evaluated using OCT scans performed for each sample (**Figure 2C**) prior to the stress relaxation tests. As the iris tissues typically exhibit extremely large strains over several seconds (up to the second order of magnitude in percentage), we decided to perform the stress relaxation experiment at 50% strain. The samples were extended with a strain rate of 10% per second for 5.0 seconds and held at constant strain (ε_0) for the next 300 seconds (**Figure 3**). All samples were clamped using sandpaper to prevent slipping (**Figure 3C**). Preconditioning was performed for 25 cycles from 0% to a maximum of 25% strain at a rate of 1% per second. Overall, samples were found to exhibit little to no hysteresis.

To quantify the relaxation behaviour of the iris tissues, we used the linear viscoelastic theory initially described by Fung[39] and the same mathematical model as in our previous study[40]. When subjected to a constant strain $\varepsilon_0 = 0.5$, the viscoelastic material will exhibit a stress relaxation response expressed as:

$$\sigma(\varepsilon_0, t) = G(t) \cdot \sigma^e(\varepsilon_0) \tag{3}$$

in which G is the reduced relaxation function, a normalized function of time, and σ^e is the elastic response function of the applied strain ε_0. The tensile stress generated instantaneously

at $t = 0$ is the peak stress, where $G(0) = 1$ and $\sigma^e(\varepsilon_0) = E_0 \varepsilon_0$, where E_0 is the instantaneous elastic modulus of the material. The function G can be expressed as:

$$G(t) = \frac{1 + c \int_{-\infty}^{+\infty} \Phi(\log \tau) \exp\left(-\frac{t}{\tau}\right) d\log\tau}{1 + c \int_{-\infty}^{+\infty} \Phi(\log \tau) d\log\tau} \tag{4}$$

where c is the relaxation ratio determined by $c = G(0)/G(\infty) - 1$, τ is the relaxation time[41] and Φ is the log distribution function of the relaxation time, which satisfies $\int_{-\infty}^{+\infty} \Phi(\log \tau) d\log\tau = 1$. We modelled the relaxation process exhibiting a Gaussian distribution in the logarithm of the relaxation time which is expressed as:

$$\Phi(\log \tau) = \frac{1}{\beta\sqrt{\pi}} \exp\left[-\frac{(\log t - \log \tau_m)^2}{\beta^2}\right] \tag{5}$$

where β is the half width of the Gaussian distribution[42] and τ_m is the mean relaxation time constant. The variable $z = \log(\tau/\tau_m)$ can be introduced[43] in Eq. 5 that satisfies $dz = d\log\tau$. Simplification of the equation yields the stress relaxation response as:

$$\sigma(t) = \frac{\sigma_0}{1+c}\left(1 + \frac{c}{\beta\sqrt{\pi}} \int_{-\infty}^{+\infty} \exp\left(-\frac{z^2}{\beta^2} - \frac{t}{\tau_m 10^z}\right) dz\right) \tag{6}$$

where σ_0 is defined as the peak stress directly obtained from the experimental data.

Using MATLAB (Version 2020b, Mathworks, Inc., Natick, MA, USA), we developed a custom algorithm to reduce noise by signal averaging and performed curve fitting of the experimental data to Eq. 6 using differential evolution[44] to estimate the three model parameters: c, β and τ_m. The two elastic moduli, E_0 and E_∞ can also be determined by

$$E_0 = \frac{\sigma_0}{\varepsilon_0} \tag{7}$$

$$E_\infty = \frac{E_0}{1+c} \tag{8}$$

OCT tissue measurements

Images obtained from this study were performed using OCT (RTVue-100, Optovue Inc, Fremont, CA, USA). The stroma and dilator tissue samples were placed on a glass slide with minimal liquid to reduce influence from liquid refraction. The acquisition mode was the 8-line radial scan (each cross-sectional scan was 22.5° apart). The images were processed using Photoshop (v2022, Adobe Inc, CA, USA) and MATLAB. Thickness and cross-sectional area were evaluated using the scale from the OCT machine provided in the images (**Figure 2**).

Stroma permeability study: Three random images were selected per sample to determine the tissue thickness after the experiment was completed for a better reflection of the tissue state during the experiment. An area of 45 × 100 pixels was selected for each image and manually converted to binary black and white using photoshop, with the average of the 3 images computed for the tissue thickness (**Figure 3A**).

Stress relaxation study: Here, tissue thickness was measured prior the experiment. It was important to position the tissue uniformly so that the horizontal width of the tissue would be accurately reflected and measured by the cross-sectional images. The entire cross-section was manually converted to binary black and white using photoshop, with the width and cross-section computed for analysis (**Figure 3B**).

Statistical Analysis

A two-sample t-test (two-tailed, unequal variance) was employed to compare the five material parameters (c, β, τ_m, E_0 and E_∞) between the dilator muscle and stroma groups (n = 28), to evaluate whether the tissues were inherently different.

Results

Stroma permeability study

The 3D tissue holder area was evaluated using OCT and determined to be 0.0391 mm^2. The average thickness of the stroma tissue samples was 0.152 ± 0.0259 mm. The PBS flow through the stroma samples was found to be slow and laminar, with a Reynold's number

<1, thus satisfying the Darcy's law approximation. Specifically, flow through the experimental setup was 0.00500 ± 0.00191 mm³/s, exerting minimal outlet pressure (7.65 ± 2.93 Pa). The hydraulic permeability of the porcine iris stroma was then calculated as 9.49 ± 3.05 × 10⁻⁵ mm²/Pa·s, with a total of 31 samples evaluated, with 1 outlier excluded from the analysis.

Stress relaxation study

Dilator muscle tissue. The average width, thickness and cross-sectional area of the dilator tissue samples were 3.78 ± 0.74 mm, 0.192 ± 0.028 mm and 0.733 ± 0.183 mm² respectively. The biomechanical properties of the dilator muscle, as determined by the differential evolution algorithm, were c = 1.41 ± 0.60, β = 2.50 ± 1.40, and τ_m = 7.43 ± 4.96 s, with the two moduli calculated to be E_0 = 14.14 ± 6.44 kPa and E_∞ = 6.08 ± 2.74 kPa.

Stroma tissue. The average width, thickness and cross-sectional area of the stroma tissue samples were 3.71 ± 0.70 mm, 0.220 ± 0.04 mm and 0.830 ± 0.263 mm² respectively. The biomechanical properties of the stroma, as determined by the differential evolution algorithm, were c = 0.707 ± 0.38, β = 2.06 ± 1.33, and τ_m = 1.28 ± 1.27 s, with the two moduli calculated to be E_0 = 9.16 ± 3.03 kPa and E_∞ = 5.54 ± 1.98 kPa.

Overall, the dilator muscle tissue exhibited greater E_0 (p < 0.001) compared to the stroma tissue but did not show significant difference in E_∞ (p = 0.41). The dilator muscle tissue also showed greater c and τ_m (p < 0.001) but no significant difference in β (p = 0.23).

Discussion

In this study, we identified the stroma and dilator muscles as two structural tissues influencing iris biomechanical behaviour. To the best of our knowledge, the biomechanics of such tissue layers (when isolated) had not been studied, and we proposed herein a methodology for doing so. Overall, we found that (1) The iris stroma was highly permeable (as opposed to the dilator); (2) the instantaneous modulus (but not the equilibrium modulus) of the dilator muscle was significantly higher than that of the stroma; and that (3) the stroma exhibited

a significantly shorter mean relaxation time constant as compared to the dilator muscle. Our work may ultimately help us identify an 'healthy' range for iris biomechanical properties in human, any deviations from which may be associated with the development of angle closure.

The dilator muscle is stiffer than the stroma tissue in a healthy iris

In this study, we found that the instantaneous modulus of the dilator muscle was significantly higher than that of the stroma tissue – but this was not true for the equilibrium modulus. Such a difference could potentially be explained by the different fibres that constitute both tissues, including stiffer smooth muscle fibres for the dilator tissue, but a sparse collagen fibre meshwork permeable to aqueous humour for the stroma, thus allowing for greater compliance. This softer stroma layer is essential for iris accommodation, since the contraction forces (for dilation) originate from a much thinner muscle layer. Recently, it was reported that glaucomatous eyes, including eyes with primary open angle glaucoma and primary angle closure glaucoma, generally display a reduction in the pupillary light response amplitudes[45-47]. Although such alterations in the pupillary light response can be attributed to ganglion cell loss or dysfunction in the disease, we hypothesise that decreased muscle innervation and changes in biomechanical behaviour such as increased stroma stiffness, are additional underlying biological changes that may contribute to pupillometric alterations in response to light for patients with glaucoma.

The iris accommodates movement rapidly to reach biomechanical equilibrium

In this study, we found that the mean relaxation time constants for both the dilator muscle (7.43 ± 4.96 s) and stroma (1.28 ± 1.27 s) were relatively small. These features may reflect the highly dynamic physiological properties of the iris that is constantly changing in shape in response to the accommodation reflex or the lighting environment. This is in contrast to other ocular tissues such as the corneo-scleral shell that exhibits considerably smaller changes in tissue stretch. The viscoelastic behaviour of stiffer, load bearing structural tissues (in terms of intraocular pressure) such as the sclera exhibits high moduli and greater mean

relaxation time constant, whereas the small amount of muscle fibres orchestrating fine and rapid pupil dilator changes result in much smaller moduli (E_∞ = 3,300 kPa for rabbit sclera vs. 5.54 kPa for iris stroma) and short mean relaxation time constants (τ_m = > 10s for rabbit sclera vs. < 10s for iris tissues)[40].

The results also show a shorter mean relaxation time constant for the stroma tissue, with it seemingly behaving close to a linear elastic material (**Figure 4**). This could be due to its porous nature and composition; most of the stroma is composed short collagen fibrils meshwork with fibroblasts and melanosomes[33, 48]. The stroma matrix deforms rapidly in both extension and compression as aqueous humour gets quickly displaced through its pores, reaching structural equilibrium within seconds. Conversely, the dilator muscle takes longer to reach biomechanical equilibrium, the simple bundles of smooth muscle cells[33] containing actin and myosin filaments passively extend irreversibly, until the filaments are activated to overlap and contract during pupil constriction.

Changes in iris tissue properties can affect iris curvature and induce angle closure

In angle closure, the behaviour and shape of the iris in the mydriatic state affects the chamber angle. Patients with angle closure glaucoma were found to have anterior convex-to-convex (in dark and light) iris configuration[49], possibly signalling a biomechanical mismatch between the iris stroma and muscle tissues. There are several possibilities leading to an anteriorly convex iris; first, if the composition of the iris stroma changes to an increase tissue stiffness, the decreased compression could result in the muscle region shortening more than the stroma. Second, another possible outcome of iris stroma composition change is an increased matrix to aqueous ratio, reducing the level of compressibility and resulting in bowing. Third, a change in stroma permeability could limit the outflow of aqueous out of the iris, thus limiting volume changes within the stroma matrix. This change would likely be attributed to morphological changes at the anterior boundary layer, where the density of the tissue is the primary limiting factor restricting aqueous fluid migration. Finally, a mismatch in biomechanical behaviour between the stroma and surrounding muscles, such as an increase in stroma mean

relaxation time constant, could affect how the iris behaves in unison. In the case of pupil dilation, an anteriorly convex iris could result initially before the stresses are evenly distributed, only becoming less convex over a longer period of time.

The lack of iris features such as crypts and furrows[50] has been linked to the development of angle closure. The presence of crypts, which are diamond shape lacunae causing discontinuities on the anterior boundary layer, could facilitate aqueous humour movement across the stroma tissue and prevent the iris from bulging and bowing during pupil dilation. The presence of lower number of crypts has been found to be proportional to the incidence of angle closure in patients[51]. Furrows, which are circumferential creases where the iris folds at the periphery during pupil dilation, could also be associated with the prevalence of angle closure. With longer furrow lengths, it was found that the irides were more likely to have greater volume and less aqueous loss during pupil dilation[52]. These iris features provide not only greater insight into their associations with angle closure, but also possible reasons for the deviations from mean iris behaviour that could be quantified biomechanically.

Our work allows us to better describe the passive extensive behaviour of the ex vivo porcine iris

This study represented the iris as a structural bilayer; the anterior stroma as a solid-liquid biphasic tissue with solid viscoelastic properties and fluid permeability, and the posterior dilator muscle as a solid with viscoelastic properties. We believe this captures the unique behaviour of the iris, which is unlike many other tissues in the body. The iris experiences large deformations created by the posteriorly positioned muscles, coupled with interaction with the surrounding fluid medium from the partially porous and anteriorly positioned stroma. By isolating the individual primary load bearing layers, it was possible to accurately determine their biomechanical behaviour. Previous research into the iris took different approaches: Whitcomb et al. performed nano-indentation of the porcine iris anterior and posterior segments to determine overall iris stiffness[28], while Narayanaswamy et al. used atomic force microscopy[53]. There are some anatomical and biomechanical points to consider for these

approaches. First, for the anterior indentation, the small level of indentation in a porous stroma could effectively be flexing fibres between the gaps of the tissue, undermining the true tissue stiffness. Second, when the antagonistic muscles contract, the iris is either in a compressive or extensive state in the radial direction, orthogonal to the direction of indentation. The assumption of an isotropic tissue may not be biomechanically accurate to represent the radially oriented dilator muscles, and it may be critical to test the tissues according to their preferred fibre orientations as we had performed herein.

Limitations

In this study, several limitations warrant further discussion. First, a more complete biomechanical breakdown of the iris tissue properties should also include the sphincter muscle. The omission of the sphincter muscle was due to the difficulty in isolating this circular tissue. However, it is theoretically possible to equate the passive biomechanical behaviour of both the dilator and sphincter muscle since they are antagonistic tissues. The differences in speeds of pupil constriction and dilation suggest possible small tissue differences, perhaps due to different nerve innervations, but microscopic studies have shown that these muscles are typical smooth muscles[33], and hence are likely to exhibit similar biomechanical properties.

Second, a limitation of experimental *ex vivo* biomechanical determination of tissues is the inability to determine active muscle properties. Changes in pupil consists of at least three tissue changes; pupil constriction requires active sphincter muscle contraction, dilator muscle extension (relaxation) and stroma extension, whilst pupil dilation requires active dilator muscle contraction, sphincter muscle extension (relaxation) and stroma compression. Whilst it would be a logistical challenge to determine active muscle forces by keeping the tissues alive, such forces might be able to be estimated with *in vivo* imaging such as OCT.

Third, the stroma undergoes both compressive and tensile stresses with pupillary changes, however, on our study we only performed tensile experiments. In addition, permeability could be both affected by tensile and compressive stress, as is true for other soft

tissues such as cartilage[54, 55]. Novel mechanical test equipment might need to be designed to assess such properties.

Conclusion

Determining the biomechanical properties of the individual iris layers may be invaluable in uncovering how and why the iris deforms in the anterior chamber in normal and eyes with angle closure. This porcine study establishes a protocol to be replicated on human iris tissues, by isolating the individual components for analysis. In learning more about iris biomechanics, we hope to establish a better understanding of the pathogenesis of angle closure glaucoma.

Acknowledgments

The authors thank the donors of the National Glaucoma Research, a program of the BrightFocus Foundation, for support of this research (G2021010S [MJAG]); the NMRC-LCG grant 'TAckling & Reducing Glaucoma Blindness with Emerging Technologies (TARGET)', award ID: MOH-OFLCG21jun-0003 [MJAG]; and the "Retinal Analytics through Machine learning aiding Physics (RAMP)" project that is supported by the National Research Foundation (NRF2019-THE002-0006 [MJAG]).

References

1.   Wang J, Yusufu M, Khor CC, Aung T, Wang N. The genetics of angle closure glaucoma. *Experimental eye research* 2019;189:107835.
2.   Nongpiur ME, Khor CC, Jia H, et al. ABCC5, a gene that influences the anterior chamber depth, is associated with primary angle closure glaucoma. *PLoS genetics* 2014;10:e1004089.
3.   Vithana EN, Khor C-C, Qiao C, et al. Genome-wide association analyses identify three new susceptibility loci for primary angle closure glaucoma. *Nature genetics* 2012;44:1142-1146.
4.   Suri F, Yazdani S, Chapi M, et al. COL18A1 is a candidate eye iridocorneal angle-closure gene in humans. *Human molecular genetics* 2018;27:3772-3786.
5.   Ahram D, Alward W, Kuehn M. The genetic mechanisms of primary angle closure glaucoma. *Eye* 2015;29:1251-1259.
6.   Congdon NG, Friedman DS. Angle-closure glaucoma: impact, etiology, diagnosis, and treatment. *Current opinion in ophthalmology* 2003;14:70-73.
7.   Cheung CY, Zheng C, Ho C-L, et al. Novel anterior-chamber angle measurements by high-definition optical coherence tomography using the Schwalbe line as the landmark. *British Journal of Ophthalmology* 2011;95:955-959.
8.   Wang B, Narayanaswamy A, Amerasinghe N, et al. Increased iris thickness and association with primary angle closure glaucoma. *British Journal of Ophthalmology* 2011;95:46-50.
9.   Sihota R, Lakshmaiah N, Agarwal H, Pandey R, Titiyal J. Ocular parameters in the subgroups of angle closure glaucoma. *Clinical & experimental ophthalmology* 2000;28:253-258.
10.   Zhou M, Wang W, Ding X, et al. Choroidal thickness in fellow eyes of patients with acute primary angle-closure measured by enhanced depth imaging spectral-domain optical coherence tomography. *Investigative Ophthalmology & Visual Science* 2013;54:1971-1978.
11.   Panda SK, Tan RK, Tun TA, et al. Changes in Iris Stiffness and Permeability in Primary Angle Closure Glaucoma. *Investigative Ophthalmology & Visual Science* 2021;62:29-29.
12.   Pant AD, Gogte P, Pathak-Ray V, Dorairaj SK, Amini R. Increased iris stiffness in patients with a history of angle-closure glaucoma: an image-based inverse modeling analysis. *Investigative ophthalmology & visual science* 2018;59:4134-4142.
13.   Thomas VS, Salinas SD, Pant AD, Dorairaj SK, Amini R. Biomechanical assessment of the Iris in relation to angle-closure glaucoma: a multi-scale computational approach. *International Symposium on Computer Methods in Biomechanics and Biomedical Engineering*: Springer; 2019:470-482.
14.   Safa BN, Bahrani Fard MR, Ethier CR. In vivo biomechanical assessment of iridial deformations and muscle contractions in human eyes. *Journal of the Royal Society Interface* 2022;19:20220108.
15.   Safa BN, Wong CA, Ha J, Ethier CR. Glaucoma and biomechanics. *Current Opinion in Ophthalmology* 2022;33:80-90.
16.   Ang LP, Aung T, Chew PT. Acute primary angle closure in an Asian population: long-term outcome of the fellow eye after prophylactic laser peripheral iridotomy. *Ophthalmology* 2000;107:2092-2096.

17.   Playfair TJ, Watson PG. Management of acute primary angle-closure glaucoma: a long-term follow-up of the results of peripheral iridectomy used as an initial procedure. *British Journal of Ophthalmology* 1979;63:17-22.

18.   Tarongoy P, Ho CL, Walton DS. Angle-closure glaucoma: the role of the lens in the pathogenesis, prevention, and treatment. *Survey of ophthalmology* 2009;54:211-225.

19.   Wright C, Tawfik MA, Waisbourd M, Katz LJ. Primary angle‑closure glaucoma: an update. *Acta ophthalmologica* 2016;94:217-225.

20.   He M, Lu Y, Liu X, Ye T, Foster PJ. Histologic changes of the iris in the development of angle closure in Chinese eyes. *Journal of glaucoma* 2008;17:386-392.

21.   Hao L, Hu Y, Xu Y, et al. Dynamic analysis of iris changes and a deep learning system for automated angle-closure classification based on AS-OCT videos. *Eye and Vision* 2022;9:1-10.

22.   Quigley HA, Silver DM, Friedman DS, et al. Iris cross-sectional area decreases with pupil dilation and its dynamic behavior is a risk factor in angle closure. *Journal of glaucoma* 2009;18:173-179.

23.   Wang W, Qian X, Song H, Zhang M, Liu Z. Fluid and structure coupling analysis of the interaction between aqueous humor and iris. *Biomedical Engineering Online* 2016;15:569-586.

24.   Huang EC, Barocas VH. Active iris mechanics and pupillary block: steady-state analysis and comparison with anatomical risk factors. *Annals of biomedical engineering* 2004;32:1276-1285.

25.   Heys JJ, Barocas VH, Taravella MJ. Modeling passive mechanical interaction between aqueous humor and iris. *J Biomech Eng* 2001;123:540-547.

26.   Zhang K, Qian X, Mei X, Liu Z. An inverse method to determine the mechanical properties of the iris in vivo. *Biomedical engineering online* 2014;13:1.

27.   Heys J, Barocas V. Mechanical characterization of the bovine iris. *Journal of biomechanics* 1999;32:999-1003.

28.   Whitcomb JE, Amini R, Simha NK, Barocas VH. Anterior–posterior asymmetry in iris mechanics measured by indentation. *Experimental eye research* 2011;93:475-481.

29.   Whitcomb JE, Barnett VA, Olsen TW, Barocas VH. Ex vivo porcine iris stiffening due to drug stimulation. *Experimental eye research* 2009;89:456-461.

30.   Tan RK, Wang X, Perera SA, Girard MJ. Numerical stress analysis of the iris tissue induced by pupil expansion: Comparison of commercial devices. *PloS one* 2018;13:e0194141.

31.   Tan RK, Wang X, Chan AS, et al. Permeability of the porcine iris stroma. *Experimental eye research* 2019;181:190-196.

32.   Quigley HA. The iris is a sponge: a cause of angle closure. *Ophthalmology* 2010;117:1-2.

33.   Freddo TF. Ultrastructure of the iris. *Microscopy research and technique* 1996;33:369-389.

34.   Chorin AJ. Numerical solution of the Navier-Stokes equations. *Mathematics of computation* 1968;22:745-762.

35.   Temam R. *Navier-Stokes equations: theory and numerical analysis*: American Mathematical Soc.; 2001.

36.   Keller JB. Darcy's law for flow in porous media and the two-space method. *Nonlinear partial differential equations in engineering and applied sciences* 1980;31:429-443.

37.   Whitaker S. Flow in porous media I: A theoretical derivation of Darcy's law. *Transport in porous media* 1986;1:3-25.

38.   Périé D, Korda D, Iatridis JC. Confined compression experiments on bovine nucleus pulposus and annulus fibrosus: sensitivity of the experiment in the determination of compressive modulus and hydraulic permeability. *Journal of biomechanics* 2005;38:2164-2171.

39.   Fung Y-c. *Biomechanics: mechanical properties of living tissues*: Springer Science & Business Media; 2013.

40.   Girard M, Suh J-KF, Hart RT, Burgoyne CF, Downs JC. Effects of storage time on the mechanical properties of rabbit peripapillary sclera after enucleation. *Current eye research* 2007;32:465-470.

41.   Nowick AS, Berry BS. Lognormal distribution function for describing anelastic and other relaxation processes I. theory and numerical computations. *IBM Journal of Research and Development* 1961;5:297-311.

42.   Olberding JE, Suh JF. A dual optimization method for the material parameter identification of a biphasic poroviscoelastic hydrogel: potential application to hypercompliant soft tissues. *Journal of biomechanics* 2006;39:2468-2475.

43.   Wagner KW. Zur theorie der unvollkommenen dielektrika. *Annalen der Physik* 1913;345:817-855.

44.   Storn R. On the usage of differential evolution for function optimization. *Proceedings of north american fuzzy information processing*: Ieee; 1996:519-523.

45.   Najjar RP, Rukmini A, Finkelstein MT, et al. Handheld chromatic pupillometry can accurately and rapidly reveal functional loss in glaucoma. *British Journal of Ophthalmology* 2021.

46.   Najjar RP, Sharma S, Atalay E, et al. Pupillary responses to full-field chromatic stimuli are reduced in patients with early-stage primary open-angle glaucoma. *Ophthalmology* 2018;125:1362-1371.

47.   Rukmini AV, Milea D, Baskaran M, et al. Pupillary responses to high-irradiance blue light correlate with glaucoma severity. *Ophthalmology* 2015;122:1777-1785.

48.   Tousimis A, FINE BS. Ultrastructure of the iris: the intercellular stromal components. *AMA Archives of Ophthalmology* 1959;62:974-976.

49.   Cheung CY-l, Liu S, Weinreb RN, et al. Dynamic analysis of iris configuration with anterior segment optical coherence tomography. *Investigative ophthalmology & visual science* 2010;51:4040-4046.

50.   Pan C-W, Qian Y-X, Li J, Zhong H. Iris surface features and anterior chamber depth in Chinese adolescents. *BMC ophthalmology* 2020;20:1-6.

51.   Chua J, Thakku SG, Tun TA, et al. Iris crypts influence dynamic changes of iris volume. *Ophthalmology* 2016;123:2077-2084.

52.   Chua J, Thakku SG, Pham TH, et al. Automated detection of iris furrows and their influence on dynamic iris volume change. *Scientific reports* 2017;7:1-8.

53.   Narayanaswamy A, Nai MH, Nongpiur ME, et al. Young's Modulus Determination of Normal and Glaucomatous Human Iris. *Investigative ophthalmology & visual science* 2019;60:2690-2695.

54.   Chen X, Zhou Y, Wang L, Santare MH, Wan LQ, Lu XL. Determining tension–compression nonlinear mechanical properties of articular cartilage from indentation testing. *Annals of biomedical engineering* 2016;44:1148-1158.

55.   Lai W, Mow VC, Roth V. Effects of nonlinear strain-dependent permeability and rate of compression on the stress behavior of articular cartilage. 1981.

Figure 1. Hydraulic permeability measurement set-up. **A.** Fluid of approximately 2,000 Pa (15 mmHg) flows through a 3D printed holder where the tissue is placed and clamped. **B.** The area for flow is approximately 0.0391 mm^2, suitable for samples that are obtained from iridotomy. **C.** Flow rate through a 0.397 mm diameter tube is measured and recorded.

Figure 2. OCT images used for determination of tissue parameters. **A.** The channel area of the custom 3D-printed holder for the permeability experiment was estimated as an ellipse using measurements from OCT. **B.** For the permeability experiment, an area of 45 × 100 pixels was selected for each image and manually converted to binary black and white, **C.** whereas the width and area were computed for the stress relaxation experiment.

Figure 3. Stress relaxation experiment was conducted on the iris tissues by **A.** Applying linear strain rate of 10% per second for 5 seconds and holding constant strain as the tissue relaxes. **B.** The same protocol was performed on both the isolated dilator (left) and stroma (right) tissues. **C.** To prevent slippage, fine sandpaper was used at the clamps of the Instron machine.

Figure 4. Stress relaxation behaviour of the porcine dilator tissue (left) and stroma tissue (right). The blue line represents the experimental data, and the orange line represents the fitted data.

Table 1. Viscoelastic parameters of the iris stroma and dilator muscle tissues (mean value ± standard deviation).

	c	β	τ_m (s)	E_0 (kPa)	E_∞ (kPa)
Dilator muscle	1.41 ± 0.60	2.50 ± 1.40	7.43 ± 4.96	14.14 ± 6.44	6.08 ± 2.74
Stroma tissue	0.707 ± 0.38	2.06 ± 1.33	1.28 ± 1.27	9.16 ± 3.03	5.54 ± 1.98