Non-specific membrane-matrix interactions influence diffusivity of lipid vesicles in hydrogel environments

Nicky Tam[1], Otto Schullian[1,2], Amaia Cipitria[1,3,4], and Rumiana Dimova[1]*

[1]Max Planck Institute of Colloids and Interfaces, Science Park Golm, 14476 Potsdam, Germany

[2]Free University of Berlin, Department of Physics, 14195 Berlin, Germany

[3]Biodonostia Health Research Institute, San Sebastián, Spain

[4]IKERBASQUE, Basque Foundation for Science, Bilbao, Spain

* Address correspondence to Rumiana.Dimova@mpikg.mpg.de

Abstract: The diffusion of extracellular vesicles and liposomes *in vivo* is affected by different tissue environmental conditions and is of great interest in the development of liposome-based therapeutics and drug-delivery systems. Here, we use a bottom-up biomimetic approach to study how steric and electrostatic interactions influence the diffusivity of synthetic large unilamellar vesicles in hydrogel environments. Single-particle tracking of these extracellular vesicle-like particles in agarose hydrogels as an extracellular matrix model shows that membrane deformability and surface charge affect the hydrogel pore spaces that vesicles have access to, which determines overall diffusivity. Moreover, we show that passivation of vesicles with PEGylated lipids, as often used in drug delivery systems enhances diffusivity, but that this effect cannot be fully explained with electrostatic interactions alone.

Key words: Extracellular vesicles, liposomes, hydrogels, PEGylation, diffusion, agarose,

Introduction

Large unilamellar vesicles (LUVs), or liposomes, are phospholipid structures 100-1000 nm in diameter that are often used as a minimal model of cell-derived extracellular vesicles (EVs). Their application in drug delivery systems takes advantage of the structure and function of their *in vivo* counterparts, as facilitators of intercellular transport[1,2] to shield their payloads from the external tissue environment and mediate their transport to and uptake by target cells [3,4]. Despite the rising interest in using such lipid nanoparticle systems, for example to deliver anti-cancer therapeutics [5,6] or as carriers of immunogenic materials in vaccine formulations[7], there is little data on how nanoparticle mobility and transport within tissues is affected by different tissue environmental conditions and the membrane material properties.

A 2009 study by Lieleg et al.[8] showed that hydrogel materials derived from extracellular matrix (ECM) can act as an electrostatic filter, sequestering charged nanoparticles while allowing neutral particles to pass through unimpeded. Later, Yu et al.[9] and Lenzini et al.[10] found that the deformability of lipid vesicles, modulated by the lipid composition of the membrane and by the presence of water-permissive channel proteins, respectively, can influence their access through hydrogel pore spaces and thus their movement and transport. Clearly, vesicle diffusion is affected by a diverse range of biophysical factors and of particular interest is the way these factors might interact to produce the complex distribution patterns observed in vivo[11].

To systematically study how different material properties of lipid vesicles and ECM-like hydrogels can influence vesicle diffusion, we use single-particle tracking[12] to study the diffusion of synthetic LUVs embedded in agarose. Agarose is a polysaccharide polymer from red algae that undergoes thermo-reversible gelation via non-covalent hydrogen bonding[13,14]. The polymer chain length can vary, thus affecting the gel mechanics[15]. While much simpler in chemical composition than the diverse molecules found in human ECM, agarose provides greater control over material properties. Stiffness and porosity of agarose gels, for example, can be found in a comparable range to human tissues such as brain or cartilage, and can be controlled with concentration and gelation conditions[16,17]. By using this biomimetic system, we aim to better understand the biophysical mechanisms that govern diffusion of extracellular-like vesicles or drug carriers in tissues, which could one day lead to more efficient targeting and delivery of lipid nanoparticle-based therapeutics and vaccine delivery[3,5–7,18].

Experimental Section

LUV production and characterization. Lipid stocks dissolved in chloroform (Avanti Polar Lipids) were used to prepare mixtures containing 4mM DOPC (1,2-dioleoyl-sn-glycero-3-phosphocholine) as a base solution. Negatively charged LUVs were made with a 2:1 molar ratio mixture of DOPC and DOPS (1,2-dioleoyl-sn-glycero-3-phospho-L-serine), while positively charged LUVs were made with a

2:1 molar ratio mixture of DOPC and DOTAP (1,2-dioleoyl-3-trimethylammonium-propane). PEGylated lipids were used to passivate vesicles for diffusion in hydrogels. Additions of 1mol% or 10mol% DSPE-mPEG1K, DSPE-mPEG2K, or DSPE-mPEG5K (1,2-distearoyl-sn-glycero-3-phosphoethanolamine-N-[methoxy(polyethylene glycol)-1000], -2000], and -5000], respectively) were added to base solutions of DOPC or DOPC/DOTAP. Fluorescent visualization was facilitated by the addition of 0.2mol% DiIC$_{18}$(5) (Thermo Fisher Scientific; 1,1'-Dioctadecyl-3,3,3',3'-Tetra-methylindodicarbocyanine, 4-Chlorobenzenesulfonate Salt).

LUVs were produced by first spreading a thin layer of a lipid mixture inside a glass vial and drying under vacuum for 1.5 hours. Next, the lipid film was hydrated with phosphate buffered saline (PBS; tablets for 200mL solutions from Sigma-Aldrich) and vortexed for 30 minutes to produce multilamellar lipid structures. The resulting solution was then extruded with a Mini Extruder (Avanti Polar Lipids), 21 passes each through a 200nm and then 100nm polycarbonate Nuclepore Track-Etched Membrane (Sigma-Aldrich).

Size distribution and zeta-potential of particles were measured using a Malvern Instruments Nano-ZS Zetasizer equipped with a 632.8nm 4mW HeNe laser to ensure sample consistency. Samples in disposable folded capillary cells (DTS1070; Malvern Panalytical) were analyzed with dynamic light scattering (DLS) at a scattering angle of 173° to determine size distribution before determination of zeta-potential. All particles were measured in high-salt buffer conditions resulting in electrostatic screening, so zeta-potential values are used to illustrate relative differences in surface charge rather than absolute charge.

Fluctuation analysis. To probe how the bending rigidity of lipid membranes changes with the presence of PEGylated lipids, we used fluctuation analysis on giant unilamellar vesicles (GUVs)[19,20]. GUVs were made using the gel-assisted swelling method[21,22] (see Section S1 in the supporting information, SI) and were visualized under phase contrast with a 40× objective on a Zeiss AXIO Observer.D1 microscope. Image sequences of 3000 frames were recorded with a pco.edge sCMOS camera at 25 frames per second (fps) with 200µs exposure. Fluctuation analysis software[20] computed the bending rigidity based on the Fourier decomposition of thermally-driven membrane fluctuations into spherical modes.

Preparation and characterization of agarose gels. Stock solutions of 2% w/v low gelling-temperature agarose (BioReagent, for molecular biology; Sigma) were made by dispersing agarose powder in PBS and microwaving at 350W power in 5-8s intervals until dissolved. Stocks were stored at 4°C and could be re-melted at 95°C using the same microwaving method. The molten agarose remained liquid down to 35°C. Gels of 1%, 0.5%, and 0.2% concentration were formed by melting stock gels and mixing with warm PBS (35°C) directly on glass slides for imaging, kept warm on a hotplate set to 35°C, or directly on a heated rheometer stage in the case of rheology measurements. Molten gels were

taken off heating apparatus to cool to ambient temperature to induce gelation. Gel osmolality, which influences degree of vesicle deflation, was varied with the addition of glucose as opposed to salts to maintain the ionic strength of the solution, avoiding electrostatic screening effects. Solution osmolality prior to the addition of agarose was adjusted with a freezing-point osmometer (Osmomat 3000, Gonotec, Germany). A list of tested gel formulations can be found in Table 2 in the SI (Section S5).

Bulk rheology of agarose hydrogels was studied in shear mode using an Anton-Paar MCR301 rheometer with 12mm cone-plate (CP12) geometry. Gels were mixed directly on the rheometer stage heated to 35°C, then cooled below 20°C to allow the sample to start to set while the probe was lowered to the measurement position on the sample. The gel was left for 5 minutes to fully set before testing up to 1% rotational strain from 1-10Hz.

Average gel pore size was estimated using a turbidimetric assay described by Aymard et al.[17] and Narayanan et al.[14] Briefly, molten agarose was added to disposable 2.5mL PMMA cuvettes (Sigma-Aldrich) and allowed to cool to ambient temperature (~22°C) to gel. Absorbance values over 600-900nm were measured using a Thermo Spectronic Helios Gamma UV-Vis Spectrophotometer (Thermo Fisher). This was compared to analytical data from Aymard et al.[17] (see Section S2, SI).

Quantifying particle mobility. LUVs were embedded in agarose gels by mixing extruded LUV solutions with molten agarose directly on a glass microscopy slide within a rubber spacer (see Section S3, SI). A glass coverslip was placed on top, such that the agarose droplet wetted both glass surfaces, forming a disk. The imaging chamber was set aside at room temperature for 5 minutes to set. For control experiments with embedded polystyrene beads, Fluoresbrite YG 0.1µm-diameter Microbeads (Polysciences, Inc) were diluted 1:100 in PBS and mixed into gels, replacing the LUV solution.

Samples were imaged with a pco.edge sCMOS camera mounted to a Zeiss AXIO Observer.D1 microscope with a 63× water immersion objective in epifluorescence mode. Image sequences of length 5s (~100 frames) were captured with 20fps frame rate and ~45ms exposure in a 100µm×100µm region of interest (ROI). Three ROIs were recorded per sample to account for internal heterogeneity. Particle mobility within gels was analyzed with the single-particle tracking plugin for FIJI developed by Sbalzarini and Koumoutsakos[12]. A sequence length of 100 frames was chosen because longer sequences resulted in decreased signal-to-noise ratio from photobleaching, leading to increased false positives in particle detection. Histograms of the log$_{10}$ diffusion coefficients (in m^{2}s^{-1}) obtained from the plugin were used to determine the mobile fraction using -14 as the cut-off. This value corresponds to the lower limit of detection of particle movement based on imaging parameters (see Section S3, SI).

We also studied the infiltration of 100nm-extruded DOPC LUVs into preformed 1% w/v agarose hydrogels to obtain a collective diffusion coefficient. The prior imaging chamber setup was done with slight adjustments (see Fig. S4, SI).

Briefly, agarose gel disks were formed without LUVs in an imaging chamber and allowed to set before a solution of LUVs (12μM lipid) was pipetted into the chamber. Three 100μm×100μm ROIs each in the gel interior and the exterior solution were imaged per time point, per sample over 100 hours. The number of particles in each ROI inside and outside the gel was counted as a function of time. Assuming slow diffusion and obtaining density gradients using finite differences, the diffusion coefficient was determined. The derivation of the diffusion coefficient from this data can be found in SI Section S4.

Statistical analysis. Histograms of $\log_{10}$ diffusion coefficients are normalized to show probability and represent pooled data from three ROIs within an individual gel. Each ROI corresponds to 100-300 diffusing particles. The variability in the number of identified particle tracks in different gels arises from differences in particle mobility. Statistics on mobile fractions were calculated with n=3 gels, presented as standard box plots. All other data are presented as mean with standard deviation. Statistical significance was determined with N-way ANOVA (as indicated) with Tukey-Kramer tests for multiple comparisons at the significance levels indicated.

Results and Discussion

Mobility of embedded LUVs. LUVs embedded inside agarose gels were imaged with epifluorescence microscopy and analyzed with single-particle tracking[12] to obtain their diffusion coefficients (Fig. 1A). The mobile fraction was determined from the distribution of $\log_{10}$ diffusion coefficients. The peak observed at a value of -15 for 100nm-extruded DOPC LUVs embedded in 1% agarose (Fig. 1B) lies below the mobility cut-off of -14 (see Section S3, SI) and thus corresponds to fully-immobilized particles. Particle immobilization and interactions in general with a gel matrix have previously been described in terms of electrostatic effects (at least for polystyrene particles)[23]. In essence, while some particles can become fully entrapped by the gel matrix, other particles will be able to diffuse unhindered within the matrix voids as if they were in liquid water. Given close enough proximity to a wall or surface, particles can transiently interact with the gel matrix, reducing their mean squared displacement and thus "effective" diffusion coefficient. It is possible in our case with flexible lipid vesicles that these interactions can also be steric, with transient trapping and freeing of particles due to thermal fluctuations. The obtained effective diffusion coefficient can thus be used as a measure of the frequency and strength of membrane-matrix interactions, including steric ones. Since virtually all particles lie below -12 (Fig. 1B), the value given by the Stokes-Einstein equation for an ideal 100nm spherical particle diffusing in liquid water, this implies that all particles in the system are interacting with the gel matrix, sterically or otherwise.

Collective LUV diffusion from gel infiltration. We next looked at the ability of DOPC LUVs to infiltrate pre-formed agarose hydrogel disks to obtain an independent measure of particle mobility based on population dynamics (Fig. 1C, SI Section S4). While many LUVs ended up adhering to and getting stuck at the edge of the agarose disks, some LUVs were observed to infiltrate into them over 100 hours of imaging. Equilibrium in the density gradient was not reached in the time frame tested. By approximating the LUV density gradient with a finite difference, we calculate a population-wide diffusion coefficient using Fick's First Law of Diffusion to be $3.92\pm0.52\times10^{-14}$m^{2}s^{-1} (see Fig. 1D and SI Section S4), corresponding to a $\log_{10}$ value of -13.41. This falls between the mobility cut-off and the value for the Stokes-Einstein particle, agreeing well with the results from the single-particle tracking of embedded LUVs (Fig. 1A, B).

Figure 1, Particle mobility assessed in two ways: diffusion of DOPC LUVs embedded in gels and infiltration of LUVs into gels. A) The diffusion of 100nm-extruded DOPC LUVs embedded in 1% agarose gels is analyzed with single particle tracking. Particle paths are indicated as an overlay on a representative time frame with different colours representing different particles. B) The base-ten logarithms of the diffusion coefficients are shown in histogram form. The values of -14 and -12 are indicated by vertical lines, the former being the lower limit of detection of particle motion for the experimental setup and the latter being the theoretical value determined from the Stokes-Einstein equation for an ideal 100nm-diameter spherical particle diffusing in liquid water. The insets show fragments of two trajectories shown in (A) corresponding to an immobilized/confined LUV (green, left) and a freely diffusing one (yellow, right). C) A measure of the collective particle diffusion is determined by incubating preformed agarose gel disks with an external solution of LUVs and monitoring their infiltration into the gel. The epifluorescence microscopy image shows the edge of an agarose gel disk, where LUVs can be seen adsorbed onto the surface. Individual LUVs in the solution are seen as tiny spots. D) The particle densities inside and outside the gel over time can be related to the diffusion coefficient (see SI Section S4). The average $\log_{10}$ diffusion coefficients computed from five independent experimental replicates are presented here with error bars showing standard deviation. The ensemble average across all experimental replicates was found to be $3.92\pm0.52\times10\text{-}14\text{m}^2\text{s}^{-1}$ (indicated as a red line with grey shaded area showing standard deviation), corresponding to a $\log_{10}$ value of -13.41.

Figure 2, Mobility of DOPC LUVs increases with osmotic defla-tion and with hydrogel pore size. A) Mobile fractions of LUVs in agarose gels with different osmolalities relative to the LUV interior with cartoon representations of a LUV at varying stages of defla-tion. B) Mobile fractions of LUVs in agarose gels of differing con-centration and osmolal strength with cartoon representations com-paring the relative sizes of pores and LUVs. Bars on graphs repre-sent statistically significant differences, as determined with one-way ANOVA and pairwise Tukey-Kramer post-hoc analysis at the p-values indicated.

Osmotic deflation of LUVs increases diffusivity. Work by Yu et al.[9] on LUV compositions of different phase tran-sition temperature and by Lenzini et al.[10] on cell-derived EVs has shown that vesicle deformability can affect their diffusion in a hydrogel. Another way to make LUVs more deformable is to deflate them by introducing them into a hy-pertonic environment. We studied the mobility of DOPC LUVs in agarose gels of differing osmolalities by adding glucose to the hydrogel solution while keeping the initial in-travesicular solution constant. Fig. 2A shows that LUV mo-bility increases with osmolality from isotonic to +12% os-

molality, and thus degree of deflation. No significant differ-ence in LUV size was detected with DLS, though size distri-butions appear to have slightly higher variability in hyper-tonic solutions (Fig. 3B). We also did not observe differ-ences in the bulk rheology of agarose gels formed with and without glucose (Fig. S5), thus the microstructure of the gel is not expected to vary more than what is naturally found in agarose[13]. The final plateau (or possible weak decrease) in mobility from +12% to +17% osmolality (Fig. 2A) could be due to a phenomenon similar to what was described by Yu et al.[9] whereby hyper-deformability hinders vesicle diffusion through matrix pores. Given an elastic hydrogel matrix like agarose with a rapid stress-relaxation response, a slightly-deflated LUV may deform enough to fit into a pore where it can then be squeezed and propelled out by thermal fluctua-tions of the matrix walls, while a hyper-deformable, more deflated LUV would remain trapped and yield as the matrix wall pushes on it.

When the pore size of the gel is increased from 100±40nm to 650±450nm by decreasing the agarose concentration from 1% to 0.5% w/v (Fig. S2), the overall mobility of LUVs in-creases (Fig. 2B). At this concentration of agarose, the dif-ference between the mobile fractions in different osmolali-ties is not statistically significant. The effect of deflation thus appears to only be relevant when the average pore diameter is comparable (i.e., on the same order of magnitude) to the diameter of the LUV. This is reasonable, as the LUVs would have greater access to matrix pores regardless of deforma-bility in the 0.5% gel.

LUV surface charge affects mobility. Lieleg et al.[8] re-ported that Matrigel, a complex mixture of cell-derived ECM materials exhibits electrostatic filtering behavior on diffusing particles. To determine whether agarose has simi-lar characteristics, we produced negatively charged LUVs from a mixture of 2:1 DOPC/DOPS as well as positively charged LUVs composed of 2:1 DOPC/DOTAP (molar ra-tios) to embed in agarose (Fig. 3A). The addition of DOPS does not significantly change LUV size (Fig. 3B), but the DOPC/DOTAP particles appear significantly larger than other tested particles, possibly due to aggregation. Figure 3C shows that the negatively charged DOPC/DOPS LUVs have greater mobility overall compared to the positively charged DOPC/DOTAP and pure zwitterionic DOPC LUVs (see also Fig. S6). Increased osmolality (i.e. LUV deflation) does not significantly improve the mobility of DOPC/DOPS LUVs, but there still appears to be an upward trend. DOPC/DOTAP LUVs remain immobile in hypertonic conditions, as well as in much lower agarose concentrations (Fig. 4A-C,E). At 0.2% w/v, agarose behaves like a liquid, being able to flow. The lack of mobility at this concentration would suggest that this interaction is not merely steric, but electrostatic, causing the positively charged LUVs to stick to the agarose polymer bundles.

Figure 3, Effect of charge and composition on particle mobility in 1% agarose gels. The lipid ratios in DOPC/DOTAP and DOPC/DOPS LUVs correspond to 2:1. A) Zeta-potential of LUVs and polystyrene beads, as measured in PBS; the sketches below roughly illustrate their surface charge. B) Diameters of LUVs, as measured with dynamic light scattering. Average diameters of DOPC/DOPS and DOPC LUVs, as well as the polystyrene beads (blue) are not significantly different, in both isotonic (black) and hypertonic (red) conditions, as determined by 2-way ANOVA with pairwise Tukey-Kramer post-hoc analysis (p>0.05). Representative size distributions of particles can be found in Fig. S6 in the SI. Sizes of DOPC/DOTAP LUVs are significantly larger than those of the other particles (p<0.05). C) Mobile fractions of different particles in isotonic (black; 290mOsm/kg) and +12% hypertonic (red; 320mOsm/kg) buffer conditions; see Fig. S6 for diffusivity data. Statistical significance was determined with 2-way ANOVA with pairwise Tukey-Kramer post-hoc analysis. # represents a significant difference across membrane compositions (p<0.01). Statistically significant differences (p<0.02) at different osmolalities is represented with * while lack of a significant difference (p>0.02) is denoted with n.s.

As a control, we compared LUV mobility to that of polystyrene beads. Despite having a similar size and negative surface charge to our DOPC/DOPS LUVs, the beads are fully immobilized in the hydrogel compared to the highly mobile DOPC/DOPS LUVs. The charge groups exposed at the surface of the LUVs (carboxyl, amino, and phosphate) are different from that of the beads (sulfate groups and hydrophobic regions), which might give rise to specific chemical interactions of the beads with the gel. Another explanation relates to the fact that the polystyrene beads are rigid while the LUVs are deformable and capable of squeezing through gel matrix pores that would otherwise be too small to pass through. The increased surface charge of the DOPC/DOPS compared to DOPC LUVs should also result in a slightly stiffer membrane[24] although this effect could be

minimized by the high salt concentration. These results reveal an interesting intersection of different factors affecting the diffusion of particles through a gel matrix. In particular, we note that the use of polystyrene nanoparticles to model the diffusion of LUVs, EVs, and other soft particles may not be accurate due to the differences in their overall deformability, even if their surface properties are matched.

PEGylation of LUVs increases their mobility. Nanoparticles are often "passivated" with PEG, a hydrophilic polymer used to prevent the adsorption of proteins on surfaces and hinder or slow down immune reactivity. It has been claimed that this passivation effect is due to the neutral charge of PEG masking the underlying surface[8,25,26]. We questioned whether this effect could restore the mobility of

our DOPC/DOTAP LUVs (Fig. 4D). For this to work, the layer of PEG chains would need to be thicker than the Debye length of the charges on the membrane. The inclusion DSPE-mPEG1K, a phospholipid coupled to a 1000Da PEG chain at 10mol% should make a PEG layer thick enough to screen out most electrostatic effects (see derivation in SI Section S7)[27,28]. This indeed appears to restore the mobility of the DOPC/DOTAP LUVs in 0.5% w/v agarose to the same level as pure DOPC LUVs (and DOPC+PEG LUVs; Fig. 4F). The mobility of the passivated DOPC/DOTAP+PEG LUVs in 1% agarose is much improved compared to that of the non-passivated DOPC and DOPC/DOTAP LUVs, but is lower than the passivated DOPC+PEG LUVs. One possible explanation for this is that LUVs need to deform to fit through the smaller pores of the 1% agarose. This could force the PEG layer to compress or deform out of the way, exposing the underlying positive charge. This is possible, as previous work has shown that PEG is highly compliant[29,30].

Figure 4, Recovery of DOPC/DOTAP LUV mobility with PEGylated lipids. A-C) Representative images of 100nm-extruded 2:1 DOPC/DOTAP LUVs in 0.2%, 0.5%, and 1% w/v agarose, respectively. Red arrows indicate abnormal particles or possible particle aggregates while white arrows indicate single particles for comparison. D) Schematic diagram of a LUV membrane containing PEGylated phospholipids. E) Mobile fractions of 2:1 DOPC/DOTAP LUVs in agarose gels/solutions of differing concentration. Agarose at 0.2% concentration behaves macroscopically as a liquid, but likely has some weak molecular network linkages. F) Comparison of mobile fractions of 2:1 DOPC/DOTAP LUVs (DOPC/DOTAP), pure DOPC LUVs (DOPC), 2:1 DOPC/DOTAP LUVs +10mol% DSPE-mPEG1K (DOPC/DOTAP + PEG), and DOPC LUVs +10mol% DSPE-mPEG1K (DOPC + PEG). # indicates statistically significant differences when comparing mobilities across LUV compositions in the same gel concentration. * indicates statistically significant differences when comparing mobilities of LUVs in different agarose gel concentrations. Mobility of DOPC/DOTAP LUVs in both 1% and 0.5% agarose, as well as that of DOPC LUVs in 1% agarose are not significantly different (n.s.). Statistical significance is determined with two-way ANOVA with pairwise Tukey-Kramer post-hoc analysis for multiple comparisons.

While PEGylation improved the mobility of DOPC/DOTAP LUVs, it also improved that of DOPC LUVs despite previous results of higher mobility in agarose with greater negative charge. To investigate further how PEG affects LUV mobility, we tested other PEG chain sizes (1000, 2000, 5000 Da) at two concentrations (1mol% and 10mol%; Fig. 5A-C). ***Figure 5***D,E shows that all PEG chain sizes improve LUV mobility in 1% agarose, while LUVs with PEG2000 and PEG5000 appear to be more mobile than those with PEG1000 in 0.5% agarose gels. LUV mobility is higher with 10mol% PEGylated lipid, where the PEG chains are in

a polymer brush conformation[28–30] compared to 1mol% polymer, where they are in mushroom conformation[28–30]. The difference in PEG chain conformations could help explain why PEG1000 appears ineffective in 0.5% agarose, as the mushroom-to-brush transition occurs at a higher concentration and is less well-defined. These results suggest that the effect that PEG has on particle mobility is not entirely electrostatic.

Figure 5, Effect of degree and density of PEGylation on LUV characteristics and mobility. Green data represents 10mol% concentration of PEGylated lipid in membranes while black data represents 1mol% concentration. A) Influence of PEG chain size and concentration on LUV size, as measured with DLS. No statistically significant differences were found (p>0.05) and size distributions appear similar (Fig. S7B in SI). B) Influence of PEG chain size and concentration on surface charge, measured as the zeta-potential. Bare DOPC LUVs are significantly more electronegative compared to PEGylated LUVs, regardless of PEG size and concentration (p<0.01, green and black *), demonstrating screening by PEG. C) Influence of PEG chain size and concentration on membrane bending rigidity, measured with fluctuation analysis on giant unilamellar vesicles (GUVs) and presented in k_BT energy units (k_B being the Boltzmann constant and T being temperature). Membranes with 10mol% PEGylated lipid are significantly stiffer than those with 1mol% PEGylated lipid. Bare DOPC membranes are significantly less stiff than PEGylated membranes only at 10mol% concentration (p<0.01). No statistically significant differences were found between different PEG chain sizes. Statistically significant differences compared to bare DOPC membranes were determined with 2-way ANOVA with pairwise Tukey-Kramer post-hoc analysis, as indicated with *. D) Mobilities of all PEGylated particles in 1% agarose are significantly greater than those of bare DOPC LUVs at both concentrations of PEGylated lipid (p<0.01, green and black *). Mobilities of LUVs with 10mol% PEGylated lipid are significantly greater than those of LUVs with 1mol% PEGylated lipid (p<0.01). E) Mobilities of LUVs with 10mol% PEG2000 and PEG5000 are significantly greater than those of bare LUVs and LUVs with 10mol% PEG1000 (p<0.01). No significant differences were found at 1mol% PEGylated lipid. Statistically significant differences compared to bare DOPC membranes are indicated with *, as determined by 3-way ANOVA with pair-wise Tukey-Kramer post-hoc analysis.

Fluctuation analysis on GUVs composed of the same lipid mixtures as the tested LUVs shows a slight stiffening of lipid membranes with the presence of PEGylated lipids (Fig. 5C). This behavior is consistent with predictions for membrane stiffening by anchored polymers[31], and experiments on membranes with biopolymer adsorption[32] as well as microemulsions[33]. However, the stiffening observed here appears too small to fully explain the dramatic increase in mobility in 1% agarose for both concentrations of PEGylated lipid tested. One possibility would be that the PEG forms a soft lubricating layer that facilitates the movement of LUVs

through matrix pores. This would be supported by the higher mobility observed with larger PEG chains and at higher PEG coverage (in the brush regime), which would form a thicker layer. Further investigation is needed to test this hypothesis. A particularly interesting question for future consideration would be whether the glycocalyx, the diverse array of polymeric sugar molecules expressed on the surfaces of cells and cell-derived EVs might play an analogous role *in vivo*.

Conclusions

The use of a bottom-up biomimetic approach to study lipid vesicle diffusion in hydrogel materials has shown that different biophysical factors contribute to particle dynamics. Even without specific biochemical interactions via cell adhesion molecules and ECM proteins, complex diffusive behaviour can arise through the combined effects of non-specific steric and electrostatic interactions. Such factors might contribute to preferential infiltration of some vesicle populations into tissues with certain ECM architectures, forming a basis for organotropic "homing" of particles. The design of lipid nanocarriers and engineered liposome-based therapeutics can thus take advantage of non-specific membrane-matrix interactions to achieve improved penetration and retention in target tissues. Further research on ECM-derived materials and more complex lipid vesicle systems is needed to better understand the diverse molecular interactions that govern the movement of vesicles in the tissue microenvironment.

Acknowledgements

N. Tam would like to acknowledge funding from the International Max Planck Research School on Multi-Scale Biosystems, as well as Alexander Becker, a summer intern supported by the German Academic Exchange Service (DAAD) RISE research internship program, for his help with experiments. A. Cipitria would like to acknowledge funding from the DFG Emmy Noether grant (CI 203/2-1), from IKERBASQUE Basque Foundation for Science, and from the Spanish Ministry of Science and Innovation (PID2021-123013OB-I00).

Supporting Information

Supplementary materials, including list of abbreviations used, details on methodology, theoretical derivations, and additional vesicle and hydrogel characterization data

Conflict of Interest Disclosure

The authors declare no conflict of interest.

AUTHOR INFORMATION

Corresponding Author

Rumiana Dimova: Rumiana.Dimova@mpikg.mpg.de

ORCID IDs

Rumiana Dimova: 0000-0002-3872-8502

Amaia Cipitria: 0000-0002-9918-1512

Otto Schullian: 0000-0002-3052-5479

Nicky Tam: 0000-0002-1590-7049

Author Contributions

N. Tam did experiments and wrote the manuscript. O. Schullian analyzed experimental data and provided theoretical derivations. R. Dimova and A. Cipitria contributed to project supervision and editing of the manuscript.

REFERENCES

1. Hessvik, N. P. & Llorente, A. Current knowledge on exosome biogenesis and release. *Cell. Mol. Life Sci.* **75**, 193–208 (2018).

2. Ono, M. *et al.* Exosomes from bone marrow mesenchymal stem cells contain a microRNA that promotes dormancy in metastatic breast cancer cells. *Sci. Signal.* **7**, ra63–ra63 (2014).

3. Kooijmans, S. A. A., Vader, P., van Dommelen, S. M., van Solinge, W. W. & Schiffelers, R. M. Exosome mimetics: A novel class of drug delivery systems. *International Journal of Nanomedicine* vol. 7 1525–1541 (2012).

4. Chen, C. C. *et al.* Elucidation of Exosome Migration Across the Blood–Brain Barrier Model In Vitro. *Cell. Mol. Bioeng.* **9**, 509–529 (2016).

5. L. Arias, J., Clares, B., E. Morales, M., Gallardo, V. & A. Ruiz, M. Lipid-Based Drug Delivery Systems for Cancer Treatment. *Curr. Drug Targets* **12**, 1151–1165 (2011).

6. Ozpolat, B., Sood, A. K. & Lopez-Berestein, G. Liposomal siRNA nanocarriers for cancer therapy. *Adv. Drug Deliv. Rev.* **66**, 110–6 (2014).

7. Sabanovic, B., Piva, F., Cecati, M. & Giulietti, M. Promising Extracellular Vesicle-Based Vaccines against Viruses, Including SARS-CoV-2. *Biology (Basel).* **10**, 94 (2021).

8. Lieleg, O., Baumgärtel, R. M. & Bausch, A. R. Selective filtering of particles by the extracellular matrix: An electrostatic bandpass. *Biophys. J.* **97**, 1569–1577 (2009).

9. Yu, M. *et al.* Temperature- and rigidity-mediated rapid transport of lipid nanovesicles in hydrogels. *Proc. Natl. Acad. Sci.* **116**, 5362–5369 (2019).

10. Lenzini, S., Bargi, R., Chung, G. & Shin, J.-W. Matrix mechanics and water permeation regulate extracellular vesicle transport. *Nat. Nanotechnol.* **15**, 217–223 (2020).

11. Wiklander, O. P. B. *et al.* Extracellular vesicle in

vivo biodistribution is determined by cell source, route of administration and targeting. *J. Extracell. Vesicles* **4**, 26316 (2015).

12. Sbalzarini, I. F. & Koumoutsakos, P. Feature point tracking and trajectory analysis for video imaging in cell biology. *J. Struct. Biol.* **151**, 182–195 (2005).

13. Stellwagen, J. & Stellwagen, N. C. Internal Structure of the Agarose Gel Matrix. *J. Phys. Chem.* **99**, 4247–4251 (1995).

14. Narayanan, J., Xiong, J. Y. & Liu, X. Y. Determination of agarose gel pore size: Absorbance measurements vis a vis other techniques. *J. Phys. Conf. Ser.* **28**, 83–86 (2006).

15. Normand, V., Lootens, D. L., Amici, E., Plucknett, K. P. & Aymard, P. New insight into agarose gel mechanical properties. *Biomacromolecules* **1**, 730–738 (2000).

16. Zarrintaj, P. *et al.* Agarose-based biomaterials for tissue engineering. *Carbohydr. Polym.* **187**, 66–84 (2018).

17. Aymard, P. *et al.* Influence of thermal history on the structural and mechanical properties of agarose gels. *Biopolymers* **59**, 131–144 (2001).

18. Schwendener, R. A. Liposomes as vaccine delivery systems: A review of the recent advances. *Ther. Adv. Vaccines* **2**, 159–182 (2014).

19. Faizi, H. A., Reeves, C. J., Georgiev, V. N., Vlahovska, P. M. & Dimova, R. Fluctuation spectroscopy of giant unilamellar vesicles using confocal and phase contrast microscopy. *Soft Matter* **16**, 8996–9001 (2020).

20. Gracià, R. S., Bezlyepkina, N., Knorr, R. L., Lipowsky, R. & Dimova, R. Effect of cholesterol on the rigidity of saturated and unsaturated membranes: fluctuation and electrodeformation analysis of giant vesicles. *Soft Matter* **6**, 1472 (2010).

21. Weinberger, A. *et al.* Gel-Assisted Formation of Giant Unilamellar Vesicles. *Biophys. J.* **105**, 154–164 (2013).

22. Dimova, R. & Marques, C. *The Giant Vesicle Book*. (Taylor & Francis, 2020).

23. Arends, F., Baumgärtel, R. & Lieleg, O. Ion-Specific Effects Modulate the Diffusive Mobility of Colloids in an Extracellular Matrix Gel. *Langmuir* **29**, 15965–15973 (2013).

24. Faizi, H. A., Frey, S. L., Steinkühler, J., Dimova, R. & Vlahovska, P. M. Bending rigidity of charged lipid bilayer membranes. *Soft Matter* **15**, 6006–6013 (2019).

25. Du, H., Chandaroy, P. & Hui, S. W. Grafted poly-(ethylene glycol) on lipid surfaces inhibits protein adsorption and cell adhesion. *Biochim. Biophys. Acta - Biomembr.* **1326**, 236–248 (1997).

26. Jokerst, J. V., Lobovkina, T., Zare, R. N. & Gambhir, S. S. Nanoparticle PEGylation for imaging and therapy. *Nanomedicine* vol. 6 715–728 (2011).

27. Israelachvili, J. N. *Intermolecular and Surface Forces. Intermolecular and Surface Forces: Third Edition* (Elsevier, 2011). doi:10.1016/C2011-0-05119-0.

28. Marsh, D., Bartucci, R. & Sportelli, L. Lipid membranes with grafted polymers: physicochemical aspects. *Biochim. Biophys. Acta - Biomembr.* **1615**, 33–59 (2003).

29. Kaufmann, S., Borisov, O., Textor, M. & Reimhult, E. Mechanical properties of mushroom and brush poly(ethylene glycol)-phospholipid membranes. *Soft Matter* **7**, 9267 (2011).

30. Lee, H. & Larson, R. G. Adsorption of Plasma Proteins onto PEGylated Lipid Bilayers: The Effect of PEG Size and Grafting Density. *Biomacromolecules* **17**, 1757–1765 (2016).

31. Hiergeist, C. & Lipowsky, R. Elastic Properties of Polymer-Decorated Membranes. *J. Phys. II* **6**, 1465–1481 (1996).

32. Mertins, O. & Dimova, R. Insights on the interactions of chitosan with phospholipid vesicles. Part II: Membrane stiffening and pore formation. *Langmuir* **29**, 14552–14559 (2013).

33. Gompper, G. *et al.* Measuring bending rigidity and spatial renormalization inbicontinuous microemulsions. *Europhys. Lett.* **56**, 683 (2001).