Co-immobilization of ciprofloxacin and chlorhexidine as a long-term broad-spectrum

antimicrobial dual-drug coating for polyvinyl chloride (PVC)-based endotracheal tubes

Diana Alves[a,b,1], Maria Olívia Pereira[a,b], Susana Patrícia Lopes[a,b,*]

[a] CEB - Centre of Biological Engineering, University of Minho, 4710-057 Braga, Portugal

[b] LABBELS – Associate Laboratory, Braga/Guimarães, Portugal

Diana Alves: diana.fba88@gmail.com

Maria Olívia Pereira: mopereira@deb.uminho.pt

Susana Patrícia Lopes: supat@deb.uminho.pt

[1] Current affiliation: INL - International Iberian Nanotechnology Laboratory, Av. Mestre José Veiga, 4715-330 Braga, Portugal

*Corresponding author at: CEB - Centre of Biological Engineering, University of Minho, 4710-057 Braga, Portugal; LABBELS – Associate Laboratory, Braga/Guimarães, Portugal. Tel. No. (+351) 253 601 968 (office). E-mail address: supat@deb.uminho.pt (S.P. Lopes)

Abstract

The endotracheal tube (ETT) affords support for intubated patients, but the ever-rising incidence of ventilator-associated pneumonia (VAP) is jeopardizing its application. ETT surfaces promote (poly)microbial colonization and biofilm formation, with a heavy burden for VAP. Devising safe, broad-spectrum antimicrobial materials to tackle ETT bioburden is needful.

Herein, we immobilized ciprofloxacin (CIP) and/or chlorhexidine (CHX), through polydopamine (pDA)-based functionalization, onto polyvinyl chloride (PVC) surfaces. These were characterized and challenged with single/polymicrobial cultures of VAP-relevant bacteria (*Pseudomonas aeruginosa*; *Acinetobacter baumannii*; *Klebsiella pneumoniae*; *Staphylococcus aureus*; *Staphylococcus epidermidis*) and fungi (*Candida albicans*).

Coatings imparted PVC surfaces with homogeneous morphology, varied wettability, and low roughness. Coated surfaces exhibited sustained CIP/CHX release, retaining long-term (10 days) stability. Surfaces evidencing no A549 lung cell toxicity exhibited broad-spectrum anti-biofilm activity. CIP/CHX co-immobilization resulted in better outcomes than CIP or CHX coatings, reducing bacteria up to >7 Log_{10}, and modestly distressing (~1 Log_{10}) *C. albicans*. Anti-biofilm effectiveness endured for dual biofilms, substantially preventing bacterial populations and fungi (~2.7 Log_{10}) in *P. aeruginosa/C. albicans* consortia. A less pronounced antifungal effect (~1 Log_{10} reduction) was found in triple-species communities, but fully preventing *P. aeruginosa* and *S. aureus* populations.

CIP/CHX co-immobilization holds a safe and robust broad-spectrum antimicrobial coating for PVC-ETTs, with the promise laying in reducing VAP incidence.

Keywords: co-immobilization; endotracheal tube; long-term coating; polymicrobial biofilm; ventilator-associated pneumonia

1. Introduction

The success of the current clinical practice is highly dependent on the use of medical devices or implants [1]. In this regard, the endotracheal tube (ETT) has been an elemental device in providing airway patency in patients requiring mechanical ventilation e.g., in cases like surgeries using general anesthesia, critical care situations, or a traumatically compromised airway [2]. Mechanical ventilation has long been acknowledged as a life-support practice which has picked up during the latest COVID-19 pandemic, given the unprecedented number of patients that had to be admitted to intensive care units (ICU) with severe symptoms of respiratory failure [3,4]. Once placed, the ETT becomes potentially harmful to critically ill patients undergoing long-term artificial ventilation, as it impairs natural defense mechanisms (e.g., cough reflex; upwards mucosal ciliated transport; clearance mechanism operative in the airway), and causes mechanical tissue irritation due to breathing cycles [5,6]. Furthermore, the ordinary ETTs, which are often made of flexible materials (e.g., polyvinyl chloride, PVC), are devoid of antimicrobial activity, being continuously exposed to ambient air, and providing an ideal source for microbial colonization and the development of a so-called biofilm, both early and frequent phenomena contributing to the development and relapses of ventilator-associated pneumonia (VAP). Indeed, microorganisms reach the ETT's distal end due to contaminated oropharyngeal contents or, eventually, gastric secretion reflux [7]. Accumulation and coaggregation of common commensal bacteria further promote the recruitment of opportunistic nosocomial pathogens, developing jointly a biofilm with serious implications ultimately leading to VAP [8]. The ETT biofilm correlates with VAP pathogenesis, as microbial cells encase themselves in a self-produced matrix of extracellular polymeric substances, conferring them protection against antimicrobial treatments and the host immune system [9]. The diversity of organisms readily colonizing the ETT surface, therefore, involve drug-resistant top-priority pathogens from the ESKAPE bacterial panel such as *Pseudomonas aeruginosa*, *Acinetobacter baumannii*, *Klebsiella pneumoniae,* or *Staphylococcus aureus*, but also others that may include commensal bacteria (*Staphylococcus epidermidis*) or even fungi (*Candida albicans*) with pathogenic potential, all contributing to the polymicrobial and recalcitrant nature of ETT biofilms [10–12].

VAP is the commonest life-threatening nosocomial infection in the developed world accounting for an estimated 22% of prevalence [13], and contributing to up to 50% of all cases in ICUs [14]. Its discrepant morbidity/mortality rates (16-44%) ICU/hospital length of stay (13-26.6 days) [15–17], and incidence range (11-84%) [16,18], with ICU antibiotic prescriptions nearby 50%, are all alarming indicators of clear action needed. Given the difficulties associated with finding an effective treatment for VAP, reducing ETT bioburden through ETT surface` modification is likely the most suitable approach to avoid VAP. Despite years of technological progress, there are still limited reports on ETT coatings. Overall, studies employ active (directly compromising surface´ microbial colonization), passive (contamination-resistant surface with altered composition and/or pattern), or combinatorial

antimicrobial and antifouling approaches, but most limitedly addressing antimicrobial activity and/or safety-of-use [19]. In addition, studies have proven insufficient in tackling polymicrobial ETT biofilms, an underappreciated issue with a significant fate for VAP. Therefore, the development of pertinent, that is, suitable and highly efficient materials endowed with broad-spectrum antimicrobial activity, biocompatibility, and cost-effectiveness features, tends to be a gold solution for the next generation of ETTs, with promise in preventing VAP.

Within the wide range of surface functionalization strategies, the bio-inspired polydopamine (pDA) coating approach [20] stands out as one that fulfills all the aforementioned requirements. In this approach, substrata are simply immersed in an alkaline solution of dopamine that then self-polymerizes and gives rise to an adhesive film with a thickness in the nanometer range. Alongside its simple processing conditions, material independence, strong reactivity for secondary functionalization, and biocompatible features have triggered its application in the immobilization of different antimicrobials to impart biomaterials' surfaces with anti-infective properties [21,22]. Chlorhexidine (CHX) has been extensively applied in different hospital protocols for oral hygiene of intubated patients to reduce the incidence of VAP [23]. CHX immobilization has shown great potential while imparting metallic surfaces with antimicrobial features against Gram-positive bacteria in the context of orthopedic infections [21]. Impregnation of ETTs with antiseptics, including CHX, has also led to auspicious antimicrobial outcomes toward drug-resistant bacteria and fungi [24–26]. Ciprofloxacin (CIP) is a second-generation quinolone with proven broad-spectrum activity against both Gram-negative and Gram-positive bacteria. Guidelines have recommended CIP as a second antipseudomonal agent in dual-combination regimens in VAP management [27], thus holding promise to be further immobilized on ETT surfaces.

This study aimed to devise a novel and safe ETT coating supporting antimicrobial activity against a wide range of VAP-relevant species that include bacteria and fungi. For that, a pDA-based functionalization strategy was explored for the (co-)immobilization of CIP and/or CHX on PVC surfaces, being the modified surfaces physically characterized (morphology, roughness, wettability), and inspected for their effectiveness in inhibiting the development of single-, dual- and triple-species biofilms without compromising the viability of A549 lung epithelial cells.

2. Materials and Methods

2.1 Microbial strains and culture conditions

Five model reference bacterial strains and one fungal strain were used throughout this study, namely *Pseudomonas aeruginosa* ATCC 27853, *Klebsiella pneumoniae* ATCC 11296, *Staphylococcus aureus* ATCC 25923 (all from American Type Culture Collection), *Acinetobacter baumannii* NIPH 501^{T} (kindly provided by Professor Alexandr Nemec, National Institute of Public Health in Prague) and *Staphylococcus epidermidis* CECT 4183 (from the Spanish Type Culture Collection). The fungal

reference strain *Candida albicans* SC5314 was also used. All bacterial/fungal strains were stored at
80 °C ± 2 °C in a broth medium with 20% (v/v) glycerol.

All microbial strains were plated from the frozen stock solutions and first streaked on a plate
containing tryptic oy agar (TSA, Liofilchem) or a Sabouraud dextrose agar (SDA, Liofilchem) plate,
respectively for bacteria and fungi. After incubation (37 °C for ± 24 h), some colonies were then
collected from the agar plates and grown overnight in batches of tryptic soy broth or Sabouraud
dextrose broth (TSB/SDB, Liofilchem) at 37 °C under agitation (120 rotations per minute, rpm) on a
horizontal shaker (Biosan OS-20). Bacterial and fungal cells were harvested by centrifugation (9000 *g*,
5 min) and washed in sterile saline solution (0.9% w/v NaCl) or phosphate-buffered saline (PBS, pH
7.4), respectively. The concentration of bacterial suspensions was then adjusted by measuring the
absorbance at 620 nm (EZ Read 800 Plus, Biochrom) and using previously established standard
curves, while fungal suspension concentration was adjusted after estimating cell numbers in a
Neubauer counting chamber.

2.2 Preparation of antimicrobial stock solutions
Stock solutions of two antimicrobial agents, CIP and CHX (both from Sigma-Aldrich, St. Louis, MO,
USA) were prepared by dissolving the powders in hydrochloric acid (HCl 0.2 M) or absolute ethanol
and further diluted in growth medium or PBS, depending on the procedure performed (susceptibility
testing and compounds release, respectively). Storage was according to the manufacturer's
instructions.

2.3 PVC preparation and functionalization
For surface functionalization, 1 mm-thickness unplasticized sheets of PVC (purchased from
Goodfellow Cambridge Ltd, Cambridgeshire, UK) were cut into 1x1 cm-squared coupons. Before
surface modification, coupons were subjected to an ultrasonic cleaning treatment in commercial
detergent (Sonasol, Henkel Ibérica, Portugal) for 5 min to remove any traces of impurities and grease.
After being thoroughly rinsed with distilled water, cleaned PVC surfaces were sterilized with 70% v/v
ethanol for 30 min, rinsed with sterile ultrapure water, and finally irradiated with UV light for 1 h. To
confer PVC surfaces with antimicrobial features, PVC functionalization with CIP and/or CHX was
performed using a previously reported one-step approach for the immobilization of CHX on stainless
steel [21], the so-called mussel-inspired coating strategy. The methodology scheme used for PVC
functionalization is depicted in Figure 1. Briefly, PVC coupons were firstly immersed in 7 mL of a 2
mg/mL solution of dopamine (Sigma) freshly prepared in 10 mM bicine buffer pH 8.5 (Sigma) for 18
h at room temperature under agitation (70 rpm). After dopamine polymerization, a pDA film/coating
was allowed to deposit on the PVC surface (Figure 1A). In regards to PVC functionalization with
antimicrobials, 2 mg/mL dopamine was added to CHX and/or CIP (that is, alone or combined) at
concentrations ranging from 0.5 to 2 mg/mL, which were dissolved together in 10 mM bicine buffer

pH 8.5. The PVC coupons were simply immersed in this solution, following the abovementioned
conditions. PVC surfaces modified with CIP, CHX, or CIP/CHX combined were obtained following
dopamine polymerization and antimicrobial immobilization (Figure 1B). All modified PVC surfaces
were then rinsed with sterile ultrapure water and air-dried for further application. With this
functionalization technique, it was expected that compounds would be incorporated throughout the
full thickness of the pDA film [28]. For comparison purposes, unmodified PVC (before pDA coating
or antimicrobial(s) immobilization) and pDA-coated surfaces were used in further assays.

145
Figure 1. Scheme of the methodology used in the PVC functionalization with CHX and/or CIP. (A) PVC immersion in an
alkaline solution (pH 8.5) of dopamine (at 2 mg/mL) resulted in its polymerization and subsequent deposition of an adhesive
film called polydopamine (pDA). (B) CHX and/or CIP immobilization was performed by immersion of PVC on dopamine
(at 2 mg/mL) combined with each or both compounds (at 0.5 mg/L or 2 mg/mL), resulting in CIP-, CHX-, or CIP/CHX-
modified PVC surfaces upon dopamine polymerization and antimicrobial(s) immobilization.

2.4 Antimicrobial activity of immobilized compounds

To inspect whether CHX and/or CIP retained antimicrobial activity upon immobilization, the
antimicrobial properties of the modified surfaces were performed as previously reported [21]. Briefly,
each microbial suspension was adjusted to ~1×10^6 CFU/mL as described above, and 20 μL of the
microbial culture was placed at the top of each unmodified/modified PVC surface and incubated at
37 °C (static conditions). The suspension was allowed to dry on the top of unmodified/modified PVC
surfaces, being then placed with the face exposed to microbial culture in contact with agar
(TSA/SDA). Agar plates were then incubated at 37 °C for 24 h, and the presence or absence of

microbial growth (contact-killing) on agar was further inspected through visual observation. The
antimicrobial activity of CIP- and CHX-modified PVC surfaces were also evaluated using an
adaptation of the Kirby-Bauer disc diffusion method [29]. For that, modified (vs unmodified) surfaces
were placed on top of TSA/SDA plates previously streaked with each microbial suspension adjusted
to $\sim 1 \times 10^8$ CFU/mL, which were then incubated (37 °C) for up to 72 h. The presence or absence of an
inhibition zone was further investigated and annotated.

2.5 Surface characterization

2.5.1 Surface morphology

Surface morphology was observed by Scanning Electron Microscopy (SEM) using an ultra-high
resolution Field Emission Gun SEM (FEG-SEM, NOVA 200 Nano SEM, FEI Company). Before
analysis, samples were first covered with a very thin film (5 nm) of Au–Pd (80–20 wt%).
Topographic images were obtained with a secondary electron detector using the following parameters:
acceleration voltage of 10 kV, ~5 mm stage distance, and 10 000 × and 50 000 × magnification.

2.5.2 Surface roughness

Atomic Force Microscopy (AFM) measurements were performed at room temperature using a CSI –
Nano-Observer Atomic Force Microscope, operating in tapping mode. The scanning area per sample
was fixed at 10 µm × 10 µm at 512-pixel resolution. Surface morphology and roughness analysis were
then conducted using Gwyddion software.

2.5.3 Surface wettability

Surface wettability was investigated by measuring the static water contact angle, using a sessile drop
method, in an automated contact angle measurement apparatus (OCA 15 Plus, Dataphysics, Germany)
that allows image acquisition and data analysis. Contact angles were measured using 3 µL drops of
ultrapure water.

2.6 CHX and CIP release profiles

To ascertain the release profiles of both antimicrobial compounds (CIP and CHX), the CIP- and
CHX-modified PVC coupons were placed in 6-well microtiter plates (Orange Scientific, USA) to
which 4 mL of PBS (pH 7.4) were added, and then incubated at 37 °C under constant agitation at 120
rpm. The PBS was all collected and refreshed at different time points (every 24 h up to 10 days). The
amount of released CHX or CIP was then determined by ultraviolet-visible spectroscopy (UV–Vis),
measuring the absorbance at 255 and 270 nm, respectively. The absorbance values were then
converted to concentration values using calibration curves previously established.

2.7 Cytotoxicity determination

Cytotoxicity was evaluated on human lung epithelial A549 cells (ATCC CCL-185), according to ISO 10993-5:2006 [30]. Cells were grown in Dulbecco-modified eagle medium (DMEM, Biochrom) supplemented with 10% fetal bovine serum (FBS, Gibco) and 1% protective antibiotic solution (ZellShield™, Biochrom) at 37 °C and 5% CO_2. Once confluence was achieved, cells were detached using trypsin-EDTA solution (0.25%/0.02%) in PBS without Ca^{2+} and Mg^{2+} (PAN Biotech GmbH, Germany), and 100 μL of cell suspension adjusted to 1×10^5 cells/mL, was transferred per well to a 96-well microtiter plate. In parallel, unmodified-/modified-PVC surfaces were inserted in 24-well plates and 1 mL of supplemented DMEM was added to each well. Both plates with cells and surfaces were incubated at 37 °C and 5% CO_2 for 24 h. After this period, the supernatant was removed and 100 μL of the medium that was in contact with the surfaces was added. Fresh-supplemented DMEM was also added as a positive control. The plate was then incubated (37 °C; 5% CO_2) for an additional 24 h. In the dark, 20 μL of MTS (3-(4,5-dimethylthiazol-2-yl)-5-(3-carboxymethoxyphenyl)-2-(4-sulfophenyl)-2H-tetrazolium) inner salt (Promega) was added to each well and the plate was further incubated for 1 h at 37 °C, 5% CO_2. The absorbance of the resulting solution was measured at 490 nm. The percentage of cell viability was calculated by the absorbance ratio between the cell growth in the presence of the coating and the control growth (cell growth in supplemented DMEM).

2.8 Anti-biofilm performance of modified PVC surfaces against single species and polymicrobial consortia

The ability of the prepared modified surfaces to prevent biofilm formation was evaluated against single-species and polymicrobial cultures encompassing the aforementioned bacterial and fungal species. Overnight cultures were used to prepare microbial inoculum with approximately 1×10^6 CFU/mL in TSB (bacterial cultures) or RPMI 1640 (fungal culture). For dual and triple-species consortia, a proportion of 1:1 and 1:1:1, respectively, of each suspended bacterial/fungal inoculum was used. Unmodified- and modified-PVC squared coupons were then inserted into a 24-well microtiter plate (Orange Scientific, USA) and inoculated with 1 mL of microbial suspensions prepared as described. As stated above, unmodified PVC and pDA-coated surfaces were used for comparison purposes. The plates containing the coupons were kept at 37 °C for 24 h, under static conditions. Coupons were then washed twice with saline solution (for bacteria) or PBS (for fungi) and transferred to new wells filled with 1 mL of saline solution or PBS. Adhered bacterial cells were removed from the PVC coupons by ultrasonic bath treatment in a Sonicor SC-52 (Sonicor Instruments) operating at 50 kHz, for 6 min, while fungal-adhered cells were removed by scrapping the surfaces (parameters previously optimized). The biofilm samples, after detached from surfaces, were afterward collected, and vortexed to disrupt possible cell aggregates, 10-fold serially diluted, and plated into appropriate agar plates that were incubated for 16-48 h at 37 °C in an aerobic incubator before biofilm cell enumeration. Estimation of bacterial and fungal cells was made on unspecific culture agar media (TSA and SDA, respectively) in single-species consortia. For microbial isolation in

polymicrobial consortia, specific solid growth media were employed. *Pseudomonas* Isolation Agar
(PIA, Sigma) was used to specifically select *P. aeruginosa* when in combination with *S. aureus*, *S.*
epidermidis, and *K. pneumoniae,* while TSA supplemented with 10 mg/L of amphotericin B (Sigma)
was used to isolate *P. aeruginosa* while suppressing *C. albicans* growth. In turn, *C. albicans* was
grown in SDA supplemented with 30 mg/L of gentamicin (Nzytech) to suppress *P. aeruginosa* growth.
S. aureus and *S. epidermidis* were both selected on Mannitol Salt Agar (MSA, Liofilchem) and *K.*
pneumoniae on Klebsiella ChromoSelect Selective Agar Base (Sigma). Unlike for the other consortia,
no selective media for *A. baumannii* was found, so the total number of adhered cells in TSA was
compared with the growth of *P. aeruginosa* only in PIA (allowing to infer about the differential
amount of *A. baumannii* cells in consortia.

2.9 Interpretation of anti-biofilm performance outcomes
The outcomes from the antimicrobial performance resulting from the co-immobilization of CHX and
CIP were classified as synergism or facilitation according to a previously reported methodology [31].
An outcome was classified as "synergism" when the coating with combined compounds was able to
prevent the adhesion of a greater fraction of microorganisms than expected if the compounds were
acting independently. The term "facilitation" was used to classify an outcome in which the coating
with combined compounds was better than the best of the single compounds, but not better than if the
antimicrobials were acting independently. For their calculation, synergism was considered when the
equation $\text{Log}_{10}(S_C) - \text{Log}_{10}(S_{CHX}) - \text{Log}_{10}(S_{CIP}) + \text{Log}_{10}(S_{MIX}) < 0$ was valid. In turn, facilitation was
considered when both equations $\text{Log}_{10}(S_{MIX}) - \text{Log}_{10}(S_{CHX}) < 0$ and $\text{Log}_{10}(S_{MIX}) - \text{Log}_{10}(S_{CIP}) < 0$
were valid. In these equations, S_C refers to the microbial density obtained in the control (unmodified
PVC surfaces), and S_{CHX}, S_{CIP}, and S_{MIX} to the surviving cell density after being in contact with
surfaces functionalized with CIP, CHX, or both antimicrobials combined (CIP/CHX), respectively.

2.10 Statistical analysis
Statistical analysis and graphs were performed using the GraphPad Prism software package
(GraphPad Software version 8.2.0). Means and standard deviations (SDs) were calculated for all
experimental conditions tested. Statistical analysis was carried out by one-way or 2way ANOVA
followed by Tukey's multiple comparisons, and p-values < 0.05 were considered significant. At least,
three independent experiments in triplicate were performed for all experiments.

3. Results

3.1 Antimicrobial screening of CIP- or CHX-modified PVC surfaces

To inspect whether CIP and CXH would retain antimicrobial activity upon immobilization, an
antimicrobial screening was made, based on the ability of CIP- or CHX-modified surfaces to prevent

microbial growth by contact-killing, and by antimicrobial diffusion/release on microbial-embedded

agar media. The outcomes from the contact-killing and "zone inhibition" tests are depicted in Table 1.

Table 1. Antimicrobial activity and qualitative release of CHX or CIP from PVC-modified surfaces. A) Microbial growth
after 24 h contact with CHX- or CIP-modified surfaces, where "+" is indicative of visible bacterial growth and "–" means no
visible growth observed. B) Release of CHX or CIP on solid agar, qualitatively evaluated by the presence (P) or absence (A)
of an inhibition zone. pDA-coated surfaces were also tested and used for comparison

A)

	pDA-coated surface	CHX-modified PVC		CIP-modified PVC	
		CHX 0.5 mg/mL	CHX 2 mg/mL	CIP 0.5 mg/mL	CIP 2 mg/mL
P. aeruginosa	+	-	-	-	-
A. baumannii	+	+	-	+	-
K. pneumoniae	+	-	-	-	-
S. aureus	+	-	-	-	-
S. epidermidis	+	-	-	-	-
C. albicans	+	-	-	+	+

B)

	pDA-coated surface	CHX-modified PVC		CIP-modified PVC	
		CHX 0.5 mg/mL	CHX 2 mg/mL	CIP 0.5 mg/mL	CIP 2 mg/mL
P. aeruginosa	P	A	P	P	P
A. baumannii	P	A	A	A	P
K. pneumoniae	P	P	P	P	P
S. aureus	P	P	P	P	P
S. epidermidis	P	P	P	P	P
C. albicans	P	A	A	A	A

Results showed that all microbial species, including bacteria and fungi, were inhibited after contacting

PVC surfaces immobilized with CHX at 2 mg/mL (Table 1A). When a lower concentration of CHX

(0.5 mg/mL) was used, the obtained PVC surfaces lost their ability to prevent the growth of *A.*

baumannii but kept antimicrobial features against all the other species. Regarding CHX diffusion on

agar plates (Table 1B), inhibition zones observed for bacterial species such as *K. pneumoniae*, *S.*

aureus, and *S. epidermidis* indicated CHX release from the coupons. For its higher concentration

tested (2 mg /mL), however, the released CHX was still not able to prevent the growth of *A.*

baumannii and *C. albicans*. Also, surfaces functionalized with a lower concentration of CHX lost

their ability to inhibit the growth of *P. aeruginosa*, when compared with those immobilized with a

higher amount (Table 1B). In turn, immobilization of CIP at its highest tested concentration (2

mg/mL) generated PVC surfaces with the ability to prevent microbial growth by contact with all
bacterial species investigated (Table 1A). However, no antimicrobial effect was observed against the
fungal strain *C. albicans*. When coming to surfaces functionalized with a lower concentration of CIP
(0.5 mg/mL), these lost the ability to prevent the growth of *A. baumannii*, as compared to the previous
finding. These effects were comparable to those observed when it comes to the ability of released CIP
to diffuse through agar plates and inhibit bacterial growth (Table 1B).

3.2 Characterization of CIP and/or CIP-modified surfaces

3.2.1 Surface morphology

The surface morphology of PVC surfaces modified with CIP, CHX, and even with both combined
(CIP/CHX) was characterized by SEM (Figure 2).

Figure 2. Surface morphology, obtained by SEM. (A) unmodified PVC surface; (B) pDA-coated surface; (C) PVC surface modified with CHX at 0.5 mg/mL or with; (D) CHX at 2 mg/mL; (E) CIP at 0.5 mg/mL; (F) CIP at 2 mg/mL; (G) CIP/CHX at 0.5 mg/mL, and (H) CIP/CHX at 2 mg/mL. The scale bars in the inset and image (in A) indicate 2 and 10 μm, respectively.

Bare PVC, that is, unmodified PVC surface (Figure 2A) exhibited a smooth morphology with some micropores, likely attributed to the evaporation of solvent during its production [32]. The pDA film formation on PVC surfaces (Figure 2B) has been suggested by the absence of micropores throughout the surface and the presence of self-polymerized pDA particles resulting from the bulk solution [33]. Dopamine polymerization in the presence of CHX and/or CIP resulted in altered morphologies

compared to bare PVC, but preserved the structure (in clusters) of pDA-coated surfaces. In general,

one-step immobilization of both compounds, either alone or combined, yielded surfaces with a more

homogeneous appearance with clusters more evenly distributed throughout the surfaces (Figure 2, C

to H). A more complete coverage of the surface was observed for CHX (Figure 2, C and D) when

compared to surfaces functionalized with CIP alone (Figure 2, E and F). Increasing the initial

concentration of the compound used for PVC functionalization apparently promoted the increase in

the number of agglomerates (Figure 2, D and F vs. C and E, respectively). Co-immobilization of CHX

and CIP (CIP/CHX; Figure 2, G and H) yielded surfaces with morphology and coverage similar to the

ones incorporating CHX alone.

3.2.2 Surface roughness and wettability

Changes in surface roughness and wettability caused by the different immobilization approaches were

investigated by AFM and by measuring the static water contact angles, respectively (Figure 3).

307
Figure 3. Surface roughness and wettability. (A) Average roughness and (B) static water contact angles of PVC surfaces
before and after immobilization with CIP or CHX or CIP/CHX at concentrations of 0.5 and 2 mg/mL. Unmodified PVC and
pDA-coated surfaces were used for comparison. The results are shown as mean ± SDs. (****) $p < 0.0001$, vs. unmodified
PVC, one-way ANOVA, Tukey`s multiple comparison test.

The average surface roughness, expressed as R_A (Figure 3A), was determined from the pictures

obtained from AFM analysis (Figure S1 in Supplementary Material). Overall, results showed that

pDA coating did not introduce significant changes in the PVC surface's roughness as well as further

functionalization with CIP and/or CHX. An exception was observed for PVC surfaces functionalized

with CIP at 2 mg/mL, which displayed a significant increase (4-fold higher) in that parameter.

Although not significantly different in most cases, results suggest an increase in the modified surfaces'

roughness as the concentration of immobilized compounds increases.

Water contact angles (Figure 3B) evidenced a hydrophobic character for unmodified PVC surfaces

$(92.6^{\circ} \pm 3.2^{\circ})$. Dopamine polymerization imparted the PVC surfaces with hydrophilic properties, as

evidenced by the significant decrease of the water contact angle to below 90° (27.3° ± 8.5°), a well-
established observation found on other materials functionalized with pDA [22,34]. Concerning
modified surfaces, the incorporation of CHX during dopamine polymerization resulted in an increase
in the water contact angle (75.3° ± 20.4° and 87.1° ± 18.0°), turning surfaces with more hydrophobic
features. On the other hand, PVC functionalization with CIP did not greatly interfere with the
hydrophilic properties imparted by pDA alone. Co-immobilization of CHX and CIP (CIP/CHX)
yielded surfaces with wettability similar to the CHX-immobilized ones. Overall, increasing the initial
concentration of the immobilized compounds, when alone or combined, slightly increased the
hydrophobic properties of the modified surfaces.

3.3 CHX and CIP release profiles

The released amount of CHX and CIP from functionalized PVC surfaces was monitored each day for
up to 10 days, by measuring the absorbance by UV-Vis and further determining the released amount
of each compound through previously established calibration curves. The profiles obtained for CIP
and CHX cumulative released mass are presented in Figure 4.

335

336
337
Figure 4. Antimicrobials release from coated surfaces. (A) Cumulative release of CIP; and (B) of CHX from PVC surfaces
functionalized with each compound at 0.5 and 2 mg/mL. Panel C depicts the outcomes from contact-killing and release of
CIP or CHX immobilized alone, and CIP/CHX co-immobilized on PVC surfaces at 0.5 and 2 mg/mL, at days 4 and 10
against *K. pneumoniae*. Bacterial growth after 24 h contact with modified surfaces is indicated at the bottom right of each
image, where "+" is indicative of visible bacterial growth and "–" means no visible growth observed. The release of
antimicrobials on solid agar was qualitatively evaluated by the presence or absence of an inhibition zone. pDA-coated
surfaces were also tested and used for comparison.

Overall, there was an initial burst release of CIP immobilized at both concentrations, which was

observed in the first 24 h after its immobilization on PVC surfaces (Figure 4A). During the following

days, CIP could not be detected (no CIP mass added). A comparable trend was noted for PVC

surfaces functionalized with a higher CIP concentration (2 mg/mL), however, showing an enhanced

released amount of CIP in comparison to those surfaces immobilized with a lower CIP concentration.

A significantly higher cumulative mass was found for CHX (Figure 4B), as compared to CIP, with

cumulative mass estimations nearby 40 µg after 10 days of release. As for CIP, a rampant rise in CHX

amount was found for the early 24 h, followed by a slower release of the antimicrobial in the

remaining days. Initially, the amount of liberated CHX increased as the immobilized CHX

concentration also increased (< 4 h). From then on, PVC surfaces functionalized with a lower CHX

concentration (0.5 mg/mL) started to release higher CHX amounts than those immobilized with CHX

at 2 mg/mL.

As stated above, the apparent CIP depletion in the PBS supernatant for the period after 24 h of release,

was likely attributed to a low-limit detection. To support this, the presence of released CIP, alone and

combined with CHX, was further investigated on days 4 and 10, based on direct contact-killing and

release approaches, as demonstrated in panel C of Figure 4. *K. pneumoniae*, shown as the most

susceptible species to both CIP and CHX in broth microdilution testing (Table S1 of Supplementary

Material), was used so that lower antimicrobial concentrations could be detected. At day 4, all CIP-

and CIP/CHX-modified surfaces exhibited contact-killing and formed inhibition zones against *K.*

pneumoniae. Such results still evidenced immobilization of CIP, either alone or combined, on the

PVC surfaces but in small quantities likely not detected by UV spectroscopy. The presence of CHX in

the supernatant was also appraised by means of contact-killing and release assets. As expected, the

absence of an inhibition zone may be a reflection of its low release concentration at day 4 (Figure 4B),

which was found below its MBC (Table S1). After 10 days of release, no inhibition zone was

observed for any modified surface, but all CIP, CHX, and CIP/CHX-modified surfaces retained their

contact-killing activity (as indicated by the symbol "(-)" at the bottom right of the images), evidence

of an effective antimicrobial immobilization.

3.4 Cytotoxicity against A549 lung epithelial cells

373   Aiming at evaluating the toxicity of PVC-modified surfaces to lung epithelial cells, PVC surfaces

374   immobilized with CIP and CHX, alone or combined, were placed in contact with a DMEM culture

375   medium, which was further exposed to A549 cells. The cell viability (expressed as a percentage), of

376   indirectly contacting PVC surfaces immobilized with CIP and/or CHX is presented in Figure 5.

Figure 5. Cell cytotoxicity. Viability of A549 lung epithelial cells after indirect contact with PVC surfaces functionalized with CIP or CHX at the highest concentration tested (2 mg/mL) and with CIP/CHX at 2 mg/mL and lower concentrations (1 mg/mL; 0.5 mg/mL, and 0.25 mg/mL). Unmodified PVC and pDA-coated surfaces were used for comparison. A threshold for cell toxicity of 70% viability was used, which is indicated by a dotted line. The results are shown as mean ± SDs. (****) $p < 0.0001$, vs. unmodified PVC, one-way ANOVA, Tukey`s multiple comparison test.

A large percentage of A549 viable cells was obtained when in indirect contact with unmodified PVC before and after pDA coating (Figure 5). Further functionalization of PVC surfaces with CIP or CHX at 2 mg/mL also produced no significant cytotoxic effect on A549 eukaryotic cells, as compared with unmodified surfaces. In turn, CIP/CHX co-immobilization with the highest antimicrobial concentration tested (2 mg/mL) on a PVC surface resulted in a decline in the number of viable cells higher than 30% (Figure 5B), evidence of toxicity (< 70% cell viability) towards eukaryotic cells. In a way to reduce cytotoxicity, doses lower than 2 mg/mL were tested for co-immobilization, and the viability of A549 cells exposed to DMEM medium which was put before in contact with these modified surfaces was also appraised. Cytotoxicity was found to be dose-dependent, with the highest antimicrobials concentrations (2 mg/mL and 1 mg/mL) causing toxic effects on A549 cells, contrariwise to CIP/CHX doses lesser than 0.5 mg/L, which did not affect cell viability. Based on these findings, only modified PVC surfaces with proven biocompatibility proceeded to the next anti-biofilm assays.

3.5 Efficacy of modified PVC surfaces in preventing single-species biofilms

As microbial adhesion is the preceding step of biofilm formation, which represents an early and recurrent event in intubated patients [8,35–37], the next stage was to appraise the effectiveness of the modified-PVC surfaces in inhibiting microbial adhesion, and so preventing the biofilm development by microorganisms commonly associated with VAP, namely *P. aeruginosa*, *A. baumannii*, *K. pneumoniae*, *S. aureus*, *S. epidermidis*, and *C. albicans*. Thus, PVC surfaces modified with CIP and/or CHX at the highest concentrations displaying no cytotoxicity (0.5 mg/mL and 2 mg/mL), were

403 challenged for 24 h with microbial suspensions of each aforementioned species, and the number of

404 cultivable cells that adhered to the surfaces was enumerated after detachment (Figure 6).

Figure 6. Efficacy against single-species biofilms. PVC surfaces modified with CIP and/or CHX challenged with single-species biofilms formed by *P. aeruginosa* (A), *A. baumannii* (B), *K. pneumoniae* (C), *S. aureus* (D), *S. epidermidis* (E), and *C. albicans* (F). Unmodified PVC and pDA-coated surfaces were used for comparison. The threshold value marked by the dotted line represents the detection limit of CFU counting. The results are shown as mean ± SDs. (****) p < 0.0001, vs. unmodified PVC, one-way ANOVA, Tukey`s multiple comparison test.

Results show that the ability to form biofilms on bare/unmodified PVC surfaces relied on the

microbial species, with most biofilms achieving high cell densities varying from 6.83 and 7.52 Log_{10}

CFU/mL after 24 h. Lower cell concentrations, however, were found for *K. pneumoniae* (Figure 6C)

and *C. albicans* (Figure 6F), reaching 5.64 and 4.57 Log_{10} CFU/mL on average, respectively. As

anticipated, the pDA film on PVC had no effect on the adhesion of any microbial species, as

evidenced by the similar number of adhered cells found compared to the unmodified PVC control.

Functionalization with CHX and/or CIP rendered the PVC surfaces with wide-ranging anti-biofilm

activities. CHX-functionalized surfaces were not enabled to prevent biofilm formation by *P.*

aeruginosa (Figure 6A) and *A. baumannii* (Figure 6B), regardless of the CHX initial concentration

applied. However, significant reductions were found for the remaining biofilm populations (Figure 6,

C-F). A dose-dependent reduction was observed for *S. aureus*, by 3.8 Log_{10} (CHX 0.5 mg/mL) and

5.5 Log_{10} (CHX 2 mg/mL) (Figure 6D), but also for *C. albicans* biofilms, which was significantly

inhibited (~ 1.1 log_{10}) when CHX 2 mg/mL was immobilized on PVC surfaces (Figure 6F).

As for CHX, great reductions and, in most cases, a dose-dependent anti-biofilm effect were observed

for CIP-functionalized PVC surfaces. For instance, *P. aeruginosa* decreased from 6.26 to 1.60 Log_{10}

CFU/mL (Figure 6A), *A. baumannii* decreased from 4.60 to 2.68 Log_{10} CFU/mL and *S. aureus* from

2.73 to 1.65 Log_{10} CFU/mL (Figure 6D) when grown on PVC immobilized with CIP at 2 mg/mL

compared to CIP at 0.5 mg/L. CIP immobilization at 2 mg/mL still caused a slight reduction (< 1

log_{10}) in the number of fungal biofilm cells (Figure 6F). The highest inhibitory outcomes were found

for biofilms of *K. pneumoniae* (Figure 6C), *S. aureus* (Figure 6D), and *S. epidermidis* (Figure 6E),

with the modified surfaces, substantially impairing their developments (cell numbers were found
below the thresholds for cultivability).

Interestingly, co-immobilization of CIP and CHX, exhibited a significant anti-biofilm effect against
all consortia investigated. The estimated outcomes of PVC co-immobilization regarding its anti-
biofilm performance (Table S1 of Supplementary Material) demonstrated a facilitative effect against
all microbial species and even a synergic outcome against *P. aeruginosa*, *A. baumannii*, and *C.*
albicans. For better understanding, calculations showed better anti-biofilm performance of CIP-CHX
co-immobilization than the best of the single compounds acting on all consortia, also enabling to
prevent the adhesion of a greater fraction of microbial cells in *P. aeruginosa*, *A. baumannii*, and *C.*
albicans biofilm communities than expected if the compounds were acting independently.

3.6 Efficacy of modified PVC surfaces against dual-species biofilms

Considering the great prevalence of *P. aeruginosa* on VAP [11,38,39], the PVC surfaces immobilized
with CIP and CHX, alone or combined, were then evaluated against the biofilm formation of this
species combined with each one of the other tested microbial species (Figure 7).

Figure 7. Efficacy against dual-species biofilms. Effect of PVC surfaces before and after pDA-based coating and
immobilization of CIP and/or CHX against dual-species biofilms of *P. aeruginosa* and *A. baumannii* (A), *P. aeruginosa* and
K. pneumoniae (B), *P. aeruginosa* and *S. aureus* (C), *P. aeruginosa* and *S. epidermidis* (D), and *P. aeruginosa* and *C.*
albicans (E). Unmodified PVC and pDA-coated surfaces were used for comparison. The threshold value marked by the
dotted line represents the detection limit of CFU counting. The results are shown as mean ± SDs. (****) $p < 0.0001$ vs. *P.*
aeruginosa growth on unmodified PVC; and ([##]) $p < 0.01$ or ([####]) $p < 0.0001$ vs. other than *P. aeruginosa* species growth on
unmodified PVC, 2way ANOVA, Tukey`s multiple comparison test.

Overall, dual-species biofilms were mostly governed by *P. aeruginosa*, regardless the PVC material
where the consortia were formed. Biofilms developed on unmodified surfaces (PVC and pDA)
presented cell numbers in orders of magnitude similar to those observed for *P. aeruginosa* alone (see
Figure 6A), denoting low influence of the other microbial species in consortia in *P. aeruginosa*
growth.

CHX-modified surfaces were able to significantly disturb all other than *P. aeruginosa* populations in
the consortia (Figure 7, A-E), lowering CFU counts to below the detection limit or even leading to full

growth prevention of some bacterial species, namely *K. pneumoniae* (Figure 7B) and *S. epidermidis* (Figure 7D). The absence of a specific medium for the isolation *A. baumannii* is a limitation of this study, preventing us to infer the influence of PVC surfaces on *A. baumannii* growth (when in consortia with *P. aeruginosa*). For PVC, pDA, and the coatings with CHX alone, no significant differences were detected between the number of adhered cells found on TSA or on the selective *P. aeruginosa* medium, PIA (Figure 7A), which is indicative that *P. aeruginosa* is still likely the most dominant species in these conditions (as ascertained by Figure S2, in Supplementary Material). It would be expected, however, a lack of effectiveness of CHX-modified surfaces against *A. baumannii* population similar to the one observed in its single-species biofilms.

When coming to CIP-modified surfaces, drastic dose-dependent reductions were estimated for the biofilm populations, as compared with those developed on unmodified PVC surfaces. Such reductions were more pronounced for the bacterial populations in all consortia (Figure 7, A-D), as compared with the fungal population (Figure 7E). Concerning *P. aeruginosa* and *A. baumannii* consortia (Figure 7A), equitable CFU numbers were found for each bacterial population within the biofilms grown in CIP-modified surfaces, with PIA estimating about 1.0 Log_{10} and 0.9 Log_{10} CFU/mL of *P. aeruginosa* cells, whereas *A. baumannii* presented ~1.3 Log_{10} and 0.7 Log10 CFU/mL, given by the difference between TSA and PIA counts, respectively (CIP 0.5 mg/mL vs. 2 mg/mL). As compared to their single-species biofilms (see Figure 6, A and B), the extent of adhesion of both populations in dual-species consortia was notoriously affected by CIP-modified surfaces, reducing *P. aeruginosa* growth by approximately 5.3 Log_{10} and 0.8 Log_{10} and *A. baumannii* by 3.3 Log_{10} and 2.0 Log_{10} (CIP 0.5 mg/mL vs. 2 mg/mL). When CIP was immobilized and combined with CHX, they also led to greater reductions in *P. aeruginosa* (~1 Log_{10}) and *A. baumannii* (~2 Log_{10}) populations, compared to its effect in single-species consortia.

Biofilm formation by *K. pneumoniae* and *S. aureus* on unmodified PVC and pDA surfaces was compromised by the presence of *P. aeruginosa*, as evidenced by ca. 1 log_{10} reduction in the number of biofilm cells compared to their single-species biofilm (Figure 7, B and C vs Figure 6, C and D, respectively). Further PVC functionalization with CIP and CHX, alone or combined, led to substantial decreases in biofilm cell numbers for both species (Figure 7, B and C), even fully preventing *K. pneumoniae* biofilm population, a result comparable to that observed for its single-species biofilm (Figure 7B vs Figure 6C). Similar to other bacterial species, *S. epidermidis* biofilm formation on untreated surfaces was impaired by the presence of *P. aeruginosa*, as evidenced by a reduction of approximately 1 log_{10} and 0.7 log_{10} for unmodified PVC and pDA surfaces, respectively. However, it should be taken into account that some of this reduction could be associated with its growth in the selective media (Figure S2). All the CIP- and/or CHX-modified surfaces caused a significant reduction in the number of *S. epidermidis* cells in the dual-species consortia (Figure 7D), an antimicrobial performance similar to the one obtained for its single-species adhesion (Figure 6E).

Contrariwise to the consortia involving only bacterial species, biofilms involving *P. aeruginosa* and *C.*
albicans were not always dominated by *P. aeruginosa* (Figure 7E). Despite the predominance of the
bacterial population when growing on both unmodified PVC and pDA-coated surfaces, an increase (~
0.7 Log_{10} and 0.3 Log_{10} compared to PVC and pDA-coated surfaces, respectively) in the fungal ability
to adhere to CIP-modified surfaces were observed relatively to *P. aeruginosa*, which endured in
CIP/CHX co-immobilized surfaces. Despite this differential growth among both bacterial and fungal
populations in the consortia, co-immobilization of CIP and CHX in PVC surfaces also caused a
significant reduction of ca. 2.7 Log_{10} on the number of adhered fungi, which was quite near the limit
threshold for CFU counting. The antimicrobial performance of this coating strategy against *P.*
aeruginosa in this consortium was similar to or better than the one obtained for its single-species
adhesion. A major reduction was also found for bacterial/fungal biofilms grown on PVC
functionalized with CHX at the highest concentration (2 mg/mL), which caused a 4.7 Log_{10} reduction
in fungal cells (as opposed to the 1.1 Log_{10} reduction achieved for its single-species adhesion).
Co-immobilization of CIP and CHX proved to result in a synergic effect against *P. aeruginosa* for all
consortia investigated, according to the calculations in Table S2 of Supplementary Material. A similar
synergic effect endured against *C. albicans* and a facilitative one against all other microbial species in
consortium with *P. aeruginosa*.

3.5 Efficacy of modified PVC surfaces against triple-species biofilms

To better mimic the true polymicrobial (that often includes inter-kingdom) nature of VAP infections
and evaluate the dual-drug CIP/CHX coating strategy's successfulness in a more complex (and
eventually, worsening) scenario, its effectiveness in preventing the development of a triple-species
biofilm was investigated. Biofilms comprised of three populations involving Gram-negative (*P.*
aeruginosa) and Gram-positive (*S. aureus*) bacterium, but also a fungal species (*C. albicans*) were
grown on CIP/CHX-modified surfaces, and their CFU number estimated after 24 h (Figure 8).

Figure 8. Efficacy against triple-species biofilms. Effect of PVC surfaces before and after pDA-based coating and immobilization of CIP and/or CHX against triple-species biofilms of *P. aeruginosa, S. aureus*, and *C. albicans*. Unmodified PVC and pDA-coated surfaces were used for comparison. The threshold value marked by the dotted line represents the detection limit of CFU counting. The results are shown as mean ± SDs. (****) $p < 0.0001$ vs. *P. aeruginosa* growth on unmodified PVC; (####) $p < 0.0001$ vs. *S. aureus* species growth on unmodified PVC; and (δ) $p < 0.05$, ($\delta\delta$) $p < 0.01$ and ($\delta\delta\delta\delta$) $p < 0.0001$ vs. *C. albicans* species growth on unmodified PVC 2way ANOVA, Tukey`s multiple comparison test.

The ability of *P. aeruginosa* or *C. albicans*, grown in triple consortia, to adhere to control unmodified PVC and pDA-coated surfaces, was not compromised by the presence of other microbial species in the biofilm, as compared to their single-species adhesion (see Figure 6, A and F). On the other hand, minor decreases (< 1 Log_{10}) occurred for *S. aureus* populations (Figure 8 vs Figure 6D), in a similar way to when it was combined with *P. aeruginosa* in dual-species consortia (see Figure 7D). All modified surfaces, immobilized with CIP and CHX alone or combined, contributed to significantly impair the adhesion of *S. aureus*. In turn, PVC functionalized with CHX alone had no effect against *P. aeruginosa* population, as expected, but its growth was considerably disturbed when biofilms were developed on CIP- and CIP/CHX- modified surfaces, even resulting in pseudomonal prevention for CIP/CHX-modified surfaces (Figure 8). However, the anti-biofilm effect of all coatings was not demonstrated for *C. albicans* populations, as attained for bacterial populations in the consortia. Furthermore, the modified surfaces had a more modest antifungal effect against triple-species biofilms when compared to that attained in dual-species *P. aeruginosa/C. albicans* biofilms (Figure 7E). Even so, the dual-drug CIP/CHX coating was promising in substantially affecting bacterial populations inside the consortia, and even modestly reducing *C. albicans* cell numbers by about 1 Log_{10} (compared to unmodified PVC).

4. Discussion

Every time an ETT is used for invasive mechanical ventilation, there is a raise of about 6 to 20 folds
in the risk of ventilated patients acquiring VAP [40,41]. This increased risk has been substantially
related to microbial proliferation on the ETT surface that rapidly evolves for biofilm formation and
eventually leads to complete occlusion of the ETT and spreading of pathogens to the lower airways,
causing persistent VAP. This sets the pace for urgent strategies effectively tackling ETT bioburden
and curbing the risk of VAP. Preventing microbial colonization has long been recognized as the best
approach to avoid biofilm formation and thus, VAP. In the last few decades, technology has advanced,
although at a slow pace, regarding the development of new active and/or passive materials for
improving ETT surfaces [19]. This relatively slow pace has been shown not to be attributable to a
shortage of new ideas, as recently evidenced [19], but to the challenge of overcoming fundamental
hurdles associated with VAP (e.g., persistent colonization/biofilm formation; mechanical ventilation
time; ICU length of stay; VAP occurrence). In addition, the design and implementation of new
biomaterials often imply following specific criteria (e.g., antimicrobial activity; safety-to-use; long-
term stability; surface physicochemical properties) to achieve clinical successfulness. This study,
which links up with our previous report showing the potential of the immobilization of CHX using a
one-step pDA-functionalization approach in the context of orthopedic devices [42], aimed to improve
PVC-ETT design by consistently employing dopamine strategy in the immobilization of CHX and
CIP on PVC surfaces. A deep characterization regarding surface properties (topography; roughness;
wettability), the release profiles, and the potential for reducing microbial colonization while retaining
the safety of use was made, so that we can go further with a great ETT coating near achieving success
in *vivo*.

The extent of microbial adhesion and subsequent formation of biofilms is highly reliant on certain
properties of the bulk polymeric substrates, such as wettability, roughness, and topography [43]. Our
prepared coatings imparted PVC surfaces with an altered homogeneously scattered morphology and
varied wettability but similar topography (low roughness) to pDA-coated surfaces. However,
CIP/CHX co-immobilization yielded coatings with homogenous, hydrophobic, and smooth
topographic properties comparable to surfaces immobilized with CHX alone. This result is in
accordance with Daud et. al that reported an increase in the hydrophobicity of stainless-steel surfaces
after CHX immobilization using a pDA-based approach [44].

In the design of antimicrobial coating strategies, the antimicrobial activity may be addressed either by
a direct contact-killing approach, in which the antimicrobial compound is permanently attached to a
surface or by a strategy in which the antimicrobial agent is released [45]. Although the first strategy
has the advantage of decreasing the propensity for cytotoxicity and development of microbial
resistance, there is a major setback associated with its application, namely the fact that the first
adherent dead cells may serve as a platform for the adhesion of the next ones, masking the
antimicrobial effect of the surface.

This is of particular concern if we bear in mind that the ETT biofilms, which often lead to severe VAP,

are comprised of many different phylogenetic organisms and develop quickly after intubation [35,46].

We, therefore, hypothesize that a dual-drug release appears to hold promise, in that it would benefit

from a multitude of features, such as a long-lasting and broad-spectrum activity, thereby declining the

emergence of antimicrobial resistance, reduction in antimicrobial doses, and good biocompatibility

[47]. Our findings showed a weighted but sustained release of CIP and CHX when immobilized on

PVC surfaces, with both compounds (alone and combined) retaining contact-killing activity for a

long-term period (up to 10 days). Unlike a variety of emergent ETT antimicrobial coatings that have

not confirmed long-term stability, our dual-drug coating drives potential application for longer than

24 h, mitigating device failure for longer time periods and, consequently, reducing the real risk for

recurrent ETT exchanges and the propensity for developing VAP.

Biocompatibility, as well as stability, is another feature often dismissed in reports addressing

antimicrobial materials for ETTs [19]. Despite the efforts that have been made to study both of these

traits, data remain scant or controversial, thereby leading to inconclusive safety and clinical usefulness

of most emergent ETT coatings. It is the case, for instance, of silver-based ETT coatings. Even though

they have rapidly reached the market with promising antimicrobial effectiveness [48,49], there is

increasing evidence of the toxicity and short stability attained by released silver ions, in addition to

the health concerns regarding the promotion of resistance in clinical isolates [50,51]. When designing

a dual-drug coating, in particular, it is imperative that the release of compounds will be assured in

doses higher enough to provide an antimicrobial effect but not so that it will be cytotoxic. In this study,

coatings incorporating only CIP or CHX did not exhibit toxicity toward mammalian cells, even for the

highest doses tested (2 mg/mL). In turn, surfaces co-immobilizing CIP/CHX caused A549 toxicity in

a dose-dependent manner, and biocompatibility was only afforded for coatings incorporating

antimicrobials with doses up to 0.5 mg/mL. Based on these findings, further antibiofilm studies were

performed for coatings displaying no toxic effects against lung epithelial cells.

A key but considerably often-neglected factor has been the ETT biofilm and its polymicrobial

etiology. Most antimicrobial coating strategies reported to fight VAP are tested against

microorganisms individually [52,53]. To the best of our knowledge, a sole polyurethane-based

hydrogel ETT coating incorporating a lead ceragenin (CSA-131) was found to address performance

against polymicrobial, including bacterial–bacterial (*P. aeruginosa*/MRSA) and bacterial-fungal (*P.*

aeruginosa/*Candida auris*) biofilms [54]. In addition, this latest report reported less efficient

antimicrobial performance against polymicrobial biofilms compared to single-species consortia [55].

The present study represents a step forward towards a collective representation of VAP pathogens,

while devising an antimicrobial coating strategy to endow the surface of ETTs with the ability to

resist the colonization of Gram-negative (*P. aeruginosa*, *K. pneumoniae*, and *A. baumannii*) and

Gram-positive bacteria (*S. aureus*, *S. epidermidis*) but also fungi (*C. albicans*), in single, dual and

triple-species consortia, thus reflecting worst-case scenarios in the context of VAP. PVC coatings

with CHX immobilized alone proved not to be effective against important Gram-negative VAP-relevant bacteria, namely *P. aeruginosa* and *A. baumannii*. In previous studies, ETTs impregnating CHX, particularly combined with other antiseptic agents, had demonstrated potential in reducing colonization by MDR gram-negative bacteria but also by Gram-positive and *Candida* spp. [24,25]. The use of another antimicrobial compound, CIP, showed auspicious in broadening the antimicrobial spectrum of our coating strategy. CIP affords antibacterial effect by binding to bacterial enzymes, DNA gyrase and topoisomerase IV, resulting in permanent double-stranded DNA and cell death [56]. Co-immobilization of CIP and CHX (CIP/CHX) imparted PVC surfaces with the ability to effectively reduce or prevent microbial colonization and biofilm formation by all five bacterial species investigated (*P. aeruginosa*, *A. baumannii*, *K. penumoniae*, *S. aureus*, *S. epidermidis*). In addition to increasing the spectrum of action, reducing antimicrobial resistance and toxicity, a combination of antimicrobials comprises additional advantages, that include rejuvenation of old antibiotics or drug synergism [47] . In fact, CIP/CHX-modified surfaces exhibited both synergic and additive effects against all species, with reduced concentrations of both compounds crucial to assure no toxicity against lung epithelial cells.

The proposed coating strategy was, therefore, further evaluated against polymicrobial consortia, namely involving two and three species. Promising led to conclude that CIP/CHX mixed coating strategy exhibited similar or even better antimicrobial effects against polymicrobial communities when compared to their single-species colonization. The microbiome of VAP has been reported to be mainly comprised of bacteria and only a small percentage of viruses and fungi [57]. The role played by such lesser common species, namely fungal species such as *C. albicans*, on the adverse clinical outcomes in patients with VAP has not been fully elucidated. First, it was assumed that the presence of *Candida* spp. in respiratory tract specimens should be considered colonization rather than infection [58]. In fact, ESCMID guidelines for the management of *Candida* spp. do not recommend antifungal therapy unless there is clear histological evidence of infection [59]. However, other studies have suggested an association between *Candida* spp. colonization and longer mechanical ventilation [60], increased risk for multi-drug resistant bacteria isolation [61], and death [62]. In the present study, *C. albicans* colonization as single species was not impaired as efficiently as the biofilms of bacterial species. However, its presence did not compromise the antibiofilm activity against two major VAP pathogens, *P. aeruginosa* or *S. aureus*, when the coating strategies were evaluated against polymicrobial consortia.

5. Conclusions

In this study, the combination of CIP and CHX, using dopamine chemistry, resulted in a dual-drug coating with antimicrobial activity towards a wide spectrum of microorganisms commonly associated with VAP without compromising the viability of lung epithelial cells. Furthermore, a safe-by-design

approach was followed, as evidenced by the reduction of the concentration of both compounds so that

a balance between antimicrobial features and biocompatibility could be obtained. Worthy of note, the

sustained antimicrobial release for a period of up to 10 days strongly evidences the long-term stability

and robustness of the antimicrobial immobilization in our dual-drug coating.

Taking all findings together, our dual-drug coating approach holds great potential to be further applied

in the next generation of EETs, with promise laying in reducing the incidence rates of VAP.

Author Statement

660 **Diana Alves:** Investigation, Methodology, Writing- Original draft preparation. **Maria O. Pereira.**:

661 Conceptualization, Supervision, Writing- Reviewing and Editing. **Susana P. Lopes**:

662 Conceptualization, Supervision, Visualization, Writing- Original draft preparation; Writing-

663 Reviewing and Editing.

Acknowledgments

This work was supported by the Portuguese Foundation for Science and Technology (FCT) under the

scope of the strategic funding of UIDB/04469/2020 unit, and by LABBELS – Associate Laboratory in

Biotechnology, Bioengineering and Microelectromechanical Systems, LA/P/0029/2020. The authors

also acknowledge the support, through the Programa Operacional Competitividade e

Internacionalização (COMPETE2020) and by national funds, through the FCT, of the POLY-

PrevEnTT project (PTDC/BTMSAL/29841/2017-POCI-01-0145-FEDER-029841). A special thanks

to Professor Alexandr Nemec from National Institute of Public Health in Prague, for kindly providing

the *A. baumannii* strain used in this study.

Appendix A. Supplementary data

674 Supplementary data to this article is submitted.

References

[1] H.J. Busscher, H.C. Van Der Mei, G. Subbiahdoss, P.C. Jutte, J.J.A.M.A.M. van den Dungen, S.A.J.J.
Zaat, M.J. Schultz, D.W. Grainger, Biomaterial-associated infection: Locating the finish line in the race
for the surface, Sci Transl Med. 4 (2012) 153rv10-153rv10.
https://doi.org/10.1126/scitranslmed.3004528.
[2] C.F. Haas, R.M. Eakin, M.A. Konkle, R. Blank, Endotracheal tubes: Old and new, in: Respir Care,
2014. https://doi.org/10.4187/respcare.02868.
[3] M. Ippolito, G. Misseri, G. Catalisano, C. Marino, G. Ingoglia, M. Alessi, E. Consiglio, C. Gregoretti,
A. Giarratano, A. Cortegiani, Ventilator-associated pneumonia in patients with covid-19: A systematic
review and meta-analysis, Antibiotics. 10 (2021) 1–19. https://doi.org/10.3390/antibiotics10050545.
[4] R. Chang, K.M. Elhusseiny, Y.C. Yeh, W.Z. Sun, COVID-19 ICU and mechanical ventilation patient
characteristics and outcomes—A systematic review and meta-analysis, PLoS One. 16 (2021) 1–16.
https://doi.org/10.1371/journal.pone.0246318.
[5] R. Pinciroli, C. Mietto, L. Berra, Respiratory therapy device modifications to prevent ventilator-
associated pneumonia., Curr Opin Infect Dis. 26 (2013) 175–83.
https://doi.org/10.1097/QCO.0b013e32835d3349.

692	[6]	P.E. Grgurich, J. Hudcova, Y. Lei, A. Sarwar, D.E. Craven, Diagnosis of ventilator-associated
693		pneumonia: controversies and working toward a gold standard., Curr Opin Infect Dis. 26 (2013) 140–
694		50. https://doi.org/10.1097/QCO.0b013e32835ebbd0.
695	[7]	A. Rouzé, I. Martin-Loeches, S. Nseir, Airway Devices in Ventilator-Associated Pneumonia
696		Pathogenesis and Prevention, Clin Chest Med. (2018). https://doi.org/10.1016/j.ccm.2018.08.001.
697	[8]	I. Vandecandelaere, T. Coenye, Microbial composition and antibiotic resistance of biofilms recovered
698		from endotracheal tubes of mechanically ventilated patients, Adv Exp Med Biol. 830 (2015) 137–155.
699		https://doi.org/10.1007/978-3-319-11038-7_9.
700	[9]	H.C. Flemming, J. Wingender, The biofilm matrix, Nat Rev Microbiol. (2010).
701		https://doi.org/10.1038/nrmicro2415.
702	[10]	S.P. Lopes, M.E. Rodrigues, C.R. Pereira, N.F. Azevedo, A. Lourenço, M. Henriques, M.O. Pereira,
703		Polymicrobial ventilator-associated pneumonia: Fighting in vitro Candida albicans-pseudomonas
704		aeruginosa biofilms with antifungal-antibacterial combination therapy, PLoS One. 12 (2017).
705		https://doi.org/10.1371/journal.pone.0170433.
706	[11]	A. Hotterbeekx, B.B. Xavier, K. Bielen, C. Lammens, P. Moons, T. Schepens, M. Ieven, P.G. Jorens, H.
707		Goossens, S. Kumar-Singh, S. Malhotra-Kumar, The endotracheal tube microbiome associated with
708		Pseudomonas aeruginosa or Staphylococcus epidermidis, Sci Rep. 6 (2016).
709		https://doi.org/10.1038/srep36507.
710	[12]	S. Cairns, J.G. Thomas, S.J. Hooper, M.P. Wise, P.J. Frost, M.J. Wilson, M.A.O. Lewis, D.W.
711		Williams, Molecular analysis of microbial communities in endotracheal tube biofilms, PLoS One. 6
712		(2011) e14759. https://doi.org/10.1371/journal.pone.0014759.
713	[13]	A.C. Kalil, M.L. Metersky, M. Klompas, J. Muscedere, D.A. Sweeney, L.B. Palmer, L.M. Napolitano,
714		N.P. O'Grady, J.G. Bartlett, J. Carratalà, A.A. el Solh, S. Ewig, P.D. Fey, T.M. File, M.I. Restrepo, J.A.
715		Roberts, G.W. Waterer, P. Cruse, S.L. Knight, J.L. Brozek, Management of Adults With Hospital-
716		acquired and Ventilator-associated Pneumonia: 2016 Clinical Practice Guidelines by the Infectious
717		Diseases Society of America and the American Thoracic Society, Clin Infect Dis. 63 (2016) e61–e111.
718		https://doi.org/10.1093/CID/CIW353.
719	[14]	D. Nora, P. Póvoa, Antibiotic consumption and ventilator-associated pneumonia rates, some parallelism
720		but some discrepancies, Ann Transl Med. (2017). https://doi.org/10.21037/atm.2017.09.16.
721	[15]	P. Arayasukawat, A. So-ngern, W. Reechaipichitkul, W. Chumpangern, I. Arunsurat, P. Ratanawatkul,
722		W. Chuennok, Microorganisms and clinical outcomes of early- and late-onset ventilator-associated
723		pneumonia at Srinagarind Hospital, a tertiary center in Northeastern Thailand, BMC Pulm Med. 21
724		(2021) 1–8. https://doi.org/10.1186/S12890-021-01415-8/TABLES/4.
725	[16]	M. Dias, P. Marçal, P. Amaro, Ventilator-associated pneumonia (VAP) - Early and late-onset
726		differences, European Respiratory Journal. 42 (2013).
727	[17]	T.L. Hedrick, R.L. Smith, S.T. McElearney, H.L. Evans, P.W. Smith, T.L. Pruett, J.S. Young, R.G.
728		Sawyer, Differences in early- and late-onset ventilator-associated pneumonia between surgical and
729		trauma patients in a combined surgical or trauma intensive care unit, J Trauma. 64 (2008) 714–720.
730		https://doi.org/10.1097/TA.0B013E31811EC18E.
731	[18]	R. Khan, H.M. Al-Dorzi, H.M. Tamim, A.H. Rishu, H. Balkhy, A. El-Saed, Y.M. Arabi, The impact of
732		onset time on the isolated pathogens and outcomes in ventilator associated pneumonia, J Infect Public
733		Health. 9 (2016) 161–171. https://doi.org/10.1016/J.JIPH.2015.09.002.
734	[19]	D. Alves, T. Grainha, M.O. Pereira, S.P. Lopes, Antimicrobial materials for endotracheal tubes: A
735		review on the last two decades of technological progress, Acta Biomater. In Press (2023).
736		https://doi.org/https://doi.org/10.1016/j.actbio.2023.01.001.
737	[20]	H. Lee, S.M. Dellatore, W.M. Miller, P.B. Messersmith, Mussel-inspired surface chemistry for
738		multifunctional coatings, Science (1979). 318 (2007) 426–30. https://doi.org/10.1126/science.1147241.
739	[21]	D. Alves, P. Borges, T. Grainha, C.F. Rodrigues, M.O. Pereira, Tailoring the immobilization and release
740		of chlorhexidine using dopamine chemistry to fight infections associated to orthopedic devices,
741		Materials Science and Engineering C. 120 (2021) 111742. https://doi.org/10.1016/j.msec.2020.111742.
742	[22]	D. Alves, A. Magalhães, D. Grzywacz, D. Neubauer, W. Kamysz, M.O. Pereira, Co-immobilization of
743		Palm and DNase I for the development of an effective anti-infective coating for catheter surfaces, Acta
744		Biomater. 44 (2016) 313–22. https://doi.org/10.1016/j.actbio.2016.08.010.
745	[23]	J. Rello, D. Koulenti, S. Blot, R. Sierra, E. Diaz, J.J. De Waele, A. Macor, K. Agbaht, A. Rodriguez,
746		Oral care practices in intensive care units: A survey of 59 European ICUs, Intensive Care Med. 33
747		(2007) 1066–1070. https://doi.org/10.1007/s00134-007-0605-3.
748	[24]	I.I. Raad, J.A. Mohamed, R.A. Reitzel, Y. Jiang, T.L. Dvorak, M.A. Ghannoum, R.Y. Hachem, A.M.
749		Chaftari, The prevention of biofilm colonization by multidrug-resistant pathogens that cause ventilator-
750		associated pneumonia with antimicrobial-coated endotracheal tubes, Biomaterials. 32 (2011) 2689–
751		2694. https://doi.org/10.1016/J.BIOMATERIALS.2010.12.015.

[25] G. Chaiban, H. Hanna, T. Dvorak, I. Raad, A rapid method of impregnating endotracheal tubes and
urinary catheters with gendine: a novel antiseptic agent, J Antimicrob Chemother. 55 (2005) 51–56.
https://doi.org/10.1093/JAC/DKH499.
[26] V. Pacheco-Fowler, T. Gaonkar, P.C. Wyer, S. Modak, Antiseptic impregnated endotracheal tubes for
the prevention of bacterial colonization, Journal of Hospital Infection. 57 (2004) 170–174.
https://doi.org/10.1016/j.jhin.2004.03.011.
[27] A. Torres, M.S. Niederman, J. Chastre, S. Ewig, P. Fernandez-Vandellos, H. Hanberger, M. Kollef, G.L.
Bassi, C.M. Luna, I. Martin-Loeches, J.A. Paiva, R.C. Read, D. Rigau, J.F. Timsit, T. Welte, R.
Wunderink, International ERS/ESICM/ESCMID/ALAT guidelines for the management of hospital-
acquired pneumonia and ventilator-associated pneumonia, European Respiratory Journal. 50 (2017)
1700582. https://doi.org/10.1183/13993003.00582-2017.
[28] A.W.G. Nijhuis, J.J.J.P. van den Beucken, O.C. Boerman, J.A. Jansen, S.C.G. Leeuwenburgh, 1-Step
Versus 2-Step Immobilization of Alkaline Phosphatase and Bone Morphogenetic Protein-2 onto Implant
Surfaces Using Polydopamine, Tissue Eng Part C Methods. 19 (2013) 610–9.
https://doi.org/10.1089/ten.tec.2012.0313.
[29] A.W. Bauer, W.M. Kirby, J.C. Sherris, M. Turck, Antibiotic susceptibility testing by a standardized
single disk method., Am J Clin Pathol. 45 (1966) 493–496. https://doi.org/10.1093/ajcp/45.4_ts.493.
[30] International Organization for Standardization, Biological evaluation of medical devices, 2009.
[31] W.N. Chaudhry, J. Concepcion-Acevedo, T. Park, S. Andleeb, J.J. Bull, B.R. Levin, Synergy and order
effects of antibiotics and phages in killing pseudomonas aeruginosa biofilms, PLoS One. 12 (2017)
e0168615. https://doi.org/10.1371/journal.pone.0168615.
[32] L. Chen, C.Y. Sheng, Y.X. Duan, J.M. Zhang, Morphology, microstructure and properties of PEG-
plasticized PVC, Polymer - Plastics Technology and Engineering. 50 (2011) 412–417.
https://doi.org/10.1080/03602559.2010.543231.
[33] I.S. Kwon, C.J. Bettinger, Polydopamine nanostructures as biomaterials for medical applications, J
Mater Chem B. 6 (2018) 6895–6903. https://doi.org/10.1039/c8tb02310g.
[34] D. Alves, P. Borges, F. Rodrigues, M.O. Pereira, Materials Science & Engineering C Tailoring the
immobilization and release of chlorhexidine using dopamine chemistry to fight infections associated to
orthopedic devices, (2020). https://doi.org/10.1016/j.msec.2020.111742.
[35] H.R. Thorarinsdottir, T. Kander, A. Holmberg, S. Petronis, B. Klarin, Biofilm formation on three
different endotracheal tubes: A prospective clinical trial, Crit Care. 24 (2020) 1–12.
https://doi.org/10.1186/S13054-020-03092-1/TABLES/6.
[36] O. Diaconu, I. Siriopol, L.I. Poloʃanu, I. Grigoraʃ, Endotracheal Tube Biofilm and its Impact on the
Pathogenesis of Ventilator-Associated Pneumonia, The Journal of Critical Care Medicine. 4 (2018) 50.
https://doi.org/10.2478/JCCM-2018-0011.
[37] I. Vandecandelaere, N. Matthijs, F. van Nieuwerburgh, D. Deforce, P. Vosters, L. de Bus, H.J. Nelis, P.
Depuydt, T. Coenye, Assessment of microbial diversity in biofilms recovered from endotracheal tubes
using culture dependent and independent approaches, PLoS One. 7 (2012) e38401.
https://doi.org/10.1371/journal.pone.0038401.
[38] J. Rello, B. Borgatta, T. Lisboa, Risk factors for pseudomonas aeruginosa pneumonia in the early
twenty-first century, Intensive Care Med. 39 (2013) 2204–2206. https://doi.org/10.1007/s00134-013-
3046-1.
[39] K. Wang, Y. qiang Chen, M.M. Salido, G.S. Kohli, J. liang Kong, H. jie Liang, Z. ting Yao, Y. tong
Xie, H. yu Wu, S. qi Cai, D.I. Drautz-Moses, A.E. Darling, S.C. Schuster, L. Yang, Y. Ding, The rapid
in vivo evolution of Pseudomonas aeruginosa in ventilator-associated pneumonia patients leads to
attenuated virulence, Open Biol. 7 (2017). https://doi.org/10.1098/rsob.170029.
[40] M. Cavalcanti, M. Ferrer, R. Ferrer, R. Morforte, A. Garnacho, A. Torres, Risk and prognostic factors of
ventilator-associated pneumonia in trauma patients, Crit Care Med. 34 (2006) 1067–1072.
https://doi.org/10.1097/01.CCM.0000206471.44161.A0.
[41] R. Pinciroli, C. Mietto, L. Berra, Respiratory therapy device modifications to prevent ventilator-
associated pneumonia, Curr Opin Infect Dis. 26 (2013) 175–183.
https://doi.org/10.1097/QCO.0b013e32835d3349.
[42] D. Alves, P. Borges, T. Grainha, C.F. Rodrigues, M.O. Pereira, Tailoring the immobilization and release
of chlorhexidine using dopamine chemistry to fight infections associated to orthopedic devices,
Materials Science and Engineering C. 120 (2021). https://doi.org/10.1016/j.msec.2020.111742.
[43] Y. Yuan, M.P. Hays, P.R. Hardwidge, J. Kim, Surface characteristics influencing bacterial adhesion to
polymeric substrates, RSC Adv. 7 (2017) 14254–14261. https://doi.org/10.1039/C7RA01571B.
[44] N. Mohd Daud, I.F. Saeful Bahri, N.A.N. Nik Malek, H. Hermawan, S. Saidin, Immobilization of
antibacterial chlorhexidine on stainless steel using crosslinking polydopamine film: Towards infection

resistant medical devices, Colloids Surf B Biointerfaces. 145 (2016) 130–139.
https://doi.org/10.1016/j.colsurfb.2016.04.046.

[45]   C. Adlhart, J. Verran, N.F. Azevedo, H. Olmez, M.M. Keinänen-Toivola, I. Gouveia, L.F. Melo, F.
Crijns, Surface modifications for antimicrobial effects in the healthcare setting: a critical overview,
Journal of Hospital Infection. 99 (2018) 239–249. https://doi.org/10.1016/j.jhin.2018.01.018.

[46]   P.E. Danin, E. Girou, P. Legrand, B. Louis, R. Fodil, C. Christov, J. Devaquet, D. Isabey, L. Brochard,
Description and Microbiology of Endotracheal Tube Biofilm in Mechanically Ventilated Subjects,
Respir Care. 60 (2015) 21–29. https://doi.org/10.4187/RESPCARE.02722.

[47]   A.R.M. Coates, Y. Hu, J. Holt, P. Yeh, Antibiotic combination therapy against resistant bacterial
infections: synergy, rejuvenation and resistance reduction, Expert Rev Anti Infect Ther. 18 (2020) 5–15.
https://doi.org/10.1080/14787210.2020.1705155.

[48]   G. Tokmaji, H. Vermeulen, M. Mca, K. Phs, S. Mj, Z. Saj, associated pneumonia in critically ill patients
(Review), (2015). https://doi.org/10.1002/14651858.CD009201.pub2.www.cochranelibrary.com.

[49]   M.H. Kollef, B. Afessa, A. Anzueto, C. Veremakis, K.M. Kerr, B.D. Margolis, D.E. Craven, P.R.
Roberts, A.C. Arroliga, R.D. Hubmayr, M.I. Restrepo, W.R. Auger, R. Schinner, Silver-Coated
Endotracheal Tubes and Incidence of Ventilator-Associated Pneumonia: The NASCENT Randomized
Trial, JAMA. 300 (2008) 805–813. https://doi.org/10.1001/JAMA.300.7.805.

[50]   A.A. de Lima e Silva, M.A. Ribeiro de Carvalho, S.A.L. L de Souza, P.M. Teixeira Dias, R.G. da Silva
Filho, C.S. de Meirelles Saramago, C.A. de Melo Bento, E. Hofer, Heavy metal tolerance (Cr, Ag AND
Hg) in bacteria isolated from sewage, Brazilian Journal of Microbiology. 43 (2012) 1620.
https://doi.org/10.1590/S1517-838220120004000047.

[51]   S. Sütterlin, M. Dahlö, C. Tellgren-Roth, W. Schaal, Melhus, High frequency of silver resistance genes
in invasive isolates of Enterobacter and Klebsiella species, Journal of Hospital Infection. 96 (2017) 256–
261. https://doi.org/10.1016/J.JHIN.2017.04.017.

[52]   B. Ozcelik, P. Pasic, P. Sangwan, C.L. Be, V. Glattauer, H. Thissen, R.A. Boulos, Evaluation of the
Novel Antimicrobial BCP3 in a Coating for Endotracheal Tubes, ACS Omega. 5 (2020) 10288–10296.
https://doi.org/10.1021/acsomega.9b04178.

[53]   A.C. Zangirolami, L.D. Dias, K.C. Blanco, C.S. Vinagreiro, N.M. Inada, L.G. Arnaut, M.M. Pereira,
V.S. Bagnato, Avoiding ventilator-associated pneumonia: Curcumin-functionalized endotracheal tube
and photodynamic action, Proc Natl Acad Sci U S A. 117 (2020) 22967–22973.
https://doi.org/10.1073/pnas.2006759117.

[54]   M.M. Hashemi, J. Rovig, J. Bateman, B.S. Holden, T. Modelzelewski, I. Gueorguieva, M. von Dyck, R.
Bracken, C. Genberg, S. Deng, P.B. Savage, Preclinical testing of a broad-spectrum antimicrobial
endotracheal tube coated with an innate immune synthetic mimic, Journal of Antimicrobial
Chemotherapy. 73 (2018) 143–150. https://doi.org/10.1093/jac/dkx347.

[55]   M.M. Hashemi, J. Rovig, J. Bateman, B.S. Holden, T. Modelzelewski, I. Gueorguieva, M. von Dyck, R.
Bracken, C. Genberg, S. Deng, P.B. Savage, Preclinical testing of a broad-spectrum antimicrobial
endotracheal tube coated with an innate immune synthetic mimic, Journal of Antimicrobial
Chemotherapy. (2018). https://doi.org/10.1093/jac/dkx347.

[56]   D. Sharma, R.P. Patel, S.T.R. Zaidi, M.M.R. Sarker, Q.Y. Lean, L.C. Ming, Interplay of the quality of
ciprofloxacin and antibiotic resistance in developing countries, Front Pharmacol. 8 (2017) 1–7.
https://doi.org/10.3389/fphar.2017.00546.

[57]   D.R. Park, The microbiology of ventilator-associated pneumonia, Respir Care. 50 (2005) 742–765.
https://doi.org/10.5772/intechopen.69430.

[58]   J. Liu, Y.T. Yu, C.H. Xu, D.C. Chen, Candida Colonization in the Respiratory Tract: What Is the
Significance?, Front Med (Lausanne). 7 (2021). https://doi.org/10.3389/fmed.2020.598037.

[59]   I. Martin-Loeches, M. Antonelli, M. Cuenca-Estrella, G. Dimopoulos, S. Einav, J.J. De Waele, J.
Garnacho-Montero, S.S. Kanj, F.R. Machado, P. Montravers, Y. Sakr, M. Sanguinetti, J.F. Timsit, M.
Bassetti, ESICM/ESCMID task force on practical management of invasive candidiasis in critically ill
patients, Intensive Care Med. (2019) 789–805. https://doi.org/10.1007/s00134-019-05599-w.

[60]   M.S. Delisle, D.R. Williamson, M.M. Perreault, M. Albert, X. Jiang, D.K. Heyland, The clinical
significance of Candida colonization of respiratory tract secretions in critically ill patients, J Crit Care.
23 (2008) 11–17. https://doi.org/10.1016/j.jcrc.2008.01.005.

[61]   M. Hamet, A. Pavon, F. Dalle, A. Pechinot, S. Prin, J.P. Quenot, P.E. Charles, Candida spp. airway
colonization could promote antibiotic-resistant bacteria selection in patients with suspected ventilator-
associated pneumonia, Intensive Care Med. 38 (2012) 1272–1279. https://doi.org/10.1007/s00134-012-
2584-2.

[62]   D.R. Williamson, M. Albert, M.M. Perreault, M.S. Delisle, J. Muscedere, C. Rotstein, X. Jiang, D.K.
Heyland, The relationship between Candida species cultured from the respiratory tract and systemic

inflammation in critically ill patients with ventilator-associated pneumonia, Canadian Journal of
Anesthesia. 58 (2011) 275–284. https://doi.org/10.1007/s12630-010-9439-5.
872
873

	Unmodified PVC	pDA coating

Control surfaces

	0.5 mg/mL	2 mg/mL

CHX-modified surfaces

CIP-modified surfaces

CIP/CHX-modified surfaces