Delivery of human adipose-derived stromal cells within mechanically resilient hydrogels induces adverse outcomes in a femoral artery ligation model in athymic *nu/nu* mice

Running title: ASCs in hydrogels induce adverse response

Fiona E. Serack[1], John A. Ronald[2,3], Brian G. Amsden[4], David A. Hess[3,5], Lauren E. Flynn*[1,6,7]

[1]School of Biomedical Engineering, Faculty of Engineering, The University of Western Ontario, London, Ontario, Canada, N6A 3K7

[2]Department of Medical Biophysics, Schulich School of Medicine and Dentistry, The University of Western Ontario, London, Ontario, Canada, N6A 5C1

[3]Robarts Research Institute, The University of Western Ontario, London, Ontario, Canada, N6A 5C1

[4]Department of Chemical Engineering, Faculty of Engineering, Queen's University, Kingston, Ontario, Canada, K7L 3N6

[5]Department of Physiology and Pharmacology, Schulich School of Medicine and Dentistry, The University of Western Ontario, London, Ontario, Canada, N6A 5C1

[6]Department of Chemical & Biochemical Engineering, Faculty of Engineering, The University of Western Ontario, London, Ontario, Canada, N6A 5B9

[7]Department of Anatomy and Cell Biology, Schulich School of Medicine and Dentistry, The University of Western Ontario, London, Ontario, Canada, N6A 5C1

* To whom correspondence should be addressed

Email: lauren.flynn@uwo.ca

Phone: +1 519 661 2111 x 87226

Funding Statement: Funding for this study was provided by the Heart and Stroke Foundation of Canada (Grant-in-Aid, G-19-0026269) and the Canadian Institutes of Health Research (CIHR MOP #378189).

Conflict of Interest Disclosure: The authors declare that there are no potential conflicts of interest associated with this research.

Data Availability Statement: The raw data supporting the conclusions of this manuscript will be made available by the authors, without undue reservation, to any qualified researcher.

Acknowledgements

Operational funding for this study was provided by the Heart and Stroke Foundation of Canada (Grant-in-Aid, G-19-0026269) and the Canadian Institutes of Health Research (CIHR MOP #378189). Fiona Serack was supported by an Ontario Graduate Scholarship and a Transdisciplinary Bone & Joint Training Award from the Bone and Joint Institute at Western University. Drs. A. Grant, R. Richards, and D. Matic are acknowledged for their clinical collaborations in providing the adipose tissue samples, as well as Drs. Pascal Morissette Martin, Amanda Hamilton, and Ying Xia for their technical support. Additionally, the authors would like to thank the London Regional Flow Cytometry Facility for access to flow cytometry equipment.

Abstract

The delivery of human adipose-derived stromal cells (hASCs) to ischemic tissues represents a promising strategy to promote vascular regeneration for patients with critical limb ischemia (CLI). Building on previous work, this study focused on the further *in vivo* characterization of a novel mechanically-resilient hydrogel system composed of peptide-functionalized methacrylated glycol chitosan (MGC-RGD) and a terminally acrylated triblock copolymer of poly(ethylene glycol) and poly(trimethylene carbonate) (PEG(PTMC-A)$_2$) as an injectable delivery platform for hASCs in mice with femoral artery ligation-induced critical limb ischemia (FAL-CLI). Consistent with previous work, preliminary laser Doppler perfusion imaging (LDPI) data supported that hASCs delivered within the hydrogels accelerated the recovery of limb perfusion in immunocompromised NOD/SCID mice. Recognizing that macrophages play important roles in vascular regeneration and inflammation, as well as the potential for ASCs to modulate the host macrophage response, subsequent studies focused on testing the cell delivery platform in the FAL-CLI model in less severely immunocompromised athymic *nu/nu* mice with normal monocyte/macrophage function. To enable longitudinal cell tracking using bioluminescence imaging (BLI), the hASCs were engineered to co-express tdTomato and firefly luciferase. Interestingly, the hASCs were better retained following delivery in saline in the *nu/nu* mice, compared to delivery using the hydrogel. Despite the enhanced cell retention, LDPI analysis indicated that the restoration of hindlimb perfusion was similar between the two cell treatment groups. Critically, delivery of the hASCs within the hydrogels induced an adverse inflammatory response in the *nu/nu* mice, which was not observed when the hASCs were delivered in saline or in hydrogel alone controls. Overall, this study emphasizes that mouse strain can greatly influence outcomes when testing biomaterials-

based cell therapies in the context of vascular regeneration, and the importance of the host immune response when assessing efficacy in pre-clinical disease models.

Keywords: Cell therapy, critical limb ischemia, vascular regeneration, adipose-derived stromal cells (ASC), hydrogels, chitosan, host response, inflammation.

1   Introduction

Atherosclerotic cardiovascular diseases remain the leading cause of mortality worldwide, with peripheral arterial disease (PAD) being the third leading cause of atherosclerotic morbidity, afflicting more than 230 million people worldwide [1], [2]. Critical limb ischemia (CLI) represents the end stages of PAD and is associated with symptoms such as limb pain at rest, non-healing ulcers, and gangrene [3]. Cell therapies for PAD involving the localized delivery of mesenchymal stromal cells (MSCs) have attracted significant interest due to their capacity to stimulate angiogenesis, modulate inflammation and promote tissue regeneration through paracrine-mediated mechanisms [4]. In particular, adipose-derived stromal cells (ASCs) represent a promising clinically-translational cell population that is more accessible and abundant than other MSC sources [5]. Notably, recent evidence suggests that ASCs may have higher pro-angiogenic regenerative potential than MSCs derived from bone marrow [6], [7].

Although delivery of MSCs has shown success in preclinical models of CLI, clinical trials to date have not clearly demonstrated the efficacy of MSC-based therapies for this application [8]. Postulated reasons for this gap in clinical translation include the poor survival and retention of the cells following directed delivery to the harsh environment within ischemic muscle tissue [9]–[11]. Seeking to address this barrier, there has been growing interest in the application of hydrogels as cell delivery platforms for vascular regeneration, including the treatment of PAD [12], [13]. Previous work from our lab developed a mechanically-resilient composite hydrogel delivery system to support the survival and pro-angiogenic capacity of ASCs as a therapy for CLI [11], [14]. Specifically, this hydrogel was composed of crosslinkable methacrylated glycol chitosan functionalized with the fibronectin-derived cell adhesive peptide motif arginine-glycine-aspartate (MGC-RGD), and a terminally acrylated triblock copolymer of poly(ethylene glycol) and

poly(trimethylene carbonate) (PEG(PTMC-A)$_2$) [15]. The MGC-RGD was chosen to provide a cell-supportive environment, while the PEG(PTMC-A)$_2$ was incorporated to match the mechanical requirements of muscle tissue by providing a structural component capable of sustaining large, repeated mechanical deformations [11], [15]. Human ASCs (hASCs) showed enhanced retention at 28 days when injected intramuscularly within the hydrogels to a femoral artery ligation-induced CLI (FAL-CLI) model in immunodeficient NOD/SCID mice as compared to delivery in saline, based on end-point analyses of human leukocyte antigen-ABC$^+$ (HLA-ABC$^+$) cells in tissue cross-sections [11]. Further, hydrogel delivery significantly enhanced the endothelial cell density in the ischemic gastrocnemius muscles compared to hASCs delivered in saline, as well as with hydrogel and saline alone controls [11].

The previous study was performed using NOD/SCID mice, selected based on their capacity to support human cell engraftment and function without xenorejection [16]. Acknowledging the importance of the host immune response in mediating tissue regeneration, follow-up testing was performed in a healthy immunocompetent rat model [14]. Interestingly, intramuscular (IM) delivery of allogeneic rat ASCs within the hydrogels augmented the recruitment and infiltration of host CD68$^+$ macrophages relative to hydrogel alone controls. Moreover, significantly more CD31$^+$ vessels were observed within and surrounding the hydrogels that incorporated rat ASCs at both 2 and 4 weeks following IM injection. Taken together, these results demonstrated that ASCs could modulate the host macrophage response to the hydrogels, and that this may be favorable for augmenting vascular regeneration.

Building from our previous work, this study sought to perform additional characterization of the MGC-RGD+PEG(PTMC-A)$_2$ delivery system using clinically-relevant human ASCs within the FAL-CLI model in athymic *nu/nu* mice, which have T-lymphocyte deficiency with normal

monocyte/macrophage content, in contrast to the NOD/SCID mice that are known to have deficiencies in macrophage number and function [16], [17]. Recognizing the value of non-invasive imaging technologies to quantitatively assess vascular regeneration and to simultaneously track the survival of therapeutic cell populations, laser Doppler perfusion imaging (LDPI) was integrated to assess changes in hindlimb perfusion over time, along with bioluminescence imaging (BLI) to longitudinally track the hASCs *in vivo*. To enable cell tracking, the hASCs were engineered through lentivirus transduction to stably co-express firefly luciferase (FLuc) for longitudinal BLI and tdTomato for endpoint quantification in muscle tissue cross-sections. Similar to the findings in NOD/SCID mice, it was hypothesized that delivery within the hydrogels in the *nu/nu* mice would augment the localized retention of viable hASCs as compared to delivery in saline, and that this would be coupled with accelerated restoration of hindlimb perfusion, indicative of enhanced vascular regeneration.

2   Methods

2.1   Materials

Unless otherwise stated, all chemicals and reagents were purchased from Millipore Sigma, Canada, and used as received.

2.2   Polymer synthesis

Polymers composed of MGC-RGD and PEG(PTMC-A)$_2$ were synthesized according to previously published protocols [11], [15]. For PEG(PTMC-A)$_2$ synthesis, PEG(PTMC)$_2$ was first prepared through the ring-opening polymerization of trimethylene carbonate (TMC) (LEAPChem), initiated by PEG diol (PEG$_{20}$, M_N = 20 kDa) . The molecular weight of the polymer was assessed using ^{1}H

NMR in deuterated DMSO (DMSO-d_6) on an Inova 600 NMR spectrometer (Varian), confirming the molar ratios of $PEG_{20}(PTMC_2)_2$. $PEG(PTMC)_2$ was subsequently acrylated using acryloyl chloride to a high degree of acrylation (85%), consistent with our previous work [11], as confirmed by [1]H NMR spectroscopy (Supplementary Figure S1A).

MGC was synthesized through the methacrylation of glycol chitosan (GC) (minimum M_N = 82 kDa, 85% degree of deacetylation, Wako Chemicals Inc.) using glycidyl methacrylate, followed by [1]H NMR spectroscopy in deuterium oxide (D_2O) at 80°C to assess the degree of methacrylation. For peptide conjugation to generate the MGC-RGD, GGGRGDS peptide (>90% purity, CanPeptides Inc.) was first acrylated using N-acryloxysuccinimide, with [1]H NMR in D_2O at 80°C used to assess the degree of acrylation. Subsequently, the acrylated RGD peptide was reacted with the MGC polymer to obtain MGC-RGD with a degree of substitution of 5%, consistent with our previous work [11], as confirmed by [1]H NMR spectroscopy (Supplementary Figure S1B).

2.3 Isolation and culture of hASCs

Resected human adipose tissue was obtained with informed consent from routine breast or abdominal reduction surgeries conducted at the London Health Sciences Centre in London, ON, Canada, with approval from the Human Research Ethics Board at Western University (HSREB# 105426). Fresh adipose tissue samples were transported to the lab on ice in sterile phosphate buffered saline (PBS) (Wisent Inc) supplemented with 2% bovine serum albumin (BSA) (Bio-shop) and hASCs were isolated according to published methods and cultured in ASC proliferation medium consisting of DMEM/F12 supplemented with 10% FBS and 1% penicillin-streptomycin (Gibco™) [18]. Media was replaced every 2-3 days, and passaging was performed at 80%

confluence. hASCs were frozen at passage 0 and stored in liquid nitrogen until needed, with hASCs at passage 3-5 used for all studies. Cell donor information is summarized in Supplementary Table S1.

2.4   hASC transduction

To enable longitudinal *in vivo* cell tracking, passage 1 hASCs were engineered through lentiviral transduction to co-express tdTomato (tdT) and codon-optimized firefly luciferase (FLuc2) under the human elongation factor 1-α promoter for constitutive expression (pEF1-alpha-tdT-FLuc2 reporter), according to previously published protocols, with a viral multiplicity of infection (MOI) of 75 and 100 μg/mL protamine sulphate [19].

2.5   Assessment of immunophenotype of transduced hASCs

Flow cytometry analyses were performed to assess the viability, immunophenotype, and tdT expression of the transduced hASCs in comparison to non-transduced controls. Passage 2 hASCs were extracted using Versene solution (Gibco™), with a 10 min incubation on ice, followed by a 10 min incubation at 37°C. Remaining adherent cells were collected in PBS using a cell scraper, and hASCs were filtered through a 100 μm filter prior to downstream staining. Samples were stained and assessed for expression of CD90, CD29, CD146, CD31 and CD45 as outlined in Table 1. Cell viability was assessed using the Live/Dead™ Fixable Aqua kit (Invitrogen™), with a 1:500 dilution. tdTomato signal was compared to non-transduced cells. Samples were analyzed with an LSR II Flow Cytometer (BD Biosciences) at the London Regional Flow Cytometry Facility. Data was analyzed using FlowJo v10 with gates set using the relevant fluorescence minus one (FMO) controls.

Table 1. List of antibody dilutions for hASC flow cytometry characterization.

Antigen	Conjugation	Dilution	Catalog Number	Company
CD90	BV605	1:800	328128	Biolegend
CD29	AF488	1:100	303016	Biolegend
CD146	APC-Fire™750	1:50	361028	Biolegend
CD31	PE-Cy7	1:400	303118	Biolegend
CD45	APC	1:200	368532	Biolegend

2.6   hASC encapsulation for in vitro studies

Hydrogels were prepared according to previously described protocols and formulations [11]. In brief, dry MGC-RGD and PEG(PTMC-A)$_2$ were decontaminated under low-intensity UV light in a biosafety cabinet for 30 min. The weight of each polymer was calculated based on a final formulation of 1% (w/v) MGC-RGD and 4% (w/v) PEG(PTMC-A)$_2$. The polymers were dissolved in sterile PBS (75% of the final volume) overnight at room temperature under constant agitation on an orbital shaker at 100 RPM.

hASCs were extracted using trypsin (Wisent Inc.), resuspended at 5×10^7 cells/mL (5X final concentration) in ASC proliferation medium (20% of the final volume) and thoroughly combined with the pre-polymer solution. Concentrated solutions of ammonium persulphate (APS) (Bio-Shop) and tetramethylethylenediamine (TEMED) (Bio-Shop) were sterile filtered and added sequentially to the combined mixture with thorough mixing with the pipette tip between each addition, to a final concentration of 5 mM each of APS and TEMED. The volumetric ratio of the final solution was 75% pre-polymer solution : 20% hASC suspension : 2.5% APS : 2.5% TEMED, with a final cell density of 10^6 cells/mL. Hydrogels for the *in vitro* cell culture studies were

prepared in syringe molds using 0.3 mL insulin syringes, and allowed to gel at 37°C for 15 min. Following gelation, 10 µL hydrogels were transferred to individual wells of a 12-well plate, and cultured in 2 mL of ASC proliferation medium, with media changes every 2 days.

2.7 *In vitro assessment of cell viability*

Live/Dead™ staining was performed at 24 h, 4 d, and 7 d post-encapsulation to assess the viability of non-transduced hASCs encapsulated within the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels. Hydrogels were first rinsed with PBS, and then incubated in a solution of 2 µM Calcein-AM (Invitrogen™) and 4 µM Ethidum homodimer-1 (Invitrogen™) in PBS for 30 min at 37°C. Following staining, hydrogels were rinsed with PBS, and imaged using a Zeiss LSM confocal microscope (Zeiss Canada) with a 10X objective. A minimum of 5 hydrogels were imaged at each timepoint (n=5).

2.8 *In vitro bioluminescence imaging*

The luminescence signals of transduced hASCs in the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels were assessed following encapsulation, as well as following 24 h, 3 d, 7 d, and 14 d of culture *in vitro*. At each timepoint, hydrogels were transferred into black bottom 96-well plates for the luminescence readings, and incubated in 100 µL D-luciferin (Syd Labs) in PBS at a concentration of 1.25 mg/mL. Luminescence imaging was performed using an IVIS Lumina XRMS Imaging System (PerkinElmer), with images captured using auto-exposure time until a peak average radiance had been reached. Photographic images were used to draw a region of interest (ROI) surrounding the hydrogels, to quantify average radiance (p/s/cm^2/sr). Four hydrogels were assessed at each time point (n=4).

2.9 Femoral artery ligation-induced critical limb ischemia (FAL-CLI) model

All animal procedures were performed in accordance with the rules and regulations set by the Canadian Council on Animal Care and were approved by the Animal Care Committee at Western University (Animal Use Protocol #2019-024). An initial *in vivo* study was performed using 8- to 10-week old NOD/SCID mice, bred in house (Jackson Labs Stock# 001303), as a follow-up to our previous work in this model [11]. More specifically, LDPI analysis was applied to verify the previous immunofluorescence staining results that showed enhanced vascular regeneration when the hASCs were delivered within the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels [11]. Following validation that similar trends were observed, a larger study was subsequently performed using 8-week old athymic *nu/nu* mice (Crl:NU-Foxn1nu, Charles River).

Unilateral hindlimb ischemia was induced in the mice through ligation and excision of a 2-5 mm portion of the femoral artery and vein in the right hindlimb, following established protocols [20], [21]. For the NOD/SCID mice, anesthesia was initially induced using intraperitoneal injection of ketamine hydrochloride (60 mg/kg) and xylazine (2 mg/kg), then maintained using inhaled isoflurane. Following anesthesia, the hair on both hindlimbs was removed by shaving and subsequent treatment with a depilatory agent. For the athymic *nu/nu* mice, anesthesia was induced and maintained using inhaled isoflurane.

Mice were allowed to recover from the FAL surgery for 24 h, and then randomly assigned to the various treatment groups. Four treatment groups were assessed: (i) hASCs in MGC-RGD+PEG(PTMC-A)$_2$ hydrogels, (ii) hASCs in saline, (iii) MGC-RGD+PEG(PTMC-A)$_2$ hydrogel alone controls, and (iv) saline alone controls. For all treatment groups, a total volume of 20 μL was injected intramuscularly into the surgical limb, just distal to the site of ligation, while

the mice were under anesthesia. Polymer solutions were prepared as described above for *in vitro* encapsulation. hASCs were delivered at a concentration of 2×10^7 cells/mL (4×10^5 cells/injection). The NOD/SCID study was performed with n=4 mice/treatment group using non-transduced hASCs. The subsequent *nu/nu* study was performed using the transduced hASCs with n=6 mice/hASC treatment group, and n=3 mice/control treatment group.

2.10 Laser Doppler perfusion imaging assessment of limb perfusion

LDPI was used to assess limb perfusion at days 1 (prior to treatment), 7, 14, 21, and 28. Additional timepoints at days 4 and 35 were included for the athymic *nu/nu* mouse study. For the NOD/SCID mice, shaving and depilatory agent treatment were always performed after imaging in preparation for the next timepoint to ensure that the LDPI readings would not be affected by the hair removal process. Mice were anesthetized with isoflurane and warmed at 37°C on a heating pad for 5 min. The mice, maintained under isoflurane anesthesia, were imaged in a supine position using a Moor LDI-2 laser Doppler imaging system (Moor Instruments). The average flux in the ischemic (surgical) and control limbs were quantified within a ROI encompassing the foot and ankle joint. The perfusion ratio (PR) was calculated as the ratio between the average flux in the surgical and control limbs and normalized relative to the perfusion ratio at day 1. All mice included in the study had a day 1 PR <0.15.

2.11 In vivo bioluminescence imaging assessment of cell retention

In the *nu/nu* mice, *in vivo* BLI was performed to assess the retention of transduced hASCs within the ischemic limbs in the FAL-CLI model at days 1 (following injection), 4, 7, 14, 21, 28, and 35. Mice were anaesthetized using isoflurane and received an intraperitoneal injection of 100 μL of 30 mg/mL D-luciferin (Syd Labs), and subsequently imaged using an IVIS Lumina XRMS *In Vivo*

Imaging System (PerkinElmer). An ROI of consistent size was drawn around the site of injection and used to quantify the average radiance ($p/s/cm^2/sr$) of the luminescence signal. Images were taken using auto-exposure until the average radiance reached a peak value. Average radiance values were normalized to the day 1 values for each mouse.

2.12 Immunofluorescence analysis of immune cell recruitment

The athymic *nu/nu* mice from the first two cohorts were euthanized at 35 days following treatment. The mice from the third cohort were euthanized at 12 days following treatment for the hASCs in MGC-RGD+PEG(PTMC-A)$_2$ group or 14 days following treatment for all other groups. The skin covering the hindlimbs was removed, and the entire thigh muscle was harvested and fixed for 24 h in 10% neutral buffered formalin solution (Fisher Scientific). Samples were then subjected to a sucrose gradient (10%, 20%, 30% sucrose in PBS; incubated for 24 h in each solution), and embedded in frozen section compound (VWR), frozen on dry ice, and stored at -80°C until further processing.

Samples were cryo-sectioned at a thickness of 10 μm and stained to assess host immune cell recruitment with antibodies for murine CD45. Sections were fixed in acetone (Fisher Scientific) for 10 min at -20°C, followed by three 2 min washes in PBS. Samples were then blocked in a solution of PBS with 0.05% tween (Bio-shop) and 10% donkey serum for 1 h at room temperature. Staining for CD45 (1:100 in blocking solution, goat polyclonal anti-CD45, Bio-Techne®, AF114) was performed overnight at 4°C. Sections were washed 3 X 2 min in PBS, and then incubated with the secondary antibody donkey anti-goat IgG Alexa Fluor™ 546 (1:400 in PBS with 0.05% tween, A11056, Invitrogen) for 1 h at room temperature. Sections were washed 3 X 2 min in PBS, then mounted using mounting medium with DAPI (Abcam) to stain cell nuclei. Stained cross sections

at 3 depths at least 200 μm apart were imaged per mouse using a Zeiss Imager M2 Microscope (Zeiss Canada) with a 10X objective. Controls without primary antibody were included to confirm staining specificity. Semi-quantitative scoring of areas of dense $CD45^+$ staining was performed. The tissue sections were given scores of 0 (no dense $CD45^+$ staining outside of the ligated vessel region), 1 (only one small region of dense $CD45^+$ staining), 2 (one medium region of dense $CD45^+$ staining or multiple small regions) or 3 (at least one large region of dense $CD45^+$ staining). Scoring was performed in a blinded manner.

2.13 Statistical Methods

All data was presented as the group mean ± standard deviation, unless otherwise noted. All statistical analyses were performed using GraphPad Prism 9 software. Area under the curve (AUC) analyses were performed on the normalized *in vivo* LDPI and BLI data [22], [23]. Differences in the immunophenotype and viability of transduced and non-transduced hASCs were assessed using multiple paired t-tests (paired across hASC donors), with Holm-Šídák post-hoc correction. Differences in *in vitro* fluorescence and luminescence values across timepoints were assessed using one-way ANOVA with Tukey's post-hoc test for multiple comparisons. Differences in perfusion ratio data between treatment groups at each time point were assessed using two-way repeated measures (RM) ANOVA, with Tukey's post-hoc test for multiple comparisons. Area under the curve data for perfusion ratio was assessed using one-way ANOVA with Tukey's post-hoc test for multiple comparisons. Differences between treatment groups at each timepoint for the *in vivo* BLI data were assessed using multiple unpaired t-tests with a false discovery rate set to 5%, while differences in the AUC for the same data were assessed using an unpaired t-test. Data was considered statistically significant when $p < 0.05$.

3   Results

3.1   Hydrogel Fabrication

hASCs were encapsulated using a thermally-induced crosslinking approach and cultured for up to 7 days *in vitro* within the composite hydrogels. As shown in Figure 1, the encapsulated hASCs remained viable across the 7-day culture period, with their morphology showing increased spreading over time. The hASCs were distributed heterogeneously throughout the gels, similar to the original study that indicated that the MGC-RGD phase provided a cell-supportive region, while the PEG(PTMC-A)$_2$ phase conferred mechanical properties aligned with the IM environment [11].

Figure 1. hASCs encapsulated in MGC-RGD+PEG(PTMC-A)$_2$ hydrogels remain viable over 7 days of culture, showing a heterogenous distribution, and increased spreading over time. Live/Dead™ staining was used to visualize hASCs within the composite hydrogels. Representative confocal microscopy imaging shows viable calcein$^+$ cells in green, and dead EthD1$^+$ cells in red. Scale bar represents 500 μm.

3.2   Initial Follow-Up Study in the FAL-CLI Model in NOD/SCID Mice

An initial *in vivo* study was performed using the FAL-CLI model in NOD/SCID mice to build on the previous findings by integrating LDPI to assess the restoration of hindlimb perfusion over time. Four treatment groups were assessed, with each group receiving a 20 μL injection distal to the

incision; hASC treatment groups received a total of $4\text{x}10^5$ hASCs ($2\text{x}10^7$ cells/mL). At day 0, all mice had a perfusion ratio (ischemic:non-ischemic limb) of < 0.15, confirming that blood flow to the ligated limbs was severely restricted. The LDPI data is presented in Figure 2, with Figure 2B showing the relative increase in the perfusion ratio over the 28-day period normalized to the day 1 values for each mouse. Notably, area under the curve (AUC) analysis showed a significant increase between the hASCs delivered in the hydrogel and the saline control groups (Figure 2C), consistent with the previously-published CD31 staining results that indicated vascular regeneration, and more specifically vessel density, was enhanced when the hASCs were delivered within the hydrogels [11].

Figure 2. hASCs delivered to the FAL-CLI model in NOD/SCID mice using the MGC-RGD+PEG(PTMC-A)$_2$ hydrogel system enhanced recovery of limb perfusion. (A) Representative LDPI images showing blood flow in the surgical (left) and control (right) limbs at days 1 and 28. (B) Mean flux was quantified within an ROI comprising the foot and ankle for both limbs. Perfusion ratio was calculated from the mean flux of the surgical limb / control limb for each mouse at each time point, and normalized to the perfusion ratio at day 1. Data presented as mean ± SD. No statistically significant differences between treatment groups at each timepoint were detected using two-way RM-ANOVA, with Tukey's post-hoc test for multiple comparisons (n=4 mice/treatment group). (C) Area under the curve (AUC) was calculated from the perfusion ratio data. The AUC for the hASCs delivered in the hydrogels was significantly greater than the saline control group (n=4 mice/treatment group). Data presented as mean ± SD. Differences in the AUC between groups were detected using one-way ANOVA, with Tukey's post-hoc test for multiple comparisons; Significant differences are indicated (** $p < 0.01$).

3.3   hASC Transduction

To enable longitudinal *in vivo* cell tracking via BLI, hASCs were engineered through lentiviral transduction to stably co-express FLuc to facilitate detection via BLI and tdT to identify the cells via flow cytometry and in tissue cross-sections [23]. Flow cytometry confirmed a high transduction efficiency (>85%) (Supplementary Figure S2). In addition, flow cytometry showed that transduction did not alter cell viability (>95%) or the hASC immunophenotype (Supplementary Figure S2).

In vitro studies using IVIS imaging to quantitatively assess luminescence associated with the transduced hASCs confirmed the sustained presence of viable hASCs following encapsulation within the composite MGC-RGD+PEG(PTMC-A)$_2$ hydrogels and culture for up to 14 days, with no significant difference in the signal over time (Figure 3).

Figure 3. *In vitro* luminescence imaging confirmed high hASC viability following hydrogel encapsulation and culture over 14 days. (A) Representative images show luminescent signal from the transduced FLuc$^+$tdT$^+$ hASCs encapsulated and cultured in the MGC+PEG(PTMC-A)$_2$ hydrogels. Scale bar = 5 mm. (B) Luminescent signals quantified across the 14-d culture period. All data presented as mean ± SD. No significant differences in average radiance across timepoints were detected using one-way ANOVA with Tukey's post-hoc test for multiple comparisons (n=4 hydrogels/timepoint).

3.4 Characterization of hASC delivery in the MGC-RGD + PEG(PTMC-A)₂ hydrogels in the FAL-CLI model in athymic nude (nu/nu) mice

Following the validation study in the NOD/SCID mice, the FAL-CLI model was applied in athymic nude mice to compare the efficacy of delivering the transduced hASCs in the composite MGC-RGD+PEG(PTMC-A)₂ hydrogels to hASC delivery in saline, with hydrogel alone and saline alone groups included as controls. Treatments were delivered at 24 h post-ligation, with all mice receiving 4×10^5 hASC (2×10^7 cells/mL) in 20 μL injections. Mice were assessed over 35 days, with weekly LDPI to assess recovery of perfusion, and weekly BLI to assess hASC viability and retention. Testing was completed on a total of 3 cohorts, with 6 mice per cohort, and each cohort was treated with a different hASC donor. Only the data from the first two cohorts are included in Figures 4 and 5, as the mice treated with the hASCs in the MGC-RGD+PEG(PTMC-A)₂ hydrogels in the third cohort had to be euthanized early due to adverse events, further detailed below.

Interestingly, mice that received hASCs delivered in saline had increased perfusion at day 21 compared to the hydrogel alone and saline alone controls (Figure 4B). However, AUC analysis revealed that the overall recovery of limb perfusion was significantly increased in the mice that received hASCs delivered in the hydrogel or saline, compared to both the hydrogel alone and saline alone controls (Figure 4C).

Figure 4. Delivery of hASCs in *nu/nu* mice with FAL increased the recovery of limb perfusion. (A) Representative LDPI images showing blood flow in the surgical and control limbs at days 1, 21, and 35 after the delivery of hASCs in hydrogel or saline, or hydrogel controls. (B) Mean flux was quantified within an ROI comprising the foot and ankle for both limbs. Perfusion ratio was calculated from the mean flux of surgical limb / control limb for each mouse at each time point, and normalized to the perfusion ratio at day 1. At day 21, mice that received hASCs in saline had significantly higher perfusion compared to mice that received the hydrogel or saline alone controls (# $p < 0.05$). This data encompasses two sets of surgeries taken out to 35 days (n=4 mice/hASC treatment group, n=2 mice/control treatment group). Data presented as mean ± SD.

Differences between treatment groups at each timepoint were detected using two-way RM-ANOVA, with Tukey's post-hoc test for multiple comparisons. (C) Area under the curve (AUC) was calculated from the perfusion ratio data. Both hASC treatment groups resulted in significantly higher AUC compared to both control groups (* $p<0.05$), indicating that hASC treatment accelerated the recovery of limb perfusion in the FAL-CLI model in nu/nu mice. Data presented as mean ± SD. Differences between treatment groups were detected using one-way ANOVA, with Tukey's post-hoc test for multiple comparisons (n=4 mice/hASC treatment group, n=2 mice/control treatment group).

The inclusion of transduced hASCs in this study also facilitated longitudinal *in vivo* cell tracking, addressing a key limitation of the previous studies [11]. Interestingly, the BLI data suggested that hASCs delivered in saline were better retained in the *nu/nu* model compared to hASCs delivered in the hydrogel (Figure 5). Of note, BLI measurements for mice that received the hASCs in saline appeared to increase from day 1 to 7, which may be attributed to enhanced delivery of the D-luciferin to the ischemic region. All mice that received hASCs delivered in saline showed >35% retention at day 35 compared to day 1, while all mice that received hASCs delivered in hydrogel showed ≤10% retention at day 35 compared to day 1, with one mouse showing 10% retention, and the other three showing ≤0.6% retention. AUC analysis showed a significant difference between the groups, supporting that cell retention was enhanced when the hASCs were delivered in saline compared to delivery within the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels (Figure 5C).

Figure 5. hASCs were better retained in the FAL-CLI model in *nu/nu* mice when delivered in saline as compared to the MGC-RGD+PEG(PTMC-A)₂ hydrogels. (A) Representative BLI images showing FLuc⁺ hASC signal in mice that received hASCs delivered in the hydrogel or saline at day 1 and 35. Each mouse received 100 μL IP injection of D-luciferin, and bioluminescent images were taken until the signal peaked within the ROI. (B) Average bioluminescent radiance ($p/s/cm^2/sr$) was calculated within an ROI around the injection site for each mouse at each timepoint, and normalized to day 1. Individual data points for each mouse are shown, with the group mean plotted as a solid line. Dotted line represents day 1 values. Normalized average radiance for mice that received hASCs in hydrogel showed variability; one mouse had ~10% retention at day 35, and one mouse had ~1% retention, while two mice showed negligible retained cells. No statistically significant differences were detected between treatment groups at any timepoint, using multiple unpaired t-tests with a false discovery rate set to 5% (n=4 mice/treatment group). (C) AUC analysis of the normalized BLI data, indicating that the hASCs delivered in saline were better retained than the hASCs delivered using the hydrogel. Data presented as mean ± SD. Differences in the AUC were assessed using an unpaired t-test (n=4 mice/treatment group); Significant differences are indicated (** $p<0.01$).

Notably, several adverse events were observed in mice that were treated with the hASCs in the

MGC-RGD+PEG(PTMC-A)₂ hydrogels, which weren't observed in any other treatment group.

Table 2 summarizes the specific adverse events and the timepoints at which they were observed. Interestingly, mice that received the hASCs within MGC-RGD+PEG(PTMC-A)$_2$ hydrogels frequently demonstrated discoloration, swelling, and possible capsule or cyst formation at the site of injection, along with stiffness, difficulty ambulating, and discoloration of the toes or toenails. These symptoms were not observed in the hydrogel alone controls, or when the cells were delivered in saline, indicating that it was the combination of the cells and the hydrogel that was causing the adverse events. In the third cohort, toe necrosis and early signs of auto-amputation were observed in the two mice that received hASCs within the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels, which necessitated early euthanasia at day 12.

Table 2. Summary of adverse events for mice that received hASCs in hydrogel treatment.

Symptom	Timepoint				
	D4	D7	D12/ D14	D21	D28
Discoloration @ injection site (dark purple)	4/6	4/6	5/6	2/4	2/4
Discoloration of toes / toenails	1/6	2/6	3/6	0/4	0/4
Necrosis of toes, signs of auto-amputation	0/6	0/6	2/6	0/4	0/4
Cyst / Capsule @ injection site	0/6	2/6	4/6	2/4	2/4
Edema	4/6	5/6	4/6	2/4	2/4
Stiffness	0/6	0/6	2/6	2/4	2/4
Difficulty ambulating	1/6	1/6	4/6	2/4	2/4
Early euthanasia required	0/6	0/6	2/6	0/4	0/4

Immunofluorescence (IF) staining was performed for murine CD45 in thigh muscle sections of the two cohorts of mice that were euthanized at day 35, as well as the cohort euthanized at the early

timepoint of day 12/14 (Figure 6A & Supplementary Figure S3). Semi-quantitative scoring was performed in a blinded manner based on the following scale: 0 (no dense CD45$^+$ staining outside of the ligated vessel region), 1 (only one small region of dense CD45$^+$ staining), 2 (one medium region of dense CD45$^+$ staining or multiple small regions) or 3 (at least one large region of dense CD45$^+$ staining). Although there were only a small number of mice analyzed at the early timepoint, regions of dense CD45$^+$ staining were only observed in the mice that received hASCs delivered in the hydrogel (Figure 6B), consistent with the discoloration, edema, and swelling in these mice that necessitated euthanasia. Overall, the results at both timepoints indicated that hASC delivery using the hydrogel was more frequently associated with a more potent inflammatory response.

Figure 6. CD45$^+$ staining results showing a more potent inflammatory response within the ischemic muscle in a higher fraction of the mice that received hASCs in the hydrogel. Large regions containing a dense population of CD45$^+$ cells were only observed in mice that received hASCs delivered in the hydrogel. (A) Representative IHC images of mouse thighs harvested post-euthanasia at days 12/14 or 35 following FAL (DAPI$^+$ cells in blue and CD45$^+$ cells in red). Scale bar represent 250 μm. Larger tiled images used for scoring are shown in Supplementary Figure S3. (B) Semi-quantitative assessment of regions of dense CD45$^+$ staining within the thigh muscles of the ligated limb was performed, with blinded scoring on a scale of 0-3. Graph includes pooled data of all samples collected post-euthanasia at days 12/14 and 35. Data points represent scoring for individual mice, with the line representing the mean score for each treatment group.

4   Discussion

The delivery of hASCs to ischemic tissues represents a promising strategy for the treatment of PAD/CLI [4]. With the goal of augmenting vascular regeneration, we previously designed the composite MGC-RGD+PEG(PTMC-A)$_2$ hydrogels to support the localized retention of viable hASCs, while having the mechanical properties required to withstand the cyclic compressive loading expected within muscle tissue [11]. Building from this previous work, an initial follow-up study was performed in the FAL-CLI model in NOD/SCID mice using LDPI to assess the restoration of hindlimb perfusion over 28 days. LDPI is the most commonly used imaging tool to longitudinally assess the recovery of perfusion in preclinical murine FAL-CLI models and relies on comparison of differences in tissue perfusion at depths limited to < 1 mm between the surgical and contralateral control limb over time [24], [25]. AUC analysis of LDPI imaging showed a significant difference between the mice that were treated with the hASCs delivered in the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels compared to saline controls, suggesting that there was improved recovery of limb perfusion in this group. These findings were consistent with the augmented CD31$^+$ capillary density previously measured in the ischemic muscles at day 28 when hASCs were delivered in the hydrogels using the same model [11].

Immunocompromised mouse models are an important tool in the preclinical evaluation of human cell-based therapies [26]. In particular, NOD/SCID mice are frequently used in studies where long-term cell engraftment is desired, due to complete ablation of T- and B-lymphocytes (SCID mutation), and reduced macrophage numbers and function (NOD mutation) [27]. However, increasing evidence suggests that endogenous host immune cells are important mediators of both inflammation and vascular regeneration [28]. In particular, monocytes and macrophages play key roles in the balance between angiogenesis and inflammation [29], [30]. Moreover, it has been suggested that the full therapeutic effects of MSCs require the presence of endogenous macrophages/monocytes [31]. For this reason, the primary focus of the current study was to characterize the response of hASCs delivered within the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels in the FAL-CLI model in athymic *nu/nu* mice. This model was selected because while *nu/nu* mice lack a T-cell response, they have more functional macrophages compared to the more severely immunocompromised NOD/SCID model. Interestingly, when the FAL-CLI model was applied in athymic *nu/nu* mice, AUC analysis for the LDPI showed a significant increase for mice that were treated with hASCs, independent of the delivery method, compared to the hydrogel alone and saline alone controls. These findings contrast with the current and previous data in the NOD/SCID model [11], which suggested that vascular regeneration was augmented when the hASCs were delivered within the hydrogels.

Recognizing that methods to track the survival and retention and fate of delivered cells are essential in the development of MSC-based cell therapies to better understand the underlying mechanisms of regeneration, we engineered the hASCs to express firefly luciferase to enable longitudinal *in vivo* cell tracking by BLI [32]. BLI offers notable advantages over the more standard practice of using cell-specific markers to detect the delivered cell populations within tissue cross-sections,

which is extremely time-consuming and challenging to accurately quantify, and can only be performed at end-point after the cells may have already been cleared [32]. Importantly, only viable cells will produce luciferase and the luciferase-luciferin reaction requires ATP to produce light, and thus BLI detects live cells and can be used to track the survival and location of transplanted hASCs within individual mice over time [33]. Interestingly, the BLI data indicated that hASC retention/survival was augmented when the cells were delivered in saline as compared to within the hydrogels. Again, these findings are in contrast to the previous study in the NOD/SCID mice, where the hASCs were detected based on staining for HLA-ABC$^+$ cells in the muscle at 4 weeks post-transplantation when delivered in the hydrogels, but not when delivered in saline [11]. Although the variations in the cell tracking methods used in the two studies prevented direct comparison between the two mouse strains, the findings suggest that differences in the host response to the hASCs delivered in the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels impaired the retention of viable hASCs within the *nu/nu* mice.

Compared to studies in the literature that have indicated there is low cell retention following delivery in saline, the BLI data indicated that >35% of the hASCs delivered in saline were retained within the thigh muscles at the 35-day timepoint in the athymic *nu/nu* mice. It is important to note that differences across studies could be related in part to the specific MSC source applied, including whether the delivered cells are syngeneic, allogeneic, or xenogeneic in nature and if immunocompetent or immunocompromised mice are used. Unfortunately, comparative data is limited as only a small number of studies to date have characterized cell retention when developing cell therapies for CLI. In contrast to our findings, Laurila *et al*. delivered 1x10^6 Luc$^+$ MSCs derived from human embryonic stem cells in saline to an FAL-CLI model in immunocompetent Fischer 344 rats and showed using BLI that the relative luminescent signal decreased to 29% at 6 h post-

delivery, and further decreased to only 1.5% of the original intensity by 24 h post-delivery [10]. Using longitudinal fluorescent imaging, Wang *et al.* showed that the signal intensity of mouse ASCs delivered in saline to an FAL-CLI model in BALB/c nude mice decreased gradually to background levels by day 14 [34]. Also applying the FAL-CLI model in BALB/c nude mice, Fan *et al*. used BLI to demonstrate ~25% of FLuc$^+$ mouse ASCs were retained on day 14 when delivered in saline, followed by a progressive decline to background levels over 6 weeks [35]. Interestingly, Fan *et al*. also used longitudinal fluorescent imaging to track the cells, which showed a more rapid decrease in signal to background levels by day 28, confirming that different imaging modalities can influence the detection of retained cells [35].

While BLI is a powerful approach for tracking cell retention and survival, it is important to note that the impaired delivery of the D-luciferin is a potential limitation of its use in the FAL-CLI model, especially during the early stages following surgery when blood flow to the ischemic limb remains highly restricted. It would be expected that as vascular regeneration progresses and hindlimb perfusion is restored, there would be augmented and/or accelerated delivery of the luciferin substrate, which could impact the signal detected, as was observed with the relative increase in signal from day 1 to 7 in the hASC in saline group in the current study. While this makes absolute quantification of cell retention challenging at early time points, BLI remains a useful tool for comparing hASC retention between the two different delivery methods applied in the current study at each respective timepoint. As an alternative substrate-free approach, future studies could explore the use of near-infrared fluorescent reporters, which would allow for improved depth of penetration of signal compared to other fluorescent reporters and have shown promise for longitudinal *in vivo* tracking of delivered cells [36].

Combining the LDPI and BLI data, our findings suggest that enhanced cell retention may be insufficient to augment vascular regeneration. These results are in contrast to our previous findings in the NOD/SCID mice [11], as well as the previously-mentioned work of Wang *et al.*, who showed that delivery of mouse ASCs within composite chitosan-hyaluronic acid-based hydrogels enhanced their retention compared to delivery in saline, and that this was correlated with the increased recovery of hindlimb perfusion based on LDPI [34]. Notably, when the hASCs were delivered in the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels in the FAL-CLI model in athymic *nu/nu* mice, adverse events consistent with a negative host inflammatory response were observed in a higher fraction of the mice, with 5/6 mice showing marked swelling and limb discoloration, and 2/6 having a severe response including tissue necrosis that necessitated euthanasia. Importantly, none of these adverse events were observed in any of the other treatment groups, indicating that it was the combination of the cells and the hydrogel that was contributing to the negative immunological response.

Overall, these results highlight the importance of animal model choice when evaluating the efficacy of cell-based therapies, particularly in the context of vascularization. Similarly, Brady *et al.* showed differences in cell survival and blood vessel formation following implantation of engineered tissues seeded with human pluripotent stem cell-derived cardiomyocytes in athymic nude mice versus athymic nude rats [37]. Moreover, mouse strain has been shown to influence the severity of ischemia [26], [38], which may have also contributed to a harsher and more inflammatory microenvironment in the athymic mouse model used in the current study. In particular, a high incidence of ischemic limb necrosis has been reported in nude mice, which although not yet well understood, is thought to be related to the immune response and the ability

to form collaterals [26], [38]. Further testing of the platform within this model was discontinued due to ethical considerations.

Consistent with the macroscopic signs of a negative host inflammatory response, IF staining revealed dense regions of infiltrating $CD45^+$ murine cells within the ischemic muscles in a higher fraction of the mice that received the hASCs delivered in the hydrogel. We hypothesize that the hASCs within the hydrogels stimulated a more potent host macrophage response in the *nu/nu* mice, which may have led to accelerated hASC clearance. This interpretation is supported by our previous studies of the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels in the healthy immunocompetent rat model, which showed enhanced recruitment and greater infiltration of $CD68^+$ macrophages when rat ASCs were delivered within the hydrogels as compared to hydrogel alone controls, with most of the macrophages expressing the pro-inflammatory "M1-like" marker CCR7 [14]. Similarly, in addition to rapid MSC clearance from the site of injection, Laurila *et al*. showed increased $CD68^+$ macrophage infiltration in mice that received MSCs compared to saline controls in the FAL-CLI model in immunocompetent rats, suggesting that the macrophages may have contributed to the low cell survival or retention observed in their study [10].

5   Conclusion

Overall, the results of this study emphasize that the choice of animal model used to assess the efficacy of cell-based therapies can have a significant impact on the outcomes. In contrast to the findings in the NOD/SCID mice, hASCs were better retained in the athymic *nu/nu* mice following delivery in saline as compared to delivery within the MGC-RGD+PEG(PTMC-A)$_2$ hydrogels. Moreover, the combined LDPI and BLI data indicated that enhancing hASC retention does not necessarily augment vascular regeneration. Notably, signs of a negative immune response were

observed when the hASCs were delivered within the hydrogels in the athymic *nu/nu* mice, which were not observed in the other treatment groups or in previous testing in the NOD/SCID mice. When assessing the delivery of MSCs using biomaterials, the interactions between the delivered cells, the materials, and the host cells must be considered and carefully evaluated. As biomaterials can influence the host immune response, as well as the function of delivered cells, it will be essential to perform testing in animal models that have more functional immune systems to better recapitulate the human response and develop strategies that have a higher likelihood of success when translated to the clinic. In particular, the application of humanized mouse models is warranted to better assess how delivered human MSCs will interact with human immune cells and modulate the inflammatory response, including systematically probing the effects of different delivery strategies and cell doses [39], [40]. In addition, it would be interesting to investigate clodronate-induced macrophage depletion in mouse models to more specifically assess the roles of macrophages in mediating the response to cell-based therapies for vascular regeneration.

6   References

[1]   S. Barquera *et al.*, "Global Overview of the Epidemiology of Atherosclerotic Cardiovascular Disease.," *Arch. Med. Res.*, vol. 46, no. 5 PG-328–38, pp. 328–338, Jul. 2015.

[2]   P. Song *et al.*, "Global, regional, and national prevalence and risk factors for peripheral artery disease in 2015: an updated systematic review and analysis," *Lancet Glob. Heal.*, vol. 7, no. 8, pp. e1020–e1030, 2019.

[3]   V. N. Varu, M. E. Hogg, and M. R. Kibbe, "Critical limb ischemia," *J. Vasc. Surg.*, vol. 51, no. 1, pp. 230–241, 2010.

[4]   M. Merimi *et al.*, "The Therapeutic Potential of Mesenchymal Stromal Cells for Regenerative Medicine: Current Knowledge and Future Understandings," *Front. Cell Dev. Biol.*, vol. 9, 2021.

[5]   J. M. Gimble, A. J. Katz, and B. A. Bunnell, "Adipose-derived stem cells for regenerative medicine," *Circulation Research*, vol. 100, no. 9. pp. 1249–1260, 2007.

[6]   Y. Ikegame *et al.*, "Comparison of mesenchymal stem cells from adipose tissue and bone marrow for ischemic stroke therapy," *Cytotherapy*, vol. 13, no. 6, pp. 675–685, 2011.

[7]   Y. J. Kim, H. K. Kim, H. K. Cho, Y. C. Bae, K. T. Suh, and J. S. Jung, "Direct comparison of human mesenchymal stem cells derived from adipose tissues and bone marrow in mediating neovascularization in response to vascular ischemia," *Cell. Physiol. Biochem.*, vol. 20, no. 6, pp. 867–876, 2007.

[8]   M. Qadura, D. C. Terenzi, S. Verma, M. Al-Omran, and D. A. Hess, "Concise Review: Cell Therapy for Critical Limb Ischemia: An Integrated Review of Preclinical and Clinical Studies," *Stem Cells*, vol. 36, no. 2, pp. 161–171, 2018.

[9]   S. Lee *et al.*, "Enhanced therapeutic neovascularization by CD31-expressing cells and embryonic stem cell-derived endothelial cells engineered with chitosan hydrogel containing VEGF-releasing microtubes," *Biomaterials*, vol. 63, pp. 158–167, 2015.

[10]   J. P. Laurila *et al.*, "Human embryonic stem cell-derived mesenchymal stromal cell transplantation in a rat hind limb injury model," *Cytotherapy*, vol. 11, no. 6, pp. 726–737, 2009.

[11]   S. A. Young *et al.*, "Mechanically resilient injectable scaffolds for intramuscular stem cell delivery and cytokine release," *Biomaterials*, vol. 159, pp. 146–160, 2018.

[12]   J. A. DeQuach *et al.*, "Injectable skeletal muscle matrix hydrogel promotes neovascularization and muscle cell infiltration in a hindlimb ischemia model," *Eur. Cells Mater.*, vol. 23, pp. 400–412, 2012.

[13]   T. Kofidis, D. R. Lebl, E. C. Martinez, G. Hoyt, M. Tanaka, and R. C. Robbins, "Novel injectable bioartificial tissue facilitates targeted, less invasive, large-scale tissue restoration on the beating heart after myocardial injury," *Circulation*, vol. 112, no. 9 SUPPL., 2005.

[14]   S. A. Young, L. E. Flynn, and B. G. Amsden, " Adipose-Derived Stem Cells in a Resilient In Situ Forming Hydrogel Modulate Macrophage Phenotype ," *Tissue Eng. Part A*, vol. 24, no. 23–24, pp. 1784–1797, 2018.

[15] F. Anjum, A. Carroll, S. A. Young, L. E. Flynn, and B. G. Amsden, "Tough, Semisynthetic Hydrogels for Adipose Derived Stem Cell Delivery for Chondral Defect Repair," *Macromol. Biosci.*, vol. 17, no. 5, pp. 1–13, 2017.

[16] L. D. Shultz *et al.*, "Multiple defects in innate and adaptive immunologic function in NOD/LtSz-scid mice.," *J. Immunol.*, vol. 154, no. 1, pp. 180–91, 1995.

[17] A. K. Sharp and M. J. Colston, "The regulation of macrophage activity in congenitally athymic mice," *Eur. J. Immunol.*, vol. 14, no. 1, pp. 102–105, 1984.

[18] L. Flynn, J. L. Semple, and K. A. Woodhouse, "Decellularized placental matrices for adipose tissue engineering," *J. Biomed. Mater. Res. - Part A*, vol. 79, no. 2, pp. 359–369, 2006.

[19] A. M. Hamilton, P. J. Foster, and J. A. Ronald, "Evaluating Nonintegrating Lentiviruses as Safe Vectors for Noninvasive Reporter-Based Molecular Imaging of Multipotent Mesenchymal Stem Cells," *Hum. Gene Ther.*, vol. 29, no. 10, pp. 1213–1225, 2018.

[20] T. Couffinhal, M. Silver, L. P. Zheng, M. Kearney, B. Witzenbichler, and J. M. Isner, "Mouse model of angiogenesis.," *Am. J. Pathol.*, vol. 152, no. 6, pp. 1667–1679, Jun. 1998.

[21] B. J. Capoccia, R. M. Shepherd, and D. C. Link, "G-CSF and AMD3100 mobilize monocytes into the blood that stimulate angiogenesis in vivo through a paracrine mechanism," *Blood*, vol. 108, no. 7, pp. 2438–2445, Oct. 2006.

[22] F. C. C. C. Van Rhijn-Brouwer, H. Gremmels, K. Den Ouden, M. Teraa, J. O. Fledderus, and M. C. Verhaar, "Human Bone Marrow Mononuclear Cells Do Not Improve Limb

Perfusion in the Hindlimb Ischemia Model," *Stem Cells Dev.*, vol. 31, no. 7–8, pp. 176–180, 2022.

[23] M. Köberle, K. Müller, M. Kamprad, F. Horn, and M. Scholz, "Monitoring disease progression and therapeutic response in a disseminated tumor model for non-hodgkin lymphoma by bioluminescence imaging," *Mol. Imaging*, vol. 14, no. 6, pp. 400–411, 2015.

[24] S. M. Krishna, S. M. Omer, and J. Golledge, "Evaluation of the clinical relevance and limitations of current pre-clinical models of peripheral artery disease," *Clin. Sci.*, vol. 130, no. 3, pp. 127–150, 2016.

[25] A. Greco *et al.*, "Repeatability, reproducibility and standardisation of a laser doppler imaging technique for the evaluation of normal mouse hindlimb perfusion," *Sensors (Switzerland)*, vol. 13, no. 1, pp. 500–515, 2013.

[26] D. Thomas *et al.*, "Variability in endogenous perfusion recovery of immunocompromised mouse models of limb ischemia," *Tissue Eng. - Part C Methods*, vol. 22, no. 4, pp. 370–381, 2016.

[27] J. E. Belizario, "Immunodeficient Mouse Models: An Overview," *Open Immunol. J.*, vol. 2, no. 1, pp. 79–85, 2009.

[28] Z. Julier, A. J. Park, P. S. Briquez, and M. M. Martino, "Promoting tissue regeneration by modulating the immune system," *Acta Biomater.*, vol. 53, pp. 13–28, 2017.

[29] K. L. Spiller, D. O. Freytes, and G. Vunjak-Novakovic, "Macrophages Modulate Engineered Human Tissues for Enhanced Vascularization and Healing," *Ann. Biomed.*

Eng., vol. 43, no. 3, pp. 616–627, 2015.

[30]   M. Heil, I. Eitenmüller, T. Schmitz-Rixen, and W. Schaper, "Arteriogenesis versus angiogenesis: Similarities and differences," *J. Cell. Mol. Med.*, vol. 10, no. 1, pp. 45–55, 2006.

[31]   F. Carty, B. P. Mahon, and K. English, "The influence of macrophages on mesenchymal stromal cell therapy: Passive or aggressive agents," *Clin. Exp. Immunol.*, vol. 188, no. 1, 2017.

[32]   P. E. de Almeida, J. R. M. van Rappard, and J. C. Wu, "In vivo bioluminescence for tracking cell fate and function," *Am. J. Physiol. - Hear. Circ. Physiol.*, vol. 301, no. 3, 2011.

[33]   P. K. Nguyen, J. Riegler, and J. C. Wu, "Stem cell imaging: From bench to bedside," *Cell Stem Cell*, vol. 14, no. 4, pp. 431–444, 2014.

[34]   X. Wang *et al.*, "Composite Hydrogel Modified by IGF-1C Domain Improves Stem Cell Therapy for Limb Ischemia," *ACS Appl. Mater. Interfaces*, vol. 10, no. 5, pp. 4481–4493, 2018.

[35]   W. Fan *et al.*, "Adipose Stromal Cells Amplify Angiogenic Signaling via the VEGF/mTOR/Akt Pathway in a Murine Hindlimb Ischemia Model: A 3D Multimodality Imaging Study," *PLoS One*, vol. 7, no. 9, 2012.

[36]   Y. Zheng *et al.*, "Stem Cell Tracking Technologies for Neurological Regenerative Medicine Purposes," *Stem Cells Int.*, vol. 2017, 2017.

[37]   E. L. Brady *et al.*, "Engineered tissue vascularization and engraftment depends on host

model," *Sci. Rep.*, vol. 13, no. 1, 2023.

[38] P. K. Shireman and M. P. Quinones, "Differential necrosis despite similar perfusion in mouse strains after ischemia," *J. Surg. Res.*, vol. 129, no. 2, pp. 242–250, 2005.

[39] R. M. Wang, J. He, Y. Xu, and K. L. Christman, "Humanized mouse model for evaluating biocompatibility and human immune cell interactions to biomaterials," *Drug Discov. Today Dis. Model.*, vol. 24, pp. 23–29, 2017.

[40] V. J. Mehler, C. Burns, and M. L. Moore, "Concise Review: Exploring Immunomodulatory Features of Mesenchymal Stromal Cells in Humanized Mouse Models," *Stem Cells*, vol. 37, no. 3, pp. 298–305, 2019.