PenTag, a Versatile Platform for Covalent Bioconjugation, Purification, and Tagging of Proteins Towards the Development of Novel Biohybrid Material Systems

Hasti Mohsenin[1,2], Jennifer Pacheco[1,2], Svenja Kemmer[1,3,4], Hanna J. Wagner[1,2], Nico Höfflin[1,2], Toquinha Bergmann[1,3,4], Tim Baumann[1,2], Alexander Ripp[5,6], Nikolaus Jork[1,5,7], Henning J. Jessen[1,5,6], Maja Köhn[1,2], Jens Timmer[1,3,4], Wilfried Weber[1,2,7,8,9]*

Keywords: covalent protein-ligand interaction, protein solubility and purification tags, stimuli-responsive hydrogels, information-processing materials, covalent crosslinking

[1] Signalling Research Centres BIOSS and CIBSS, University of Freiburg, Freiburg, Germany

[2] Faculty of Biology, University of Freiburg, Freiburg, Germany

[3] Institute of Physics, University of Freiburg, Freiburg, Germany

[4] Freiburg Center for Data Analysis and Modelling (FDM), University of Freiburg, Freiburg, Germany

[5] Institute of Organic Chemistry, University of Freiburg, Freiburg, Germany

[6] Cluster of Excellence LivMats, University of Freiburg, Freiburg, Germany

[7] SGBM - Spemann Graduate School of Biology and Medicine, University of Freiburg, Freiburg, Germany

[8] INM – Leibniz Institute for New Materials, Saarbrücken, Germany

[9] Department of Materials Science and Engineering, Saarland University, Saarbrücken, Germany

Abstract

Protein tags play an important role in various chemical biological applications and synthetic biological systems. An ideal protein tag enables labelling of proteins, their monitoring, and detection. Moreover, it forms a stable bond with its specific ligand, which is ideally an available and cheap molecule. Current protein tagging systems are often challenging due to unspecific binding, unstable coupling, or expensive and difficult-to-synthesize ligand molecules. Here, we

present PenTag, an approach for the biorthogonal, and covalent conjugation of a specific protein

tag to its ligand for various applications in chemical and synthetic biology. We engineered a new

truncated version of penicillin-binding protein 3 (PBP3) and showed that this protein tag can be

used for the stable conjugation of proteins to dyes, polymers, or solid supports. We applied

PenTag as crosslinking tool for synthesizing stimuli-responsive hydrogels or for the development

of a biohybrid material performing computational operations emulating a 4:2 encoder. Based on

this broad applicability and the use of a small, cheap and easy-to-functionalize ligand and a stable,

soluble recombinant protein, we see PenTag as a versatile alternative to existing protein tags.

Introduction

Protein tags are fundamental modification tools that in recent years have resulted in better

understanding of cellular functions, development of novel therapeutics, advanced imaging

techniques, and synthesis of protein-based materials[1–6]. Protein tags that bind covalently to their

substrates, create a platform for stable and robust anchoring of proteins to small molecules and

materials[7–12].

Several techniques have been developed for site-specific conjugation and modification of

proteins through covalent binding that have paved their way through various applications in

visualizing and manipulating biological processes[13]. Moreover, covalent attachment of chemicals

to antibodies or oligonucleotides have resulted in antibody-drug conjugates (ADCs) and antibody-

oligonucleotide conjugates (AOCs) as novel therapeutic vehicles for the treatment of various

cancers and for non-oncological diseases[14–17]. For example for site-specific protein conjugation,

cysteine residues in proteins can be used for bioconjugation of proteins via Thiol-Michael

addition reactions of maleimides or vinylsulfones[18–20]. However, if more specific site-selectivity

is required, enzymatic labelling techniques, based on, for example *E. coli* biotin ligase BirA, or

Staphylococcus aureus sortase A (SrtA)-mediated transpeptidation reactions are superior[21,22].

Another technique for site-specific protein labelling uses protein tags that do not require the

addition of an additional enzyme that catalyses the coupling reaction[13]. SNAP-, Halo-, and CLIP-

Tags are three examples of versatile protein tags that can be used for labelling of proteins for

diverse applications such as the specific immobilization and purification of proteins[23–27]. These

tags are based on engineered self-modifying enzymes that spontaneously react with O[6]-

benzylguanine (BG), chloroalkane, and benzylcytosine (BC) derivatives, respectively, leading to a

covalent conjugation of the protein to its ligand. These tags are widely used for the spontaneous

coupling of proteins to different ligands. However, the required reactive groups are fine

chemicals and available in small quantities at rather high prices. Amine-functionalized BG, BC,

and HaloTag ligands cost 170, 600, and 140 USD per gram, respectively[28].

In addition to mediating site-specific conjugation, an ideal protein tag for synthetic and chemical

biology applications enables the detection, visualization, and purification of its fusion partner,

confers increased solubility and is able to link the protein of interest to various types of

substrates. For some applications, it would be beneficial if the protein tag is small in size and

forms a fast and stable bond at a variety of different temperatures and buffer conditions[8,29].

Additionally, an ideal ligand would be a simple and cheap chemical that is widely commercially

available.

ß-lactam antibiotics such as ampicillin have the interesting property that they bind specifically

and covalently to penicillin-binding proteins (PBPs). PBPs are transpeptidase enzymes involved in

bacterial cell-wall biosynthesis and are the target of ß-lactam antibiotics[30]. Interaction of PBPs

with ß-lactam antibiotics starts with the formation of a non-covalent Henri-Michaelis complex

and is followed by the attack of the serine residue in the active site of the enzyme to the ß-lactam

ring, that results in a covalent acyl-PBP bond[31,32]. In previous works we have applied this specific

coupling for the development of microfluidic, point-of-care-suitable assays for electrochemical

antibiotics detection in various settings[33–36].

Here, we exploit the spontaneous, covalent interaction between ampicillin and PenTag for the

development of a protein tag and demonstrate its application in protein immobilization and

purification. We use this conjugation technique as a building block towards the design of

biohybrid materials performing fundamental computational operations, while showing its

biorthogonality to the already existing systems. Besides broad application potential and ease of

handling, the bulk availability of ampicillin at very low cost (1.6 USD per gram[28]) is an interesting

factor in synthesizing larger quantities of bioconjugates.

Results

Engineered truncated PBP3 binds stably to ß-lactam antibiotics

Large proteins devour more metabolic energy during overexpression in *E. coli* compared to

smaller proteins[29]. Further, large proteins represent a less favourable cost-benefit ratio if only

one part of the protein structure is needed. However, reducing the size of proteins must be

carefully planned and tested to avoid a negative impact on their functionalities. We therefore

aimed at the design of a truncated version of PBP3, which is still able to bind to ß-lactam

antibiotics. To this aim, we exploited a mutated PBP3[33,37] and the known crystal structure of

PBP3[38] to truncate the C-terminal hydrophobic membrane anchor thereby generating a new

version of PBP3, termed PBP3-t (Fig. 1a). We produced hexahistidine-functionalized PBP3-t in *E.*

coli, purified it by immobilized metal affinity chromatography (IMAC), and performed analysis by

SDS-PAGE and Coomassie staining. The protein migrated at a position corresponding to 30.2 kDa,

which is in agreement with its predicted molecular weight (Fig. S1a).

As shown in Figure 1b, derivatives of ß-lactam antibiotics are expected to undergo ring opening

when coupled to PenTag. This covalent conjugation could be a useful candidate for protein

immobilization and purification, and moreover towards development of smart materials. To

evaluate the functionality of PBP3-t compared to PBP3, we separately reacted both proteins with

bocillin-FL penicillin, a fluorescent derivative of ß-lactam antibiotics, in a 1:1 protein to bocillin-

FL molar ratio at room temperature. To compare the bond between bocillin-FL and both PBP3

versions, we measured fluorescence polarization of these conjugates (Fig. 1c). No significant

difference could be seen between the polarization of PBP3 and PBP3-t.

Furthermore, we tested the stability of the bond between PBP3-t and bocillin-FL over time. We

measured the fluorescence polarization of a mixture of PBP3-t and bocillin-FL over 7 days at 4 °C.

We did not observe a statistically significant difference in the polarization over time (Fig. 1d).

Moreover, we showed that our PenTag-antibiotic complex is most stable at physiological pH

(between pH 7.5 and 8.5), which is of high relevance for biorthogonal conjugations (data shown

in Supplementary Information, Fig. S1b,c). A major challenge in protein overproduction in *E. coli*

is the formation of insoluble aggregates[39]. One promising strategy to overcome this limitation is

the fusion to solubilization domains[40], therefore, here we evaluated whether PenTag can be used

to increase solubility of an otherwise difficult-to-produce protein and showed its ability to

enhance protein solubilization (data shown in Supplementary Information, Fig. S2a).

PenTag as a novel synthesis strategy for stimuli-responsive hydrogels

After validating the interaction between PBP3 versions and ampicillin, we sought to extend this

protein-ligand framework in biohybrid hydrogel synthesis. Programmable hydrogels are

attractive materials for controlled delivery of biomolecules or as biosensing devices[41–43]. We

aimed to develop stimuli-responsive hydrogels benefiting from the covalent bond between the

PenTag and its small molecule ligand, ampicillin. For this, we first functionalized four-arm

poly(ethylene glycol) succinimidyl carboxymethyl ester (4-arm PEG-SCM) with ampicillin

(Supplementary Information Fig. S3), followed by purification via reversed-phased preparative

high-performance liquid chromatography (HPLC) to remove unbound ampicillin molecules

(Supplementary Information Fig. S4a). For the characterization of the 4-arm PEG-tetra ampicillin,

we performed NMR and matrix-assisted laser desorption/ionization time-of-flight (MALDI–ToF)

of the purified samples (Fig. S5, and Fig. S4b respectively). The obtained results were in

agreement with the expected NMR and MALDI–ToF characterizations.

As a crosslinker we designed an mCherry protein which was N- and C-terminally fused to PBP3-t

via a linker containing cleavage sites for caspase-3 protease (Casp3). We then mixed 4-arm PEG-

ampicillin with the protein crosslinker at a 1 : 4 molar ratio of PenTag : ampicillin. Within 40 h,

gelation was observed (Fig. 2a). To test whether a controlled degradation of the hydrogel and

release of mCherry is achievable by the stimulus, Casp3, we traced the fluorescence of mCherry

in the supernatant after addition of different amounts of Casp3 (Fig. 2b). Whereas no significant

mCherry release was observed in the absence of Casp3, increasing protease concentrations

correlated with higher mCherry release. These data show that PenTag offers a simple way of

synthesizing biohybrid materials e.g., for the controlled, stimulus-dependent release of
biomolecular cargos.

PenTag as affinity tag for immobilization of proteins on crosslinked agarose beads

Immobilization of proteins and biomolecules on solid supports enables the development of
affinity matrices, micro devices, and bead-based protein assays for multiplexed analytical
devices[7,44]. To produce an immobilization matrix to covalently bind PenTag, we functionalized
cyanogen bromide (CNBr)-activated crosslinked agarose with ampicillin. CNBr first reacts with
hydroxy groups of crosslinked agarose resulting in the formation of reactive cyanate ester groups.
The primary amino group of ampicillin subsequently reacts with the cyanate ester, resulting in
stable isourea linkages (Fig. 3a)[45]. To test whether ampicillin-functionalized beads can be used
for the immobilization and subsequent release of PenTagged proteins, we genetically fused
mCherry either to PBP3 or to PBP3-t. In both constructs, a protein linker containing the cleavage
site for Casp3 was introduced to allow the release of mCherry from the beads by the addition of
Casp3 (Fig. 3b). To measure the binding capacity of the beads, we measured the fluorescence of
Casp3-released mCherry and calculated the amount of released protein according to an mCherry
standard per ml settled beads (Fig. 3c). The binding capacity of >2 mg protein per ml settled
ampicillin-functionalized beads compares favourably to the existing bead functionalization
methods of HaloTag and SNAP-Tag with binding capacities of 7 mg and 1 mg protein per ml
settled beads, respectively. To assess long-term stability of ampicillin-functionalized beads, the
beads were lyophilized and reconstituted in buffer directly after lyophilization or after 18 days
storage at 4°C. The binding capacity was assessed as described above and no statistically
significant decline was observed in either condition. Moreover, no significant difference was
observed between two PenTag versions, meaning that both of them can be used
interchangeably. We further assessed PenTag as a purification tag for proteins and compared it
to protein purification via IMAC and could show that PenTag can successfully be used as a
purification tag as well. Data shown in Supplementary Information Fig. S2b.

Design, characterization, and development of an information processing material system

Biocomputing materials perceive several input stimuli, process those stimuli according to

fundamental computational operations and produce a corresponding output. Examples include

materials that can count the number of input pulses or that act as signal amplifier via integrated

feedback and feedforward loops[11,12,46]. Materials with information-processing capacity enable

multiple applications for example in diagnostics or personalized therapy[13]. Among computational

operations, the encoder functionality is fundamental in binary data processing with manifold

applications e.g. in therapies, medical image analysis, or biosensor fabrication[47,48]. The

functionality and the operation characteristics of a 4:2 encoder as well as its implementation by

connecting two OR gates is depicted in Fig. 4a,b.

To assemble an encoder material framework, we capitalized on our ampicillin-functionalized

agarose beads for protein immobilization via PenTag. We first developed two separate agarose-

based orthogonal OR gates (Fig. 4c,d), each being responsive to two different proteases and

releasing a fluorescent protein, mCherry or GFP, as output. The first OR gate is composed of

mCherry genetically fused to PenTag via a linker containing cleavage sites for Casp3 as well as for

the tobacco vein mottling virus (TVMV) protease. The fusion protein is covalently coupled to

ampicillin-functionalized crosslinked agarose. The addition of either protease is expected to

result in the release of mCherry that can be quantified by fluorescence measurement (Fig. 4c).

The second OR gate is synthesized from GFP protein genetically fused to HaloTag via a linker

containing cleavage sites for tobacco etch virus protease (TEV) and Casp3. This fusion protein is

covalently coupled to Halo-ligand-functionalized crosslinked agarose, commercially available

HaloLink resin. The addition of TEV OR Casp3 results in the release of GFP that is quantified by

fluorescence measurement (Fig. 4d).

To characterize each of the OR gates, we first monitored dose-dependent release of mCherry and

GFP upon addition of their input proteases (Fig. 4e and Fig. 4f, respectively). We further

characterized the cleavage kinetics in response to protease addition. For this, we fixed the

protease concentration to the lowest value that resulted in a plateau in the above dose-response

measurements (for the mCherry gate: 1.25 µg ml^{-1} for Casp3 and 225 µg ml^{-1} for TVMV; for the

GFP gate: 0.625 µg ml^{-1} for Casp3 and 3.125 µg ml^{-1} for TEV). The kinetic data from these

experiments were used to parameterize a quantitative mathematical model based on ordinary

differential equations (ODEs). In order to identify a parameter combination in which the

assembled system would show 4:2 encoder functionality within a desired timeframe (30 min),

we simulated the performance of the assembled system as a function of the concentrations of

all input proteases (Fig. 4i left) (details of the mathematical model can be found in Supplementary

Information, Fig. S6, S7 and Table S2).

To confirm the model predictions, an experiment was conducted with the following predicted

parameters: final concentrations of 6, 14, and 800 µg ml^{-1} for Casp3, TEV, and TVMV respectively.

To assemble the 4:2 encoder, we combined both modules with each other in a single pot in the

presence or absence of each of the three input proteases (time-resolved model predictions for

the encoder response are shown in Fig. S8a). An output pattern specific for a 4:2 encoder was

predicted (Fig. 4i left). This pattern could experimentally be obtained, which demonstrates the

functionality of the overall computing network and validates the predictions of the mathematical

model (Fig. 4i right, kinetic data in Supplementary Information Fig. S8b).

This set-up shows that this novel conjugation platform is biorthogonal to existing protein tags

(HaloTag) and can further serve as a robust building block towards the development of

information-processing materials.

Discussion

We developed a truncated version of PBP3 and demonstrated the covalent binding of both PBP3

versions to ampicillin and termed this technology as PenTag. The spontaneous binding of PenTag

to its small molecule ligand opened the door for multiple applications in chemical biology and

biorthogonal coupling. Protein tags that not only solve purification issues of proteins of interest,

but also facilitate protein labelling by organic dyes are extremely beneficial for protein

visualization and detection[8]. Moreover, embedding proteins of interest into hydrogels through a

covalent protein-ligand interaction can serve as attractive means for the immobilization and

controlled delivery of proteins and other molecules[7,13]. Furthermore, such a system that is

orthogonal to the existing systems, can extend the library for covalent protein immobilization on

materials and enable the development of information-processing materials[9]. A drawback of the

already existing systems is the expensive and difficult-to-synthesize small molecules. Here, we

benefit from ampicillin as the ligand, a small, available, and cheap molecule that can easily be

coupled via its primary amino group to a large variety of N-hydroxy succinimide (NHS)-

functionalized commercially available reagents. For example, NHS-functionalized dyes, biotin-

labelling reagents, surfaces, polymers, and beads are readily available[34,49–53].

In order to introduce a multi-functional protein tag, we first engineered a truncated version of

PBP3 with a size of 30.2 kDa, which is 12 kDa smaller than the previous PBP3 version, yet as active

as the 42 kDa version. PenTag was shown to enhance the solubility of a fused insoluble protein

of interest, to address a common challenge when working with proteins[54]. Our system has shown

to be stable at physiological pH values, the environment where most proteins are stable at.

Despite the increase in size when fusing PenTag to proteins of interest, this method offers high

specificity and does not require addition of an enzyme as for enzyme-based conjugation

methods[55–57]. This facilitates downstream processing of functionalized materials.

We used PenTag strategy for covalent immobilization of proteins of interest into hydrogels and

their controlled release by defined environmental cues. Due to the easy coupling of ampicillin to

other molecules, different polymers with various sizes can be functionalized with ampicillin, and

thereby desired hydrogels can be tailored depending on the final applications. Here, we chose a

4-arm PEG-SCM and functionalized it with ampicillin and could establish covalent crosslinks using

PenTag where a controlled release of protein of interest from the hydrogel was achieved by

addition of Casp3 protease.

Furthermore, we synthesized ampicillin functionalized crosslinked agarose that has applications

in various fields, such as protein microdevice assays or for high purity purifications[44,58].

Lyophilized ampicillin agarose beads were shown to be stable, which allows the off-the-shelf

usage for protein immobilization or capture[59].

Signalling and logic circuit designs using proteases have significantly been advanced in the recent

years[12,60,61]. Implementation of such circuits onto materials frameworks would add another level

of applicability and dimension towards development of powerful information-processing

materials[10,11]. Benefiting from various synthetic biological building blocks, we integrated

conceptual engineering principles into materials. These materials sense environmental cues as
their inputs, can then process information, and finally exhibit a regulated output. In this work,
we first assembled simple OR gate material modules using PenTag and compared it to the existing
systems. We then did thorough characterization of the both systems by a mathematical model,
and finally developed a one-pot combined system that could perform more complicated
information processing and produce regulated and clear outputs in a 4:2 encoder design manner.
We further validated the predictions of the mathematical model by experimental data.

In summary, we introduced a specific and multifunctional protein tag which is highly modular
regarding the protein of interest, and even useful when working with insoluble proteins of
interest. We showed broad applications for PenTag and specifically demonstrated that hydrogels
and other materials systems can be tailored to response to environmental cues, or to perform
sensory functions using this strategy.

We see PenTag as a versatile, modular tool, orthogonal to existing systems, which is an
advantageous candidate for implementation and detection of biological molecules in material
frameworks by means of a simple small molecule. Due to its simplicity, cost-efficiency, and high
specificity, proteins of interest could covalently and stably be coupled onto different substrates
such as hydrogels and other solid supports. We expect that this platform will find broad
application not only in chemical and synthetic biology, but also in advanced devices for analytical
and diagnostic applications, as controlled drug delivery vehicles, or in tissue engineering and
regenerative medicine.

Methods

Cloning of the plasmids

The amino acid sequence of all plasmids and their description are listed in Supplementary
Information Table S1. Constructs were cloned by Gibson assembly[62].

Protein expression and purification

For production of all recombinant proteins, plasmids were transformed into *E. coli* BL21 (DE3)

pLysS (Invitrogen). Cells were grown at 37 °C while shaking at 150 rpm in LB medium containing

100 μg ml^{-1} ampicillin (Carl Roth) and 36 μg ml^{-1} chloramphenicol (Carl Roth). Once an OD$_{600}$ of

0.6 was reached, the cultures were induced with 1 mM isopropyl ß-D-1-thiogalactopyranoside

(IPTG) and incubated overnight at 18 °C or for 4 h at 30 °C or 37 °C (pKJ57 4 h at 37 °C). Cells were

harvested by centrifugation at 6000 x g for 10 min and were subsequently resuspended in 35 ml

nickel-lysis buffer (50 mM NaH$_2$PO$_4$, 300 mM NaCl, 10 mM imidazole, pH 8.0), flash frozen and

stored at -80 °C until further use. For lysis, cells were sonicated at 60% amplitude and 0.5 s/ 1 s

pulse/ pause intervals with a Sonopuls HD3100 (Bandelin). Crude lysates were centrifuged at

30,000 x g for 30 min. The protein in the supernatant were purified IMAC, using Ni-NTA Superflow

agarose beads (Qiagen) or using ampicillin functionalized agarose. For Ni-NTA purification

following the manufacturer's instructions, proteins were loaded onto the already Ni lysis-

equilibrated columns, unbound protein was washed away by two wash steps using Ni wash buffer

(50 mM NaH$_2$PO$_4$, 300 mM NaCl, 20 mM Imidazole, pH 8.0), followed by elution with Ni elution

buffer (50 mM NaH$_2$PO$_4$, 300 mM NaCl, 250 mM Imidazole, pH 8.0). Eluted proteases were

additionally supplemented with 10 mM 2-β-mercaptoethanol (2-ME). All eluted proteins were

dialyzed against 5 L 1x PBS using SnakeSkin dialysis tubes with 3.5k molecular weight cut-off

(MWCO) (Thermo Fisher Scientific) at 4 °C. Proteins were subsequently analyzed by SDS-PAGE

(15% (w/v) gels at 160 V), stained by Coomassie brilliant blue staining, and the concentration of

the protein was determined either by SDS-PAGE or by Bradford assay using protein assay dye

reagent (Bio-Rad) and bovine serum albumin (Carl Roth) as standard. Measurement was

performed in a Multiskan GO spectrophotometer at 575 nm (Thermo Fisher Scientific). In some

cases, proteins were concentrated using Spin-X UF 6 columns (Corning Inc., Corning, USA).

Purified proteins were supplemented with 15% (v/v) glycerol and stored at -80 °C for further use.

For solubility tag experiments, PBP3-t was N-terminally fused to an insoluble construct containing

a Pyruvate dehydrogenase complex repressor (PdhR) and an intrinsically disordered protein

domain. Protein expression was performed at 18 °C for 16 h.

Fluorescence polarization

To analyze the binding between ampicillin and PenTag, a fluorescent derivate of penicillin,

Bocillin-FL (Thermo Fisher Scientific), was incubated with both PBP3 versions in a molar ratio of

1:1 at 4 °C, with a final concentration of 50 µM in 1x PBS. Blank samples in the absence of protein

were prepared to measure background fluorescence and the fluorescence quenching of the

fluorophore when incubated for several days at 4 °C. The mixtures were allowed to reach

equilibrium for 1 h at room temperature and then transferred to 4 °C. Fluorescence polarization

of 15 µl of the samples in a 384-well plates (Corning 3575) was measured by exciting the samples

with polarized light at 485/20 nm and emission at 528/20 nm at a parallel and perpendicular

angle for 40 min with an interval of 5 min to make sure the plateau is maintained using a Synergy

4 plate reader (BioTek Synergy 4, Vermont, United States). Fluorescence polarization was then

calculated using the following equation:

$$P = \frac{(F_{\parallel} - F_{\perp})}{(F_{\parallel} + F_{\perp})}$$

316 $F_{\parallel}$ = fluorescence parallel to the excitation plane; $F_{\perp}$ = fluorescence perpendicular to the

317 excitation plane). As negative control the FP of Bocillin-FL alone was measured and its

318 fluorescence quenching over days was used for data normalization.

Functionalization of 4-arm PEG with ampicillin

4-arm PEG-NHS, MW 5k (4-arm PEG-SCM, Creative PEG works, Durham, USA) and ampicillin

(Roth) were both dissolved in dimethylformamide (DMF) with a concentration of 100 mg ml^{-1} and

20 mg ml^{-1} respectively. A 6x molar excess of ampicillin (192 µmol) was mixed with 15 µmol

triethylamine (Sigma) prior to being added drop-wise to PEG-SCM (32 µmol). All steps were

conducted in an exicator under argon flow. For purification, preparative HPLC (Agilent

Technologies 1260 Infinity I/II) was conducted to separate excess ampicillin from PEG-tetra-

ampicillin. Briefly, preparative HPLC was employed using a reversed-phase C18 column

(Macherey-Nagel VP 250/21 Nucleodur 100-5) with a mobile phase solvent A (Water + 0.05%

vol/vol trifluoroacetic acid (TFA)), solvent B (acetonitrile + 0.05% vol/vol TFA). The column was

eluted with a gradient of solvent B 10-90% over 20 minutes at a flow rate of 20 ml min^{-1}, and

fractions were monitored by UV-absorption at 230 nm.

Characterization of the polymer

Samples of collected fractions of preparative HPLC were monitored by MALDI-ToF mass

spectrometry to confirm the right size of the purified samples. For this, samples were dissolved

in acetonitrile (HPLC grade). 5 μl of the sample solution was mixed with 5 μl of a saturated

solution of α-cyano-4-hydroxycinnamic acid matrix for MALDI-MS (Sigma-Aldrich) in acetonitrile.

1.5 μl of the latter mixture was applied to the MALDI target and let dry. Analysis was carried out

on a Microflex MALDI mass spectrometer (Bruker) and data was processed via mMass software

and GraphPad Prism.

For precise characterization of the final product and free ampicillin molecule, ^{1}H NMR spectra

were recorded at room temperature on a Bruker Avance Neo (400 MHz). Samples were dissolved

in deuterated DMSO or chloroform.

Once the fractions were characterized, they were freeze-dried and lyophilized. Samples were

subsequently diluted in ddH$_2$O and stored at -20 °C for further use.

Hydrogel synthesis

For hydrogel synthesis, purified PBP3t-mCherry-PBP3t (pHM528) was concentrated to ~150 mg

mL^{-1} by centrifugation using Spin-X UF 20 mL centrifugal concentrators (30 kDa MWCO, Corning

Inc., Corning, USA). Hydrogels of 10 μL volume were produced by mixing 14.6 nmol PBP3t-

mCherry-PBP3t (pHM528) with PEG-tetra-ampicillin in PBS in a 1:4 PenTag : ampicillin molar ratio.

Glass slides were siliconized by Sigmacote (Sigma-Aldrich) according to manufacturer's

instructions. Briefly, clean glass slides were immersed in Sigmacote, air-dried under a fume hood,

and were subsequently washed with water and let dry. The polymer-protein mixture was spotted

on siliconized glass slides and incubated at room temperature for ~40 h under humidifying

atmosphere. Afterwards, the hydrogels were transferred to 1 mL 1x PBS and incubated for 6 h to

let the hydrogels swell. Swollen hydrogels were subsequently transferred to different

experimental set-ups and incubated for 2 h in 200 μL 1x PBS with 10 mM 2-ME and at room

temperature on an orbital shaker. Fluorescent measurements of the supernatant were carried

out at desired time points at 575/620 nm Ex/Em and the % dissolution was measured by dividing

the fluorescent intensity by the maximum mCherry fluorescent intensity upon complete gel

dissolution.

Functionalization of CNBr-activated Sepharose 4B beads

Ampicillin-beads were produced by coupling ampicillin to CNBr-activated Sepharose beads (GE

Healthcare). Coupling was performed according to manufacturer's instructions. Briefly, 1 g of the

lyophilized beads were washed for 30 min with ice cold 1 mM HCl to preserve the activity of the

reactive groups. The beads were then equilibrated with coupling buffer (0.1 M $NaHCO_3$, 0.5 M

NaCl, pH 8.3) and subsequently 1 ml ampicillin (4.57 mM diluted in water) was added to the

beads. The mixture was incubated overnight at 4 °C on a rotary shaker. The next day, excess

ampicillin was washed away with coupling buffer. To block any remaining active groups, the

beads were slowly agitated for 2 h in blocking buffer (0.1 M Tris-HCl, pH 8.0) followed by four

wash cycles with alternating pH buffers (0.1 M acetic acid/sodium acetate with 0.5 M NaCl, pH 4

and 0.1 M Tris-HCl with 0.5 M NaCl, pH 8.0). Finally, beads were washed with deionized water

(ddH_2O) and transferred to 10 mg mL^{-1} BSA dissolved in water and incubated overnight at 4 °C on

a rotary shaker. After coupling, the beads were lyophilized (Christ Alpha 1-4 LSCbasic, Germany)

and stored at 4 °C for further use.

Binding capacity and purification tag

For binding capacity tests, 500 µl of the settled ampicillin beads were incubated overnight at 4°C

with 4.5 mg of protein PBP3-CCS-mCherry (pHM151) or PenTag-CCS-mCherry (pHM525). On the

following day, the beads were washed four times with 1x PBS and the supernatant of the wash

fractions was kept for later measurements. To measure the binding capacity, 80 µl of the settled

beads bound to the protein were added to 200 µl 1x PBS containing 10 mM 2-ME and 20 µl of

Casp3 (0.5 mg ml^{-1}). After incubating for 1 h the relative fluorescence unit (RFU) of the

supernatant was measured at 575/620 nm Ex/Em using an Infinite M200 pro micro plate reader

(Tecan). The fluorescence was correlated to dilution series of each protein with concentrations

between 0 and 1.5 mg ml^{-1} and thereby the binding capacity was reported as mg protein per ml

settled beads.

386   Encoder system

Prior to assembling the encoder system, each OR-gate was established separately. OR gate 1 was

prepared by immobilizing PBP3-fused mCherry protein (pHM151) onto ampicillin-functionalized

crosslinked material as explained in "binding capacity" section. To characterize this system, a

dose-dependent mCherry release was monitored by the addition of different concentrations of

TEV (pRK793) and Casp3 (pKJ57) proteases, using 7 µl settled beads per reaction, all reactions in

200 µl 1x PBS supplemented with 10 mM 2-ME and Tween-20 and the respective protease

concentrations. For time kinetic measurements, a specific concentration for each protease was

chosen (1.25 µg ml^{-1} for Casp3 and 225 µg ml^{-1} for TVMV). For each time point, a 200 µl reaction

mixtures was prepared. Samples were taken in triplicates and measured at 575/625 nm Ex/Em

as explained above. For OR Gate 2, HaloTagged GFP (pHM150) was coupled onto HaloLink™ resin

(Promega) following the manufacturer's instructions. Briefly, 500 µl of settled beads were

equilibrated with binding buffer (100 mM Tris/HCl, 150 mM NaCl, 0.5% Triton, pH 7.6) and

incubated with 3.6 mg GFP protein on a rotary shaker overnight at 4 °C. On the following day,

beads were washed 4 times with binding buffer. Conduction of the dose-response and kinetic

measurements were similar to the first OR gate. For dose response measurements, the only

difference was that 5 µl of settled beads were used for each condition. For time kinetic

measurements, 0.625 µg ml^{-1} Casp3 and 3.125 µg ml^{-1} TEV were used. For the encoder system,

both proteins were coupled onto their respective material frameworks and the crosslinked

materials (5 µl GFP settled beads, and 7 µl mCherry settled beads) were mixed together in 2 ml

1x PBS, supplemented with 10 mM 2-ME and final concentrations of 6, 14, and 800 µg ml^{-1} for

Casp3, TEV, and TVMV were added respectively. The measured RFU for each gate was normalized

to the maximum RFU values after 55 min and values were reported as percentage of released

proteins. A time kinetic measurement was performed for the encoder system combination for 55

min every 5 min.

Code availability

413   The numerical integration, fitting process and identifiability analysis with the profile likelihood

414   method were performed in R using the freely available software package dMod. Used equations

415   and model details can be found in the Supplementary Information. Source data are provided with

416   this paper.

References

1. Macdonald, J. I., Munch, H. K., Moore, T. & Francis, M. B. One-step site-specific modification of native proteins with 2-pyridinecarboxyaldehydes. *Nat. Chem. Biol.* **11**, 326–331 (2015).

2. Griffin, B. A., Adams, S. R. & Tsien, R. Y. Specific covalent labeling of recombinant protein molecules inside live cells. *Science (80-.).* **281**, 269–272 (1998).

3. Shiraiwa, K., Cheng, R., Nonaka, H., Tamura, T. & Hamachi, I. Chemical Tools for Endogenous Protein Labeling and Profiling. *Cell Chem. Biol.* **27**, 970–985 (2020).

4. Backus, K. M. *et al.* Proteome-wide covalent ligand discovery in native biological systems. *Nature* **534**, 570–574 (2016).

5. Nomura, D. K., Dix, M. M. & Cravatt, B. F. Activity-based protein profiling for biochemical pathway discovery in cancer. *Nat. Rev. Cancer* **10**, 630–638 (2010).

6. Xue, L., Karpenko, I. A., Hiblot, J. & Johnsson, K. Imaging and manipulating proteins in live cells through covalent labeling. *Nat. Chem. Biol.* **11**, 917–923 (2015).

7. Gawade, P. M., Shadish, J. A., Badeau, B. A. & DeForest, C. A. Logic-Based Delivery of Site-Specifically Modified Proteins from Environmentally Responsive Hydrogel Biomaterials. *Adv. Mater.* **31**, 1–6 (2019).

8. Hoelzel, C. A. & Zhang, X. Visualizing and Manipulating Biological Processes by Using HaloTag and SNAP-Tag Technologies. *ChemBioChem* **21**, 1935–1946 (2020).

9. Ikeda, M. *et al.* Installing logic-gate responses to a variety of biological substances in supramolecular hydrogel-enzyme hybrids. *Nat. Chem.* **6**, 511–518 (2014).

10. Wagner, H. J. *et al.* Synthetic biology-inspired design of signal-amplifying materials systems. *Mater. Today* (2018).

11. Beyer, H. M. *et al.* Synthetic Biology Makes Polymer Materials Count. *Adv. Mater.* **30**, 1–7 (2018).

12. Wagner, H. J., Kemmer, S., Engesser, R., Timmer, J. & Weber, W. Biofunctionalized Materials Featuring Feedforward and Feedback Circuits Exemplified by the Detection of Botulinum Toxin A. *Adv. Sci.* **6**, (2019).

13. Wagner, H. J., Mohsenin, H. & Weber, W. Synthetic Biology-Empowered Hydrogels for Medical Diagnostics BT - Tunable Hydrogels: Smart Materials for Biomedical Applications. in (eds. Lavrentieva, A., Pepelanova, I. & Seliktar, D.) 197–226 (Springer International Publishing, 2021).

14. Theocharopoulos, C., Lialios, P. P., Samarkos, M., Gogas, H. & Ziogas, D. C. Antibody-drug conjugates: Functional principles and applications in oncology and beyond. *Vaccines* **9**, (2021).

15. Dugal-Tessier, J., Thirumalairajan, S. & Jain, N. Antibody-oligonucleotide conjugates: A
twist to antibody-drug conjugates. *J. Clin. Med.* **10**, 1–17 (2021).

16. Cao, W. *et al.* Antibody–siRNA conjugates (ARC): Emerging siRNA drug formulation. *Med.*
Drug Discov. **15**, 100128 (2022).

17. Fu, Z., Li, S., Han, S., Shi, C. & Zhang, Y. Antibody drug conjugate: the "biological missile"
for targeted cancer therapy. *Signal Transduct. Target. Ther.* **7**, (2022).

18. Lyon, R. P. *et al.* Self-hydrolyzing maleimides improve the stability and pharmacological
properties of antibody-drug conjugates. *Nat. Biotechnol.* **32**, 1059–1062 (2014).

19. Masri, M. S. & Friedman, M. Protein reactions with methyl and ethyl vinyl sulfones. *J.*
Protein Chem. **7**, 49–54 (1988).

20. Nair, D. P. *et al.* The Thiol-Michael addition click reaction: A powerful and widely used tool
in materials chemistry. *Chem. Mater.* **26**, 724–744 (2014).

21. Chen, I., Howarth, M., Lin, W. & Ting, A. Y. Site-specific labeling of cell surface proteins
with biophysical probes using biotin ligase. *Nat. Methods* **2**, 99–104 (2005).

22. Voloshchuk, N., Liang, D. & Liang, J. Sortase A Mediated Protein Modifications and Peptide
Conjugations. *Curr. Drug Discov. Technol.* **12**, 205–213 (2016).

23. Keppler, A. *et al.* A general method for the covalent labeling of fusion proteins with small
molecules in vivo. *Nat. Biotechnol.* **21**, 86–89 (2003).

24. Los, G. V *et al.* HaloTag: A Novel Protein Labeling Technology for Cell Imaging and Protein
Analysis. *ACS Chem. Biol.* **3**, 373–382 (2008).

25. Gautier, A. *et al.* An Engineered Protein Tag for Multiprotein Labeling in Living Cells. *Chem.*
Biol. **15**, 128–136 (2008).

26. Liss, V., Barlag, B., Nietschke, M. & Hensel, M. Self-labelling enzymes as universal tags for
fluorescence microscopy, super-resolution microscopy and electron microscopy. *Sci. Rep.*
5, 1–13 (2015).

27. Wilhelm, J. *et al.* Kinetic and Structural Characterization of the Self-Labeling Protein Tags
HaloTag7, SNAP-tag, and CLIP-tag. *Biochemistry* **60**, 2560–2575 (2021).

28. Scifinder. *'Chemical CAS no. search results', Accessed April 12, 2023.* Available at:
https://scifinder-n.cas.org/.

29. Waugh, D. S. Making the most of affinity tags. *Trends Biotechnol.* **23**, 316–320 (2005).

30. Hamed, R. B. *et al.* The enzymes of β-lactam biosynthesis. *Nat. Prod. Rep.* **30**, 21–107
(2013).

31. Shalaby, M. A. W., Dokla, E. M. E., Serya, R. A. T. & Abouzid, K. A. M. Penicillin binding
protein 2a: An overview and a medicinal chemistry perspective. *Eur. J. Med. Chem.* **199**,
112312 (2020).

32.   Proteins, P. Kinetics of b -Lactamases and Penicillin-Binding Proteins 12. 195–214 (2020).

33.   Bruch, R. *et al.* Clinical on-site monitoring of ß-lactam antibiotics for a personalized
489   antibiotherapy. *Sci. Rep.* **7**, 1–10 (2017).

490   34.   Ates, H. C. *et al.* Biosensor-Enabled Multiplexed On-Site Therapeutic Drug Monitoring of
491   Antibiotics. *Adv. Mater.* **34**, (2022).

492   35.   Glatz, R. T., Ates, H. C., Mohsenin, H., Weber, W. & Dincer, C. Designing electrochemical
493   microfluidic multiplexed biosensors for on-site applications. *Anal. Bioanal. Chem.* (2022).

494   36.   Johnston, M. *et al.* Multiplexed biosensor for point-of-care COVID-19 monitoring: CRISPR-
495   powered unamplified RNA diagnostics and protein-based therapeutic drug management.
496   *Mater. Today* **61**, 129–138 (2022).

497   37.   Zhang, J., Wang, Z., Wen, K., Liang, X. & Shen, J. Penicillin-binding protein 3 of
498   Streptococcus pneumoniae and its application in screening of β-lactams in milk. *Anal.
499   Biochem.* **442**, 158–165 (2013).

500   38.   Morlot, C. *et al.* Crystal structure of a peptidoglycan synthesis regulatory factor (PBP3)
501   from Streptococcus pneumoniae. *J. Biol. Chem.* **280**, 15984–15991 (2005).

502   39.   Chayen, N. E. Turning protein crystallisation from an art into a science. *Curr. Opin. Struct.
503   Biol.* **14**, 577–583 (2004).

504   40.   Ki, M. R. & Pack, S. P. Fusion tags to enhance heterologous protein expression. *Appl.
505   Microbiol. Biotechnol.* **104**, 2411–2425 (2020).

506   41.   Gübeli, R. J. *et al.* Remote-Controlled Hydrogel Depots for Time-Scheduled Vaccination.
507   5355–5362 (2013).

508   42.   Li, J. & Mooney, D. J. Designing hydrogels for controlled drug delivery. *Nat. Rev. Mater.* **1**,
509   16071 (2016).

510   43.   Badeau, B. A. & Deforest, C. A. Programming Stimuli-Responsive Behavior into
511   Biomaterials. *Annu. Rev. Biomed. Eng.* **21**, 241–265 (2019).

512   44.   Chan, L. *et al.* Covalent attachment of proteins to solid supports and surfaces via sortase-
513   mediated ligation. *PLoS One* **2**, 1–5 (2007).

514   45.   Wilchek, M., Oka, T. & Topper, Y. J. Structure of a soluble super active insulin is revealed
515   by the nature of the complex between cyanogen bromide activated Sepharose and amines
516   (N substituted isoureas/N1 N2 disubstituted guanidines/insulin Sepharose/insulin
517   insensitivity/super active peptid. *Proc. Natl. Acad. Sci. U. S. A.* **72**, 1055–1058 (1975).

518   46.   Wagner, H. J. *et al.* Synthetic biology-inspired design of signal-amplifying materials
519   systems. *Mater. Today* **22**, 25–34 (2019).

47.   He, K. *et al.* Transformers in medical image analysis. *Intell. Med.* **3**, 59–78 (2023).

48.   Kang, D. *et al.* DNA biomolecular-electronic encoder and decoder devices constructed by

multiplex biosensors. *NPG Asia Mater.* **4**, 1–6 (2012).

49.   Sigen, A. *et al.* Hyperbranched PEG-based multi-NHS polymer and bioconjugation with
BSA. *Polym. Chem.* **8**, 1283–1287 (2017).

50.   Thalla, P. K. *et al.* Chondroitin sulfate coatings display low platelet but high endothelial cell
adhesive properties favorable for vascular implants. *Biomacromolecules* **15**, 2512–2520
(2014).

51.   Jonkheijm, P., Weinrich, D., Schröder, H., Niemeyer, C. M. & Waldmann, H. Chemical
strategies for generating protein biochips. *Angew. Chemie - Int. Ed.* **47**, 9618–9647 (2008).

52.   Kwon, J. *et al.* Bright ligand-activatable fluorescent protein for high-quality multicolor live-
cell super-resolution microscopy. *Nat. Commun.* **11**, 1–11 (2020).

53.   Liang, Q., Huang, Z., Zhang, Y. & Li, H. Immobilization of Ulp1 protease on NHS-activated
Sepharose: a useful tool for cleavage of the SUMO tag of recombinant proteins. *Biotechnol.*
Lett. **39**, 1025–1031 (2017).

54.   Costa, S., Almeida, A., Castro, A. & Domingues, L. Fusion tags for protein solubility,
purification, and immunogenicity in Escherichia coli: The novel Fh8 system. *Front.*
Microbiol. **5**, 1–20 (2014).

55.   Tanaka, T., Yamamoto, T., Tsukiji, S. & Nagamune, T. Site-specific protein modification on
living cells catalyzed by sortase. *ChemBioChem* **9**, 802–807 (2008).

56.   Fernández-Suárez, M. *et al.* Redirecting lipoic acid ligase for cell surface protein labeling
with small-molecule probes. *Nat. Biotechnol.* **25**, 1483–1487 (2007).

57.   Schumacher, D. *et al.* Versatile and Efficient Site-Specific Protein Functionalization by
Tubulin Tyrosine Ligase. *Angew. Chemie - Int. Ed.* **54**, 13787–13791 (2015).

58.   Zucca, P., Fernandez-Lafuente, R. & Sanjust, E. Agarose and its derivatives as supports for
enzyme immobilization. *Molecules* **21**, 1–25 (2016).

59.   Hwang, J. M. D., Piccinini, T. E., Lammel, C. J., Hadley, W. K. & Brooks, G. F. Effect of storage
temperature and pH on the stability of antimicrobial agents in MIC trays. *J. Clin. Microbiol.*
23, 959–961 (1986).

60.   Gao, X. J., Chong, L. S., Kim, M. S. & Elowitz, M. B. Programmable protein circuits in living
cells. *Science (80-.).* **361**, 1252–1258 (2018).

61.   Fink, T. *et al.* Design of fast proteolysis-based signaling and logic circuits in mammalian
cells. *Nat. Chem. Biol.* **15**, 115–122 (2019).

62.   Gibson, D. G. *et al.* Enzymatic assembly of DNA molecules up to several hundred kilobases.
Nat. Methods **6**, 343–345 (2009).

63.   Jumper, J. *et al.* Highly accurate protein structure prediction with AlphaFold. *Nature* **596**,
583–589 (2021).

64.   Schrödinger, L. The PyMOL Molecular Graphics System. (2010).

 Fig. 1| Engineering a new truncated version of PBP3. a, Structure of full-length PBP3 (with

membrane anchor, left) and upon truncation (right). The membrane anchor is shown in dark cyan

and the rest of the protein shown in light cyan. In red, the active site of the protein consisting of

motif 1, 2, 3 and Ω-like loop is shown. Protein structure prediction is done by AlphaFold 2[63] and

figures are generated by PyMOL[64]. **b**, Mechanism of conjugation of ß-lactam antibiotics to PenTag

and an overview of applications that could benefit from this conjugation technique. **c,**

Fluorescence polarization measurements to compare the PBP3/bocillin-FL bond with PBP3-

t/bocillin-FL bond at RT. **d**, Fluorescence polarization of PBP3-t/bocillin-FL complex over several

days at 4 °C in PBS. Fluorescence polarization measurements consist of 3 separate replicates,

each measured twice and are shown as mean and indicating replicates.

Fig. 2| Synthesis of a stimuli-responsive hydrogel and its dissolution kinetics. a, Picture of
synthesized hydrogels on a coated glass-slide and schematic of the building blocks involved in

572   crosslinking. **b**, Time-resolved dissolution of hydrogels upon addition of different Casp3 amounts.

573   Data represent 3-5 separate replicates for each condition, dotted lines connect the means of

574   each condition.

Fig. 3| **Conjugation PenTagged proteins onto agarose beads. a**, Functionalization of CNBr-activated agarose beads with ampicillin. **b**, Schematic representation of coupled PBP3-/or PBP3-t- fused mCherry on beads and mCherry release by adding Casp3 protease. **c**, mCherry release from ampicillin beads, captured by PenTag (either PBP3, or PBP3-t) at three different steps after functionalizing beads: right after functionalization, after lyophilization, and 18 days post-lyophilization. Binding capacity is reported as mg released protein per ml of settled beads. Bar charts represent the mean of 3 separate replicates.

 Figure 4| Development of two orthogonal material-based OR gates and their combination in a

4:2 encoder set-up. a, Schematic of a 4:2 encoder (left) and 4 different input/output

combinations of such a 4:2 encoder (right). **b**, Combination of two different OR gates sharing one

same input towards a 4:2 encoder. **c**, Schematic of mCherry OR gate. Output mCherry is supposed

to be released in presence of either Casp3, or TVMV protease, or both. Molecular design of

mCherry module consists of mCherry fused to PenTag by a linker containing cleavage sites for

Casp3 and TVMV. Protein is bound through PenTag on ampicillin functionalized crosslinked

agarose. **d**, Schematic of GFP OR gate. Output GFP is supposed to be released in presence of

either Casp3, or TEV protease, or both. Molecular design of GFP module, consisting of GFP fused

to HaloTag by a linker containing cleavage sites for TEV and Casp3. Output GFP is released in

presence of each of proteases. Protein is bound through HaloTag on HaloLink material. **e**, Data

and model fits of the dose-dependent release of mCherry from ampicillin material module upon

addition of different concentrations of TVMV and Casp3. **f**, Data and model fits of the dose-

dependent release of the GFP from HaloLink material module upon addition of different

concentrations of Casp3 and TEV. **g**, Data and model fits of the time-resolved measurements of

mCherry module upon addition of Casp3 or TVMV over time. **h**, Data and model fits of the time-

resolved measurements of GFP module upon addition of TEV or Casp3 over time. **i**, Combination

of both systems towards a 4:2 encoder system predicted by the mathematical model (left) and

validated by experiments (right). Triplicates were measured for the samples, and duplicates for

negative controls.