Technique for rapidly forming networks of microvessel-like structures

Sarah A. Hewes[a,*], Fariha N. Ahmad[a,*], Jennifer P. Connell[a] and K. Jane Grande-Allen[a,b]

a. Department of Bioengineering, Rice University, Houston, TX
b. Corresponding author
* Contributed equally to this work

Author Contact Information

Sarah A. Hewes
Department of Bioengineering, Rice University
PO Box 1892 - MS 142
Houston, TX 77251-1892
Telephone: 206-218-4485
Email: sh62@rice.edu

Fariha N. Ahmad
Department of Bioengineering, Rice University
PO Box 1892 - MS 142
Houston, TX 77251-1892
Telephone: 956-330-0502
Email: fna2@rice.edu

Jennifer P. Connell
Department of Bioengineering, Rice University
PO Box 1892 - MS 142
Houston, TX 77251-1892
Telephone: 713-348-3615
Email: jp10@rice.edu

K. Jane Grande-Allen (Corresponding author)
Department of Bioengineering, Rice University
PO Box 1892 - MS 142
Houston, TX 77251-1892
Telephone: 713-348-3704
Email: grande@rice.edu

Abstract

Modelling organ-blood barriers through the inclusion of microvessel networks within *in vitro* tissue models could lead to more physiologically accurate results, especially since organ-blood barriers are crucial to the normal function, drug transport, and disease states of vascularized organs. Microvessel networks are difficult to form, since they push the practical limit of most fabrication methods, and it is difficult to coax vascular cells to self-assemble into structures larger than capillaries. Here we present a method for rapidly forming networks of microvessel-like structures using sacrificial, alginate structures. Specifically, we encapsulated endothelial cells within short alginate threads, then embedded them in collagen gel. Following enzymatic degradation of the alginate, the collagen gel contained a network of hollow channels seeded with cells, all surrounding a perfusable central channel. This method uses a 3D printed coaxial extruder and syringe pumps to generate short threads in a way that is repeatable and easily transferrable to other labs. The cell-laden, sacrificial alginate threads can be frozen after fabrication and thawed before embedding without significant loss of cell viability. The ability to freeze the threads enables future scale up and ease of use. Within microfluidic devices that restrict access to media, the threads enhance cell survival under static conditions. These results indicate the potential for use of this method in a range of tissue engineering applications.

Impact Statement (100 words or less)

Generating microvascular networks is a challenge in tissue engineering. Popular 3D bioprinting techniques use sacrificial structures to generate vascular networks, but those approaches can require expensive equipment and extensive troubleshooting. In this article, a method is presented for easy and rapid generation of centimeter-scale microvascular networks using endothelial cells frozen within sacrificial structures. The method for fabricating and freezing the sacrificial threads of alginate containing cells using a 3D printed coaxial extruder is also described. Experimental results indicate that these microstructures have the potential to enhance cell survival in environments with restricted access to media.

Introduction

Blood vessel networks are hierarchical; larger blood vessels branch into microvessels that branch into capillaries. Numerous *in vitro* and *in vivo* studies have shown that endothelial cells will self-assemble to form a capillary network within a scaffold material, such as collagen, even over centimeter scales.[1] These self-assembled capillaries form with diameters of around 5-30 μm.[2] Large vessels can be created by mechanical means, such as molding or 3D printing.[3,4] However, in extrusion bioprinting, the diameter of the nozzle used to print live cells is typically limited to a minimum size around 100 μm[5] due to mechanical forces that negatively impact cell viability at smaller diameters.[6] Microvessel networks containing blood vessels larger than capillaries are the most difficult to form since they push the practical limit of most fabrication methods and since it can be challenging to coax cells into self-assembling vascular networks at this scale.

One approach to establish 3D vasculature *in vitro* is to fabricate hollow spaces in a hydrogel where blood vessels are desired. As a general observation, endothelial cells cultured *in vitro* tend to spread to cover available space before branching out through a solid matrix. Many investigators take advantage of this behavior by seeding endothelial cells within pre-formed vascular structures.[7–9] Sacrificial materials are typically employed to create these spaces by excluding the bulk material while it solidifies and subsequently dissolving the sacrificial material by chemical, thermal, or enzymatic means. To seed cells within a structure prepared with sacrificial material, the channels must be able to be perfused. In a complex structure with disconnected forms, direct infusion of cells becomes impractical, so the cells are sometimes encapsulated within the sacrificial structures.

Alginate is a common choice for a sacrificial material because the conditions for its gelation and degradation are compatible with live human cells. Endothelial cells encapsulated within or grown on the outside of alginate beads or fibers have been used to generate vasculature *in vitro* in combination with gelatin, fibrin, or collagen.[10–14] Though cells cannot degrade alginate and thus cannot proliferate within alginate structures, alginate is a highly biocompatible material that is widely used in tissue engineering.[15] Despite its limited utility for cell scaffolding, alginate is an excellent material for temporary cell encapsulation, due to its reversible gelation properties. Although a calcium chelator such as sodium citrate is a popular method for reversing alginate gelation, enzymatic degradation using alginase is an alternative approach to assure that the alginate structure does not re-form when calcium-containing media is introduced to the system.

The goal of this work was to create a platform for studying vascularized tissues *in vitro*. Here, we describe a method for rapidly forming microvessel networks from cellularized, sacrificial structures that can be premade, stored, and used from frozen aliquots.

Materials and Methods

Fabrication of coaxial extruder

Figure 1. Coaxial extruder and alginate threads. A) Schematic of coaxial extruder for making alginate threads. The CaCl2 port nearest to the Luer-lock connector of the needle created the fluid sheath that formed the threads. The further CaCl2 port created the crossflow to shear the threads off at regular lengths. B) Macroscopic image of alginate threads. Bar = 1 cm.

A coaxial extruder was designed to produce alginate structures of a desired diameter and length (**Figure 1A**). The simple extruder consisted of a needle positioned lengthwise through the center of a larger tube. A mixture of cells and alginate was flowed through the needle while calcium chloride was flowed through the larger outer tube, creating a sheath of $CaCl_2$ around an alginate core. The alginate core was quickly crosslinked by the calcium ions to form a thread-like, alginate structure encapsulating cells. The minimum goal for the extruder design was to be able to produce at least 1 mL of threads in under 30 min, while using at most 120 mL of $CaCl_2$. To prevent shear-induced cell death, the needle diameter had to be greater than 100 µm (32 gauge). To achieve alginate threads with diameters smaller than the needle diameter of 432 µm (23 gauge), the flow rate within the $CaCl_2$ sheath needed to be substantially higher than the flow rate in the alginate core.

Once prototypes of the simple coaxial extruder could produce continuous alginate threads of consistent diameter, the crossflow portion of the extruder was added. The crossflow periodically dragged the threads downstream away from the needle abruptly, thereby shearing them into threads of consistent length (**Figure 1B**). The tip of the needle was positioned 2 mm from the center of the crossflow and the crossflow channel had a 1 mm radius. Extruders with crossflow center to needle tip distances of 0 – 6 mm were tested. The length of the alginate threads appears to scale with the distance from the extruder, except that very small diameter threads were produced when the tip of the needle was at the edge of the crossflow. The distance between the tip of the needle and the crossflow portion was found empirically, with the goal of producing threads around 4 mm long that would be less likely to tangle and bind together, but long enough to produce vessels resembling a physiological network.

The extruder was also designed to be easily reproducible. The extruder sheath was printed with a Form 2 SLA printer with Dental SG resin (Formlabs, Boston, MA), thoroughly washed with isopropyl alcohol, cured, and attached to a 23 gauge ½" length blunt tip needle (McMaster-Carr, Elmhurst, IL) using Loctite GO2 glue. The use of a commercial SLA printer, together with the alignment features on the extruder sheath, allowed for consistent reproduction of these core-sheath extruders.

Fabrication of alginate threads

Alginate threads were fabricated using the 3D printed coaxial extruder. After assembling the extruder and allowing the glue to cure for 24 hours, the extruder assembly and all tubing was autoclaved. To encapsulate HUVECs within alginate threads and facilitate the formation of threads significantly smaller than the needle diameter, the alginate flow rate was set at 30 mL/hr and the $CaCl_2$ flow rate was set at 40 mL/min at each inlet port. Since the sheath flow rate was significantly higher than the core flow rate, two syringe pumps were used. One syringe pump dispensed the alginate and cell mixture to the needle with a 5 mL syringe, and the other dispensed $CaCl_2$ from two 60 mL syringes that were connected to the two extruder ports (**Figure 1A**). A 2% solution of alginate buffered with 15 mM HEPES containing green fluorescent protein-expressing human umbilical vein endothelial cells (GFP-HUVECS) (3 million cells/mL) was flowed through the needle. A solution of 80 mM $CaCl_2$ in 15 mM HEPES, adjusted to pH ~7, was flowed through the other two ports. Consistent volumes of cell-laden alginate threads were collected in conical tubes. After allowing the threads to settle, the calcium chloride was aspirated off. The threads were then collected in cryovials and resuspended in 10% DMSO, 90% FBS. The threads were frozen for 24 hours at -80°C and then stored in liquid nitrogen for up to 7 months.

Figure 2. Schematics of oval flow device and flow loop. A) Flow loop assembly labeled with arrows indicating flow direction. B) Close up of millifluidic device (grid is 0.5 inch squares). C) Flow loop hooked into peristaltic pump. D) 3D printed mold for millifluidic device taken at red dashed line at in panel. Light blue indicates glass. E. G) cross section of the center of the microfluidic device in E perpendicular to the dashed red line.

Design of vascular network culture device

The flow device that would support the collagen-embedded vascular network was created with several considerations in mind. To ensure that device would sustain a perfusable network for the intended durations of cell culture it was designed to include a media reservoir and to have the capacity for recirculating flow at the desired flow rates (**Figure 2A-C**). The surface area of the device was approximately 1.28 cm^2 (four times the area of one well of a 96-well plate) to accommodate a volume of cells that would enable the collection of abundant mRNA and proteins for biomarker detection assays. A central channel was created by molding the collagen around a needle, inserted along the long axis of the device. The size of the central channel was designed to be 500 μm, which was considered sufficiently large to avoid clogging with bubbles or cell clumps, yet small enough to avoid collapse when fabricated from 5 mg/mL rat tail collagen. The height of the collagen gel was limited to 2 mm due to imaging constraints.

To fabricate the device, 3D printed negative molds were printed in polylactic acid (PLA) and attached to glass with Loctite GO2 glue (**Figure 2D**). After allowing the glue to set for 24 hours, polydimethylsiloxane (PDMS) was mixed in a 1:10 ratio of crosslinker to prepolymer, bubbles were removed using a vacuum chamber, and the PDMS was poured into the molds with a 508 μm diameter wire (McMaster-Carr) inserted (**Figure 2D)** to create a channel for the needle to be inserted in a later step. After removing any remaining bubbles, the molds were covered with a plastic sheet to create a flat top surface. The PDMS was cured at room temperature for 48 hours. After removing the PDMS from the negative molds, the PDMS was baked for 1 hour at 90°C. A 1.5 mm biopsy punch was used to create ports on either side of the chamber, connected to the central channel. The PDMS device was then plasma bonded to cover glass using a laboratory corona treater (Electro-Technic Products, Chicago, IL). A thinner cover glass was used to facilitate imaging. Small slabs of PDMS, used for sealing the device chamber, were cut from cured PDMS in 4 mm thick rectangular slabs approximately 15 mm by 30 mm. The devices were autoclaved before use.

Culturing of HUVECS

GFP-HUVECs were cultured in EGM-2 media on uncoated tissue culture flasks. Media was changed every second day. After a total of three days of culture in an incubator (37°C, 5% CO_2) or upon reaching 80% confluence, the cells were passaged with a 1:6 split. GFP-HUVECs were not allowed to become confluent. For passaging, cells were detached from the flask using 0.05% trypsin, which was then neutralized with EGM-2. The cells were used in experiments at passage seven.

Viability studies

The ability to retrieve cell-containing sacrificial structures from frozen aliquots greatly simplifies experiments. To verify that the cells were not compromised by this process, cell viability was assessed using Calcein-AM and Ethidium Homodimer-1 (Eth-D). Cells that had been frozen in liquid nitrogen for a minimum of 24 hours were thawed quickly in a 37°C bead bath. Eth-D and Calcein-AM were added in concentrations of 2 μl/mL and 1 μl/mL, respectively, and incubated with the cells for 10 minutes before imaging on a fluorescence microscope . Cells were counted using CellProfiler (Broad Institute, Boston, MA).[16] Cell viability was evaluated for cells after passaging, cells that had been thawed after

freezing, cells that had been encapsulated, and encapsulated cells that had been thawed after freezing. The results were collected over three separate encapsulation experiments.

Figure 3. Schematic of sacrificial alginate threads process. A) Millifluidic device with single channel molded in collagen. B) Embedded alginate threads containing endothelial cells with empty channel in collagen containing alginase. C) Alginate has dissolved, releasing the cells into the newly-formed channels. D) Cells have spread out and covered the channels and holes left by the dissolved alginate. E) Capillaries have sprouted and connected to the main channel.

Embedding in collagen

To evaluate whether the encapsulated structures would promote the formation of a microvascular network, cells were seeded under two conditions (Figure 3A). GFP-HUVECs were randomly seeded within a collagen gel, or a similar number of GFP-HUVECs that had been encapsulated within sacrificial alginate threads were mixed within the collagen gel as described below.

GFP-HUVECs were encapsulated within alginate threads of approximately 330 ± 100 μm diameter and 4 ± 0.6 mm length, using the custom-designed, 3D printed coaxial extruder. To begin embedding the alginate threads in collagen (**Figure 3**), a frozen aliquot of threads was quickly thawed in a 37°C bead bath.

After aspirating the freezing media, the threads were transferred into the device chamber that had a 25 gauge 2" length blunt tip needle (McMaster-Carr) inserted to form a central channel (**Figure 2E-G**). A solution of high concentration rat tail collagen was diluted to 5 mg/mL on ice and neutralized with 1 N NaOH, added 1 μL dropwise until neutral pH was demonstrated by the solution's peach color. Alginate lyase was added to the neutralized collagen to a final concentration of 0.05 UN/mL, including the volume of the alginate threads. The neutralized collagen/alginase solution was added to the device chamber over the alginate threads, suspending them in the collagen (**Figure 3**). The final gel volume in the devices was approximately 250 μL, with uncertainty coming from the exact volume of the alginate threads.

To prepare control collagen gels containing randomly seeded cells, a solution of 1.5 million cells/mL was suspended in the neutralized collagen/alginase solution and then added to the device chamber.

In both conditions, the filled devices were placed on ice for 15 min to promote the formation of more optically transparent collagen gels that would be favorable for imaging. The devices containing gels were then incubated at 37°C for 30 min to fully solidify the collagen. In the condition of the microfluidic devices, before removing the needle, 200 μL warm media was added to the top chamber, a slab of PDMS was glued to cover the top, and the needle was back filled with media. When the needle was removed in this manner, the central channel remained intact. The needle hole in the PDMS on the side of the device was sealed with Loctite GO2 glue. In the condition of the well plate control, the samples were seeded and gelled as described above, but within a 24-well plate instead of a microfluidic device. In the well plate control, 2 mL of media was added on top of the gels after they were fully set. The results in **Figure 5B** are from 2-3 samples under each condition.

Sterile flow loop setup

To create the reservoir for the flow loop, a 3 mm hole was drilled into a 15 mL conical tube using a Dremel tool. Next, a 28 cm tube and a 22 cm microbore Tygon tube with 0.020" inner diameter and 0.060"outer diameter (Cole-Parmer) were inserted into the cap with the ends offset 6 cm within the tube, and the tubes were secured with Loctite GO2 glue. The ends were offset to ensure that bubbles from the outlet were not recaptured at the inlet. After curing for 24 hours, the flow loop was assembled as shown in **Figure 2A**. To form the part of the flow loop that attaches to the device, a 14 gauge ½" blunt tip needle (McMaster-Carr) was inserted into the long Tygon tube attached to the reservoir and another into a loose 22 cm Tygon tube. To create the part of the flow loop that attaches to the pump, the luer-lock ends of the needles were connected to a 11 cm long piece of 1/16" ID silicone tubing (Cole-Parmer) using 2x luer-lock female to barb connectors (McMaster-Carr). The assembled loops were autoclaved before use.

Application of flow

To connect the vascular network device to a flow system, a sterile flow loop was filled with warm media, then primed using a peristatic pump to bring the meniscus to the end of the loop closest to the reservoir, ensuring that perfusion into the device would begin upon pump activation (**Figure 2A**). The media formed a drop at the end of the tube that allowed it to be connected without introducing bubbles to the device. Bubbles elsewhere in the loop would be trapped by the reservoir. This end was pressure fit to the device and then glued. The other end was attached to the device in a similar way and then the pump was run to remove bubbles from the loop. The loop could be disassembled at the barb connectors to add holders for the peristaltic pump if desired. Flow was introduced to the devices at a rate of 710 µL/min. The media in the device reservoirs was exchanged with pre-warmed fresh media after 2 days, consistent with standard HUVEC culture. Flow was not introduced to the well plate controls.

Imaging

Using a Nikon A1-Rsi confocal with a 10x objective, images were taken of 1.3 mm by 3.4 mm sections of the devices centered on the central channel approximately in the middle of the device, 2 cm from the outlet end. The closed loops were removed from the incubator for about 30 min at a time for this imaging, and then immediately returned to their static or flow conditions. This schedule allowed the imaging of the live cells in these devices and in well plates at 0, 1, 2, and 3 days post seeding. Large images (**Figure 5E-F**) were obtained using a Nikon Eclipse Ti2 with a 4x objective. Exposure time and laser power were kept consistent for all images in an experiment to simplify automated image analysis.

Image analysis

Total cell volume was quantified using MATLAB. A subset of images was used to manually set the fluorescence threshold for all images across experiments and timepoints. Cell count for the cell viability assays was performed using a CellProfiler pipeline and was validated with a manual count of cells that intersected a grid overlay.

Statistical analysis

Quantitative data are shown as mean ± standard deviation. Statistical analysis was performed using GraphPad Prism 9.1.2 (San Diego, CA). Comparison between the viability data shown in **Figure 4A** was carried out using a two-way analysis of variance (ANOVA). Multiple unpaired t-tests were performed on the data in **Figure 5B**. Differences with a p-value of <0.05 met the threshold for significance.

Experiment

Figure 4. Viability of cells within alginate threads. A) Viability of HUVECs when passed, in threads immediately after extrusion, and after freezing then thawing. B) 10x image of HUVECs in alginate threads in phase. C) Calcein-AM live stain of HUVECS within alginate threads. D) Eth-D dead stain of HUVECS.

Cell viability test

The alginate threads containing cells could be frozen and thawed with minimal impact on cell viability, comparable to unencapsulated cells (**Figure 4A**). This was confirmed by two-way ANVOA of the variation between the freezing condition and encapsulation state. While freezing did significantly impact viability (p = 0.03), encapsulation did not (p = 0.54). The viability of encapsulated cells that had been frozen then thawed (76±10%) was not significantly different from the viability of unencapsulated cells that had been frozen then thawed (81±17%). The viability of the encapsulated cells and unencapsulated cells before freezing were 92±3% and 94±4%, respectively.

Figure 5. GFP-HUVECs encapsulated in collagen. A) Z-stack maximum intensity projections of GFP-HUVECs under conditions (top label), on day 0 or day 3 (left label) B) GFP-HUVEC volume over time in the conditions listed in A. C) GFP-HUVECs seeded within threads after three days of culture magnified from lower right image in panel A. D) Z-stack cross section from C showing vessel lumen (diameter ~30 µm). E) Phase image of microfluidic device culture chamber containing GFP-HUVECs seeded within threads and cultured for 3 days under static conditions. F) Corresponding GFP-HUVEC fluorescence from E.

Cell proliferation as a function of seeding

After three days of culture within collagen gels, the cells within the well plates proliferated in both the random and alginate thread seeding conditions, nearly doubling in total cell volume (**Figure 5**) and were not significantly different between these two conditions (p = 0.94). Within the microfluidic devices under static conditions, the alginate thread seeding condition generated large amounts of cell growth, similar to the threads in the plate condition. Seeding with threads in the static condition yielded significantly increased cell proliferation compared to the randomly seeded samples under static conditions (p <0.05) (**Figure 5B**). In areas of high local cell density, new structures appeared to bridge between the channels formed by the threads (**Figure 5C**). Based on confocal imaging, these bridging structures appear to be capillaries of ~ 30 µm diameter with a hollow lumen (**Figure 5C-D**). The functionality of these possible vessels could not be visualized with dye due to the blind ended nature of the structures, so verification of that

these structures are hollow has not been confirmed. The device has an area of 1.28 cm^2, with these capillary-like structures spanning the entire area (**Figure 5F**). These results indicate that alginate threads are useful for creating centimeter-scale networks of microvessel-like structures. In addition, the rapid formation of lumenized capillaries bridging the hollow alginate structures demonstrates that hierarchical network formation can be prompted by this patterning method.

Cell proliferation test as a function flow

Under flow conditions, the cells in the alginate threads cultured in the device initially began to elongate and connect with neighboring cells, but by the third day, the fluorescent cell population decreased sharply (**Figure 5A-B**). Randomly seeded cells cultured within devices were nearly completely dead by their second day under flow conditions (**Figure 5A**). While there was a statistically significant difference between these two groups (p = 0.01), it is negligible because of the extensive cell death observed when the thread and random seeding conditions were subjected to flow. It is notable that the cells exposed to flow began to die off around the channel in the randomly seeded conditions, though the extent or large-scale geometry of this local die-off was not captured by the image size. This flow-related cell death might be prevented by lowering the volume of media in the flow loop, changing the flow rate, or introducing flow at a later time point after the cells have fully recovered from being frozen.

Discussion

Cells behave differently in 2D compared to 3D; therefore, it is important to develop vascularized 3D models of tissues. While other groups have used sacrificial structures to create single vessels[17] or structures with beads[11] or fibers[7], the technique we present here results in a hierarchical microvascular structure and is easy to implement without expensive fabrication equipment. Other groups have also used coaxial flow to generate tubular cellular structures.[12,18] However, our 3D printable coaxial extruder is easily transferrable to other labs and could be readily altered to create sacrificial structures of other dimensions.

In this report, we have described a compact, disposable flow loop including a built-in bubble trap and a reservoir for easy media changes. The inclusion of cell-laden alginate threads into the collagen gels under static conditions generated hierarchical microvascular networks, as would be necessary to support large, complex, 3D tissue models. The sacrificial threads can be frozen and thawed for use, making this system convenient and easy to implement in co-culture experiments. These results were in line with other encapsulation systems for cryopreservation.[19] We showed that the viability of encapsulated cells were not significantly affected by the encapsulation process or freezing, compared with unencapsulated cells.

The cell seeding experiments within collagen gels demonstrated the utility of this method in generating microvascular networks. The collagen concentration and cell density have been optimized for capillary formation in previous work.[1] We observed a lower degree of vascular morphogenesis than reported in the literature, however this can be explained by the shorter culture period and the recently unfrozen status of the cells. The conditions within the well plate were sufficient to allow cell survival, whereas the device was only able to support the cells seeded within the sacrificial threads. The cells likely survived in this condition because the increased porosity of the collagen gel (~30%) due to the voids formed

by the sacrificial threads was sufficient to allow the diffusion of nutrients. Under flow, there was a sharp decrease in cell viability, possibly due to the washout of homeostatic factors or low-flow mediated apoptosis. Starting flow after the cells have completely recovered from freezing and grown to confluence, perhaps one week after seeding, may prevent this problem. All these results indicate that this technique for forming microvessels has utility in bioengineering for generating microvessel networks.

The networks resulting from this technique more closely resemble *in vitro* microvascular networks than the cellular structures created by a seemingly comparable technique that uses cell-covered gelatin beads,[11] owing to the formation of distinct lumens instead of monolayers forming around voids between spheres and the potential to be able to adjust the diameter of the sacrificial structures. Similarly, the application of this technique also results in the approximate doubling of cells soon after seeding. Another notable work used a single sacrificial alginate vessel to create a channel within a microfluidic device.[17] The technique presented here expands upon that concept to create a technique that is more suited toward generating large scale microvascular networks in a flexible format that can be used from frozen aliquots.

Although these results are compelling, they must be considered in the appropriate context. It can be challenging to pipette the threads with standard pipette tips. This limitation influenced the open top design of the oval microfluidic device. The diameter of the threads varied along their length, though the threads consistent to each other in overall shape. Though this may not be a drawback when trying to randomly form any network, it would make it difficult to isolate the effects of vessel diameter on the network formation. Lastly, since the threads are randomly oriented within the collagen gel, there is significant variability of the orientation and density of structures within the sample.

In conclusion, here we present a method for generating sacrificial, alginate structures and embedding them within collagen to speed the formation of microvessel networks. The alginate threads were created using a 3D printed coaxial extruder and syringe pump; a simple method that is easily transferrable to other labs and flexible for others to tailor to their needs. The encapsulated cells retained viability within the alginate threads after encapsulation and after freezing. The flow loop and microfluidic device create a solid platform for studying in vitro tissues under recirculating flow. Experiments confirmed that the cells within alginate structures survive better than randomly seeded cells under static conditions with limited access to media, indicating that this technique could be useful in bioengineering applications with low levels of diffusion. The methods and tools presented here will contribute to the development and scale-up of lab-grown, vascularized tissues.

Acknowledgements

The authors thank Linda Liu for assistance with device fabrication. Sarah Hewes was supported by the National Science Foundation Graduate Research Fellowship Program. This research was funded by d the National Institutes of Health (NIAID: U19AI116497).

Author Disclosure Statement

No competing financial interests exist.

References

1. Morgan, J.T., Shirazi, J., Comber, E.M., Eschenburg, C., and Gleghorn, J.P. Fabrication of centimeter-scale and geometrically arbitrary vascular networks using in vitro self-assembly. Biomaterials. **189**, 37, 2019.

2. Andrée, B., Ichanti, H., Kalies, S., Heisterkamp, A., Strauß, S., Vogt, P.-M., et al. Formation of three-dimensional tubular endothelial cell networks under defined serum-free cell culture conditions in human collagen hydrogels. Sci Rep. Nature Publishing Group, **9**, 5437, 2019.

3. Papaioannou, T.G., Manolesou, D., Dimakakos, E., Tsoucalas, G., Vavuranakis, M., and Tousoulis, D. 3D Bioprinting Methods and Techniques: Applications on Artificial Blood Vessel Fabrication. Acta Cardiol Sin. **35**, 284, 2019.

4. Zhu, W., Ma, X., Gou, M., Mei, D., Zhang, K., and Chen, S. 3D printing of functional biomaterials for tissue engineering. Curr Opin Biotechnol. **40**, 103, 2016.

5. Duan, B., Hockaday, L.A., Kang, K.H., and Butcher, J.T. 3D Bioprinting of Heterogeneous Aortic Valve Conduits with Alginate/Gelatin Hydrogels. J Biomed Mater Res A. **101**, 1255, 2013.

6. Li, M., Tian, X., Zhu, N., Schreyer, D.J., and Chen, X. Modeling Process-Induced Cell Damage in the Biodispensing Process. Tissue Eng Part C Methods. Mary Ann Liebert, Inc., publishers, **16**, 533, 2009.

7. Lee, J.B., Wang, X., Faley, S., Baer, B., Balikov, D.A., Sung, H.-J., et al. Development of 3D Microvascular Networks Within Gelatin Hydrogels Using Thermoresponsive Sacrificial Microfibers. Adv Healthc Mater. **5**, 781, 2016.

8. Wang, X.-Y., Jin, Z.-H., Gan, B.-W., Lv, S.-W., Xie, M., and Huang, W.-H. Engineering interconnected 3D vascular networks in hydrogels using molded sodium alginate lattice as the sacrificial template. Lab Chip. **14**, 2709, 2014.

9. Kinstlinger, I.S., Saxton, S.H., Calderon, G.A., Ruiz, K.V., Yalacki, D.R., Deme, P.R., et al. Generation of model tissues with dendritic vascular networks via sacrificial laser-sintered carbohydrate templates. Nat Biomed Eng. Nature Publishing Group, 1, 2020.

10. Sakai, S., Yamaguchi, S., Takei, T., and Kawakami, K. Oxidized Alginate-Cross-Linked Alginate/Gelatin Hydrogel Fibers for Fabricating Tubular Constructs with Layered Smooth Muscle Cells and Endothelial Cells in Collagen Gels. Biomacromolecules. American Chemical Society, **9**, 2036, 2008.

11. Liu, Y., Sakai, S., and Taya, M. Engineering tissues with a perfusable vessel-like network using endothelialized alginate hydrogel fiber and spheroid-enclosing microcapsules. Heliyon [Internet]. **2**, 2016 [cited 2017 Mar 31]. Available from: http://www.ncbi.nlm.nih.gov/pmc/articles/PMC4946008/

12. Onoe, H., Okitsu, T., Itou, A., Kato-Negishi, M., Gojo, R., Kiriya, D., et al. Metre-long cell-laden microfibres exhibit tissue morphologies and functions. Nat Mater. **12**, 584, 2013.

13. Hewes, S., Wong, A.D., and Searson, P.C. Bioprinting microvessels using an inkjet printer. Bioprinting. **7**, 14, 2017.

14. Andrique, L., Recher, G., Alessandri, K., Pujol, N., Feyeux, M., Bon, P., et al. A model of guided cell self-organization for rapid and spontaneous formation of functional vessels. Sci Adv [Internet]. **5**, 2019 [cited 2020 Jul 13]. Available from: https://www.ncbi.nlm.nih.gov/pmc/articles/PMC6561743/

15. Lee, K.Y., and Mooney, D.J. Alginate: properties and biomedical applications. Prog Polym Sci. **37**, 106, 2012.

16. McQuin, C., Goodman, A., Chernyshev, V., Kamentsky, L., Cimini, B.A., Karhohs, K.W., et al. CellProfiler 3.0: Next-generation image processing for biology. PLOS Biol. Public Library of Science, **16**, e2005970, 2018.

17. Takei, T., Sakai, S., Yokonuma, T., Ijima, H., and Kawakami, K. Fabrication of Artificial Endothelialized Tubes with Predetermined Three-Dimensional Configuration from Flexible Cell-Enclosing Alginate Fibers. Biotechnol Prog. **23**, 182, 2007.

18. Jun, Y., Kang, E., Chae, S., and Lee, S.-H. Microfluidic spinning of micro- and nano-scale fibers for tissue engineering. Lab Chip. **14**, 2145, 2014.

19. Zhang, C., Zhou, Y., Zhang, L., Wu, L., Chen, Y., Xie, D., et al. Hydrogel Cryopreservation System: An Effective Method for Cell Storage. Int J Mol Sci. **19**, 3330, 2018.