Label-free imaging of DNA interactions with 2D materials

Jenny Sülzle[1],*, Wayne Yang[2],*,†, Yuta Shimoda[2], Nathan Ronceray[2], Eveline Mayner[2], Suliana Manley[1],†, and Aleksandra Radenovic[2],†

[1] Institute of Physics and Institute of Bioengineering, Laboratory of Experimental Biophysics (LEB), École Polytechnique Fédérale de Lausanne (EPFL), Switzerland

[2] Institute of Bioengineering, Laboratory of Nanoscale Biology (LBEN), École Polytechnique Fédérale de Lausanne (EPFL), Switzerland

* Equal contribution

† Corresponding authors:

aleksandra.radenovic@epfl.ch; suliana.manley@epfl.ch; wayne.yang@epfl.ch

Abstract:

Two-dimensional (2D) materials offer potential as substrates for biosensing devices, as their properties can be engineered to tune interactions between the surface and biomolecules. Yet, not many methods can measure these interactions in a liquid environment without introducing labeling agents such as fluorophores. In this work, we harness interferometric scattering (iSCAT) microscopy, a label-free imaging technique, to investigate the interactions of single molecules of long dsDNA with 2D materials. The millisecond temporal resolution of iSCAT allows us to capture the transient interactions and to observe the dynamics of unlabeled DNA binding to a hexagonal boron nitride (hBN) surface in solution for extended periods (including a fraction of 10%, of trajectories lasting longer than 110 ms). Using a Focused Ion Beam (FIB) technique to engineer defects, we find that DNA binding affinity is enhanced at defects; when exposed to long lanes, DNA binds preferentially at lane edges. Overall, we demonstrate that iSCAT imaging is a useful tool to study how biomolecules interact with 2D materials, a key component in engineering future biosensors.

Keywords: DNA-surface interactions, interferometric scattering, 2D materials, biosensing

Two-dimensional (2D) materials have been developed as DNA sensing platforms owing to

their chemical, electronic and mechanical properties which accommodate a variety of sensing

modalities such as membrane-embedded nanopores[1–7], tunneling junctions[8,9] and field-effect

transistors[10,11]. Such devices have succeeded in sensing individual DNA strands, both optically and

electronically[12–16]. Different sensing modalities and functionalisations can be integrated to detect a

whole host of biological analytes with a single device, which due to a high surface-to-volume ratio can

be performed on limited sample volumes.

An important remaining challenge is to control surface interactions and to prevent fouling of

the devices[17]. Toward this end, understanding DNA interactions with 2D materials is crucial to improve

biosensor designs by reducing unwanted interactions and by promoting desired ones. A common

approach is to label DNA fluorescently with intercalating dyes (such as YOYO-1) and study it with

optical microscopy[18]. Alternatively, atomic force microscopy (AFM) can simultaneously detect

molecular binding and map the surfaces[19,20]. Electron microscopy (EM) has also been used to image

2D materials in the presence of biomolecules at even higher spatial resolution[21–23]. However, each of

these approaches suffers from limitations. Intercalating dyes change the length and stiffness of

DNA[24,25], and such dyes suffer from photobleaching and quenching near 2D material surfaces[26,27]. AFM

offers imaging in liquid, but only for hydrophilic substrates such as mica. In the case of prototypical 2D

materials, such as graphene, hexagonal boron nitride (hBN) or transition metal dichalcogenides

(TMDCs), imaging is often limited to dried DNA on 2D material surfaces. EM is largely confined to dry

specimens and thus lacks dynamic information, or requires special liquid holders or the use of gold

nanoparticles as labels[28–32]. This may explain in part why simulation has led experiment in investigating

interactions of DNA with more complex materials and device designs[33–36].

In this work we harness interferometric scattering (iSCAT) microscopy[37,38] to investigate single

molecules of long double stranded (ds)DNA interacting with the surface of hBN. As an analyte in

solution approaches the surface, interference between the light it scatters and the light reflected by

the liquid-solid interface boosts the signal contrast, enabling single-molecule detection. Because iSCAT

uses the molecules themselves to generate signal, it does not require labeling. Liberated from the

limited photon budget of fluorescent dyes, the technique allows millisecond temporal resolution, and

theoretically indefinite imaging times. So far, iSCAT has been used to study the mass distribution of

short single-stranded and double-stranded DNA[39], protein oligomers down to molecular weights of 10

kDa[40,41], and the products of other biomolecular reactions[42] as well as the dynamics of more complex

cellular processes[43]. To study the effects of surface properties on DNA binding, we study its

interactions with pristine hBN as well as engineered defects and nanostructures[44].

We chose hBN as our substrate due to its optical properties: it is transparent because of its

band gap of 6 eV[45], and it uniquely among 2D materials[27,46–48] lacks fluorescence quenching which

allows integration with fluorescent sensing strategies. Additionally, we note the potential for future

engineering[33] due to its regular shaped crystal edges[49–51] and single layer films which appear promising

candidates for high-quality large-scale production[52–54]. hBN was exfoliated on coverslips and imaged

with iSCAT (Figure 1a, SI Experimental Section). The hBN flakes show a static uniform scattering

background when illuminated in water, with stronger scattering from their edges. To prevent edge

scattering from overwhelming the weaker signal from dsDNA, we imaged the larger flakes, and

ensured they filled the selected FOV (Figure S1). Furthermore, we use multiple frames to calculate a

running averaged scattering background and to produce a differential contrast image.

Upon the addition of DNA, we observe the appearance of large scattering signals (blobs) with

bright and dark regions in images following median-filtered background removal (Figure 1b). We

measure similar patterns for a range of different DNA lengths: 10, 20, and 48 kbp (Figure S2). These

sizes were chosen based on our observed lower detection limit of 10 kbp dsDNA. We expect that the

observed blobs of DNA are of single molecules, consistent with observations of both labeled and

unlabeled DNA by other single molecule sensing techniques employing similar concentrations (pM-

nM) of DNA[55–57].

Theoretical and experimental studies have demonstrated that iSCAT is highly sensitive to the

axial position of scattering particles, and even nanometric changes can result in a contrast inversion

in the temporally-filtered images, due to constructive and destructive interference[58,59]. These studies

measured biomolecules much smaller than the diffraction limit, which led to compact, circularly

shaped interferometric point spread functions (iPSF). In our case, the estimated radii of gyration for

the measured DNA molecules are 238 nm (10 kbp dsDNA), 337 nm (20 kbp) and 521 nm (48 kbp). We

speculate that the complex scattering signal is a superposition of multiple iPSFs from different parts

of the same molecule, which spans several hundred nanometers axially. Similar studies with iSCAT

show a linear correlation of the contrast signal to the molecular mass of the analyte for molecules

much smaller than the diffraction limit[39,40,60]. Here, we chose the mean contrast signal of each

localization to investigate its relationship to molecular weight, but we did not find a correlation for

these large DNA molecules.

In time-lapse experiments, we qualitatively observe motion of the scattering blobs (Figure 1b,

Figure S3 and Movie S1). The overall signal contrast is typically low in the frames when a particle

approaches or leaves the surface, but it increases when particles are moving along the surface. We

wished to quantify this motion, but we noticed that the same molecule could change contrast, shape,

and size from frame to frame. We speculate that this is due to changing 3D conformations of the

dsDNA on the hBN surface. Existing strategies for detection and localization such as thresholding and

spot detection yield poor efficiency due to this complex appearance - this motivated us to develop a

customized image analysis pipeline.

We developed an approach to segment and localize the particles for data with a temporal

median-filtered background normalization (Figure 2a, Figure S4, S5, S6). We use the absolute value of

the signal, to combine both constructive and destructive interference contributions to the signal. We

optimize the threshold to avoid false positives from the noisy background, while still detecting faint

signals. Each particle's absolute contrast-weighted center of mass defines its location, which can be

connected in time to reconstruct trajectories (SI Experimental Section). We manually validated the

automatically-tracked results by checking each step in the pipeline for a randomly selected subset of

particles. We define each detected localization as a DNA binding site, and the total time of

reconstructed trajectories as dwell time.

On pristine hBN, we observe a wide range of trajectory geometries and lengths (Figure 2b).

We split them into two groups (Figure 2c): those that are shorter than or equal to 110 ms (523 out of

581 total trajectories) and those that are longer than 110 ms (58 out of 581 total trajectories). Overall,

the measured mean dwell time for 20 kbp dsDNA on pristine hBN is 51.2 [49.0, 57.4] ms (N= 581

trajectories, *Mean [95% confidence interval*). We noticed some particles diffusing out of the measured

FOV (3.4 μm x 3.4 μm), which would lead to a slight underestimate of dwell times. The observed

dynamic nature of the DNA trajectories suggests that interactions of dsDNA with the hBN surface are

transient, allowing molecules to adsorb temporarily on the surface, and diffuse laterally before

detaching and diffusing back into the bulk solution.

Additionally, we noticed a large proportion of brief interactions; in our dataset we measured

554 single-frame binding events, and 581 trajectories that last at least for two frames. Single-frame

binding events likely correspond to DNA interacting transiently with the surface due to weak charge-

mediated surface interactions. To test this idea, we varied the salt concentration by adding 50 mM of

KCl. Under this condition, there appears to be fewer binding events per area and time (Movie S3).

Transient binding events, where the DNA molecule diffuses in and out of the imaging volume vs. along

the surface, are expected to be short-lived, lasting less than a few milliseconds corresponding to a

fraction of a frame. Detecting these events with fluorescence microscopy would be challenging due to

their brief duration; however, with iSCAT microscopy, we were able to take advantage of its temporal

resolution to capture these events.

We hypothesized that it would be possible to influence the DNA binding kinetics by

engineering the surface with fabricated structures that host more defects and hence present more

binding sites. To test this idea, we turned to a recently developed surface engineering method[44]

(Figure 3a, SI Experimental Section). While the technique was first demonstrated to produce optical

emitters, we saw two potential advantages for our application: there may be minimal damage to the

underlying surface of hBN revealed after the water etching step is completed, and the controlled

etching may reduce background scattering of the patterned hBN surfaces and edges. As a

demonstration, we patterned an array of craters, and monitored the surface with AFM imaging (Figure

3b). The sample was submerged in H_2O to etch away the patterned surface, and within 15 min craters

started forming. We continued imaging the sample until the depth of the craters stabilised at ~12 nm

after about one hour. We also etched lanes using the same process, 1 μm wide, 35 nm deep, and

spaced 1 μm apart (Figure 3c). To characterize our structures, we quantified the RMS roughness of the

surface. The RMS roughness along the inner trench area of the lanes is 2 nm, while for a single line

scan it is even lower (0.3- 0.5 nm), and of the surrounding hBN flake area is 1.8 nm (Figure S7).

To observe the effect of surface modifications on the DNA binding affinity, we performed

iSCAT imaging experiments on a single large square FIB-milled onto a flake. Similar FIB milling

processes have yielded increased densities of optically active emitters (up to 40x increase, Figure S8)

in hBN indicating an increase in defect sites. We reconstructed the trajectories of the DNA on the FIB-

milled areas (Figure 4a), and found a mean dwell time of 77.9 [74.8, 86.4] ms (N= 874 trajectories,

Mean [95% confidence interval]; Figure 4b). This is significantly larger than the dwell time of 51.2 [49.0,

57.4] ms on the native flake. This indicates that there is an increased binding affinity, possibly from

interactions with the FIB milling induced defects on the hBN flake. The nanoscopic origins and strength

of these interactions are still up for debate but a few hypotheses include increased electrostatic

interactions[36], hydrogen bonding[61], stacking of the DNA on the hBN[61,62] and reactivity with chemical

species along the defect sites[63].

Next, we performed iSCAT imaging on hBN patterned with narrow lanes by the same process

described above for the square (Figure 4c, Movie S2). The edges of the lanes offered scattering

contrast, allowing us to contextualize the binding of 20 kbp DNA to the surface. We observed an

accumulation of DNA localizations along the edges of the etched lanes (x axis, Figure 4d, Figure S9).

The peaks of the accumulation are located between 200- 400 nm away from the edges, within the

trenches. In contrast, along the direction of the lanes (y axis), binding events appear uniformly

distributed. We examined whether scattering from the lane edges could lead to an increased contrast

signal for localizations at the edges, increasing the probability of detecting events in those regions and

therefore give a false impression of enhanced binding. Further analysis of the mean absolute contrast

intensity revealed no such differences in contrast of binding events, and ruled out this possibility

(Figure S10). We therefore interpret the data to indicate enhanced binding of DNA to the inside of the

lanes. We estimate a DNA polymer radius of gyration of approximately 330 nm, consistent with the

location of the peaks displaced from the edges of the lanes.

We wondered whether the preferential binding to lane edges would lead to anisotropic

trajectories, e.g. DNA particles preferentially moving along the lanes. To investigate this, we created

polar plots of trajectories (Figure S11), and decomposed mean squared displacement (MSD) and step

size distributions – along and perpendicular to the lanes (Figure S12, S13, S14). The polar plots do not

show a preferential movement along one axis, including when considering only long trajectories.

Similarly, the MSD and step size distributions appeared isotropic.

In summary, we present a versatile method based on iSCAT for determining dynamic behavior

of DNA on two-dimensional materials, in solution and without labels. We demonstrate that iSCAT can

distinguish the binding properties of different interfaces. Additionally, the patterning of 2D material

surfaces shows that it is possible to engineer the interaction with dsDNA to create sites with increased

interactions. Surprisingly, we did not observe the directed motion of DNA along tracks. This calls for

future exploration. Nevertheless, biosensing devices can use engineered interactions to enrich

molecules within specific sensing regions[64] such as the nanopore's orifice[65,66], ultimately leading to

improved sensitivity in single-molecule sensing[67].

The data may contain more information about naked DNA's internal configurations and

dynamics. We envision that better control over the background signal and new future analyses

incorporating iSCAT PSF modeling or deep-learning[41,68] will give more insights into these aspects. Since

we avoid modification to DNA's biophysical properties arising from labeling DNA with dye[48] our

method will help to guide the computational modelling of DNA- 2D material interactions[36,66]. Our

measurements were performed with a temporal resolution of ~11 ms, but other iSCAT instruments

demonstrated a temporal resolution of up 1 MHz[69]. This could help understanding conformational

changes in the range of microseconds.

Acknowledgments

W.Y. and A.R. would like to acknowledge funding from SNF grant CRSII5_193740. This work was

supported by the National Centre for Competence in Research (NCCR) Chemical Biology (S.M., J.S.).

We thank Lucie Navratilova for help and useful discussions on the plasma FIB milling. We acknowledge

Michal Macha for the help with pFIB. We thank Kyle Douglass, the EPFL Hub for Image Analysis and

Daniel Sage for their help and useful discussions on the image analysis workflow. We thank Nicolas

Hundt for access to and support with the script for median-filtered iSCAT image processing.

Supporting information

Experimental section and figures as described in the text (PDF)

Supplementary Movie S1: Example of 20 kbp dsDNA on pristine hBN imaged with iSCAT (AVI)

Supplementary Movie S2: Example of 20 kbp dsDNA on FIB-milled hBN imaged with iSCAT (AVI)

Supplementary Movie S3: Example of 20 kbp dsDNA on pristine hBN in DI water and 50 mM KCl (AVI)

Author contribution

J.S., W.Y., S.M. and A.R. conceived the project and designed experiments. J.S., with assistance of W.Y.,

performed iSCAT imaging experiments. J.S. implemented the image processing framework and

performed data analysis. W.Y. prepared the samples, carried out FIB milling, performed fluorescence

imaging with the assistance of Y.S. and N.R. and carried out AFM measurements with assistance from

E.M.. J.S., W.Y., S.M. and A.R. designed figures and wrote the manuscript.

References

(1) Merchant, C. A.; Healy, K.; Wanunu, M.; Ray, V.; Peterman, N.; Bartel, J.; Fischbein, M. D.; Venta,
K.; Luo, Z.; Johnson, A. T. C.; Drndić, M. DNA Translocation through Graphene Nanopores. *Nano*
Lett. **2010**, *10* (8), 2915–2921. https://doi.org/10.1021/nl101046t.
(2) Garaj, S.; Hubbard, W.; Reina, A.; Kong, J.; Branton, D.; Golovchenko, J. A. Graphene as a
Subnanometre Trans-Electrode Membrane. *Nature* **2010**, *467* (7312), 190–193.
https://doi.org/10.1038/nature09379.
(3) Verschueren, D. V.; Yang, W.; Dekker, C. Lithography-Based Fabrication of Nanopore Arrays in
Freestanding SiN and Graphene Membranes. *Nanotechnology* **2018**, *29* (14), 145302.
https://doi.org/10.1088/1361-6528/aaabce.
(4) Graf, M.; Lihter, M.; Thakur, M.; Georgiou, V.; Topolancik, J.; Ilic, B. R.; Liu, K.; Feng, J.; Astier, Y.;
Radenovic, A. Fabrication and Practical Applications of Molybdenum Disulfide Nanopores. *Nat*
Protoc **2019**, *14* (4), 1130–1168. https://doi.org/10.1038/s41596-019-0131-0.
(5) Schneider, G. F.; Kowalczyk, S. W.; Calado, V. E.; Pandraud, G.; Zandbergen, H. W.; Vandersypen,
L. M. K.; Dekker, C. DNA Translocation through Graphene Nanopores. *Nano Lett.* **2010**, *10* (8),
3163–3167. https://doi.org/10.1021/nl102069z.
(6) Liu, K.; Pan, C.; Kuhn, A.; Nievergelt, A. P.; Fantner, G. E.; Milenkovic, O.; Radenovic, A. Detecting
Topological Variations of DNA at Single-Molecule Level. *Nat Commun* **2019**, *10* (1), 3.
https://doi.org/10.1038/s41467-018-07924-1.
(7) Danda, G.; Masih Das, P.; Chou, Y.-C.; Mlack, J. T.; Parkin, W. M.; Naylor, C. H.; Fujisawa, K.;
Zhang, T.; Fulton, L. B.; Terrones, M.; Johnson, A. T. C.; Drndić, M. Monolayer WS2 Nanopores
for DNA Translocation with Light-Adjustable Sizes. *ACS Nano* **2017**, *11* (2), 1937–1945.
https://doi.org/10.1021/acsnano.6b08028.
(8) Caneva, S.; Gehring, P.; García-Suárez, V. M.; García-Fuente, A.; Stefani, D.; Olavarria-Contreras,
I. J.; Ferrer, J.; Dekker, C.; van der Zant, H. S. J. Mechanically Controlled Quantum Interference in
Graphene Break Junctions. *Nature Nanotech* **2018**, *13* (12), 1126–1131.
https://doi.org/10.1038/s41565-018-0258-0.
(9) Huang, S.; He, J.; Chang, S.; Zhang, P.; Liang, F.; Li, S.; Tuchband, M.; Fuhrmann, A.; Ros, R.;
Lindsay, S. Identifying Single Bases in a DNA Oligomer with Electron Tunnelling. *Nature Nanotech*
2010, *5* (12), 868–873. https://doi.org/10.1038/nnano.2010.213.
(10) Heerema, S. J.; Dekker, C. Graphene Nanodevices for DNA Sequencing. *Nature Nanotech* **2016**,
11 (2), 127–136. https://doi.org/10.1038/nnano.2015.307.

(11) Girdhar, A.; Sathe, C.; Schulten, K.; Leburton, J.-P. Graphene Quantum Point Contact Transistor
for DNA Sensing. *Proceedings of the National Academy of Sciences* **2013**, *110* (42), 16748–16753.
https://doi.org/10.1073/pnas.1308885110.
(12) Yamazaki, H.; Kimura, S.; Tsukahara, M.; Esashika, K.; Saiki, T. Optical Detection of DNA
Translocation through Silicon Nanopore by Ultraviolet Light. *Appl. Phys. A* **2014**, *115* (1), 53–56.
https://doi.org/10.1007/s00339-013-7956-0.
(13) Soni, G. V.; Singer, A.; Yu, Z.; Sun, Y.; McNally, B.; Meller, A. Synchronous Optical and Electrical
Detection of Biomolecules Traversing through Solid-State Nanopores. *Review of Scientific
Instruments* **2010**, *81* (1), 014301. https://doi.org/10.1063/1.3277116.
(14) Assad, O. N.; Di Fiori, N.; Squires, A. H.; Meller, A. Two Color DNA Barcode Detection in
Photoluminescence Suppressed Silicon Nitride Nanopores. *Nano Lett.* **2015**, *15* (1), 745–752.
https://doi.org/10.1021/nl504459c.
(15) Yang, W.; Dekker, C. Single-Molecule Ionic and Optical Sensing with Nanoapertures. In *Single
Molecule Sensing Beyond Fluorescence*; Bowen, W., Vollmer, F., Gordon, R., Eds.; Nanostructure
Science and Technology; Springer International Publishing: Cham, 2022; pp 367–387.
https://doi.org/10.1007/978-3-030-90339-8_12.
(16) Pitchford, W. H.; Kim, H.-J.; Ivanov, A. P.; Kim, H.-M.; Yu, J.-S.; Leatherbarrow, R. J.; Albrecht, T.;
Kim, K.-B.; Edel, J. B. Synchronized Optical and Electronic Detection of Biomolecules Using a Low
Noise Nanopore Platform. *ACS Nano* **2015**, *9* (2), 1740–1748.
https://doi.org/10.1021/nn506572r.
(17) Schneider, G. F.; Xu, Q.; Hage, S.; Luik, S.; Spoor, J. N. H.; Malladi, S.; Zandbergen, H.; Dekker, C.
Tailoring the Hydrophobicity of Graphene for Its Use as Nanopores for DNA Translocation. *Nat
Commun* **2013**, *4* (1), 2619. https://doi.org/10.1038/ncomms3619.
(18) Lu, C.; Liu, Y.; Ying, Y.; Liu, J. Comparison of MoS2, WS2, and Graphene Oxide for DNA
Adsorption and Sensing. *Langmuir* **2017**, *33* (2), 630–637.
https://doi.org/10.1021/acs.langmuir.6b04502.
(19) Pyne, A.; Thompson, R.; Leung, C.; Roy, D.; Hoogenboom, B. W. Single-Molecule Reconstruction
of Oligonucleotide Secondary Structure by Atomic Force Microscopy. *Small* **2014**, *10* (16), 3257–
3261. https://doi.org/10.1002/smll.201400265.
(20) Pyne, A. L. B.; Noy, A.; Main, K. H. S.; Velasco-Berrelleza, V.; Piperakis, M. M.; Mitchenall, L. A.;
Cugliandolo, F. M.; Beton, J. G.; Stevenson, C. E. M.; Hoogenboom, B. W.; Bates, A. D.; Maxwell,
A.; Harris, S. A. Base-Pair Resolution Analysis of the Effect of Supercoiling on DNA Flexibility and
Major Groove Recognition by Triplex-Forming Oligonucleotides. *Nat Commun* **2021**, *12* (1),
1053. https://doi.org/10.1038/s41467-021-21243-y.
(21) Gentile, F.; Moretti, M.; Limongi, T.; Falqui, A.; Bertoni, G.; Scarpellini, A.; Santoriello, S.;
Maragliano, L.; Proietti Zaccaria, R.; di Fabrizio, E. Direct Imaging of DNA Fibers: The Visage of
Double Helix. *Nano Lett.* **2012**, *12* (12), 6453–6458. https://doi.org/10.1021/nl3039162.
(22) Zellweger, R.; Lopes, M. Dynamic Architecture of Eukaryotic DNA Replication Forks In Vivo,
Visualized by Electron Microscopy. In *Genome Instability: Methods and Protocols*; Muzi-Falconi,
M., Brown, G. W., Eds.; Methods in Molecular Biology; Springer: New York, NY, 2018; pp 261–
294. https://doi.org/10.1007/978-1-4939-7306-4_19.
(23) Cerf, A.; Alava, T.; Barton, R. A.; Craighead, H. G. Transfer-Printing of Single DNA Molecule Arrays
on Graphene for High-Resolution Electron Imaging and Analysis. *Nano Lett.* **2011**, *11* (10), 4232–
4238. https://doi.org/10.1021/nl202219w.
(24) Günther, K.; Mertig, M.; Seidel, R. Mechanical and Structural Properties of YOYO-1 Complexed
DNA. *Nucleic Acids Research* **2010**, *38* (19), 6526–6532. https://doi.org/10.1093/nar/gkq434.
(25) Rocha, M. S.; Ferreira, M. C.; Mesquita, O. N. Transition on the Entropic Elasticity of DNA
Induced by Intercalating Molecules. *The Journal of Chemical Physics* **2007**, *127* (10), 105108.
https://doi.org/10.1063/1.2768945.

(26) Tan, A. T. L.; Kim, J.; Huang, J.-K.; Li, L.-J.; Huang, J. Seeing Two-Dimensional Sheets on Arbitrary
Substrates by Fluorescence Quenching Microscopy. *Small* **2013**, *9* (19), 3253–3258.
https://doi.org/10.1002/smll.201300049.
(27) Kasry, A.; Ardakani, A. A.; Tulevski, G. S.; Menges, B.; Copel, M.; Vyklicky, L. Highly Efficient
Fluorescence Quenching with Graphene. *J. Phys. Chem. C* **2012**, *116* (4), 2858–2862.
https://doi.org/10.1021/jp207972f.
(28) Dunn, G.; Adiga, V. P.; Pham, T.; Bryant, C.; Horton-Bailey, D. J.; Belling, J. N.; LaFrance, B.;
Jackson, J. A.; Barzegar, H. R.; Yuk, J. M.; Aloni, S.; Crommie, M. F.; Zettl, A. Graphene-Sealed
Flow Cells for In Situ Transmission Electron Microscopy of Liquid Samples. *ACS Nano* **2020**, *14*
(8), 9637–9643. https://doi.org/10.1021/acsnano.0c00431.
(29) Yuk, J. M.; Park, J.; Ercius, P.; Kim, K.; Hellebusch, D. J.; Crommie, M. F.; Lee, J. Y.; Zettl, A.;
Alivisatos, A. P. High-Resolution EM of Colloidal Nanocrystal Growth Using Graphene Liquid
Cells. *Science* **2012**, *336* (6077), 61–64. https://doi.org/10.1126/science.1217654.
(30) de Jonge, N.; Ross, F. M. Electron Microscopy of Specimens in Liquid. *Nature Nanotech* **2011**, *6*
(11), 695–704. https://doi.org/10.1038/nnano.2011.161.
(31) Zheng, H.; Claridge, S. A.; Minor, A. M.; Alivisatos, A. P.; Dahmen, U. Nanocrystal Diffusion in a
Liquid Thin Film Observed by in Situ Transmission Electron Microscopy. *Nano Lett.* **2009**, *9* (6),
2460–2465. https://doi.org/10.1021/nl9012369.
(32) Chen, Q.; Smith, J. M.; Park, J.; Kim, K.; Ho, D.; Rasool, H. I.; Zettl, A.; Alivisatos, A. P. 3D Motion
of DNA-Au Nanoconjugates in Graphene Liquid Cell Electron Microscopy. *Nano Lett.* **2013**, *13*
(9), 4556–4561. https://doi.org/10.1021/nl402694n.
(33) Zhang, L.; Wang, X. DNA Sequencing by Hexagonal Boron Nitride Nanopore: A Computational
Study. *Nanomaterials* **2016**, *6* (6), 111. https://doi.org/10.3390/nano6060111.
(34) Manzanares-Palenzuela, C. L.; Pourrahimi, A. M.; Gonzalez-Julian, J.; Sofer, Z.; Pykal, M.;
Otyepka, M.; Pumera, M. Interaction of Single- and Double-Stranded DNA with Multilayer
MXene by Fluorescence Spectroscopy and Molecular Dynamics Simulations. *Chem. Sci.* **2019**, *10*
(43), 10010–10017. https://doi.org/10.1039/C9SC03049B.
(35) Chen, S. H.; Bell, D. R.; Luan, B. Understanding Interactions between Biomolecules and Two-
Dimensional Nanomaterials Using in Silico Microscopes. *Advanced Drug Delivery Reviews* **2022**,
186, 114336. https://doi.org/10.1016/j.addr.2022.114336.
(36) Shankla, M.; Aksimentiev, A. Step-Defect Guided Delivery of DNA to a Graphene Nanopore. *Nat.*
Nanotechnol. **2019**, *14* (9), 858–865. https://doi.org/10.1038/s41565-019-0514-y.
(37) Lindfors, K.; Kalkbrenner, T.; Stoller, P.; Sandoghdar, V. Detection and Spectroscopy of Gold
Nanoparticles Using Supercontinuum White Light Confocal Microscopy. *Phys. Rev. Lett.* **2004**, *93*
(3), 037401. https://doi.org/10.1103/PhysRevLett.93.037401.
(38) Jacobsen, V.; Stoller, P.; Brunner, C.; Vogel, V.; Sandoghdar, V. Interferometric Optical Detection
and Tracking of Very Small Gold Nanoparticles at a Water-Glass Interface. *Opt. Express* **2006**, *14*
(1), 405. https://doi.org/10.1364/OPEX.14.000405.
(39) Li, Y.; Struwe, W. B.; Kukura, P. Single Molecule Mass Photometry of Nucleic Acids. *Nucleic Acids*
Research **2020**, *48* (17), e97. https://doi.org/10.1093/nar/gkaa632.
(40) Young, G.; Hundt, N.; Cole, D.; Fineberg, A.; Andrecka, J.; Tyler, A.; Olerinyova, A.; Ansari, A.;
Marklund, E. G.; Collier, M. P.; Chandler, S. A.; Tkachenko, O.; Allen, J.; Crispin, M.; Billington, N.;
Takagi, Y.; Sellers, J. R.; Eichmann, C.; Selenko, P.; Frey, L.; Riek, R.; Galpin, M. R.; Struwe, W. B.;
Benesch, J. L. P.; Kukura, P. Quantitative Mass Imaging of Single Biological Macromolecules.
Science **2018**, *360* (6387), 423–427. https://doi.org/10.1126/science.aar5839.
(41) Dahmardeh, M.; Mirzaalian Dastjerdi, H.; Mazal, H.; Köstler, H.; Sandoghdar, V. Self-Supervised
Machine Learning Pushes the Sensitivity Limit in Label-Free Detection of Single Proteins below
10 kDa. *Nat Methods* **2023**, *20* (3), 442–447. https://doi.org/10.1038/s41592-023-01778-2.
(42) Hundt, N.; Cole, D.; Hantke, M. F.; Miller, J. J.; Struwe, W. B.; Kukura, P. Direct Observation of
the Molecular Mechanism Underlying Protein Polymerization. *Science Advances* **2022**, *8* (35),
eabm7935. https://doi.org/10.1126/sciadv.abm7935.

(43) Küppers, M.; Albrecht, D.; Kashkanova, A. D.; Lühr, J.; Sandoghdar, V. Confocal Interferometric
Scattering Microscopy Reveals 3D Nanoscopic Structure and Dynamics in Live Cells. *Nat*
Commun **2023**, *14* (1), 1962. https://doi.org/10.1038/s41467-023-37497-7.
(44) Glushkov, E.; Macha, M.; Räth, E.; Navikas, V.; Ronceray, N.; Cheon, C. Y.; Ahmed, A.; Avsar, A.;
Watanabe, K.; Taniguchi, T.; Shorubalko, I.; Kis, A.; Fantner, G.; Radenovic, A. Engineering
Optically Active Defects in Hexagonal Boron Nitride Using Focused Ion Beam and Water. *ACS*
Nano **2022**, *16* (3), 3695–3703. https://doi.org/10.1021/acsnano.1c07086.
(45) Wickramaratne, D.; Weston, L.; Van de Walle, C. G. Monolayer to Bulk Properties of Hexagonal
Boron Nitride. *J. Phys. Chem. C* **2018**, *122* (44), 25524–25529.
https://doi.org/10.1021/acs.jpcc.8b09087.
(46) Deng, H.; Yang, X.; Gao, Z. MoS2 Nanosheets as an Effective Fluorescence Quencher for DNA
Methyltransferase Activity Detection. *Analyst* **2015**, *140* (9), 3210–3215.
https://doi.org/10.1039/C4AN02133A.
(47) Kaminska, I.; Bohlen, J.; Rocchetti, S.; Selbach, F.; Acuna, G. P.; Tinnefeld, P. Distance
Dependence of Single-Molecule Energy Transfer to Graphene Measured with DNA Origami
Nanopositioners. *Nano Lett.* **2019**, *19* (7), 4257–4262.
https://doi.org/10.1021/acs.nanolett.9b00172.
(48) Richter, L.; Szalai, A. M.; Manzanares-Palenzuela, C. L.; Kamińska, I.; Tinnefeld, P. Exploring the
Synergies of Single-Molecule Fluorescence and 2D Materials Coupled by DNA. *Advanced*
Materials **2023**, *35* (41), 2303152. https://doi.org/10.1002/adma.202303152.
(49) Liu, K.; Lihter, M.; Sarathy, A.; Caneva, S.; Qiu, H.; Deiana, D.; Tileli, V.; Alexander, D. T. L.;
Hofmann, S.; Dumcenco, D.; Kis, A.; Leburton, J.-P.; Radenovic, A. Geometrical Effect in 2D
Nanopores. *Nano Lett.* **2017**, *17* (7), 4223–4230. https://doi.org/10.1021/acs.nanolett.7b01091.
(50) Dai, C.; Popple, D.; Su, C.; Park, J.-H.; Watanabe, K.; Taniguchi, T.; Kong, J.; Zettl, A. Evolution of
Nanopores in Hexagonal Boron Nitride. *Communications Chemistry* **2023**, *6* (1), 108.
https://doi.org/10.1038/s42004-023-00899-1.
(51) Gilbert, S. M.; Dunn, G.; Azizi, A.; Pham, T.; Shevitski, B.; Dimitrov, E.; Liu, S.; Aloni, S.; Zettl, A.
Fabrication of Subnanometer-Precision Nanopores in Hexagonal Boron Nitride. *Scientific Reports*
2017, *7* (1), 15096. https://doi.org/10.1038/s41598-017-12684-x.
(52) Caneva, S.; Weatherup, R. S.; Bayer, B. C.; Brennan, B.; Spencer, S. J.; Mingard, K.; Cabrero-
Vilatela, A.; Baehtz, C.; Pollard, A. J.; Hofmann, S. Nucleation Control for Large, Single Crystalline
Domains of Monolayer Hexagonal Boron Nitride via Si-Doped Fe Catalysts. *Nano Lett.* **2015**, *15*
(3), 1867–1875. https://doi.org/10.1021/nl5046632.
(53) Fukamachi, S.; Solís-Fernández, P.; Kawahara, K.; Tanaka, D.; Otake, T.; Lin, Y.-C.; Suenaga, K.;
Ago, H. Large-Area Synthesis and Transfer of Multilayer Hexagonal Boron Nitride for Enhanced
Graphene Device Arrays. *Nature Electronics* **2023**, *6* (2), 126–136.
https://doi.org/10.1038/s41928-022-00911-x.
(54) Liu, S.; He, R.; Ye, Z.; Du, X.; Lin, J.; Jiang, H.; Liu, B.; Edgar, J. H. Large-Scale Growth of High-
Quality Hexagonal Boron Nitride Crystals at Atmospheric Pressure from an Fe–Cr Flux. *Crystal*
Growth & Design **2017**, *17* (9), 4932–4935. https://doi.org/10.1021/acs.cgd.7b00871.
(55) Bell, N. A. W.; Muthukumar, M.; Keyser, U. F. Translocation Frequency of Double-Stranded DNA
through a Solid-State Nanopore. *Phys. Rev. E* **2016**, *93* (2), 022401.
https://doi.org/10.1103/PhysRevE.93.022401.
(56) Wanunu, M.; Morrison, W.; Rabin, Y.; Grosberg, A. Y.; Meller, A. Electrostatic Focusing of
Unlabelled DNA into Nanoscale Pores Using a Salt Gradient. *Nature Nanotech* **2010**, *5* (2), 160–
165. https://doi.org/10.1038/nnano.2009.379.
(57) Lastra, L. S.; Bandara, Y. M. N. D. Y.; Nguyen, M.; Farajpour, N.; Freedman, K. J. On the Origins of
Conductive Pulse Sensing inside a Nanopore. *Nat Commun* **2022**, *13* (1), 2186.
https://doi.org/10.1038/s41467-022-29758-8.
(58) Mahmoodabadi, R. G.; Taylor, R. W.; Kaller, M.; Spindler, S.; Mazaheri, M.; Kasaian, K.;
Sandoghdar, V. Point Spread Function in Interferometric Scattering Microscopy (iSCAT). Part I:

Aberrations in Defocusing and Axial Localization. *Opt. Express, OE* **2020**, *28* (18), 25969–25988.
https://doi.org/10.1364/OE.401374.

(59) Dong, J.; Maestre, D.; Conrad-Billroth, C.; Juffmann, T. Fundamental Bounds on the Precision of
iSCAT, COBRI and Dark-Field Microscopy for 3D Localization and Mass Photometry. *J. Phys. D:*
Appl. Phys. **2021**, *54* (39), 394002. https://doi.org/10.1088/1361-6463/ac0f22.

(60) Heermann, T.; Steiert, F.; Ramm, B.; Hundt, N.; Schwille, P. Mass-Sensitive Particle Tracking to
Elucidate the Membrane-Associated MinDE Reaction Cycle. *Nat Methods* **2021**, *18* (10), 1239–
1246. https://doi.org/10.1038/s41592-021-01260-x.

(61) Ding, N.; Chen, X.; Wu, C.-M. L.; Li, H. Adsorption of Nucleobase Pairs on Hexagonal Boron
Nitride Sheet: Hydrogen Bonding versus Stacking. *Phys. Chem. Chem. Phys.* **2013**, *15* (26),
10767–10776. https://doi.org/10.1039/C3CP50912E.

(62) Lee, J.-H.; Choi, Y.-K.; Kim, H.-J.; Scheicher, R. H.; Cho, J.-H. Physisorption of DNA Nucleobases on
H-BN and Graphene: vdW-Corrected DFT Calculations. *J. Phys. Chem. C* **2013**, *117* (26), 13435–
13441. https://doi.org/10.1021/jp402403f.

(63) Ronceray, N.; You, Y.; Glushkov, E.; Lihter, M.; Rehl, B.; Chen, T.-H.; Nam, G.-H.; Borza, F.;
Watanabe, K.; Taniguchi, T.; Roke, S.; Keerthi, A.; Comtet, J.; Radha, B.; Radenovic, A. Liquid-
Activated Quantum Emission from Pristine Hexagonal Boron Nitride for Nanofluidic Sensing.
Nat. Mater. **2023**, *22* (10), 1236–1242. https://doi.org/10.1038/s41563-023-01658-2.

(64) Dong Hoon Shin; Sung Hyun Kim; Kush Coshic; Kenji Watanabe; Takashi Taniguchi; Gerard
Verbiest; Sabina Caneva; Aleksei Aksimentiev; Peter G. Steeneken; Chirlmin Joo. Diffusion of
DNA on Atomically Flat 2D Material Surfaces. *bioRxiv* **2023**, 2023.11.01.565159.
https://doi.org/10.1101/2023.11.01.565159.

(65) Cao, Z.; Yadav, P.; Barati Farimani, A. Which 2D Material Is Better for DNA Detection: Graphene,
MoS2, or MXene? *Nano Lett.* **2022**, *22* (19), 7874–7881.
https://doi.org/10.1021/acs.nanolett.2c02603.

(66) Wells, D. B.; Belkin, M.; Comer, J.; Aksimentiev, A. Assessing Graphene Nanopores for
Sequencing DNA. *Nano Lett.* **2012**, *12* (8), 4117–4123. https://doi.org/10.1021/nl301655d.

(67) Shin, D. H.; Yang, X.; Caneva, S. Single-Molecule Protein Fingerprinting with Photonic Hexagonal
Boron Nitride Nanopores. *Acc. Mater. Res.* **2023**, *4* (4), 307–310.
https://doi.org/10.1021/accountsmr.3c00016.

(68) Boyle, M. J.; Goldman, Y. E.; Composto, R. J. Enhancing Nanoparticle Detection in
Interferometric Scattering (iSCAT) Microscopy Using a Mask R-CNN. *J. Phys. Chem. B* **2023**, *127*
(16), 3737–3745. https://doi.org/10.1021/acs.jpcb.3c00097.

(69) Spindler, S.; Ehrig, J.; König, K.; Nowak, T.; Piliarik, M.; Stein, H. E.; Taylor, R. W.; Garanger, E.;
Lecommandoux, S.; Alves, I. D.; Sandoghdar, V. Visualization of Lipids and Proteins at High
Spatial and Temporal Resolution via Interferometric Scattering (iSCAT) Microscopy. *J. Phys. D:*
Appl. Phys. **2016**, *49* (27), 274002. https://doi.org/10.1088/0022-3727/49/27/274002.

432 **Figure 1.** Interaction of 2D materials and DNA probed by iSCAT. (a) Schematic setup of the experiment.

433 (b) Two examples of median-filtered time series of 20 kbp dsDNA particles diffusing on the hBN

434 surface, illustrating changes in shape, size, and contrast of the same molecule from frame-to-frame.

435 Scale bar is 1 μm.

Figure 2. Overview of image processing workflow and of trajectories on pristine hBN. (a) Schematic of image processing workflow. (b) Examples of short and long trajectories on pristine hBN. (c) Dwell time of 20 kbp DNA on pristine hBN. The histogram represents all reconstructed trajectories from three pooled measurement with each 10,000 frames imaged at 90.5 Hz. N (total trajectories) = 581, N (L ≤ 110 ms) = 523, N (L > 110 ms) = 58. Scale bars are 1 μm.

Figure 3. AFM image of pFIB-milled, water-assisted etching of hBN. (a) Illustration of the formation of hBN wells in H_2O. (b) Time series of a dot-patterned hBN flake upon immersion in water. (c) AFM surface map of tracks milled in hBN flake. (d) AFM height profile scan as indicated by the dashed line in (c), RMS roughness along the trench of the lanes is 2 nm.

Figure 4. DNA interaction with FIB-milled hBN samples. (a) Native iSCAT image of an hBN flake with an etched square (dashed line). Area used for quantitative analysis is highlighted in blue. (b) Comparison of dwell time of 20 kbp dsDNA on three different surfaces: FIB-etched hBN (FIB square), pristine hBN and hBN patterned with lanes. The histogram represents all reconstructed trajectories from each three pooled measurements. The data was fit to an exponentially decaying distribution. N (FIB square) = 874 trajectories, N (pristine hBN) = 581 and N (FIB lanes) = 703. ***P-value = 0.000021, **P-value = 0.0019. (c) Native iSCAT image of an hBN flake with etched lanes. (d) Distribution of binding spots of 20 kbp dsDNA on sample shown in (c). The scatter histogram represents all localizations from three pooled measurements on the FIB lanes sample shown in (c). N = 9130 localizations. Scale bars are 1 μm.