Matrix stiffness modulates 3D spheroid sorting and burst-like collective migration

Grace Cai[1], Xinzhi Li[2,#], Shan-Shan Lin[3,#], Samuel Chen[4], Katherine Koning[5], Dapeng Bi[6,*] and Allen P. Liu[1,4,5,7,8,*]

[1] Applied Physics Program, University of Michigan, Ann Arbor, MI, USA

[2] Department of Physics, Carnegie Mellon University, Pittsburgh, PA, USA

[3] Institute of Molecular Medicine, College of Medicine, National Taiwan University, Taipei, Taiwan

[4] Department of Mechanical Engineering, University of Michigan, Ann Arbor, MI, USA

[5] Cellular and Molecular Biology Program, University of Michigan, Ann Arbor, MI, USA

[6] Department of Physics, Northeastern University, Boston, MA, USA

[7] Department of Biomedical Engineering, University of Michigan, Ann Arbor, MI, USA

[8] Department of Biophysics, University of Michigan, Ann Arbor, MI, USA

[#] Equal contribution

* Corresponding authors:

Dapeng Bi: d.bi@northeastern.edu

Allen P. Liu: allenliu@umich.edu

Abstract

While it is known that cells with differential adhesion tend to segregate and preferentially sort, the physical forces governing sorting and invasion in heterogeneous tumors remain poorly understood. To investigate this, we develop a composite hydrogel that uncouples matrix stiffness and collagen fiber density, mimicking changes in the stiffness of the tumor microenvironment, to explore how physical confinement influences individual and collective cell migration in 3D spheroids. The mechanical properties of the hydrogel can be tuned through crosslinking and crosslink reversal. Using this hydrogel system and computational Self-Propelled Voronoi modeling, we show that spheroid sorting and invasion into the matrix depend on the balance between cell-generated forces and matrix resistance. Sorting is driven by high confinement and reducing matrix stiffness triggers a collective fluidization of cell motion. Cell sorting, which depends on cell-cell adhesion, is crucial to this phenomenon, and burst-like migration does not occur for unsorted spheroids irrespective of matrix stiffness. The findings support a model where matrix stiffness modulates 3D spheroid sorting and unjamming in an adhesion-dependent manner, providing insights into the mechanisms of cell sorting and migration in the primary tumor and toward distant metastatic sites.

Keywords: Hydrogels; 3D cell culture; cell–cell adhesion; cancer invasion; collagen and alginate

Introduction

The primary tumor microenvironment plays a crucial role in facilitating the movement of cancer cells beyond the primary tumor. These cells navigate through the stroma, eventually infiltrating nearby microvessels through the process of intravasation (*1–3*). In confined tumors that exhibit a high cellular density, cancer cells must proliferate and migrate in order to promote tumor growth and metastasis. However, unchecked proliferation within these restricted spaces can lead to confinement stress (*4–6*). This stress in turn induces changes in cell-cell interactions and influences tumor development and compartmentalization (*7, 8*). Many cell-cell interactions depend on E-cadherin-based cell-cell junctions to preserve tissue cohesion and maintain active force transmission (*9–11*). During cancer metastasis, E-cadherin is downregulated in the epithelial-to-mesenchymal transition (EMT), which destabilizes cell-cell junctions and promotes invasiveness (*12, 13*). Cancer invasion and metastasis have been shown to occur in both E-cadherin-expressing and -deficient tumors (*11*). However, how the tumor microenvironment directly impacts intercellular interactions in tumors exhibiting intratumoral heterogeneity remains unclear.

A heterogeneous cell composition effectively replicates the physiological tumor microenvironment and introduces heterotypic cell-cell interactions (*14, 15*). Mixtures of two cell types with differences in cell-cell adhesion have been observed to undergo sorting (*16, 17*), however the cell-cell and cell-substrate interactions driving such sorting in tumors are not well understood. Recent work suggests that changes to cell-cell adhesion associated with EMT are related to cellular jamming and unjamming (*18, 19*). When cells are jammed, they behave as a solid-like state in which individual cellular motion becomes arrested, and unjamming represents a shift to a fluid-like state in which cells exchange neighbors and the tissue flows in response to

fluctuations (*20, 21*). In essence, the physical mechanisms that orchestrate jamming—unjamming behavior are driven by cellular properties, such as cell-cell and cell-substrate interactions (*22*).

In addition to adherens junctions, microenvironmental conditions involving cell-substrate interactions play a key role in regulating collective migration (*23, 24*). Many cell types exert integrin-based traction forces on the extracellular substrate to migrate and higher cell-substrate adhesion leads to increased cell spreading and motility (*22, 25, 26*). Notably, the mechanical attributes of the substrate are also an important factor, as cells tend to spread more and migrate faster on stiffer substrates (*27–29*). Prior studies tuned matrix stiffness by changing the concentration of collagen (*30*). To disentangle the influence of matrix stiffness from that of collagen fiber density, we developed a tunable collagen-alginate composite hydrogel to investigate how physical forces, such as confinement stress, influence cancer cell invasion. Our choice of type I collagen, the most abundant ECM protein in mammals (*31*), stemmed from its ability to provide adhesion sites for cells. In contrast, alginate, which cells cannot adhere to, is viscoelastic and controls gel stiffness by tunable crosslinking (*32, 33*). By leveraging calcium and calcium chelators like ethylene glycol tetraacetic acid (EGTA), we can manipulate the stiffness of the hydrogel in a time-dependent manner, mimicking the physical properties found in the tumor microenvironment. Invasive cancer cells can degrade collagen by secreting matrix metalloproteinases (MMPs) (*34*); however, alginate is not degradable and is more applicable to contexts where degradation is limited or not possible. Overall, collagen-alginate composite hydrogels offer the ability to adjust the matrix stiffness independently of collagen fiber density.

In our investigation into the impact of matrix stiffness on cancer migration, we propose that tumor cell migration occurs in two distinct stages. Mesenchymal cells are segregated and sorted to the tumor periphery, where they proliferate and secrete enzymes to degrade the surrounding ECM. Following this, cellular invasion takes place. In this study, we utilize a composite hydrogel with tunable mechanical properties to illustrate the critical role that ECM stiffness plays in tumor development and distant metastasis. When matrix degradation is limited in a stiff hydrogel with low available ECM space, the pressure inside the spheroid core increases, and the cells become jammed. A reduction in matrix confinement causes the collective fluidization of cell motion, propelling normal epithelial cells and cancer cells into the matrix with high velocity. Using a computational Self-Propelled Voronoi (SPV) model to simulate a heterogeneous tissue, we confirm the experimental finding and further show that decreasing the cell-medium contact tension downregulates confinement stress and leads to cell invasion. The results yield insights into the interplay between confinement stress, cell-cell adhesion, and 3D jamming–unjamming transitions in breast cancer metastasis.

Results

3D matrix confinement inhibits single-cell cancer migration

Spheroids are extensively utilized as a three-dimensional *in vitro* multicellular model, mirroring the structure and function of tissues (*35, 36*). To form co-culture spheroids, we selected MCF10A, a non-tumorigenic breast epithelial cell line, and MDA-MB-231, a triple negative, highly invasive cancer cell line (*38*). MCF10A cells have stable adherens junctions with high E-

cadherin expression, whereas MDA-MB-231 cells lack E-cadherin (*39*). We generated stable cell lines expressing Lifeact or a soluble fluorescence protein as markers to denote different cell types and mixed normal epithelial cells and cancer cells to replicate intratumoral heterogeneity. Subsequently, we encapsulated mixed spheroids in collagen-alginate hydrogels and manipulated the matrix stiffness by varying the concentration of $CaCl_2$ to crosslink alginate (**Fig. 1A**), yielding Young's moduli ranging from ~2.67 kPa to ~5.75 kPa (**Fig. S1**). This falls within the ECM stiffness range of 2-20 kPa found in breast tumors (*40*, *41*). By maintaining the concentration of collagen, the number of cell adhesion sites, which depend on the density of collagen fibers, remains constant.

Over the course of 4 days, MDA-MB-231 cells sorted to the spheroid boundary and migrated as single cells into the surrounding matrix, depending on hydrogel stiffness (**Fig. 1, B and C**). Under low confinement, single cancer cells escaped the tumor spheroid and invaded into the hydrogel after 4 days of culture, whereas the higher confinement in crosslinked gels inhibited cancer cell migration into the matrix (**Fig. 1B**). Breast carcinoma cells, which are known to be mechanically soft compared to the surrounding normal cells (*39*), possessed low F-actin (**Fig. S2**), suggesting higher deformability than the MCF10A cells confined to the spheroid. As a measure of cell sorting and migration, a distance index was calculated for each cell using the relative distance of the cell to the spheroid center (*17*). Cancer cells in hydrogels with low matrix stiffness exhibited a higher distance index (**Fig. 1D**) and were more elongated (**Fig. 1E**). Although MDA-MB-231 cells localized to the spheroid boundary after 4 days of culture regardless of gel stiffness, high matrix stiffness restricted the cancer cells to the periphery and prevented invasion into the matrix. Furthermore, cancer cells cultured in a stiffer matrix displayed a round morphology (**Fig. 1B**). Cancer cell invasion was not impeded in mixed spheroids cultured in collagen gels with 10 mM $CaCl_2$ (**Fig. S3**), showing that the behavior observed was not caused by the presence of calcium.

To study the kinematics of 3D cancer cell migration in co-culture spheroids, we performed experiments with varying degrees of alginate crosslinking and computed the mean square displacement (MSD) in log-log scale of cells in different conditions of matrix confinement, with the average slopes (α values) representing super-diffusive ($\alpha > 1$), diffusive ($\alpha = 1$), and sub-diffusive ($\alpha < 1$) cell motility (*17*, *42*). Under low confinement, MDA-MB-231 cells were more diffusive than MCF10A cells (i.e., α of ~1.51 vs. ~1.21), whereas diffusivity was similar for both cell types under high confinement (i.e., α of ~0.86 vs. ~0.83, **Fig. 1, F and G**). Normal breast epithelial cells and cancer cells both demonstrated lower diffusivity when cultured in crosslinked hydrogels (**Fig. 1H**). Cancer cells cultured in hydrogels with low matrix stiffness were more elongated, which possibly correlated with super-diffusive behavior (**Fig. 1G**), linking cell shape to diffusive motion (*43*, *44*).

High ECM confinement drives spheroid sorting

To investigate how the metastatic potential of the cancer cell line impacts migration behavior under confinement, we generated MCF10A and MCF7 co-culture spheroids. MCF7 is a poorly metastatic breast epithelial cell line that does not express membrane type 1-matrix metalloproteinase 1 (MT1-MMP)/MMP14 (*11*). As a result, MCF7 cells are unable to degrade or remodel ECM and are non-invasive. When under matrix confinement due to alginate

crosslinking, these mixed spheroids undergo different degrees of sorting, showing minimal sorting in 0 mM $CaCl_2$, intermediate sorting in 5 mM $CaCl_2$, and complete sorting in 10 mM $CaCl_2$ (**Fig. 2, A and B**). After 4 days of culture, mixed spheroids cultured in low-stiffness hydrogels were significantly larger than those cultured in crosslinked, stiffer hydrogels (**Fig. S4**). To quantify the spatial organization of MCF10A and MCF7 cells within spheroids as matrix confinement increased, we measured the distance index for the subpopulations, which yielded notable cell sorting under high matrix stiffness (**Fig. 2C**). Cell sorting was evident, as the subpopulations were distinctly separated into the core and edge regions of the spheroids (**Fig. 2C**). This observation is correlated with differences in E-cadherin expression, as measured by fluorescence intensity normalized to the number of each cell type, where MCF10A cells at the core expressed higher E-cadherin levels than MCF7 cells localized to the boundary compartment (**Fig. 2D**). As a measure of the differential E-cadherin expression in sorted spheroids, the relative adhesion ratio was calculated for individual spheroids as the ratio of E-cadherin expression of the adhesive cell type to the less adhesive cell type, based on their fluorescence intensity (**Fig. 2E**). The adhesion ratio increased with spheroid sorting in hydrogels with high matrix stiffness, indicating that sorting is indeed linked to intercellular adhesion strength, consistent with the differential adhesion hypothesis (DAH) (*45*).

Moreover, under high matrix stiffness, mixed spheroids transitioned from a homogeneous adhesion state to a sorted state with a defined core with high adhesion and a boundary compartment with low adhesion. These results suggest that physical confinement stress generated by the mechanical properties of the matrix was sensed by and transduced through cells, resulting in differential sorting. To confirm that the sorting behavior observed was not induced by the addition of calcium, we showed that the spheroids failed to sort when cultured in collagen gels with 10 mM $CaCl_2$ that had a Young's modulus of ~2 kPa (**Fig. S5**). Together, these experiments indicate that, in our model system, cell sorting is driven by increased matrix stiffness and is dependent on cell-cell adhesions.

Tumor spheroid sorting depends on E-cadherin expression

When investigating the correlation between sorting and differential E-cadherin upregulation, we observed that monoculture MCF10A Lifeact-RFP and MCF10A EGFP spheroids failed to sort when subjected to high matrix confinement (**Fig. 3A**), consistent with our hypothesis that sorting is linked to differences in cell–cell junction strength and stability. In the absence of alginate, MCF10A spheroids collectively invaded into the surrounding matrix when cultured in collagen gels with 10 mM $CaCl_2$ (**Fig. S6**). However, when embedded in collagen-alginate gels, MCF10A spheroids neither sorted nor invaded due to a lack of space in the composite hydrogel network. MCF10A E-cadherin levels decreased when cultured in hydrogels with high matrix stiffness (**Fig. 3B**), and a similar result was found when MCF10A cells were co-cultured with invasive mesenchymal cells (**Fig. 1B**). Thus, the sorting behavior observed in mixed spheroids is likely attributed to the difference in E-cadherin expression in breast cancer cells and normal breast epithelial cells.

Next, we asked if differences in E-cadherin expression regulated spheroid sorting. We knocked down E-cadherin (encoded by CDH1 gene) in MCF10A cells with inducible short hairpin RNA (shRNA) (**Fig. 3C**), as previously established (*6, 46*), generating shCDH1 KD cells.

Subsequently, MCF10A Lifeact-RFP and MCF10A shCDH1 KD co-culture spheroids were formed. The DAH proposes that strongly adhesive cells have a higher tissue surface tension and should preferentially adhere to each other and be enveloped by less adhesive cells. In agreement with the DAH, Lifeact-RFP cells clustered together at the core of the spheroid and were surrounded by layers of shCDH1 KD cells (**Fig. 3D**). In low-stiffness hydrogels, single cells detached from the spheroid and migrated into the surrounding matrix. Calculating the distance index for the distinct subpopulations in mixed spheroids generated a clear spatial separation between the different cell types in hydrogels with high matrix stiffness (**Fig. 3D**). According to the DAH, tumors behave like fluids, and surface tension-like effects hold shCDH1 KD cells and non-invasive cancer cells within the spheroid boundary (*16, 45*). Since these cells lack the ability to remodel ECM, they are unable to break through compartment boundaries and invade into the surrounding matrix. shCDH1 KD cells in co-culture exhibit the same sorting behavior observed in MCF7 cells, showing that the sorting process is regulated by the difference in E-cadherin expression between the co-culture cell types (**Fig. 3E**).

Sorted tumor spheroids unjam when matrix confinement is released

Having established that spheroid sorting is a result of increased matrix stiffness, we then investigated whether reducing matrix stiffness will permit invasion. Addition of the calcium chelator EGTA relieves crosslinked alginate by binding to and removing calcium ions from the crosslinked hydrogel, lowering matrix confinement. MCF10A Lifeact-RFP and MCF10A EGFP spheroids were used as a control and cultured in a medium with 10 mM $CaCl_2$ (**Fig. 4A**). Then, after 4 days of culture, the spheroids were treated with 0 or 5 mM EGTA. Fluorescence imaging 2 days after treatment showed that EGTA-treated control spheroids did not migrate into the surrounding matrix (**Fig. 4A**), indicating that EGTA treatment and reduced matrix stiffness do not initiate invasion in unsorted spheroids.

Next, we explored whether lowering matrix stiffness restores single-cell migration in MCF10A Lifeact-RFP and shCDH1 KD spheroids. We hypothesized that reversing the crosslinking reduces the confinement pressure responsible for spheroid sorting and the lack of cell migration into the matrix. Spheroids that were not treated with EGTA maintained a sorted state and were unable to invade. In EGTA-treated spheroids, after matrix stiffness was lowered, MCF10A Lifeact-RFP cells emerged from the spheroid core by rupturing the surrounding shCDH1 KD cell layer (**Fig. 4B**). The downregulation of E-cadherin corresponded with the upregulation of the mesenchymal marker vimentin (**Fig. 3C**), and vimentin expression in wildtype and shCDH1 KD cells was not influenced by confinement conditions (**Fig. S7**). As a benign epithelial cell line, MCF10A cells express low levels of vimentin (**Fig. 4A**), and as EMT is known to replace the keratin cytoskeleton with vimentin (*16*), the upregulation of vimentin observed in shCDH1 KD cells suggests a partial EMT.

Lowering matrix stiffness for sorted spheroids stimulates burst-like migration

To examine the migration of sorted spheroids upon lowering matrix stiffness, we performed timelapse imaging for a 24-h period following EGTA treatment. Thus far, we have analyzed spheroid compartmentalization at different time scales, however time-lapse sequences are critical to capturing cell speed and trajectories. Since EGTA chelates calcium at a 1:1 ratio, we tested

whether complete reversal of alginate crosslinking via the addition of 10 mM EGTA can further promote invasive behavior in co-culture spheroids. We generated two types of mixed spheroids: MCF10A Lifeact-RFP cells co-cultured with MCF10A EGFP or shCDH1 KD cells, and cultured the spheroids as previously described. On day 4, CaCl2 was removed from the medium, and the spheroids were treated with 0 or 10 mM EGTA for 1 h prior to imaging. As expected, wildtype spheroids failed to sort or migrate regardless of EGTA treatment (**Fig. S8**), whereas untreated mixed shCDH1 KD spheroids remained in a sorted state over the 24-h period (**Movie S1 and Fig. 5A**, top). At the spheroid core, where cell density is high, MCF10A Lifeact-RFP cells were jammed, whereas the surrounding shCDH1 KD cells were in a fluid-like yet confined state where fluctuations were contained by the barrier of high matrix confinement (**Fig. 5B**, top). In sorted spheroids, EGTA treatment reduced matrix stiffness, resulting in the dissemination of both cell types (**Fig. 5A and Fig. 5B**, bottom). Cells that were sorted to the spheroid core rapidly migrated outwards into the matrix with high motility (**Movie S1**).

The results presented thus far led us to hypothesize that the jamming—unjamming transition in 3D can be manipulated by modulating matrix stiffness. To statistically quantify the spatial organization of spheroids over time, we tracked individual MCF10A EGFP or MCF10A shCDH1 KD cells within the two types of mixed spheroids and calculated the change in distance index compared to the initial time point. The average distance travelled by shCDH1 KD cells away from the spheroid core in treated spheroids was significantly higher than in non-treated spheroids (**Fig. 5C**). Corresponding to the change in distance index (quantified as the difference between the mean distance index of cells for a given spheroid at a specified time point and the cells' initial mean distance index), EGTA treatment triggered and accelerated the migration of shCDH1 KD cells, whereas wildtype MCF10A cell motility was not impacted (**Fig. 5D**). Computation of the MSD revealed that EGTA treatment increased diffusivity for both cell types, however shCDH1 KD cells were more diffusive than their wildtype counterparts under the same conditions (**Fig. 5E**).

In theory and experiment, matrix confinement governs spheroid sorting and invasion

In order to understand the impact of matrix confinement on cellular invasion, we utilized a SPV model (*47, 48*), which mimics the dynamics of a heterogeneous tissue comprised of two different types of cells. Our simulations produced a well-sorted tissue, a result of setting differential adhesions parameters (*45, 49*) at cell-cell junctions (**Fig. S9**). Using the sorted tissue as a starting point, we manipulated the cell-medium contact tensions (τ) to study changes in cell sorting and invasion behaviors.

Fig. 6A presents representative snapshots illustrating cellular dispersion under conditions of high (left), medium (middle) and low (right) confinement stress (σ_n). These computational results suggest that cells in a well-sorted state manage to breach their boundaries and invade the ECM when confinement is diminished. In order to quantify this cellular dispersion of cells, we calculated a sorting index, defined as $I = 1 - N_{cluster}/N$, where $N_{cluster}$ is the count of isolated cell clusters and N is the total cell count for each cell type. In instances where the cells are fully sorted, each cell type would form a single cluster, resulting in a sorting index of $I \approx 1$. If the cells are dispersed, they form a mixed state, and each cell forms an isolated cluster unconnected from others, making the sorting index 0. The sorting index I, as a function of σ_n, is shown in

Fig. 6B. We can classify the behavior of the cell dispersion into three distinct phases. On the left of the white dashed line, the tissue experiences high confinement. Both A and B cells remain sorted with sorting index $I \approx 1$, corresponding to the left snapshot of **Fig. 6A** (marked by a star). The middle region, located between the white and black dashed lines, shows that the outer-layered red B cells have dispersed while the A cells stayed sorted, corresponding to the middle snapshot in **Fig. 6A** (marked by a circle). On the right of the black dashed line, the confinement has essentially vanished. The B cells have completely dispersed, and A cells begin to invade into the ECM, corresponding to the right snapshot in **Fig. 6A** (marked by a square).

Taken together, our results corroborate a model in which matrix stiffness promotes spheroid sorting in an adhesion-dependent manner and subsequently affects cellular unjamming processes (**Fig. 7**). Starting from a mixture of wildtype and shCDH1 KD spheroids encapsulated in collagen-alginate hydrogels, the addition of 10 mM $CaCl_2$ crosslinked the hydrogel, increasing matrix stiffness and confinement, which caused the spheroids to sort. The ability of cells to invade the surrounding matrix hinges on the competition between the forces generated by the cells and the resistance exerted by the matrix. Crosslinking the hydrogel amplifies its yield stress which hinders spheroid volume expansion (*50*). At the spheroid core where cell density is high, the adhesive wildtype cells cannot overcome the solid stress to intercalate positions with neighboring cells, leading to a jammed state (*51*). Conversely, shCDH1 KD cells at the spheroid boundary are not jammed, however the cells do not have sufficient energy to escape their compartment boundary. By reversing the crosslinking, the resistance to cell motion is removed, and the cells flow in an unjamming transition, reminiscent of the release of solid stress and elastic energy when the mechanical confining structure of an excised tumor is disrupted (*52*). 5 mM EGTA treatment partially reversed the crosslinking and correspondingly reduced ECM confinement. As a result, the compacted wildtype cells escaped from the spheroid core as a strand and broke through the surrounding layers of shCDH1 KD cells. When the crosslinking was completely reversed by the addition of 10 mM EGTA, the cells displayed collective and super-diffusive motion as they were pushed into the matrix with high velocity (**Movie S1**).

Discussion

In the present study, we show that tuning matrix stiffness regulates 3D spheroid sorting and collective cell migration into the ECM. ECM stiffness is known to play a significant role in cancer spread and metastasis in the body (*53–55*), and we first establish that single-cell cancer migration is restricted by matrix stiffness in collagen-alginate hydrogels, where collagen provides cell adhesion sites and alginate limits degradation by MMPs. We then demonstrate the sorting of non-invasive cancer cells and normal breast epithelial cells in co-culture spheroids. The DAH assumes that sorting is a result of cells rearranging to minimize interfacial tension, which is directly proportional to differences in cell-cell adhesion (*16, 22, 45*), and as a result, spheroid sorting achieves an equilibrium thermodynamic state (*45*). In hydrogels with minimal crosslinking, sorting does not occur, and the spheroid size increases after 4 days of culture as cells proliferate. However, in response to high matrix confinement, spheroids exhibit sorting behavior, and the pressure inside the spheroids increase. In monoculture spheroids of benign breast epithelial cells, E-cadherin expression is reduced in response to high matrix stiffness, suggesting that in the absence of mesenchymal cells to induce sorting and secrete enzymes to remodel the matrix, normal cells undergo a partial EMT to promote cell invasion (*56*). Normal

cells adapt to confined conditions by adjusting the properties of the cellular collective, however an undegradable hydrogel with low available ECM space presents a barrier that the cells are unable to overcome.

By crosslinking the hydrogel, the barrier to cell motion into the matrix is high, and the cells become jammed from the increased solid stress resulting from spheroid sorting. Stably downregulating E-cadherin identifies differences in intercellular adhesion as the primary driver of cell sorting and jamming. Spheroid sorting generates high local cell density in the core, where cells strengthen cell-cell adhesions, reduce cell volume, and exhibit jammed behavior. In this jammed state, cells are constrained by adhesion and the tension along cell-cell interfaces increases (22, 57, 58). One open question is how stress fluctuations driven by nearby cell division impact cell motility and structural rearrangements in the dense spheroid core (22). Core cells require energy to escape the boundary constraints imposed by their neighbors and the surrounding matrix. Less adhesive mesenchymal cells are relegated to the outer edges of the spheroid and exist in an unjammed state, where the cells can rearrange within the compartment boundary. Cell sorting, which requires cell-cell adhesions, leads to a buildup of pressure within the spheroid, and reducing matrix stiffness results in a pressure difference between the spheroid and the surrounding matrix. Burst-like cellular motion was recorded in soft collagen matrices (0.5 mg/ml) and attributed to the pressure increase within the cancer aggregate due to cellular swelling (30). In this study, we provide evidence that manipulating matrix stiffness directly impacts 3D spheroid sorting, as well as individual and collective cell invasion. In comparison to single-cell cancer migration, pressure-driven burst-like migration provides an outlet for cells confined by the spheroid boundary, and tumor cells can rapidly escape into the surrounding matrix.

Our findings present a composite hydrogel with mechanically tunable properties while maintaining a constant collagen concentration. Hydrogel stiffness is modified by the crosslinking of sodium alginate into calcium alginate and the reversal of crosslinking via the calcium chelator EGTA. In tumor development, cancer cells are confined by compartment boundaries until a late stage (16, 59). Primary tumors are encapsulated and confined by a basement membrane, and as the tumor cells proliferate, the tumor experiences high confinement stress and is driven to sort according to the DAH. In a degradable matrix, the highly proliferative cancer cells sorted to the spheroid boundary secrete MMPs to remodel the surrounding matrix, reducing ECM confinement. This decrease in confinement can instigate an unjamming transition, leading to a rapid spread of tumor cells. Our work presents new insights into the impact of matrix mechanical properties on the mechanisms of collective cell motion in the primary tumor and cancer migration towards distant metastatic sites as individual cells and as cellular aggregates.

Materials and Methods

Cell culture

The cell lines MCF10A, MCF7 and MDA-MB-231 were gifts from Sofia Merajver (University of Michigan). MCF10A cells were obtained from Gloria Heppner at the Michigan Cancer Foundation where the cell line was originally developed, MCF7 cells were originally obtained from ATCC, and MDA-MB-231 cells were obtained from Janet Price (MD Anderson Cancer Center) where the cell line was originally developed. MCF10A cells were cultured in DMEM/F12 medium (Gibco) supplemented with 5% horse serum, 20 ng/ml epidermal growth factor (EGF), 0.5 μg/ml hydrocortisone, 100 ng/ml cholera toxin and 10 μg/ml insulin. MCF7 and MDA-MB-231 cells were cultured in DMEM medium (Gibco) supplemented with 10% FBS. Cells were cultured in a humidified atmosphere containing 5% CO_2 at 37°C.

Stable cell lines

Stable cell lines expressing EGFP or Lifeact-RFP were generated via lentiviral transduction. EGFP lentivirus was produced from pSMPVW-EGFP obtained from Andrew Tai (University of Michigan). The lentiviral transfer plasmid pLVX-puro-RFP-Lifeact was cloned from RFP-Lifeact obtained from Gaudenz Danuser (UT-Southwestern). Lentiviruses were generated by transfecting HEK 293T cells with the transfer vector, psPAX2 packaging vector, and pMD2.G envelope vector. Viral supernatant was collected 48 h after transfection and used to infect the target cell lines. After 24 h, transduced cells were selected with 2 μg/mL puromycin for 5 days.

E-cadherin knockdown

MCF10A cells expressing inducible shRNA knockdown of E-cadherin was generated using a transfer plasmid provided by Valerie Weaver at UCSF (*46*). The transfer vector consisted of a modified pLKO.1 neo plasmid (Addgene) with expression of the shRNA sequences under control of 3× copies of the lac operator. The E-cadherin shRNA had the following sequence: 5' - GAACGAGGCTAACGTCGTAAT - 3'; scramble shRNA (Sigma #SHC002) had the following sequence: CCGGCAACAAGATGAAGAGCACCAACTCGAGTTGGTGCTCTTCATCTTGTTGTTTTT. MCF10A cells were transduced with E-cadherin shRNA or scramble non-targeting control shRNA for 48 h. shCDH1 and scramble cells were selected with 200 μg/ml G-418 (Sigma) and 2 μg/mL puromycin, respectively. E-cadherin knockdown was induced in shCDH1 cells by adding 200 μM isopropyl-β-D-thiogalactoside (IPTG; Sigma) 72 h prior to experiments.

Encapsulation of tumor spheroids in a collagen-alginate hydrogel

Inverse pyramidal PDMS microwells (AggreWell™, Stem Cell Technologies) were treated with anti-adherence rinsing solution (Stem Cell Technologies) to prevent cell adhesion. Cells were detached with 0.25% trypsin-EDTA (Life Technologies) and added to the microwells at a concentration of ~1,000 cells per microwell. For co-culture spheroids, MCF10A cells were mixed with MDA-MB-231, MCF7 or MCF10A shCDH1 KD cells at a 2:1 ratio. The cells were centrifuged at 300g for 5 min to aggregate the cells at the bottom of the microwells, and spheroids

formed overnight. The following day, the spheroids were harvested from the microwells and encapsulated in collagen-alginate hydrogels consisting of 3 mg/ml type I rat tail collagen (RatCol, Advanced BioMatrix) and 0.25% alginate (Nalgin HG, Tilley Chemical). Subsequently, the hydrogels were incubated at 37°C for 1 h for collagen polymerization, and then the encapsulated spheroids were imaged (day 0). Alginate crosslinking density and hydrogel stiffness were independently modulated through the concentration of $CaCl_2$ that was added to the cell culture medium after imaging on day 0. On day 4, the spheroids were imaged and then washed 1× with PBS. Afterward, the spheroids were either fixed for immunofluorescence staining or incubated with 0, 5 or 10 mM EGTA in PBS for 1 h to reverse the alginate crosslinking process. The solution was then replaced with fresh medium, and on day 6, the spheroids were fixed for immunofluorescence staining.

The Young's moduli of collagen-alginate hydrogels were measured after 4 days of incubation with 0, 5 or 10 mM $CaCl_2$ using a MicroSquisher (CellScale). A microbeam with a diameter of 203.2 μm, modulus of 411,000 MPa, and length of 59.5 mm was fixed to a 0.75 mm diameter glass bead and mounted to the vertical actuator. The samples were submerged in a solution of 1% BSA in PBS to reduce adhesion and compressed 3–4 times at different locations with a vertical displacement of 50–150 μm and at a loading rate of 1 μm/s. The Young's modulus was calculated using the linear slope of the stress-strain curve.

Confocal microscopy

Images were taken using an oil immersion UplanFL N 10 x/1.30 NA (Olympus) objective on an inverted microscope (Olympus IX-81) equipped with an iXON3 EMCCD camera (Andor Technology), National Instrument DAQ-MX controlled laser (Solamere Technology), and a Yokogawa CSU-X1 spinning disk confocal unit. Z-stack images of spheroids expressing EGFP or Lifeact-RFP and fluorescently labeled for DAPI were taken at excitation wavelengths of 488, 561 and 405 nm, respectively. Z-stack images of spheroids fluorescently labeled for E-cadherin, vimentin, or F-actin (by 670-phalloidin) were taken at an excitation wavelength of 640 nm.

Immunofluorescence staining and analysis

Spheroids embedded in hydrogels were washed with PBS and fixed with 4% paraformaldehyde for 1 h, washed with PBS, and permeabilized with 0.1% Triton X-100 in PBS for 4 h. Then, cells were washed with PBS and blocked with 3% BSA in PBS overnight at 4°C. The following morning, cells were incubated with a mouse anti-E-cadherin antibody at 1:500 (610181, BD Biosciences) or a rabbit anti-vimentin antibody at 1:400 (D21H3, Cell Signaling) in 3% BSA overnight at 4°C. Next, cells were washed 3× with PBS for 30 minutes per wash and incubated with DAPI and a secondary antibody in 3% BSA overnight at 4°C. Hydrogels were washed 3× with PBS as described above and imaged by spinning disk confocal microscopy.

To quantify cell sorting and the E-cadherin signal, the median slice from each z-stack was analyzed. Using the Fit Ellipse and Centroid options in Fiji, the coordinates of the center of the spheroid and the semi-major axis of the spheroid were extracted. Using the Multi-point tool, the coordinates of individual cells were recorded. As a measure of cell sorting, the distance index (DI) was calculated by dividing the cell's distance from the spheroid center by the spheroid's semi-

major axis (*17*). The E-cadherin signal at cell–cell contacts was quantified by measuring fluorescence intensity at the cell membrane and was calculated per cell by dividing the integrated density by the number of cells (indicated by DAPI) for each image.

Time-lapse imaging and analysis

For time-lapse imaging, images were acquired on an Olympus IX-81 inverted microscope, as previously described, or a Nikon-A1 laser scanning confocal microscope, equipped with an environmental chamber. Cell motility was recorded at 1-hour intervals over 18 or 24 h, with a 4 µm z-step. Individual cell trajectories were obtained using TrackMate in Fiji, where the LoG detector was used for spot detection with median filtering and subpixel localization, and the linear motion LAP tracker was used to link spots. After exporting the tracks as XML files, cell motility rates were calculated for each spheroid (*60*), and MSDs were analyzed using a MATLAB per-value class for MSD analysis of particle trajectories (*42*) and plotted in log-log scale, where the slope gives the diffusion coefficient α.

To calculate distance index from time-lapse sequences, z-stacks captured at 0, 8, 16 and 24 h were analyzed. Using the 3D projections of z-stacks taken at 0 h, the initial time point, the centroid location and semi-major axis of each spheroid were extracted in MATLAB via the "regionprops" function, which approximates spheroids as ellipses. Next, individual cell positions were acquired in TrackMate using the median slice of each z-stack. After exporting the cell coordinates as XML files, the distance index for each cell at all four time points was calculated using custom MATLAB code.

Western blotting

Samples were run on SDS–PAGE 4–20% Bio-Rad gels (15 well/15 µl). SDS-PAGE gels were run at a constant 120 V for 90 min. Proteins were transferred to a nitrocellulose membrane using the iBlot transfer system and the membrane was blocked in 5% milk in TBS-T for 1 h at room temperature. Blots were incubated with a primary rabbit GAPDH antibody at 1:1000 (D16H11, Cell Signaling), a mouse anti-E-cadherin antibody at 1:2000 (610181, BD Biosciences), and a primary rabbit anti-vimentin antibody at 1:1000 (D21H3, Cell Signaling) in 5% BSA in TBS-T overnight at 4 °C. GAPDH was used as a loading control for quantifying relative gene expression. Blots were washed 3× with TBS-T, incubated with secondary antibodies for 1 h at room temperature, and then washed again with TBS-T as described above. Western blots were imaged using an Azure Biosystems Sapphire System.

Statistical analysis

Statistical analysis was carried out in Origin and performed with one-way ANOVA followed by Tukey post-hoc multiple comparisons test. Results were collected from three independent experiments and data from individual cells or spheroids were plotted as mean ± S.E. or shown as boxplots, depending on the experiment. Statistical significance was denoted by asterisks in the figure panels, with $* = p < 0.05$, $** = p < 0.01$, $*** = p < 0.001$.

Self-Propelled Voronoi (SPV) model of a heterogeneous tissue

To investigate how cells behave invasively under different confinement levels, we use the recently developed SPV model (*47, 48*) In the SPV model, the basic degrees of freedom are the set of 2D cell centers r_i and cell shapes are given by the resulting Voronoi tessellation. The complex biomechanics that govern intracellular and intercellular interactions can be coarse-grained (*61–67*) and expressed in terms of a mechanical energy functional for individual cell shapes.

$$E = \frac{1}{2} \sum_{i=1}^{N} [K_A(A_i - A_0)^2 + K_P(P_i - P_0)^2] + 2 \sum_{<ij>} \lambda_{ij} L_{ij}. \qquad (1)$$

The SPV energy functional is quadratic in both cell areas (A_i) with modulus K_A and cell perimeters (P_i) with modulus K_P. The parameters A_0 and P_0 set the preferred values for area and perimeter, respectively. To simulate a heterogeneous tissue (*68*), we have a linear tension term in the energy function Eq. (1). λ_{ij} is the junctional tension shared by cells i and j with contact edge length L_{ij}. In a heterogeneous tissue with two types of cells, λ_{ij} is determined by the cell type of i and j. For example, in a tissue with two cell types A and B, we can define tensions as τ_{AA}, τ_{BB} and τ_{AB} for A-A, B-B and A-B cell contacts.

The deformation of the actin-myosin cortex concentrated near the cell membrane is mainly responsible for changes to cell perimeters. After expanding Eq. (1), the term $\frac{1}{2} K_P P_i^2$ corresponds to the elastic energy associated with deforming the cortex. The linear term in cell perimeter, $-K_P P_0 P_i$, and $\lambda_{ij} L_{ij}$ represent the effective line tension in the cortex and gives rise to a 'preferred perimeter' P_0. The value of P_0 can be decreased by upregulating the contractile tension in the cortex (*63, 64, 67*) and it can be increased by upregulating cell-cell adhesion. A_0 is set to be equal to the average area per cell and $\sqrt{A_0}$ is used as the unit of length. After non-dimensionalizing Eq. (1) by $\frac{1}{2} K_A A_0^2$ as the unit energy scale, we choose $K_P/(K_A A_0) = 1$ such that the perimeter and area terms contribute equally to the cell shapes. The choice of K_P does not affect the results presented. The preferred cell perimeter is rescaled $p_0 = P_0/\sqrt{A_0}$ and varied between 3.7 (corresponding to the perimeter of a regular hexagon with unit area) and 4.6 (corresponding to the perimeter of an equilateral triangle with unit area) (*67*). The ground states of Eq. 1 are amorphous tilings where the cells have approximately equal area, but varying perimeters as dictated by the preferred cell perimeter p_0. It has been shown that at a critical value of $p_0^* \approx 3.81$, the tissue collectively undergoes a solid-fluid transition (*67*). When $p_0 < p_0^*$, the cells must overcome finite energy barriers to rearrange and the tissue behaves as a solid, while above p_0^*, the tissue behaves as a fluid with a vanishing shear modulus as well as vanishing energy barriers for rearrangements (*67*).

The effective mechanical interaction force experienced by cell i is defined as $\boldsymbol{F}_i = -\boldsymbol{\nabla}_i E$. In addition to $\boldsymbol{F}_i$, cells can also move due to self-propelled motility. Just as in SPP models, we assign a polarity vector $\hat{\boldsymbol{n}}_i = (\cos\theta_i, \sin\theta_i)$ to each cell; along $\hat{\boldsymbol{n}}_i$ the cell exerts a self-propulsion force with constant magnitude v_0/μ, where μ is the mobility (the inverse of a frictional drag). Together these forces control the over-damped equation of motion of the cell center $\boldsymbol{r}_i$

$$\frac{d\boldsymbol{r}_i}{dt} = \mu \boldsymbol{F}_i + v_0 \widehat{\boldsymbol{n}}_i. \qquad (2)$$

The polarity is a minimal representation of the front/rear characterization of a motile cell (69). While the precise mechanism for polarization in cell motility is an area of intense study, here we model its dynamics as a unit vector that undergoes random rotational diffusion,

$$
\begin{aligned}
\partial_t \theta_i &= \eta_i(t), \\
\langle \eta_i(t)\eta_j(t') \rangle &= 2D_r \delta(t-t')\delta_{ij},
\end{aligned} \qquad (3)
$$

where θ_i is the polarity angle that defines $\widehat{\boldsymbol{n}}_i$, and $\eta_i(t)$ is a white noise process with zero mean and variance $2D_r$. The value of angular noise D_r determines the memory of stochastic noise in the system, giving rise to a persistence time scale $1/D_r$ for the polarization vector $\widehat{\boldsymbol{n}}$.

The mechanical state of cell i is characterized by a local stress tensor $\sigma_{\alpha\beta}^i$ given by (70, 71)

$$\sigma_{\alpha\beta}^i = -\Pi_i \delta_{\alpha\beta} + \frac{1}{2A_i} \sum_{l_{ij} \in i} \tau_{ij}^\alpha l_{ij}^\beta, \qquad (4a)$$

$$\Pi_i = -\frac{\partial E}{\partial A_i}, \quad \tau_{ij} = \frac{\partial E}{\partial \boldsymbol{l}_{ij}}, \qquad (4b)$$

where $\tau_{ij} = \tau_{ij}\widehat{\boldsymbol{l}}_{ij}$ is the edge tension shared by cell i and j with $\widehat{\boldsymbol{l}}_{ij} = \boldsymbol{l}_{ij}/|\boldsymbol{l}_{ij}|$, and Π_i is the hydrostatic cellular pressure. Here $i, j, \dots$ are cell labels, and α, β denote Cartesian components. Both the tension along the edge and the intracellular pressure force perpendicularly to an edge contribute to the mechanical force balance at every vertex for a solid tissue (72). In our simulations, the instantaneous tensions and pressures can be calculated based on Eq. (4b),

$$\tau_{ij} = K_P\big[(P_i - P_0) + (P_j - P_0)\big] + 2\lambda_{ij}, \quad \Pi_i = -K_A(A_i - A_0), \qquad (5)$$

where P_i is the perimeter and A_i is the area of cell i respectively. The tissue stress is related to the cellular stress as

$$\sigma_{\alpha\beta} = \frac{1}{A_T} \sum_i A_i \, \sigma_{\alpha\beta}^i, \qquad (6)$$

where A_T is the area of the tissue. The tissue compressive stress is the trace of the stress tensor $\sigma_n = (\sigma_{xx} + \sigma_{yy})/2$.

We simulate tissues containing two cell types (A and B) under periodic boundary condition. Each cell type has $N_A = N_B = 72$ cells. To initialize the simulation, a set of random cell centers are generated. Each cell is also randomly assigned a cell index and cell type label, A or B. $A_0 = 1$, $P_0 = 4.2$ and motility $v_0 = 0.3$ are set to be constant values for all cells throughout the

simulations. The cell shapes are obtained via Voronoi tessellations based on cell centers at each time step of the simulation. Therefore, the initial configuration is an amorphous tissue with cells A and B randomly mixed.

Junctional tensions are defined based on the types of neighboring cells, τ_{AA}, τ_{BB} and τ_{AB} for A-A, B-B, and A-B cell contacts. In accordance with prior studies of cell sorting and the differential adhesion hypothesis (45, 49), we set $\tau_{AB} > \frac{\tau_{AA}+\tau_{BB}}{2}$ to obtain an engulfed state showing in **Fig. S9**.

Subsequently, we used the engulfed configuration as the starting state and manipulate the contact tensions between cells and medium τ_{AM} and τ_{BM}, to investigate the effects of confinement on cell invasion. We solved eq. (2) using Euler's method by running 2 x 10^5 steps with time interval $\Delta t = 0.01$. To quantify the cell invasion, we calculated the sorting index $I_A = 1 - N_{A\ cluster}/N_A$ for A cells and $I_B = 1 - N_{B\ cluster}/N_B$ for B cells under changing confinements. Here, $N_{A\ cluster}$ means the total number of isolated clusters of A cells. When the state is well sorted, there is only one A or B cell cluster, and the sorting index is $I \approx 1$. At low confinement, cells are invading into the medium to form a mixed configuration, therefore the sorting index is $I \approx 0$.

Acknowledgements

The authors thank the Liu lab, particularly Sung-Won Hwang and Hossein Moghimianavval, for helpful discussions.

Funding: Work in A.P.L.'s laboratory has been supported by the National Institutes of Health (grant number R21GM134167) and the National Science Foundation (grant number CMMI-1927803). G.C. thanks support from the University of Michigan Rackham Merit Fellowship. X.L. and D.B. acknowledge support from the National Science Foundation (grant numbers DMR-2046683 and PHY-2019745), the Alfred P. Sloan Foundation, the Human Frontier Science Program, and the Northeastern University Discovery Cluster.

Author contributions: Conceptualization: G.C. and A.P.L. Methodology: G.C., X.L., S.C., and K.K. Investigation: G.C., S.-S.L., S.C., and K.K. Visualization: G.C. and X.L. Computational modeling: X.L. and D.B. Supervision: D.B. and A.P.L. Writing—original draft: G.C. and X.L. Writing—review & editing: G.C., S.-S.L., D.B., and A.P.L.

Data availability: The data required to reproduce these findings are available upon request.

References

1. H. Yamaguchi, J. Wyckoff, J. Condeelis, Cell migration in tumors. *Curr Opin Cell Biol*. **17**, 559–564 (2005).
2. F. Van Zijl, G. Krupitza, W. Mikulits, Initial steps of metastasis: Cell invasion and endothelial transmigration. *Mutat Res*. **728**, 23 (2011).
3. J. Fares, M. Y. Fares, H. H. Khachfe, H. A. Salhab, Y. Fares, Molecular principles of metastasis: a hallmark of cancer revisited. *Signal Transduction and Targeted Therapy 2020 5:1*. **5**, 1–17 (2020).
4. J. M. Tse, G. Cheng, J. A. Tyrrell, S. A. Wilcox-Adelman, Y. Boucher, R. K. Jain, L. L. Munn, Mechanical compression drives cancer cells toward invasive phenotype. *Proceedings of the National Academy of Sciences*. **109**, 911–916 (2012).
5. M. Luo, G. Cai, K. K. Y. Ho, K. Wen, Z. Tong, L. Deng, A. P. Liu, Compression enhances invasive phenotype and matrix degradation of breast Cancer cells via Piezo1 activation. *BMC Mol Cell Biol*. **23**, 1–17 (2022).
6. G. Cai, A. Nguyen, Y. Bashirzadeh, S.-S. Lin, D. Bi, A. P. Liu, Compressive stress drives adhesion-dependent unjamming transitions in breast cancer cell migration. *Front Cell Dev Biol*. **0**, 1983 (2022).
7. J. M. Northcott, I. S. Dean, J. K. Mouw, V. M. Weaver, Feeling Stress: The Mechanics of Cancer Progression and Aggression. *Front Cell Dev Biol*. **6**, 17 (2018).
8. H. Yan, D. Ramirez-Guerrero, J. Lowengrub, M. Wu, Stress generation, relaxation and size control in confined tumor growth. *PLoS Comput Biol*. **17**, e1009701 (2021).
9. A. F. Mertz, Y. Che, S. Banerjee, J. M. Goldstein, K. A. Rosowski, S. F. Revilla, C. M. Niessen, M. C. Marchetti, E. R. Dufresne, V. Horsley, Cadherin-based intercellular adhesions organize epithelial cell-matrix traction forces. *Proc Natl Acad Sci U S A*. **110**, 842–847 (2013).
10. T. Lecuit, A. S. Yap, E-cadherin junctions as active mechanical integrators in tissue dynamics. *Nature Cell Biology 2015 17:5*. **17**, 533–539 (2015).
11. O. Ilina, P. G. Gritsenko, S. Syga, J. Lippoldt, C. A. M. La Porta, O. Chepizhko, S. Grosser, M. Vullings, G. J. Bakker, J. Starruß, P. Bult, S. Zapperi, J. A. Käs, A. Deutsch, P. Friedl, Cell–cell adhesion and 3D matrix confinement determine jamming transitions in breast cancer invasion. *Nature Cell Biology 2020 22:9*. **22**, 1103–1115 (2020).
12. Y. Kang, J. Massagué, Epithelial-mesenchymal transitions: Twist in development and metastasis. *Cell*. **118**, 277–279 (2004).
13. J. F. Lima, S. Nofech-Mozes, J. Bayani, J. M. S. Bartlett, EMT in Breast Carcinoma—A Review. *Journal of Clinical Medicine 2016, Vol. 5, Page 65*. **5**, 65 (2016).
14. D. Hanahan, R. A. Weinberg, The Hallmarks of Cancer. *Cell*. **100**, 57–70 (2000).
15. D. P. Tabassum, K. Polyak, Tumorigenesis: it takes a village. *Nature Reviews Cancer 2015 15:8*. **15**, 473–483 (2015).
16. S. Pawlizak, A. W. Fritsch, S. Grosser, D. Ahrens, T. Thalheim, S. Riedel, T. R. Kießling, L. Oswald, M. Zink, M. L. Manning, J. A. Käs, Testing the differential adhesion hypothesis across the epithelial−mesenchymal transition. *New J Phys*. **17**, 083049 (2015).

17. L. Perrin, E. Belova, B. Bayarmagnai, E. Tüzel, B. Gligorijevic, Invadopodia enable cooperative invasion and metastasis of breast cancer cells. *Communications Biology 2022 5:1*. **5**, 1–14 (2022).

18. G. F. Le Bras, K. J. Taubenslag, C. D. Andl, The regulation of cell-cell adhesion during epithelial-mesenchymal transition, motility and tumor progression. *Cell Adh Migr*. **6**, 365 (2012).

19. L. Atia, J. J. Fredberg, N. S. Gov, A. F. Pegoraro, Are cell jamming and unjamming essential in tissue development? *Cells & Development*. **168**, 203727 (2021).

20. M. Sadati, N. Taheri Qazvini, R. Krishnan, C. Y. Park, J. J. Fredberg, Collective migration and cell jamming. *Differentiation*. **86**, 121–125 (2013).

21. L. Oswald, S. Grosser, D. M. Smith, J. A. Käs, Jamming transitions in cancer. *J Phys D Appl Phys*. **50**, 483001 (2017).

22. E. Lawson-Keister, M. L. Manning, Jamming and arrest of cell motion in biological tissues. *Curr Opin Cell Biol*. **72**, 146–155 (2021).

23. W. J. Polacheck, I. K. Zervantonakis, R. D. Kamm, Tumor cell migration in complex microenvironments. *Cell Mol Life Sci*. **70**, 1335 (2013).

24. V. Salvatore, G. Teti, S. Focaroli, M. C. Mazzotti, A. Mazzotti, M. Falconi, The tumor microenvironment promotes cancer progression and cell migration. *Oncotarget*. **8**, 9608 (2017).

25. X. Trepat, M. R. Wasserman, T. E. Angelini, E. Millet, D. A. Weitz, J. P. Butler, J. J. Fredberg, Physical forces during collective cell migration. *Nature Physics 2009 5:6*. **5**, 426–430 (2009).

26. A. Huttenlocher, A. R. Horwitz, Integrins in Cell Migration. *Cold Spring Harb Perspect Biol*. **3**, 1–16 (2011).

27. C. M. Lo, H. B. Wang, M. Dembo, Y. L. Wang, Cell Movement Is Guided by the Rigidity of the Substrate. *Biophys J*. **79**, 144–152 (2000).

28. A. Saez, M. Ghibaudo, A. Buguin, P. Silberzan, B. Ladoux, Rigidity-driven growth and migration of epithelial cells on microstructured anisotropic substrates. *Proc Natl Acad Sci U S A*. **104**, 8281–8286 (2007).

29. M. R. Ng, A. Besser, G. Danuser, J. S. Brugge, Substrate stiffness regulates cadherin-dependent collective migration through myosin-II contractility. *Journal of Cell Biology*. **199**, 545–563 (2012).

30. S. Raghuraman, A. S. Schubert, S. Bröker, A. Jurado, A. Müller, M. Brandt, B. E. Vos, A. D. Hofemeier, F. Abbasi, M. Stehling, R. Wittkowski, J. Ivaska, T. Betz, Pressure Drives Rapid Burst-Like Coordinated Cellular Motion from 3D Cancer Aggregates. *Advanced Science*. **9**, 2104808 (2022).

31. B. Sun, The mechanics of fibrillar collagen extracellular matrix. *Cell Rep Phys Sci*. **2** (2021), doi:10.1016/j.xcrp.2021.100515.

32. C. Liu, D. Lewin Mejia, B. Chiang, K. E. Luker, G. D. Luker, Hybrid collagen alginate hydrogel as a platform for 3D tumor spheroid invasion. *Acta Biomater*. **75**, 213–225 (2018).

33. T. Hu, A. C. Y. Lo, Collagen–Alginate Composite Hydrogel: Application in Tissue Engineering and Biomedical Sciences. *Polymers (Basel)*. **13** (2021), doi:10.3390/POLYM13111852.

34. A. Jabłońska-Trypuć, M. Matejczyk, S. Rosochacki, A. J. Jabłon´, J.-T. Trypuc´, Matrix metalloproteinases (MMPs), the main extracellular matrix (ECM) enzymes in collagen degradation, as a target for anticancer drugs. *https://doi.org/10.3109/14756366.2016.1161620*. **31**, 177–183 (2016).

35. S. Lagies, M. Schlimpert, S. Neumann, A. Wäldin, B. Kammerer, C. Borner, L. Peintner, Cells grown in three-dimensional spheroids mirror in vivo metabolic response of epithelial cells. *Communications Biology 2020 3:1*. **3**, 1–10 (2020).

36. K. Białkowska, P. Komorowski, M. Bryszewska, K. Miłowska, Spheroids as a Type of Three-Dimensional Cell Cultures—Examples of Methods of Preparation and the Most Important Application. *Int J Mol Sci*. **21**, 1–17 (2020).

37. S. Nam, J. Lee, D. G. Brownfield, O. Chaudhuri, Viscoplasticity Enables Mechanical Remodeling of Matrix by Cells. *Biophys J*. **111**, 2296–2308 (2016).

38. Y. Shen, B. U. S. Schmidt, H. Kubitschke, E. W. Morawetz, B. Wolf, J. A. Käs, W. Losert, Detecting heterogeneity in and between breast cancer cell lines. *Cancer Convergence 2020 4:1*. **4**, 1–11 (2020).

39. M. H. Lee, P. H. Wu, J. R. Staunton, R. Ros, G. D. Longmore, D. Wirtz, Mismatch in Mechanical and Adhesive Properties Induces Pulsating Cancer Cell Migration in Epithelial Monolayer. *Biophys J*. **102**, 2731 (2012).

40. C. Liu, M. Li, Z. X. Dong, D. Jiang, X. Li, S. Lin, D. Chen, X. Zou, X. D. Zhang, G. D. Luker, Heterogeneous microenvironmental stiffness regulates pro-metastatic functions of breast cancer cells. *Acta Biomater*. **131**, 326–340 (2021).

41. H. T. Nia, L. L. Munn, R. K. Jain, Physical traits of cancer. *Science (1979)*. **370** (2020), doi:10.1126/SCIENCE.AAZ0868/ASSET/5D0A72D9-30DE-4D81-96F5-8D7E0B0B58B2/ASSETS/GRAPHIC/370_AAZ0868_F3.JPEG.

42. N. Tarantino, J. Y. Tinevez, E. F. Crowell, B. Boisson, R. Henriques, M. Mhlanga, F. Agou, A. Israël, E. Laplantine, Tnf and il-1 exhibit distinct ubiquitin requirements for inducing NEMO-IKK supramolecular structures. *Journal of Cell Biology*. **204**, 231–245 (2014).

43. S. Grosser, J. Lippoldt, L. Oswald, M. Merkel, D. M. Sussman, F. Renner, P. Gottheil, E. W. Morawetz, T. Fuhs, X. Xie, S. Pawlizak, A. W. Fritsch, B. Wolf, L. C. Horn, S. Briest, B. Aktas, M. L. Manning, J. A. Kas, Cell and Nucleus Shape as an Indicator of Tissue Fluidity in Carcinoma. *Phys Rev X*. **11**, 011033 (2021).

44. W. Kang, J. Ferruzzi, C. P. Spatarelu, Y. L. Han, Y. Sharma, S. A. Koehler, J. A. Mitchel, A. Khan, J. P. Butler, D. Roblyer, M. H. Zaman, J. A. Park, M. Guo, Z. Chen, A. F. Pegoraro, J. J. Fredberg, A novel jamming phase diagram links tumor invasion to non-equilibrium phase separation. *iScience*. **24**, 103252 (2021).

45. R. A. Foty, M. S. Steinberg, The differential adhesion hypothesis: a direct evaluation. *Dev Biol*. **278**, 255–263 (2005).

46. J. M. Muncie, N. M. E. Ayad, J. N. Lakins, X. Xue, J. Fu, V. M. Weaver, Mechanical Tension Promotes Formation of Gastrulation-like Nodes and Patterns Mesoderm Specification in Human Embryonic Stem Cells. *Dev Cell*. **55**, 679-694.e11 (2020).

47. D. Bi, X. Yang, M. C. Marchetti, M. L. Manning, Motility-driven glass and jamming transitions in biological tissues. *Phys Rev X*. **6**, 021011 (2016).

48. D. M. Sussman, cellGPU: Massively parallel simulations of dynamic vertex models. *Comput Phys Commun*. **219**, 400–406 (2017).

49. M. S. Steinberg, Differential adhesion in morphogenesis: a modern view. *Curr Opin Genet Dev*. **17**, 281–286 (2007).

50. I. Gladukh, M. Podorozhna, Study of structural and mechanical properties of sodium alginate gels. *EUREKA: Health Sciences*, 82–89 (2021).

51. W. Lee, N. Kalashnikov, S. Mok, R. Halaoui, E. Kuzmin, A. J. Putnam, S. Takayama, M. Park, L. McCaffrey, R. Zhao, R. L. Leask, C. Moraes, Dispersible hydrogel force sensors reveal patterns of solid mechanical stress in multicellular spheroid cultures. *Nature Communications 2019 10:1*. **10**, 1–14 (2019).

52. H. T. Nia, H. Liu, G. Seano, M. Datta, D. Jones, N. Rahbari, J. Incio, V. P. Chauhan, K. Jung, J. D. Martin, V. Askoxylakis, T. P. Padera, D. Fukumura, Y. Boucher, F. J. Hornicek, A. J. Grodzinsky, J. W. Baish, L. L. Munn, R. K. Jain, Solid stress and elastic energy as measures of tumour mechanopathology. *Nature Biomedical Engineering 2016 1:1*. **1**, 1–11 (2016).

53. V. Gkretsi, T. Stylianopoulos, Cell Adhesion and Matrix Stiffness: Coordinating Cancer Cell Invasion and Metastasis. *Front Oncol*. **8**, 145 (2018).

54. L. Wullkopf, A. K. V. West, N. Leijnse, T. R. Cox, C. D. Madsen, L. B. Oddershede, J. T. Erler, Cancer cells' ability to mechanically adjust to extracellular matrix stiffness correlates with their invasive potential. *Mol Biol Cell*. **29**, 2378 (2018).

55. J. Winkler, A. Abisoye-Ogunniyan, K. J. Metcalf, Z. Werb, Concepts of extracellular matrix remodelling in tumour progression and metastasis. *Nature Communications 2020 11:1*. **11**, 1–19 (2020).

56. M. Saitoh, Involvement of partial EMT in cancer progression. *The Journal of Biochemistry*. **164**, 257–264 (2018).

57. S. Garcia, E. Hannezo, J. Elgeti, J. F. Joanny, P. Silberzan, N. S. Gov, Physics of active jamming during collective cellular motion in a monolayer. *Proc Natl Acad Sci U S A*. **112**, 15314–15319 (2015).

58. L. Atia, D. Bi, Y. Sharma, J. A. Mitchel, B. Gweon, S. A. Koehler, S. J. Decamp, B. Lan, J. H. Kim, R. Hirsch, A. F. Pegoraro, K. H. Lee, J. R. Starr, D. A. Weitz, A. C. Martin, J. A. Park, J. P. Butler, J. J. Fredberg, Geometric constraints during epithelial jamming. *Nature Physics 2018 14:6*. **14**, 613–620 (2018).

59. E. Batlle, D. G. Wilkinson, Molecular Mechanisms of Cell Segregation and Boundary Formation in Development and Tumorigenesis. *Cold Spring Harb Perspect Biol*. **4** (2012), doi:10.1101/CSHPERSPECT.A008227.

60. G. E. Wheeler, A. Purkayastha, E. N. Bunker, D. M. Bortz, X. Liu, Protocol for Analysis and Consolidation of TrackMate Outputs for Measuring Two-Dimensional Cell Motility using Nuclear Tracking. *J Vis Exp*. **2021** (2021), doi:10.3791/62885.

61. T. Nagai, H. Honda, A dynamic cell model for the formation of epithelial tissues. *https://doi.org/10.1080/13642810108205772*. **81**, 699–719 (2009).

62. L. Hufnagel, A. A. Teleman, H. Rouault, S. M. Cohen, B. I. Shraiman, On the mechanism of wing size determination in fly development. *Proc Natl Acad Sci U S A*. **104**, 3835–3840 (2007).

63. R. Farhadifar, J. C. Röper, B. Aigouy, S. Eaton, F. Jülicher, The Influence of Cell Mechanics, Cell-Cell Interactions, and Proliferation on Epithelial Packing. *Current Biology*. **17**, 2095–2104 (2007).

64. D. B. Staple, R. Farhadifar, J. C. Röper, B. Aigouy, S. Eaton, F. Jülicher, Mechanics and remodelling of cell packings in epithelia. *The European Physical Journal E 2010 33:2*. **33**, 117–127 (2010).

65. A. G. Fletcher, M. Osterfield, R. E. Baker, S. Y. Shvartsman, Vertex Models of Epithelial Morphogenesis. *Biophys J*. **106**, 2291–2304 (2014).

66. D. Bi, J. H. Lopez, J. M. Schwarz, M. Lisa Manning, Energy barriers and cell migration in densely packed tissues. *Soft Matter*. **10**, 1885–1890 (2014).

67. D. Bi, J. H. Lopez, J. M. Schwarz, M. L. Manning, A density-independent rigidity transition in biological tissues. *Nat Phys*. **11**, 1074–1079 (2015).

68. X. Li, A. Das, D. Bi, Mechanical Heterogeneity in Tissues Promotes Rigidity and Controls Cellular Invasion. *Phys Rev Lett*. **123**, 058101 (2019).

69. A. Szabó, R. Ünnep, E. Méhes, W. O. Twal, W. S. Argraves, Y. Cao, A. Czirók, Collective cell motion in endothelial monolayers. *Phys Biol*. **7**, 046007 (2010).

70. S. Ishihara, K. Sugimura, Bayesian inference of force dynamics during morphogenesis. *J Theor Biol*. **313**, 201–211 (2012).

71. X. Yang, D. Bi, M. Czajkowski, M. Merkel, M. L. Manning, M. C. Marchetti, Correlating cell shape and cellular stress in motile confluent tissues. *Proc Natl Acad Sci U S A*. **114**, 12663–12668 (2017).

72. L. Yan, D. Bi, Multicellular Rosettes Drive Fluid-solid Transition in Epithelial Tissues. *Phys Rev X*. **9**, 011029 (2019).

Figures

Figure 1. 3D matrix confinement inhibits the migration of cancer cells in co-culture spheroids. (A) Schematic depicting a spheroid encapsulated in a collagen-alginate hydrogel. Adding Ca^{2+} to crosslink sodium alginate into calcium alginate increases matrix stiffness, leading to high matrix confinement. **(B)** Representative fluorescence images of MCF10A and MDA-MB-231 co-culture spheroids encapsulated in collagen-alginate hydrogels, imaged on days 0 and 4, and immunostained for E-cadherin and DAPI. On day 0, the spheroids were encapsulated and 0, 5 or 10 mM $CaCl_2$ was added. **(C)** Schematic depicting a MCF10A (red) and MDA-MB-231 (blue) co-culture spheroid embedded in a collagen-alginate hydrogel. Addition of Ca^{2+} increases confinement stress. **(D)** Boxplot of distance index for MDA-MB-231 cells in co-culture spheroids (with MCF10A cells) after 4 days of culture. **(E)** Boxplot of cell aspect ratio for MDA-MB-231 cells on day 4. **(F & G)** Mean square displacements (MSDs) of **(F)** MCF10A EGFP cells or **(G)** MDA-MB-231 EGFP cells in co-culture spheroids (with MCF10A Lifeact-RFP cells) plotted over an 18-h period. Each line represents the mean MSD for $n = 12$ spheroids. The plots are shown in log-log scale, and the power law exponent α is shown for each condition. **(H)** Effective diffusion coefficient is shown for MCF10A and MDA-MB-231 cells for $n = 12$ spheroids per condition. Scale bars are 90 μm. $* = p < 0.05$, $*** = p < 0.001$.

Figure 2. High confinement drives cell sorting in co-culture spheroids. (A) Fluorescence images of MCF10A and MCF7 co-culture spheroids encapsulated in collagen-alginate hydrogels and imaged on day 0 (day of encapsulation). 0, 5 or 10 mM CaCl$_2$ was added on day 0, and the spheroids were imaged again on day 4. Spheroids were immunostained for E-cadherin and stained for DAPI. **(B)** Schematic depicting a MCF10A (red) and MCF7 (blue) co-culture spheroid embedded in a collagen-alginate hydrogel. Under high matrix confinement, MCF7 cells sort to the periphery and MCF10A cells form a cluster at the spheroid core. **(C)** Boxplot of distance index for MCF10A and MCF7 cells after 4 days of culture (n = 12 spheroids per condition). **(D)** Boxplot of E-cadherin fluorescence per cell for MCF10A and MCF7 co-culture spheroids on day 4 (n = 12 spheroids per condition). **(E)** Boxplot of the corresponding relative adhesion ratio of MCF10A and MCF7 co-culture spheroids. Scale bars are 90 µm. $** = p < 0.01$, $*** = p < 0.001$.

Figure 3. Tumor spheroid sorting depends on E-cadherin expression. (A) Representative fluorescence images of MCF10A Lifeact-RFP and EGFP co-culture spheroids encapsulated in collagen-alginate hydrogels and imaged on day 0 (day of encapsulation) and day 4 (day of fixation). Spheroids were immunostained for E-cadherin and stained for DAPI. **(B)** Boxplot of E-cadherin fluorescence per cell for MCF10A Lifeact-RFP and EGFP spheroids in hydrogels with 0, 5 or 10 mM $CaCl_2$. **(C)** Western blot illustrating IPTG-induced shCDH1 KD in MCF10A cells and of vimentin expression in MCF10A scramble and shCDH1 KD cells. GAPDH was used as the loading control. **(D)** Representative fluorescence images of MCF10A Lifeact-RFP and shCDH1 KD mixed spheroids imaged on days 0 and 4. $CaCl_2$ was added on day 0. **(E)** Boxplot of E-cadherin fluorescence per cell for MCF10A Lifeact-RFP and shCDH1 KD subpopulations in co-culture spheroids ($n = 12$ spheroids per condition). Scale bars are 90 μm. $* = p < 0.05$, $** = p < 0.01$, $*** = p < 0.001$.

Figure 4. Sorted tumor spheroids unjam when matrix stiffness is lowered. (A & B) Representative fluorescence images of **(A)** MCF10A EGFP and **(B)** shCDH1 KD spheroids (co-cultured with MCF10A Lifeact-RFP cells) encapsulated in collagen-alginate hydrogels and imaged on day 0 (day of encapsulation), day 4, and day 6 (day of fixation). 0, 5 or 10 mM $CaCl_2$ was added on day 0. On day 4, the spheroids were incubated with 0 or 5 mM EGTA for 1 h, after which the solution was replaced with fresh medium, and the spheroids were cultured until day 6. Spheroids were immunostained for vimentin and stained for DAPI ($n = 12$ spheroids per condition). Scale bars are 90 µm.

Figure 5. The reversal of alginate crosslinking stimulates burst-like migration in sorted spheroids. (A) Timelapse of MCF10A Lifeact-RFP and shCDH1 co-culture spheroids over a 24-h period, starting on day 4 after incubation with 0 or 10 mM EGTA for 1 h, after which the solution was replaced with fresh medium prior to time-lapse imaging. **(B)** Corresponding tracked trajectories of MCF10A shCDH1 KD cells in spheroids treated with 0 mM EGTA (top) and 10 mM EGTA (bottom). **(C)** Boxplot of distance index for MCF10A EGFP or shCDH1 KD cells in co-culture spheroids (with MCF10A Lifeact-RFP cells) analyzed at 8-hour intervals over 24 h. A positive change in distance index indicates cell motion away from the spheroid core. **(D)** Boxplot of average cell motility for MCF10A EGFP or shCDH1 KD cells (n = 9–12 spheroids per condition). **(E)** MSDs for MCF10A EGFP or shCDH1 KD cells plotted over a 24-h period. Each line represents the mean MSD for n = 12 spheroids. The plots are displayed in log-log scale. Scale bars are 90 μm.

Figure 6. SPV simulations portraying a heterogeneous tissue with two cell types, blue A cells and red B cells. **(A)** Representative snapshots of cell invasion into the ECM under varying confinement levels. Left: high confinement prevents dispersion. Middle: dispersion of the outer-layered B cells. Right: both A and B cells invade under low confinement. The three snapshots are marked as star, circle, and square in panel **(B)**. **(B)** Cell sorting index I is plotted as a function of compressive stress σ_n. By downregulating σ_n, the cells could disperse into the ECM and the sorting index decreases. The dashed white and black lines denote the commencement of dispersion for B and A cells respectively. The invasion behavior bifurcates into three distinct regimes: (1) Red region to the left of the white dashed line indicates high compressive stress and a sorted tissue. (2) Blue region between white and black dashed lines signifies dispersed B cells and sorted A cells. (3) Green region to the right of the black dashed line represents vanishing compressive stress and unsorted A and B cells.

Figure 7. Tumor spheroid sorting and burst-like migration in a composite hydrogel with tunable stiffness. Summary depicting a spheroid generated from a mixture of cells with high cell-cell adhesion (red) and cells with low cell-cell adhesion (blue) on day –1, encapsulation of the spheroid in a collagen-alginate hydrogel on day 0 and sorting under high-confinement ECM on day 4. The rightmost panel depicts, on day 6, the spheroid sustaining the sorted state after 0 mM EGTA treatment (top), a strand-like cluster emerging from the spheroid core after 5 mM EGTA treatment (middle) and burst-like unjamming after 10 mM EGTA treatment (bottom).