Compositional editing of extracellular matrices by CRISPR/Cas9 engineering of human mesenchymal

stem cell lines

Sujeethkumar Prithiviraj [1,2], Karin Linderfalk [1,2], Sonia Ferveur [1,2], Alejandro Garcia Garcia [1,2], David

Hidalgo[1, 2], Ludvig Nilsén Falck [3], Agatheeswaran Subramaniam [3], Paul E Bourgine [1,2].

[1]Cell, Tissue & Organ engineering laboratory, BMC B11, 22184, Department of Clinical Sciences, Lund Stem

Cell Centre, Lund University, Lund, Sweden

[2]Wallenberg Centre for Molecular Medicine, Lund University, Lund, Sweden

[3]Division of Molecular Medicine and Gene Therapy, Lund Stem Cell Centre, Lund University, 22184 Lund,

Sweden

Abstract (250 words)

Tissue engineering strategies predominantly rely on the production of living substitutes, whereby

implanted cells actively participate in the regenerative process. Beyond cost and delayed graft availability,

the patient-specific performance of engineered tissues poses serious concerns on their clinical translation

ability. A more exciting paradigm consist in exploiting cell-laid, engineered extracellular matrices (eECM),

which can be used as off-the-shelf materials. Here, the regenerative capacity solely relies on the

preservation of the eECM structure and embedded signals to instruct an endogenous repair. We recently

described the possibility to exploit custom human stem cell lines for eECM manufacturing. In addition to

the conferred standardization, the availability of such cell lines opened avenues for the design of tailored

eECMs by applying dedicated genetic tools. In this study, we aim at demonstrating the possibility of

exploiting CRISPR/Cas9 as a high precision system for editing the composition and function of eECMs. To

this end, human mesenchymal stromal/stem cell (hMSC) lines were modified to knockout VEGF and

RUNX2 and assessed for their capacity to generate osteoinductive cartilage matrices. We report the

successful editing of hMSCs, subsequently leading to targeted VEGF and RUNX2-knockout cartilage

eECMs. Despite the absence of VEGF, eECMs retained full capacity to instruct ectopic endochondral

ossification. Conversely, RUNX2-edited eECMs exhibited impaired hypertrophy which resulted in delayed

bone formation in vivo. In summary, our approach can be harnessed to identify the necessary eECM

factors driving endogenous repair. Our work paves the road towards the compositional eECMs editing and

their exploitation in broad regenerative contexts.

Introduction

Extracellular matrices (ECMs) are complex networks of proteins providing tissue structural and mechanical support, but also acting as growth factor storing and presenting entities[1]. As such, ECMs are receiving increasing attention in tissue engineering as templates capable of guiding homeostasis, remodeling and regenerative processes[2,3,4].

ECMs can be derived from native tissue or organs (native ECMs, nECMs) by applying a decellularization step which effectively removes the cellular fraction. The resulting nECMs are commonly used as biomaterials in regenerative medicine[5,6], offering a natural biocompatible structure. However, they suffer from substantial batch-to-batch variation with their properties being largely affected by the tissue source and the decellularization process[5,6]. Importantly, while displaying a high level of biological complexity and fidelity, the composition of nECMs cannot be tailored to specific needs.

A valuable option emerged from recent advances in bioengineering which led to the development of synthetic ECMs (sECMs). These tunable materials are predominantly composed of biopolymers such as poly(lactic acid) (PLA), poly(glycolic acid) (PGA), poly(lactic co-glycolic acid) (PLGA) and Poly (ethylene glycol) (PEG), which can be functionalized with bioactive substances such as peptides, growth factors or enzymes[3,7,8,]. The possible modulation of sECM's composition and chemistry offers precise control over their mechanical properties, degradability, and temporal release of instructive molecules towards improved tissue repair. Despite holding great promises, yet their structure and function remain simplified compared to their native counterpart [9,10].

With the aim of combining high biological fidelity and design flexibility, engineered ECMs (eECMs) have become a credible alternative. Those consist in the exploitation of stem/progenitor populations capable of depositing ECMs under specific in vitro culture conditions[11,12,13,14], which can be subsequently isolated from the cellular fraction and exploited as a cell-laid product. Early studies were conducted using eECM derived from primary cells, exhibiting variable performance associated with the inter-donor variability[15,16]. Most recently, we demonstrated the possibility to standardize the production of eECMs through the engineering of dedicated human mesenchymal stromal/stem cell (hMSC) lines[17]. Precisely, the Mesenchymal Sword of Damocles – BMP2 (MSOD-B) line offered the generation of eECMs in the form of human cartilage templates[18]. Those cartilage templates can be further devitalized, lyophilized and stored as an *off-the-shelf* tissue, retaining remarkable bone formation capacity by instructing endochondral ossification[18,19].

The exploitation of cell lines as an unlimited cell source for eECM generation offers unprecedented standardization in graft production and performance. Meanwhile, it also consists of a robust cellular

platform facilitating their further genetic engineering, to achieve the production of eECMs tailored in

composition and function. Towards this objective, CRISPR/Cas9 appears as a versatile and efficient gene-

editing tool. While this technology has been extensively used for genetic screening or disease

modeling[20,21,22], the possibility to edit hMSCs and study the compositional impact on deposited eECMs has

not been investigated so far.

In this study, we aim at demonstrating that CRISPR/Cas9 can be applied as an editing tool for the

engineering of custom eECMs. As proof-of-principle, our strategy relies on the CRISPR/Cas9-guided editing

of the MSOD-B line for knocking out Vascular endothelial growth factor (VEGF) and Runt related

transcription factor 2 (RUNX2), respectively a key pro-angiogenic protein and transcription factor critically

involved in the endochondral ossification pathway. The resulting hMSC lines will be evaluated for their

capacity to generate hypertrophic cartilage in vitro and instruct in vivo bone formation as a cell-free and

lyophilized template. If successful, our study is expected to validate the use of CRISPR/Cas9 for eECMs

edited in composition, while providing a novel platform towards decoding the necessary molecular signals

driving effective tissue repair.

Results

CRISPR/Cas9 editing of hMSC lines lead to efficient VEGF knockout in cartilage tissues

VEGF is a known master regulator of angiogenesis[23] and a key mediator of endochondral ossification.

When reaching hypertrophy, chondrocytes highly express VEGF, prompting vasculature invasion and

subsequent osteoprogenitor recruitment. This was proven to be essential for cartilage template

remodeling into bone and bone marrow[24]. Here, we thus first aimed at engineering a hMSC line

CRISPR/Cas9-edited for VEGF knockout and evaluate the corresponding impact on cartilage and

endochondral bone formation (Figure 1A). To this end, specific guide RNAs (gRNAs) targeting different

regions of the VEGF gene but conserved across all isoforms of VEGF were designed based on a previously

established protocol[25]. Three gRNAs targeting exon 1 (VEGF_1.1, VEGF_1,2, VEGF1.3), one targeting exon

2 (VEGF_2.1), and one targeting exon 8 (VEGF_8.1) were designed (Figure 1B, Supplementary Figure 1A).

These gRNAs were cloned into the pU6-(BbsI)_CBh-Cas9-T2A-mCherry vector encoding the Streptococcus

pyogenes Cas9 (SpCas9) machinery. Following transfection in MSOD-B cells, single cell clones were sorted

based on the transient mCherry expression and expanded for characterization (Figure 1A). Out of 163

single clones, 14 could be successfully expanded (8.5 %). From these clones, five were retrieved from the

gRNA 1.1, six from gRNA 1.3 and three from gRNA 8.1. In order to assess a successful editing and directly

correlate it to a knockout of VEGF, an ELISA assay was performed to measure the concentration of VEGF

in the supernatant of expanded MSOD-B clones (Figure 1C). In non-edited cells (MSOD-B, control), 5000

pg/mL were secreted and detected by ELISA. From the successfully expanded clones, most of them

showed reduced but non-abolished secretion of VEGF. However, two clones exhibited undetectable levels

of VEGF, both resulting from the gRNA targeting the Exon1 of the VEGF gene. These clones were defined

as MSOD-BΔV1 and MSOD-BΔV2 and further characterized for their capacity to form cartilage.

To this end, clones were expanded and seeded on collagen scaffold and induced for three weeks towards

chondrogenic differentiation. As anticipated with the MSOD-B tissues, histological assessment revealed

the formation of a collagenous matrix (Masson's Trichrome) with cartilage features (Safranin-O, Figure 1D

and Supplementary Figure 1B). Similarly, a successful chondrogenic differentiation and deposition of

glycosaminoglycans could be observed in the MSOD-BΔV1 (Figure 1D) and MSOD-B ΔV2 (Supplementary

Figure 1B) constructs. A quantitative assessment (blyscan assay) confirmed the comparable content in

glycosaminoglycans in MSOD-B and VEGF-edited clones (Figure 1E, Supplementary Figure 1C).

Importantly, VEGF quantification in corresponding pellets validated the successful knockout of the

protein, barely detectable in the MSOD-BΔV1 and ΔV2 tissues (47.64 pg/pellet in edited clones versus

552.7 pg/pellet in MSOD-B, Figure 1F and Supplementary Figure 1D).

Taken together, this data indicates the successful generation of MSOD-B lines knocked-out in VEGF. The

MSOD-BΔV1 and MSOD-BΔV2 clones exhibited frank cartilage formation capacity with minimal level of

VEGF. This validates the use of CRISPR/Cas9 as a precision tool to edit the composition of cartilage tissue.

VEGF knockout cartilage tissues retain bone remodeling capacity despite reduced early-stage

vascularization

To verify the impact of the VEGF knockout on the graft capacity to undergo endochondral ossification,

cartilage grafts were implanted subcutaneously in an immunodeficient mouse model. Importantly, prior

to implantation, tissues were lyophilized using a pre-established protocol[18]. This allowed us to assess the

performance of the generated tissue itself, in line with the idea of developing off-the-shelf substitutes.

Samples were extracted after two and six weeks as early and late development timepoints. Since the two

clones exhibited similar in vitro tissue formation capacity, only the MSOD-BΔV1 was selected for in vivo

performance assessment. After two weeks in vivo, we first evaluated the angiogenic potential of tissues

by quantitative confocal microscopy imaging of 100 μm thick sections stained for CD31, a well-defined

marker for angiogenesis. This allowed us to evidence a dense vascular network in MSOD-B constructs,

covering the entirety of the grafts (Figure 2A). Instead, MSOD-BΔV1 displayed a more limited

vascularization, pre-dominant at tissue periphery (Figure 2A). Quantification confirmed these

observations with MSOD-B exhibiting a significantly higher volume of vessels per total section volume

(0.191 % versus 0.132 % for MSOD-B and MSOD-BΔV1 respectively, Figure 2B).

Using microtomography, we further assessed the amount of mineralized tissue formed in a temporal

fashion. At two weeks, the formation of a cortical ring of mineralized tissues could already be observed in

both MSOD-B and MSOD-BΔV1 tissues (Figure 2C). Quantifications revealed a similar bone/mineralized

volume normalized to the total volume of the graft (BV/TV, Figure 2D) with 0.17 % and 0.16 % in MSOD-

B and MSOD-BΔV1 samples respectively.   At the six-week timepoint, trabecular structures could be

observed in reconstructed 3D scans from both groups (Figure 2C). Remarkably, histological analysis

confirmed the similar development of the tissues with frank bone formation (Masson´s trichrome) already

at two weeks post-implantation and minimal remnants of cartilage (Safranin O) (Figure 2E). At six weeks

both samples remodeled into fully mature bone organs, characterized by presence of cortical and

trabecular structures as well as a bone marrow tissue filling the cavity (Figure 2E).

These results indicate that the absence of VEGF in cartilage tissue can delay the early vascularization of

MSOD-BΔV samples. However, this did not prevent nor impact the remodeling of the lyophilized grafts

into bone and bone marrow tissues indicating that VEGF is non-essential in order to efficiently instruct

endochondral ossification.

RUNX2 knockout does not prevent chondrogenic differentiation but impairs hypertrophy

We next investigated whether the composition and thus function of a graft could be modified by editing

transcriptional factors involved in mesenchymal cell differentiation. Using CRISPR/Cas9, we thus targeted

the RUNX2, a known master regulator particularly important for chondrocyte differentiation and

hypertrophy[26,27]. We designed gRNAs targeting the coding regions involved in cell signaling integration,

activation, and inhibition domain which are conserved in both isoforms of RUNX2 (Figure 3A,

Supplementary Figure 3A).

One gRNA was designed for targeting exon 2 (RUNX2_2.1), one targeting exon 5 (RUNX2_5.1), two

targeting exon 6 (RUNX2_6.1 and RUNX2_6.2) and one targeting exon 8 (RUNX2_8.1). Similar to the VEGF

set-up, gRNAs were transfected in MSOD-B cells together with a pU6-(BbsI)_CBh-Cas9-T2A-mCherry

plasmid to ensure transfection efficiency and single cell sorting of positive clones. Out of 385 single clones,

62 could be successfully expanded, corresponding to a 16.1% efficiency. From these clones, five were

derived from the RUNX2_5.1 gRNA, 18 from RUNX2_6.1, 15 from RUNX26.2 and 24 from RUNX2_8.1.

To identify successfully edited clones, we first screened for those exhibiting a decrease in their RUNX2

protein expression using intra cellular flow cytometry. Among the 62 clones, 17 displayed a reduced

RUNX2 pattern as compared to the MSOD-B control (Figure 3B and Supplementary Figure 3B) and were

further sent for sequencing analysis. This led to the identification of two successfully edited clones,

demonstrating a point mutation in the exon 6 of RUNX2 gene (Supplementary Figure 3C). To confirm the

knockout impact on the transcription factor structure, a Western Blot analysis was conducted on cellular

extracts of in vitro cultured cells. MSOD-B cells exhibited intact RUNX2 proteins of 52 - 62 kDa[28,29](Figure

3C). Instead, the RUNX2-edited cells displayed truncated versions of 32 - 42 kDa, consistent with the

expected mRNA shortening.

These two clones were defined as MSOD-BΔR1 and MSOD-BΔR2 and further assessed for their ability to

form cartilage in vitro. Following 3D chondrogenic differentiation, samples were processed for histological

analysis. The presence of cartilage structures embedded in a rich collagenous matrix could be observed in

all MSOD-B, MSOD-BΔR2 (Figure 3D) and MSOD-BΔR1 tissues (Supplementary Figure 3D). Quantification

of glycosaminoglycans revealed a similar content in all the groups (Figure 3E, Supplementary Figure 3E).

Using immunostaining combined with quantitative confocal microscopy, the possible impact of RUNX2-

editing on tissue hypertrophy was further investigated. First, Collagen Type II (COL2) staining confirmed

the similar distribution of cartilage matrix across MSOD-B, MSOD-BΔR1 and MSOD-BΔR2 samples (Figure

3F and Supplementary Figure 3F). However, we observed a clear distinction in the Collagen Type X (COLX)

expression pattern, a specific marker of hypertrophy which was hardly detectable in MSOD-BΔR tissues

(Figure 3F and Supplementary Figure 3F). Subsequent quantification confirmed a significant reduction of

COLX volume in MSOD-BΔR1 (0.46 %) and MSOD-BΔR2 (0.32 %) compared to MSOD-B (0.81 %) (Figure 3G,

Figure 3H, Figure 3I).

In summary, we here report the successful RUNX2 knockout in MSOD-B lines using CRISPR/Cas9. RUNX2

did not impair chondrogenesis but prevented the tissue hypertrophy, evidenced by residual COLX content

in engineered cartilages.

184   **RUNX2 knockout in cartilage tissues disrupts effective bone formation**

185   To assess the corresponding impact of RUNX2-edited cartilages on bone formation, MSOD-B tissues (as

186   control) and MSOD-BΔR1 were lyophilized and implanted subcutaneously in immunodeficient mice for

187   two to six weeks. From microtomography image reconstructions, we observed an evident reduction of

188   mineralization in MSOD-BΔR1 compared to MSOD-B (Figure 4A) already after two weeks. This qualitative

189   and visual difference in mineralization persisted after six weeks in vivo (Figure 4A). Subsequent

190   quantifications confirmed these observations with a clear reduction in BV/TV as early as week 2 (16.46 %

191   in MSOD-B and 7.01 % in MSOD-BΔR1) and persisting at week 6 (20.03% in MSOD-B and 4.25 % in MSOD-

192   BΔR1) (Figure 4B). Histological analysis revealed an early bone formation at two weeks in both samples,

193   but to a lower extent in the MSOD-BΔR1 group (Figure 4C). As anticipated, MSOD-B tissues underwent full

194   remodeling after six weeks in vivo. In sharp contrast, the MSOD-BΔR1 only displayed a partial maturation

195   with limited presence of bone and bone marrow.

196   Altogether, this indicates an incomplete remodeling of RUNX2 edited samples with significantly delayed

197   cortical and trabecular structure formation. This correlates with the impaired hypertrophic phenotype in

198   the corresponding in vitro samples.

199

200   **Discussion**

201   We here report the possibility to edit the composition and function of eECM by CRISPR/Cas9 engineering

202   of human mesenchymal lines. VEGF knockout led to successful in vitro formation of cartilage with targeted

203   protein depletion. Upon implantation, this impacted the graft vascularization onset but not the

204   endogenous instruction of the endochondral program. In turn, RUNX2 knockout prevented cartilage

205   hypertrophy in vitro, significantly delaying bone and bone marrow formation in vivo.

206   A clear interdependency of angiogenesis and osteogenesis occurs upon bone formation[30,31]. For this

207   reason, VEGF-enrichment has been naturally proposed as a strategy to accelerate or increase bone graft

208   vascularization[32,33]. Our study demonstrates that VEGF knocked-out cartilage templates retained full

209   osteoinductive potential in a challenging ectopic environment. Those results are in sharp contrast with

210   intramembranous strategies[34,35], including our previous work[17], whereby grafts remain insufficient in

211   promoting complete bone remodeling even upon VEGF-enrichment. This suggests that the first stage of

212   host progenitor recruitment by our eECM is not VEGF dependent, although subsequent tissue

213   vascularization and remodeling may be orchestrated in a second step by endogenous cell secretion. Other

pro-angiogenic proteins embedded in the matrix may also have compensated for the lack of VEGF, such

as BMP-2[18] known to stimulate endothelial cell proliferation, migration and differentiation[36,37].

Conversely, RUNX2 deletion was shown to fully prevent cartilage hypertrophy, in line with published

mouse models also reporting a lack of endochondral ossification and lethality at birth upon RUNX2

knockout[38,27]. Here, MSOD-BΔR cartilage templates still exhibited frank bone formation capacity, but with

cortical and trabecular structures largely reduced as compared to controls. Future work may clarify if this

strictly results from the absence of COLX, or if an additional specific cartilage matrix component (e.g.

matrix metalloproteinases) impaired the instruction of endochondral ossification.

CRISPR/Cas9 editing of human mesenchymal cells has previously been explored for gene and cell therapy

applications[20,21], for tailoring the immunomodulatory and/or differentiation capacity of engineered cells.

However, no studies have described the exploitation of editing strategies for the generation of eECMs,

whereby modified cells are absent from the final grafting product. Our work illustrate that this can be

achieved by direct targeting of secreted factors typically embedded upon ECM deposition, as

demonstrated with VEGF. Alternatively, we also propose the knockout of key transcription factors as a

strategy for custom eECM generation by impacting their tissue developmental/maturation stages.

A clear implication of our work lies in the possibility to decipher the necessary factors capable of

instructing de novo tissue formation. Those findings will be of high relevance for the design of eECMs

tailored in composition. Beyond bone repair, our study also bears high relevance in other regenerative

contexts. In fact, one could envision further preventing the in vivo remodeling of engineered cartilage

templates and obtain stable cartilage graft for joint repair[39,40]. This remains an open challenge in the

skeletal field, with bone marrow MSCs (BM-MSCs) cartilage systematically reaching hypertrophy and

subsequent ossification[41,42,43]. An exciting opportunity also lies in harnessing CRISPR/Cas9 for editing

eECMs and tuned their immunogenicity. Key inflammatory components could be turned down, leading to

improved efficacy of repair in line with the immuno-engineering principles[44,45].

Importantly, our study describes the exploitation of eECMs in a lyophilized form, thus conferring an off-

the-shelf storage solution. Together with the standardization of production conferred by stable cell

sources, our concept offers exciting translational opportunities. In fact, instrumental to this work is the

use of dedicated hMSC lines. The genetic modification of primary cells is laborious, and their limited

lifespan ex vivo challenges their selection, characterization and exploitation for tissue engineering

applications[46,47]. Here, the MSOD-B was harnessed as an unlimited cell source with robust differentiation

potential. Nonetheless, the editing of eECMs remains tedious in part due to the limited CRISPR/Cas9

efficiency and potential off-target effects, calling for a systematic clonal selection. In addition, while large

CRISPR/Cas9 screening can be performed in other stem cell systems[48,49], the critical cell mass required for effective cartilage formation affects parallelization and leads to limited throughput. Nonetheless, after the identification and characterization process, the resulting cell lines can be banked and used for unlimited tissue manufacturing.

The MSOD-B line remains the only human cell source capable of priming endochondral ossification by engineering living or cell-free grafts. This was demonstrated to be driven by the combined low dose of BMP-2 embedded in the tissue (~40 ng/tissue) together with glycosaminoglycans and other thousands of identified ECM proteins[18]. The BMP-2 amount is thus far below the typical amount used in sECMs approaches for effective osteoinduction, falling in the microgram to milligram range[18]. This is one key advantage of eECM graft, exhibiting a biological complexity that so far has not been matched by sECMs. Ideally, the two approaches are complementary as the editing of eECMs could inform on the necessary but sufficient factors driving effective regeneration. Those would in turn be embedded in a sECMs strategy and offer a fast and possibly cost-effective solution.

To conclude, the present work offers a platform for decoding factors involved in tissue regeneration and generate tailored eECM. Here, illustrated in the context of skeletal repair, our study may offer similar opportunities in other regenerative situations.

Acknowledgements

We express our gratitude to the following institutions and individuals for their invaluable support and contributions to this study: Lund University, Medical Faculty, FACS Facility (Anna Hammarberg), Cell and Gene Therapy core facility (Pia Johansson) and Imaging Facility at Lund Stem Cell Centre, as well as the Lund University Bioimaging Centre, for providing access to the X-ray CT system. The funding for this research was made possible by a Knut and Alice Wallenberg grant, the Medical Faculty at Lund University, the Swedish Research Council, the European Research Council (Starting grant hOssicle #948588 to P.E.B), and Region Skåne. Figures were generated using BioRender.com. Special thanks to Ani Grigoryan and Dimitra Zacharaki for their expertise and valuable insights regarding FACS experiments, and to Steven Dupard for his advice and guidance on the design of gRNAs and molecular techniques. Christian Hansen deserves our appreciation for providing the mcherry plasmid and offering valuable guidance and knowledge related to CRISPR-Cas9.

Materials and Methods:

Cell expansion

277 MSOD-B cells and their modified progeny were cultured in a humidified incubator at 37 °C and 5% CO_2

278 using complete medium consisting of α-minimum essential medium (αMEM) supplemented with 10%

279 fetal bovine serum, 1% HEPES, 1% sodium pyruvate, 1% penicillin-streptomycin-glutamine solution, and 5

280 ng/ml of fibroblast growth factor-2 (FGF-2) (all from Gibco). Cells were seeded at a density of 3200

281 cells/cm^2 until they reached 90% confluency. The medium was replaced twice a week.

Chondrogenic differentiation

MSOD-B cells and their modified progeny were harvested from culture flasks by adding Trypsin-EDTA

(0.25%) (Gibco) and subsequently seeded on cylindrical Collagen Type I scaffold (Avitene™ Ultrafoam™

Collagen Sponge, Davol) of 6 mm in diameter and 3 mm in thickness at a density of 2×10^6 cells per scaffold

in 12 well plates coated with 1 % agarose (Sigma). Tissue constructs were cultured for three weeks in

chondrogenic medium (DMEM supplemented with 1% penicillin-streptomycin-glutamine, 1% HEPES (1M),

1% sodium pyruvate (100 mM), 1% ITS (100x) (Insulin, Transferrin, Selenium) (all from Gibco), 0,47 mg/ml

linoleic acid (Sigma), 0.12% bovine serum albumin (25 mg/mL) (BSA) (Sigma), 0.1 mM ascorbic acid

(Sigma), 10^{-7} M dexamethasone (Sigma) and 10 ng/ml TGF-β3 (Novartis)). Media were replaced twice a

week.

Lyophilization

293 After three weeks of chondrogenic differentiation, the tissue constructs were rinsed twice with PBS 7.2

294 (without calcium/magnesium Gibco), snap frozen in liquid nitrogen for five minutes and then lyophilized

295 using a freeze dryer (-80 °C and 0.05 mbar) overnight. Thereafter, the lyophilized tissue constructs were

296 stored at 4 °C.

Transfection of MSOD-B cells with gRNAs

MSOD-B cells were seeded at a density of 400,000 cells per well in 12 well plates to reach a minimum of

80% confluency the following day. The medium was replaced before transfection. The transfection was

performed with a / ratio of 2 μL lipofectamine to 1 μg DNA. A DNA mix was prepared for each of the five

gRNAs and the two plasmid controls. DNA mixtures were composed of 1 μg of plasmid, 2 μL of P3000

reagent and 50 μL of OptiMEM (Thermo-Fischer). A lipofectamine cocktail was prepared for all DNA

mixtures consisting of 24 μL of lipofectamine 3000 in 400 μL of OptiMEM. Lipofectamine and the DNA

mixtures were added at a 1:1 ratio. After 48h, cells were analyzed and mCherry positive clones were FACS

sorted as single cells in 96-well plates using ARIAIII (BD Biosciences). Successfully expanded clones were

then further characterized.

ELISA

VEGF protein content was measured in supernatant collected from cells seeded at 100´000 in T175 flask

and cultured for 3 days. Content from engineered cartilage tissues was assessed following digestion in

RIPA buffer. The Quantikine ELISA kit for Human VEGF-A Immunoassay from the R&D System was used

according to the manufacturer instructions to determine protein concentration.

Intracellular flow cytometry

MSOD-B and MSOD-B ΔRUNX2 cells were trypsinized, fixed and permeabilized using the

Fixation/Permeabilization Kit (BD Biosciences). Following a blocking step in 10% normal donkey serum

(Sigma), cells were stained with a primary antibody against RUNX2 (Rabbit anti-human, Thermo-Fischer

PA5-82787) for one hour at room temperature. After primary antibody incubation, cells were washed and

stained with an Allophycocyanin (APC) labeled secondary antibody (Donkey anti-rabbit IgG DyLight™ 649,

Biolegend 406406) for 30-45 minutes at room temperature in 2% normal donkey serum. The Control

samples consisted of unstained cells (negative control) and cells incubated only with the secondary

antibody (secondary Ab control). Data were recorded on a BD LSRFortessa™ Cell Analyzer (BD

Biosciences). FCS files were analyzed using the FlowJo™ software (FlowJo LLC, 10.5.3, BD Biosciences).

Western blotting

MSOD-B and MSOD-B ΔRUNX2 cells were trypsinized and washed with ice cold PBS twice and lysed on ice

for 10 min in RIPA buffer (#10017003, Thermo Fisher Scientific) supplemented with 1× proteinase and

phosphatase inhibitor cocktail (#78440, Thermo Fisher Scientific). The lysates were centrifuged at 16,

000g for 15 min +4 °C, and the supernatants were collected. Sample buffer (Laemmli buffer (#161-0737,

BioRad) supplemented with 5% 2-mercaptoethanol, 1× proteinase and phosphatase inhibitor cocktail

(#78440, Thermo Fisher Scientific) was added to the supernatant at 1:1 ratio. Samples were boiled at 95

°C for 5 minutes and stored at −80 °C or kept on ice until gel loading. Proteins were separated using Bolt

gels according to manufacturer's protocol (#NW04122, #B0002, Thermo Fisher Scientific). iBlot2 system

was used to transfer the proteins on polyvinylidene fluoride membrane (PVDF) membrane according to

manufacturer's protocol (#IB24001, Thermo Fisher Scientific). PVDF membrane was washed once in 1×

PBST buffer (#28352, Thermo Fisher Scientific) and blocked in 2% blocking solution (#10156414, Thermo

Fisher Scientific) for 1 h at room temperature. Membranes were incubated overnight at +4 °C with primary

antibodies at recommended concentrations in 1% blocking solution. Membranes were washed three

times (5 min for each wash) with 1× PBST buffer, and secondary HRP-conjugated antibodies in 1% blocking

solution were added to the membranes at 1:5000 concentration for 1 h incubation at room temperature.

Membranes were washed three times with 1× PBST and proteins were detected by chemiluminescence

according to manufacturer's protocol (#RPN2232, Thermo Fisher Scientific). The following antibodies

were used. primary antibodies: RunX2 (D1L7F - 12556) from Cell Signaling Technology and Actin (612656)

is from Becton Dickinson. The secondary antibodies were anti-Mouse (GENA931) from Sigma-Aldrich, anti-

Rabbit (NA9340V) from Thermo Fisher Scientific.

Biochemical analysis (GAG analysis)

Lyophilized tissue constructs were digested by overnight incubation in 0.5 ml of Proteinase K solution

(Proteinase K 1 mg/mL, Sigma; pepstatin A 10 ug/ml, Sigma; 1 mM EDTA, Sigma; Iodoacetamide 100 mM;

Tris 5 0mM) at pH 7.6 and 56 °C. The GAG content of digested samples was analyzed using

Glycosaminoglycan Assay Blyscan kit (Biocolor) following the manufacturer instruction.

Mice

FoxN1 KO BALB/C (nude mice) 6–8-weeks old, were obtained from Charles River Laboratories. All mouse

experiments and animal care were performed in accordance with the Lund University Animal Ethical

Committee guidelines (ethical permit #M15485–18). Mice were housed at a 12-hour light cycle in

individually ventilated cages at a positive air pressure and constant temperature. Mice were fed with

autoclaved diet and water ad libitum. During the implantation procedure, anaesthesia was performed

with 2-3 % Isoflurane (Attane). The mice were kept on a heating pad during the procedure to avoid the

heat loss.

Micro-CT scanning

In vivo samples were explanted and fixed overnight with 4% formaldehyde before ex vivo micro-CT

analysis using a U-CT system (MILABS, Netherland) equipped with a tungsten x-ray source at 50 kV and

0.21 mA. Volumes were reconstituted at 10 μm isotropic voxel size and were saved as. nii files. For total

volume (TV) analysis, each sample was assessed with Blender (v2.82a, Netherland). First, the .nii file was

opened in Fiji software, applying default parameters, and accessing the 3D Viewer Plugin. The threshold

level was adjusted to identify the Ossicle, and the resulting surface was saved as .obj and .mtl files in

Blender. Subsequently, the .obj file was imported into Blender, followed by remeshing and centering the

sample within the cage. The "shrinkwrap" volume dialogue box was utilized to position the sample within

the network. The volume was then calculated and obtained in cm^3. For bone volume (BV) analysis, the

highly mineralized tissue volume was quantified using Seg3D (v2.2.1, NIH, NCRR, Science Computing and

Imaging Institute (SCI)). The .nii file was converted to BMP files in Fiji. Seg3D was employed to import the

BMP files and create a threshold layer highlighting the bone. The sample was then converted into a 3D

representation, and the BV was calculated based on pixel units. To obtain the volume in mm^3, the value

was divided by 1,000,000, taking into account the appropriate voxel size.

Sample preparation for histological analysis

In vitro samples were directly fixed prior to sectioning. In vivo samples were fixed and subsequently

decalcified with a 10% EDTA solution, pH = 8, at 4 °C for two weeks prior to tissue embedding.

Paraffin embedding was performed on samples fixed in 4% formalin (Solveca AB). Tissues were

dehydrated by immersion in consecutive solutions of 35%, 70%, 95%, and 99.5% graded ethanol solution

(Solveco AB). Immersion in a 99.5% ethanol/xylene solution (1:1, Fisher Scientific) was then performed

for ten minutes followed by two rinsing in xylene (Fisher Scientific) for 20 minutes. Subsequently,

tissues were embedded in paraffin at 56 °C overnight, before sectioning with a microtome (Microm HM

355 Rotary Microtome) in 5 - 10 µm sections. The sections were then dried overnight at 37 °C before

staining. Prior to staining, sections were deparaffinized by two washes in xylene for 7 minutes and once

in 99.5% ethanol/xylene solution (1:1) for 3 minutes. Afterwards, sections were hydrated twice in

consecutive solutions of 99.5%, 95%, 70%, and 35% ethanol, for 7 minutes each.

Agarose embedding was performed on samples fixed overnight with 4% paraformaldehyde (Thermo

Scientific), using 4% low-melting agarose (Sigma). Sections of 100 µm thickness were obtained using a

7000smz vibratome (Campden) with stainless steel or ceramic blades.

Safranin O Staining

Paraffin-embedded sections were stained using Mayer's hematoxylin solution (Sigma-Aldrich) for 10

minutes. Samples were then placed under running distilled water to remove superfluous staining from

the sections. Subsequently, sections were stained with 0.01% fast green solution (Fisher Scientific) for five

minutes, and rinsed with 1% acetic acid solution (0.5 ml acetic acid in 49.5 ml distilled water) for

15 seconds. After that, the slides were stained with 0.1% safranin O (Fisher Scientific) solution for 5

minutes. Dehydration and clearing were performed by immersion in 95%, 99.5% ethanol, 99.5%

ethanol/xylene solution (1:1) and xylene twice successively for 2 minutes. Finally, the stained slides were

mounted with glass slides using PERTEX mounting medium (PERTEX, HistoLab).

Masson's trichrome staining

Masson's trichrome staining was performed using the trichrome staining kit (Sigma-Aldrich Sweden AB)

according to the manufacturer's guidelines. Briefly, tissue sections were deparaffinized and immersed in

cold running deionized water for 3 minutes. Then the sections were kept in Bouin's solution at room

temperature overnight or at 56 °C for 15 minutes. The slides were washed by running tap water and

stained using working Weigert's iron hematoxylin solution (Sigma) for five minutes for nuclei detection

(in black). After washing the slides, the cytoplasm was stained in red with Biebrich Scarlet-Acid fuchsin for

five minutes followed by clearing the slides by immersion in working phosphotungstic/ phosphomolybdic

acid solution (25 ml P. tungstic + 25 ml P. molybdic+ 50 ml distilled water) for five minutes. Collagen

stained blue by immersion in aniline blue solution for five minutes followed by clearing in 1% acetic acid solution diluted in distilled water (glacial, Fisher Scientific) for two minutes and washing with running deionized water. Finally, the sections were dehydrated in graded ethanol solutions (95% once, 100% twice) for two minutes each before washing with xylene twice for two minutes and mounted with PERTEX mounting medium.

Immunofluorescence

Agarose-embedded sections were treated with 0.5% Triton X-100 (Sigma) in PBS supplemented with 20% donkey serum (Jackson ImmunoResearch) for one hour at room temperature (RT) for blocking and permeabilization. After blocking/permeabilization, sections were stained with primary antibodies (mouse anti-Collagen II (Invitrogen, MA137493), rabbit anti-Collagen Type X (ColX) (abbexa, abx101469),) at 4 °C overnight. Sections were washed three times using cold PBS with 0.1% Triton X-100, 20 minutes each, followed by staining with secondary antibodies (CF568 donkey anti-rabbit (Biotium, 20098), CF633 donkey anti-mouse (Sigma-Aldrich, SAB4600131 in 2% donkey serum for three hours at room temperature. Sections were washed three times using cold PBS with 0.1% Triton X-100, 20 minutes each once more. For vasculature assessment, paraffin-embedded sections were stained following a previously established protocol[50] (primary antibody: Goat anti mouse/rat CD31 (R&D system, YZU0119121), secondary antibody:), CF567 anti-goat (Invitrogen, A11057)).

All sections were mounted using the Vectashield antifade mounting medium containing DAPI (Vector Laboratories, H1200). A LSM780 confocal microscope (Zeiss) with a 10x/20x objective was used to capture images and image series of whole tissue sections (z-step = 2 μm). The IMARIS 9.5 software package (Oxford Instruments) was used to analyse the data.

References

1. Bonnans C, Chou J, Werb Z. Remodelling the extracellular matrix in development and disease. *Nat Rev Mol Cell Biol*. 2014;15(12):786-801. doi:10.1038/nrm3904

2. Hussey GS, Dziki JL, Badylak SF. Extracellular matrix-based materials for regenerative medicine. *Nat Rev Mater*. 2018;3(7):159-173. doi:10.1038/s41578-018-0023-x

3. Fattahi R, Chamkhorami FM, Taghipour N, Keshel SH. The effect of extracellular matrix remodeling on material-based strategies for bone regeneration: Review article. *Tissue Cell*. 2022;76(January):101748. doi:10.1016/j.tice.2022.101748

4. Mouw JK, Ou G, Weaver VM. Extracellular matrix assembly: A multiscale deconstruction. *Nat Rev Mol Cell Biol*. 2014;15(12):771-785. doi:10.1038/nrm3902

5. Assunção M, Dehghan-Baniani D, Yiu CHK, Später T, Beyer S, Blocki A. Cell-Derived Extracellular Matrix for Tissue Engineering and Regenerative Medicine. *Front Bioeng Biotechnol*.

438   2020;8(December):1-10. doi:10.3389/fbioe.2020.602009

439   6.   Hinderer S, Layland SL, Schenke-Layland K. ECM and ECM-like materials - Biomaterials for
440   applications in regenerative medicine and cancer therapy. *Adv Drug Deliv Rev*. 2016;97:260-269.
441   doi:10.1016/j.addr.2015.11.019

442   7.   Tang G, Liu Z, Liu Y, et al. Recent Trends in the Development of Bone Regenerative Biomaterials.
443   *Front Cell Dev Biol*. 2021;9(May):1-18. doi:10.3389/fcell.2021.665813

444   8.   Gao C, Peng S, Feng P, Shuai C. Bone biomaterials and interactions with stem cells. *Bone Res*.
445   2017;5(May):1-33. doi:10.1038/boneres.2017.59

446   9.   Filippi M, Born G, Chaaban M, Scherberich A. Natural Polymeric Scaffolds in Bone Regeneration.
447   *Front Bioeng Biotechnol*. 2020;8(May). doi:10.3389/fbioe.2020.00474

448   10.   Reddy MSB, Ponnamma D, Choudhary R, Sadasivuni KK. A comparative review of natural and
449   synthetic biopolymer composite scaffolds. *Polymers (Basel)*. 2021;13(7).
450   doi:10.3390/polym13071105

451   11.   Decaris ML, Leach JK. Design of experiments approach to engineer cell-secreted matrices for
452   directing osteogenic differentiation. *Ann Biomed Eng*. 2011;39(4):1174-1185.
453   doi:10.1007/s10439-010-0217-x

454   12.   Harvestine JN, Orbay H, Chen JY, Sahar DE, Leach JK. Cell-secreted extracellular matrix,
455   independent of cell source, promotes the osteogenic differentiation of human stromal vascular
456   fraction. *J Mater Chem B*. 2018;6(24):4104-4115. doi:10.1039/c7tb02787g

457   13.   Hoch AI, Mittal V, Mitra D, Vollmer N, Zikry CA, Leach JK. Cell-secreted matrices perpetuate the
458   bone-forming phenotype of differentiated mesenchymal stem cells. *Biomaterials*. 2016;74:178-
459   187. doi:10.1016/j.biomaterials.2015.10.003

460   14.   Haumer A, Bourgine PE, Occhetta P, Born G, Tasso R, Martin I. Delivery of cellular factors to
461   regulate bone healing. *Adv Drug Deliv Rev*. 2018;129:285-294. doi:10.1016/j.addr.2018.01.010

462   15.   Sadr N, Pippenger BE, Scherberich A, et al. Enhancing the biological performance of synthetic
463   polymeric materials by decoration with engineered, decellularized extracellular matrix.
464   *Biomaterials*. 2012;33(20):5085-5093. doi:10.1016/j.biomaterials.2012.03.082

465   16.   Prewitz MC, Seib FP, von Bonin M, et al. Tightly anchored tissue-mimetic matrices as instructive
466   stem cell microenvironments. *Nat Methods*. 2013;10(8):788-794. doi:10.1038/nmeth.2523

467   17.   Bourgine PE, Gaudiello E, Pippenger B, et al. Engineered Extracellular Matrices as Biomaterials of
468   Tunable Composition and Function. *Adv Funct Mater*. 2017. doi:10.1002/adfm.201605486

469   18.   Pigeot S, Klein T, Gullotta F, et al. Manufacturing of Human Tissues as off-the-Shelf Grafts
470   Programmed to Induce Regeneration. *Adv Mater*. 2021;33(43). doi:10.1002/adma.202103737

471   19.   Grigoryan A, Zacharaki D, Balhuizen A, et al. Engineering human mini-bones for the standardized
472   modeling of healthy hematopoiesis, leukemia, and solid tumor metastasis. *Sci Transl Med*.
473   2022;14(666):1-16. doi:10.1126/scitranslmed.abm6391

474   20.   Golchin A, Shams F, Karami F. Advancing Mesenchymal Stem Cell Therapy with CRISPR/Cas9 for
475   Clinical Trial Studies. In: *Cell Biology and Translational Medicine,*. Vol 8. ; 2019:89-100.
476   doi:10.1007/5584_2019_459

21. Hazrati A, Malekpour K, Soudi S, Hashemi SM. CRISPR/Cas9-engineered mesenchymal
stromal/stem cells and their extracellular vesicles: A new approach to overcoming cell therapy
limitations. *Biomed Pharmacother*. 2022;156:113943. doi:10.1016/j.biopha.2022.113943

22. Geurts MH, Clevers H. CRISPR engineering in adult stem cell-derived organoids for gene repair
and disease modelling. 2023;1(January):32-45. doi:10.1038/s44222-022-00013-5

23. Hu K, Olsen BR. The roles of vascular endothelial growth factor in bone repair and regeneration.
Bone. 2016;91:30-38. doi:10.1016/j.bone.2016.06.013

24. Duda GN, Geissler S, Checa S, Tsitsilonis S, Petersen A, Schmidt-Bleek K. The decisive early phase
of bone regeneration. *Nat Rev Rheumatol*. 2023;19(February):78-95. doi:10.1038/s41584-022-
00887-0

25. Ran FA, Hsu PD, Wright J, Agarwala V, Scott DA, Zhang F. Genome engineering using the CRISPR-
Cas9 system. *Nat Protoc*. 2013;8(11):2281-2308. doi:10.1038/nprot.2013.143

26. Otto F, Thornell AP, Crompton T, et al. Cbfa1, a candidate gene for cleidocranial dysplasia
syndrome, is essential for osteoblast differentiation and bone development. *Cell*. 1997;89(5):765-
771. doi:10.1016/S0092-8674(00)80259-7

27. Komori T, Yagi * H., Nomura S, Yamaguchi A. Targeted disruption of. *Proc Natl Acad Sci U S A*.
1998;95(15):8692-8697.
http://www.pubmedcentral.nih.gov/articlerender.fcgi?artid=21138&tool=pmcentrez&rendertyp
e=abstract.

28. Kim HJ, Kim WJ, Ryoo HM. Post-Translational Regulations of Transcriptional Activity of RUNX2.
Mol Cells. 2020;43(2):160-167. doi:10.14348/molcells.2019.0247

29. Hattori EY, Masuda T, Mineharu Y, et al. A RUNX-targeted gene switch-off approach modulates
the BIRC5/PIF1-p21 pathway and reduces glioblastoma growth in mice. *Commun Biol*.
2022;5(1):1-11. doi:10.1038/s42003-022-03917-5

30. Kusumbe AP, Ramasamy SK, Adams RH. Coupling of angiogenesis and osteogenesis by a specific
vessel subtype in bone. *Nature*. 2014;507(7492):323-328. doi:10.1038/nature13145

31. Tuckermann J, Adams RH. The endothelium–bone axis in development, homeostasis and bone
and joint disease. *Nat Rev Rheumatol*. 2021;17(10):608-620. doi:10.1038/s41584-021-00682-3

32. Largo RD, Burger MG, Harschnitz O, et al. VEGF Over-Expression by Engineered BMSC Accelerates
Functional Perfusion, Improving Tissue Density and In-Growth in Clinical-Size Osteogenic Grafts.
Front Bioeng Biotechnol. 2020;8(July):1-13. doi:10.3389/fbioe.2020.00755

33. Yang YQ, Tan YY, Wong R, Wenden A, Zhang LK, Rabie ABM. The role of vascular endothelial
growth factor in ossification. *Int J Oral Sci*. 2012;4(2):64-68. doi:10.1038/ijos.2012.33

34. Burger MG, Grosso A, Briquez PS, et al. Robust coupling of angiogenesis and osteogenesis by
VEGF-decorated matrices for bone regeneration. *Acta Biomater*. 2022;149:111-125.
doi:10.1016/j.actbio.2022.07.014

35. Behr B, Tang C, Germann G, Longaker MT, Quarto N. Locally applied vascular endothelial growth
factor A increases the osteogenic healing capacity of human adipose-derived stem cells by
promoting osteogenic and endothelial differentiation. *Stem Cells*. 2011;29(2):286-296.

doi:10.1002/stem.581

36.   Zuo WH, Zeng P, Chen X, Lu YJ, Li A, Wu J Bin. Promotive effects of bone morphogenetic protein 2
518   on angiogenesis in hepatocarcinoma via multiple signal pathways. *Sci Rep*. 2016;6(July):1-9.
519   doi:10.1038/srep37499

520   37.   Lowery JW, de Caestecker MP. BMP signaling in vascular development and disease. *Cytokine*
521   *Growth Factor Rev*. 2010;21(4):287-298. doi:10.1016/j.cytogfr.2010.06.001

522   38.   Kamekura S, Kawasaki Y, Hoshi K, et al. Contribution of runt-related transcription factor 2 to the
523   pathogenesis of osteoarthritis in mice after induction of knee joint instability. *Arthritis Rheum*.
524   2006;54(8):2462-2470. doi:10.1002/art.22041

525   39.   Park DY, Min BH, Park SR, et al. Engineered cartilage utilizing fetal cartilage-derived progenitor
526   cells for cartilage repair. *Sci Rep*. 2020;10(1):1-13. doi:10.1038/s41598-020-62580-0

527   40.   Zeng J, Huang L, Xiong H, et al. Injectable decellularized cartilage matrix hydrogel encapsulating
528   urine-derived stem cells for immunomodulatory and cartilage defect regeneration. *npj Regen*
529   *Med*. 2022;7(1):1-12. doi:10.1038/s41536-022-00269-w

530   41.   Sekiya I, Vuoristo JT, Larson BL, Prockop DJ. In vitro cartilage formation by human adult stem cells
531   from bone marrow stroma defines the sequence of cellular and molecular events during
532   chondrogenesis. *Proc Natl Acad Sci U S A*. 2002;99(7):4397-4402. doi:10.1073/pnas.052716199

533   42.   Pelttari K, Winter A, Steck E, et al. Premature induction of hypertrophy during in vitro
534   chondrogenesis of human mesenchymal stem cells correlates with calcification and vascular
535   invasion after ectopic transplantation in SCID mice. *Arthritis Rheum*. 2006;54(10):3254-3266.
536   doi:10.1002/art.22136

537   43.   Mueller MB, Tuan RS. Functional characterization of hypertrophy in chondrogenesis of human
538   mesenchymal stem cells. *Arthritis Rheum*. 2008;58(5):1377-1388. doi:10.1002/art.23370

539   44.   Chen Z, Klein T, Murray RZ, et al. Osteoimmunomodulation for the development of advanced
540   bone biomaterials. *Mater Today*. 2016;19(6):304-321. doi:10.1016/j.mattod.2015.11.004

541   45.   Xie Y, Hu C, Feng Y, et al. Osteoimmunomodulatory effects of biomaterial modification strategies
542   on macrophage polarization and bone regeneration. *Regen Biomater*. 2020;7(3):233-245.
543   doi:10.1093/rb/rbaa006

544   46.   Aamodt JM, Grainger DW. Extracellular matrix-based biomaterial scaffolds and the host
545   response. *Biomaterials*. 2016;86:68-82. doi:10.1016/j.biomaterials.2016.02.003

546   47.   Ramakrishnaiah Siddappa, Ruud Licht, Clemens van Blitterswijk J de B. Donor variation and loss of
547   multipotency during in vitro expansion of human mesenchymal stem cells for bone tissue
548   engineering. *J Orthop Res*. 2007;25(8). https://onlinelibrary.wiley.com/doi/10.1002/jor.20402.

549   48.   LaFleur MW, Nguyen TH, Coxe MA, et al. A CRISPR-Cas9 delivery system for in vivo screening of
550   genes in the immune system. *Nat Commun*. 2019;10(1):1-10. doi:10.1038/s41467-019-09656-2

551   49.   Bock C, Datlinger P, Chardon F, et al. High-content CRISPR screening. *Nat Rev Methods Prim*.
552   2022;2(1). doi:10.1038/s43586-021-00093-4

553   50.   Zaqout S, Becker LL, Kaindl AM. Immunofluorescence Staining of Paraffin Sections Step by Step.
554   *Front Neuroanat*. 2020;14(November):1-11. doi:10.3389/fnana.2020.582218

Figure 1. CRISPR/Cas9 editing of mesenchymal cell lines lead to efficient VEGF knockout in cartilage tissues. A) Experimental scheme depicting the generation of CRISP/Cas9-edited MSOD-B lines, and the subsequent in vitro and in vivo tissue formation assessment. B) Overview of the native human VEGF coding sequence composed of eight exons. Designed gRNAs and their targeted binding sites are illustrated, as well as the corresponding expected impact on the coding sequence. gRNAs targeting exon 1 (orange) disrupt translation initiation and inhibit protein expression, gRNA targeting exon 2 (blue) disrupts VEGF receptor binding, and gRNA targeting exon 8 (green) alters the C-Terminal sequence and repress activation of protein. C) ELISA-based quantitative analysis of VEGF protein content in cell culture supernatant from expanded single cell colonies. From all clones, only two had no detectable level of VEGF (1.3_3 and 1.3_6). These clones were subsequently defined as MSOD-BΔV1 and MSOD-BΔV2. D) Histological assessment of in vitro differentiated constructs using Safranin O (top panel) and Masson's trichrome (bottom panel) stains. Both the MSOD-B and MSOD-BΔV1 displayed glycosaminoglycans (GAG) (orange to reddish in Safranin O) and collagen content (Blueish in Masson's trichrome), indicating successful cartilage formation (Scale bars = 200 μm). Left bottom inserts show the whole tissue section. E) Quantitative assessment of the total GAG content in MSOD-B and MSOD-BΔV1 in vitro differentiated constructs. F) ELISA-based quantitative assessment of VEGF protein in in vitro differentiated constructs. Unpaired t-test, n = 3-4 biological replicates, ****p < 0.0001, n.s. = not significant.

Figure 2. VEGF knockout cartilage tissues retain bone remodeling capacity despite reduced early-stage vascularization

A) Immunofluorescence images of MSOD-B and MSOD-BΔV1 tissues two weeks post-in vivo implantation. Displayed images consist of 3D-stacks from 80-100 μm thick sections, vessels stained with mouse CD31 (red) and nuclei with DAPI (blue) (Scale bars at 200 μm except for magnified white inserts at 5μm). Box "a" and "c" display the periphery whereas Box "b" and "d" show the central region of MSOD-B and MSOD-BΔV1 constructs respectively. A reduction in tissue vascularization is observed in MSOD-BΔV1 samples. B) Quantitative analysis of the CD31 signal using an isosurface-based strategy (IMARIS software). C) Representative macroscopic and microtomography images of in vivo constructs retrieved at two and six weeks post-implantation. D) Microtomography-based quantification of the sample's bone/ mineralized volume over their total volume (ratio). No significant differences between MSOD-B and MSOD-BΔV1 could be observed. (BV: Bone Volume, TV: Total Volume). E) Histological analysis of in vivo tissues using Safranin O and Masson's trichrome stains, at two (2W) and six weeks (6W) post-implantation. Both sample types underwent full remodeling into a bone organ after 6 weeks, with presence of bone structures and a bone marrow compartment (Scale bars = 200 μm). CB – cortical bone; BM – bone marrow. TB – trabecular bone. Unpaired t-test, n=3-8 biological replicates, **p < 0.01, n.s.=not significant.

Figure 3. RUNX2 knockout does not prevent chondrogenic differentiation but impairs hypertrophy A) Overview of the human RUNX2 coding sequence comprising 8 exons. gRNAs and their corresponding expected protein structure. The gRNA targeting exon 2 (orange) disrupts the DNA binding domain, gRNA targeting exon 5 (violet) disrupts nuclear translocation, gRNAs targeting exon 6 (blue) disrupt the transcriptional activation domain and gRNAs targeting exon 8 (green) disrupt the nuclear matrix targeting signal and repress the protein function. B) Intracellular flow cytometry for RUNX2 detection in MSOD-B and RUNX2-edited clones. A clear protein reduction could be observed in the 6.1_1 and 6.1_23 clones. C) Western blot analysis of RUNX2 in cultured MSOD-B and RUNX2-edited cells. The genetic editing of RUNX2 is confirmed by the detection of the truncated proteins. Actin is used as a control to normalize the protein content. D) Histological analysis of in vitro constructs using Safranin O (top) and Masson's trichrome (bottom) stains, indicating the presence of cartilage matrices (Scale bars = 200 μm). E) Quantitative assessment of the total GAG content in corresponding in vitro generated tissues. F) Immunofluorescence images of MSOD-B and MSOD-BΔR1 tissues. Displayed images consist of 3D-stacks from 80-100 μm thick sections, stained for DAPI (blue), Collagen Type II (COL2, yellow) and Collagen Type X (COLX, red). A clear reduction in the COLX signal could be observed in the MSOD-BΔR1 tissues, indicating impaired hypertrophy. G) Isosurface-based quantification of the COL2 immunofluorescent signal using the IMARIS software. No significant difference between groups confirm the retention of cartilage formation in RUNX2-edited constructs. H) Isosurface-based quantification of the COLX immunofluorescent signal using the IMARIS software, confirming the disruption of hypertrophy in the MSOD-BΔR1 constructs. Unpaired t-test, n=3, *p < 0.05, n.s. = not significant.

Figure 4. RUNX2 knockout in cartilage tissues disrupts effective bone formation A) Representative macroscopic and microtomography images of in vivo constructs retrieved at two and six weeks post-implantation. B) Microtomography-based quantification of the sample's bone/mineralized volume over their total volume (ratio). (BV: Bone Volume, TV: Total Volume). A marked difference is observed as early as two weeks, with a clear lower mineral content in MSOD-BΔR1 samples. Unpaired t-test, n=3 biological replicates, *p < 0.05, **p < 0.01. C) Histological analysis of in vivo constructs using Safranin O and Masson's trichrome stains. After two weeks (2W), a higher bone formation is already evident in the MSOD-B control group. The MSOD-BΔR1 samples explanted after 6 weeks (6W) displayed presence of cortical and trabecular bone, but also large amount of fibrous tissue indicating an incomplete remodeling. (Scale bars = 200 µm).