Assessment of bovine cortical bone fracture behavior using impact microindentation as a surrogate of fracture toughness

Babak Jahani[1*], Rachana Vaidya[1*], James M. Jin[1], Donald A. Aboyotes[1], Kaitlyn S. Broz[1,3], Siva Khrotapalli[4], Bhanuteja Pujari[4], Simon Y. Tang[1,2,3]
* These authors contributed equally to the manuscript.

Authors affiliation:
[1]Department of Orthopaedic Surgery, Washington University in St. Louis, St. Louis, Missouri, USA,
[2]Department of Biomedical Engineering, Washington University in St. Louis, St. Louis, Missouri, USA
[3]Department of Mechanical Engineering and Materials Science, Washington University in St. Louis, St. Louis, Missouri, USA
[4]School of Medicine, St Louis University, MO, USA

Corresponding Author:
Simon Y. Tang, Ph.D., MSCI
Associate Professor
Orthopedic Surgery, Biomedical Engineering,
Mechanical Engineering & Materials Science
Washington University in St. Louis
simon.tang@wustl.edu

Abstract

The fracture behavior of bone is critically important for assessing its mechanical competence and

ability to resist fractures. Fracture toughness, which quantifies a material's resistance to crack

propagation under controlled geometry, is regarded as the gold standard for evaluating a

material's resistance to fracture. However properly conducting this test requires access to

calibrated mechanical load frames the destruction of the bone samples, making it impractical for

obtaining clinical measurement of bone fracture. Impact microindentation offers a potential

alternative by mimicking certain aspects of fracture toughness measurements, but its relationship

with mechanistic fracture toughness remains unknown. In this study, we aimed to compare

measurements of notched fracture toughness and impact microindentation in fresh and boiled

bovine bone. Skeletally mature bovine bone specimens (n=48) were prepared, and half of them

were boiled to denature the organic matrix, while the other half remained preserved in frozen

conditions. Notched fracture toughness tests were conducted on all samples to determine

Initiation toughness (K_{IC}), and an impact microindentation test using the OsteoProbe was

performed to obtain the Bone Material Strength index. Boiling the bone samples resulted in a

significant reduction in both K_{IC} ($p < 0.0001$) and the average Bone Material Strength index ($p <$

0.0001), leading to impaired resistance of bone to crack propagation. Remarkably, the average

Bone Material Strength index exhibited a high correlation with K_{IC} ($r = 0.86$; $p < 0.001$). The

ranked order difference analysis confirmed excellent agreement between the two measures. This

study provides the first evidence that impact microindentation could serve as a surrogate measure

for bone fracture behavior. The potential of impact microindentation to non-destructively assess

bone fracture resistance could offer valuable insights into bone health without the need for

elaborate testing equipment and sample destruction.

Keywords: Indentation; fracture toughness; biomechanics; bone strength; fracture risk

assessment

Introduction

Catastrophic fractures are a significant public health problem with an alarming prevalence and substantial economic burden. Epidemiological data indicate that approximately 40% of women aged 50 and above will experience a fracture at the hip, vertebrae, or forearm in their remaining lifetime, with increased risk of complications and mortality[1-3]. Furthermore, it is projected that osteoporotic fractures in the United States alone will reach an annual incidence exceeding 3 million by 2025 and costs above 25.3 billion dollars per year[4,5]. This rise in fracture incidence can largely be attributed to progressive deterioration in bone strength and fracture resistance associated with aging and disease.

The fracture resistance of bone is influenced by multiple factors including bone geometry, density, and material properties of the bone matrix. Clinical imaging modalities such as X-ray and Dual Energy X-ray Absorptiometry (DXA) can robustly measure the geometry and metrics associated with mineral density[6], however, directly assessing the mechanical properties of the bone matrix presents clinical challenges. Destructive mechanical testing methods, like bending, tension, compression, shear, indentation, and fracture toughness measurements, have been employed to characterize the mechanical competence of the bone matrix[7-13]. Each of these methods employ different mechanical principles and assumptions to analyze mechanical and material properties. To simulate a realistic failure of bone the fracture toughness method is considered the most definitive and realistic as it involves the controlled loading and expansion of a premade flaw.[11,13]. However, the destructive nature of these tests makes them impossible to implement in living organisms and humans.

In recent years, reference point indentation has emerged as a promising method for assessing the material behavior of bone tissue. Reference point indentation can fall under one of

two categories: cyclic microindentation or impact microindentation. Cyclic microindentation,

employs a reference probe that defines the reference position and then applies a trapezoid

waveform with equal ramping, holding, and unramping that delivers successive indentations as the

probe progressively penetrates the material. Cyclic microindentation provides a range of

quantitative metrics that have demonstrated correlations with various bending behaviors observed

in cortical bone tissue[14,15]. Conversely, impact microindentation (OsteoProbe) utilizes a reference

force (rather than a reference position) to assess mechanical properties of cortical bone by

measuring the normalized depth of indentation. The resultant impact microindentation

measurements are associated with bending toughness[16] and indentation hardness (e.g. Rockwell

and Vickers Hardness tests)[17] as well as compositional variations in bone tissue such as

mineralization, collagen cross linking, and cortical porosity[14,18,19]. The application of reference

point indentation technique to bone tissue enables the non-destructive assessments of mechanical

behavior. Yet, the relationship between impact microindentation and fracture toughness

measurements of the bone tissue has not been directly investigated. Thus, the objective of this

study is to compare measurements of notched fracture toughness and impact microindentation in

fresh and denatured bovine bone.

Materials and methods

Sample collection and preparation

Six bovine femurs were locally sourced from cows aged 12- to 18- months of age, the bones were wrapped in saline-soaked gauze and stored at -20ºC prior to experimentation. From each femur, two beams were obtained per quadrant along the longitudinal axis (anterior, posterior, lateral, and medial) resulting in a total of forty-eight beams (Figure 1). The beams were cut and machined into rectangular parallelepipeds using a low-speed sectioning saw under constant water irrigation (UKAM, Industrial Superhard tools, Valencia CA, USA). The dimensions of the beams were as follows: Width (W) = 6 mm, Length (L) ~50mm and thickness (B) = 3 mm.

For fracture toughness measurements, a single-edged V-notch and a pre-crack were introduced on the periosteal side of each beam. A diamond-wafered blade with a 30° taper was employed to create a 3 mm notch (the 'a' parameter) at the center of the beam. A pre-crack of 0.1 mm was introduced on each beam using a single-edge box cutter and Alumina suspension polish (0.3µm particle size; Allied High Tech, Compton, CA, USA). The dimensions of the notch and pre-crack combined approximated an aspect ratio of a/W=0.5.

Following machining and preparation, the beams were divided into two groups, with one bone of the pair assigned to be boiled and the other served as the control group. The boiled group was immersed in boiling water for a duration of 3 hours, while the control group remained stored at -20℃ until mechanical testing. Boiling the bone aimed to denature the organic matrix network components without impacting the mineral phase. All mechanical testing was conducted at standard room conditions (20℃, 50% humidity).

Fracture toughness test

In accordance with ASTM E399 [20], the fracture toughness test was conducted in a three-

point bending configuration (Span 'S'= 30 mm, 1.5 mm support radius) using a Instron 5866 load

frame (Instron Co, Norwood, MA). The samples were pre-loaded with 10N, similar to the 10N

reference force of the impact indentation device, and then subjected to a loading rate of 0.2

mm/min until complete fracture, during which force-displacement data were collected. The critical

stress intensity factor (K_{IC}) of each beam was subsequently calculated using the following

equation[20]:

$$K_{IC} = \frac{P_Q \cdot S}{B\sqrt{W^3}} \cdot f\left(\frac{a}{W}\right) \text{ (Equation 1)}$$

P_Q: The maximum load of the linear region of load-displacement curve

S: Span of each beam under the load (30 mm)

B: Thickness of beam (3 mm)

W: Width of each beam (6 mm)

$f\left(\frac{a}{W}\right)$ is the geometric correction term, given as follows:

$$f\left(\frac{a}{W}\right) = 3\left(\sqrt{\frac{a}{W}}\right) \times \frac{\left[1.99\left(\frac{a}{W}\right)\left(1-\frac{a}{W}\right) \times \left(2.15 - 3.93\left(\frac{a}{W}\right) + 2.7\left(\frac{a}{W}\right)^2\right)\right]}{2\left(1+\frac{2a}{W}\right)\left(1-\frac{a}{W}\right)^{\frac{3}{2}}} \text{ (Equation 2)}$$

Impact Microindentation test

Impact microindentation was performed on the periosteal side of each beam at least 20 mm

away from the notch using OsteoProbe (Active Life Scientific, Santa Barbara, CA), a handheld

device that is designed to measure the resistance of cortical bone to the indentation[17]. A reference

load of 10N was manually applied by the operator using the measurement probe, and followed by

application of a 30 N (total of 40N) load to the measurement surface at a rate of 120,000 N/s. The

depth of penetration into the bone is recorded typically ranging from ~150-400µm, and the

outcome was reported as a singular scalar value, known as the Bone Material Strength index

(BMSi)[17,21,22]. To calculate the BMSi value, eight indentations are made on the bone and the

harmonic mean of the measured penetration distances into the bone is divided by the harmonic

mean of ten penetration distances into a polymethylmethacrylate (PMMA) reference material and

then multiplied by 100. PMMA measurements are made before and after each set of bone sample

measurements.

Measurement of Cortical Porosity and Tissue Mineral Density (TMD)

The 48 bovine beams were wrapped in PBS-soaked gauze and scanned using the µCT50

microCT scanner (Scanco Medical; Wangen-Brüttisellen, Switzerland) to evaluate tissue mineral

density (TMD), cortical porosity, and resultant fracture surface. The entire half from each bone

sample was scanned. The cortical bone analyses were obtained at a voxel size of 20 µm, while

the fracture surface and indentation site visualization was obtained at 3 µm. The x-ray tube

potential was 70 kVp with an intensity of 57 µA 500 projections and a 700 ms integration time.

TMD and cortical porosity values were derived from the cortical analysis module in the

Scanco Evaluation software (v 1.2.30.0). Cortical porosity was calculated as the percentage of

voxel bone volume divided by the total volume, with the final value subtracted from 100. 3D

renderings of the bovine beams were generated by importing the CT image DICOMs into the 3D

Slicer image analysis software (v 5.3.1, National Alliance for Medical Image Computing). The

segment editor module was used to apply a threshold, determined by the distribution of air and

bone attenuation constants, to segment the bone tissue from its surrounding, and then the fracture

surfaces were rendered accordingly. The Scanco Visualizer software (v 1.2.13.0) was employed

to visualize and qualitatively assess the crack surface, encompassing the region from the notch to

the endosteal side of the beam[23]. The indentation regions were viewed from cross-sections that

were created by aligning the virtual axis with the physical axis of the beam, and then

successively sectioned until the largest indentation impression has been reached.

Statistical methods

The measured outcomes were plotted as histograms to examine distributions. . Data remained

paired and were compared between groups by Repeated Measures analysis of variance (ANOVA).

Pearson's correlations were run to identify the linear correlation between fracture toughness K_{IC}

and Bone score (BMSi). Respective measurements were then ranked from high to low in order to

perform a ranked order difference analyses[24] to identify the systemic bias between Bone Score

(BMSi) and fracture toughness (K_{IC}). All analyses were conducted using PRISM 9 (GraphPad,

San Diego, USA) or Excel (Microsoft, Redmond USA).

147
Figure 1: Overview of the experimental design. Forty-eight beams were extracted from six bovine

femurs and paired by quadrant (Created with <u>BioRender.com</u>). All the beams were cut to the same

dimensions of 50 mm x 6mm x 3mm. The boiled group underwent a 3-hour boiling while the

control (fresh) group was stored in -20°C until testing. Following the treatments, single edge

notches were created on the periosteal side of each beam. Each notch was initiated using a

diamond wafered blade to a depth of 1mm, then advanced to a pre-crack using a surgical blade

with a polishing solution containing 0.3 μm diameter alumina suspensions. The notch width = 1

mm, point angle = 30°, and radius of the slit tip of 0.05 mm. The overall length of the notch and

pre-crack was a=3 mm to maintain a/W=0.5. The beams subsequently underwent 3-point bending

test with a preload of 10N and a loading rate of 0.2 mm/min until failure. Indentation measurements

were performed using the OsteoProbe device, and the Bone Scores were reported as an average of

8 indentations. MicroCT scans were taken to evaluate the crack surfaces and the indentation sites.

RESULTS

Boiling does not affect cortical porosity nor tissue mineral density.

The cortical bone porosity analyses revealed no significant difference in cortical porosity

(p=0.57) between the boiled and fresh bones. The mean porosities for the fresh group and the

boiled group were 0.20% (± 0.32%) and 0.27% (± 0.40%) respectively. Similarly, no

significant differences were observed in tissue mineral density between the two groups (Figure

2B). The mean TMD values for the fresh and boiled group were 1005 ($\pm$ 25.93) mg HA/cm^3 and

1011($\pm$ 31.44) mg HA/cm^3, respectively. Taken together, these results confirm that boiling did

not substantially affect the microstructure or mineral composition of the bone.

F*igure 2*: Boiling did not influence the (A) cortical porosity (p = 0.574) nor the (B) tissue

mineral density (p = 0.462) of the bone beams. Samples were evaluated using microCT scanned

at 20 µm spatial resolution.

Fracture toughness discerns the effects of boiling and quadrant-dependent variations of bone

fracture behavior.

The fracture toughness measurements of cortical bone in both fresh and boiled beams revealed a

significant decrease in fracture toughness in boiled beams compared to fresh beams in all four

quadrants of the bone (p<0.0001) (Figure 3A). We also observed an effect of quadrant on

fracture toughness (p=0.002). Analysis of the fracture surfaces revealed distinct differences

between the fresh and boiled samples (Figure 3B). Fresh beams exhibited a greater occurrence of

crack deflection and toughening behavior, resulting in irregular and larger crack. (Figure 3B).

These results confirm that boiling significantly deteriorates bone material properties and

compromises the bone's resistance to fracture.

Figure 3: (A) Fracture toughness measurements show that fresh bovine beams had significantly

higher fracture toughness (6.18 ± 0.81 MPa $\sqrt{m}$) than boiled beams in samples taken from all 4

quadrants (2.46 ± 0.507 MPa $\sqrt{m}$) (B) Inspection of the fracture surfaces from microCT revealed

that the fresh bones had extensive crack deflection prior to failure, while the boiled samples

showed little to no deflection of the crack. (**** $p < 0.0001$; *** $p < 0.001$; ** $p < 0.01$; * $p <$

0.05).

Impact microindentation measurements are strongly correlated with initiation toughness.

Impact microindentation was deployed to assess bone material properties in both fresh and

boiled groups. The indentation measurements revealed a significantly lower average BMSi

values in the boiled group, indicating detectable impairments in bone material caused by boiling

(Figure 4A). No significant differences were observed between quadrants (p=0.160). High-

resolution microCT illustrated that the reference load applied by the probe creates a observable

impression similar to the stress concentrating pre-crack in the notched bone beams. Given the

equal reference load applied on the bones of both groups, the boiled group incurred a larger and

deeper impression (Figure 4B). Consistent with the BMSi readout, the subsequent indentation

applied by the additional 30 N of force created a larger impression in the boiled group than in the

fresh group. Importantly, a strong correlation was identified between the average BMSi and

increasing fracture toughness (K_{IC}) (Figure 5A). The ranked order difference analysis revealed

that approximately 43 of the 48 measurements were within the Upper Acceptable Limits and

Lower Acceptable Limits defined by the 95% confidence interval. Moreover, the bias converges

towards zero where the fragile bones are ranked (Figure 5B).

Figure 4*: (A) Impact microindentation results showed that the average BMSi is significantly

lower in the boiled group (90.6 ± 1.27 [unitless]) compared to the fresh group (103 ± 2.19

[unitless]) (p<0.0001) (B) MicroCT scans at 3μm resolution show that fresh beams show smaller

indentation depths, 35.64 μm and 120.55 μm; compared to boiled beams, 52.89 μm and 158.63

μm, after preload of 10N, and full load of 40N, respectively.

Figure 5. (A) The Bone Score (Average BMSi) measurements are strongly correlated to fracture

toughness (K_{IC}) (r=0.86, p<0.001). (B) The ranked difference analysis reveals approximately

90% of measurements lie well within the 95% CI Acceptable Limits. Moreover, the bias

converges towards zero at the higher ranks where fragility occurs in these samples. This data

suggests that Bone Score is an outstanding surrogate for fracture toughness K_{IC} in weakened

bone.

DISCUSSION

In this study, we investigated the fracture behavior of boiled and fresh bovine cortical

bone using impact microindentation and fracture toughness testing. We subjected the bones to

boiling, which denatures the protein tertiary structures, as a controlled method to deteriorate

bone's organic phase without affecting the inorganic phase[25]. MicroCT analyses confirmed that

boiling did not alter the inorganic phase shown here as no differences in cortical porosity or

tissue mineral density between groups. While the inorganic phase showed no differences we

noted a significant reduction in mechanical properties, specifically fracture toughness in the

boiled samples. The loss of fracture toughness in the boiled beams was accompanied by

distinctive morphologies of the crack surface (Figure 3B). The boiled samples exhibited

smoother crack surfaces that signifies brittle fracture behavior and rapid crack propagation with

minimal plastic deformation. In contrast, the fresh samples exhibited more tortuous crack

surfaces that are typically associated with ductile fracture behavior, characterized robust

deflection mechanisms[25,26]. The critical stress intensity factor (K_{IC}) was used as the measure of

fracture toughness and is based on linear-elastic assumptions for the bone material. This

assumption minimizes the contribution from plastic deformation and thus does not account for

crack-growth toughening[27-29]. Therefore, these results likely underestimate the true fracture

toughness of bone. In contrast, impact microindentation measurements include elements of

elastic and plastic behavior and may be a more comprehensive evaluation of the material's

damage behavior. To our knowledge, this is the first study to examine the relationship between

fracture toughness and microindentation measurements using the OsteoProbe. It is worth noting

that the notched fracture toughness is conducted at the millimeter scale, and therefore likely

detected the contributions from microstructural variations known to occur across bone

quadrants[30]. On the other hand, the micrometer-scale indentation measurements are at a smaller

length-scale and therefore were not affected by these features[7]. The excellent correspondence

between K_{IC} and BMSi suggests that measurements of the OsteoProbe provide insights on the

fracture toughness of bone. The ranked order difference analysis is the gold-standard for

comparing two analytical measurements with disparate units[24], and this analysis revealed the

bias for approximately 90% of the measurements were within the acceptable limits defined by

the 95% confidence interval. Moreover, the magnitude of bias diminished in lower K_{IC} and

BMSi (higher ranked) samples. While these limits will need to be refined with additional

clinical data, the bias range here is considered good to excellent[31].

Bone fractures occur though a complex interplay of material and biological factors.

However, clinical assessments of fracture risk typically do not account for the material behavior

of bone. The lack of clinical information of in vivo bone material quality highlights the

importance of measuring bone fracture properties for fracture risk prediction. For examples, bone

mineral density (BMD), measured by DXA, is currently considered the gold standard for

determining fracture risk, yet, BMD has been shown to explain only one-third of an individual's

fracture risks in middle-aged and elderly women[32,33]. Due to the fact that bone is a complex

biocomposite, its fracture behavior is determined by a number of bone density-independent

factors including degraded collagenous matrix, increased porosity, accumulation of

microcracks[14,28,34-38], among others. Combining BMD and material-level measures such as

indentation improves the prediction of bone strength[38]. Impact microindentation methods have

been successful in detecting changes in bone composition[39], adaptations to bone therapeutics[40-

42], and pathological bone diseases[19,39-41,43-54] with BMSi reported to be lower in the respective

pathological populations. Our findings here suggest that these differences detected by

indentation likely reflect the changes in bone fracture toughness in these patients.

It is also important to note that changes in BMSi do not always correlate with prevalent

fractures[55-58]. Bone with impaired fracture resistance is more likely to fracture *ceteris paribus*,

but whether a fracture event occurs can vary with individual loading history, exposure to

traumatic loads, and current bone metabolism. Therefore, the ability to measure bone fracture

resistance in a patient should be interpreted in context of their individual propensity and other

risk factors. Nonetheless, *in vivo* fracture toughness of bone is undoubtedly a critical aspect of

fragility especially in susceptible individuals.

There are a number of limitations that should be noted in this study. We used bovine

cortical bone in our experiments, which may not perfectly emulate the properties of human bone.

Although bovine bones are from skeletally mature animals, these animals are relatively young

compared to elderly humans. Therefore, boiling to deteriorate bone's organic phase produces

dramatic changes and may not recapitulate the progressive biological changes that occur in bones

due to aging and disease.

In summary, our findings demonstrate that impact microindentation can detect

differences caused by heat denaturation, and these measurements closely correspond to the

critical stress intensity factor measurement from a notched fracture toughness test. Although it is

not possible to perform direct measures of fracture toughness in vivo, in vivo measurements of

impact microindentation[59] on bone could be considered a surrogate measure of bone fracture

toughness.

CONCLUSION

Our findings support that impact microindentation quantifies changes in bone fracture

behavior. Bone material strength index was highly correlated with the critical stress intensity

factor of fracture toughness measured in boiled and fresh bovine bone.

ACKNOWLEDGEMENTS

This study was supported by the National Institutes of Health (P30 AR074992, R44 AG071034,

R01 AR074441, R01 AR077678).

References:

1. Black DM, Rosen CJ. Clinical Practice. Postmenopausal Osteoporosis. N Engl J Med. Jan 21 2016;374(3):254-62.
2. Vestergaard P, Rejnmark L, Mosekilde L. Increased mortality in patients with a hip fracture-effect of pre-morbid conditions and post-fracture complications. Osteoporos Int. Dec 2007;18(12):1583-93. Epub 20070614.
3. Pike C, Birnbaum HG, Schiller M, Sharma H, Burge R, Edgell ET. Direct and indirect costs of non-vertebral fracture patients with osteoporosis in the US. Pharmacoeconomics. 2010;28(5):395-409.
4. Burge R, Dawson-Hughes B, Solomon DH, Wong JB, King A, Tosteson A. Incidence and economic burden of osteoporosis-related fractures in the United States, 2005-2025. J Bone Miner Res. Mar 2007;22(3):465-75. Epub 2006/12/06.
5. Roche JJ, Wenn RT, Sahota O, Moran CG. Effect of comorbidities and postoperative complications on mortality after hip fracture in elderly people: prospective observational cohort study. BMJ. Dec 10 2005;331(7529):1374. Epub 2005/11/22.
6. Liu XS, Cohen A, Shane E, Yin PT, Stein EM, Rogers H, et al. Bone density, geometry, microstructure, and stiffness: Relationships between peripheral and central skeletal sites assessed by DXA, HR-pQCT, and cQCT in premenopausal women. J Bone Miner Res. Oct 2010;25(10):2229-38. Epub 2010/05/26.
7. Wagner HD, Weiner S. On the relationship between the microstructure of bone and its mechanical stiffness. J Biomech. Nov 1992;25(11):1311-20. Epub 1992/11/01.
8. Weiner S, Traub W, Wagner HD. Lamellar bone: structure-function relations. J Struct Biol. Jun 30 1999;126(3):241-55. Epub 1999/09/04.
9. Lipson SF, Katz JL. The relationship between elastic properties and microstructure of bovine cortical bone. J Biomech. 1984;17(4):231-40. Epub 1984/01/01.
10. Martin RB, Boardman DL. The effects of collagen fiber orientation, porosity, density, and mineralization on bovine cortical bone bending properties. J Biomech. Sep 1993;26(9):1047-54. Epub 1993/09/01.
11. Behiri JC, Bonfield W. Orientation dependence of the fracture mechanics of cortical bone. J Biomech. 1989;22(8-9):863-72. Epub 1989/01/01.
12. Khandaker M, Ekwaro-Osire S. Weibull analysis of fracture test data on bovine cortical bone: influence of orientation. Int J Biomater. 2013;2013:639841. Epub 2014/01/05.
13. Bonfield W, Datta PK. Fracture toughness of compact bone. J Biomech. 1976;9(3):131-4. Epub 1976/01/01.
14. Abraham AC, Agarwalla A, Yadavalli A, Liu JY, Tang SY. Microstructural and compositional contributions towards the mechanical behavior of aging human bone measured by cyclic and impact reference point indentation. Bone. Jun 2016;87:37-43. Epub 2016/03/30.
15. Uppuganti S, Granke M, Manhard MK, Does MD, Perrien DS, Lee DH, et al. Differences in sensitivity to microstructure between cyclic- and impact-based microindentation of human cortical bone. J Orthop Res. Jul 2017;35(7):1442-52. Epub 2016/08/12.
16. Gallant MA, Brown DM, Organ JM, Allen MR, Burr DB. Reference-point indentation correlates with bone toughness assessed using whole-bone traditional mechanical testing. Bone. Mar 2013;53(1):301-5. Epub 2013/01/01.

17.   Ly FS, Proctor A, Hoffseth K, Yang HT, Hansma PK. Significant correlation of bone
material strength index as measured by the OsteoProbe with Vickers and Rockwell hardness.
Rev Sci Instrum. Aug 1 2020;91(8):084102. Epub 2020/09/03.
18.   Rokidi S, Bravenboer N, Gamsjaeger S, Misof B, Blouin S, Chavassieux P, et al. Impact
microindentation assesses subperiosteal bone material properties in humans. Bone. Feb
2020;131:115110. Epub 20191023.
19.   Rokidi S, Bravenboer N, Gamsjaeger S, Chavassieux P, Zwerina J, Paschalis E, et al.
Impact microindentation measurements correlate with cortical bone material properties measured
by Fourier transform infrared imaging in humans. Bone. Aug 2020;137:115437. Epub 20200527.
20.   ASTM Standard E399-22, Standard Test method for linear-Elastic plane-Strain fracture
toughness of metallic materials PA: ASTM International; 2022.
21.   Rufus-Membere P, Holloway-Kew KL, Diez-Perez A, Appelman-Dijkstra NM, Bouxsein
ML, Eriksen EF, et al. Reference Intervals for Bone Impact Microindentation in Healthy Adults:
A Multi-Centre International Study. Calcif Tissue Int. Mar 2023;112(3):338-49. Epub
2023/02/03.
22.   Idkaidek A, Jasiuk I. Modeling of Osteoprobe indentation on bone. J Mech Behav
Biomed Mater. Feb 2019;90:365-73. Epub 2018/11/07.
23.   Diab T, Sit S, Kim D, Rho J, Vashishth D. Age-dependent fatigue behaviour of human
cortical bone. Eur J Morphol. Feb-Apr 2005;42(1-2):53-9.
24.   CLSI. Measurement procedure comparison and bias estimation using patient samples;
Approved guideline - 3rd edition. CLSI document EP09-A3 Wayne, PA. (2013);Clinical and
Laboratory Standards Institute.
25.   Peterlik H, Roschger P, Klaushofer K, Fratzl P. From brittle to ductile fracture of bone.
Nat Mater. Jan 2006;5(1):52-5. Epub 20051211.
26.   Sieverts M, Obata Y, Rosenberg JL, Woolley W, Parkinson DY, Barnard HS, et al.
Unraveling the effect of collagen damage on bone fracture using in situ synchrotron
microtomography with deep learning. Communications Materials. 2022;3(1):78.
27.   Phelps JB, Hubbard GB, Wang X, Agrawal CM. Microstructural heterogeneity and the
fracture toughness of bone. J Biomed Mater Res. Sep 15 2000;51(4):735-41. Epub 2000/07/06.
28.   Wang X, Shen X, Li X, Agrawal CM. Age-related changes in the collagen network and
toughness of bone. Bone. Jul 2002;31(1):1-7. Epub 2002/07/12.
29.   De Santis R, Anderson P, Tanner KE, Ambrosio L, Nicolais L, Bonfield W, et al. Bone
fracture analysis on the short rod chevron-notch specimens using the X-ray computer micro-
tomography. J Mater Sci Mater Med. Oct 2000;11(10):629-36. Epub 2004/09/07.
30.   Lucksanasombool P, Higgs WA, Higgs RJ, Swain MV. Fracture toughness of bovine
bone: influence of orientation and storage media. Biomaterials. Dec 2001;22(23):3127-32.
31.   Giavarina D. Understanding Bland Altman analysis. Biochem Med (Zagreb).
2015;25(2):141-51. Epub 20150605.
32.   Siris ES, Chen YT, Abbott TA, Barrett-Connor E, Miller PD, Wehren LE, et al. Bone
mineral density thresholds for pharmacological intervention to prevent fractures. Arch Intern
Med. May 24 2004;164(10):1108-12. Epub 2004/05/26.
33.   Leslie WD, Morin SN, Lix LM, Manitoba Bone Density P. Rate of bone density change
does not enhance fracture prediction in routine clinical practice. J Clin Endocrinol Metab. Apr
2012;97(4):1211-8. Epub 2012/01/27.
34.   McCalden RW, McGeough JA, Barker MB, Court-Brown CM. Age-related changes in
the tensile properties of cortical bone. The relative importance of changes in porosity,

mineralization, and microstructure. J Bone Joint Surg Am. Aug 1993;75(8):1193-205. Epub
1993/08/01.
35.   Wang H, Ba Y, Xing Q, Du J-L. Diabetes mellitus and the risk of fractures at specific
sites: a meta-analysis. BMJ open. 2019;9(1):e024067.
36.   Yeni YN, Brown CU, Wang Z, Norman TL. The influence of bone morphology on
fracture toughness of the human femur and tibia. Bone. Nov 1997;21(5):453-9. Epub
1997/11/14.
37.   Yeni YN, Brown CU, Norman TL. Influence of bone composition and apparent density
on fracture toughness of the human femur and tibia. Bone. Jan 1998;22(1):79-84. Epub
1998/01/23.
38.   Abraham AC, Agarwalla A, Yadavalli A, McAndrew C, Liu JY, Tang SY. Multiscale
Predictors of Femoral Neck In Situ Strength in Aging Women: Contributions of BMD, Cortical
Porosity, Reference Point Indentation, and Nonenzymatic Glycation. J Bone Miner Res. Dec
2015;30(12):2207-14. Epub 2015/06/11.
39.   Furst JR, Bandeira LC, Fan WW, Agarwal S, Nishiyama KK, McMahon DJ, et al.
Advanced Glycation Endproducts and Bone Material Strength in Type 2 Diabetes. J Clin
Endocrinol Metab. Jun 2016;101(6):2502-10. Epub 2016/04/27.
40.   Mellibovsky L, Prieto-Alhambra D, Mellibovsky F, Guerri-Fernandez R, Nogues X,
Randall C, et al. Bone Tissue Properties Measurement by Reference Point Indentation in
Glucocorticoid-Induced Osteoporosis. J Bone Miner Res. Sep 2015;30(9):1651-6. Epub
2015/03/05.
41.   Nogues X, Prieto-Alhambra D, Guerri-Fernandez R, Garcia-Giralt N, Rodriguez-Morera
J, Cos L, et al. Fracture during oral bisphosphonate therapy is associated with deteriorated bone
material strength index. Bone. Oct 2017;103:64-9. Epub 2017/06/29.
42.   Sundh D, Nilsson M, Zoulakis M, Pasco C, Yilmaz M, Kazakia GJ, et al. High-Impact
Mechanical Loading Increases Bone Material Strength in Postmenopausal Women-A 3-Month
Intervention Study. J Bone Miner Res. Jul 2018;33(7):1242-51. Epub 20180427.
43.   Nilsson AG, Sundh D, Johansson L, Nilsson M, Mellstrom D, Rudang R, et al. Type 2
Diabetes Mellitus Is Associated With Better Bone Microarchitecture But Lower Bone Material
Strength and Poorer Physical Function in Elderly Women: A Population-Based Study. J Bone
Miner Res. May 2017;32(5):1062-71. Epub 2016/12/13.
44.   Farr JN, Drake MT, Amin S, Melton LJ, 3rd, McCready LK, Khosla S. In vivo
assessment of bone quality in postmenopausal women with type 2 diabetes. J Bone Miner Res.
Apr 2014;29(4):787-95. Epub 2013/10/15.
45.   Malgo F, Hamdy NA, Papapoulos SE, Appelman-Dijkstra NM. Impact Microindentation:
Consistency of Serial Measurements and Alterations in Patients With Paget's Disease of the
Tibia. J Bone Miner Res. Dec 2017;32(12):2375-80. Epub 2017/08/18.
46.   Malgo F, Hamdy NAT, Rabelink TJ, Kroon HM, Claessen K, Pereira AM, et al. Bone
material strength index as measured by impact microindentation is altered in patients with
acromegaly. Eur J Endocrinol. Mar 2017;176(3):339-47. Epub 2017/01/13.
47.   Duarte Sosa D, Fink Eriksen E. Women with previous stress fractures show reduced bone
material strength. Acta Orthop. Dec 2016;87(6):626-31. Epub 20160620.
48.   Sosa DD, Eriksen EF. Reduced Bone Material Strength is Associated with Increased Risk
and Severity of Osteoporotic Fractures. An Impact Microindentation Study. Calcif Tissue Int. Jul
2017;101(1):34-42. Epub 20170228.

49.   Rozental TD, Walley KC, Demissie S, Caksa S, Martinez-Betancourt A, Parker AM, et
al. Bone Material Strength Index as Measured by Impact Microindentation in Postmenopausal
Women With Distal Radius and Hip Fractures. J Bone Miner Res. Apr 2018;33(4):621-6. Epub
20171205.
50.   Herrera S, Perez-Lopez J, Molto-Abad M, Guerri-Fernandez R, Cabezudo E, Novelli S,
et al. Assessment of Bone Health in Patients With Type 1 Gaucher Disease Using Impact
Microindentation. J Bone Miner Res. Jul 2017;32(7):1575-81. Epub 20170511.
51.   Perez-Saez MJ, Herrera S, Prieto-Alhambra D, Vilaplana L, Nogues X, Vera M, et al.
Bone density, microarchitecture, and material strength in chronic kidney disease patients at the
time of kidney transplantation. Osteoporos Int. Sep 2017;28(9):2723-7. Epub 20170511.
52.   Schoeb M, Malgo F, Peeters JJM, Winter EM, Papapoulos SE, Appelman-Dijkstra NM.
Treatments of osteoporosis increase bone material strength index in patients with low bone mass.
Osteoporos Int. Sep 2020;31(9):1683-90. Epub 20200408.
53.   Schoeb M, Winter EM, Sleddering MA, Lips MA, Schepers A, Snel M, et al. Bone
Material Strength Index as Measured by Impact Microindentation is Low in Patients with
Primary Hyperparathyroidism. J Clin Endocrinol Metab. Jun 16 2021;106(7):e2527-e34.
54.   Holloway-Kew KL, Betson A, Rufus-Membere PG, Gaston J, Diez-Perez A, Kotowicz
MA, et al. Impact microindentation in men with impaired fasting glucose and type 2 diabetes.
Bone. Jan 2021;142:115685. Epub 20201010.
55.   Rudang R, Zoulakis M, Sundh D, Brisby H, Diez-Perez A, Johansson L, et al. Bone
material strength is associated with areal BMD but not with prevalent fractures in older women.
Osteoporos Int. Apr 2016;27(4):1585-92. Epub 20151202.
56.   Popp KL, Caksa S, Martinez-Betancourt A, Yuan A, Tsai J, Yu EW, et al. Cortical Bone
Material Strength Index and Bone Microarchitecture in Postmenopausal Women With Atypical
Femoral Fractures. J Bone Miner Res. Jan 2019;34(1):75-82. Epub 20181105.
57.   Johansson L, Sundh D, Zoulakis M, Rudang R, Darelid A, Brisby H, et al. The
Prevalence of Vertebral Fractures Is Associated With Reduced Hip Bone Density and Inferior
Peripheral Appendicular Volumetric Bone Density and Structure in Older Women. J Bone Miner
Res. Feb 2018;33(2):250-60. Epub 20171115.
58.   Jaiswal R, Zoulakis M, Axelsson KF, Darelid A, Rudang R, Sundh D, et al. Increased
Bone Material Strength Index Is Positively Associated With the Risk of Incident Osteoporotic
Fractures in Older Swedish Women. J Bone Miner Res. Jun 2023;38(6):860-8. Epub 20230509.
59.   Diez-Perez A, Bouxsein ML, Eriksen EF, Khosla S, Nyman JS, Papapoulos S, et al.
Technical note: Recommendations for a standard procedure to assess cortical bone at the tissue-
level in vivo using impact microindentation. Bone Rep. Dec 2016;5:181-5. Epub 20160726.
463