Nutrient availability influences *E. coli* biofilm properties and the structure of purified curli amyloid fibers

Macarena Siri*[12], Mónica Vázquéz-Dávila[1], Cécile M. Bidan*[1]

1. *Max Planck Institute of Colloids and Interfaces, Department of Biomaterials, Potsdam14476, Germany*
2. *Max Planck Queensland Centre, Potsdam 14476, Germany*

*corresponding authors

ABSTRACT

Bacterial biofilms are highly adaptable and resilient to challenges. Nutrient availability can induce changes in biofilm growth, biomass, morphology, architecture and mechanical properties. Bacterial extracellular matrix plays a major role in achieving biofilm stability under different environmental conditions. Curli amyloid fibers are determining for the architecture and stiffness of *E. coli* biofilms, but how this major matrix component adapts to different environmental cues remains unclear.

Here, we investigated for the first time the effect of nutrient availability on both i) biofilm materials properties and ii) the structure and properties of curli amyloid fibers extracted from the biofilms. For this, we cultured *E. coli* W3110, which main matrix component is curli fibers. We quantified the size, mass and water content of the resulting biofilms and estimated their mechanical properties by microindentation. The curli amyloid fibers were then purified from the biofilms and their molecular structure and properties were studied by spectroscopic techniques. Our results show that the availability of nutrients in the substrate influences the yield of curli fibers, their structural composition and chemical stability, and suggest that these molecular features contribute to the stiffness of the biofilms. Biofilms grown on substrates with high nutrient concentration are softer, contain less curli fibers, and these fibers exhibit low β-sheet content and chemical stability.

Our multiscale study sheds new light on the relationship between the molecular structure of bacterial matrix and the macroscopic properties of biofilms. This knowledge will benefit the development of both anti-biofilm strategies and biofilm-based materials.

Keywords: biofilm, amyloids, *E. coli*, curli, protein structure, spectroscopy, mechanical properties

1 Graphical abstract

2
3

1 Introduction

Bacteria co-exist in a community where they produce an extracellular matrix. Such living material is called a biofilm. Biofilm matrix typically contains DNA, exo-polysaccharides and proteins.[1] Such ecosystems is a form of organization that, among other functions, protects the bacteria from environmental challenges. Biofilm properties thus depend on environmental physical cues such as temperature, pH and water availability.[2]

The availability of nutrients is also proposed to play a major role in the growth, phenotype, mechanical properties and matrix composition.[2–4] For instance, nutrient limitations in the substrate might lead to spatial gradients of activities and molecules influencing the functioning of biofilms.[5] Variation of nutrient availability and their effect on different biofilm aspects have been studied for different bacteria such as *Bacillus sp.*,[4,6] *P. fluorescence*[7,8] and *V. fischeri*[9]. The development and composition of biofilms can be influenced by nutrient availability through i) the variation of a specific nutrient,[9] ii) the effect of metabolites in bacterial growth rate and mechanical properties[10], iii) alteration of the environment by metabolites and iv) the addition of a substrate to promote the production of specific biopolymers by bacteria within the biofilm.[9–11] Nevertheless, how these variations affect the molecular properties of the bacterial matrix and impact biofilm properties remains to be understood.

In amyloid-containing biofilms, like in *E. coli* and *P. aeruginosa*, amyloid fibers are known as the backbone of the biofilm as they provide structural integrity.[12] In most cases, their molecular structure is influenced by the biofilm growth conditions.[7,13,14] There is also evidence of a correlation between the biofilm macroscopic properties (physico-chemical and mechanical) and the molecular composition and structure of the material (interactions and entanglement between the matrix polymers and charged smaller molecules).[2,7,14]

Typically, amyloid fibers have a characteristic and stable quaternary conformation: cross-β structure with the β-strands arranged perpendicular to the fiber axis.[15,16] Their structure and fibrillation mechanism have been studied throughout the years under *in vitro* conditions.[6,14,15,17] Nonetheless, different studies describe not only an interaction between amyloids and components found in the biofilm matrix[13], but also changes in the macroscopic features of the biofilm related to these protein assemblies.[3,7,12,14] This kind of evidence allows new questions regarding how the natural environment in which amyloids are fibrillated contribute to determine their final structure.

This work focuses on the influence of nutrient availability on the structure of biofilm amyloid fibers and biofilm mechanics. We used the *E. coli* strain K12 W3110 that only produces curli fibers as the main component of its matrix, and cultured biofilms on agar substrates with

different nutrient concentrations (i.e. yeast extract and tryptone). After 5 days, we quantified

the size, mass and water content of the biofilms and estimated their mechanical properties by

microindentation. Curli fibers were then purified from the biofilms, and fluorescence and ATR-

FTIR spectroscopy were used to study the differences in their structure and functional

properties like hydrophobicity and chemical stability. Overall, we provide knowledge to

deepen the understanding of the relation between molecular features of the matrix

components (e.g. fiber conformation) and macroscopic properties of the biofilm (e.g.

stiffness).

Results

Biofilm from *E. coli* K12 W3110 bacteria were grown on salt-free Lysogenic Broth (LB) agar

substrates with different nutrient contents (0.75, 1.5, 3.0, 6.0 and 12.0 % w/v) (**Figure S1,**

Table S1). We analyzed the macroscopic features (i.e. size, mass, bacterial growth rate, total

protein expression and biofilm stiffness) of the biofilms obtained in the different growth

conditions. Curli fibers were then purified from the different biofilms and their structural and

chemical characteristics were determined using spectroscopy techniques.

Of note, the agar composition containing 1.5 % nutrients is referred to as the standard biofilm

growth condition because it has the same composition as the LB agar plates used to grow

single bacterial colonies, without NaCl to promote biofilm formation.[18]

Nutrient availability influences biofilm size, mass and rigidity.

Variation in the nutrient availability of the agar substrate yielded biofilms different in size and

morphology (**Figure 1a-b** and **Figure S2**). The area of biofilms increased from 220.2 ± 31.6 mm^2

for substrates containing 0.75 % w/v nutrients, to 374.2 ± 15.8 mm^2 for substrates containing

3.0 % w/v nutrients. The biofilm size decreased for biofilms grown on salt-free LB agar

substrates containing higher nutrient content, reaching a size of 178.0 ± 34.7 mm^2 on

substrates containing 12.0 % w/v nutrients (**Figure 1b** and **Figure S2**). This last condition also

yielded biofilms different in shape (**Figure 1a** and **Figure S2**).

Along with their size, changes in the biofilm wet mass (M_{wet}) were quantified by weighing

(**Table 1**). We considered the *E. coli* W3110 biofilms wet mass (M_{wet}) as the sum of the masses

of i) the water, and ii) the bacteria and matrix, also considered as the dry mass (M_{dry}). Within

M_{dry}, we discriminate between i) curli fibers (as the main matrix component) and ii) bacteria

and other secondary matrix components. Biofilms grown on salt-free LB agar substrates

containing 6.0 % w/v nutrients showed the highest wet mass, while biofilms grown at low

nutrient availability (0.75 % w/v) presented the lowest wet mass (**Figure 1c**). The rest of the

conditions resulted in biofilms with similar wet mass. A similar trend was observed for the

estimated dry mass in the biofilms (M_{dry}) (**Figure S3** and **Table 1**).

We carried out microindentation experiments to study whether these changes in size and wet

mass had an effect on the stiffness of the biofilms (**Figure 1d** and **Figure S4**). The biofilm

stiffness was estimated by indenting up to 10 μm in the center of the biofilm (10 % of its

thickness approximately) to avoid influence of the substrate during the measurement (**Figure**

S4, inset). Biofilms grown on substrates containing 1.5 % w/v nutrients presented the highest

stiffness value, 15.28 ± 5.07 kPa (**Figure 1d**). Biofilms grown on substrates containing 3.0 and

12.0 % w/v nutrients showed the lowest values with 3.71 ± 2.78 and 4.26 ± 2.42 kPa,

respectively. Results suggest that the stiffness from the biofilm is independent of their size or

their wet mass.

Figure 1 Macroscopic properties of *E. coli* W3110 biofilms agar substrates with various nutrient concentrations.
(a) Representative phenotype of five-days old biofilms grown on substrates with different nutrient concentration.
Scale bar= 5 mm. (b) Biofilm size based on their area. The statistical analysis was done with Man Whitney U test
(p<0.0001, **** | p<0.001, *** | p<0.01, ** | p<0.05, * | ns = non-significant), where the 1.5 % w/v nutrient
concentration condition was used as reference. Data acquired from 15 independent biofilms per condition. (c)
Biofilm wet mass. Values are calculated for a single biofilm from four independent experiments. The statistical
analysis was done with One-way ANOVA (p<0.0001, **** | p<0.001, *** | p<0.01, ** | p<0.05, * | ns = non-
significant), where the 1.5 % w/v nutrient concentration condition was used as reference for the post-test
multicomparisons. (d) Averaged reduced Young's modulus obtained from microindentation experiments performed
on biofilm surfaces. 10–23 individual measurements were done per condition. The statistical analysis was done with
Man Whitney U test (p<0.00=1, **** | p<0.001, *** | p<0.01, ** | p<0.05, * | ns = non-significant), where the 1.5
% w/v nutrient concentration condition was used as reference for the post-test multicomparisons.

Substrate nutrient concentration (% w/v)	Biofilm size (mm)	Units	Total mass (M_{wet})	Water	Dry mass	CsgA[a]	Bacteria[a]
0.75	16.65 ± 1.49	mg	11.38 ± 2.60	8.35 ± 1.75	3.04 ± 0.86	0.01 ± 0.00	3.03 ± 0.86
		%	100	73	27	0.35	99.65
1.50	18.19 ± 1.92	mg	23.56 ± 2.53	17.57 ± 2.00	6.01 ± 0.57	0.02 ± 0.01	5.99 ± 0.57
		%	100	75	26	0.36	99.64
3.00	19.91 ± 2.06	mg	24.64 ± 1.28	18.38 ± 0.96	6.29 ± 0.32	0.03 ± 0.01	6.26 ± 0.32
		%	100	75	26	0.50	99.50
6.00	19.76 ± 1.59	mg	60.04 ± 4.79	40.24 ± 4.26	19.86 ± 0.96	0.05 ± 0.01	19.80 ± 0.97
		%	100	67	33	0.28	99.72
12.00	12.85 ± 0.91	mg	26.53 ± 4.74	17.63 ± 3.05	8.90 ± 1.69	0.01 ± 0.00	8.89 ± 1.69
		%	100	66	34	0.10	99.90

Nutrient availability influences biofilm composition and ability to uptake water.

Biofilms were further characterized to estimate their composition, including their water content and their water uptake ability (**Figure 2** and **Table 1**). The water content was assessed by weighing the biofilms before and after dehydration. Biofilms grown at low nutrient availability (0.75 – 3.0 % w/v) presented the highest water content c.a. 74 % w/w, while biofilms grown at high nutrient availability presented the lowest water content, approximately 66 % w/w (**Figure 2a**). The water uptake ability of the biofilms was tested upon overnight rehydration (**Figure 2b**). Except for biofilms grown on salt-free LB agar containing 3.0 and 6.0 % w/v nutrients, all biofilms presented a similar rehydration behavior. Biofilms grown at low nutrient availability (and at 12.0 % w/v nutrient concentration) absorbed 55 – 70 % more of water than their original weight. Biofilms grown on salt-free LB agar containing 3.0 and 6.0 % w/v nutrients absorbed 30 % of water more than their original weight. Analysis of the water uptake per gram of dry biofilm after rehydration showed that, the lower the nutrient availability, the higher the water uptake (**Figure 2c**).

To deepen our understanding on how the biofilm matrix changes with biofilm growth conditions, we focused on the biofilm composition and first estimated the total amount of proteins using a Bradford assay (see Experimental section for more details). Biofilms grown on salt-free LB agar containing 3.0 and 6.0 % w/v nutrients had the highest total protein concentration (**Figure 2d**). The trend observed for the biofilm protein concentration is similar to the one observed for the size and wet mass of the biofilms, as well as for the dry mass of

the biofilms (**Figure S3**). The SDS-PAGE electrophoresis gel run with aliquots of each total

protein extraction showed that the pattern of proteins expressed by the bacteria is similar

between conditions (**Figure 2e**).

To clarify whether these differences in protein production are due to the growth and the

metabolism of the bacteria, we monitored the bacteria growth for 8 hours in liquid salt-free LB

media and calculated their doubling time (T_d) (**Figure S5-S6**). While the growth curves and T_d

was similar for all conditions, the final optical density of the bacteria increased with the

nutrient availability in the media (**Figure S6**). The bacteria metabolic activity was also studied

in each phase of their growth curve (**Figure S6**). *E. coli* bacteria in liquid salt-free LB media

containing 12 % w/v nutrients were more metabolically active from the beginning of the

exponential phase compared to the other nutrient concentrations tested.

Among the proteins present in the biofilm, curli amyloid fibers are the main components in the

biofilm matrix. We purified them and estimated a yield by quantifying the monomeric unit

(CsgA) and normalizing per gram of dry biofilm (**Figure 2f**). Interestingly, biofilms grown on

salt-free LB agar substrates containing 12.0 % w/v yield two times less purified curli fibers

compared to the other conditions. No significant differences were observed for the other

yields in fiber production. We observe that the curli fibers yield does not follow the trend of

the biofilm total protein concentration, nor the trend of the bacterial metabolic activity.

However, there is a tendency for increased biofilm water uptake at higher fiber yields. (**Figure

S7**).

Figure 2 General characteristics of the composition of *E. coli* W3110 biofilms grown on substrates with different nutrient contents. (a) Biofilm water content. (b) Biofilm water uptake upon overnight rehydration of dry mass. (c) Biofilm water uptake per gram of dry mass. (d) Biofilm total protein concentration (see experimental section for details). (e) SDS-PAGE electrophoresis gel with showing the protein pattern of the samples studied in (d). (f) Purification yield of the curli fibers extraction process in milligram of CsgA per gram of dry mass. All data presented here come from N=4 independent biofilm cultures for each condition tested. The statistical analysis was done with One-way ANOVA ($p<0.0001$, **** | $p<0.001$, *** | $p<0.01$, ** | $p<0.05$, * | ns = non-significant), where the 1.5 % w/v nutrient concentration condition was used as reference for the post-test multicomparisons.

1 *Nutrient availability influences the packing and structure of curli amyloid fibers in the*

2 *biofilms*

The structure of curli fibers after the purification process was examined by transmission
electron microscopy (TEM), by Thioflavin T fluorescence emission (ThioT) and by Fourier
transform infrared (ATR-FTIR) spectroscopy (**Figure 3a-c**). TEM confirmed the presence of curli
fibers in the purified product (**Figure S7**). Following basic amyloid fiber characterization, we
stained the fibers with ThioT. This dye undergoes a fluorescence enhancement when
immobilized in the β-sheets of the amyloid fibers due to binding.[19] Despite every sample
having ThioT fluorescence emission, there were differences in the intensity values (**Figure 3a**).
When normalizing the intensity value against the free ThioT signal, fibers produced on
substrates containing 1.5 and 3.0 % w/v of nutrient showed an increase of c.a. 15 times of the
ThioT intensity (**Figure 3b**). Fibers produced in a context of higher or lower nutrient availability
showed only a five-fold increase in the ThioT intensity. The differences observed here suggest
differences in the packing or in the β-sheet content of the fibers.[14]
ATR-FTIR spectroscopy was used to further study the fiber structure (**Figure 3c-d**). We focused
on the amide I band (from 1700 to 1600 cm^{-1}), i.e. the fingerprint region for protein analysis
(**Figure 3c**).[20–22] All samples showed spectra expected for curli amyloid fibers (**Figure 3c** and
Figure S8): a band around 1620 cm^{-1} assigned to β-sheet structures, and second band around
1660 cm^{-1} usually assigned to β-turns structures.[14,15] The intensity and width of the band at
1660 cm^{-1} increased with the nutrient availability, indicating differences in the secondary
structure composition of the fibers (**Figure S8**). We used a band fitting method to decompose
the spectra into the secondary structure components (**Table 1**).[14,20] Purified curli fibers
obtained from biofilm grown at low nutrient availability (0.75 and 1.5% w/v) had the highest
content of β-sheet and the lowest content of β-turn structures (**Figure 3d** and **Table S3**). In
contrast, purified curli fibers obtained from biofilm grown at higher nutrient availability (3.0 –
12.0 % w/v) had the lowest content of β-sheet and the highest content of β-turn structures
(**Figure 3d** and **Table S3**). Differences in the β-sheet structure of the fibers was also observed
by CD spectroscopy (**Figure S9**). These results do not follow the trend presented in the ThioT
experiment, suggesting that the latter does not mainly report differences in β-sheet content.
Thus, in this case, differences in ThioT intensity mainly report differences in fiber packing.

Figure 3 Characterization of the structure of purified curli fibers. (a) ThioT fluorescence emission spectra of the fibers at equivalent mass concentrations. (b) Values describing the increase in intensity of ThioT when bound to the purified fibers. Quantification of the increase was estimated by division of the area under the curve of each spectra of the probe with each fiber by the area under the curve of the emission spectra of the probe alone. The statistical analysis was done with One-way ANOVA (p<0.001, *** | p<0.01, ** | p<0.05, * | ns = non-significant), where the 1.5 % w/v nutrient concentration condition was used as reference for the post-test multicomparisons. (c) Representative Amide I' region of an ATR-FTIR spectrum for curli fibers. Each peak assigned to the different secondary component is highlighted in their respective color. (d) Distribution of the three types of secondary structure in the curli fibers obtained in the different growth conditions. The data was obtained from the Amide I' region of each spectra. The statistical analysis was done with One-way ANOVA (p<0.0001, **** | p<0.001, *** | p<0.01, ** | p<0.05, * | ns = non-significant), where the 1.5 % w/v nutrient concentration condition was used as reference for the post-test multicomparisons.

Fiber packing and structure determine curli physico-chemical features

Since the structure of a molecule is often related to its properties and functions, we explored if the differences observed on the fiber conformation are reflected in their physico-chemical features. The global hydrophobic character of the purified curli fibers was studied by binding to Nile Red (NR) (**Figure 4a** and **S10a**). NR is a solvatochromic dye reporting the hydrophobic character of the molecule it binds to. As the emission spectrum of NR in buffer is different from the emission spectrum of NR in ethanol, we used these spectra as references to assess the hydrophobic character of the amyloid fibers obtained in the different conditions (**Figure**

4a). All purified fibers present a strong hydrophobicity. However, as the nutrient availability in

the substrate increased, the hydrophobic character of the fibers also increased (**Figure S10a**).

Curli fibers are made of CsgA monomers, each of them containing a single tryptophan (Trp).

Trp is an amino acid behaving as a solvatochromic fluorophore (**Figure S10b**),[14] which position

of maximum fluorescence emission gives information on the hydrophobicity of its

environment (**Figure 4b, inset**).[23] Curli fibers grown at a low nutrient concentration (0.75 %

and 1.5 % w/v) presented a Trp population in a less hydrophobic environment than the other

fibers.

Finally, we studied the implication of the different structures of purified curli fibers by testing

their chemical stability (**Figure 4c-d**). Fiber denaturation into CsgA monomers was monitored

by the fluorescence intensity emitted by ThioT.[14] Curli fibers obtained from biofilms grown on

salt-free LB agar containing 1.5 % w/v nutrients had the highest stability, while fibers grown at

lower nutrient availability (0.75 % w/v) or higher than 3.0 % w/v presented low chemical

stability (**Figure 4c**). Interestingly, fibers with a high packing degree and a high β-sheet content,

presented high chemical stability (**Figure 4e-f**). The higher the packing in the fiber, the higher

the chemical stability. While biofilm stiffness may be influenced by different fiber properties,

no further particular trend emerged (**Figure S11**).

Figure 4 **Structure-function features of the purified curli fibers.** (a) Fluorescence spectra of fibers stained with Nile

Red (NR). The spectra of NR in ethanol and in buffer are represented as references for the emission of NR in a

hydrophobic and hydrophilic environment, respectively. A sketch of the position of peaks for the NR in non-polar

and polar environments is represented in the inset.[24] The shadowed areas in the main plot indicate these exposure

extremes. N=3-4 independent biofilm cultures for each condition tested. (b) Intrinsic fluorescence of the fibers

through Trp emission. The spectrum of soluble Trp (NATA) in buffer is represented as reference for the maximum

exposure possible of the Trp to the surface (λ_{exc} = 280 nm). A sketch of the position of peaks for buried and exposed

Trp is represented in the inset.[25] The shadowed areas in the main plot indicate these exposure extremes. N=3-4

independent biofilm cultures for each condition tested. (c) Chemical stability of the purified fibers upon

denaturation with increasing urea concentrations (0.1 – 8 M). The presence of the fibers was observed by ThioT

fluorescence emission intensity. I_0 corresponds to the ThioT emission when bound to fibers without urea in the

solution. (d) IC50 values for each curve in panel (c) IC50 corresponds to the urea concentration at which the ThioT

intensity is 50 % of the initial one. (e) Relationship between fiber packing (ThioT ratio) and their chemical stability.

(f) Relationship between fiber β-sheet content and their chemical stability. N=6 independent fiber samples. The

statistical analysis was done with One-way ANOVA (p<0.0001, **** | p<0.001, *** | p<0.01, ** | p<0.05, * | ns =
non-significant), where the 1.5 % w/v nutrient concentration condition was used as reference for the post-test
multicomparisons.

Discussion

In the present work, we studied how nutrient availability influences *E. coli* biofilms from the
macroscopic to the molecular scale (**Figure 5**). The results show that biofilm size, mass and
rigidity change as the amount of surrounding nutrients varies (**Figure 1**). Such effects of yeast
extract and tryptone variations on macroscopic biofilm properties (e.g. morphology, thickness
and density) have been reported for other bacteria strains.[4,9,26] In the case of *E. coli* K12
W3110, we observed that the relation is not monotonic and rather shows a maximum of these
properties at intermediate nutrient availability, namely 6 % w/v for the size and mass and 1.5
% w/v for the stiffness (**Figure 1**). The existence of such optima may result from simultaneous
and opposite effects of substrates properties that cannot be decoupled from the nutrient
content. For example, both the presence of nutrients and water are expected to promote
biofilm growth respectively *via* the stimulation of bacterial activity, the lubrication of the
surface and biofilm swelling,[26,28] yet salt-free LB agar containing higher amounts of nutrients
also happen to contain less free water (**Figure S1 a-c**). Nutrient availability has also proven to
be as important at the initial steps of the biofilm formation e.g. in the layout of the bacteria,[29]
as at the later stages in which water channels form for nutrient distribution,[11] and gradients
are established.[30] The implication of nutrients at different hierarchical levels of the biofilm
architecture can thus explain the effect of their concentration on a broad range of biofilm
properties.[31]
23

Figure 5 Summary of the relationship between nutrient variation in the salt-free LB agar and the macro- and microscopic features of the biofilms grown under each condition. The figure serves as a visual global analysis of the data acquired and guide to the following discussion integrating the results obtained in this work. We indicate color shade the position of the parameter value in the column on the left of one of the conditions compared to the other conditions studied (yellow for the lowest value, to fuscia for the highest value).

As we decomposed the biofilm mass obtained into the contributions of water, bacteria and curli fibers, we observed that biofilm water content and curli fiber yield both tend to be higher when nutrients are less abundant (**Figure 2a** and **2f**). Although not the sole factor, amyloid fibers are known to contribute to keeping a hydrated microenvironment within biofilms.[32] This can be explained by the potential of amyloid fibers to take up and bind water (**Figure 2b and c**).[33] Our work suggests that this potential is enhanced when curli fibers are extracted from biofilms grown in environments with limited nutrients, as indicated by their higher polarity (**Figure 4a**). More generally, the water uptake of biofilms is regulated by the composition and characteristics of their extracellular matrix.[34] Indeed, biofilm matrix influences the osmotic pressure driving water flows leading to nutrient transport and subsequent bacterial growth, but also to biofilm expansion *via* matrix swelling, as showed for *B. subtilis* and *V. cholera*.[34,35] The trend of higher curli fiber yield when nutrients are less abundant is also consistent with bacteria having less metabolic and proliferation activities in such conditions (**Figure 2d** and **2e**). The nutrient concentration and more generally the composition of the substrate influence the composition of the biofilm matrix and subsequently biofilm properties.[4,9,11] In *B. subtilis* biofilms for example, the composition of the growth medium was shown to actively contribute

to the production, the distribution and the characteristics of the amyloid fibers found in the

extracellular matrix.[4] *V. fischeri* biofilms also acquire different morphologies and resistance to

mechanical disruption depending on the nutrients available to the bacteria.[9] Interestingly,

bacteria grown on agar with the highest nutrient content (12% w/v) produced smaller biofilms

containing less curli fibers (**Figure 1** and **2**). This observation is consistent with the general

understanding of matrix secretion and subsequent biofilm formation as part of the multiple

bacteria responses to starvation.[32,36]

Biofilms can be considered as hydrogels and their mechanical properties are expected to be

determined by both their network of biopolymers and their water content.[5] Here we observe

the counterintuitive result that biofilm stiffness is higher in conditions where biofilm water

content is larger (**Figure 1d** and **2a**). This can be explained by a denser biopolymer network as

indicated by the larger yield of curli fibers obtained in these conditions (**Figure 2f**). Beyond

their amount, curli fibers are likely to contribute to the macroscopic mechanical properties of

the biofilms through their molecular structure (**Figure S12**). Indeed, curli fibers are known for

the relatively high rigidity provided by the cross-β sheet arrangement adopted by the CsgA

subunit.[15,17,37] Variations in the conformation of the amyloid proteins are thus expected to

induce variations in the rigidity of the fibers, which in turn are expected to influence biofilm

stiffness. Consistently, analyzing the structure of the curli fibers extracted from biofilms

obtained in the various conditions revealed a relatively higher packing and β-sheet content,

when obtained from the stiffest biofilms, i.e. at 1.5 % w/v nutrient concentration (**Figure 2d,**

3b and **3d,** and **Figure S9**). We interpret the ThioT ratio of each fiber as fiber packing due to a

combined interpretation of the ATR-FTIR spectroscopy, CD spectroscopy and intrinsic

fluorescence analysis (**Figure 3d, Figure S9** and **Figure 4b**). Specifically, the curli fibers that

showed low ThioT intensity presented a low β-sheet content with ATR-FTIR and CD

spectroscopy as well as change in the Trp environment. Combined, these results suggests the

ThioT signal could be describing the fiber packing.[19] These structural variations could also

explain the different fluorescence emission spectra in the presence of Nile Red, and thus the

different amyloid fiber polarity measured as a function of nutrient availability during biofilm

growth (**Figure 4a** and **S10a**).[38] The same reasoning can apply to the Trp amino acid present in

the CsgA subunits, which intrinsic fluorescence indicates the hydrophobicity of its close

environment (**Figure 4b,** and **S10b**).[23] Testing the integrity of the different samples in the

presence of urea also revealed that the chemical stability of curli increases with fiber packing,

including an additional influence of their β-sheet content (**Figure 4d-f**). Considering the mode

of action of urea, this result is consistent with the idea that the access of urea to the peptide is

easier in loosely packed fibers, thus facilitating amyloid denaturation.[14,39]

The multiple experiments presented in this work converge to the major finding that nutrient

availability in the surroundings of the bacteria affects not only the production, but also the

structure of the curli amyloid fibers they produce (**Figure 6**). As this result may appear

surprising in light of the existing literature on the bacterial amyloid curli, it is important to

highlight that the structural investigations reported here were performed on amyloid curli

fibrillated *in vivo*, i.e. in the native biofilm micro-environment.[13] The present physico-chemical

context is thus significantly different, which may have a substantial impact on the resulting

fiber conformation. For example, bacterial cell membranes, as well as the presence of

lipopolysaccharides (LPS) may promote fiber aggregation.[13] The matrix molecular crowding,

especially the presence of extracellular DNA, is also contributing to the fibrillation process of

amyloid fibers.[13] Other environmental conditions, such as pH were also shown to influence this

process (although *in vitro*).[15]

Considering the protective function of biofilm matrix in challenging environments, one can

question whether these variations in curli structure and their implications at the biofilm scale

are the result of incidental physico-chemical interactions during the fibrillation process, or

whether *E. coli* bacteria actively tune this process to provide amyloid curli fibers with specific

properties (e.g. polarity, chemical stability, stiffness) in order to support the survival of the

community (e.g. nutrient storage and transport, water retention, physico-chemical shield).[32]

An attempt to address this point with further experiments indicates that these two hypotheses

are not necessarily exclusive (**Figure S13**). Indeed, after denaturing[40] the curli fibers and

repolymerizing the CsgA units in different media, the overall structural conformations of the

original fibers obtained from biofilms grown in different conditions was retained (**Figure S13g**

and h). Bacteria may thus produce CsgA monomers that are slightly different (probably in

structure) depending on the matrix fiber structure and properties they need to cope with the

given environment. Nevertheless, curli fibers reconstituted from CsgA monomers purified from

biofilms grown in abundance of nutrient (LB 6%w/v) also showed structural variations

depending on the re-fibrillation conditions (**Figure S13g and h**). Although the present approach

allowed us to establish a proof of feasibility, another approach yielding more purified curli

fibers is required to efficiently tackle the related questions about CsgA structure, adaptability,

and curli biogenesis.

In general, the fundamental outcomes of this work can have great implications for the

development of both anti-biofilm strategies and biofilm-based materials. Indeed, we found out

that *E. coli* form overall weaker biofilms when exposed to environments that are either very

poor or very rich in nutrients, mainly by altering the amount, packing and conformation of the

amyloid curli fibers constituting their extracellular matrix (**Figure 5**).[36] This information could

possibly motivate an overfeeding of bacteria coupled with antibiotic treatments to prevent the

formation of strong biofilms and simultaneously target the vulnerable bacteria.[41] In contrast,

the relatively more robust curli fibers harvested from biofilms formed by *E. coli* exposed to

intermediate nutrient levels may represent building blocks with high potential for making

amyloid-based materials.[42] The possibility of tuning properties of the bacterial amyloids *via* the

conditions of their genesis may even expand the range of possibilities in the emerging field of

engineered living materials.[43]

Experimental Section

Bacterial strain and growth

The biofilm-forming bacterial strain *E. coli* K-12 W3110 was used throughout this study. Salt-

free agar plates (15mm diameter) were prepared with 1.8% w/v of bacteriological grade

agar–agar (Roth, 2266), supplemented with 0.75%, 1.5%, 3.0%, 6.0% or 12.0% w/v tryptone

(Roth, 8952) and 0.25%, 0.5%, 1.0%, 2.0% and 4.0% w/v yeast extract (Roth, 2363),

respectively. After agar pouring, the plates were left to dry for 10 minutes with the lid open

and 10 minutes with the lid partially open to avoid future condensation. Each agar plate was

left to rest for 48 hours at room temperature before bacteria seeding. A suspension of bacteria

was prepared from a single colony and grown overnight in Luria–Bertani (LB) medium at 37 °C

with shaking at 250 rpm. Each plate was inoculated with arrays of 9 drops of 5µL of bacterial

suspension (OD600 ~ 0.5 after 10x dilution). After inoculation, the excess water evaporated

from the drops and left bacteria-rich dry traces of comparable sizes from 4 to 8mm diameter,

depending on the growth condition. Biofilms were grown for 5 days in total (~120h) inside an

incubator at 28 °C. Monitoring the relative humidity in the incubator showed that it remains

around 30 %RH.

Biofilm imaging

Three biofilms per condition were imaged with a stereomicroscope (AxioZoomV.16, Zeiss,

Germany) using the tiling function of the acquisition software (Zen 2.6 Blue edition, Zeiss,

Germany). To estimate the biofilm size, at least 12 independent biofilms were used to

calculate their area using the Fiji software.[44]

Biofilm dry mass and water uptake

The water content and water uptake of the biofilms were determined by scrapping 7 biofilms

per condition from the respective agar substrates after 5 days of growth (~120 h). Biofilms

were placed in plastic weighing boats, and oven-dried at 60 °C for 3 h. Wet and dry masses

(M_{wet}, M_{dry}) were determined before and after drying weighing the biofilm masses in an

analytical balance, sensing up to 3 decimal positions.[27] To determine the water uptake (W_{up}),

we added Millipure water in excess (5 mL) to the biofilms harvested from each condition,

covered them with aluminum foil to avoid evaporation and left overnight. The water excess

was removed and the biofilm samples were weighed again (M_{rewet}). The biofilms water content

in each growth condition was estimated with **Eq. (2)**

Eq. (2) $W = (M_{wet} - M_{dry})/M_{wet} \times 100\%$ w/w

The percentage of water uptake of biofilms after rehydration $(\%W_{up})$ was determined with

respect to the biofilm initial wet mass as described in **Eq. (3)**

Eq. (3) $\%W_{up} = (M_{rewet} - M_{dry})/M_{wet} \times 100 \% \ w/w$

The water uptake per gram of dry biofilm (W_{up}) was calculated with **Eq. (4)**

Eq. (4) $W_{up} = (M_{rewet} - M_{dry})/M_{dry}$

All procedures were carried out in four independent experiments.

Microindentation on biofilms

Biofilms were grown for 5 days and stored at 4 °C, the Petri dishes were sealed with parafilm

to prevent evaporation. A total of 4 biofilm samples were tested per condition.

Microindentation measurements were carried out using a TI 950 Triboindenter instrument

(Hysitron Inc.) to determine the load−displacement curves p−δ. The instrument was calibrated

in air. Indentations were performed with a spherical diamond tip of radius R = 50 µm on a

stage designed for the measurement of soft biological samples. The sample surface was

approached up to 400 - 300 µm above the surface and retracted to the starting position while

recording the measured force over the whole range. Loading rates ranged from 20 to 30 µm.s⁻

¹, which corresponds to loading and unloading times of 10 s. Between 8 and 10 measurements

were performed in the central region of each biofilm, which were still attached to the

respective agar substrates. Average and standard deviations were calculated over all

measurements from a respective condition. The lateral distance between two measurement

points was at least 200 µm in x and y directions. A Hertzian contact model was fitted to the

loading part of the curve (indentation depth range δ = 0−10 µm) to obtain the reduced Young's

modulus (see **Figure S3** for more details).

Biofilm total protein extraction and quantification

One biofilm per condition was scrapped and placed in an Epperndorf® tube with 200 µL of lysis

buffer (1% SDS, 1% RIPA, 1% Tritonx100). The biofilms were disrupted mechanically using a

XENOX MHX 68500 homogenizer for one minute, before being sonicated for 15 minutes in a

bath sonicator. After sonication, biofilms were again disrupted for one minute and incubated

at 26 °C for 20 minutes. The samples were then centrifuge at 17000 g for 10 minutes at 4 °C

and the pellet was discarded. Aliquots of 50 µL were taken and mixed with an equal volume of

an acetone/methanol 1:1 solution for protein precipitation. After an overnight incubation at -

20 °C, the samples were centrifuged at 18000 g for 30 minutes at 4 °C. The supernatant of each

sample was discarded and pellets were resuspended in 15 µL of PBS 1X for protein

quantification.

Protein quantification was done using a Bradford assay. Briefly, in a 96-well microplate, 5 µL of

sample was incubated with 195 µL of Bradford reagent (Quick Start™ Bradford 1x Dye Reagent

#5000205, BioRad). Absorbance was measured at 550 nm after a 5-10 minutes incubation

protected from the light. BSA (heat shock fraction, protease free, fatty acid free, essentially

globulin free, pH 7, ≥ 98%, (A7030) Sigma) was used in different concentrations as a calibration

curve. The experiments were repeated with three independent biofilms.

Bacterial growth curve

Salt-free Luria-Bertani liquid media were prepared at different nutrient concentrations for this

experiment (0.75, 1.5, 3.0, 6.0 or 12.0 % w/v). Single colonies of *E. coli* W3110 K-12 bacteria

were first grown on LB agar and were then inoculated in 10 mL of salt free LB media in 50 mL

Falcon® tubes (one single colony per condition). The cultures were grown aerobically in a

shaker (250 rpm) at 37 °C for 8 hours. Bacterial growth was monitored by measuring the

OD_{600nm} of each culture every 30 minutes (see **Figure S4-5**). Three independent samples were

tested for each condition.

The doubling time (T_d) of each independent growth curve was calculated as **Eq. (5)**

Eq. (5) $T_d = \frac{ln2}{B}$

Where B is derived from the exponential fit of the linear part of the growth curve (see **Figure**

S4-5 for more details).

Bacterial metabolic activity (MTT)

Salt-free Luria-Bertani liquid media were prepared containing different nutrient concentrations

for this experiment (0.75, 1.5, 3.0, 6.0 or 12.0 % w/v). Single colonies of *E. coli* W3110 K-12

bacteria were first grown on LB agar and were then inoculated in 10 mL of salt free LB media in

50 mL Falcon® tubes (one single colony per condition). The cultures were grown aerobically in

a shaker (250 rpm) at 37 °C for 8 hours. Aliquots of sample from the liquid cultures were taken

at 60, 120, 240 and 360 minutes after the start point of the experiment to measure the

metabolic activity of the bacteria. A protocol adapted from Oh et al.[45] was used to perform an

MTT (3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide) assay.

Briefly, 100 µL of sample were washed twice in PBS 1X by centrifugation at 1000 g for 5

minutes at 4 °C. The pellet was resuspended to a final volume of 100 µL PBS 1X. In a 96-well

microplate, each sample was incubated with 10 µL of MTT 0.5 mg/mL in PBS for 15 minutes at

37 °C, protected from the light. After incubation, 100 µL of NaOH 1M was added to each

sample in order to solubilize the formazan crystals. Absorbance values were recorded at 570

nm and PBS 1X was used as blank. The experiment was done with three independent bacteria

liquid cultures per condition.

Curli fiber purification

Fiber purification involved a similar process as reported in previous works.[14,46] Briefly, a total of

27 biofilms (~ 1 g of biofilm material) were scraped from the surface of the substrates. Biofilms

were blended five times on ice with an XENOX MHX 68500 homogenizer for 1 minute at 2-

minute intervals. The bacteria were pelleted by centrifuging two times at low speed (5000 g at

4 °C for 10 min). A final concentration of NaCl 150 mM was added to the supernatant and the

curli pelleted by centrifuging at 12.000 g at 4 °C for 10 minutes. The pellet was resuspended in

1 mL of solution containing 10 mM tris (pH 7.4) and 150 mM NaCl, and incubated on ice for 30

min before being centrifuged at 16.000 g at 4 °C for 10 minutes. This washing procedure was

repeated thrice. The pellet was then resuspended in 1 mL of 10 mM tris solution (pH 7.4) and

pelleted as described above (16.000 g at 4 °C for 10 minutes). The pellet was again suspended

in 1 mL of 10 mM tris (pH 7.4) and centrifuged at 17.000 g at 4 °C for 10 minutes. This washing

step was repeated twice. The pellet was then resuspended in 1 mL of SDS 1 % v/v solution and

incubated for 30 min. The fibers were pelleted by centrifuging at 19.000 g at 4 °C for 15 min.

The pellet was resuspended in 1 mL of Milli-Q water. This washing procedure was repeated

thrice. The last resuspension was done in 0.1 mL of Milli-Q water supplemented with 0.02 %

sodium azide. The fiber suspension was stored at 4 °C for later use. The protein concentration

in monomeric units of the suspensions was determined by the absorbance from an aliquot

incubated in 8 M urea at 25 °C for 2 h, a treatment leading to complete dissociation of the

fibrils as verified by Thioflavin T measurements.

Transmission electron microscopy (TEM)

2 μL drops of fiber suspension were adsorbed onto Formvar-coated carbon grids (200 mesh),

washed with Milli-Q water, and stained with 1 % w/v uranyl acetate. The samples were imaged

in a JEOL-ARM F200 transmission electron microscope (JEOL GmbH, Germany) equipped with

two correctors for imaging and probing. For the observations, we applied an acceleration

voltage of 200 kV.

Attenuated total reflectance Fourier transform infrared spectroscopy (ATR-FTIR)

IR spectra were acquired with a spectrophotometer (Vertex 70v, Bruker Optik GmbH,

Germany) equipped with a single reflection diamond reflectance accessory continuously

purged with dry air to reduce water vapor distortions in the spectra. Fibers samples in Milli-Q

water (~10 µL) were spread on a diamond crystal surface, dried under N_2 flow to obtain the

protein spectra. A total of 64 accumulations were recorded at 25 °C using a nominal resolution

of 4 cm^{-1}.

Spectra were processed using Kinetic software developed by Dr. Erik Goormaghtigh at the

Structure and Function of Membrane Biology Laboratory, Université Libre de Bruxelles,

Brussels, Belgium. After subtraction of water vapor and side chain contributions, the spectra

were baseline corrected and area normalized between 1700 and 1600 cm^{-1} (**Figure S7**). For a

better visualization of the overlapping components arising from the distinct structural

elements, the spectra were deconvoluted using Lorentzian deconvolution factor with a full

width at the half maximum (FWHM) of 20 cm^{-1} and a Gaussian apodization factor with a

FWHM of 30 cm^{-1} to achieve a line narrowing factor K = 1.5.[21] Second derivative was

performed on the Fourier self-deconvoluted spectra for band assignment. The bands identified

by both procedures were used as initial parameters for a least square iterative curve fitting of

the original IR band (K = 1) in the amide I' region, using mixed Gaussian/Lorentzian bands. Peak

positions of each identified individual component were constrained within ±2 cm^{-1} of the

initial value.

Table 2 FWHH input values in cm^{-1} and their physically plausible ranges expected for each type of secondary
structure[16, 20, 21]

Secondary structure component		FWHH input (cm^{-1})	Lower limit (cm^{-1})	Upper limit (cm^{-1})
β-sheet	High wavenumber component	9	8	11
	Low wavenumber component	17	14	19
α-helix/ random		20	5	30
Turns		20	5	30

Fluorescence spectroscopy

Corrected steady-state emission spectra were acquired with a FluoroMax®-4

spectrofluorometer (HORIBA). Spectra were recorded at 25 °C using a 3-mm path cuvette

(Hellma® Analytics). Thioflavin T(ThioT) measurements were performed at final concentrations

of 3 µM protein, 1 mM probe in Glycine buffer, pH 8.2, using λ_{exc} = 446 nm and spectral

bandwidths of 10 nm. Nile red (NR) measurements were performed at a final concentration of

7 µM protein, 7 mM probe in water, using λ_{exc} = 560 nm and spectral bandwidths of 10 nm.

Intrinsic fluorescence spectra (5 µM protein) were acquired using λ_{exc}= 280 nm and 5/5 nm slit

bandwidths. 5 µM solution of soluble Trp (N-Acetyl-L-tryptophan, NATA) was included as a

reference of the emission spectrum of a fully exposed Trp.

Chemical stability assay

To test the chemical stability of the protein fibers, 5 μM samples were prepared by incubation

of increasing urea concentration (0 – 8 M) and left for 2 h at room temperature to ensure

equilibrium. ThioT was then added in a final concentration of 1 mM and fluorescence emission

spectra of the samples were acquired under excitation at λ_{exc} = 446 nm and spectral bandwidth

of 5 nm. Emission of the ThioT in urea was done and no significant signal was detected.

The IC50 value was estimated by fitting the data to a linear regression (Y = a * X + b) and then

calculating IC50 = (0.5 - b)/a.

Statistical analysis

For each experiment, 3 to 4 fiber solutions were used, where each solution came from

different fiber purification batches. For each purification, 27 biofilms were cultured in each of

the 5 growth conditions tested (i.e. on salt-free LB-agar plate containing 0.75 %, 1.5 %, 3.0 %,

6.0 % and 12.0 % w/v nutrient, respectively). For each batch of biofilm culture, the different

samples of fibers obtained were treated simultaneously (or in consecutive days) to prevent

variability due to unavoidable slight variations in the implementation of the protocols (e.g.

temperature and humidity in the laboratory during agar preparation and/or biofilm seeding).

For statistical analysis, a One-way ANOVA test was carried out. Mechanical properties data

was analyzed using a Mann-Whitney U test. Unless otherwise stated in the caption, Dunn's

post-test for multiple comparisons were done with respect to the 1.5 % w/v nutrient salt-free

LB-agar condition, considered as the standard seeding condition. Details of each test are

described in the legend of the figures.

Supporting Information

The following files are available free of charge:

• Table S1: Composition of salt-free LB agar substrates

• Figure S1: Characterization of the salt-free LB-agar substrates

• Figure S2: Biofilm morphology

• Figure S3: Microindentation loading curve

• Table S2: Composition of the *E. coli* W3110 biofilms grown on substrates of different

nutrient concentration

• Figure S4: Biofilm mass

• Figure S5: Bacteria growth curve

• Figure S6: Bacteria in liquid media

- Figure S7: B Purified curli fiber TEM images
- Figure S8: ATR- FTIR spectra of the purified curli fibers
- Table S3: Secondary structure analysis of the purified curli fibers assessed by ATR-FTIR
- Figure S9: Fiber structure by circular dichroism (CD) spectroscopy
- Figure S10: Fiber polarity
- Figure S11: Curli fibers and the CsgA subunit
- Figure S12: Relationship structure/function between purified curli fibers and the biofilm mechanical properties
- Figure S13: Proof of concept: from purified curli fibers to CsgA to fibers again

Data Availability Statement

The data that support the findings of this study are available from the corresponding authors upon reasonable request.

AUTHOR INFORMATION

Corresponding Author

*Macarena Siri: macarena.siri@mpikg.mpg.de

*Cécile M. Bidan: cecile.bidan@mpikg.mpg.de

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript. The authors declare no competing interests.

CRediT author statement

Conceptualization: C.M.B and M.S. **Visualization:** C.M.B and M.S. **Methodology:** C.M.B and M.S. **Investigation:** M.S, and M.V.D. **Writing Original Draft:** M.S **– Review and Editing:** C.M.B and M.S. **Supervision:** C.M.B. **Project Administration:** C.M.B. **Resources:** C.M.B.

ACKNOWLEDGMENT

M.S. acknowledges support from the Max Planck Queensland Centre on the Materials Science for Extracellular Matrices. The authors also thank Christine Pilz-Allen for her technical support in the laboratories and Heike Runge for her help in doing the transmission electronic microscopy experiments. The authors are grateful to Dr. Agustín Mangiarotti for the useful discussions throughout this study. The authors are also grateful to Regine Hengge (HU Berlin)

for providing the *E. coli* strain W3110 and to Eric Goormaghtigh from the SFMB group at the Université Libre de Bruxelles for providing the Kinetics Software.

References

1. Serra, D. O. & Hengge, R. Stress responses go three dimensional - The spatial order of physiological differentiation in bacterial macrocolony biofilms. *Environ. Microbiol.* **16**, 1455–1471 (2014).

2. Flemming, H. C. *et al.* The biofilm matrix: multitasking in a shared space. *Nat. Rev. Microbiol.* **0123456789**, (2022).

3. Chen, D. *et al.* Characteristics and influencing factors of amyloid fibers in S. mutans biofilm. *AMB Express* **9**, 1–9 (2019).

4. Chaves, S. *et al.* Control of microbial biofilm formation as an approach for biomaterials synthesis. *Colloids Surfaces B Biointerfaces* **194**, (2020).

5. Wilking, J. N., Angelini, T. E., Seminara, A., Brenner, M. P. & Weitz, D. A. Biofilms as complex fluids. *MRS Bull.* **36**, 385–391 (2011).

6. Liu, S. *et al.* Probing the growth and mechanical properties of Bacillus subtilis biofilms through genetic mutation strategies. *Synth. Syst. Biotechnol.* **7**, 965–971 (2022).

7. Zeng, G. *et al.* Functional bacterial amyloid increases Pseudomonas biofilm hydrophobicity and stiffness. *Front. Microbiol.* **6**, 1–14 (2015).

8. Allen, A., Habimana, O. & Casey, E. The effects of extrinsic factors on the structural and mechanical properties of Pseudomonas fluorescens biofilms: A combined study of nutrient concentrations and shear conditions. *Colloids Surfaces B Biointerfaces* **165**, 127–134 (2018).

9. Marsden, A. E., Grudzinski, K., Ondrey, J. M., DeLoney-Marino, C. R. & Visick, K. L. Impact of salt and nutrient content on biofilm formation by Vibrio fischeri. *PLoS One* **12**, 1–19 (2017).

10. Bowden, G. H. & Li, Y. H. Nutritional influences on biofilm development. *Adv. Dent. Res.* **11**, 81–99 (1997).

11. Bottura, B., Rooney, L. M., Hoskisson, P. A. & McConnell, G. Intra-colony channel morphology in Escherichia coli biofilms is governed by nutrient availability and substrate stiffness. *Biofilm* **4**, 100084 (2022).

12. Romero, D., Aguilar, C., Losick, R. & Kolter, R. Amyloid fibers provide structural integrity to Bacillus subtilis biofilms. *Proc. Natl. Acad. Sci. U. S. A.* **107**, 2230–2234 (2010).

13. Akbey, Ü. & Andreasen, M. Functional amyloids from bacterial biofilms – structural properties and interaction partners. *Chem. Sci.* **13**, 6457–6477 (2022).

14. Siri, M., Mangiarotti, A., Vázquez-Dávila, M. & Bidan, C. M. Curli fibers in Escherichia coli biofilms: the influence of water availability on amyloid structure and properties. *Macromol. Biosci.* 2022.11.21.517345 (2023) doi:doi.org/10.1002/mabi.202300234.

15. Dueholm, M. S. *et al.* Fibrillation of the major curli subunit CsgA under a wide range of conditions implies a robust design of aggregation. *Biochemistry* **50**, 8281–8290 (2011).

16. Siri, M., Herrera, M., Moyano, A. J. & Celej, M. S. Influence of the macromolecular crowder alginate in the fibrillar organization of the functional amyloid FapC from Pseudomonas aeruginosa. *Arch. Biochem. Biophys.* **713**, 109062 (2021).

17. Sleutel, M., Pradhan, B., Volkov, A. N. & Remaut, H. Structural analysis and architectural principles of the bacterial amyloid curli. *Nat. Commun.* **14**, 1–14 (2023).

18. Serra, D. O., Klauck, G. & Hengge, R. Vertical stratification of matrix production is essential for physical

integrity and architecture of macrocolony biofilms of Escherichia coli. *Environ. Microbiol.* **17**, 5073–5088 (2015).

19. Biancalana, M. & Koide, S. Molecular mechanism of Thioflavin-T binding to amyloid fibrils. *Biochim. Biophys. Acta - Proteins Proteomics* **1804**, 1405–1412 (2010).

20. Sarroukh, R., Goormaghtigh, E., Ruysschaert, J. M. & Raussens, V. ATR-FTIR: A 'rejuvenated' tool to investigate amyloid proteins. *Biochim. Biophys. Acta - Biomembr.* **1828**, 2328–2338 (2013).

21. GOORMAGHTIGH, E., CABIAUX, V. & RUYSSCHAERT, J. -M. Secondary structure and dosage of soluble and membrane proteins by attenuated total reflection Fourier-transform infrared spectroscopy on hydrated films. *Eur. J. Biochem.* **193**, 409–420 (1990).

22. Moran, S. D. & Zanni, M. T. How to get insight into amyloid structure and formation from infrared spectroscopy. *J. Phys. Chem. Lett.* **5**, 1984–1993 (2014).

23. Eftink, M. R. Fluorescence Techniques for Studying Protein Structure. in *Methods of Biochemical Analysis* 127–205 (1991). doi:https://doi.org/10.1002/9780470110560.ch3.

24. Jameson, D. M. Introduction to Fluorescence. *Principles of Fluorescence Spectroscopy* 1–26 at https://doi.org/10.1007/978-0-387-46312-4_1 (2006).

25. Lakowicz, J. R. *Principles of fluorescence spectroscopy, 3rd Principles of fluorescence spectroscopy, Springer, New York, USA, 3rd edn, 2006. Principles of fluorescence spectroscopy, Springer, New York, USA, 3rd edn, 2006.* (2006). doi:10.1007/978-0-387-46312-4.

26. Soares, A., Gomes, L. C., Monteiro, G. A. & Mergulhão, F. J. The influence of nutrient medium composition on escherichia coli biofilm development and heterologous protein expression. *Appl. Sci.* **11**, (2021).

27. Ziege, R. *et al.* Adaptation of Escherichia coli Biofilm Growth, Morphology, and Mechanical Properties to Substrate Water Content. *ACS Biomater. Sci. Eng.* **7**, 5315–5325 (2021).

28. Trinschek, S., John, K., Lecuyer, S. & Thiele, U. Continuous versus Arrested Spreading of Biofilms at Solid-Gas Interfaces: The Role of Surface Forces. *Phys. Rev. Lett.* **119**, 1–5 (2017).

29. Nijjer, J. *et al.* Mechanical forces drive a reorientation cascade leading to biofilm self-patterning. *Nat. Commun.* **12**, (2021).

30. Jo, J., Price-Whelan, A. & Dietrich, L. E. P. Gradients and consequences of heterogeneity in biofilms. *Nat. Rev. Microbiol.* **20**, 593–607 (2022).

31. Serra, Di. O. & Hengge, R. Bacterial Multicellularity: The Biology of Escherichia coli Building Large-Scale Biofilm Communities. *Annu. Rev. Microbiol.* **75**, 269–290 (2021).

32. Flemming, H. C. & Wingender, J. The biofilm matrix. *Nat. Rev. Microbiol.* **8**, 623–633 (2010).

33. Thirumalai, D., Reddy, G. & Straub, J. E. Role of water in protein aggregation and amyloid polymorphism. *Acc. Chem. Res.* **45**, 83–92 (2012).

34. Ido, N. *et al.* Bacillus subtilis biofilms characterized as hydrogels. Insights on water uptake and water binding in biofilms. *Soft Matter* **16**, 6180–6190 (2020).

35. Yan, J., Nadell, C. D., Stone, H. A., Wingreen, N. S. & Bassler, B. L. Extracellular-matrix-mediated osmotic pressure drives Vibrio cholerae biofilm expansion and cheater exclusion. *Nat. Commun.* **8**, (2017).

36. Nguyen, D. *et al.* Active Starvation Responses Mediate Antibiotic Tolerance in Biofilms and Nutrient-Limited Bacteria. *Science (80-.).* **334**, 982–986 (2011).

37. Evans, M. L. & Chapman, M. R. Curli biogenesis: Order out of disorder. *Biochim. Biophys. Acta - Mol. Cell Res.* **1843**, 1551–1558 (2014).

38. Mishra, R., Sjölander, D. & Hammarström, P. Spectroscopic characterization of diverse amyloid fibrils in

vitro by the fluorescent dye Nile red. *Mol. Biosyst.* **7**, 1232–1240 (2011).

39. Zou, Q., Habermann-Rottinghaus, S. M. & Murphy, K. P. Urea effects on protein stability: Hydrogen bonding and the hydrophobic effect. *Proteins Struct. Funct. Genet.* **31**, 107–115 (1998).

40. Christensen, L. F. B., Nowak, J. S., Sønderby, T. V., Frank, S. A. & Otzen, D. E. Quantitating denaturation by formic acid: imperfect repeats are essential to the stability of the functional amyloid protein FapC. *J. Biol. Chem.* **295**, 13036–13041 (2020).

41. Mishra, R. *et al.* Natural Anti-biofilm Agents: Strategies to Control Biofilm-Forming Pathogens. *Front. Microbiol.* **11**, (2020).

42. Duraj-Thatte, A. M. *et al.* Water-processable, biodegradable and coatable aquaplastic from engineered biofilms. *Nat. Chem. Biol.* **17**, 732–738 (2021).

43. Nguyen, P. Q., Courchesne, N. M. D., Duraj-Thatte, A., Praveschotinunt, P. & Joshi, N. S. Engineered Living Materials: Prospects and Challenges for Using Biological Systems to Direct the Assembly of Smart Materials. *Adv. Mater.* **30**, 1–34 (2018).

44. Schindelin, J. *et al.* Fiji: An open-source platform for biological-image analysis. *Nat. Methods* **9**, 676–682 (2012).

45. Oh, Y. J. & Hong, J. Application of the MTT-based colorimetric method for evaluating bacterial growth using different solvent systems. *Lwt* **153**, 112565 (2022).

46. Chapman, M. R. *et al.* Role of Escherichia coli curli operons in directing amyloid fiber formation. *Science (80-.).* **295**, 851–855 (2002).