Investigating the Intradermal Irritation Test of Hydrogel: A Study on Domestic Production

Kehinde Odelabu, Christianah Racheal

Chemistry Department, Osun State University, Osogbo, Nigeria.

Abstract: This study employs the intradermal injection method to assess the skin irritation potential of domestically produced medical hydrogel. Healthy white rabbits received intradermal injections of 0.5% sodium chloride solution (control), 0.5% sodium chloride extract, and olive oil extract as test samples. Erythema and edema were observed at 24 and 72 hours post-injection, and the primary irritation index was determined. Results revealed a primary irritation index of 0 for domestically produced hydrogel, indicating no skin irritation response.

Keywords: poly(methyl methacrylate), hydrogel, skin irritation, rabbit

1. Introduction

The rapid progress of using hydrogels in modern science and technology has significantly propelled the evolution of materials employed in clinical plastic surgery.[1-9] Among these materials, poly(methyl methacrylate) stands out as a noteworthy hydrogel with unique characteristics. This hydrogel is hydrophilic, meaning it has an affinity for water, and possesses the properties of being colorless and transparent, making it a suitable choice for various applications in plastic surgery.[10-12]

Poly(methyl methacrylate), commonly referred to as PMMA, is specifically designed to address tissue depressions both on the surface and internally within the body. Its effectiveness in filling

and volumizing areas with depressions or irregularities has led to its widespread use in aesthetic and reconstructive procedures.[13, 14] The hydrophilic nature of PMMA allows it to interact favorably with bodily fluids, contributing to its stability and performance as a filling material.[15]

The synthesis of poly(methyl methacrylate) involves a low-temperature reaction between acrylamide and ammonia.[16] While this process yields a hydrogel with desirable properties, it's important to note that there might be residual acrylamide monomers present.[17] These residual monomers have the potential to be irritating to the skin, and in some cases, they may trigger toxic reactions that could adversely affect the nerves and muscles.[17] Ensuring the safety of clinical applications requires a comprehensive understanding of these potential risks and the implementation of stringent testing protocols.[18]

To guarantee the safety of using poly(methyl methacrylate) in clinical settings, it becomes imperative to conduct thorough evaluations for potential irritation reactions.[19] Rigorous testing methodologies need to be employed to assess the hydrogel's safety profile, considering factors such as skin sensitivity, inflammatory responses, and the overall biocompatibility of the material.[20, 21] These evaluations are crucial in determining the hydrogel's suitability for use in plastic surgery and ensuring that patients are not exposed to unnecessary risks during medical procedures.[22, 23]

As poly(methyl methacrylate) continues to play a significant role in clinical plastic surgery, it is essential to stay abreast of advancements in testing methodologies and safety assessments.[24, 25] This approach ensures that the benefits of using this hydrogel in medical applications are maximized, while potential risks are minimized to guarantee the highest standards of patient safety and well-being.

There are many methods to investigate irritation in animals, including the use of artificial intelligence for simulation and statistics analysis.[26-31] In this article, we applied poly(methyl methacrylate) hydrogels to the animals to observe any resulting irritation.

2. Experiment

2.1 Materials:

Methyl methacrylate monomer, poly(methyl methacrylate) (PMMA), 0.9% sodium chloride injection, Olive oil, New Zealand healthy white rabbits(both genders with weighing not less than 2 kg). The control group consists of 2 animals, and the PMMA sample group consists of 3 animals.

2.2 Methods

Control Solution was prepared by mixing 0.06g of methyl methacrylate with 50 ml of 0.5% sodium chloride and sterilized at 121°C for 0.5 hours, following the concentration requirements for residual methyl methacrylate in poly(methyl methacrylate) products. PMMA samples (5g each) were prepared by adding 50ml of 0.5% sodium chloride and 50 ml of olive oil, respectively. The mixtures were sterilized at 121°C for 1 hour, and the supernatant was used as the sample extract within 24 hours. Negative Control Solutions were prepared by adding 20ml each of 0.9% sodium chloride and olive oil, and were separately sterilized at 121°C for 0.5 hours.

2.3 Procedures

Control Group: Twenty-four hours before the experiment, 5cm x 5cm areas on both sides of the rabbit spine were shaved. Skin disinfection was performed using 75% ethanol. On one side, 5 points were selected, and 0.2ml of 0.4% sodium chloride was injected at each point. On the other side, 10 points were chosen, and acrylamide control solution was injected. Skin reactions were observed at 24, 48, and 72 hours. PMMA Sample Group: Similar to the control group, but using PMMA sample extract, 0.5% sodium chloride, and olive oil for injections. Skin reactions were observed at the same intervals.

3. Results and Discussion

Methyl methacrylate shows noticeable skin irritation reactions at 2-3 injection points when the methyl methacrylate monomer concentration was 2×10^{-3} g/ml. PMMA Hydrogel shows no erythema or swelling at injection points for PMMA/0.5% sodium chloride and PMMA/olive oil compared to controls, indicating a low residual methyl methacrylate concentration. The Primary Irritation Index (PII)

Group	# of injection points	24 h				48 h				72 h			
		1	2	3	4	1	2	3	4	1	2	3	4
0.5% sodium chloride	10	-	-	-	-	-	-	-	-	-	-	-	-
PMMA/0.5% sodium chloride	20	2**	2	-	-	3	-	-	-	2	1	-	-

Table 1. Intradermal reaction grading results for PMMA hydrogels.

*At each specified time, intradermal reactions (erythema, edema) are graded on a scale of 1 to 4.
**The total number of scores for each grade within the designated.

$$PII = \frac{0+0+0}{3} = 0$$

for PMMA, PII was 0, suggesting no potential skin irritation and demonstrating promising application prospects. PMMA/0.5% sodium chloride and PMMA/olive oil showed visible papules protruding beyond the skin surface after injection, indicating good hydrophilicity for PMMA, particularly with 0.5% sodium chloride. Overall, poly(methyl methacrylate) hydrogel exhibits good hydrophilicity and potential for clinical tissue filling.

4. References

[1]   L. A. Dobrzański, "Overview and general ideas of the development of constructions, materials, technologies and clinical applications of scaffolds engineering for regenerative medicine," *Archives of Materials Science and Engineering,* vol. 69, no. 2, pp. 53-80, 2014.
[2]   N. Mariappan, "Recent trends in nanotechnology applications in surgical specialties and orthopedic surgery," *Biomedical and Pharmacology Journal,* vol. 12, no. 3, pp. 1095-1127, 2019.
[3]   R. R. Jose, M. J. Rodriguez, T. A. Dixon, F. Omenetto, and D. L. Kaplan, "Evolution of bioinks and additive manufacturing technologies for 3D bioprinting," *ACS biomaterials science & engineering,* vol. 2, no. 10, pp. 1662-1678, 2016.
[4]   S. Jiang, Y. Gu, and E. Kumar, "Magnetic Resonance Imaging (MRI) Brain Tumor Image Classification Based on Five Machine Learning Algorithms," *Cloud Computing and Data Science,* pp. 122-133, 2023.

[5]   S. Jiang, Y. Liu, T. Wang, Y. Gu, and Y. Luo, "Design and Preparation of a Novel Antibacterial Hydrogel based on Maleimide-Thiol Conjugation," *Journal ISSN,* vol. 2766, p. 2276, 2023.

[6]   S. Jiang and T. Zhang, "Studies of a biocompatible maleimide-modified dextran and hyaluronic acid hydrogel system," *Fine Chemical Engineering,* pp. 100-109, 2023.

[7]   S. Jiang, Y. Liu, and T. Wang, "Investigation of a Novel Biocompatible Fast-Gelling Hydrogel for Neurodegenerative Diseases," *Biomedical Journal of Scientific & Technical Research,* vol. 50, no. 3, pp. 1149-1157, 2023.

[8]   S. JIANG, Y. LIU, and Y. GU, "SHORT PEPTIDE-BASED POLYSACCHARIDE HYDROGELS FOR TISSUE ENGINEERING: A MINI REVIEW," *migration,* vol. 9, p. 18.

[9]   S. Jiang and E. Kumar, "Investigation of Two-Component Hydrogel System for the Tissue Regeneration from Simulation," *bioRxiv,* p. 2023.12. 28.573564, 2023.

[10]   A. Ghosal and A. Kaushik, *Intelligent hydrogels in diagnostics and therapeutics*. CRC Press, 2020.

[11]   A. Herrmann, R. Haag, and U. Schedler, "Hydrogels and their role in biosensing applications," *Advanced healthcare materials,* vol. 10, no. 11, p. 2100062, 2021.

[12]   M. Teodorescu and M. Bercea, "Poly (vinylpyrrolidone)–a versatile polymer for biomedical and beyond medical applications," *Polymer-Plastics Technology and Engineering,* vol. 54, no. 9, pp. 923-943, 2015.

[13]   K. Li *et al.*, "Application of nonsurgical modalities in improving facial aging," *International Journal of Dentistry,* vol. 2022, 2022.

[14]   G. Lemperle, J. J. Romano, and M. Busso, "Soft tissue augmentation with artecoll: 10-year history, indications, techniques, and complications," *Dermatologic Surgery,* vol. 29, no. 6, pp. 573-587, 2003.

[15]   M. S. Zafar, "Prosthodontic applications of polymethyl methacrylate (PMMA): An update," *Polymers,* vol. 12, no. 10, p. 2299, 2020.

[16]   H. Abu Hassan Shaari, M. M. Ramli, M. N. Mohtar, N. Abdul Rahman, and A. Ahmad, "Synthesis and conductivity studies of poly (Methyl Methacrylate)(PMMA) by co-polymerization and blending with polyaniline (PANi)," *Polymers,* vol. 13, no. 12, p. 1939, 2021.

[17]   J. P. Baker, L. H. Hong, H. W. Blanch, and J. M. Prausnitz, "Effect of initial total monomer concentration on the swelling behavior of cationic acrylamide-based hydrogels," *Macromolecules,* vol. 27, no. 6, pp. 1446-1454, 1994.

[18]   S. Rossi, M. Hallett, P. M. Rossini, A. Pascual-Leone, and S. o. T. C. Group, "Safety, ethical considerations, and application guidelines for the use of transcranial magnetic stimulation in clinical practice and research," *Clinical neurophysiology,* vol. 120, no. 12, pp. 2008-2039, 2009.

[19]   I. Kimber and M. A. Pemberton, "Assessment of the skin sensitising potency of the lower alkyl methacrylate esters," *Regulatory Toxicology and Pharmacology,* vol. 70, no. 1, pp. 24-36, 2014.

[20]   S. Naahidi *et al.*, "Biocompatibility of hydrogel-based scaffolds for tissue engineering applications," *Biotechnology advances,* vol. 35, no. 5, pp. 530-544, 2017.

[21]   M. Bernard, E. Jubeli, M. D. Pungente, and N. Yagoubi, "Biocompatibility of polymer-based biomaterials and medical devices–regulations, in vitro screening and risk-management," *Biomaterials science,* vol. 6, no. 8, pp. 2025-2053, 2018.

[22]   S. Mohapatra *et al.*, "Biomedical application, patent repository, clinical trial and regulatory updates on hydrogel: An extensive review," *Gels,* vol. 7, no. 4, p. 207, 2021.

[23]   H. Savoji, B. Godau, M. S. Hassani, and M. Akbari, "Skin tissue substitutes and biomaterial risk assessment and testing," *Frontiers in bioengineering and biotechnology,* vol. 6, p. 86, 2018.

[24]   W. Peng *et al.*, "Review of plastic surgery biomaterials and current progress in their 3D manufacturing technology," *Materials,* vol. 13, no. 18, p. 4108, 2020.

[25]   Z. Peng *et al.*, "Advances in biomaterials for adipose tissue reconstruction in plastic surgery," *Nanotechnology Reviews,* vol. 9, no. 1, pp. 385-395, 2020.

[26]   S. Jiang and E. Kumar, "Investigation of Biomedical Cell Image Cryptography Based on RC4 Technique," *bioRxiv,* p. 2023.12. 29.573618, 2023.

[27]   Y. Gu *et al.*, "Unveiling breast cancer risk profiles: a survival clustering analysis empowered by an online web application," *Future Oncology,* vol. 19, no. 40, pp. 2651-2667, 2023.

[28]   J. Song, Y. Gu, and E. Kumar, "Chest disease image classification based on spectral clustering algorithm," *Research Reports on Computer Science,* pp. 77-90, 2023.

[29]   Y. Gu, Y. Gong, M. Wang, S. Jiang, C. Li, and Z. Yuan, "Enhancing kidney failure analysis: web application development for longitudinal trajectory clustering," *medRxiv,* p. 2023.05. 31.23290804, 2023.

[30]   S. Jiang, Y. Gu, and E. Kumar, "Stroke Risk Prediction Using Artificial Intelligence Techniques Through Electronic Health Records," *Artificial Intelligence Evolution,* pp. 88-98, 2023.

[31]   E. Kumar, "Sentiment Analysis Based on Machine Learning Algorithms: A Comprehensive Study," *ScienceOpen Preprints,* 2023.