*Title*

**Assessment of thermochromic phantoms for characterizing microwave ablation devices**

Ghina Zia, Amber Lintz, Clay Hardin, Anna Bottiglieri, Jan Sebek, Punit Prakash*

Department of Electrical and Computer Engineering, Kansas State University, Manhattan, KS 66506, USA

*Corresponding author:

Email: prakashp@ksu.edu

Postal address: 3078 Engineering Hall, Department of Electrical and Computer Engineering, Kansas State University, Manhattan, KS 66506, USA

*Running Title:* Microwave ablation thermochromic phantom

*Keywords*:

Tissue mimicking phantoms; thermochromic phantoms; microwave ablation

## ABSTRACT

*Background and Purpose:* Thermochromic gel phantoms provide a controlled medium for visual assessment of thermal ablation device performance. However, there are limited studies reporting

20    on the comparative assessment of ablation profiles assessed in thermochromic gel phantoms against those in *ex vivo* tissue. The objective of this study was to compare microwave ablation zones in a thermochromic tissue mimicking gel phantom and *ex vivo* bovine liver, and to report on measurements of the temperature dependent dielectric and thermal properties of the phantom.

*Methods:* Thermochromic polyacrylamide phantoms were fabricated following a previously

25    reported protocol. Phantom samples were heated to temperatures in the range of 20 – 90 °C in a temperature-controlled water bath, and colorimetric analysis of images of the phantom taken after heating were used to develop a calibration between color changes and temperature to which the phantom was heated. Using a custom, 2.45 GHz water-cooled microwave ablation antenna, ablations were performed in fresh *ex vivo* liver and phantoms using 65 W applied for 5 min or 10

30    min (*n* = 3 samples in each medium for each power/time combination). Broadband (500 MHz – 6 GHz) temperature-dependent dielectric and thermal properties of the phantom were measured over the temperature range 22 – 100 °C. Measured dielectric and thermal properties of the phantom were employed in a previously validated computational model of microwave ablation to comparatively assess model predicted extents of heating against experimental observations in the

35    phantom.

*Results:* Colorimetric analysis showed that the sharp change in gel phantom color commences at a temperature of 57 °C. Short and long axes of the ablation zone in the phantom (as assessed by the 57 °C isotherm) for 65 W, 5 min ablations were aligned with extents of the ablation zone observed in *ex vivo* bovine liver. However, for the 65 W, 10 min setting, ablations in the phantom

40 were on average 23.7% smaller in short axis and 7.4 % smaller in long axis than those observed in *ex vivo* liver. Measurements of the temperature dependent relative permittivity, thermal conductivity, and volumetric heat capacity of the phantom largely followed similar trends to published values for *ex vivo* liver tissue. After incorporating measured dielectric and thermal properties of the phantom, model predictions of ablation zone linear dimensions ranged between

45 16 – 50% larger than those observed experimentally.

*Conclusion:* Thermochromic tissue mimicking phantoms provide a suitable, controlled, and reproducible medium for comparative assessment of microwave ablation devices and energy delivery settings, though ablation zone size and shapes may not accurately represent ablation sizes and shapes observed in *ex vivo* liver tissue under similar conditions.

50 ## **INTRODUCTION**

Thermal ablation is a local intervention that aims to treat biological tissue by elevating tissue temperature to cytotoxic levels. Ablation systems are in clinical use across a range of indications, including treatment of cardiac arrhythmias [1], [2], neuromodulation [3], tumor ablation [4], tissue reshaping [5], and others. An ablation procedure involves localized delivery of energy to the

55 targeted anatomy. The increase of the temperature results from the absorption of energy within the tissue. At temperatures above ~60 °C, most tissues can be considered ablated within a few seconds [6]. The extent of the ablation zone is a function of the spatial and temporal profiles of energy distribution and absorption within tissue, subsequent passive thermal diffusion, and the cooling effects of blood perfusion [7]. Systems employing a range of energy modalities, including lasers,

60 microwaves, radiofrequency current, and ultrasound, have been developed and are in clinical use [8].

During the design and development of ablation devices, pre-clinical assessment, and training procedures, it is desirable to have a reliable, controlled medium for evaluating device performance and spatial extents of the anticipated ablation zone. *Ex vivo* animal tissues – most frequently liver,

65 lung, and muscle – are a widely used substrate for evaluation of ablation zone extents as a function of applied power and ablation duration, and manufacturer provided instructions for use commonly include these data [9]. The ablation zone boundary is estimated based on the extent of visible tissue discoloration, thus providing a simple method for assessing dimensions of the ablation zone; the sharpness of the ablation boundaries can be augmented through the use of viability stains when

70 using freshly excised tissue [10], [11]. However, it can be cumbersome to obtain freshly excised tissue, and care needs to be taken to preserve tissue samples following excision to maintain sample integrity, and limit desiccation which can considerably alter tissue physical properties [12]. Additionally, the presence of tissue pathologies, which are seldom known *a priori* in excised

animal tissue, can introduce heterogeneity in tissue physical properties, influence ablation outcomes, and thus confound assessment of devices under test. While *ex vivo* tissue does not account for the heat sink effect of blood perfusion, experiments in non-perfused tissue can serve to bound the largest extent of ablation zone anticipated under *in vivo* conditions (i.e. all else equal, if blood perfusion were present, the ablation zone would likely be smaller); *ex vivo* perfused tissue models have also been developed and reported [13]. It is noted that the initial temperature of tissue (i.e. room temperature or ~37 °C physiologic temperature) also has a considerable impact on the extent of the observed ablation zone in benchtop experiments.

Tissue mimicking phantoms serve as an important platform for the assessment of medical devices and systems, and are widely used for quality assurance of clinical imaging and therapy systems. While experiments in *ex vivo* and *in vivo* tissue may be more representative of the intended clinical use, tissue mimicking phantoms can be constructed in a repeatable and reliable manner, with material properties tailored to match the target tissue properties. In the context of thermal therapy devices, tissue mimicking phantoms (e.g., opaque agar phantoms [14, p.], [15], [16], [17] and transparent polyacrylamide phantoms [18]) have been widely used for evaluating the spatial power absorption profile by the device under evaluation, and for comparative assessment against performance predicted by computational models [19], [20]. These require the use of temperature sensors (typically invasive, such as fiber-optic sensors) to capture transient temperature profiles during power exposure. For short duration exposures, the rate of heating is proportional to the power absorption in the medium, thus providing a means to evaluate the spatial power absorption pattern with appropriately positioned temperature sensors [21]. The estimated spatial power absorption profile is prone to errors due to inaccurate temperature sensor placement, and the spatial resolution of measurements is constrained by the number of temperature sensors

available. The development of fiber-optic thermometry based on fiber bragg grating (FBG) technology has provided a means for considerably improved spatial sampling of temperature profiles, due to the ability to record temperatures at multiple points along a fiber [22]. Non-invasive, volumetric thermometry techniques such as magnetic resonance imaging (MRI) thermometry, can also be used, but integrating ablation instrumentation within the MRI environment is a considerable barrier.

Recent reports have presented a range of gel phantoms that provide a facile means for estimating the extent of the ablation zone due to color change in the phantom material at a tunable temperature. Chen *et al* [23] utilized an agarose-albumin-based phantom to visualize the ablation outcomes of an optically tracked radiofrequency needle device. They used the positional data of the device in computational ablation models to generate predictive models of ablation extents. William *et al* [24] presented a liquid crystal phantom embedded within a gel matrix (impedance adjusted to match myocardial tissue) for myocardial tissue ablation with color change between 50 °C (red) and 78 °C (black). Bu Lin et al [18] used bovine serum albumin with polyacrylamide gel during radiofrequency ablation to visualize coagulation temperature distribution in 3D space (displayed as ivory white color). Negussie *et al* [25] reported on a polyacrylamide gel phantom incorporating a thermochromic ink to provide a facile means for spatial assessment of thermal profiles. The thermochromic ink irreversibly changes color when exposed to temperatures in the range ~55 – 70 °C for a few seconds/minutes, thus providing a means to evaluate the extent of ablation profiles after an ablative exposure. These thermo-chromic phantoms could provide a suitable tool for validation of applicator performance during translation of medical devices from academic/early-stage innovation labs to quality manufacturing systems, quality assurance of clinical devices, and for training of clinicians [26]. These phantoms have been employed for

120    evaluating ablation profiles of focused ultrasound [27] , radiofrequency [28], and microwave

ablation [29] systems. Other studies have reported on the use of such phantoms for training of

clinical operators and demonstration of new ablation technologies [30]. However, the extant

literature provides limited information on how microwave ablation zone profiles observed in the

phantom compare against ablation zones observed in established media such as freshly excised *ex*

125    *vivo* tissue under similar conditions. Additionally, there are limited data available on the physical

properties of the phantoms, which are requisite for comparative assessment of experimental

measurements against computational modeling.

The overall objective of this study was to comparatively assess ablation profiles created by a

2.45 GHz microwave ablation applicator in a thermochromic tissue mimicking gel phantom and

130    freshly excised *ex vivo* bovine liver tissue in a benchtop experimental setup. We also report on

experimental characterizations of the frequency and temperature dependent dielectric properties,

and temperature dependent thermal properties of the phantom.

## MATERIALS AND METHODS

135    *Thermochromic phantom preparation*

Phantoms were prepared according to the protocol described by Mikhail *et al* [28]. To

prepare 50 ml of phantom, combine 38.05 ml distilled water (at room temperature), 8.75 ml

aqueous 40% acrylamide/bis-acrylamide (19:1 feed; a9926, Sigma Aldrich), 2.5 ml magenta ink

(Kromagen WB Flexo Ink Magenta K60), and 450 mg sodium chloride in a beaker using a

140    magnetic stirrer. A micro-pipette was used for measuring out small liquid volumes. The materials

were continuously stirred until the ink had thoroughly combined. Then, 70 mg ammonium

persulfate (a3678, Sigma Aldrich) was added to the mixture and stirred continuously until

combined. Finally, 0.07 ml N, N, N', N' tetramethylethlenadiamine (TEMED, t9281, Sigma Aldrich) was added to the mixture, while continuously stirring for 30 s. The mixture was then

145    promptly poured into storage containers and stored in a refrigerator (4 °C). All phantoms were stored in a refrigerator overnight (~12-18 hours) prior to use in any experiments.

### *Baseline characterization of colorimetric change following heating*

Experiments were conducted to assess colorimetric changes to the gel phantom following exposure to temperatures in the range ~20 – 90 °C, to validate the range of temperatures over

150    which color changes are observed. For these experiments, a total of 50 ml of phantom was prepared and individual 3 ml samples were each placed in 4 ml glass vials (i.e., one sample consists of ~3 ml of phantom placed in a vial), and stored overnight in a refrigerator prior to use. Prior to conducting these experiments, the vials were removed from the refrigerator and allowed to equilibrate to room temperature on the bench. The vials were then placed in a temperature-

155    controlled water-bath (PolyScience, 2L water bath) set to temperatures in the range ~20 – 90 °C. A needle thermocouple (MT-23, Physitemp, Clifton, NJ) was placed into the phantom during these experiments to observe the temperature of the phantom. When the phantom reached the desired temperature, and was maintained at that temperature for 1 min, the vial was removed from the water bath and allowed to rest on the bench for 1 min. Next, the vials were placed on a white

160    background in a portable Mini Photo Studio Box (SANOTO, Whittier, CA) and a 12 MP iPhone 11 camera was used to capture digital images in consistent background lighting conditions. Images were then transferred to a computer for analysis. A custom-made tool in MATLAB was utilized to perform color correction on the images (based on a background color correction algorithm) and to analyze the intensity of the images in the red (R), green (G), and blue (B) color space. For each

165    sample, a 3x3 region of interest in the center of the phantom was carefully selected to ensure

minimal impact of lighting artifact; all data reported are the mean values of the intensity within the region of interest. Measurements were performed on a total of $n = 35$ phantom samples.

*Dielectric property characterization of the thermochromic phantom*

170    The broadband (1 – 6 GHz) temperature-dependent dielectric properties of the tissue mimicking phantom were measured using the open-ended coaxial probe method, following a protocol similar to previously published studies [31]. Briefly, dielectric property measurements were made with the Keysight 85070E probe coupled with an HP 8753D Vector Network Analyzer (VNA). The probe was calibrated with measurements on three standards: open circuit, short circuit, and room temperature deionized water. Samples of the phantom were prepared and cut into cubes

175    measuring approximately 2 cm × 2 cm × 2 cm, and placed into a custom sample holder made from copper. The sample holder was placed on the surface of a hot plate, with custom fins extending from the surface of the hot plate to the top of the sample holder, providing a means to raise the sample temperature while attempting to limit the thermal gradient across the sample. The 85070E probe was positioned roughly in the center of the phantom, and with the aid of a lab jack, the

180    sample was raised to the probe such that the probe extended ~5 mm into the phantom sample. A fiber-optic temperature sensor was affixed to the 85070E probe (~5 mm proximal from the surface) to provide a collocated estimate of the sample temperature. The hot plate surface temperature was set to 300 °C, and dielectric properties were measured at 1 °C increments over the temperature range 22 °C to 100 °C. Measurements were performed on $n = 3$ phantom samples.

185    *Thermal property characterization of the thermochromic phantom*

    Thermal properties were measured using a thermal needle system (SH-3 dual-needle, METER Group, Inc. USA) and a digital thermal analyzer (Tempos, METER Group, Inc. USA) including two parallel needles of 3 mm diameter and 30 mm length each and a 6 mm spacing

between the two needles. The measurement mechanism of the system consists of a heating and a

190    cooling phase. During the heating phase, one of the two needles is heated at a defined temperature

$T_0$ for about 30 s thus the heat is transferred through the sample. During the cooling phase the final

temperature $T_f$ is measured on the second needle. The values of thermal conductivity $k$ (W·K⁻1·m⁻

¹), thermal diffusivity D (m²· s⁻¹) and volumetric heat capacity $C$ (J· K⁻¹ ·m⁻³) displayed by the

system are the output parameters that minimize the difference between $T_f$ and $T_0$ according to the

195    least square method.

The measurements were conducted on a total of $n = 3$ tissue mimicking phantoms exposed

to a thermal controlled water bath set at a designed temperature. Each phantom was cut to fit a

metallic container used to prevent the infiltration of water. The dual-needle system was placed in

each sample ensuring a 15 mm margin to minimize the effect of the boundaries. The measurement

200    procedure was initiated when the thermal equilibrium between the water bath and the phantom

was reached. Thermal properties were measured for the range of temperatures: 22-90 °C at which

each phantom was exposed. The measurements were repeated 6 times. A dataset of 18

measurements in total including at least 6 measurements per temperature value were collected and

analyzed.

205    ***Microwave ablation experiments in thermochromic phantoms and ex vivo bovine liver tissue***

Gel phantom samples (of volume approximately 220 ml) were prepared in the lab and

refrigerated. For ablation experiments, the phantoms were taken out of the refrigerator and was

left on the benchtop to stabilize the temperature of the gel to room temperature (~23 °C). The gel

phantoms were allowed to set in a custom designed acrylic template with slots positioned for

210    careful arrangement of a 14 G microwave ablation applicator. Microwave ablations were

performed with a custom, water-cooled monopole antenna, augmented with a choke (located at ?

mm from the tip of the antenna), operating at 2.45 GHz [32]. Microwave power was supplied by a solid-state generator (Sairem GMS 200W). Cooled water (∼7-10 °C) was circulated through the applicator using a peristaltic pump (Cole Parmer 7554–90, Vernon Hills, IL, USA) at a rate of 40

215 ml/min. With an applied power of 65 W, $n = 3$ experiments were performed for a heating duration of 5 min and $n = 3$ experiments were performed for a heating duration of 10 min. After the ablation experiment, the gel phantom was sliced, in a plane parallel to the applicator insertion axis, using a sharp-edged copper sheet in order to avoid disintegration of the gel phantom. Digital images of the phantoms were taken in the light-box for further analysis.

220 A similar procedure was followed for ablations in *ex vivo* bovine liver tissue. Briefly, freshly excised bovine liver tissue was obtained from a local slaughterhouse. Livers were placed in thin plastic bags, placed in an insulated cool box filled with ice, and transported to the lab. Within ~4-16 hours post excision, livers were sectioned into ~6 cm × 6 cm × 6 cm pieces, placed in sealed Ziploc bags, and allowed to equilibrate to room temperature (~23 °C) by placing the sealed Ziploc

225 bags in a temperature-controlled water-bath. Once tissue samples had equilibrated to room temperature, they were removed from the Ziploc bags and transferred to the bench. The ablation applicator was positioned within the tissue sample and ablations were performed using applied power settings of 65 W, 5 min ($n = 3$) and 65 W, 10 min ($n = 3$). Following ablations, liver samples were sectioned in a plane parallel to the axis of insertion of the ablation applicator, and digital

230 images of the tissue samples were taken.

### *Computational modeling of microwave ablation in the thermochromic phantom*

A computational model of microwave absorption and bioheat transfer was implemented using the finite element method (COMSOL Multiphysics). The model was adapted from a previously described model that was validated against MRI thermometry data in *ex vivo* liver tissue

235    [33]. Briefly, the model solves the Helmholtz electromagnetic wave equation to determine the time-averaged electric field and power absorption in the phantom. The transient heat transfer equation is solved to determine transient temperature profiles. The measured temperature dependent dielectric properties and thermal properties of the gel phantom were incorporated in the models. Model predicted extents of isotherms were comparatively assessed against experimental

240    measurements.

## **RESULTS**

Figure 1 illustrates the sample sets to demonstrate color change as a function of temperature from room temperature (22 ℃) to 90 ℃. Each phantom vial was heated in a temperature-controlled water-bath to characterize the color of the phantom at the specific peak temperature (mentioned

245    below the vial). The example sets of phantoms in Figure 1 indicate that from 22 ℃ to 55 ℃ peak temperature, the phantom's light-yellow color remains consistent. The phantom starts changing its color from light-yellow to light-pink around a peak temperature of 58 ℃. The phantom color gradually varies from light-pink to magenta color in range of maximum achieved sample temperatures 58 ℃ to 70 ℃. For samples with peak temperatures above 70 ℃, the color remains

250    Magenta.

**Figure 1.** Example sets of gel phantom illustrating colorimetric changes from room temperature value (22 ℃) at different peak temperature values.

Figure 2 depicts the mean RGB values obtained from the gel phantom samples after heating them to different peak temperature values. From the RGB value analysis, we determined the lowest temperature at which the color of phantom noticeably changed. This temperature and corresponding RGB values served for later ablation boundary estimation in phantom samples as
255  well as in temperature maps predicted by the computational model. The most drastic change occurs in the green channel ("G" value) from the RGB values as compared to the red channel (or "R" values) and blue channel (or "B" values). When the phantom is exposed to peak temperatures from 57 °C to 72 °C, the "G" value drops by 98% of its baseline value (at 57 °C peak temperature). After 72 °C, all three color channels reach a plateau with the value of green channel being close to 0.
260  Therefore, we used RGB values at 57 °C isotherm to determine ablation boundary in the phantom.

**Figure 2.** Colorimetric analysis of phantoms when exposed to temperatures in the range 20 – 90 °C in a temperature-controlled water bath.

Figure 3 shows example phantom and liver ablations at 65 W, 5 min, and at 65 W, 10

min. As expected, with the same power of 65 W, the 10-minute ablations in both phantom and *ex*

265    *vivo* liver samples are significantly larger than the 5-minute ablations. Tables 1 and 2 present the

dimensions of the ablations recorded in phantom and liver samples at 65 W, 5 min, and 65 W, 10

min, respectively. We analyzed images of the phantom in MATLAB to measure the width and

height of the 57 °C peak temperature contour representing the phantom ablation dimensions. We

used tissue discoloration in *ex vivo* liver samples to measure the width and height of ablations.

**(a) Sample phantom ablation at 65 W and 5 min**

**(b) Sample phantom ablation at 65 W and 10 min**

**(c) Sample liver ablation at 65 W and 5 min**

**(d) Sample liver ablation at 65 W and 10 min**

**Figure 3.** Comparison of (a) phantom and (c) *ex vivo* liver following 65 W, 5 min ablation. Comparison of (b) phantom and (d) *ex vivo* liver following 65 W, 10 min ablation.

Table 1 lists the ablation dimensions, average width and height of 65W 5-min ablation in

phantom and *ex vivo* liver tissue samples. The average width of the phantom ablations is $2.4 \pm 0.1$

cm, which lies in the range of the average width of *ex vivo* liver tissue ablation, i.e., $2.3 \pm 0.3$ cm.

The average height of the phantom ablations is $2.9 \pm 0.3$ cm, which lies in the range of the average

275    width of *ex vivo* liver tissue ablation, i.e., $3.0 \pm 0.1$.

**Table 1. Ablation zone dimensions in phantom and liver at 65 W, 5 min**

| Sample | Ablation dimensions [cm $\times$ cm] | Average width of ablation [cm] | Average height of ablation [cm] |
|---|---|---|---|
| Phantom (Sample 1) | $2.5 \times 3.2$ | $2.4 \pm 0.1$ | $2.9 \pm 0.3$ |
| Phantom (Sample 2) | $2.3 \times 2.9$ | | |
| Phantom (Sample 3) | $2.3 \times 2.7$ | | |
| Liver (Sample 1) | $2.2 \times 3.2$ | $2.3 \pm 0.3$ | $3.0 \pm 0.1$ |
| Liver (Sample 2) | $2.1 \times 2.9$ | | |
| Liver (Sample 3) | $2.7 \times 3.0$ | | |

Table 2 lists the ablation dimensions, average width and height of 65 W, and 10-min

ablation in phantom and *ex vivo* liver tissue samples. The average width of the phantom ablations

280    is $2.9 \pm 0.1$ cm, which is around 1 cm smaller than the average width of *ex vivo* liver tissue ablation,

i.e., $3.8 \pm 0.3$ cm. The average height of the phantom ablations is $3.8 \pm 0.1$ cm, which is around

0.3 cm smaller than the average width of *ex vivo* liver tissue ablation, i.e., $4.1 \pm 0.1$ cm.

**Table 2. Ablation dimensions in phantom and liver at 65 W, 10 min**

| Sample | Ablation dimensions [cm $\times$ cm] | Average width of ablation [cm] | Average height of ablation [cm] |
|---|---|---|---|
| Phantom (Sample 1) | 2.9 x 3.9 | $2.9 \pm 0.1$ | $3.8 \pm 0.1$ |
| Phantom (Sample 2) | 2.9 x 3.8 | | |
| Phantom (Sample 3) | 2.8 x 3.7 | | |
| Liver (Sample 1) | 4.0 x 4.1 | $3.8 \pm 0.3$ | $4.1 \pm 0.1$ |
| Liver (Sample 2) | 4.0 x 4.1 | | |
| Liver (Sample 3) | 3.5 x 4.0 | | |

285    Figure 4 compares the broadband dielectric properties of gel phantom at 35 °C over the

frequency range of 500 MHz to 6 GHz for relative permittivity, $\varepsilon_r$, and for effective conductivity,

$\sigma_{eff}$. For comparison, also shown are the broadband dielectric properties of *ex vivo* bovine liver

assessed at the same temperature (taken from [31]).

**Figure 4.** Broadband dielectric properties (relative permittivity, $\varepsilon_r$, and effective conductivity, $\sigma_{eff}$) of gel phantom at 35 ℃ for gel phantom (three samples with the average values) in comparison to *ex vivo* bovine liver broadband dielectric properties (average value with 95% confidence interval taken from Fallahi *et al*. 2021).

290   Figure 5 shows the comparison of the measured relative permittivity $\varepsilon_r$, and effective conductivity $\sigma_{eff}$ of gel phantom and *ex vivo* bovine liver (taken from [31]) at Industrial, Scientific and Medical (ISM) frequencies (i.e., 915 MHz, 2.45 GHz, and 5.8 GHz) over the temperature range ~ 22 °C to 100 °C. Several practical ablation systems have been developed for operation at ISM frequencies.

**Figure 5.** Temperature-dependent dielectric properties (relative permittivity, $\varepsilon_r$, and effective conductivity, $\sigma_{eff}$) of the gel phantom at 915 MHz, 2.45 GHz and 5.8 GHz. gel phantom (three samples with the average values) in comparison to *ex vivo* bovine liver temperature-dependent dielectric properties (average value with 95% confidence interval taken from Fallahi *et al.* 2021).

Figure 6 illustrates the comparison of temperature-dependent thermal properties of the gel phantom and *ex vivo* bovine liver (values taken from [34]) ; a) thermal diffusivity measured in $mm^2.s^{-1}$, b) Thermal conductivity measured in $W.m^{-1}. K^{-1}$, and c) volumetric heat capacity measure in $MJ. m^{-3} K^{-1}$, for three phantom samples and their averages over the 20-85 ºC temperature range.

**Figure 6.** Temperature-dependent thermal properties of thermochromic gel phantom over the temperature range, 20 -85 ℃ a) Thermal diffusivity, b) Thermal conductivity, and c) Volumetric heat capacity in comparison to *ex vivo* bovine liver temperature-dependent thermal properties (average with confidence interval; values taken from Lopresto *et al.* 2019).

Figure 7 compares the phantom experiments with the computer models for 65 W, 5 min (a and b) ablations and 65 W, 10 min ablations (c and d). The 57 °C peak temperature contour is used as the ablation boundary to compare the ablation dimensions between the experiments and computer simulations. For 65 W, 5 min, the average (*n* = 3 samples) width of phantom ablation in

305    experiments is 2.4 ± 0.1 cm, and the average ablation height is 2.9 ± 0.3 cm. The computer model predicts the average width of the phantom is 3.4 ± 0.2 cm, and the average ablation height is 3.7 ± 0.07 cm.  For 65 W, 10 min, the average width of phantom ablation in experiments is 2.86 cm ± 0.06, and the average ablation height is 3.8 ± 0.1 cm. The computer model predicts the average width of the phantom is 4.3 ± 0.1 cm, and the average ablation height is 4.4 ± 0.1 cm.

**(a) Phantom experiment at 65W and 5 min**  **(b) Phantom simulation at 65 W and 5 min**

**(c) Phantom experiment at 65W and 10 min**  **(d) Phantom simulation at 65W and 10 min**

**Figure 7.** (a) Experimentally observed and (b) simulated extents of ablation zones following 65 W, 5 min ablation in the thermochromic phantom. (c) Experimentally observed and (d) simulated extents of ablation zones following 65 W, 10 min ablation in the thermochromic phantom

## **DISCUSSION**

This study aimed to comparatively assess microwave ablation zones in a previously reported thermochromic phantom with ablation zones created in *ex vivo* liver when using the same ablation device and applied energy levels in both media. The colorimetric analysis was conducted to identify the working temperature range of the phantom (i.e., the range of temperatures in which the phantom significantly changes its color). The extent of the ablation zone in phantoms was determined from the 57 °C isotherm, as estimated from colorimetric analysis of phantoms heated in water baths (Figures 1 and 2). As seen in Figure 3, for 5 min ablations with 65 W applied power,

320 similarly sized ablation zones were observed in phantoms ($2.4 \pm 0.1 \times 2.9 \pm 0.3$ cm$^2$) and fresh *ex vivo* bovine liver ($2.3 \pm 0.3 \times 3.0 \pm 0.1$ cm$^2$). However, for 65 W, 10 min ablations, the ablation zone in phantoms ($2.9 \pm 0.1 \times 3.8 \pm 0.1$ cm$^2$) were on average 23.7% smaller in short axis and 7.4 % smaller in long axis than ablation zones observed in *ex vivo* liver ($3.8 \pm 0.3 \times 4.1 \pm 0.1$ cm$^2$). Of note, the dynamics of tissue discoloration are a function of the time-temperature history during

325 heating, rather than temperature alone [35]. Longer heating of tissue may yield discoloration at lower temperatures; however, for the phantom analysis, the 57 °C isotherm was used independent of duration of ablation.

    We hypothesized that these differences in ablation zone extents could be due in part to differences in the physical properties (dielectric properties, thermal properties, and their

330 temperature dependencies) of the thermochromic phantom and *ex vivo* liver. We measured broadband (500 MHz – 6 GHz) dielectric properties of the phantom at temperatures ranging from ~22 °C to ~100 °C (Figures 4 and 5). At a frequency of 2.45 GHz, the relative permittivity of the phantom gradually dropped with increasing temperature, with a sharp drop at ~ 80 °C. The electrical conductivity of the phantom gradually increased at temperatures up to ~80 °C, before a

335 sharp drop at ~ 80 °C. While trends in relative permittivity changes with temperature for the phantom at 2.45 GHz were similar to those of relative permittivity of *ex vivo* liver reported in the literature [31], [36], [37], the trends in electrical conductivity were somewhat different. At 2.45 GHz, electrical conductivity remains relatively stable/slightly decreases at temperatures up to ~60 °C, and transitions to a low value over the range ~60 °C – 80 °C as tissue desiccates, and settles at

340 this lower value at elevated temperatures. This is in contrast to the slight increase in electrical conductivity with temperature up to 80 °C observed for phantoms in the present study; it is noted,

however, that this discrepancy may be due to the limited number of phantom samples on which measurements were conducted.

The thermal conductivity of the phantom increased with increasing temperature (Figure 6), similar to liver tissue [34], although it is noted that the baseline value of the thermal conductivity of the phantom (~0.6 W m$^{-1}$ K$^{-1}$) was ~20% higher than the value for liver at similar temperatures (~0.5 W m$^{-1}$ K$^{-1}$). While some variations in volumetric heat capacity of the phantom were observed at varying temperatures, there was no clear trend and variation over the entire temperature range was ~5-8 %.

However, when we applied these measured dielectric and thermal properties of the phantom in a previously established computational model of microwave heating, model predictions of the extent of the ablation zone (approximate with the 57 °C isotherm) were considerably larger than those observed experimentally (Figure 7). For 65 W, 5 min ablations, model predictions of ablation zone short axis were 42% larger than experimental observation, and model prediction of ablation zone long axis were 28% larger. For 65 W, 10 min ablations, model predictions of ablation zone short axis were 50% larger than experimental observation, and model prediction of ablation zone long axis were 16% larger. These data suggest that the differences in the ablation zone extent observed in experiments between *ex vivo* liver and the phantom should not be solely attributed to differences in their dielectric and thermal properties; the thermo-elastic properties of tissue and the phantom may also differ and further contribute to observed differences. We also note that colorimetric analyses of the phantoms were performed on samples heated uniformly in a water bath, at rates likely slower than the rate of heating during microwave ablation. Differences in the temporal evolution of color change between the calibrations obtained from

colorimetric analyses compared to changes observed during heterogeneous and more rapid heating with a microwave antenna may contribute to the observed differences.

Given the increasing use of thermochromic phantoms in device evaluations and for medical simulation/training, it is important to recognize the differences in ablation zone size and shape that could be anticipated between the phantom and tissue. Further, in the *in vivo* setting, additional variability is anticipated due to the blood perfusion heat sink, and considerable variability in tissue physical properties across pathologic and normal tissue. Nevertheless, this does not diminish the utility of the phantoms, which present a controlled, stable medium for comparative assessment of ablation devices and energy delivery settings.

## ACKNOWLEDGEMENTS

This work was supported in part by NIH grants R01CA218357 and R01EB028848.

## REFERENCES

[1]  D. M. Nguyen, P. Qian, T. Barry, and A. McEwan, "Cardiac radiofrequency ablation tracking using electrical impedance tomography," *Biomed Phys Eng Express*, vol. 6, no. 1, p. 015015, Jan. 2020, doi: 10.1088/2057-1976/ab5ce8.

[2]  P. Qian *et al.*, "A Novel Microwave Catheter Can Perform Noncontact Circumferential Endocardial Ablation in a Model of Pulmonary Vein Isolation," *J Cardiovasc Electrophysiol*, vol. 26, no. 7, pp. 799–804, Jul. 2015, doi: 10.1111/jce.12683.

[3]  F. M. Gonzalez, J. Huang, and J. Fritz, "Image-Guided Radiofrequency Ablation for Joint and Back Pain: Rationales, Techniques, and Results," *Cardiovasc Intervent Radiol*, vol. 46, no. 11, pp. 1538–1550, Nov. 2023, doi: 10.1007/s00270-023-03393-2.

[4]  T. P. Ryan, P. F. Turner, and  and B. Hamilton, "Interstitial microwave transition from hyperthermia to ablation: Historical perspectives and current trends in thermal therapy," *Int. J. Hyperthermia*, vol. 26, no. 5, pp. 415–433, 2010.

[5]  E. H. Abello *et al.*, "Temperature Profile Measurement From Radiofrequency Nasal Airway Reshaping Device," *Laryngoscope*, Aug. 2023, doi: 10.1002/lary.30942.

[6]  J. A. Pearce, "Models for thermal damage in tissues: processes and applications," *Crit Rev Biomed Eng*, vol. 38, no. 1, pp. 1–20, 2010.

[7]  D. Haemmerich, "1 - Mathematical modeling of heat transfer in biological tissues (bioheat transfer)," in *Principles and Technologies for Electromagnetic Energy Based Therapies*, P. Prakash and G. Srimathveeravalli, Eds., Academic Press, 2022, pp. 1–24. doi: 10.1016/B978-0-12-820594-5.00012-5.

[8]  M. Ahmed, C. L. Brace, F. T. Lee, and S. N. Goldberg, "Principles of and advances in percutaneous ablation," *Radiology*, vol. 258, no. 2, pp. 351–369, Feb. 2011, doi: 10.1148/radiol.10081634.

[9] R. Hoffmann *et al.*, "Comparison of four microwave ablation devices: an experimental study in ex vivo bovine liver," *Radiology*, vol. 268, no. 1, pp. 89–97, Jul. 2013, doi: 10.1148/radiol.13121127.

[10] J. E. Coad and J. C. Bischof, "Histologic differences between cryothermic and hyperthermic therapies," Jun. 2003, pp. 27–36. doi: 10.1117/12.476334.

[11] B. T. Grisez, R. M. Jones, and J. E. Coad, "Evolution of pathology techniques for evaluating energy-based tissue effects," in *Energy-based Treatment of Tissue and Assessment VII*, SPIE, Feb. 2013, pp. 150–158. doi: 10.1117/12.2006949.

[12] A. Shahzad, S. Khan, M. Jones, R. M. Dwyer, and M. O'Halloran, "Investigation of the effect of dehydration on tissue dielectric properties in ex vivo measurements," *Biomed. Phys. Eng. Express*, vol. 3, no. 4, p. 045001, Jun. 2017, doi: 10.1088/2057-1976/aa74c4.

[13] D. Fuentes, R. Cardan, R. J. Stafford, J. Yung, G. D. Dodd, and Y. Feng, "High-fidelity computer models for prospective treatment planning of radiofrequency ablation with in vitro experimental correlation," *J Vasc Interv Radiol*, vol. 21, no. 11, pp. 1725–1732, Nov. 2010, doi: 10.1016/j.jvir.2010.07.022.

[14] S. N. Goldberg *et al.*, "Radio-Frequency Thermal Ablation with NaCl Solution Injection: Effect of Electrical Conductivity on Tissue Heating and Coagulation—Phantom and Porcine Liver Study," *Radiology*, vol. 219, no. 1, pp. 157–165, Apr. 2001, doi: 10.1148/radiology.219.1.r01ap27157.

[15] S. A. Solazzo *et al.*, "Radiofrequency Ablation: Importance of Background Tissue Electrical Conductivity—An Agar Phantom and Computer Modeling Study," *Radiology*, vol. 236, no. 2, pp. 495–502, Aug. 2005, doi: 10.1148/radiol.2362040965.

[16] "Full article: Characterization of the RF ablation-induced 'oven effect': The importance of background tissue thermal conductivity on tissue heating." Accessed: Feb. 05, 2024. [Online]. Available: https://www.tandfonline.com/doi/full/10.1080/02656730600609122

[17] "RF Ablation at Low Frequencies for Targeted Tumor Heating: In Vitro and Computational Modeling Results | IEEE Journals & Magazine | IEEE Xplore." Accessed: Feb. 05, 2024. [Online]. Available: https://ieeexplore.ieee.org/abstract/document/5597936

[18] Z. Bu-Lin, H. Bing, K. Sheng-Li, Y. Huang, W. Rong, and L. Jia, "A polyacrylamide gel phantom for radiofrequency ablation," *International Journal of Hyperthermia*, vol. 24, no. 7, pp. 568–576, Jan. 2008, doi: 10.1080/02656730802104732.

[19] A. Dabbagh, B. J. J. Abdullah, C. Ramasindarum, and N. H. Abu Kasim, "Tissue-mimicking gel phantoms for thermal therapy studies," *Ultrason Imaging*, vol. 36, no. 4, pp. 291–316, Oct. 2014, doi: 10.1177/0161734614526372.

[20] P. Prakash, M. C. Converse, D. M. Mahvi, and J. G. Webster, "Measurement of the specific heat capacity of liver phantom," *Physiol Meas*, vol. 27, no. 10, pp. N41-46, Oct. 2006, doi: 10.1088/0967-3334/27/10/N01.

[21] G. Deshazer, P. Prakash, D. Merck, and D. Haemmerich, "Experimental measurement of microwave ablation heating pattern and comparison to computer simulations," *International Journal of Hyperthermia*, vol. 33, no. 1, pp. 74–82, Jan. 2017, doi: 10.1080/02656736.2016.1206630.

[22] T. Boers *et al.*, "An anthropomorphic thyroid phantom for ultrasound-guided radiofrequency ablation of nodules," *Med Phys*, Dec. 2023, doi: 10.1002/mp.16906.

[23] C.-C. R. Chen, M. I. Miga, and R. L. Galloway, "Characterization of tracked radiofrequency ablation in phantom," *Medical Physics*, vol. 34, no. 10, pp. 4030–4040, 2007, doi: 10.1118/1.2761978.

[24] W. W. b. Chik *et al.*, "High Spatial Resolution Thermal Mapping of Radiofrequency Ablation Lesions Using a Novel Thermochromic Liquid Crystal Myocardial Phantom," *Journal of Cardiovascular Electrophysiology*, vol. 24, no. 11, pp. 1278–1286, 2013, doi: 10.1111/jce.12209.

[25] A. H. Negussie *et al.*, "Thermochromic tissue-mimicking phantom for optimisation of thermal tumour ablation," *International Journal of Hyperthermia*, vol. 32, no. 3, pp. 239–243, Apr. 2016, doi: 10.3109/02656736.2016.1145745.

[26] A. H. Negussie, R. Morhard, J. Rivera, J. F. Delgado, S. Xu, and B. J. Wood, "Thermochromic phantoms and paint to characterize and model image-guided thermal ablation and ablation devices: a

review," *Functional Composite Mater*, vol. 5, no. 1, p. 1, Jan. 2024, doi: 10.1186/s42252-023-00050-2.

[27] W. Zhang *et al.*, "Anatomic thermochromic tissue-mimicking phantom of the lumbar spine for pre-clinical evaluation of MR-guided focused ultrasound (MRgFUS) ablation of the facet joint," *Int J Hyperthermia*, vol. 38, no. 1, pp. 130–135, 2021, doi: 10.1080/02656736.2021.1880650.

[28] A. S. Mikhail, A. H. Negussie, C. Graham, M. Mathew, B. J. Wood, and A. Partanen, "Evaluation of a tissue-mimicking thermochromic phantom for radiofrequency ablation," *Med Phys*, vol. 43, no. 7, pp. 4304–4311, Jul. 2016, doi: 10.1118/1.4953394.

[29] N. A. Varble *et al.*, "Morphometric characterization and temporal temperature measurements during hepatic microwave ablation in swine," *PLoS One*, vol. 18, no. 8, p. e0289674, 2023, doi: 10.1371/journal.pone.0289674.

[30] X. Zhong, P. Zhou, Y. Zhao, W. Liu, and X. Zhang, "A novel tissue-mimicking phantom for US/CT/MR-guided tumor puncture and thermal ablation," *International Journal of Hyperthermia*, vol. 39, no. 1, pp. 557–563, Dec. 2022, doi: 10.1080/02656736.2022.2056249.

[31] H. Fallahi, J. Sebek, and P. Prakash, "Broadband Dielectric Properties of Ex Vivo Bovine Liver Tissue Characterized at Ablative Temperatures," *IEEE Trans Biomed Eng*, vol. 68, no. 1, pp. 90–98, Jan. 2021, doi: 10.1109/TBME.2020.2996825.

[32] J. Sebek, P. Taeprasartsit, H. Wibowo, W. L. Beard, R. Bortel, and P. Prakash, "Microwave ablation of lung tumors: A probabilistic approach for simulation-based treatment planning," *Med Phys*, vol. 48, no. 7, pp. 3991–4003, Jul. 2021, doi: 10.1002/mp.14923.

[33] P. Faridi, P. Keselman, H. Fallahi, and P. Prakash, "Experimental assessment of microwave ablation computational modeling with MR thermometry," *Med Phys*, vol. 47, no. 9, pp. 3777–3788, Sep. 2020, doi: 10.1002/mp.14318.

[34] V. Lopresto, A. Argentieri, R. Pinto, and M. Cavagnaro, "Temperature dependence of thermal properties of *ex vivo* liver tissue up to ablative temperatures," *Physics in Medicine & Biology*, vol. 64, no. 10, p. 105016, May 2019, doi: 10.1088/1361-6560/ab1663.

[35] V. K. Nagarajan, J. M. Ward, and B. Yu, "Association of Liver Tissue Optical Properties and Thermal Damage," *Lasers Surg Med*, vol. 52, no. 8, pp. 779–787, Oct. 2020, doi: 10.1002/lsm.23209.

[36] V. Lopresto, R. Pinto, G. A. Lovisolo, and M. Cavagnaro, "Changes in the dielectric properties ofex vivobovine liver during microwave thermal ablation at 2.45 GHz," *Phys. Med. Biol.*, vol. 57, no. 8, pp. 2309–2327, Mar. 2012, doi: 10.1088/0031-9155/57/8/2309.

[37] Z. Ji and C. L. Brace, "Expanded modeling of temperature-dependent dielectric properties for microwave thermal ablation," *Phys Med Biol*, vol. 56, no. 16, pp. 5249–5264, Aug. 2011, doi: 10.1088/0031-9155/56/16/011.