Measuring PETase enzyme kinetics by single-molecule microscopy

Running title: Single-molecule PETase study

Yuwei Zhang[1] and William O. Hancock[1,2] *

[1] Department of Biomedical Engineering, Pennsylvania State University, University Park, Pennsylvania, USA

[2] Department of Chemistry, Pennsylvania State University, University Park, Pennsylvania, USA

* Corresponding author:
William O. Hancock
Email: woh1@psu.edu

Abstract:

Polyethylene terephthalate (PET) is one of the most widely produced man-made polymers and is a significant contributor to microplastics pollution. The environmental and human health impacts of microplastics pollution have motivated a concerted effort to develop microbe- and enzyme-based strategies to degrade PET and similar plastics. A PETase derived from the bacteria *Ideonella sakaiensis* was previously shown to enzymatically degrade PET, triggering multidisciplinary efforts to improve the robustness and activity of this and other PETases. However, because these enzymes only erode the surface of the insoluble PET substrate, it is difficult to measure standard kinetic parameters, such as k_{on}, k_{off} and k_{cat}, complicating interpretation of the activity of mutants using traditional enzyme kinetics frameworks. To address this challenge, we developed a single-molecule microscopy assay that quantifies the landing rate and binding duration of quantum dot-labeled PETase enzymes interacting with a surface-immobilized PET film. Wild-type PETase binding durations were well fit by a biexponential with a fast population having a 2.7 s time constant, interpreted as active binding events, and a slow population interpreted as non-specific binding interactions that last tens of seconds. A previously described hyperactive mutant, S238F/W159H had both a faster on-rate and a slower off-rate than wild-type PETase, potentially explaining its enhanced activity. Because this single-molecule approach provides a more detailed mechanistic picture of PETase enzymatic activity than standard bulk assays, it should aid future efforts to engineer more robust and active PETases to combat global microplastics pollution.

Statement of significance:

Plastic pollution is a global environmental and human health problem. PETases are recently discovered enzymes that degrade the ubiquitous plastic polyethylene terephthalate (PET). A push is underway to understand and optimize these enzymes to enable large-scale microplastics

remediation. Here, we use single-molecule fluorescence microscopy to visualize the interactions
of PETase enzyme molecules with a thin film of PET. We identify specific binding interactions of
a few seconds that differ between wild-type and PETase mutants that have been previously shown
to have altered activities. These single-molecule investigations provide a new window into the
mechanism and activity of PETase enzymes, and provide a platform for characterizing and
optimizing novel PETases with improved function and stability.

Introduction

Polyethylene terephthalate (PET) is one of the most widely produced man-made polymers, and

is derived from petroleum by the esterification of terephthalic acid and ethylene glycol.

Accumulation of PET and other microplastics in the environment is a pressing global problem that

has motivated efforts to develop microbe- and enzyme-based strategies to degrade PET (1, 2). In

2016, Yoshida *et al.* reported a newly discovered bacterium, *Ideonella sakaiensis* 201-F6, that was

able to use PET as its major carbon and energy source for growth. The PETase enzyme derived

from this microbe, *Is*PETase, was shown to convert PET to mono(2-hydroxyethyl) terephthalic acid

(MHET), with trace amounts of terephthalic acid (TPA) and bis(2-hydroxyethyl)-TPA (BHET) as

secondary products (3). This discovery set off a global interdisciplinary effort to identify,

characterize and optimize PET degrading enzymes, with the hope that these biodegradation

approaches can be scaled up to reduce microplastics pollution in the environment (4, 5).

Current methods to evaluate the specific activity of PETases have included analysis of PET surface

erosion by scanning electron microscope (SEM), quantifying decreases in PET crystallinity using

differential scanning calorimetry, and measuring product released by HPLC (6–8). These bulk

assays provide quantitative information on enzyme activity, but relating these measurements to

the specific enzyme kinetic parameters of the PETase enzymes is complicated by the insolubility

of PET and the fact that enzymes only act on exposed surfaces. Alternatively, there are

turbidimetric or colorimetric methods for PETase enzyme activity, such as the soluble substrates

p-nitrophenyl acetate (pNPA) and p-nitrophenyl butyrate (pNPB), but these soluble substrates are

poor analogs for crystalline PET (7, 9).

Like PETases, cellulases and cutinases are enzymes that react only with the surface of their

insoluble subtrates (10). Because the effective surface: volume relationship is generally not

known, it is difficult to directly apply the Michaelis-Menten formalism to these reactions.

Specifically, the resulting K_M values are not in typical molar concentrations, making it difficult to

extract the bimolecular on- and off-rates, k_{on} and k_{off}, as well as the enzyme turnover rate, k_{cat}.

One approach that has been used extensively on enzymes like cellulases or cutinases is to vary

the enzyme concentration rather than the substrate concentration in the solution, such that

enzymes partition to bound and soluble fractions (11–13). However, even here the available area,

A_0, is a key parameter that must be estimated rather than precisely measured. In contrast, single-

molecule approaches directly measure binding rates and durations, and thus they offer more

direct access to true biochemical parameters of enzymes. Further, because the activity of the

enzyme (rather than the substrate) is monitored, they sidestep the requirement of relating

exposed surface area to substrate mass or volume, which bulk assays typically require. To this end,

by imaging the cellulase Cel7A binding to and moving along its insoluble substrate, cellulose, we

were able to extract enzyme kinetic parameters from the single-molecule tracking dynamics (14).

Previous work that used bulk enzymatic assays and molecular dynamics simulations to investigate

key residues in the substrate binding cleft of *Ideonella sakaiensis* PETase identified two mutants

with altered activities (6). A hyperactive mutant, S238F/W159H, was created that narrowed the

substrate binding cleft towards that of native cutinase, and an impaired mutant, W185A was

created by mutating a highly mobile tryptophan thought to play a role in substrate binding. The

altered enzyme activities were measured by imaging the surface erosion of PET using electron

microscopy and by monitoring changes in the crystallinity of the PET substrate. These

experimental approaches clearly showed changes in enzyme activity, particularly the enhanced

activity of the hyperactive mutant, but because the methodology did not quantify k_{on}, k_{off} and k_{cat},

it is difficult to define in enzymatic terms which transition rates are altered by the mutations.

In the present work, we measured the single-molecule binding dynamics of *Ideonella sakaiensis*

PETase wild-type and both the hyperactive and impaired mutants characterized previously. We

used total internal reflection fluorescence microscope (TIRFM) of quantum dot (Qdot) labeled

PETase reversibly binding to glass coverslips functionalized with a thin film of PET. By measuring

the residence time of the enzymes on the substrate, we calculate an apparent off-rate that

provides information about both the turnover rate of the enzyme and its binding affinity to the

PET substrate. This work provides new insights into PETase function and introduces a new

approach for investigating the enzymology of other enzymes that react with insoluble substrates.

Materials and methods

Expression and purification of PETase enzymes

DNA plasmids for wild-type PETase (PETase, *I. sakaiensis*, accession number: A0A0K8P6T7,

Addgene number: #112202), hyperactive mutant (Addgene number: #112203) and the impaired

mutant (Addgene number: #112204) were purchased from Addgene (6). Plasmids were

transformed into *E. coli* C41(DE3) (Lucigen) and inoculated on a Nutrient Agar plate containing

100 μg/mL ampicillin (VWR; Cas: 69-52-3). After culturing overnight at 37°C, single colonies for

each variant were inoculated into a started culture of 5 mL Terrific Broth media (Thermo Scientific)

containing 100 μg/mL ampicillin and grown at 37°C overnight in a 180 rpm shaking incubator.

Each starter culture was then transferred into 2 L flasks with 400 mL media containing 100 μg/mL

ampicillin and grown at 37°C at 200 rpm until the optical density at 600 nm reached 0.6-0.8.

Protein expression was induced by adding 1 mM isopropyl β-D-1-thiogalactopyranoside (IPTG)

(EMD Millipore Corp.; Cas: 367-93-1). Cells were then incubated for 18 to 20 hours at 20°C at 200

rpm, harvested by centrifugation at 5000 rpm for 20 min, and stored at -80°C for later purification.

Frozen cell pellets were resuspended in a lysis buffer (300 mM NaCl, 10 mM imidazole, 20 mM

Tris HCl, pH 7.4,) and lysed by sonication. Lysate was clarified by centrifugation at 45,000 rpm for

35 minutes. The supernatant was then applied to a 2 mL Ni Sepharose 6 Fast Flow (Cytiva) column

and eluted by elution buffer containing 300 mM NaCl, 300 mM imidazole, 20 mM Tris HCl, pH 7.5.

Microscopy and image analysis

121 PET film (Goodfellow, UK) was cleaned in purified water by sonication, wiped with 100% ethanol,

122 cut into pieces, and dissolved in trifluoroacetic acid (TFA) (Sigma Aldrich; Cas: 76-05-1) to a

123 concentration of 1 wt%. 5-7 μL of PET solution was dripped onto a plasma cleaned coverslip,

124 covered with a second cleaned coverslip, and the two coverslips were then separated and dried

in air at room temperature for 30 min. Next, the coverslips were transferred to a 120°C oven for 20 min to achieve a smooth PET coating, followed by cooling at room temperature. Flow cells were assembled with the PET-coated coverslips using double-sided tape. The PET surface was blocked to minimize nonspecific protein adsorption by flowing 0.33 mg/mL casein into the flow cell for 3 min, followed by an enzyme solution consisting of 8 nM wild-type PETase or its mutant labeled with 0.8 nM $Qdot_{655}$ (Thermo Scientific), 2 mM 2-Mercaptoethanol (Sigma-Aldrich; Cas: 60-24-2), and 4 mM 4-Nitrophenyl acetate (Sigma-Aldrich; Cas: 830-03-5) in a buffer containing 100 mM NaCl and 50 mM sodium phosphate, pH 7.4. The $Qdot_{655}$-labeled PETase was imaged by total internal reflection fluorescence microscopy (TIRFM) using a 488 nm laser (70 mW or 150 mW) on a custom-built microscope (15). Movies began immediately before the enzyme solution was added to the flow cells. All experiments were performed at 22°C. The 10:1 enzyme:Qdot ratio was chosen because binding events were quite rare and lower ratios resulted in insufficient particle counts to accurately calculate landing rate and duration parameters.

PETase landing events and binding durations on the surface-immobilized PET film were measured by Kymograph analysis in ImageJ, as follows. Image stacks consist of a cube of x-y images at sequential times, t. First, the "Reslice" command was used to generate multiple x-t (horizontal) slices at varying y (vertical). The "Output spacing" was set to 5 pixels, which corresponds to the ~300 nm full width at half maximum of the point spread function of our microscope (15). Next, the "Grouped z projection" command was used to compress the multiple slices along the y axis into a single x-t image (see Fig. 1). From this kymograph, the binding durations are measured by the length of the vertical lines, where one pixel equals one frame, and the landing rate is measured by counting the total number of events throughout the entire movie. This approach of generating an x-t Kymograph is similar in principle to the approach of Pettersson *et al* (16). Binding duration distributions were fit to biexponentials in Python 3.9.19 using the 'scipy.optimize' library.

Results

Figure 1. PETase binds reversibly to PET film. (A) Experimental design for single-molecule TIRF analysis of Qdot-labeled PETase interacting with surface-immobilized PET film. Image is not to scale. (B) Kymograph analysis. A movie, consisting of a stack of x-y images at various t is captured and resliced into x-t frames for each y, and then compressed into a single x-t image. The image is then rotated by 90° to generate a single x-t kymograph (shown at right), where vertical streaks are single-molecule binding events of varying durations. (C) Binding durations of wild-type PETase, plotted as 1 − cumulative distribution function (1-cdf). Fitting to a biexponential function reveals a fast phase, representing reversible binding interactions, as well as a slow phase. Inset: first 15 s to show details of fast phase.

Qdot$_{655}$-labeled PETase binds reversibly to PET substrate

To observe the behavior of PETase enzymes on an immobilized PET surface, PET was dissolved in trifluoroacetic acid and dripped onto the surface of a coverslip, which was then covered by another plasma cleaned coverslip to make thin PET film on the surface of both coverslips. The PET-functionalized coverslip was incorporated into a flow cell, and 0.33 mg/ml casein was flowed through to reduce nonspecific protein adsorption. *Ideonella sakaiensis* PETase (Addgene Number: #112202) (6) was bacterially expressed and biotinylated (see Methods), and combined with

streptavidin-coated Qdot particles at a 10:1 enzyme:Qdot ratio. The PETase-Qdot complexes were

then introduced into the flow cell and allowed to interact with the PET surface. Landing events

were imaged by total internal reflection fluorescence microscopy (TIRFM) on a custom-built

multimodal microscope (15), and movies were obtained of the enzymes reversibly binding to the

surface-immobilized PET.

To quantify the reversible binding interactions, we developed a kymograph-based approach (Fig.

1B; described in Methods) to measure the frequency and duration of PETase binding events. The

5 frames/s video consists of a stack of x-y images through time. The binding events in our assay

are focal-limited spots of diameter ~300 nm, corresponding to the point-spread function of the

microscope (15). Because the events are relatively rare, we can collapse a given image in y-

without superimposing different events. When this image is rotated by 90°, the resulting image

corresponds to the positions in x along the horizontal axis and time along the vertical axis (Fig.

1B). From this kymograph, the binding durations are measured by the length of the vertical lines,

where one pixel equals one frame, and the landing rate is measured by counting the total number

of events throughout the entire movie.

We found that the distribution of binding durations of wild-type PETase was well fit by a double

exponential function consisting of a fast phase with a time constant of 2.7 ± 0.12 s (fit ± SE of the

fit for all time constants) and a slow phase with a time constant of 38.6 s (Fig. 1C).

Figure 2. Time constant of the slow phase varies with laser power. (A) Binding durations of PETase-free Qdots at 70

mW illumination with biexponential fit. Inset: early times to show fast phase. (B) Binding durations of PETase-free

Qdots at 150 mW illumination with biexponential fit. (C) Photobleaching rates of immobilized Qdots at varying

illumination intensities. Particles were nonspecifically bound to the surface and the average image intensity over

192 time plotted at 70 mW and 150 mW illumination intensities. Fit to exponential fall gives time constants for Qdot

193 photobleaching of 117.9 s and 76.3 s at 70 mW and 150 mW illumination, respectively.

Slow binding phase is consistent with non-specific binding

196 To better understand the origin of the fast and slow binding populations, we carried out a control

197 experiment using Qdots with no PETase bound. Using 70 mW laser power, Qdots were observed

198 to reversibly bind to the surface, and the binding durations followed a biexponential with a fast

199 phase of 1.5 ± 0.08 s (faster than the PETase fast phase of 2.7 s) and a slow phase of 51.1 ± 2.0 s

200 (Fig. 2A). We hypothesized that the slow time constant may be due to nonspecific and/or

201 irreversible binding of Qdots to the surface, with the apparent unbinding rate being due to

202 photobleaching or blinking of the Qdots. If this were the case, then increasing laser power to

203 accelerate bleaching should shorten the time constant of the slow phase. To test this, we repeated

204 the control Qdot experiment using a 150 mW laser illumination and found that the slow time

205 constant shortened from 51.1 s to 23.3 s, as expected, while the fast time constant remained at

206 1.5 s (Fig. 2B). This result is consistent with the slow phase being due to irreversible binding

207 events whose durations are truncated by photobleaching or blinking, rather than dissociation.

208 To further validate our photobleaching hypothesis, we immobilized Qdots on the surface and

209 quantified their population-level photobleaching rate. To do this, we flowed 50 pM Qdots (lacking

210 PETase) into the flow cell without first blocking the PET surface to prevent nonspecific adsorption,

211 washed away any free Qdots that did not bind, and imaged these nonspecifically-bound Qdots

212 under continuous laser illumination. The average fluorescence intensity of the image fell

213 exponentially over time due to photobleaching of the immobilized Qdots (Fig. 2C). At 70 mW laser

214 power, the time constant was 118 s, and at 150 mW laser power, the time constant fell to 76.3 s,

215 consistent with faster Qdot photobleaching at higher laser powers. This population-level result

216 reinforced our single-molecule result in Fig. 2AB, supporting our conclusion that the slow time

217 constant in the PETase experiments (Fig. 1) is due to slow photobleaching of Qdots that are

218 nonspecifically bound to the surface.

Figure 3. Hyperactive and impaired mutants have different fast-phase time constants and overall landing rates. (A) Distribution of binding durations of hyperactive PETase mutant, fit by a biexponential. Inset: first 15 s to show details of fast phase. (B) Distribution of binding durations of impaired PETase mutant, fit by biexponential. Inset: first 15 s to show details of fast phase. (C) Time constants of fast phase for wild-type (from Fig. 1C), and impaired and hyperactive mutant PETase (From Fig. 3A and B, respectively). Dashed line is time constant fast phase from Qdot control (see Fig. S1 for Qdot binding duration distribution). Error bars are standard error of the fit. (D) Single-molecule PETase landing rates, including all events independent of duration. Dashed line indicates PETase-free Qdot control landing rate. Error bars are SEM with N = 7 to 11 screens. Asterisks denote data are significantly different from one another with p <0.05 by a two-sample t-test. Additionally, all landing rates were significantly different from the Qdot control (red dashed line), with p<0.05 by two sample t-test.

On- and off-rates of hyperactive and impaired PETases differ from wild-type

We next used our single-molecule PETase assay to investigate the reversible binding dynamics of two previously described PETase mutants. Austin *et al*. generated a hyperactive double mutant, S238F/W159H, which was designed to narrow the active site of the enzyme and was found to degrade crystalline PET more effectively than wild-type (6). They also generated an inactive mutant W185A, which was found to have impaired activity compared to wild-type PETase (6).

Repeating our wild-type approach, we bacterially expressed, purified, and biotinylated the two

mutants, adsorbed them to Qdots, and quantified their binding durations. Comparing the fast

phases, which correspond to reversible binding, the hyperactive mutant had a time constant of

4.0 ± 0.07 s (fit ± SE of the fit), longer than the wild-type (2.7 ± 0.12 s), whereas the impaired

variant had a time constant of 1.7 ± 0.18 s, shorter than wild-type (Fig. 3A-C). These binding

durations are consistent with the hyperactive mutant having a higher PET binding affinity, and the

impaired mutant having a lower binding affinity than wild-type.

To quantify the relative on-rates for PET binding, we quantified the binding frequency of the three

PETase enzymes along with the Qdot control (Fig. 3D). Binding rates were normalized to the

enzyme concentration and to the area of the microscope image. The binding rate of the impaired

mutant, 1014 ± 282 $\mu m^{-2} \cdot s^{-1} \cdot M^{-1}$ (mean ± SEM for N=7 movies) was similar to the wild-type rate

of 1070 ± 310 $\mu m^{-2} \cdot s^{-1} \cdot M^{-1}$ (N = 9). Notably, the hyperactive mutant landed more frequently, at

2141 ± 254 $\mu m^{-2} \cdot s^{-1} \cdot M^{-1}$ (N = 7) than wild-type. Taken together, the results suggest that the

hyperactive mutant achieves a higher PET binding affinity through both a faster on-rate and a

slower off-rate. Finally, the landing rate for the Qdot control lacking PETase was 394 ± 113 /

$\mu m^2 \cdot s \cdot M$ (N = 11), roughly 1/3 of wild-type PETase (Fig. 3D, dashed line). This nonspecific Qdot-

PET interaction in the absence of enzyme means that the observed landing rates of the three

enzymes are somewhat overestimated; it follows that the measured enhancement of the landing

rate of the hyperactive mutant is a lower limit of the effect. A rough correction for this nonspecific

binding fraction is to consider the dashed red line in Fig 3D as the baseline.

Figure 4. The competitive inhibitor pNPA blocks PETase binding to PET. (A) Time constant for fast phase of Qdot control, impaired mutant, wild-type PETase, and hyperactive mutant in the presence (green bar) or absence of 4 mM pNPA (blue bar). See Fig. S2 for binding duration distributions. (B) Overall landing rate of Qdot control, impaired mutant, wild-type PETase, and hyperactive mutant in the presence (green bar) and absence of 4 mM pNPA (blue bar). (C) Relative amplitude in biexponential fit of the fast phase for Qdot control, impaired mutant, wild-type PETase and hyperactive mutant in the absence (blue bar) and presence of 4mM pNPA (green bar). (D) Corrected landing rate (defined as the overall landing rate multiplied by the relative amplitude of the fast phase) for Qdot control, impaired mutant, wild-type PETase and hyperactive mutant in the presence (green bar) and absence of 4 mM pNPA (blue bar). Error bars are SE of the fit.

pNPA acts as a competitive inhibitor for PET binding

To more thoroughly confirm that the observed binding interactions truly reflect the enzymatic activity of the wild-type and mutant PETases, we used a PETase inhibitor to more clearly separate out specific binding from the various non-specific interactions that may be occurring. 4-Nitrophenyl acetate (pNPA) is a model soluble substrate that is used for measuring the activity of esterases including PETases (7). We reasoned that when used at high concentrations, pNPA should

serve as a competitive inhibitor of the PETases, occupying the active site and blocking enzyme

binding to the immobilized PET film. Thus, we repeated the single-molecule binding experiments

in the presence of 4 mM pNPA.

pNPA reduced the binding duration of wild-type PETase and the hyperactive variant, but had

negligible effect on the binding durations of the impaired mutant and the control Qdots lacking

bound PETase (Fig. 4A). The clear effects of pNPA on the wild-type and hyperactive PETase provide

further validation that the fast binding durations are reporting productive interactions of the

enzymes with the immobilized PET. In contrast, the finding that the binding duration of the

impaired mutant did not change in the presence of pNPA calls into question whether this mutant

is specifically binding to the immobilized PET at all under our conditions.

The impacts of pNPA on the landing rate mirrors the effects on the binding duration. Specifically,

pNPA strongly diminished the landing rate of the wild-type and hyperactive mutant, whereas it

had a negligible effect on the landing rate of the impaired mutant and the Qdot control (Fig. 4B).

To better separate out contributions to the landing rate from specific binding versus nonspecific

binding, we first quantified the relative amplitudes of the fast and slow phases from the

biexpontial fits (Fig. 4C). For wild-type and the hyperactive mutant, the amplitudes of the fast

durations were diminished by pNPA, consistent with the inhibitor blocking the specific (fast)

interactions. As expected, the relative amplitudes of the impaired mutant and the Qdot control

were unaffected by pNPA. In the final analysis in Fig. 4D, we multiplied the overall landing rate

from Fig. 4B by the relative amplitude of the fast phase from Fig. 4C. This corrected landing rate

corresponds to the degree to which the pNPA inhibitor blocks functional binding of the PETases

to the immobilized PET. In summary, the pNPA results argue that both wild-type and hyperactive

mutant PETase bind specifically and reversibly to the PET, with hyperactive mutant having a faster

relative on-rate.

Discussion

Despite a number of studies that have used bulk assays and computational simulations to investigate the enzymatic activities of PETases, there has been little work at the single-molecule level aimed at uncovering their enzymology. Because the single-molecule approaches developed here enable us to measure and quantify binding events directly, they provide new information that can be integrated into more comprehensive studies of the enzymology of PETases and similar enzymes. These molecular insights can point to new directions for optimizing PETases to the point that they can be scaled up to tackle the significant problem of microplastics pollution in the environment.

The most challenging aspect of these single-molecule investigations was separating specific binding of the enzymes from nonspecific binding by the Qdot probes. Due to autofluorescence of the PET sample, labeling the PETases with standard fluorophores such as rhodamine resulted in an insufficient signal-to-noise for reliable detection. Instead, we turned to Qdots, which gave a very good signal-to-noise, but suffered from non-specific binding to the PET. We explored using surfactants to reduce nonspecific binding but were unable to find conditions that eliminated nonspecific binding while retaining specific binding. Thus, we carried out a series of control experiments to determine source of the fast and slow time constants we identified in our biexponential dwell times fits.

By characterizing Qdots lacking bound PETase and varying laser intensity to characterize photobleaching, we concluded that the slow time constant (~tens of seconds) of our biexponential fit to the dwell time distributions was due to nonspecific binding. The Qdot control lacking any bound enzymes had a residual binding interaction with a dwell time of 1.9 ± 0.12 s, but the landing frequency was substantially lower than Qdots containing a bound PETase (Fig. 3C and D). This lower landing rate and the elevated binding durations of the wild-type PETase and the hyperactive mutant were the first indication that the assays were detecting specific PET-PETase interactions. The strongest evidence that the fast binding population was indeed specific binding of the PETase to the immobilized PET was the fact that in the presence of the inhibitor pNPA, both the dwell times and the landing rates of the wild-type PETase and the hyperactive

mutant fell to near the Qdot control (Fig. 4). The most important experimental result was that the

mean dwell time of wild-type PETase was 2.7 s, the dwell time of the hyperactive S238F/W159H

mutant was 4.0 s, and the dwell time of the impaired W185A mutant was 1.7 s, which was similar

to control Qdots.

What can single-molecule imaging of enzymes tell us about their kinetic parameters? The

Michaelis-Menten framework consists of a reversible binding step, with rates k_{on} and k_{off}, and a

catalytic step, k_{cat}.

$$E + S \underset{k_{off}}{\overset{k_{on}}{\rightleftharpoons}} ES \overset{k_{cat}}{\rightarrow} E + P$$

The standard assumption is that product unbinding is fast relative to the catalytic step and is thus

lumped into k_{cat}. For single-molecule visualization of enzymes binding to an insoluble substrate,

we are visualizing the ES complex (meaning the clock starts when the fluorescent enzyme binds

to the surface). What we measure is dissociation from the surface, which is described by the

apparent dissociation rate, $k_{off}^{app.} = k_{off} + k_{cat}$. If we assume that the fast binding durations we

measure are reflecting the residence time of the enzyme on the PET substrate, then this apparent

off-rate can be calculated from our binding durations as $k_{off}^{app.} = \frac{1}{\tau_{fast}}$. From the fast time

constants in Fig. 3C, $k_{off}^{app.}$ are 0.37 s^{-1} for the wild-type, 0.25 s^{-1} for the hyperactive mutant, and

0.6 s^{-1} for the impaired mutant.

The first result that comes out of this analysis is that the upper limit for k_{cat} for wild-type PETase

is 0.37 s^{-1}. This conclusion comes from the fact that dissociation of the enzyme from the substrate

is either through unbinding before catalysis (k_{off}) or via a catalytic event followed by dissociation

from the "product" (cleaved PET in our case), with rate k_{cat}. It should be noted that the catalytic

event may be considerably faster than this, meaning that the lumped k_{cat} parameter is rate-

limited by product release. However, the functional turnover rate would be the same in this case,

as would the apparent k_{cat} that we observed. This relatively slow turnover rate presumably is

related to the crystallinity of PET film and the fact that experiments were performed at room

temperature. Previous work showed that higher degrees of crystallinity lead to greater resistance

of PET to enzymatic hydrolysis (17, 18). It is proposed that as temperatures approach the glass

transition temperature of PET, the mobility of the PET chain increases and results in more rapid

enzymatic hydrolysis (11, 19). Using bulk assays with the same wild-type PETase as used here,

Erickson et al measured a k_{cat} of 1.5 s^{-1} on amorphous PET and 0.8 s^{-1} on crystalline PET at 30 °C

(20), somewhat faster, but within the range of our k_{cat} of 0.37 s^{-1} at 22 °C.

The enzyme dissociation rates that we measure also provide insights into how mutations alter the

kinetic parameters of the enzymes. We interpret our data in the context of the simple Michaelis-

Menten model showin in Fig. 5. The hyperactive mutant, S238F/W159H was chosen by Austin *et*

al. because the mutations narrowed the active cleft of the enzyme to match that of other

cutinases (6). Induced fit docking simulations predicted that this double mutant would have much

higher affinity for PET, though no predictions were made on how the mutations may alter k_{cat}. We

find that $k_{off}^{app.}$ drops from 0.37 s^{-1} for the wild-type to 0.25 s^{-1} for the hyperactive mutant. First,

because a faster k_{cat} predicts a faster $k_{off}^{app.}$ (Fig. 5), our data argue that the greater surface erosion

and decrease in crystallinity seen with this mutant in a previous study (6) do not result from an

elevated k_{cat}. Consistent with this, Erickson et al. measured a k_{cat} of 0.5 s^{-1} for this hyperactive

mutant at 30 °C, slower than their wild-type k_{cat} of 0.8 – 1.5 s^{-1} in the same study (20). This value

at 30 °C is twice our inferred k_{cat} at 22 °C, which is reasonable agreement. However, this lower

k_{cat} measured by Erickson et al. seems at odds with the elevated PET surface erosion of this

mutant (6). One possible explanation of our slower apparent off-rate is that the rate of reversible

binding from the substrate, k_{off}, is slowed in the hyperactive mutant. The first effect of slowing k_{off}

is a lower K_M, which will improve performance at sub-saturating substrate concentrations. The

second effect is that for every enzyme-substrate encounter, there is a higher probability that the

enzyme will hydrolyze the substrate (with $p_{catalysis} = \frac{k_{cat}}{k_{cat}+k_{off}}$; Fig. 5) rather than simply

unbinding without acting on the substrate (with probability $p_{unbind} = \frac{k_{off}}{k_{cat}+k_{off}}$).

We can also use this analysis to interpret the impaired mutant. Previous work suggested that

residue W185 reorients upon productive binding to PET and may contribute π-stacking

interactions with aromatic groups in the PET substrate (6). The W185A mutation was found to

have reduced surface erosion activity on PET and a smaller reduction in PET crystallinity,

compared to wild-type (6). First, it should be noted that, because we found that τ_{fast} for the

impaired mutant was indistinguishable from that for Qdots alone (Fig. 3C), the $k_{off}^{app.}$ of 0.6 s^{-1} for

the impaired mutant should be considered a lower limit. Importantly, the landing rate of the

impaired mutant was considerably faster than Qdots alone (Fig. 3D), which argues that the

impaired mutant is not totally inactive. The simplest interpretation of the faster apparent off-rate

is that the off-rate of the impaired mutant from the PET substrate is considerably faster than wild-

type. This effect makes sense based on the proposed role of W185 in PET binding, and in bulk

assays would lead to a larger K_M. Another way to describe the mutation is that for every binding

encounter, the probability of a catalytic event, $p_{catalysis} = \dfrac{k_{cat}}{k_{cat}+k_{off}}$, is smaller, making the

enzyme less productive.

Conclusion and future outlook

We show here that single-molecule imaging can be used to deduce kinetic parameters of PETase

enzymes. This approach provides a new tool that can be combined with existing bulk methods

and computational tools to engineer more active and robust PETases that address microplastics

pollution. Further development of this single-molecule approach will require reducing the non-

specific adsorption that complicates interpretation of the kinetic data. Potential solutions include

using probes other than Qdots to label the enzymes, improved processing of the PET substrate to

reduce the autofluorescence, and identifying surfactants or other alterations in buffer conditions

that minimize nonspecific binding. Notably, more active enzymes that have higher k$_{cat}$ values are

predicted to bind for shorter durations, and nonspecific Qdot binding currently limits the upper

limit of apparent k$_{off}$ values that can be measured. One approach that has been explored for

improving PETase function is attaching a Carbohydrate Binding Module (CBM) or another

hydrophobic domain to PETases to improve their PET binding affinities (21, 22). If such a strategy

is successful in creating a processive enzyme that diffuses along the surface while carrying out

multiple chain cleavage reactions, this activity should be measurable as both a slower apparent

off-rate of the enzyme measured by the current approach, as well as diffusive movements that

could be detected by single-molecule tracking. In conclusion, the methods developed here

provide a new tool for screening engineered PETases with enhanced functions, which should

contribute to multidisciplinary efforts to use biocatalysts to reduce microplastics pollution in the

environment.

E + S   ES   E + P

Figure 5. Kinetic model of PETase binding to PET film. Free PETase in solution binds to PET film reversibly with

association rate constant k_{on} to form an enzyme-substrate complex. The complex then either disassociates with rate

constant k_{off} or proceed to the PET cleavage step with turnover rate k_{cat}, followed by rapid dissociation. Qdot-labeled

PETase molecules bind in the ES state and dissociate with an apparent rate constant $k_{off}^{app.} = k_{off} + k_{cat}$, which is

equal to the inverse of the fast phase dwell time. For each binding interaction, the probability that catalysis proceeds

rather than the enzyme unproductively dissociating is: $p_{catalysis} = \frac{k_{cat}}{k_{cat}+k_{off}}$.

Acknowledgements

420   The authors thank members of the Hancock lab for helpful suggestions and Dr. Justin Brown for

421   advice in PET preparation. This work was supported by NIH grant R35GM139568.

References

424   1.   Liu, K., T. Wu, X. Wang, Z. Song, C. Zong, N. Wei, and D. Li. 2019. Consistent Transport of
425   Terrestrial Microplastics to the Ocean through Atmosphere. *Environ. Sci. Technol.*
426   53:10612–10619.

427   2.   Materić, D., H.A. Kjær, P. Vallelonga, J.-L. Tison, T. Röckmann, and R. Holzinger. 2022.
428   Nanoplastics measurements in Northern and Southern polar ice. *Environ. Res.* 208:112741.

3. Yoshida, S., K. Hiraga, T. Takehana, I. Taniguchi, H. Yamaji, Y. Maeda, K. Toyohara, K.
Miyamoto, Y. Kimura, and K. Oda. 2016. A bacterium that degrades and assimilates poly
(ethylene terephthalate). *Science*. 351:1196–1199.

4. Wei, R., G. Von Haugwitz, L. Pfaff, J. Mican, C.P.S. Badenhorst, W. Liu, G. Weber, H.P. Austin,
D. Bednar, J. Damborsky, and U.T. Bornscheuer. 2022. Mechanism-Based Design of Efficient
PET Hydrolases. *ACS Catal.* 12:3382–3396.

5. Oda, K., and A. Wlodawer. 2024. Development of Enzyme-Based Approaches for Recycling
PET on an Industrial Scale. *Biochemistry*. acs.biochem.3c00554.

6. Austin, H.P., M.D. Allen, B.S. Donohoe, N.A. Rorrer, F.L. Kearns, R.L. Silveira, B.C. Pollard, G.
Dominick, R. Duman, K. El Omari, V. Mykhaylyk, A. Wagner, W.E. Michener, A. Amore, M.S.
Skaf, M.F. Crowley, A.W. Thorne, C.W. Johnson, H.L. Woodcock, J.E. McGeehan, and G.T.
Beckham. 2018. Characterization and engineering of a plastic-degrading aromatic
polyesterase. *Proc. Natl. Acad. Sci.* 115:E4350–E4357.

7. Pirillo, V., L. Pollegioni, and G. Molla. 2021. Analytical methods for the investigation of
enzyme-catalyzed degradation of polyethylene terephthalate. *FEBS J.* 288:4730–4745.

8. Kotova, I.B., Yu.V. Taktarova, E.A. Tsavkelova, M.A. Egorova, I.A. Bubnov, D.V. Malakhova,
L.I. Shirinkina, T.G. Sokolova, and E.A. Bonch-Osmolovskaya. 2021. Microbial Degradation
of Plastics and Approaches to Make it More Efficient. *Microbiology*. 90:671–701.

9. Pirillo, V., M. Orlando, D. Tessaro, L. Pollegioni, and G. Molla. 2021. An Efficient Protein
Evolution Workflow for the Improvement of Bacterial PET Hydrolyzing Enzymes. *Int. J. Mol.*
Sci. 23:264.

10. Kari, J., M. Andersen, K. Borch, and P. Westh. 2017. An Inverse Michaelis–Menten
Approach for Interfacial Enzyme Kinetics. *ACS Catal.* 7:4904–4914.

11. Ronkvist, Å.M., W. Xie, W. Lu, and R.A. Gross. 2009. Cutinase-catalyzed hydrolysis of poly
(ethylene terephthalate). *Macromolecules*. 42:5128–5138.

12. Scandola, M., M.L. Focarete, and G. Frisoni. 1998. Simple kinetic model for the
heterogeneous enzymatic hydrolysis of natural poly (3-hydroxybutyrate). *Macromolecules*.
31:3846–3851.

13. Wei, R., T. Oeser, M. Barth, N. Weigl, A. Lübs, M. Schulz-Siegmund, M.C. Hacker, and W.
Zimmermann. 2014. Turbidimetric analysis of the enzymatic hydrolysis of polyethylene
terephthalate nanoparticles. *J. Mol. Catal. B Enzym.* 103:72–78.

14. Haviland, Z.K., D. Nong, K.L.V. Kuntz, T.J. Starr, D. Ma, M. Tien, C.T. Anderson, and W.O.
Hancock. 2021. Nanoscale dynamics of cellulose digestion by the cellobiohydrolase
TrCel7A. *J. Biol. Chem.* 297.

15. Nong, D., Z.K. Haviland, K.V. Kuntz, M. Tien, C.T. Anderson, and W.O. Hancock. 2021.
Integrated multi-wavelength microscope combining TIRFM and IRM modalities for imaging
cellulases and other processive enzymes. *Biomed. Opt. Express*. 12:3253–3264.

16. Pettersson, J.R., F. Lanni, and G.S. Rule. 2017. Dual Lifetimes for Complexes between
Glutathione- *S* -transferase (hGSTA1-1) and Product-like Ligands Detected by Single-
Molecule Fluorescence Imaging. *Biochemistry*. 56:4073–4083.

17. Chen, C., X. Han, T. Ko, W. Liu, and R. Guo. 2018. Structural studies reveal the molecular
mechanism of PET ase. *FEBS J.* 285:3717–3723.

18. Mueller, R.-J. 2006. Biological degradation of synthetic polyesters—Enzymes as potential
catalysts for polyester recycling. *Process Biochem.* 41:2124–2128.

19. Zimmermann, W., and S. Billig. 2011. Enzymes for the biofunctionalization of poly
(ethylene terephthalate). *Biofunctionalization Polym. Their Appl.* 97–120.

20. Erickson, E., T.J. Shakespeare, F. Bratti, B.L. Buss, R. Graham, M.A. Hawkins, G. König, W.E.
Michener, J. Miscall, K.J. Ramirez, N.A. Rorrer, M. Zahn, A.R. Pickford, J.E. McGeehan, and
G.T. Beckham. 2022. Comparative Performance of PETase as a Function of Reaction
Conditions, Substrate Properties, and Product Accumulation. *ChemSusChem*.
15:e202101932.

21. Dai, L., Y. Qu, J.-W. Huang, Y. Hu, H. Hu, S. Li, C.-C. Chen, and R.-T. Guo. 2021. Enhancing PET
hydrolytic enzyme activity by fusion of the cellulose–binding domain of cellobiohydrolase I
from Trichoderma reesei. *J. Biotechnol.* 334:47–50.

22. Rennison, A.P., P. Westh, and M.S. Møller. 2023. Protein-plastic interactions: The driving
forces behind the high affinity of a carbohydrate-binding module for polyethylene
terephthalate. *Sci. Total Environ.* 870:161948.

Measuring PETase enzyme kinetics by single-molecule microscopy

Yuwei Zhang and William O. Hancock

Departments of Chemistry and Biomedical Engineering, Pennsylvania State University, University Park, Pennsylvania, USA

Figures S1-S2.

Figure S1 (related to Fig. 3): Binding durations of PETase-free Qdot control. Distribution of binding durations of Qdot control, fit by a biexponential. Inset: first 15 s to show details of fast phase.

Figure S2 (related to Fig. 4): **Binding durations in the presence of 4 mM pNPA.** (A) Distribution of binding durations of Qdot control in the presence of 4 mM pNPA, fit by a biexponential. Inset: first 15 s to show details of fast phase. (B) Distribution of binding durations of wild-type PETase in the presence of 4 mM pNPA, fit by a biexponential. Inset: first 15 s to show details of fast phase. (C) Distribution of binding durations of the inactive PETase mutant in the presence of 4 mM pNPA, fit by a biexponential. Inset: first 15 s to show details of fast phase. (D) Distribution of binding durations of the hyperactive PETase mutant in the presence of 4 mM pNPA, fit by a biexponential. Inset: first 15 s to show details of fast phase.