The Influence of Crosslinker Architecture on Dynamic Covalent Hydrogel Viscoelasticity

Authors: *Yung-Hao Lin[1], Junzhe Lou[2], Yan Xia[3] and Ovijit Chaudhuri[4] **

Abstract

Dynamic covalent crosslinked (DCC) hydrogels represent a significant advance in biomaterials for regenerative medicine and mechanobiology. These gels typically offer viscoelasticity and self-healing properties that more closely mimic *in vivo* tissue mechanics than traditional, predominantly elastic, covalent crosslinked hydrogels. Despite their promise, the effects of varying crosslinker architecture – side chain versus telechelic crosslinks – on the viscoelastic properties of DCC hydrogels have not been thoroughly investigated. This study introduces hydrazone-based alginate hydrogels and examines how side-chain and telechelic crosslinker architectures impact hydrogel viscoelasticity and stiffness. In side-chain crosslinked gels, higher polymer concentrations, enhances stiffness and decelerates stress relaxation, while an off-stoichiometric hydrazine-to-aldehyde ratio leads to reduced stiffness and shorter relaxation time. In telechelic crosslinked gels, maximal stiffness and stress relaxation occurs at intermediate crosslinker concentrations for both linear and star crosslinkers, with higher crosslinker valency further increasing stiffness and decreasing relaxation rates. Our result suggested different ranges of stiffness and stress relaxation are accessible with the different crosslinker architectures, with side-chain crosslinking leading to gels with slower stress relaxation times relative to the other architectures, and star crosslinked gels providing increased stiffness and slower stress relaxation relative to linear crosslinked gels. The mechanical properties of hydrogels with star crosslinking are more robust to changes induced by competing chemical reactions compared to linear crosslinking. Our research underscores the pivotal role of crosslinker architecture in defining hydrogel stiffness and viscoelasticity, providing crucial insights for the design of DCC hydrogels with tailored mechanical properties for specific biomedical applications.

[1]Department of Chemical Engineering, Stanford University, Stanford, CA, USA
[2]Wyss Institute for Biologically Inspired Engineering, Harvard University, Boston, MA, USA
[3]Department of Chemistry, Stanford University, Stanford, CA, USA
[4]Department of Mechanical Engineering, Stanford University, Stanford, CA, USA

*Address correspondence to chaudhuri@stanford.edu

1. Introduction

Mechanotransduction, the dynamic process by which cells translate mechanical cues into biochemical signals, has become a focal point of research over the past decade. This burgeoning interest stems from significant advancements in biomaterial design, fluorescent microscopy, and molecular biology tools, propelling our understanding of the intricate molecular pathways involved. Historically confined to the simplistic environment of petri dishes, the study of cellular behaviors has evolved, adopting specially treated surfaces and 2D cultures atop biomaterial hydrogels, and progressing to 3D culture of cells within engineered hydrogels with tailored properties[1]. This evolution marks a critical step towards accurately mimicking the cellular microenvironment, mirroring both the physical constraints and the complex composition of the extracellular matrix (ECM) [2–6]. The importance of these advancements is underscored by a growing body of literature and clinical evidence, which suggests that variations in ECM stiffness or viscoelasticity serve as indicators and drivers of disease progression[7–13]. It is understood that biological tissues are viscoelastic[14,15], and that the viscoelastic properties of the matrix critically influence cellular behaviors, including cell spreading[16,17], cell migration[18,19], ECM secretion[16,20,21], stem cell differentiation[13,22–24] , morphogenesis[25,26], cell cycle progression[27,28], and even immune cell phenotypic changes[29]. Consequently, the rational design of biomaterial hydrogels, aimed at precisely modulating stiffness and viscoelasticity, has emerged as a cornerstone in the fields of regenerative medicine and mechanobiology.

Among the myriad of biomaterials, dynamic covalent crosslinked (DCC) hydrogels, particularly those utilizing Schiff-base chemistries including hydrazone, imine, and oxime bonds for crosslinking, have garnered attention for their injectability[30–34], self-healing[35–38], and viscoelastic nature[16,17,23,25,39–43]. The hydrazone linkage, a reversible bond formed between hydrazine and aldehyde, is renowned for its biocompatibility and rapid kinetics, establishing it as a frontrunner in DCC chemistry for both regenerative medicine applications and mechanobiology investigations. Researchers have develop various strategies to modify either synthetic or natural polymers for hydrazone crosslinked hydrogels, for example, polyethylene glycol (PEG)[20,42,43], poly(L-glutamic acid) (PLGA)[44], alginate[39,45,46], xanthan[36], hyaluronic acid (HA)[16,31], and elastin-like protein[23,32,47,48]. Numerous studies have investigated how different parameters modulate the mechanical properties of the hydrazone hydrogels, such as polymer weight percentage[16,47,49], molecular weight of the polymers[33], degree of substitution (DS%) of chemical groups on the polymers[25,33,47,49], the stoichiometry of hydrazine to aldehyde [33,47], the relative ratio between aldehyde and benzaldehyde[16,20,23,25,32], the valency of the crosslinker[49], or the concentration of small molecule catalyst and competitor [31,32,49,50]. We have recently elucidated that, among these parameters, the viscoelasticity of hydrogels is primarily determined by two factors: the exchange rate of crosslinks and the number of effective crosslinks per polymer chain[49]. However, the specific impact of crosslinker architectures—the polymeric structure of the crosslinks—on the stiffness and viscoelasticity of hydrazone hydrogels has not been thoroughly explored.

To elucidate how the structure of crosslinker regulates hydrogel mechanical properties, we developed alginate and PEG-based hydrazone crosslinked hydrogels formed from side-chain

crosslinking or telechelic crosslinking using crosslinkers with linear or star architectures (Figure 1A). Side-chain crosslinking occurs when hydrazine functionalized on the side-chain of alginate (AG-HYD) crosslinks with aldehyde functionalized on the side-chain of alginate (AG-ALD). Telechelic crosslinking occurs when AG-HYD is crosslinked with aldehyde functionalized at the end-points PEG, including linear PEG-dialdehyde (2ALD) and "star" shaped 4-arm PEG-aldehyde (4ALD). The lack of cell adhesion binding site on either alginate or PEG offers an unbiased approach to study pure mechanistic effects on cellular behavior without the presence of biochemical cues. Most *in vitro* 3D cell culture systems using biopolymer hydrogels or reconstituted ECMs have a stiffness range from 10 to 100 kPa[2,4,5,8,14,20,23,26]. Extensive studies have been performed using side-chain crosslinking with hydrazone gels. However, most of these gels do not exhibit physiologically relevant viscoelasticity (i.e., stress relaxation half-times of $\tau_{1/2}$ = 10-1000 sec) hydrogels with this range of stiffness (Table. 1), unless an interpenetrating networks (IPNs) of collagen is incorporated to provide faster mode of relaxation[16,17]. The telechelic crosslinker architectures have gained popularity due to the ease of using small molecule adipic acid dihydrazide as a crosslinker[39,41,44,46]. However, few studies report the tunable range of stiffness and viscoelasticity of linear crosslinked hydrogels, and none indicate the range relevant for star crosslinking hydrogels[36]. Another architecture star-star crosslinking, where hydrazone-modified multi-arms PEG crosslinked with aldehyde-modified multi-arms PEG, was not investigated in our work, but data from previous literatures were provided as comparison. Fast relaxation could only be achieved with either IPNs or extremely high polymer concentrations[42,43,51].

Here we demonstrate that side-chain, linear, and star crosslinked DCC hydrazone-based hydrogels exhibit distinct ranges of stiffness and viscoelasticity. Polymer concentration and the stoichiometry of hydrazine to aldehyde modulated stiffness and stress relaxation time of side-chain crosslinking gels. Crosslinkers with different MW and valencies impacted the stiffness and viscoelasticity for telechelic crosslinking gels. Further, we report that the mechanical properties of star crosslinked hydrogels were not significantly altered by encapsulation of high cell density, further highlighted the importance of crosslinker architectures. This work aims to serve as a guidance of polymer and crosslinker architecture selection tailored to biomedical applications where stiffness and viscoelasticity are critical aspects.

2. Results and discussion

2.1 Controlled Functionalization of Alginate with Hydrazine or Aldehyde via Click Chemistry

To elucidate the role of crosslinker architecture in dictating the viscoelastic properties of hydrogels, we engineered alginate-based hydrogels featuring diverse dynamic crosslinker architectures. Alginate was chosen as backbone polymers for its ubiquity in biomedical applications and amenability to chemical modifications. We modified 10% of carboxylate groups on alginate polymers with hydrazine or aldehyde following our previously reported two-step click functionalization (Figure 1B; Figure S1 and S2, Supporting Information)[16]. This synthetic method ensured equivalent functionalization levels of hydrazine and aldehyde on AG-HYD and AG-ALD, respectively. Notably, this click chemistry strategy for aldehyde functionalization circumvents the polymer degradation observed with oxidation methods. Dynamic covalent crosslinked (DCC) hydrogels were formed *in situ* via the hydrazone bond formation under physiological conditions when mixing hydrazine-containing polymer with aldehyde-containing polymers (Figure 1A). Side-chain crosslinking hydrogels were formed by mixing AG-HYD with AG-ALD. For telechelic crosslinking, an extensive array of commercially available aldehyde-functionalized polyethylene glycol (PEG) variants, differing in valency and molecular weight, was employed (Figure 1C). Linear crosslinking hydrogels were formed by mixing AG-HYD with PEG-dialdehyde (PEG-2ALD), and star crosslinking hydrogels were formed by mixing AG-HYD with 4-arm PEG-aldehyde (PEG-4ALD). Two of the star crosslinking hydrogels dyed with different colors were used to demonstrate self-healing capability of DCC hydrogels (Figure 1D; Figure S8, Supporting Information). To ensure a fair comparison of viscoelastic properties across different architectures, the degree of substitution (DS%) of hydrazine on AG-HYD was fixed, given its substantial influence on the hydrogels' elastic modulus[33].

2.2 Side-chain Crosslinking Hydrogels Exhibit Slow Stress Relaxation

To investigate the mechanical properties of side-chain crosslinking hydrogels, we utilized a model system consisting of AG-HYD and AG-ALD, both at a molecular weight (MW) of 28 kDa and a degree of substitution (DS) of approximately 10%. The use of side-chain crosslinker architecture offered several distinct advantages: the simplicity of employing identical polymer backbones modified with different chemical groups; the availability of a broad spectrum of biopolymers, primarily polysaccharides, with side-chain functional groups amenable to chemical modifications; and flexibility of tuning the degree of substitution for range of crosslinking density. The viscoelastic properties of these hydrogels were adjusted by varying the total polymer concentration and the stoichiometry of the hydrazine and aldehyde functional groups. The evaluation of mechanical properties was conducted through a series of rheological tests: a time sweep, frequency sweep, and a stress relaxation test (Figure 1E, 2A and 2B). As expected, at a 1:1 stoichiometry of AG-HYD to AG-ALD, an increase in total polymer concentration resulted in a higher elastic modulus, attributed to the greater amount of polymer and higher density of crosslinking sites (Figure 2C)[16,52]. Hydrogels with 1 wt% alginate exhibited an elastic modulus of 0.99 kPa, which increased to 17.85 kPa at a concentration of 4 wt%.[16,49] Hydrogels formulated with off-stoichiometric ratio of hydrazine to aldehyde (either 1:3 or 3:1) demonstrated reduced stiffness and accelerated stress relaxation at the same overall polymer concentration (Figure 2F), aligning with the biphasic influence of stoichiometry on stiffness observed in prior studies[33].

However, the similar biphasic relationship on stress relaxation time was not reported in literatures. Overall, side-chain crosslinking hydrogel presented substantial range of stiffness tunability, from 0.24 to 18 kPa across the 1 to 4 wt% gel formulations of various hydrazine to aldehyde ratio. Nonetheless, their viscoelasticity range was constrained. The stress relaxation half-times ($\tau_{1/2}$), the time required for stress in hydrogel to relax to half of its initial value, were consistently exceeding 1,500 seconds (Figure 2E, H) and loss tangent remaining below 0.03 (Figure 2D, G), fall beyond biological relevant range[15].

2.3 Intermediate crosslinker concentration leads to maximum stiffness and stress relaxation time in telechelic crosslinking

We next tested the range of properties accessible for hydrogels with telechelic crosslinking. We utilized the hydrazone hydrogels consisting of AG-HYD and PEG-2ALD for linear crosslinking or PEG-4ALD for star crosslinking. Similar to side-chain crosslinking, we hypothesized that an intermediate ratio of hydrazine to aldehyde within telechelic crosslinking structures would yield the peak in both stiffness and stress relaxation half-time. Indeed, we found that in either linear crosslinking (Figure 3A, B) or star crosslinking (Figure 3C, D), the intermediate PEG-aldehyde crosslinker concentration leads to maximal stiffness and stress relaxation time under the same AG-HYD concentration. At low crosslinker concentrations, there were not sufficient levels of interchain crosslinking to form robust percolating polymer networks. Conversely, excessive aldehyde crosslinker lead to saturation of hydrazine groups on alginate chains, resulting in dangling PEG on alginate chain that don't contribute to the crosslinked network[53]. This higher polymer concentration does not contribute to higher stiffness, indicating the hydrazine to aldehyde ratio dominates the mechanical properties of the hydrogel instead of entanglement (Figure S7, Supporting Information). Overall, within telechelic crosslinker architectures, the intermediate concentration of crosslinker leads to peak stiffness with slowest stress relaxation.

2.4 Modulation of Viscoelastic Properties by Crosslinker Molecular Weight and Valency in Telechelic Crosslinking

To further explore the parameters that could modulate the telechelic crosslinking hydrogel viscoelasticity, we delved into the roles of crosslinker molecular weight (MW) and valency. We hypothesized that with telechelic crosslinking, under the same crosslinker molar concentration (mM), crosslinkers with higher MW may lead to higher stiffness and stress relaxation time due to potential entanglement associated with higher polymer weight concentrations. Surprisingly, crosslinkers of intermediate MW exhibited the higher levels of stiffness and stress relaxation, observable in both linear (Figure 3A, B) and star (Figure 3C, D) crosslinker architectures. This phenomenon may arise from the intermediate crosslinkers' length aligning more closely with the spacing between available hydrazine groups in the networks, optimizing interchain crosslinking. Shorter crosslinkers likely fail to bridge two alginate chains, while longer crosslinkers may inadvertently facilitate intrachain crosslinking, subsequently reducing the overall hydrogel elasticity. Further, we hypothesized that, under the same crosslinker molar concentration and MWs, crosslinkers with higher valency (e.g., 4-arm for star) would yield more elastic hydrogel compared to those with lower valency (e.g. 2-wrm for linear). Consistent with this expectation, star crosslinking resulted in up to a 33-fold increase in stiffness and 20-fold increase in stress

relaxation time relative to linear crosslinking (Figure 3E, F; Figure S9, Supporting Information). This agrees with the previous study that increasing the number of crosslinking sites per chain slows stress relaxation[49].   Notably, stress relaxation time exhibited a positive logarithmic correlation with elastic modulus across different crosslinker architectures (Figure 3G). Though, the slopes of these relationships did depend upon the crosslinker MW and valency. These findings underscore the pivotal influence of crosslinker MW and valency on the viscoelastic characteristics of DCC hydrogels.[18]

2.5 DCC hydrogel viscoelasticity is crosslinker architecture dependent

To elucidate whether crosslinker architectures could contribute to different range of viscoelasticity of DCC hydrogel, we overlayed all the measurements collected in this work on stress relaxation versus stiffness plot with colors indicating the loss tangent (Figure 4A). Surprisingly, we observed distinct regions among side-chain, linear, and star crosslinking hydrogels, with minimal overlap. Linearly crosslinked gels lie in a regime of low stiffness, fast stress relaxation, and high loss tangent. Side-chain crosslinked gels occupy a region of slow stress relaxation and minimal loss tangent. Star crosslinking leads to higher stiffness gels, but with a lower loss tangent and slower stress relaxation, relative to linear crosslinking. Data from existing literature were consistent with our results, though less data existed for linear crosslinking and no data was found for star crosslinking (Figure 4B). Overall, side-chain crosslinking hydrogels exhibit a broad stiffness range but predominantly fall in a slow relaxation regime (>4,000 sec). Achieving faster stress relaxation requires a high off-stoichiometric ratio of hydrazine to aldehyde, which significantly reduces stiffness (Figure 2F, H). In contrast, linear crosslinking hydrogels demonstrate much faster stress relaxation, akin to biological tissues, but with a limited stiffness range of 0.3 to 1.1 kPa (Figure 3A, B)[15]. Star crosslinking hydrogels, however, offer a wide stiffness spectrum while maintaining fast stress relaxation close to the physiological relevant range. Overall, these findings underscore the unique viscoelastic ranges presented by DCC hydrazone hydrogels of varied crosslinker architectures. Further and importantly, understanding the interplay between various crosslinking parameters can guide the design of studies designed at elucidating how one mechanical property of the hydrogels independently regulates cellular behaviors of interest. For instance, to investigate the mode of cell migration in DCC hydrogels of same stiffness but different stress relaxation time[18], hydrogels that follow a vertical line in Figure 4A can be utilized.

2.6 Impact on Mechanical Properties from Encapsulated Cells Depends on Crosslinker architectures

The impact of encapsulated cells on the viscoelastic properties of hydrogels was assessed to gauge the limitation of these materials for 3D cell culture or cell and drug delivery applications. Given the marked increase in stiffness and stress relaxation time from star compared to linear crosslinking, we speculated that the additional valency with star crosslinking might enhance resistance to competitive chemical reactions that threaten the integrity of hydrazone bonds. Such competitive interactions may arise from glucose in its open-chain form found in cell culture media, as well as free amines from amino acids, serum, cell membrane proteins, and secreted ECM components[54,55]. We focused on hydrogels with the highest identified stiffness and stress relaxation time for both linear and star crosslinking configurations, as shown in Figure 3A and

Figure 3C: 2wt% AG-HYD with 8 mM PEG-2ALD (2 kDa) for linear crosslinking and 2wt% AG-HYD with 4 mM PEG-4ALD (10 kDa) for star crosslinking. In linear crosslinked hydrogels, encapsulating 10 million MDA-MB-231 breast cancer cells per milliliter resulted in an approximate 70% decrease in initial stiffness and a 40% reduction in stress relaxation time (Figure 5A, B). Conversely, star crosslinked hydrogels maintained their stiffness and exhibited only a minor reduction in stress relaxation time under identical conditions of AG-HYD concentration and cell density, showcasing the valency-dependent resistance of hydrazone bonds against competitive reactions. Interestingly, side-chain crosslinked hydrogels at the same alginate concentration also demonstrated a 30% reduction in stiffness. However, a 6wt% alginate hydrogel with side-chain crosslinking, possessing a polymer content comparable to the star crosslinking formulation, did not show compromised stiffness, though its stress relaxation time was halved upon cell encapsulation (Figure S10, Supporting Information). This suggests that within a given crosslinker architecture, the stability of hydrazone bonds against competitive reactions may also be influenced by the crosslink density associated with the increased polymer content. These observations underscore the critical need for careful selection of crosslinker architecture, especially when alterations in mechanical properties due to encapsulated entities are of concern in applications. For example, in hydrogel-based cell, gene, and drug delivery systems, the influence of payload density on mechanical properties and release kinetics may require careful study.

2.7 3D cell culture in hydrogels of varied crosslinker architecture
Next, we explored 3D cell culture in hydrogels with different crosslinker architectures. After 24 hours of culture, the MDA-MB-231 cell cross section area and circularity were analyzed. In side-chain crosslinking gels (E=17.8 kPa, $\tau_{1/2}$=4,492 sec), cells predominantly adopted a rounded morphology, characterized by a mean circularity of 0.835 and a cross-sectional area of 241.3 μm^2 (Figure 5C, D). In contrast, cells in star crosslinked gels (E=18.7 kPa, $\tau_{1/2}$=1,139 sec) displayed an ellipsoidal shape, with a decreased mean circularity of 0.513 and an increased cross-sectional area of 468.2 μm^2. This shows that under the same stiffness, the hydrogel with faster stress relaxation leads to more elongated cell morphology (Figure 5E). Linear crosslinking hydrogels, however, experienced rapid disintegration within 24 hours in cell culture media, precluding any cell shape and area analysis. This fast erosion is likely due to the reversible nature of hydrazone bonds, the limited valency of PEG-dialdehyde crosslinkers, and competitive interactions from free amines targeting imine bond formation. To improve the stability of linear crosslinked hydrogels in cell culture conditions, strategies such as increasing the degree of substitution (DS%) of AG-HYD or incorporating PEG-dibenzaldehyde for more durable hydrazone linkages may be necessary[16,20].

3. Conclusion
In this work, we demonstrate the influences of dynamic covalent crosslinked (DCC) hydrazone hydrogel crosslinker architectures —whether side-chain or telechelic—on viscoelasticity and stiffness of the resulting biomaterial. We have identified that side-chain crosslinking yields hydrogels with a considerable range of stiffness but consistently slower stress relaxation. In contrast, telechelic crosslinking, particularly with star-shaped crosslinkers, affords a versatile

modulation of hydrogel mechanical properties, enabling the achievement of higher stiffness than linear crosslinking counterparts and more rapid stress relaxation in comparison to side-chain crosslinking gels. Furthermore, we elucidate that hydrogels with star crosslinker architecture exhibit remarkable mechanical stability with high encapsulating cell density. These findings underscore the importance of crosslinker architecture consideration in the design of biomaterial hydrogels tailored for specific biomedical applications.

4. Experimental Section

Alginate modification

Alginate-alkyne (AG-ALK)

The alginate modification scheme was adapted from a previous study that reported the coupling of alkyne and hydrazine groups to hyaluronic acid[16] (Fig. S1). Low molecular weight alginate (#4200501, batch BP-1212-24, PRONOVA, UP VLVG) (1 g, 5.7 mmol, 1 eq.) was fully dissolved in 100 mL MES buffer (200 mM MES hydrate, 154 mM NaCl, pH=4.5). The following chemicals were then added quickly to the 1 wt% alginate solution with the following order: N-hydroxysuccinimide (NHS) (261.6 mg, 2.3 mmol, 0.4 eq., #130672 Sigma Aldrich), EDC (435.5 mg, 2.27 mmol, 0.4 eq., #E6383, Sigma Aldrich), then propargylamine (145.6 uL, 2.273 mmol, 0.4 eq., #P50900, Sigma Aldrich). After adjusting pH of the mixture to 6, the solution was stirred at room temperature for 4 hrs, followed by quenching with hydroxylamine hydrochloride (631.7 mg, 9.09 mmol, 4 eq., #159417 Sigma-Aldrich) for 30 min. The solution was dialyzed (MWCO = 10 kDa) in deionized (DI) water at 4°C, with two water exchange in the first hour and 8 more times in the following 3 days. The solution was lyophilized (Labconco freezone 4.5 lyophilizer) for 5 days to get white cotton-like alginate-alkyne (AG-ALK) product. The AG-ALK product was stored at -30°C until use.

Alginate-hydrazine (AG-HYD) and Alginate-aldehyde (AG-ALD)

AG-ALK (500.0 mg, 2.347 mmol, 1 eq.) was dissolved in 25 mL of 0.1M PBS (10 mM NaH2PO4, 9 mM Na2HPO4, 0.1 M NaCl, pH=7.4), then N-(3-azidoethyl)-2-hydrazineylacetamide (compound **2**, 296.71 mg, 1.878 mmol, 0.8 eq.) or azido-aldehyde (compound **3**, 424.41 mg, 1.878 mmol, 0.8 eq.) was added to the alginate solution. Sodium ascorbate (1045.8 mg in 1.5 mL DI water, #11140 Sigma-Aldrich), copper sulfate pentahydrate (176.1 mg in 1.5 mL DI water, #209198 Sigma-Aldrich), and alginate solution were sealed in separated vials and bubbled with nitrogen for at least 30 min. Sodium ascorbate (200 uL; 139.4 mg, 0.704 mmol, 0.3 eq.) and copper sulfate pentahydrate solutions (100 uL; 11.74 mg, 0.047 mmol, 0.02 eq.) were added to the alginate solution sequentially under continuing nitrogen bubbling. The alginate solution was stirred for 1 day at room temperature (or 2 days at 4°C for AG-ALD) while protected from light. The reaction was quenched with 0.5 wt% EDTA (10 mL, 0.4x v/v to alginate solution) for 30 min at room temperature. The solution was dialyzed (MWCO = 10 kDa) in DI water at 4°C with 10 buffer exchanges in 3 days, then filtered through 0.22 µm filter. The filtered solution was lyophilized for 5 days to get white cotton-like AG-HYD or AG-ALD product. The final lyophilized product was stored at -30°C until use. The degree of substitution (DS%) on alginate was determined using NMR spectroscopy under 70°C by integration of the proton signal on triazole relative to the proton on the first carbon of guluronic acid on alginate backbone and assumed guluronic acid to mannuronic acid ratio of 1.5. 1H NMR integration indicated that ~10% of the carboxylate groups on the alginate backbone have been functionalized with either hydrazine or aldehyde. Triazole H: ^{1}H NMR (500 MHz, D$_2$O) δ 7.88 (s, 1H). Guluronic acid H: ^{1}H NMR (500 MHz, D$_2$O) δ 5.03 (s, 1H).

Hydrogel preparation

AG-HYD, AG-ALD, and PEG-aldehyde of various molecular weight and valencies were dissolved in low glucose Dulbecco's modified Eagle's medium (DMEM-LG) (#11885084, Gibco) with 25 mM of HEPES and adjust pH to 7.4~7.5, monitored by micro pH probe (pH Sensor InLab® Micro,

#51343160, METTLER TOLEDO). It has been shown that free amines, either from amino acids or proteins, may compete with the hydrazone bonds via imine bond formation with free aldehydes [54,55]. Thus, we intentionally excluded fatal bovine serum and antibiotics from the low glucose Dulbecco's Modified Eagle Medium (DMEM-LG) to reconstitute the AG-HYD and AG-ALD polymers when performing rheological tests. Due to the pH sensitivity of hydrazone bond formation, we supplemented 25 mM of HEPES in the media to help with buffering the pH when CO_2 control was not feasible under the shear rheometer. The pH of the reconstituted polymer was monitored and adjusted to neutral using micro pH meter before each measurement to minimize the artifact of changing stiffness and stress relaxation time results from the gradually rising pH in atmospheric condition. By mixing AG-HYD with either AG-ALD or PEG-aldehyde in eppendorf, hydrogels were rapidly formed after few seconds of vortexing. For example, to prepare a 100 uL of 2wt% side-chain crosslinking (HYD : ALD = 1 : 1) hydrogel, 50 uL of 4wt% AG-ALD was first mixed with 25 uL of media. Then 50 uL of 4wt% AG-HYD was added to the mixture. To prepare a 100 uL of 2wt% star crosslinking hydrogel with 4 mM of PEG-4ALD, 16 uL of 25 mM PEG-4ALD was first mixed with 34 uL of media. Then 50 uL of 4wt% AG-HYD was added to the mixture.

Rheological characterization
Rheology measurements were performed on Discovery HR-2 hybrid rheometer (TA Instruments) to quantify the frequency-dependent viscoelastic properties including storage modulus, loss modulus. The rheometer was heated to 37°C before measurements. 60 uL of hydrogels were deposited directly onto the rheometer base plate. An 8-mm flat plate was then immediately lowered to contact the gel to form an 8-mm disk. Mineral oil (Sigma) was applied to seal the edges of the gel to prevent hydration. Time sweep was performed at 1 rad s^{-1} and 1% strain until storage and loss modulus plateaued. Assuming Poisson's ratio (v) of 0.45, the elastic modulus was calculated based on the equation:

$$E = 2(1 + v)G^*$$ (1)

were the complex modulus (G^*) was derived from the measured storage (G') and loss modulus (G") by:

$$G^* = (G'^2 + G"^2)^{1/2}$$ (2)

Frequency sweep measurements was then performed from 0.1 to 100 rad s^{-1} at 1% strain. For stress relaxation measurement, after letting hydrogel sit for 5 min to equilibrate, a constant strain of 15% was applied to the gel and the resulting stress was recorded. The stress relaxation time ($\tau_{1/2}$) was defined as the time that resulting stress decayed to one-half of the initial value. The mechanical characterization from previous works were analyzed by an online data-capturing program WebPlotDigitizer (Rohatgi, WebPlotDigitizer, 2022).

Encapsulation of cells in hydrogel
MDA-MB-231 cells were cultured in high glucose Dulbecco's modified Eagle's medium (#11995065, Gibco) containing 10% fetal bovine serum (#35-015-CV, Corning) and 1%

penicillin/streptomycin (#15140122, Gibco). Cells were passaged around 70% confluency, spun down, resuspended in DMEM-LG containing 10% fetal bovine serum and 1% penicillin/streptomycin. Cell density was measured using Vi-CELL cell viability analyzer (Beckman Coulter). To make a cell-containing hydrogel for mechanical characterization, cell suspension was added to the mixture of media and AG-ALD or PEG-aldehyde, before mixing with AG-HYD. The final cell density in the hydrogels were 10^7 cells/mL. For 24 hours of 3D cell culture, MDA-MB-231 cells were encapsulated at 10^6 cells/mL. 100 µL of cell-containing hydrogels were added to the bottom of a well in 8-well LabTek chamber (#155360, Thermo Scientific). After 30 minutes, 100 uL of cell culture media was added on top of each gel, then the hydrogels were incubated in incubator for 24 hours. Calcein-AM dye (#C1430) of 1:1000 dilution was then used to stain cells for 30 minutes in the incubator before imaging. The formulation of side-chain crosslinking hydrogel was 2wt% of alginate with AG-HYD to AG-HYD ratio of 1:1. The formulation of linear crosslinking hydrogel was 2wt% AG-HYD with 8 mM of 2 kDa PEG-dialdehyde. The formulation of star crosslinking hydrogel was 2wt% of AG-HYD with 4 mM of 10 kDa 4-arm PEG-aldehyde.

Confocal microscopy
Microscopy was performed on a laser-scanning Leica SP8 confocal microscope with 25x 0.95-NA water immersion objective. Cell morphologies in 3D culture were recorded by confocal imaging and the cross-section area and circularity of cells were analyzed on Fiji ImageJ.

Statistical analysis
Statistical analyses were performed using GraphPad Prism software. Data are presented as mean ± SD if not otherwise mentioned. One-way analysis of variance with Tukey's multiple comparison was used to analyze the elastic modulus, loss tangent, and stress relaxation half-time of side-chain crosslinking hydrogels (Fig. 2C-H, Fig.S7). Multiple unpaired Welch's t-test with Holm-Šídák multiple comparison was used to compare the mechanical properties of star versus linear crosslinking (Fig. 3E, F), and cell encapsulation effects on mechanical properties comparing three different crosslinker architectures (Fig. 5A, B). Two-tailed unpaired t-test was used to compare cell circularity and cross section area of star versus side-chain crosslinking hydrogels (Fig. 5C, D). n.s. not significant, $*p < 0.05$, $**p < 0.01$, $***p < 0.001$, $***p < 0.0001$.

5. Author contributions
Y.H.L., Y.X., and O.C. conceived the ideas and designed experiments; Y.H.L conducted experiments and analyzed data; Y.H.L. and J.L. designed the synthesis schemes; Y.X. and O.C. provided supervision and oversight to the work; Y.H.L and O.C. wrote and edited the manuscript; J.L. and Y.X. reviewed the manuscript.

6. Acknowledgements
O.C. gratefully acknowledges funding support for this work from the NIH grant R01 AR081993, R37 CA214136.

7. Conflicts of interest
There are no conflicts to declare.

8. References

[1]   E. Cukierman, R. Pankov, D. R. Stevens, K. M. Yamada, *Science (1979)* **2001**, *294*, 1708.

[2]   B. Yang, K. Wei, C. Loebel, K. Zhang, Q. Feng, R. Li, S. H. D. Wong, X. Xu, C. Lau, X. Chen, et al., *Nat Commun* **2021**, *12*, DOI 10.1038/s41467-021-23120-0.

[3]   C. Loebel, R. L. Mauck, J. A. Burdick, *Nat Mater* **2019**, *18*, 883.

[4]   N. Huebsch, P. R. Arany, A. S. Mao, D. Shvartsman, O. A. Ali, S. A. Bencherif, J. Rivera-Feliciano, D. J. Mooney, *Nat Mater* **2010**, *9*, 518.

[5]   S. Khetan, M. Guvendiren, W. R. Legant, D. M. Cohen, C. S. Chen, J. A. Burdick, *Nat Mater* **2013**, *12*, 458.

[6]   C. M. Madl, B. L. Lesavage, R. E. Dewi, C. B. Dinh, R. S. Stowers, M. Khariton, K. J. Lampe, D. Nguyen, O. Chaudhuri, A. Enejder, et al., *Nat Mater* **2017**, *16*, 1233.

[7]   C. J. Walker, C. Crocini, D. Ramirez, A. R. Killaars, J. C. Grim, B. A. Aguado, K. Clark, M. A. Allen, R. D. Dowell, L. A. Leinwand, et al., *Nat Biomed Eng* **2021**, DOI 10.1038/s41551-021-00709-w.

[8]   O. Chaudhuri, S. T. Koshy, C. Branco Da Cunha, J. W. Shin, C. S. Verbeke, K. H. Allison, D. J. Mooney, *Nat Mater* **2014**, *13*, 970.

[9]   R. S. Stowers, A. Shcherbina, J. Israeli, J. J. Gruber, J. Chang, S. Nam, A. Rabiee, M. N. Teruel, M. P. Snyder, A. Kundaje, et al., *Nat Biomed Eng* **2019**, *3*, 1009.

[10]   P. Agarwal, H. pyo Lee, P. Smeriglio, F. Grandi, S. Goodman, O. Chaudhuri, N. Bhutani, *Nat Biomed Eng* **2021**, DOI 10.1038/s41551-021-00691-3.

[11]   J. Chang, A. Saraswathibhatla, Z. Song, S. Varma, C. Sanchez, N. H. K. Alyafei, D. Indana, R. Slyman, S. Srivastava, K. Liu, et al., *Nat Mater* **2023**, 2022.07.28.501930.

[12]   J. S. Silver, K. A. Günay, A. A. Cutler, T. O. Vogler, T. E. Brown, B. T. Pawlikowski, O. J. Bednarski, K. L. Bannister, C. J. Rogowski, A. G. McKay, et al., *Sci Adv* **2021**, *7*, 1.

[13]   A. R. Killaars, C. J. Walker, K. S. Anseth, *Proc Natl Acad Sci U S A* **2020**, *117*, 21258.

[14]   O. Chaudhuri, L. Gu, D. Klumpers, M. Darnell, S. A. Bencherif, J. C. Weaver, N. Huebsch, H. P. Lee, E. Lippens, G. N. Duda, et al., *Nat Mater* **2016**, *15*, 326.

[15]   O. Chaudhuri, J. Cooper-White, P. A. Janmey, D. J. Mooney, V. B. Shenoy, *Nature* **2020**, *584*, 535.

[16]   J. Lou, R. Stowers, S. Nam, Y. Xia, O. Chaudhuri, *Biomaterials* **2018**, *154*, 213.

[17]   A. N. Borelli, M. W. Young, B. E. Kirkpatrick, M. W. Jaeschke, S. Mellett, S. Porter, M. R. Blatchley, V. V. Rao, B. V. Sridhar, K. S. Anseth, *Adv Healthc Mater* **2022**, *11*, 1.

[18]   K. Adebowale, Z. Gong, J. C. Hou, K. M. Wisdom, D. Garbett, H. pyo Lee, S. Nam, T. Meyer, D. J. Odde, V. B. Shenoy, et al., *Nat Mater* **2021**, *20*, 1290.

[19]   H. P. Lee, F. Alisafaei, K. Adebawale, J. Chang, V. B. Shenoy, O. Chaudhuri, *Sci Adv* **2021**, *7*, DOI 10.1126/sciadv.abd4058.

[20]   B. M. Richardson, D. G. Wilcox, M. A. Randolph, K. S. Anseth, *Acta Biomater* **2019**, *83*, 71.

[21]   H. P. Lee, L. Gu, D. J. Mooney, M. E. Levenston, O. Chaudhuri, *Nat Mater* **2017**, *16*, 1243.

[22]   O. Chaudhuri, L. Gu, D. Klumpers, M. Darnell, S. A. Bencherif, J. C. Weaver, N. Huebsch, H. P. Lee, E. Lippens, G. N. Duda, et al., *Nat Mater* **2016**, *15*, 326.

[23]   J. G. Roth, M. S. Huang, R. S. Navarro, J. T. Akram, B. L. LeSavage, S. C. Heilshorn, *Sci Adv* **2023**, *9*, eadh8313.

[24]   H. pyo Lee, R. Stowers, O. Chaudhuri, *Nat Commun* **2019**, *10*, DOI 10.1038/s41467-019-08465-x.

[25]   D. R. Hunt, K. C. Klett, S. Mascharak, H. Wang, D. Gong, J. Lou, X. Li, P. C. Cai, R. A. Suhar, J. Y. Co, et al., *Advanced Science* **2021**, *8*, 1.

[26]   D. Indana, P. Agarwal, N. Bhutani, O. Chaudhuri, *Advanced Materials* **2021**, *2101966*, 1.

[27]   S. Nam, V. K. Gupta, H. pyo Lee, J. Y. Lee, K. M. Wisdom, S. Varma, E. M. Flaum, C. Davis, R. B. West, O. Chaudhuri, *Sci Adv* **2019**, *5*,

[28]   S. Nam, O. Chaudhuri, *Nat Phys* **2018**, *14*, 621.

[29]   K. Adu-Berchie, Y. Liu, D. K. Y. Zhang, B. R. Freedman, J. M. Brockman, K. H. Vining, B. A. Nerger, A. Garmilla, D. J. Mooney, *Nat Biomed Eng* **2023**,

[30]   T. C. Tseng, L. Tao, F. Y. Hsieh, Y. Wei, I. M. Chiu, S. H. Hsu, *Advanced Materials* **2015**, *27*, 3518.

[31]   J. Lou, F. Liu, C. D. Lindsay, O. Chaudhuri, S. C. Heilshorn, Y. Xia, *Advanced Materials* **2018**, *30*, 1.

[32]   S. M. Hull, J. Lou, C. D. Lindsay, R. S. Navarro, B. Cai, L. G. Brunel, A. D. Westerfield, Y. Xia, S. C. Heilshorn, *Sci Adv* **2023**, *9*, eade7880.

[33]   N. de P. Narciso, R. S. Navarro, A. Gilchrist, M. L. M. Trigo, G. A. Rodriguez, S. C. Heilshorn, *Adv Healthc Mater* **2023**, *2301265*, 1.

[34]   H. Ren, Z. Zhang, X. Cheng, Z. Zou, X. Chen, C. He, *Sci Adv* **2023**, *9*, eadh4327.

[35]   S. Basu, S. Pacelli, A. Paul, *Acta Biomater* **2020**, *105*, 159.

[36]   P. K. Sharma, S. Taneja, Y. Singh, *ACS Appl Mater Interfaces* **2018**, *10*, 30936.

[37]   C. Cheng, X. Zhang, Y. Meng, Z. Zhang, J. Chen, Q. Zhang, *Soft Matter* **2017**, *13*, 3003.

[38]   M. J. W. Rachel C. Ollier, Yuanhui Xiang, Adriana M. Yacovelli, *Chem Sci* **2023**

[39]   F. L. C. Morgan, J. Fernández-Pérez, L. Moroni, M. B. Baker, *Adv Healthc Mater* **2022**, *11*, 1.

[40]   B. M. Richardson, C. J. Walker, L. J. MacDougall, J. W. Hoye, M. A. Randolph, S. J. Bryant, K. S. Anseth, *Biomater Sci* **2020**, *8*, 3804.

[41]   F. A. A. Ruiter, F. L. C. Morgan, N. Roumans, A. Schumacher, G. G. Slaats, L. Moroni, V. L. S. LaPointe, M. B. Baker, *Advanced Science* **2022**, *9*, 1.

[42]   S. Sinha, M. Ayushman, X. Tong, F. Yang, *Adv Healthc Mater* **2023**, *12*, 1.

[43]   D. D. McKinnon, D. W. Domaille, J. N. Cha, K. S. Anseth, *Advanced Materials* **2014**, *26*, 865.

[44]   S. Li, D. Niu, T. Shi, W. Yun, S. Yan, G. Xu, J. Yin, *ACS Biomater Sci Eng* **2023**

[45]   S. Kim, S. Jung, *Carbohydr Polym* **2020**, *250*, 116934.

[46]   L. Qiao, C. Liu, C. Liu, L. Yang, M. Zhang, W. Liu, J. Wang, X. Jian, *J Mater Sci* **2019**, *54*, 8814.

[47]   D. Zhu, H. Wang, P. Trinh, S. C. Heilshorn, F. Yang, *Biomaterials* **2017**, *127*, 132.

[48]   H. Wang, D. Zhu, A. Paul, L. Cai, A. Enejder, F. Yang, S. C. Heilshorn, *Adv Funct Mater* **2017**, *27*, 1.

[49]   J. Lou, S. Friedowitz, K. Will, J. Qin, Y. Xia, *Advanced Materials* **2021**, *33*, 1.

[50]   J. Lou, Y. Xia, *ACS Macro Lett* **2022**, 1312.

[51]   D. D. McKinnon, D. W. Domaille, T. E. Brown, K. A. Kyburz, E. Kiyotake, J. N. Cha, K. S. Anseth, *Soft Matter* **2014**, *10*, 9230.

[52]   G. A. Parada, X. Zhao, *Soft Matter* **2018**, *14*, 5186.

[53]   D. C. Schoenmakers, A. E. Rowan, P. H. J. Kouwer, *Nat Commun* **2018**, *9*, 1.

[54]   J. L. Buss, P. Ponka, *Biochim Biophys Acta Gen Subj* **2003**, *1619*, 177.

[55]   P. Kovaříková, Z. Mrkvičková, J. Klimeš, *J Pharm Biomed Anal* **2008**, *47*, 360.

9. Main figures and table

Figure 1. DCC alginate hydrazone hydrogels with side-chain, linear, and star crosslinker architectures were investigated in this work. A) DCC hydrogel can be formed from side-chain crosslinking or telechelic crosslinking with linear or star crosslinker architectures. B) Time evolution of storage and loss modulus of side-chain (left), linear (center), and star (right) crosslinking hydrogels. C) Alginate was functionalized with either hydrazine or aldehyde groups. D) Selection of commercially available linear and star PEG-aldehyde crosslinker studied in this work. E) Representative image of star crosslinked DCC hydrazone hydrogels placed in 6 mm cell culture dish, colored with food dyes.

Crosslinking architecture	Materials (MW, kDa)	Total polymer (wt%)	Elastic modulus (kPa)	Stress relaxation $\tau_{1/2}$ (sec)	Literature
Side-chain	ELP-HYD-RGD (37) HA-ALD or BLD (100)	2	2.2 ~ 2.5	1,529 ~ 8,701	Roth, J. & Huang M. 2023
Side-chain	HA-hydrazide (85) HA-aldehyde (96)	3	4.6	700	A. N. Borelli, Adv. Healthc. Mater. 2022
Side-chain	HA-HYD (39/75) HA-ALD (39/75)	2	0.7 ~ 5.1	1,217 ~ 3,558	J. Lou, Adv. Mater. 2021
Side-chain	ELP-HYD-RGD (37) HA-ALD or BLD (100)	2	1.1 ~ 2.64	1,507 ~ 64,800	D. R. Hunt, Adv. Sci. 2021
Side-chain	HA-HYD (20/120); COL HA-ALD or BLD (20/120)	1 ~ 2.25	0.01 ~ 0.5	*233~18,000	J. Lou, Biomaterials, 2018
Linear	PLGA-HYD (150) PEG-2ALD (4)	5 ~ 11	1.5 ~ 6.4	-	S. Li, ACS Biomater. Sci. Eng. 2023
Linear	Adipic dihydrazide Oxidized alginate (114)	2	0.7	302	F. L. C. Morgan, Adv. Healthc. Mater. 2022
Linear	Adipic dihydrazide Oxidized alginate (69.6)	2	0.1	4,100	F. A. A. Ruiter, Adv. Sci. 2022
Linear	Alginate-HYD (420) PEG-2BLD (2)	3 ~ 10	30 ~ 300	-	L. Qiao, J. Mater. Sci. 2019
Star	8-arm PEG-HYD (20) Oxidized Xanthan	3 ~ 5	0.2 ~ 0.8	-	P. K. Sharma, ACS Appl. Mater. Interfaces 2018
Star-star	8-arm PEG-HYD (10); COL 8-arm PEG-ALD or BLD (10)	2.75	0.4	*187 ~ 21,000	S. Sinha, Adv. Healthc. Mater. 2023
Star-star	8-arm PEG-HYD (10) 8-arm PEG-ALD or BLD (10)	3	15.2	4,262~ 9,789	B. M. Richardson, Adv. Healthc. Mater. 2021
Star-star	8-arm PEG-HYD (20) 8-arm PEG-ALD (20)	5 ~ 10	1.6	-	P. K. Sharma, Biomacromolecules 2019
Star-star	8-arm PEG-HYD (20) 8-arm PEG-ALD or BLD (20)	5	58	1,980 ~ 14,904	B. M. Richardson, Acta Biomater. 2019
Star-star	8-arm PEG-HYD (10) 8-arm PEG-ALD (10)	120	31.9	85	D. D. McKinnon, Soft Matter 2014
Star-star	8-arm PEG-HYD (10) 4-arm PEG-HYD (20) 4-arm PEG-ALD (10) 4-arm PEG-ALD (10)	36	1.7 ~ 26.1	19 ~ 47	D. D. McKinnon, Adv. Mater. 2014

Table 1. Stiffness and stress relaxation measured in previous studies using hydrazone-crosslinked hydrogels of various crosslinker architectures.

Figure 2. Rheological characterizations of hydrogels with side-chain crosslinking. A-B) Representative of frequency sweep (average of n = 4) and stress relaxation (average of n = 3) tests using formulation of 2 wt% alginate at AG-HYD to AG-ALD ratio of 1:1. C-E) The elastic modulus, loss tangent, and stress relaxation half-time of hydrogels varying alginate concentration under same AG-HYD to AG-ALD ratio of 1:1. F-G) The elastic modulus, loss tangent, and stress relaxation half-time of hydrogels varying AG-HYD to AG-ALD ratio under same alginate concentration of 2 wt%.

Figure 3. Rheological characterizations of hydrogels with telechelic crosslinking, using crosslinkers with either linear or star architectures. A-B) The elastic modulus and stress relaxation half-time of hydrogels with linear crosslinkers and varying concentrations of PEG-dialdehyde crosslinkers of different molecular weight. C-D) The elastic modulus and stress relaxation half-time of hydrogels with star crosslinkers and varying concentrations of 4-arm PEG-dialdehyde crosslinker of different molecular weight. E-F) Elastic modulus and stress relaxation half-time of linear versus star crosslinking hydrogels. Multiple unpaired Welch's t-test with Holm-Šídák multiple comparison. G) Telechelic crosslinking alginate-hydrazone hydrogels present correlation of stress relaxation half-time and elastic modulus. Pearson r coefficient and P value: linear 1 kDa

(0.69, *), 2 kDa (0.62, *), and 10 kDa (0.59, *); star 2 kDa (0.92, ****), 10 kDa (0.76, **), and 20 kDa (0.82, **)

Figure 4. DCC hydrogel stiffness and viscoelasticity are crosslinker architecture dependent. A) The elastic modulus, stress relaxation half-time, and loss tangent of side-chain, linear, and star crosslinking hydrazone hydrogels collected in this work. B) The stress relaxation half-time and loss tangent of side-chain, linear, and star crosslinking hydrazone hydrogels collected in this work. C) Combined data from previous works and this work demonstrate side-chain, linear, and star crosslinking hydrazone hydrogels present distinct range of stiffness and stress relaxation half-time with minimal overlaps. Side-chain (circle), linear (square), and star (triangle).

Figure 5. 3D cell culture and impact of cell encapsulation on hydrogel mechanical properties. A-B) The impact of encapsulating 10 million cells per milliliter in side-chain, linear, and star crosslinking gels on stiffness and stress relaxation half-time. Multiple unpaired Welch's t-test with Holm-Šídák multiple comparison. C-D) The cross-section area and circularity of MDA-MB-231 cells encapsulated in side-chain and star crosslinking hydrogels of similar stiffness (17.8 vs 18.7 kPa) but varied stress relaxation time (4,492 vs 1,139 sec). n=148 for side-chain and n=62 for star crosslinking. Two-tailed unpaired t-test. E) representative images of cell morphology in side-chain and star crosslinking hydrogels, stained with Calcein-AM dye in green. Scale bar = 100 μm.