A clinically defined and xeno-free hydrogel system for regenerative medicine.

John Ong [1,2,3], George Gibbons [4], Lim Yee Siang [5], Zhou Lei [3], Junzhe Zhao [1],

Alexander W. Justin [1], Federico Cammarata [1], Ravisankar Rajarethinam [6], Colleen

Limegrover [4], Sanjay Sinha [7][*], Andras Lakatos [4][*], Foad J. Rouhani [8][*], Dan Yock

Young [3][*], Athina E. Markaki [1][*]

denotes senior authorship.

[1] Department of Engineering, University of Cambridge, UK

[2] School of Clinical Medicine, University of Cambridge, UK

[3] Department of Medicine, National University of Singapore, Singapore

[4] John van Geest Centre for Brain Repair, University of Cambridge, UK

[5] Genomic Institute of Singapore, Singapore

[6] Institute of Molecular and Cell Biology, Singapore

[7] Cambridge Stem Cell Institute, University of Cambridge, UK

[8] Wellcome Sanger Institute, Wellcome Genome Campus, Cambridge, UK

Correspondence:

Professor Athina E. Markaki

Department of Engineering, University of Cambridge

Trumpington Street

Cambridge CB2 1PZ, United Kingdom

Tel: +44-1223 766417, Email: am253@cam.ac.uk

Dr John Ong

Clinical Lecturer in Hepatology

School of Clinical Medicine, University of Cambridge

Addenbrooke's Hospital, Hills Road

Cambridge CB2 0SP, United Kingdom

Tel: +44-1223 336700, Email: jo401@cam.ac.uk

ABSTRACT (174/200 words)

Biofabricated scaffolds facilitate bona fide cellular interactions, cell type specification,

and the formation of three-dimensional tissue architecture from human pluripotent

stem cells (hPSCs). However, poorly defined and non-clinically approved synthetic

biomaterials greatly hinder the translation of lab-grown therapies into clinical practice.

Here, we describe a protein screen-based hydrogel system biofabricated from widely

available clinical-grade human components. We show that "Alphagel", a base hydrogel

comprising human embryonic matrices, supports the trilineage differentiation of

hPSCs into neural, cardiac, and liver tissue. Alphagel is also biocompatible and

biodegradable *in vivo*. Further, by adding select proteins found in the maturing human

foetal liver, the resulting hydrogel (termed "Hepatogel") enhances the differentiation of

hPSC-derived hepatocytes (H-iHeps) compared to Matrigel, a xenogenic and

commonly used hydrogel that is prohibited in clinical use. Importantly, when injected

into mice livers, Hepatogel significantly improves the engraftment rates of H-iHeps

compared to standard cell injections. Altogether, our results provide proof of concept

that this customisable hydrogel system is a useful tool for developing organ-specific

and clinically translatable therapies for regenerative medicine and tissue engineering.

Keywords: hydrogel, liver, stem cells, regenerative medicine, tissue engineering

INTRODUCTION

51   Three-dimensional (3D) stem cell and organoid platforms recapitulate *in vivo* cellular

52   and biomechanical interactions better than two-dimensional culture systems, enabling

53   the development of novel diagnostics and therapeutics for disease (1,2). The spatial

54   arrangement of stem cells and niche factors orchestrated by biofabricated scaffolds

55   promote the self-organisation of cell masses and the formation of early organoids for

tissue development. This geometry controls organoid patterning (3) and remains an important factor that underpins our capability to engineer whole organs in vitro. Human pluripotent stem cells (hPSC), which comprise induced pluripotent stem cells (iPSCs) and embryonic stem cells (ESCs), have the potential to generate any cell type in the human body. However, hPSC and organoid culture are heavily reliant on xenogenic matrices that often cause significant immune-related reactions when transplanted, contributing to the failure of many tissue-engineered therapies at clinical trials (4).

Presently, Matrigel and Matrigel-derived matrices are often used to culture hPSCs and organoids derived from bi- or multi-potent adult stem cells (5,6). This is problematic because of widely recognised problems with the mouse sarcoma-derived matrix. Poor definability (7,8), batch-to-batch variability in growth factor concentrations (9,10), composition (11) and physical properties (10), immunogenicity (12), and pathogen transmission (13) are widely recognised issues that prevent clinical translation (14). Alternatively, synthetic biomaterials such as polyethene glycol (PEG), polyacrylic acid (PAA), polycaprolactone (PCL), or polyacrylamide (PAAm) have been explored (15). However, PEG-based biomaterials can have rapid reaction kinetics, resulting in inhomogeneous hydrogels (16). PAA hydrogels are mechanically weak, which limits their use as scaffolds in tissue engineering (17). PCL hydrogels exhibit poor cell adhesion and involve toxic reagents during synthesis (18). PAAm hydrogels require complex chemical or photo-crosslinking (19), precluding gelation and retention at target sites for convenient and effective cell delivery (7,20). Importantly, synthetic biomaterials frequently lack the physiological niche factors which, while avoiding unwanted matrix interactions, also lack the biochemical cues for efficient hPSC culture and differentiation (15,21).

Recently, attempts have been made to deconstruct components of Matrigel and conjugate these with various polymeric backbones (22,23). However, these are unsuitable for hPSC culture because some components adversely affect stem cell pluripotency by causing predilection or spontaneous differentiation towards particular lineages (24–26). For example, Laminin 111, a major component of Matrigel, promotes epithelial-to-mesenchymal transition in human ESCs by the α3β1-integrin/extracellular matrix metalloproteinase inducer complex (25).

To address these issues, we biofabricated a xenofree and clinically compatible system mimicking the stages of embryonic development and organogenesis. We hypothesised that hPSC-derived target cells would resemble primary cells closer when cultured in customised hydrogels with organ-specific matrices instead of generic biomaterials like Matrigel or synthetic hydrogels. In that vein, we aimed to biofabricate a liver extracellular matrix (ECM)-specific hydrogel as a proof-of-concept. Through a reductionist approach, we performed a focused protein screen and created a base hydrogel (termed "Alphagel") that supported hPSC culture and trilineage differentiation in 3D. We then added select proteins found in maturing liver ECM to Alphagel. The resulting hydrogel, termed "Hepatogel", produced hPSC-derived hepatocytes that were closer to maturing human hepatocytes than Matrigel, and it improved the engraftment of hPSC-derived hepatocytes when injected into the livers of immunocompromised mice. A summary of the workflow is illustrated in Fig.1(A). Herein, we contribute evidence that organ-specific hydrogels produce better end-target cells than generic hydrogels, and this system is a useful tool for developing organ-specific and effective therapies for regenerative medicine.

RESULTS

Focused screening revealed Laminin 521 and Fibrinogen as common components of the embryological and hepatic niche that contribute to hPSC pluripotency.

We previously (27) exposed iPSCs maintained on vitronectin in a defined feeder-free system to a library of proteins identified within the adult human liver by the Human Matrisome Project (http://matrisomeproject.mit.edu; Massachusetts Institute of Technology, USA). In doing so, we were able to long-list hepatic matrix proteins that enhance the *in vitro* differentiation of iPSCs to adult hepatocytes when exposed to hepatic differentiation factors(27). However, to biofabricate a hydrogel that can support PSC expansion seen in embryogenesis and liver organogenesis, we first investigated whether any of the long-listed proteins could also maintain PSC pluripotency in the absence of routine hepatic differentiation factors. Successful hits could then be used as components to biofabricate a hydrogel that is primed for liver tissue engineering when hepatic differentiation conditions are introduced. To that end, we optimised an

automated high throughput imaging pipeline to identify PSCs by nuclear area and nuclear markers of stem cell pluripotency (NANOG, SOX2, and OCT4). Cell morphology and the mean fluorescent intensities (MFI) of pluripotency markers were used to define normal hPSC characteristics for positive selection; Supplementary Figure 1. Human fibroblasts were used for threshold setting (negative control).

Using machine learning, the pipeline successfully identified pluripotent hPSCs as single cells growing in 2D colonies with a sensitivity of 89.5% and a positive likelihood ratio of 160.8, e.g. Fig.1(B). Single-cell analyses were performed to exclude culture artefacts and cell clumps which reduce the accuracy of automated image analysis. The pipeline also identified non-pluripotent cell populations with a specificity of 99.4% and a negative likelihood ratio of 0.1), e.g. Fig.1(C). The final readout of the pipeline was the Stemness Index (SI), a ratio of the number of pluripotent cells to the total number of cells identified by DAPI. The SI ranged from 0, denoting the poorest performing matrix at maintaining hPSC pluripotency, to 1, denoting pluripotency was maintained in all hPSCs cultured in a matrix. Importantly, it reliably discriminated between undifferentiated hPSCs and differentiated hPSCs within the same cell population; Fig.1(D). When tested, this platform demonstrated excellent discriminatory performance (Area Under the Curve (AUC) of 0.977); Fig.1(E).

Using this platform, we screened twenty-two proteins over a thousand conditions and found select proteins in both the embryological and fetal liver niches that affect hPSC pluripotency. An example of a short-term (1-week) focused screening panel is illustrated in Supplementary Figure 2. In summary, the best candidate was chosen for its ability to maintain the highest SI in hPSCs after prolonged culture; Laminin 521 had the highest SI (between 0.95 to 1.0) after 3-4 months in culture. Thus, we sought to combine Laminin 521 with a polymeric backbone to obtain a 3D scaffold since a pure or physiologically relevant Laminin 521 hydrogel is not currently available. We found human fibrinogen was the most suitable polymeric protein for pairing with Laminin 521 because of its mechanical tunability, and at low concentrations, it did not cause rapid spontaneous differentiation of hPSCs (SI: 0.77 to 0.84). Notably, other polymeric backbones, such as albumin and collagen, that we investigated either resulted in poor hPSC attachment (27) or triggered significant spontaneous differentiation of hPSCs (SI < 0.5); examples are shown in Supplementary Figure 3. In summary, in our focused

screen, Laminin 521 and fibrinogen showed high SIs, supporting stem cell pluripotency and 2D expansion in vitro. Thus, we biofabricated a hydrogel using these two candidates as base components.

Fibrinogen and Laminin concentrations inversely affected hPSC growth in 3D.
To determine the optimum conditions for culturing hPSCs in 3D, we evaluated different compositions of Laminin 521-enriched fibrin hydrogels (FLGs) versus fibrin hydrogels (FGs) as controls. We found that both categories of hydrogels displayed distinctive characteristics. In 2D cell culture, cell attachment and expansion were significantly better in FLGs (70-100% confluence) versus FGs (10%-20% confluence) after 4-5 days in culture, Fig.2(A). This was reflected in the average fold increase in cell populations at 7 days (38.5 ± 5.6 vs 1.0 ± 0.2, p < 0.0001), respectively. In 3D cell culture, higher fibrinogen and lower laminin concentrations resulted in poor colony expansion and "dark" unhealthy hPSC colonies, Fig.2(B); widely recognised features of spontaneous differentiation in hPSC culture (28–30). This was corroborated across several conditions by a significant decrease in SOX2, NANOG, OCT4 MFIs, and SIs compared to hPSCs grown on 2D Matrigel as standard practice (Supplementary Figure 4). Nonetheless, the optimal balance between fibrinogen, thrombin and laminin concentrations was identified by a combination of SI in hPSCs and the stability of FLGs in cell culture; hydrogels with low fibrin concentrations (≤ 1mg/ml) disintegrated after a week in cell culture. This optimum ratio (50%:50% v/v Laminin 521 and 2.5mg/ml fibrin hydrogel) was termed "Alphagel". Alphagel was found to be up to a third more cost-effective than Matrigel for 3D hPSC cell culture (Supplementary Figure 5). Unlike other compositions of FLGs, Alphagel supported the healthy expansion of hPSCs into 3D cell aggregates closely resembling embryoid bodies (EBs), Fig.2(B).

To visualise the differences between fibrin-only hydrogels and Alphagel, scanning electron microscopy (SEM) was performed on acellular hydrogels. This demonstrated smaller pores and thinner fibrin fibres as previously observed in laminin-fibrin hydrogels (31,32). Thin membranes in between inter-connecting fibrin fibres in Alphagel were observed and these were absent in fibrin-only hydrogels; Fig.2(C) and Fig.2(D). As protein concentration alters the elastic properties of hydrogels, we next measured Young's modulus of fibrin-only hydrogels, FLGs, and Alphagel. We found that hydrogel stiffness increased significantly with laminin and fibrin concentrations;

Fig.2(E). The Young's modulus in FLGs containing 1.5 mg/ml fibrin was higher compared to 1.5 mg/ml fibrin-only hydrogels (fold increase 3.6 ± 0.6, $p < 0.0001$) and 2.5 mg/ml fibrin-only hydrogels (fold increase 2.6 ± 0.2, $p < 0.0001$). Despite the increase in stiffness, cell viability was notably higher in Alphagel compared to fibrin-only hydrogels (98.7 ± 0.3% vs 80.8% ± 8.3% respectively, $p < 0.05$; Fig.2(F). There were no significant differences in cell viability across Alphagel and the 2D substrates.

Next, to determine if the FLG hydrogels were stable, we measured the amount of Laminin 521 leached from acellular Alphagel into the culture media over time. This showed that the greatest loss of Laminin 521 from the hydrogel occurred during the first 24 hr of conjugation (approximately 3% leached into media). Thereafter, the leaching of Laminin 521 into the culture media was negligible, and approximately 97% of the laminin remained within the hydrogel after 9 days; Fig.2(G) and Fig.2(H). Then, to optimise 3D culture conditions, we tested the performance of hPSC-laden Alphagel paired with different stem cell maintenance media over 2 months. Stem cell culture media E8™, TeSR-E8™, mTeSR™ 1, mTeSR™ Plus, and TeSR™ 2 were used. We found the best stem cell culture media that maintained markers of hPSC pluripotency with Alphagel were the TeSR-only family i.e. TeSR™ 2, mTeSR™ 1 and mTeSR™ Plus, yielding SIs of hPSCs between 0.95 to 1.0; Supplementary Figure 4. Despite prolonged culture, pluripotency markers (OCT4, NANOG, and SOX2) were still strongly expressed in the 3D hPSCs aggregates. For validation, these aggregates were dissociated into smaller cell clusters and grown as a single cell layer in 2D. Importantly, these hPSCs continued to proliferate in 2D and continued to express all 3 pluripotent nuclear markers (Supplementary Figure 6). In summary, Alphagel was found to be a stable hydrogel that supports the formation and expansion of embryoid-like bodies in prolonged 3D hPSC culture, displaying different biological and physical characteristics compared to fibrin-only hydrogels.

Alphagel supported the tri-lineage differentiation of hPSC bodies into cardiac, neural, and hepatic tissue in 3D.

To rigorously demonstrate that hPSCs cultured in Alphagel remained pluripotent, we cultured hPSCs bodies in Alphagel then performed directed 3D differentiation of

hPSCs into all three germ cell lines: mesoderm (cardiac), ectoderm (neurons), and endoderm (hepatic).

During cardiac specification, hPSC bodies in Alphagel successfully proliferated and formed 3D contractile cardiac tissue after initiating cardiac differentiation; Fig.3(A) and Supplementary Movie 1. Immunofluorescent staining (IF) of cells for the cardiac marker Troponin T (TnT) and the general myoblast marker α-SMA (33) was strongly positive; Fig.3(B). Cardiomyocytes were observed to start beating at a rate of 30 to 50 beats/min between Day 5 to Day 8 of the cardiac differentiation process; early contractions were weak and asynchronous (Supplementary Movie 1). However, the contractility rate increased to 60 − 80 beats/min, and contractions were noticeably stronger and synchronous by Day 12 − 14 (Supplementary Movie 2). There was no significant difference in differentiation efficiency (proportion of TnT positive cells) between Alphagel and Matrigel (75.4 ± 18.5% vs 78.2 ± 15.4% respectively, $p = 0.14$). In fibrin-only hydrogels, the differentiation efficiency was significantly lower versus Alphagel (34.9 ± 21.3%; $p < 0.001$; Supplementary Figure 7(A).

For neural specification, hPSCs were subjected to a commonly applied protocol utilising dual-SMAD inhibition (34,35). For comparison, both a fibrin-only control and an aggregate-based (neurosphere) method were included. Neurospheres are derived from hPSCs cultured with Matrigel, and then differentiated in suspension culture. At Day 16, all conditions showed successful acquisition of a neural fate as demonstrated by co-expression of the neuroepithelial progenitor markers SOX2, nestin, and β-catenin (36); Fig.3(C). Quantifications at this time point showed comparable cell composition of SOX2 immunoreactive (IR) progenitor cells in Alphagel (79.5 ± 5.0%) and neurospheres (82.4 ± 9.3%) conditions. In the fibrin-only condition, there were slightly fewer SOX2 IR cells (74.1 ± 12.6%); however, this difference was not statistically significant; Supplementary Figure 7(B). To ascertain if the structural properties of Alphagel could improve the organization and morphology of differentiated neuroepithelia, we determined the number and size of lumens demarcated by nestin/β-catenin co-labelled apical cells and compared to that seen in fibrin-based hydrogels and neurospheres. We found that the frequency of polarized areas (approximately $0.03/mm^2$) was consistent across all conditions, albeit less variable under hydrogel conditions; Fig.3(D). However, the average lumen area was

significantly increased in hydrogel conditions with Alphagel (403.29 μm^2; p = 0.0007)

versus neurospheres (105.46 μm^2); Fig.3(D). Large lumen areas are observed when

neural progenitors coalesce and mature (37,38), forming the structural architecture of

the neural progenitor niche. The correct organisation of polarised tissue is crucial to

neurodevelopment, and aberrant formation is involved in neural tube defects.

Nonetheless, no differences were observed in the frequency of polarised puncta in

Alphagel versus neurospheres; Fig.3(E). Cumulatively, these results show that

Alphagel supports efficient ectodermal differentiation of hPSCs into neuroepithelia.

For hepatic specification, successful differentiation of hPSCs into hepatocytes (iHeps)

was demonstrated through IF staining, showing previously established gene

expression signatures (39), and functional assays. Positive IF staining for hepatocyte

markers Albumin, HNF1A, HNF4A, CYP2A6, CD147, and E-cadherin was

demonstrated in 3D differentiated cells, Fig.4(A). Similarly, key hepatocyte genetic

markers HNF4A, CEBPA and CYP3A4 were shown to be expressed in iHeps derived

in Alphagel and at similar levels as iHeps derived in Matrigel; Fig.4(B). However,

CYP3A7 and AFP expression were significantly higher in Alphagel and Matrigel

compared to adult primary human hepatocytes (PHH); p < 0.0001 for both, Fig.4(B).

Notably, TBX3 expression was also high in Alphagel and Matrigel but there was no

statistically significant difference compared to PHH. For further characterisation, 18

other hepatocyte-related genes were analysed (Supplementary Figure 8). 10 of 18

genes showed differences between PHH and Alphagel-derived hepatocytes.

Specifically in the latter, BAAT, ABCC2, and TAT were down-regulated, whilst

CYP3A5, GATA4, GATA6, FOXA1, SOX9, LGR5, and CK19 were up-regulated

compared to PHH (p values in Supplementary Figure 8). BAAT and TAT code for liver

enzymes and ABCC2 is a cell-membrane transporter. CYP3A5 codes for a hepatic

enzyme that increases as the foetal liver matures. GATA4, GATA6, FOXA1 are

important transcription factors involved in hepatic differentiation. LG5R and SOX9 are

markers for hepatic progenitors (hepatoblasts) that give rise to the two main cell types

within the liver (hepatocytes and cholangiocytes). CK19 is a biliary marker.

To assess the functionality of iHeps derived in Alphagel, albumin secretion,

cytochrome 3A4 activity, LDL update, as well as CDFDA uptake and excretion were

investigated at the end of the hepatic differentiation process. Albumin, a key marker

of hepatocyte synthetic function (40), was found to be secreted in similar amounts by PHH and iHeps cultured in Alphagel and Matrigel; Fig.4(C). However, CYP3A4 activity was lower in Alphagel and Matrigel than PHH, as reported by other groups (39,41); Fig.4(D). Importantly, low-density lipoprotein (LDL) uptake and 5-(and-6)-Carboxy-2',7'-Dichlorofluorescein Diacetate (CDFDA) secretion, both features of hepatocyte metabolic function, were demonstrated in Alphagel; Fig.4(E) and Fig.4(F). These were also present in primary hepatocytes and hepatocytes derived in Matrigel. There was no statistically significant difference in differentiation efficiency between Alphagel and Matrigel (defined herein by the proportion of albumin-positive cells). This was approximately 70.6% and 69.9%, respectively (p=0.73). In fibrin-only hydrogels, the differentiation efficiency was significantly lower versus Alphagel (28.8%, p<0.0001); Supplementary Figure 7(C).

In summary, the results above show that Alphagel maintains hPSCs pluripotency and supports their trilineage differentiation in 3D. Using established and chemically defined differentiation protocols, cardiac, neural, and hepatic tissue were derived in 3D and positively characterised.

Alphagel demonstrated good biocompatibility and biodegradability *in vivo*

To explore if Alphagel could be used as a biomaterial for clinical therapy, we next sought to determine its biocompatibility *in vivo*. To that end, we injected immune-competent Black 6 (C57BL/6) mice subcutaneously with Alphagel (test group), 0.9% saline (negative control), and 1.0% v/v croton oil (inflammatory agent, positive control) to assess for an immune response; n=3 for each group and time point. Mice were then observed and culled over 6 weeks. Histological slides were evaluated by a veterinary histopathologist who was blinded to the groups. Each slide was scored objectively using an international scoring tool (Supplementary Figure 9) and graded using standardised nomenclature (42–44).

Cumulatively, the results showed that mice injected with Alphagel had mild inflammation at the site of injection between 1 to 2 weeks; Fig.5(A). However, this resolved completely between 4 to 6 weeks; Fig.5(B). Mice injected with 0.9% saline also had inflammation at the injection site after 1 week although this was minimal and had resolved completely by 2 weeks. Mice injected with 1% croton oil developed

ongoing severe inflammation, which progressed to wound dehiscence by 6 weeks;

these mice were culled humanely when wound inflammation became visibly severe.

The histological scores were consistent with the qualitative reporting of the histological

slides, Fig.5(C).

Neoplasia was not observed at the injection sites in all groups, and Alphagel was not

visible at the injection sites between 4 to 6 weeks. In summary, the data derived from

immunocompetent Black 6 mice provide evidence that fibrin-laminin hydrogels are

biocompatible and biodegradable *in vivo*.

Alphagel enriched with liver-specific ECM (Hepatogel) enhanced the phenotype

of human iHeps

To test our hypothesis that hydrogels enriched with organ-relevant ECM can improve

stem cell-derived phenotypes, we added Laminin 411 and Laminin 111 to Alphagel.

These were specific ECMs that we found to be important in liver development (27).

Various combinations of protein concentrations were tested, and the optimum

concentration of Laminins 521, 411 and 111 was termed "Hepatogel". iHeps derived

in Hepatogel, Alphagel and Matrigel were compared against PHH using the same

panel of liver-specific genes and functional assays. Key changes in the gene

expression profile are highlighted in Fig.6(A). Briefly, Hepatogel increased the gene

expression for the hepatic glycoprotein Transferrin (TF) versus Alphagel (1.5 ± 0.4 fold

increase, $p < 0.0001$) and PHH (2.2 ± 0.6 fold increase, $p < 0.001$). The gene

expression for the liver enzyme Gamma Glutamyl-Transferase (GGT) was also

significantly increased across all three hydrogels compared to PHH but it was highest

in Hepatogel (3.3 ± 0.3 fold increase vs PHH, $p < 0.05$). Notably, gene expression for

liver enzyme Glucose-6 Phosphatase (G6PC) was significantly lower in Matrigel

versus PHH (-6.7 ± 0.6 fold lower, $p < 0.05$), however, expression in Hepatogel was

comparable to PHH. Bipotent-hepatoblast marker LGR5 was significantly upregulated

in Alphagel (6.0 ± 0.6 fold increase; $p<0.01$) and Hepatogel (6.5 ± 0.5 fold increase; p

< 0.01) versus PHH. Importantly, expression of immature fetal liver markers CYP3A7

and AFP were significantly lower in Hepatogel versus Matrigel (1.8 ± 0.4 fold decrease;

$p < 0.05$ and 1.3 ± 0.1 fold decrease; $p < 0.05$, respectively). The remaining results of

the hepatocyte gene panel are attached in Supplementary Figure 10.

The synthetic function of hepatocytes was assessed by albumin secretion. Hepatogel induced the highest albumin secretion compared to Alphagel, PHH, and Matrigel; Fig.6(B). The metabolic function of hepatocytes was assessed by CYP3A4 activity and Apolipoprotein B (APOB) secretion. CYP3A4 activity was highest in PHH. iHeps derived in Hepatogel had higher CYP3A4 activity than Alphagel (2.4 ± 0.1 fold increase; $p < 0.05$) and Matrigel. However in the latter, the increase was marginal and not statistically significant (1.2 ± 0.5; $p = 0.47$), Fig.6(C). APOB secretion was higher in Hepatogel compared to PHH however there were no differences between Hepatogel and Alphagel (Supplementary Figure 11). In summary, the two liver-relevant ECM added to Alphagel resulted in higher TF expression, CYP3A4 activity, and Albumin secretion compared to Alphagel alone. Interestingly, up-titrating Laminin 411 concentrations in Hepatogel significantly increased APOB secretion. Conversely, this promoted the formation of branching 3D tubular structures with a corresponding rise in Alkaline Phosphatase (ALP) in the culture media (Supplementary Figure 11). Interestingly, these structures were lined with cells which expressed biliary markers CK7, CK19, and SOX9 (Supplementary Figure 12, Supplementary Movie 3 and Supplementary Movie 4). In summary, we have shown that a hydrogel biofabricated from hepatic niche proteins (Hepatogel), enhanced several important markers of hepatocyte maturity in hPSC-derived hepatocytes compared to genetic hydrogels (Alphagel and Matrigel), producing hepatic tissue in 3D.

Hepatogel improved the engraftment of transplanted hepatocytes compared to standard therapy.

Since iHeps cultured in Hepatogel (H-iHeps) had a better synthetic (protein synthesis) and metabolic profile than Alphagel, we next investigated if by introducing a proliferative/regenerative liver niche at the site of transplantation, the engraftment of transplanted hepatocytes could be improved. Currently, hepatocyte engraftment rates in cell therapy are poor, and Matrigel and its derivatives, are not permitted in clinical use (14). To that end, we injected equal quantities of H-iHeps in Hepatogel and H-iHeps in aqueous solution (standard practice) directly into normal livers of immune-compromised mice (NSG[TM] mice, n=6 each group per time point, 3 time points). NSG[TM] mice were used to minimize acute cellular rejection from xeno-transplantation. Mice were monitored for human albumin in their serum and then culled for liver histology. Three days after intrahepatic injections, the first group of mice were culled

and examined. On post-mortem, It was evident that H-iHeps transplanted in Hepatogel were still present at the injection site, visible as pale-coloured cell masses within the liver. These were more distinct compared to H-iHeps delivered in aqueous solution (0.9% Saline); Fig.6(D).

Respectively, these macroscopic appearances corresponded to immunofluorescence staining of engrafted cells that were strongly positive for human albumin at the injection sites (cell masses) and not in other regions of the livers; Fig.6(E). Likewise, the number of H-iHeps was significantly higher in liver histology; Fig.6(F). Significantly higher concentrations of human albumin in mice serum were also observed over time and corroborated the histological findings; Fig.6(G). Notably, human albumin remained detectable in mice transplanted with H-iHeps and Hepatogel at Day 6, whereas in mice transplanted with H-iHeps in solution, it was undetectable after the second day, suggesting poor engraftment rates. Nonetheless, beyond 8 days human albumin decreased significantly and was undetectable in both groups. The remaining mice in both groups were culled at 7 days and 2 months after transplantation; no H-iHeps colonies or tumours were seen at the injection sites, demonstrating the clearance of injected H-iHeps by residual innate immunity. In summary, Hepatogel improved the engraftment of H-iHeps compared to standard therapy when injected directly into the liver, however sustained H-iHep proliferation was not observed.

DISCUSSION

In this work, we found that a select group of physiologically relevant proteins could be used as biomaterials for 3D hPSC culture. Importantly, we observed that organ-specific hydrogels can produce better end-target phenotypes compared to Matrigel and its derivatives; a generic mouse sarcoma-derived substrate. This was evidenced by significantly higher albumin expression paired with lower fetal liver markers CYP3A7 and AFP in hepatocytes derived from Hepatogel compared to Matrigel. ECM properties vary from organ to organ, in health and disease. Although 2D stem cell culture and organoid technology were established using Matrigel as a central substrate, compositional and mechanical differences to physiological ECM likely contribute to immature phenotypes compared to adult primary cells (45). Importantly, Matrigel derivatives are not approved for clinical use and thus Alphagel is an alternative for 3D hPSC culture and differentiation where hPSCs can be used to derive

all cell types in an organ for tissue engineering. In that vein, alternative substrates for

hPSC culture, Laminin 521 and vitronectin, are not readily available as pure 3D

hydrogels. Laminin 521 has recently been conjugated with silk (Biosilk, Biolamina) to

form a generic hydrogel for 3D stem cell and organoid culture (46). However, silk is

not native to the human ECM and Biosilk is not licensed for clinical use. Notably, some

hPSC differentiation protocols using vitronectin require the dissociation of cells mid-

process as well as a change in the substrate (47); this disrupts any early 3D structures

that may form in vitro.

We found that the combination of high Laminin 521 concentrations with low fibrinogen

concentrations was a good pairing to create a novel hydrogel for 3D hPSC culture.

Physiologically, Laminin 521 and 511 are present in the inner cell mass of the

blastocyst and its basement membranes during embryological development (48,49).

Its expression remains constant throughout inner cell mass expansion and during

differentiation, whereas Laminin 511 expression decreases during differentiation (49).

Importantly, through RNAreq of human adult and foetal liver tissue (27), we had

established that Laminin 521 is differentially expressed in the maturing fetal liver, along

with a small group of ECM proteins that also support stem cell pluripotency to some

extent. Notably, Fibrinogen is produced by trophoblasts during early development

(50,51), and has the potential for use as an injectable biomaterial being abundantly

present in human serum. Cell and protein adhesion is supported by arginine-glycine-

aspartate (RGD) binding motifs at positions 96 and 572-574 on the α chains, heparin-

binding domains (HBDs) also on the α chains, and a carboxy-terminal peptide

(HHLGGAKQAGDV) at position 400-11 on the γ chains (52,53). Likewise, multiple

binding sites on the α chains (RGD and HBD) and β chains (mainly RGD) in laminins

facilitate cell and protein adhesion (54,55). Importantly, human fibrin is widely used in

clinical practice (56), and clinical-grade laminins are commercially available

(Biolamina), making the clinical translation of fibrin-laminin hydrogels easily feasible.

Nonetheless, there are conflicting data on the effects of fibrin hydrogels on stem cell

culture. Gandhi et al (57) reported that fibrin gels (30 mg/ml) could be used for iPSC

culture. Notably, fibrin concentration is directly proportional to the stiffness of fibrin

matrices (58). Our FLGs were finetuned to a Young's modulus of ~ 250-400 Pa to

mimic the stiffness of embryological liver (59,60) and the 10 mg/ml fibrin-only gels that

we tested had a Young's modulus of ~ 2 kPa. In our experience, high concentrations of fibrin (≥ 4 mg/ml) promoted spontaneous differentiation across 3 hPSC cell lines (2 ESC cell lines and 1 iPSC cell line) and this was augmented by the type of stem cell maintenance media used (Supplementary Figure 4). This was evidenced by the low differentiation efficiency and sub-optimal end-target cell phenotypes in fibrin-only hydrogels (e.g. our hepatic differentiation results in Fig.4). and independent studies that showed compliant substrates maintain self-renewal of ESCs by downregulating cell-matrix tractions whilst stiffer substrates promote spontaneous differentiation with downregulation of OCT3/4 expression (61,62). Interestingly, Liu et al (62) demonstrated that compliant fibrin-only gels (1 mg/ml, ~ 100 Pa) promoted the selection and growth of tumour cells that express stem cell markers CD133, Nestin, BMI-1, C-kit but not stem cell markers OCT3 and NANOG. In our study, the addition of Laminin 521 to low-concentration fibrin matrices preserved high OCT4 and NANOG expression in hPSCs over prolonged culture (2-3 months), and similarly fibrin-only hydrogels resulted in absent OCT3 and NANOG expression. Furthermore, no tumour growth was observed after H-iHeps were transplanted into the NSG™ mice. In that vein, the mild local inflammation in the immunocompetent Black 6 mice in our biocompatibility experiments was likely a combination of iatrogenic injury (given similar reactions with saline injections) and the implantation of xenogeneic biomaterials (human ECM proteins). Nonetheless, the mild degree of inflammation and its complete resolution by 6 weeks indicates good biocompatibility that would likely be tolerated well in human studies.

Since the benefits of fibrin-only matrices are limited in hPSC culture, several groups have recently attempted to create ECM-enriched fibrin hydrogels for regenerative medicine and cell therapy. Laminin 111 enriched fibrin matrices, loaded with (32,63) and without (64,65) cells were used to promote musculoskeletal regeneration after injury. Interestingly, Broguiere et al (22) attempted to mimic Matrigel by enriching fibrin gels with laminin 111 and collagen IV; they then demonstrated it could support the growth of adult stem cells (ASCs) through the propagation of cystic gastrointestinal organoids (intestinal, pancreatic and hepatic organoids). In our experiments, we found that Laminin 111 could maintain hPSC pluripotency (Supplementary Figure 2); however, over limited passages. hPSCs cultured on Laminin 111 were observed to change morphology and form colonies of spontaneously differentiated cells within 1-2

weeks (Supplementary Figure 13). Independently, several groups have also concluded that Laminin 111 triggers the spontaneous differentiation of hPSCs; likely through the α1 chain and β1 chain binding to the α3β1-integrin receptor (24–26). Therefore, hydrogels highly enriched with Laminin 111 may be used for ASCs but these are likely to cause phenotypic instability with hPSCs. In our experiments, differentiation efficiency varied between hPSC cell lines, however, these were similar in the reported literature (66–68).

The organization and polarization of tissues are important to tissue function. In particular, this has been a defining feature previously optimized in neural organoid protocols (69). While these methods typically rely on embedding early aggregates in Matrigel, we show that Alphagel has similar properties, allowing the spontaneous development of organized neural tissue with enlarged apical lumens. Besides consistency, a major advantage of the Alphagel system is that it allows simultaneous differentiation and structural organization without the need for further physical manipulations or tedious time-consuming steps, and thus could be useful to explore as a substrate for brain organoid generation. Similarly, we show the platform is useful in generating 3D cardiac tissue without the need for substrate changes mid-differentiation, thus holding promise in developing injectable regenerative therapies for cardiac disease or ex vivo cardiac tissue engineering.

Finally, we demonstrated that Hepatogel improves the engraftment efficiency of H-iHeps in murine livers, highlighting its potential for use as cell therapy for liver disease. At present, human hepatocytes are commonly delivered in solution via injections either directly into the liver or at various vascular sites that feed directly into the liver for cell therapy (70). However, in these approaches, engraftment rates are poor (70,71). Transplanted hepatocytes commonly occupy microvascular spaces, and the resulting ischaemic injury triggers vascular and immune responses within the local niche, which usually has a deleterious effect on the transplanted cells (71). This limits cell engraftment, treatment efficacy and the broader use of cell therapy in liver disease. Other methods of cell delivery involve the injection of cells encapsulated with degradation-resistant matrices such as alginate into the abdomen (72). This is often a temporising measure to bridge patients with liver failure to liver transplantation; in this situation, the encapsulation limits cell engraftment and repopulation. Therefore, we

evaluated if biomaterials (Hepatogel) could improve the engraftment rates of
transplanted iHeps by replacing the hostile environment with a "regenerative" liver
niche. To that end, we show that H-iHeps transplanted into mice liver engrafted better
with Hepatogel than H-iHeps in aqueous solution. This was evidenced by the post-
mortem findings, higher H-iHep cell counts, and the level of human albumin in mice
serum after transplantation; Fig.6(F) to Fig.6(G). However, although Hepatogel
improved engraftment, H-iHeps did not proliferate to replace native hepatocytes in the
host liver beyond one to two weeks. This may have been caused by the
immunogenicity of hPSC cells (73), limitations of current iHep technology (74), or
immunological responses in the recipient mice; NSG^{TM} mice have preserved
neutrophils and monocyte function. Limited repopulation of transplanted iHeps
remains a universal challenge, and our long-term observations are similar to others
reported in the literature (71). Nonetheless, as biotechnology advances, the derivation
of high-quality non-immunogenic lab-derived hepatocytes will improve, and clinically
applicable hydrogels will serve as useful adjuncts in hepatocyte derivation and cell
therapy by improving cell delivery, engraftment, and treatment efficacy (20).
543

CONCLUSION
We have shown proof-of-concept that bioengineered organ-specific hydrogels can
improve the phenotypes of hPSC-derived end-target cells compared to generic
hydrogels. Our fully defined and liver-specific hydrogel (Hepatogel) increased gene
expression and metabolic function in induced hepatocytes compared to Matrigel.
Being biodegradable, injectable, and composed of clinical-grade biomaterials,
Hepatogel may serve as a useful clinical adjunct to improve hepatocyte engraftment
for cell therapy.
552

MATERIALS AND METHODS
Protein Screening
Protein screening was performed using the Opera Phenix High-Content High-
Throughput (HCHT) screening system (PerkinElmer, USA). Briefly, the MFI of OCT4,
NANOG, and SOX2, were measured in hPSCs (positive control) cultured on Geltrex
(Thermofisher, #A1413302) and human fibroblasts (negative control) cultured on
uncoated plates. Optimised antibody concentrations are listed below. Nuclear
measurements were measured using DAPI. Differential characteristics between the

two populations were used to identify thresholds for machine learning. A screening

pipeline was created using Harmony High-Content Imaging and Analysis software

(Perkin Elmer, USA) and validated for accuracy as reported. hPSCs were then plated

on 96-well tissue culture-treated plates (Greiner Cellstar, #M0812) coated with single

substrates at 4 different concentrations. The measure of pluripotency within a stem

cell population was then defined as the "Stemness Index" (SI), which was calculated

by:

$$\text{Stemness Index (SI)} = \frac{\text{Total number of Stem Cells Identified}}{\text{Total number of Cells In Population}}$$

The maximum values of SI are 0 and 1, and the equation was incorporated into the

pipeline. This enabled the automated calculation of results and identification of

proteins that maintained stem cell pluripotency. Positive hits were checked using

brightfield microscopy.

2D cell culture

hPSCs were maintained on Geltrex-coated plates in feeder-free mTeSR-1™ and

mTeSR Plus™ media (Stemcell Technologies #85850 and #100-0276) using an

established protocol (75). Geltrex was substituted for other substrates during protein

screening. During maintenance, cells were split at 70-80% confluence using Accutase

(Millipore, #SCR005), washed with DMEM/F12 (Life Technologies, #11330032) and

re-seeded onto Geltrex-coated 6-well plates (Greiner, #657160) at a ratio of 1:6 to 1:8.

1mM Y27632 ROCK inhibitor (Stratech Scientific, #S1049-SEL-2mg) was used to

increase cell attachment. Media was supplemented with penicillin and streptomycin

(Millipore, #TMS-AB2-C). For screening experiments, human ESCs (KCL033) and

human iPSCs (RMA and BOB cell lines) were used. These were gifted by Dr Tamir

Rashid (King's College London). For other experiments, 2 ESC cell lines (H1 and H9,

WiCell #WA01 and #WA09 respectively) and 1 episomal iPSC cell line (ThermoFisher,

#A18945) were used. Cell viability in 2D and 3D experiments was assessed using

Trypan Blue (Sigma, #15250061).

Human dermal fibroblasts were available in-house (Sigma, #106-05a). Depending on

experiments, these were cultured either on uncoated tissue culture flasks (Corning,

#CLS3275) or Geltrex-coated 6-well plates. Fibroblasts were maintained in

DMEM/F12 media (Life Technologies, #11330032), 10% foetal bovine serum (Sigma,

#A9418), and 1% penicillin and streptomycin (Millipore, #TMS-AB2-C). Fibroblasts

were passaged using Trypsin (ThermoFisher, #11538876).

Primary human hepatocytes from 3 different non-diseased donors were obtained

commercially (Lonza, #HUCPI). These were quality-controlled, characterised and

came from three different lots; Lot no. HUM182701, HUM182641, and HUM191381.

Cells were thawed, plated on collagen-1 coated plates, and recovered for at least 24

hr in Hepatocyte Culture Media™ (HCM) including the complete HCM bullet kit (Lonza,

#CC-3198) according to the supplier's protocol. Experiments commenced after 24 –

48 hr of cell recovery.

3D cell culture

hPSCs were cultured in 3D domes of Matrigel, fibrin-only gels, or FLGs plated on

hydrophobic non-tissue culture-treated hydrophobic plates under normoxic conditions

at 37 °C. 50 µl domes were used for 24-well plates (Sarstedt, #83.3922.500) or 25 µl

domes for 96-well plates (Ibidi, #89621). H1, H9 and episomal cell lines were used for

these experiments. Feeder-free mTeSR-1™ and mTeSR Plus™ media (Stemcell

Technologies #85850 and #100-0276) were used for routine stem cell maintenance.

hPSCs designated for animal experiments were maintained in xeno-free TeSR™ 2

media (Stemcell Technologies, #05860). Cells were split every 5-6 days using TrypLE

Express (Gibco, #12604013). Each dome required 20-25 min in TrypLE Express with

manual pipetting for successful dissociation. Domes were then re-loaded with 12,500

to 225,00 cells depending on experiments.

For experiments investigating the effect of stem cell culture media on hPSC

pluripotency in Alphagel, TeSR-E8™ culture media (Stemcell Technologies, #05990),

E8™ culture medium (ThermoFisher, #A1517001), and TeSR-E8TM culture medium

(Stemcell Technologies, #05990) were used in addition to those described above. All

culture media were supplemented with 1% penicillin and streptomycin (Millipore,

#TMS-AB2-C). Media were refreshed on alternate days. EBs formed after three to four

days in FLGs and Matrigel.

3D cardiac differentiation

hPSCs designated for cardiac differentiation were transitioned to E8^{TM} culture medium

(ThermoFisher, #A1517001) supplemented with 2.25 ng/ml of Fibroblast Growth

Factor-2 (FGF-2: Qkine, #Qk053), and 1.74 ng/ml of Transforming Growth Factor Beta

(TGF-b: Bio-techne, #7754-BH). This media is primed for cardiac differentiation as

previously described (76). When hESC colonies reached the desired number and size,

cardiac differentiation was initiated using a previously established protocol (77).

Briefly, mesodermal specification was initiated by replacing the FGF-2 and TGF-b

enriched E8 maintenance media with CDM-BSA (Sanjay Sinha Lab, University of

Cambridge) containing 20 ng/ml of FGF-2/ml, 10 µM of 2-(4-Morpholinyl)-8-phenyl-4

H-1-benzopyran-4-one (Ly294002: Promega, #V120A), 50 ng/ml of Activin A

(Stemcell Technologies, #78132.2), and 10 ng/ml of Bone Morphogenic Protein-4

(BMP-4: RnD system, #314-BP-050). After 42 hr (Day 1.5), this was replaced with

CDM-BSA containing 8 ng/ml of FGF-2, 10 ng/ml of BMP-4, 1µM of retinoic acid

(Sigma, #R2625) and Wnt/β-catenin signalling inhibitor endo-IWR1 (R&D systems,

#3532). Media was refreshed after 48 hr (Day 3.5). After another 48 hr (Day 5.5), the

media was replaced with CDM-BSA containing 8 ng/ml of FGF-2 and 10 ng/ml of BMP-

4. Standard CDM-BSA media was then refreshed every 48 hr (Day 7.5 onwards).

3D neuronal differentiation

hPSCs designated for neuronal differentiation were transitioned into Stem Flex media

(ThermoFisher, # A3349401) with the addition of 10µM Y-27632 (Tocris, #1254)

before initiating differentiation. Media was refreshed daily. When EBs were of sufficient

number and size in Alphagel, neuronal differentiation was performed using an

established protocol (78). Briefly, after four days of expansion in Alphagel with Stem

Flex media, the media was switched to N2B27 media (in-house) supplemented with 5

µM SB-431542 (Tocris, #1614), 200 nM LDN-193189 (Miltenyi, #130-103-925), and 2

µM XAV-939 (Tocris, #3748). Media with these factors was refreshed daily for ten

days. After this, cells were maintained in N2B27 media only for a further six days.

3D hepatic differentiation

Hepatocyte differentiation was performed using a previously established protocol (75). Briefly, hPSCs were cultured in RMPI (ThermoFisher, #22400089) supplemented with 2% B27 minus insulin (ThermoFisher, #A1895601), 100 ng/ml of Activin A, 20 ng/ml of FGF-2 (ThermoFisher, #PHG0023) and 10 ng/ml of Bone Morphogenic Protein-4 (BMP-4: R&D system, #314-BP-050) on differentiation days 1 — 2 to initiate differentiation. From differentiation days 3 — 5, the media was replaced with RMPI supplemented with 2% B27 minus insulin and 100 ng/ml Activin A only. Hepatic endoderm specification was initiated on differentiation days 6 — 10 using RMPI supplemented with 2% B27 and insulin (ThermoFisher, #17504044), 10 ng/ml FGF-2, and 20 ng/ml BMP-4, followed by RMPI with 2% B27, insulin, and 20 ng/ml hepatocyte growth factor (HGF: Peprotech, #100-39-250) on differentiation days 11 — 15. Maturation of hepatic endoderm was initiated on differentiation days 16 — 21 using complete HCM media supplemented with 10 ng/ml Oncostatin M (OSM: R&D systems, # 8475-OM-050), 20 ng/ml HGF and 0.1 µM Dexamethasone (ThermoFisher, #A17590.06).

Synthesis of fibrin hydrogels

Human fibrinogen from non-diseased donors (Merck Millipore, #341576-1GM) was reconstituted in sterile 0.9% saline to a stock concentration of 67 mg/ml. Human thrombin (Sigma, #T6884-100UN) was reconstituted in sterile 0.9% saline supplemented with human serum albumin (0.1% w/v) giving a stock concentration of 50 U/ml. DMEM/F12 was then added to various volumes of fibrinogen and thrombin to achieve the desired final fibrinogen concentration of the fibrin gels. Final fibrinogen concentrations in the hydrogels that we tested ranged from 1 mg/ml to 10 mg/ml. The final concentration of thrombin in these hydrogels was maintained at 1 U/ml. For cell experiments, hPSCs were loaded into the DMEM/F12 compartment.

Synthesis of Alphagel and Hepatogel

Alphagel and Hepatogel were synthesised using similar methods of fibrin-laminin enrichment previously reported (22,32) with minor adjustments. Briefly, for acellular Alphagel domes, human recombinant laminin 521 (Biolamina, #CT521-0501/LN521-05), human fibrinogen and DMEM/F12 were incubated in sterile Eppendorf (Elkay Lab, #MICR-050) at 37 °C for 15 min. The mixture was then mixed and left to incubate for a further 15 min. Lastly, thrombin diluted in DMEM/F12 at room temperature was

added to the mixture for gelation. 50 µl domes of the final mixture were then plated on 24-well flat bottom hydrophobic plates (Sarstedt, #83.3922.500) using wide bore pipette tips (Starlab UK, #I1011-8000). The final composition of Alphagel contained a 50:50 v/v mixture of Laminin 521, 2.5 mg/ml fibrinogen and 1 U/ml thrombin. For Hepatogel, Laminin 411 (Biolamina, #LN411) and Laminin 111 (Biolamina, #LN111) were first purified using Amicon Ultra-0.5 centrifugal filter units (Merck Millipore, UFC5003) and reconstituted in sterile PBS. Then, Laminin 521, 411, and 111 were mixed in the respective ratio of 5:1:2. For cell experiments, hPSCs were loaded in the laminin(s)-DMEM/F12-fibrinogen compartment and incubated as described above. Lastly, the thrombin-DMEM/12 compartment was added for polymerisation. The cell-laden mixture was then seeded at 50 µl per dome in 24-well plates and inverted to allow the cells to remain suspended in 3D. These plates were kept inverted for a further 30 min to allow to gelation complete fully. Thereafter, plates were turned over and 1 ml of media was added to each well. Media was refreshed at a frequency determined by experiments.

Scanning Electron Microscopy (SEM)

Fibrin-only hydrogels and FLGs samples for SEM were prepared following a previously published protocol (79). Briefly, fibrin-only and FLGs were mounted and gelled in 444 ferritic stainless-steel scaffolds (Nikko Techno Ltd., Japan) for mechanical support. An hour after gelation, samples were fixed in 10% formalin (VWR International, #11699455) and left in a fume hood overnight. The following day, samples were washed three times with PBS and then dehydrated in increasing concentrations of ethanol-de-ionised (DI) water mixtures; 30, 50, 70, 80, 90, 95 and 100% ethanol. The final step with 100% ethanol was repeated twice. Samples were submerged for 30 min in each ethanol-DI mixture. For dehydration, the samples were immersed in increasing concentrations of hexamethyldisilazane (HMDS)-ethanol mixtures in a fume hood; 33.3, 66.6 and 100% HMDS (Sigma, #440191) respectively. Samples were immersed in each HMDS-ethanol mixture for 40 min. The final step involving 100% HMDS was repeated twice, and then samples were left submerged in 100% HMDS overnight in a fume hood until completely dry the following day. Dried samples were gold plated before imaging with Evo LS 15 (Zeiss, Germany) scanning electron microscope.

Immunofluorescence (IF) staining

For 2D protein screening experiments, culture media was aspirated, and cells were washed twice with phosphate buffer saline (PBS; Sigma, #806552) using volumes of 100 µl per well for 96-well plates. Fixation was performed using 4% paraformaldehyde (PFA, Insight Biotechnology, #sc-281692) for 20 min at 4 °C followed by two further PBS washes. 50 µl of blocking solution containing 3% donkey serum (Sigma, #D9663-10ML), 0.1% Triton-X (Sigma, #X100-500ML), 1% BSA (Sigma, #12657), and 95.9% PBS was then added to each well. The plate was left for 30 min at room temperature for permeabilization, and blocking, then aspirated for the addition of the primary antibodies without washing. The list of primary antibodies is listed in Table 1. After two hr at room temperature, the primary antibodies were aspirated, and cells were washed twice with 100 µl/well PBS in each wash. 50 µl/well of secondary antibodies were then added and samples were left to incubate at room temperature in the dark for 2 hr. The list of secondary antibodies is listed in Table 2. After 2 hr, secondary antibodies were aspirated, and cells were washed twice with PBS (100 µl/well) followed by the addition of DAPI solution (NucBlue^{TM} Fixed, Life Technologies #R37606). Imaging was then performed within 24 hr.

For 3D cardiac and hepatic experiments, cell-laden hydrogel domes first underwent two fifteen-minute washes with PBS (1 ml/well for a 24-well place). Samples were then fixed for 60 min at 4 °C with 4% paraformaldehyde (1 ml/well) followed by three 15 min washes with PBS (1ml/well). Subsequently, cells were permeabilized and blocked in 1% (w/v) bovine serum (Sigma, #A9418), 3% donkey serum (Sigma, #D9663), and 0.1% Triton X-100 (Sigma, #X100) in sterile PBS for one hour at room temperature. The blocking solution was then aspirated, and primary antibodies (1ml/well) were added without any washing. Samples were left overnight at 4 °C to incubate. The following day, primary antibodies were aspirated, and samples underwent two fifteen-minute PBS washes. Next, secondary antibodies were added, and samples were left in the dark at room temperature to incubate for ≥3 hr. Thereafter, the DAPI solution was added and images were acquired at least 30 min after the addition of the DAPI solution. For 3D neural experiments, hydrogels were fixed in 4% PFA for 45 min at room temperature then transferred into a 30% w/v sucrose solution (Sigma Aldrich, #S0389) and left for 24 hr. Sucrose-saturated samples were subsequently placed in OCT (ThermoFisher, #23-730-571) and stored at -20 °C. These frozen blocks were then cut into 12 µm sections and mounted on coated slides (ThermoFisher,

#J1800AMNZ). Sections were then blocked and permeabilised in a 0.3% Triton-X solution containing 10% normal goat serum at room temperature for an hour. Primary antibodies diluted in 0.1% Triton-X containing 5% normal goat serum were then added and incubated overnight at 4 °C. The following day, sections were washed with PBS and secondary antibodies were added and left for an hour at room temperature. Lastly, samples were incubated in DAPI solution for 15 min and then mounted using FluorSave (VWR, #345789).

Table 1: List of primary antibodies.

Primary Antibodies (species raised in)	Vendor	Catalogue no.	Dilution factor
OCT4 (rabbit)	ThermoFisher	710788	1:250
NANOG (rabbit)	Abcam	ab109250	1:100
SOX2 (rabbit)	ThermoFisher	PA1-094	1:100
SOX2 (goat)	RnD Systems	AF2018	10 µg/ml
Albumin (goat)	Bethyl	A80-129A	1:100
CD147 (mouse)	Abcam	Ab666	1:100
HNF1A (rabbit)	Cell Signalling	D7Z2Q	1:400
HNF4A (rabbit)	ThermoFisher	MA5-14891	1:2000
Cyp2A6 (chicken)	University of Eastern Finland	Collaborator	1:200
E-cadherin (mouse)	Santa Cruz	SC-31021	1:100
Troponin-T (goat)	Abcam	ab64623	1:100
Smooth Muscle α-Actin (mouse)	Dako	M0851	1:100
Nestin (mouse)	Sigma	N5413-100UG	1:500
B-catenin (rabbit)	ThermoFisher	14-2567-82	1:250

Table 2: List of secondary antibodies.

Secondary Antibodies	Vendor	Catalogue no.
AlexaFluor 488 donkey anti-goat	ThermoFisher	A11055
AlexaFluor 488 donkey anti-rabbit	Abcam	ab150073
AlexaFlour 488 donkey anti-rabbit	ThermoFisher	A21206
AlexaFluor 564 donkey anti-mouse	ThermoFisher	A10037
AlexaFluor 647 donkey anti-rabbit	Abcam	ab150075
AlexaFluor 647 donkey anti-mouse	ThermoFisher	A32795
AlexaFluor 647 donkey anti-mouse	ThermoFisher	A31571

For IF staining of tissue sections, glass slides with paraffin-embedded sections were rehydrated in xylene (5 min x3), then transferred to reducing concentrations of ethanol (100% for 5 min x2, 90% for 2 min, and 70% for 2 min). Thereafter, slides were washed in distilled water for 5 min and transferred to pH 6.0 antigen retrieval buffer and heated to 121 °C for 15 min. After cooling, the slides were re-washed with distilled water. A hydrophobic pen was used to mark the area of interest. Then, TrueBlack® (Biotium, #23007) dissolved in 70% ethanol (1X) was added to the samples for 30 sec to reduce autofluorescence. Subsequently, slides were rinsed with distilled water and blocking solution, as described above, was added and the samples were left for 30 min at room temperature. After 30 min, the blocking solution was discarded without washing the samples and goat anti-human albumin primary antibody dissolved in sterile PBS to a final concentration of 1:100 ((as described above) was added to the samples. Slides were then left to incubate at 4 °C overnight. The following day, the slides were washed with distilled water, and then 1:200 Alexa Fluor 647 donkey anti-goat secondary antibody (as above) was added. The slides were left for one hour to incubate in the dark at room temperature and then washed again before adding Fluoroshield™ mounting media containing DAPI (Sigma, #F6057). Lastly, coverslips were placed and sealed with nail polish.

Imaging

2D IF and brightfield images of hPSCs were acquired using the Opera Phenix HCHT screening system (PerkinElmer, USA). Optimal acquisition settings were determined

as 100 ms exposure time and 90% excitation strength; these were kept constant during screening. 3D images of cardiac and hepatic cells and tissue were captured using an LSM710 (Zeiss, Germany) laser scanning confocal microscope at x10 and x20 objectives with corresponding filters. Bright-field images were acquired using an Axio-Obsorber.Z1 (Zeiss, Germany) fluorescence microscope. Images of CDFDA uptake and excretion in iHeps were acquired using an SP-DM8 (Leica, Germany) microscope. 3D images of neuronal cells were acquired using a DM 6000 B (Leica, Germany) microscope.

Young's modulus measurements

Fibrin-only and FLGs were examined under compression using a customised "see-saw" method that was previously described (80) and loads were applied by pumping liquid via a syringe pump. This method minimises sample strain during measurements - excessive straining occurs easily with such highly compliant materials and can produce misleading results. Briefly, two arms of a see-saw were first balanced before counterweights were added onto the free-extending arm to match the height of the loading platen with the sample height. Next, the load was ramped up at a constant rate of 10^{-3} N s^{-1} by pumping liquid, via a PHD ULTRA syringe pump (Harvard Apparatus, USA), into a container fixed on top of the loading platen. The resulting displacement was measured using a biaxial laser micrometre (resolution of ±3 μm, Keyence, #TM-040). Nominal stresses (σ) and strains (ε) were plotted, and a line was least-square fitted to the data points. From the tangent slope of the stress-strain curves, the through-thickness Young's modulus was calculated (n=5 in each group).

Gene expression analyses by quantitative polymerase chain reaction (qPCR)

Ribonucleic acid (RNA) was extracted using TriZOL^{TM} (ThermoFisher, #15596026) and purified using the Direct-zol RNA Miniprep Kit (Zymo Research, #R2050-R2053). cDNA was made using Superscript Reverse Transcriptase IV (ThermoFisher, #18090010) following the manufacturer's protocol. Quantitative PCR was run on Quantstudio 5 (ThermoFisher, #A34322I) using the KAPA SYBR FAST qPCR kit (Roche, #KK4601). Data were analysed using the 2^(ΔΔCt) method. Sequences of the primer pairs are listed in Table 3.

Table 5.3: Sequences for forward and reverse primers used.

Target gene	Forward primer sequence	Reverse primer sequence
ABCC2	TTCGTTCCAGACGCAGTCCAGG	CCAGGAGCCATAGGTAGCCCAA
APOB	TGTTAGGACACCAGCCCTCCA	GCCCGAAGGCTGAAATGGTCT
AFP	AACTATTGGCCTGTGGCGAGG	TGAAGCATGGCCTCCTGTTGG
BAAT	TGTGCCTCAACGACCCACGAT	GGGGGAGACATTCCGCCATGAA
CEBPA	AAGTCGGTGGACAAGAACAGCAA	TTGTCACTGGTCAGCTCCAGCA
CYP27A1	GCTGTTCGTTCAAGGCTATGCCC	ACTGGGTACTTGCCCTCTTGCC
CYP3A4	TGTGCCTGAGAACACCAGAG	GTGGTGGAAATAGTCCCGTG
CYP3A5	ACAAGACCCCTTTGTGGAGAGC	TTGTTTGTCGTTGAGGCGACTT
CYP3A7	TGGACCCAGAAACTGCATTGGC	ATCAGGCTCCACTTACGGTCTCA
CK7	AAGCAGGATATGGCACGGCAG	CACTCCATCTCCAGCCAACCG
CK19	GGCGATGTGCGAGCTGATAGT	CGGTAGGTGGCAATCTCCTGC
FOXA1	CCTTCAACCACCCGTTCTCCA	CGGGCAACGTAGAGCCGTAAG
FOXA2	GCCTACGAACAGGTGATGCACTA	CAGGCCCGTTTTGTTCGTGAC
GATA6	AGCACCAATCCCGAGAACAGC	GTCGCACGGAGGACGTGACTT
GATA4	TCCATCCACCCTGTCCTCTCG	GCTTGGAGCTGGTCTGTGGAG
G6PC	TACAGCAACACTTCCGTGCCCC	GCACAGCCCAGAATCCCAACCA
GGT	ACAACCAGCTTCTGCCCAACG	GACGCGATCTGGGTGTGATGG
HNF4A	GAGATGCTGCTGGGAGGGTCC	GGGTCTCAGGGGTGGACATCT
LGR5	CCTGCTTGATGGCTGGCTGAT	CACTGCTGCGATGACCCCAAT
PDK4	TACAGCAACACTTCCGTGCCCC	GCACAGCCCAGAATCCCAACCA
SOX9	CAACAGATCGCCTACAGCCCC	CGTACTGTGAGCGGGTGATGG
TAT	TGGAAACCTGCCTACAGACC	TAGCTTCTAGGGGTGCCTCA
TF	CCGATGGTCCCAGTGTTGCTT	AACTCTGCCACCACAGGCTTC
TBX3	GGGACACTGGAAATGGCCGAA	GGAGAAGAAGCCTGGGCGAAG
MUC2	GCTGACGAGTGGTTGGTGAATG	GATGAGGTGGCAGACAGGAGAC

Enzyme-linked immunosorbent assays (ELISA)

Laminin concentrations in supernatants were measured using a laminin ELISA kit (Insight Biotechnology, #Boster Pikokine™ EK0434). Acellular FLGs and fibrin gels were synthesized, and sterile DMEM/F12 media was added 30 min after gelation. Media was collected the next day (Day 1) and then every other day for two weeks. Supernatants were stored at -20 °C until they were analysed alongside stock concentrations of laminin for comparison using the Laminin ELISA kit as per the manufacturer's instructions. Sample absorbance readings were then taken using a FLUOstar® Omega plate reader (BMG Labtech Ltd, UK) at 450 nm. The residual amount of laminin in FLGs was estimated by the following equation:

$$1 - \frac{Total\ Laminin\ 521\ in\ supernatant\ after\ hydrogel\ gelation\ (weight)}{Measured\ Laminin\ 521\ in\ stock\ solution\ added\ to\ the\ hydrogel\ (weight)}$$

Albumin concentrations in supernatants were measured using a human albumin ELISA quantification kit (Bethyl Lab, #E80-129). Sample absorbance was measured with a Synergy HTX microplate reader (BioTek, USA). Supernatants from PHH hepatocytes were collected 24 hr after the completion of cell recovery. Supernatants from iHeps were collected 2 days after (Day 22) the end of the differentiation protocol (Day 20); media was refreshed every other day as per differential protocol).

APOB secretion in the supernatant was quantified using the human APOB ELISA quantification kit (Mabtech, # 3715-1H-6) according to product literature. Sample absorbance was measured with an Infinite M1000 PRO microplate reader (Tecan, Switzerland). Supernatants from iHeps were collected 2 days after (Day 22) the end of the differentiation protocol (Day 20); media was refreshed every other day as per differential protocol).

Cytochrome 3A4 (CYP3A4) assay
CYP3A4 activity was measured using the P450-Glo™ CYP3A4 Assay kit (Promega, #V9001) as per the manufacturer's protocol. Fluorescence in samples was measured using the Synergy HTX microplate reader. PHH after 24 hr of cell recovery and Day 22 iHeps were used.

Low-density Lipoprotein (LDL) uptake cell-based assay
LDL uptake was demonstrated using a cell-based kit (Cayman chem, #10011125) following the manufacturer's protocol. iHeps were incubated for 12 hr, then the HCM media was replaced with PBS. Images were then acquired immediately. Day 22 iHeps and hPSCs (negative control) were used.

5-(and-6)-Carboxy-2',7'-Dichlorofluorescein Diacetate (6-CDF)
6-CDF was used to demonstrate hepatocyte function following a protocol previously described (39). 3D iHeps (Day 22) were incubated for 2 hrs with HCM media containing 1 µmol/L of 6-CDF (Thermofisher, #C-369). Samples were then washed with PBS for 15 min before staining with Hoescht in HCM.

Gamma-glutamyl Transfer (GGT) assay

GGT activity was determined by a fluorometric GGT assay kit (Abcam, #ab241030) as per product literature. Fluorescence in samples was measured with the Infinite M1000 PRO microplate reader. PHH after 24 hr of cell recovery and Day 22 iHeps were used. PHH after 24 hr of cell recovery and Day 22 iHeps were used.

Animal experimentation

Biocompatibility studies were performed in immunocompetent general-purpose C57BL/6 ("Black 6") mice obtained from InVivos (www.invivos.com.sg). Only healthy, normal strain male mice between two to three months old ($\sim$ 30 g to 35 g) were used. 100% croton oil (Merck, #C6719-10G) was emulsified in corn oil to a final concentration of 1.0% *v/v, referred to herein as "croton oil".* Croton oil was used as a positive control because it is a well-known skin allergen that is commonly used to study inflammation in murine models (81). 200 µl of croton oil (n=9), Alphagel (n=9), fibrin-only gel (n=9), and 0.9% saline (n=9) was injected subcutaneously using 18G hypodermic needles and 1 ml low dead volume syringes into the flanks or scruffed backs of Black 6 mice with aseptic techniques. These volumes were within internationally recommended limits for subcutaneous murine injections (American Association for Laboratory Animal Science). Three mice from each group were culled at 1 week, 2 weeks, and 6 weeks post-injection. Mice were culled by cervical dislocation under general anaesthesia with isofluorane. Injection sites were excised and fixed in 10% formalin for 24 hr then transferred into 70% ethanol. Tissues were then embedded in liquid paraffin, sectioned by microtome, and placed on glass slides. Slides were stained for hematoxylin and eosin (H&E) to allow for evaluation for signs of inflammation, then imaged with the TissueFAXS i-plus system (TissueGnostics, Vienna, Austria).

Both male and female mice were used. All mice were between four to five months old and weight $\sim$ 40 g to 50 g. All mice were anaesthetised with isoflurane and had their abdomen shaved pre-operatively. Surgical laparotomies were then performed aseptically to reveal the lower liver margin for injections. For H-iHep transplantations, 3×10^6 million freshly harvested Day 22 H-iHeps were harvested and re-suspended in 75 µl of either Hepatogel (n=9) or sterile 0.9% saline (n=9), then injected under direct vision with a 1 ml low dead volume syringe and 18G hypodermic needle into the inferior

margins of the right liver lobe. All mice were given prophylactic antibiotics and

analgesia subcutaneously for three days after the operation. 3 mice from each group

were culled on Day 3, Day 7-, and 2 months post-hepatocyte transplantation.

All mice were fed rodent maintenance food (#2918 Teklad Irradiated Global, 18%

Protein rodent diet, Envigo, Hackensack, NJ) and kept on bedding from BioCOB.

Approval for all animal work was granted by the National University of Singapore

Institutional Animal Care and Use Committee (IACUC), protocol number R20-0822.

Statistical analyses

Prism 9.3.0 (GraphPad, USA) was used for data analyses and the generation of bar

graphs. Data were tested for normal distribution using the Shapiro-Wilk method.

Parametric data and their bar charts were presented as mean and standard deviation

unless otherwise stated. For comparison between two groups of values, the student's

t-test was used to compare means for parametric values; the Chi-squared test or

Mann-Whitney U test was used to test for associations in non-parametric values.

When more than two groups were compared, one-way analysis of variance (ANOVA)

with Tukey correction was performed on parametric data; the Kruskal-Wallis test was

used when data were not parametric All tests were two-sided, and the alpha was set

at 5%.

Data availability statement: The authors confirm that the data supporting the findings

of this study are available within the article and/or its supplementary materials.

Funding statement: JO was supported by the University of Cambridge (UoC) WD

Armstrong graduate studentship, the UoC Engineering in Clinical Practice grant, the

National University of Singapore (NUS) Talent Development grant, and the NUS

Postdoctoral Development grant. JZ was supported by Trinity College and the

Cambridge Commonwealth, European, and International Trust (UoC). AWJ was

supported by an Engineering and Physical Sciences Research Council grant, the

Rosetree Trust and the Isaac Newton Trust.

Conflict of Interest Disclosure: The authors have none to declare.

Ethics approval statement: This study did not involve human subjects. The National

University of Singapore Institutional Animal Care and Use Committee (IACUC) granted

ethical approval for animal research, *protocol number R20-0822.*

References

1. Hofer M, Lutolf MP. Engineering organoids. Nat Rev Mater. 2021 May;6(5):402–20.

2. Pampaloni F, Reynaud EG, Stelzer EHK. The third dimension bridges the gap between cell culture
and live tissue. Nat Rev Mol Cell Biol. 2007 Oct;8(10):839–45.

3. Gjorevski N, Nikolaev M, Brown TE, Mitrofanova O, Brandenberg N, DelRio FW, et al. Tissue
geometry drives deterministic organoid patterning. Science. 2022 Jan 7;375(6576):eaaw9021.

4. Salthouse D, Novakovic K, Hilkens CMU, Ferreira AM. Interplay between biomaterials and the
immune system: Challenges and opportunities in regenerative medicine. Acta Biomater. 2023 Jan
1;155:1–18.

5. Chan SW, Rizwan M, Yim EKF. Emerging Methods for Enhancing Pluripotent Stem Cell Expansion.
Front Cell Dev Biol [Internet]. 2020 Feb 14 [cited 2024 Dec 17];8. Available from:
https://www.frontiersin.org/journals/cell-and-developmental-
biology/articles/10.3389/fcell.2020.00070/full

6. Heo JH, Kang D, Seo SJ, Jin Y. Engineering the Extracellular Matrix for Organoid Culture. Int J Stem
Cells. 2022 Feb 28;15(1):60–9.

7. Aisenbrey EA, Murphy WL. Synthetic alternatives to Matrigel. Nat Rev Mater. 2020 Jul;5(7):539–
51.

8. Baker M. Stem cells in culture: defining the substrate. Nat Methods. 2011 Apr;8(4):293–7.

9. Vukicevic S, Kleinman HK, Luyten FP, Roberts AB, Roche NS, Reddi AH. Identification of multiple
active growth factors in basement membrane Matrigel suggests caution in interpretation of
cellular activity related to extracellular matrix components. Exp Cell Res. 1992 Sep;202(1):1–8.

10. Soofi SS, Last JA, Liliensiek SJ, Nealey PF, Murphy CJ. The elastic modulus of Matrigel as
determined by atomic force microscopy. J Struct Biol. 2009 Sep;167(3):216–9.

11. Hughes CS, Postovit LM, Lajoie GA. Matrigel: a complex protein mixture required for optimal growth of cell culture. Proteomics. 2010 May;10(9):1886–90.

12. Passaniti A, Kleinman HK, Martin GR. Matrigel: history/background, uses, and future applications. J Cell Commun Signal. 2022 Dec;16(4):621–6.

13. Liu H, Bockhorn J, Dalton R, Chang YF, Qian D, Zitzow LA, et al. Removal of lactate dehydrogenase-elevating virus from human-in-mouse breast tumor xenografts by cell-sorting. J Virol Methods. 2011 May;173(2):266–70.

14. Segers VFM, Lee RT. Biomaterials to enhance stem cell function in the heart. Circ Res. 2011 Sep 30;109(8):910–22.

15. Farhat W, Hasan A, Lucia L, Becquart F, Ayoub A, Kobeissy F. Hydrogels for Advanced Stem Cell Therapies: A Biomimetic Materials Approach for Enhancing Natural Tissue Function. IEEE Rev Biomed Eng. 2019;12:333–51.

16. Cruz-Acuña R, Quirós M, Huang S, Siuda D, Spence JR, Nusrat A, et al. PEG-4MAL hydrogels for human organoid generation, culture, and in vivo delivery. Nat Protoc. 2018 Sep;13(9):2102–19.

17. Amzad Hossain M, Kumar Roy C, Don Sarkar S, Roy H, Hasan Howlader A, H. Firoz S. Improvement of the strength of poly(acrylic acid) hydrogels by the incorporation of functionally modified nanocrystalline Cellulose. Mater Adv. 2020;1(6):2107–16.

18. Ilyas RA, Zuhri MYM, Norrrahim MNF, Misenan MSM, Jenol MA, Samsudin SA, et al. Natural Fiber-Reinforced Polycaprolactone Green and Hybrid Biocomposites for Various Advanced Applications. Polymers. 2022 Jan 3;14(1):182.

19. Labouesse C, Tan BX, Agley CC, Hofer M, Winkel AK, Stirparo GG, et al. StemBond hydrogels control the mechanical microenvironment for pluripotent stem cells. Nat Commun. 2021 Oct 21;12(1):6132.

20. Wang X, Rivera-Bolanos N, Jiang B, Ameer GA. Advanced Functional Biomaterials for Stem Cell Delivery in Regenerative Engineering and Medicine. Adv Funct Mater. 2019;29(23):1809009.

21. Yin S, Cao Y. Hydrogels for Large-Scale Expansion of Stem Cells. Acta Biomater. 2021 Jul 1;128:1–20.

22. Broguiere N, Isenmann L, Hirt C, Ringel T, Placzek S, Cavalli E, et al. Growth of Epithelial Organoids in a Defined Hydrogel. Adv Mater. 2018;30(43):1801621.

23. Ye S, Boeter JWB, Mihajlovic M, van Steenbeek FG, van Wolferen ME, Oosterhoff LA, et al. A Chemically Defined Hydrogel for Human Liver Organoid Culture. Adv Funct Mater. 2020;30(48):2000893.

24. Domogatskaya A, Rodin S, Boutaud A, Tryggvason K. Laminin-511 but Not -332, -111, or -411 Enables Mouse Embryonic Stem Cell Self-Renewal In Vitro. STEM CELLS. 2008;26(11):2800–9.

25. Horejs CM, Serio A, Purvis A, Gormley AJ, Bertazzo S, Poliniewicz A, et al. Biologically-active laminin-111 fragment that modulates the epithelial-to-mesenchymal transition in embryonic stem cells. Proc Natl Acad Sci U S A. 2014 Apr 22;111(16):5908–13.

1016   26.   Li L, Arman E, Ekblom P, Edgar D, Murray P, Lonai P. Distinct GATA6- and laminin-dependent
1017   mechanisms regulate endodermal and ectodermal embryonic stem cell fates. Dev Camb Engl.
1018   2004 Nov;131(21):5277–86.

1019   27.   Ong J, Serra MP, Segal J, Cujba AM, Ng SS, Butler R, et al. Imaging-Based Screen Identifies
1020   Laminin 411 as a Physiologically Relevant Niche Factor with Importance for i-Hep Applications.
1021   Stem Cell Rep. 2018 Mar 13;10(3):693–702.

1022   28.   Borowski M, Giovino-Doherty M, Ji L, Shi MJ, Smith KP. Basic pluripotent stem cell culture
1023   protocols. In: Laning J, editor. StemBook [Internet]. Cambridge (MA): Harvard Stem Cell Institute;
1024   2008 [cited 2023 May 13]. Available from: http://www.ncbi.nlm.nih.gov/books/NBK133258/

1025   29.   Stem Cell Culture Guide [Internet]. [cited 2023 May 13]. Available from:
1026   https://www.atcc.org/resources/culture-guides/stem-cell-culture-guide

1027   30.   Goetzke R, Keijdener H, Franzen J, Ostrowska A, Nüchtern S, Mela P, et al. Differentiation of
1028   Induced Pluripotent Stem Cells towards Mesenchymal Stromal Cells is Hampered by Culture in 3D
1029   Hydrogels. Sci Rep. 2019 Oct 30;9(1):15578.

1030   31.   Jones M, Gabriel DA. Influence of the subendothelial basement membrane components on
1031   fibrin assembly. Evidence for a fibrin binding site on type IV collagen. J Biol Chem. 1988 May
1032   25;263(15):7043–8.

1033   32.   Marcinczyk M, Elmashhady H, Talovic M, Dunn A, Bugis F, Garg K. Laminin-111 enriched
1034   fibrin hydrogels for skeletal muscle regeneration. Biomaterials. 2017 Oct;141:233–42.

1035   33.   Woodcock-Mitchell J, Mitchell JJ, Low RB, Kieny M, Sengel P, Rubbia L, et al. Alpha-smooth
1036   muscle actin is transiently expressed in embryonic rat cardiac and skeletal muscles. Differ Res Biol
1037   Divers. 1988 Dec;39(3):161–6.

1038   34.   Maroof AM, Keros S, Tyson JA, Ying SW, Ganat YM, Merkle FT, et al. Directed differentiation
1039   and functional maturation of cortical interneurons from human embryonic stem cells. Cell Stem
1040   Cell. 2013 May 2;12(5):559–72.

1041   35.   Chambers SM, Fasano CA, Papapetrou EP, Tomishima M, Sadelain M, Studer L. Highly
1042   efficient neural conversion of human ES and iPS cells by dual inhibition of SMAD signaling. Nat
1043   Biotechnol. 2009 Mar;27(3):275–80.

1044   36.   Hofrichter M, Nimtz L, Tigges J, Kabiri Y, Schröter F, Royer-Pokora B, et al. Comparative
1045   performance analysis of human iPSC-derived and primary neural progenitor cells (NPC) grown as
1046   neurospheres in vitro. Stem Cell Res. 2017 Dec;25:72–82.

1047   37.   Ladiwala U, Basu H, Mathur D. Assembling Neurospheres: Dynamics of Neural
1048   Progenitor/Stem Cell Aggregation Probed Using an Optical Trap. PLoS ONE. 2012 Jun
1049   5;7(6):e38613.

1050   38.   Kim HJ, Lee E, Nam M, Chung JK, Joo S, Nam Y, et al. Contribution of Extracellular Matrix
1051   Component Landscapes in the Adult Subventricular Zone to the Positioning of Neural
1052   Stem/Progenitor Cells. Exp Neurobiol. 2021 Aug 31;30(4):275–84.

1053   39.   Ramli MNB, Lim YS, Koe CT, Demircioglu D, Tng W, Gonzales KAU, et al. Human Pluripotent
1054   Stem Cell-Derived Organoids as Models of Liver Disease. Gastroenterology. 2020
1055   Oct;159(4):1471-1486.e12.

1056   40.   Maepa SW, Ndlovu H. Advances in generating liver cells from pluripotent stem cells as a tool
1057   for modeling liver diseases. STEM CELLS. 2020;38(5):606–12.

1058   41.   Ang LT, Tan AKY, Autio MI, Goh SH, Choo SH, Lee KL, et al. A Roadmap for Human Liver
1059   Differentiation from Pluripotent Stem Cells. Cell Rep. 2018 Feb;22(8):2190–205.

1060   42.   Schafer KA, Eighmy J, Fikes JD, Halpern WG, Hukkanen RR, Long GG, et al. Use of Severity
1061   Grades to Characterize Histopathologic Changes. Toxicol Pathol. 2018 Apr;46(3):256–65.

1062   43.   Thuilliez C, Dorso L, Howroyd P, Gould S, Chanut F, Burnett R. Histopathological lesions
1063   following intramuscular administration of saline in laboratory rodents and rabbits. Exp Toxicol
1064   Pathol Off J Ges Toxikol Pathol. 2009 Jan;61(1):13–21.

1065   44.   National Toxicology Program [Internet]. [cited 2023 May 24]. Nonneoplastic Lesion Atlas.
1066   Available from: https://ntp.niehs.nih.gov/atlas/nnl

1067   45.   Avior Y, Sagi I, Benvenisty N. Pluripotent stem cells in disease modelling and drug discovery.
1068   Nat Rev Mol Cell Biol. 2016 Mar;17(3):170–82.

1069   46.   Sozzi E, Kajtez J, Bruzelius A, Wesseler MF, Nilsson F, Birtele M, et al. Silk scaffolding drives
1070   self-assembly of functional and mature human brain organoids. Front Cell Dev Biol. 2022 Oct
1071   14;10:1023279.

1072   47.   Hannan NRF, Segeritz CP, Touboul T, Vallier L. Production of hepatocyte like cells from
1073   human pluripotent stem cells. Nat Protoc. 2013 Feb;8(2):430–7.

1074   48.   Klaffky E, Williams R, Yao CC, Ziober B, Kramer R, Sutherland A. Trophoblast-specific
1075   expression and function of the integrin alpha 7 subunit in the peri-implantation mouse embryo.
1076   Dev Biol. 2001 Nov 1;239(1):161–75.

1077   49.   Pook M, Teino I, Kallas A, Maimets T, Ingerpuu S, Jaks V. Changes in Laminin Expression
1078   Pattern during Early Differentiation of Human Embryonic Stem Cells. PloS One.
1079   2015;10(9):e0138346.

1080   50.   Galanakis D, Nuovo G, Spitzer S, Kaplan C, Scharrer I. Fibrinogen mRNA and antigen co-
1081   present in human trophoblasts in situ: possible implications. Thromb Res. 1996 Jan 15;81(2):263–
1082   9.

1083   51.   Weisel JW, Litvinov RI. Fibrin Formation, Structure and Properties. Subcell Biochem.
1084   2017;82:405–56.

1085   52.   Sánchez-Cortés J, Mrksich M. The platelet integrin alphaIIbbeta3 binds to the RGD and AGD
1086   motifs in fibrinogen. Chem Biol. 2009 Sep 25;16(9):990–1000.

1087   53.   Suehiro K, Mizuguchi J, Nishiyama K, Iwanaga S, Farrell DH, Ohtaki S. Fibrinogen binds to
1088   integrin alpha(5)beta(1) via the carboxyl-terminal RGD site of the Aalpha-chain. J Biochem
1089   (Tokyo). 2000 Oct;128(4):705–10.

1090   54.   Wondimu Z, Omrani S, Ishikawa T, Javed F, Oikawa Y, Virtanen I, et al. A Novel Monoclonal
1091   Antibody to Human Laminin α5 Chain Strongly Inhibits Integrin-Mediated Cell Adhesion and
1092   Migration on Laminins 511 and 521. PLOS ONE. 2013 Jan 7;8(1):e53648.

1093   55.   Ishihara J, Ishihara A, Fukunaga K, Sasaki K, White MJV, Briquez PS, et al. Laminin heparin-
1094   binding peptides bind to several growth factors and enhance diabetic wound healing. Nat
1095   Commun. 2018 Jun 4;9(1):2163.

1096   56.   Presser N, Kerr H, Gao T, Begala M, Paschal S, Shoskes DA, et al. Fibrin Glue Injections: A
1097   Minimally Invasive and Cost-Effective Treatment for Post-Renal Transplant Lymphoceles and
1098   Lymph Fistulas. Am J Transplant Off J Am Soc Transplant Am Soc Transpl Surg. 2016
1099   Feb;16(2):694–9.

1100   57.   Gandhi JK, Knudsen T, Hill M, Roy B, Bachman L, Pfannkoch-Andrews C, et al. Human
1101   Fibrinogen for Maintenance and Differentiation of Induced Pluripotent Stem Cells in Two
1102   Dimensions and Three Dimensions. Stem Cells Transl Med. 2019 Feb 15;8(6):512–21.

1103   58.   Duong H, Wu B, Tawil B. Modulation of 3D fibrin matrix stiffness by intrinsic fibrinogen-
1104   thrombin compositions and by extrinsic cellular activity. Tissue Eng Part A. 2009 Jul;15(7):1865–
1105   76.

1106   59.   Frye M, Taddei A, Dierkes C, Martinez-Corral I, Fielden M, Ortsäter H, et al. Matrix stiffness
1107   controls lymphatic vessel formation through regulation of a GATA2-dependent transcriptional
1108   program. Nat Commun. 2018 Apr 17;9(1):1511.

1109   60.   Garcia-Abrego C, Zaunz S, Toprakhisar B, Subramani R, Deschaume O, Jooken S, et al.
1110   Towards Mimicking the Fetal Liver Niche: The Influence of Elasticity and Oxygen Tension on
1111   Hematopoietic Stem/Progenitor Cells Cultured in 3D Fibrin Hydrogels. Int J Mol Sci. 2020
1112   Jan;21(17):6367.

1113   61.   Chowdhury F, Li Y, Poh YC, Yokohama-Tamaki T, Wang N, Tanaka TS. Soft substrates
1114   promote homogeneous self-renewal of embryonic stem cells via downregulating cell-matrix
1115   tractions. PloS One. 2010 Dec 13;5(12):e15655.

1116   62.   Liu J, Tan Y, Zhang H, Zhang Y, Xu P, Chen J, et al. Soft fibrin gels promote selection and
1117   growth of tumourigenic cells. Nat Mater. 2012 Jul 1;11(8):734–41.

1118   63.   Genovese P, Patel A, Ziemkiewicz N, Paoli A, Bruns J, Case N, et al. Co-delivery of fibrin-
1119   laminin hydrogel with mesenchymal stem cell spheroids supports skeletal muscle regeneration
1120   following trauma. J Tissue Eng Regen Med. 2021;15(12):1131–43.

1121   64.   Ziemkiewicz N, Hilliard GM, Dunn AJ, Madsen J, Haas G, Au J, et al. Laminin-111-Enriched
1122   Fibrin Hydrogels Enhance Functional Muscle Regeneration Following Trauma. Tissue Eng Part A.
1123   2022 Apr;28(7–8):297–311.

1124   65.   Nam K, Maruyama CL, Wang CS, Trump BG, Lei P, Andreadis ST, et al. Laminin-111-derived
1125   peptide conjugated fibrin hydrogel restores salivary gland function. PLOS ONE. 2017 Nov
1126   2;12(11):e0187069.

1127   66.   Huch M, Boj SF, Clevers H. Lgr5(+) liver stem cells, hepatic organoids and regenerative
1128   medicine. Regen Med. 2013 Jul;8(4):385–7.

1129   67.   Jha R, Xu RH, Xu C. Efficient Differentiation of Cardiomyocytes from Human Pluripotent Stem
1130   Cells with Growth Factors. Methods Mol Biol Clifton NJ. 2015;1299:115–31.

1131   68.   Rhee YH, Puspita L, Sulistio YA, Kim SW, Vidyawan V, Elvira R, et al. Efficient Neural
1132   Differentiation of hPSCs by Extrinsic Signals Derived from Co-cultured Neural Stem or Precursor
1133   Cells. Mol Ther. 2019 Jul 3;27(7):1299–312.

1134   69.   Lancaster MA, Corsini NS, Wolfinger S, Gustafson EH, Phillips AW, Burkard TR, et al. Guided
1135   self-organization and cortical plate formation in human brain organoids. Nat Biotechnol. 2017
1136   Jul;35(7):659–66.

1137   70.   Dhawan A, Puppi J, Hughes RD, Mitry RR. Human hepatocyte transplantation: current
1138   experience and future challenges. Nat Rev Gastroenterol Hepatol. 2010 May;7(5):288–98.

1139   71.   Forbes SJ, Gupta S, Dhawan A. Cell therapy for liver disease: From liver transplantation to
1140   cell factory. J Hepatol. 2015 Apr;62(1 Suppl):S157-169.

1141   72.   Dhawan A, Chaijitraruch N, Fitzpatrick E, Bansal S, Filippi C, Lehec SC, et al. Alginate
1142   microencapsulated human hepatocytes for the treatment of acute liver failure in children. J
1143   Hepatol. 2020 May;72(5):877–84.

1144   73.   Zhao T, Zhang ZN, Rong Z, Xu Y. Immunogenicity of induced pluripotent stem cells. Nature.
1145   2011 May 13;474(7350):212–5.

1146   74.   Tricot T, Verfaillie CM, Kumar M. Current Status and Challenges of Human Induced
1147   Pluripotent Stem Cell-Derived Liver Models in Drug Discovery. Cells. 2022 Jan;11(3):442.

1148   75.   Mallanna SK, Duncan SA. Differentiation of hepatocytes from pluripotent stem cells. Curr
1149   Protoc Stem Cell Biol. 2013 Sep 20;26:1G.4.1-1G.4.13.

1150   76.   Cheung C, Bernardo AS, Pedersen RA, Sinha S. Directed differentiation of embryonic origin-
1151   specific vascular smooth muscle subtypes from human pluripotent stem cells. Nat Protoc. 2014
1152   Apr;9(4):929–38.

1153   77.   Burridge PW, Holmström A, Wu JC. Chemically Defined Culture and Cardiomyocyte
1154   Differentiation of Human Pluripotent Stem Cells. Curr Protoc Hum Genet. 2015 Oct 6;87:21.3.1-
1155   21.3.15.

1156   78.   Tyzack GE, Sitnikov S, Barson D, Adams-Carr KL, Lau NK, Kwok JC, et al. Astrocyte response to
1157   motor neuron injury promotes structural synaptic plasticity via STAT3-regulated TSP-1 expression.
1158   Nat Commun. 2014 Jul 11;5:4294.

1159   79.   Katarivas Levy G, Ong J, Birch MA, Justin AW, Markaki AE. Albumin-Enriched Fibrin Hydrogel
1160   Embedded in Active Ferromagnetic Networks Improves Osteoblast Differentiation and Vascular
1161   Self-Organisation. Polymers. 2019 Oct 24;11(11):1743.

1162   80.   Varley MC, Neelakantan S, Clyne TW, Dean J, Brooks RA, Markaki AE. Cell structure, stiffness
1163   and permeability of freeze-dried collagen scaffolds in dry and hydrated states. Acta Biomater.
1164   2016 Mar;33:166–75.

1165   81.   Kitajima M, Kimura A, Suzuki H. Cutting Edge: Nqo1 Regulates Irritant Contact
1166   Hypersensitivity against Croton Oil through Maintenance of Dendritic Epidermal T Cells. J
1167   Immunol Baltim Md 1950. 2018 Mar 1;200(5):1555–9.

1168

Figure 1. A) Schematic of workflow. B) Automated pipeline identifying hPSC colonies as pluripotent stem cells; green = positive selection by machine learning, scale bar = 100 μm. C) Machine learning identifying human fibroblasts as non-pluripotent cells (red); scale bar = 100 μm. D) Machine learning discriminating undifferentiated hPSCs (green) from spontaneously differentiated hPSCs (red) after intentionally extended culture to trigger spontaneous differentiation (Day 9), scale bar = 200 μm. E) A Receiver Operator Characteristic curve showing excellent discriminatory performance of our machine-learning platform with an Area Under the Curve (AUC) of 0.977.

Figure 2. A) hPSC confluence in 2D growth factor reduced Matrigel (Geltrex), Laminin 521, fibrin-laminin hydrogel, and fibrin gel after 4 days. Scale bar = 100 μm. B) hPSCs cultured in 3D hydrogels. Top panel: Fibrin (5 mg/mL) gel. Bottom panel: Alphagel containing structures resembling embryoid bodies, scale bar = 200 μm. SEM of (C) fibrin gel and (D) Alphagel, scale bar = 1 μm, magnification 20K X, iProbe = 13 pA, 2.00 kV, WD = 4.4 mm for both images. E) Young's moduli in hydrogels with varying fibrin and laminin concentrations. One-way ANOVA; ** = $p < 0.01$, *** = $p < 0.001$, and **** = $p < 0.0001$. F) Cell viability of hPSCs cultured in Alphagel, fibrin-only hydrogels, and 2D standard substrates. Mean ± S.E.M displayed. t-test; * = $p < 0.05$. G) ELISA of Laminin 521 in culture media used with acellular Alphagel and H) the calculated amount of fibrin-bound laminin over time.

continued

Figure 3: A) Macroscopic and microscopic appearances of cells in Alphagel. Contractile cardiomyocyte colonies (*) are visible by Day 6. By Day 14 contractile tissue resembling trabeculae carnae is observed. Scale bar: full line = 100 μm, dotted line = 1 cm. B) Troponin T (TnT), alpha-smooth muscle actin (α-SMA), and DAPI in cardiomyocytes cultured with Alphagel. Scale bar = 100 μm (fibres), 50 μm (colonies), and 20 μm (cells). C) Alphagel-derived neuroepithelia expressing β catenin (CTNNB1), SOX2 and Nestin. Arrows indicate apical zones demarcated by β catenin. Scale bar = 100 μm. D) Average lumen area of neuroepithelia in Alphagel, fibrin gel, and neurospheres (Matrigel). E) Frequency of polarized puncta per mm^2. The Kruskal-Wallis test was used for (D) and (E). *** = p < 0.001, and **** = p < 0.0001.

Figure 4: A) Key hepatocyte markers in Alphagel-derived iHeps. ALB = albumin, HNF = Hepatocyte Nuclear Factor, CYP2A6 = Cytochrome 2A6, CD147 = Cluster of Differentiation protein 147, and E-CAD = E-cadherin. Scale bar = 25 μm. B) Key hepatocyte markers by gene expression (qPCR). C) Albumin secretion (ELISA) and D) CYP3A4 activity (P450-Glo^{TM}) in PHH vs iHeps cultured in various gels (Day 22). HCM = Hepatocyte Culture Media (Lonza). (E) LDL uptake (red) in Alphagel-derived iHeps versus hPSCs. Scale bar = 100 μm. F) CDFDA secretion (green) in Alphagel-derived iHeps vs hPSCs. Top panel scale bar = 20 μm, bottom panel scale bar = 50 μm. One-way ANOVA was used; * = $p < 0.05$, ** = $p < 0.01$, *** = $p < 0.001$, and **** = $p < 0.0001$.

Inflammation Severity

	Week 1: Grade (Score)	Week 2: Grade (Score)	Weeks 4-6: Grade (Score)
1% Croton oil	Severe (13.3 ± 2.5)	Severe (14.7 ± 4.0)	Culled (N/A)
Alphagel	Mild (4.3 ± 1.5)	Minimal (3.3 ± 0.6)	Normal (0)
0.9% Saline	Minimal (0.25 ± 0.05)	Normal (0)	Normal (0)

Figure 5: A) H&E stains of sites injected with 1% Croton Oil, Alphagel, and 0.9% Saline at 1 and 2 weeks. Black arrow denotes areas of granulation and inflammation, * denotes necrotic and degenerating muscle fibres, and # denotes supportive changes around affected muscle fibres. Scale bar = 200 μm. B) H&E stain of Alphagel injection site after 6 weeks showing complete resolution of previously mild inflammation. Scale bar = 200 μm. C) Histological grade and scores of injection sites over 6 weeks. One-way ANOVA; * = p < 0.05, ** = p < 0.01, *** = p < 0.001, and **** = p < 0.0001.

Figure 6: A) Differentially expressed genes in iHeps; Hepatologel, Alphagel, Matrigel, and adult primary human hepatocytes (PHH). B) Albumin ELISA of culture media and C) Luciferin-based measure of CYP3A4 activity; 2 days after completion of iHep differentiation and 2 days after plating PHH. One-way ANOVA; * = p < 0.05, ** = p < 0.01, *** = p < 0.001, and **** = p < 0.0001. D) Mouse livers 3 days after intra-hepatic injection with H-iHeps in Hepatogel and 0.9% saline. Red box = area magnified. * = site of injection, dotted white lines demarcate engrafted cell mass, scale bar = 1 mm. E) Human albumin (stained red) in engrafted iHeps 3 days after intra-hepatic injection. Scale bar = 100 μm. F) H-iHeps identified by albumin staining on liver histology 3 days after intra-hepatic injection. G) ELISA of mouse serum for human albumin after injection with H-iHeps in Hepatogel and 0.9% saline over time. Day 0 = serum levels before injection. T-test; *** = p < 0.001, and **** = p < 0.0001.