# Nanoporous Platinum Microelectrode Arrays for Neuroscience Applications

**Nicolai Winter-Hjelm**[1,✉]**, Leik Isdal**[2]**, Peter A. Köllensperger**[3]**, Axel Sandvig**[1,4]**, Ioanna Sandvig**[1]**, and Pawel Sikorski**[2,✉]

[1]Department of Neuromedicine and Movement Science, Faculty of Medicine and Health Sciences, Norwegian University of Science and Technology (NTNU), Norway
[2]Department of Physics, Faculty of Natural Sciences, Norwegian University of Science and Technology (NTNU), Trondheim, Norway
[3]NTNU NanoLab, Norwegian University of Science and Technology (NTNU), Trondheim, Norway
[4]Department of Neurology and Clinical Neurophysiology, St Olav´s University Hospital, Trondheim, Norway

## Abstract

**Microelectrode arrays are invaluable tools for investigating the electrophysiological behaviour of neuronal networks with high spatiotemporal precision. In recent years, it has become increasingly common to functionalize such electrodes with highly porous platinum to increase their effective surface area, and hence their signal-to-noise ratio. Although such functionalization significantly improves the electrochemical performance of the electrodes, the impact of various electrode morphologies on biocompatibility and electrophysiological performance in cell cultures remains poorly understood. In this study, we introduce reproducible protocols for depositing highly porous platinum with varying morphologies on microelectrodes designed for neural cell cultures. We also evaluate the impact of morphology and electrode size on the signal-to-noise ratio in recordings from rat cortical neurons cultured on these electrodes. Our results indicate that electrodes with a uniform layer of highly nanoporous platinum offer the best trade-off between biocompatibility, electrochemical, and electrophysiological performance. While more microporous electrodes exhibited lower impedance, nanoporous electrodes detected higher extracellular signal amplitudes from neurons, suggesting reduced distance between perisomatic neuronal areas and the electrodes. Additionally, these nanoporous electrodes showed fewer thickness variations at their edges compared to the more porous electrodes. Such edges can be mechanically broken off during cell culturing and contribute to long-term cytotoxic effects, which is highly undesirable. We hope this work will contribute to better standardization in creating and utilizing nanoporous platinum microelectrodes for neuroscience applications. Improving the accessibility and reproducibility of this technology is crucial for enhancing the quality of electrophysiological data and advancing our understanding of neuronal network function and dysfunction.**

Neuroengineering | Platinum black | MEA | In Vitro | Electrophysiology | Bioelectronics

**Correspondence:** *nicolai.winter-hjelm@ntnu.no & pawel.sikorski@ntnu.no*

## Introduction

Microelectrode arrays (MEAs) are extensively used to study neuronal signaling and behaviour from the cellular to the network level (1). These microelectrodes detect voltage fluctuations caused by propagating action potentials, commonly referred to as spikes, with high temporal precision. By monitoring the spiking activity of tens to thousands of neurons simultaneously, key principles of neuronal function and dysfunction can be deciphered (2, 3). Optimizing MEAs for high-quality neuronal recordings typically involves a trade-off between high selectivity and a high signal-to-noise ratio (SNR). Ideally, electrodes should be the size of individual neurons, ranging from 10 to $100\,\mu m$, to ensure high selectivity. However, the electrode surface area is inversely proportional to impedance. To increase SNR without increasing electrode diameter, porous platinum has been employed (4–6), including the functionalization of microelectrodes for neuroscience applications (7–11). Porous platinum, also known as platinum black, is highly permeable platinum that absorbs a large portion of incoming light, appearing black under a microscope (12, 13). Its high porosity creates a large electrochemically active surface area, significantly reducing electrode impedance. The increased surface area additionally generates higher currents in response to applied potentials, allowing for lower voltages to stimulate neuronal networks. Consequently, the likelihood of exceeding the so-called water window is reduced. Exceeding this threshold can trigger oxidation and reduction reactions, leading to electrolysis, which can be detrimental to nearby biological tissues (8). Thus, porous platinum can substantially enhance both the electrophysiological performance and biocompatibility of extracellular microelectrodes.

Platinum black can be formed through various fabrication methods, ranging from bottom-up electrochemical synthesis to laser roughening (14, 15). These methods yield surfaces with a range of morphologies (16, 17). One of the most reliable methods for forming platinum black is electrochemical deposition, also know as electroplating (7, 8, 18, 19). In this process, electrodes are submerged in a liquid containing platinum ions, typically chloroplatinic acid (20). An external potential is applied to electrochemically reduce the platinum ions, which then form nuclei and grow into dendritic protrusions. Traditionally, additives such as lead have been introduced to the bath. While the exact nucleation and growth mechanisms of platinum nano- and microstructures are not fully understood, various additives are believed to either inhibit the growth of platinum islands (21) or assist in electron transfer between the electrode and the platinum ions (22, 23). However, these additives can leak into cell media and induce cytotoxicity, and they complicate the deposition process due to the complexity of the electrochemical reactions involved (10). In 2015, Boehler *et al.* introduced an alternative process using formic acid in the electrolyte solution, proposed to have less impact on cell viability (8). Later, they demonstrated that depositions could occur even without any additives (10).

A challenge in fabricating porous microelectrodes is the un-

predictability of the deposition process, which can result in heterogeneous metallic protrusions across the surface. Many publications report using platinum black electrodes without characterizing their morphology or biocompatibility. The deposition kinetics often lead to the formation of high, irregular edges, commonly referred to as edge effects, that can impede neuronal growth and increase the neuron-electrode junction size. While signals can still be acquired from neurons near the electrodes, these edges prevent neurons from growing directly on top of the electrodes. Additionally, these metallic protrusions can break off during fabrication or use with cell cultures. Although platinum is widely used in biological and medical electrode applications due to its inertness and high electrical conductivity (24), studies have shown that platinum nanoparticles can cause cytotoxic and inflammatory effects in neurons both *ex vivo* and *in vivo* (25, 26). Therefore, it is desirable to have uniformly layered platinum deposits without discernible protrusions that could break off. Wang *et al.* demonstrated that such electrodes could be achieved by applying constant currents to the electrodeposition system (11). However, using constant current for electroplating presents challenges, as the same deposition parameters cannot be reliably used for different electrode sizes or heights (i.e., deposition times). This is because the depositions continuously change the surface area and thus the current distribution in the system. This variability makes the depositions highly inconsistent, as even minor changes in electrode conditions can lead to significant variations in the morphologies of the platinum deposits. Therefore, more reproducible and standardized protocols are needed for creating nanoporous microelectrodes for neuroscience applications.

In this study, we present a reproducible method for fabricating nanoporous, biocompatible microelectrodes with uniform thickness for bioelectronic applications. We compare various electrochemical deposition schemes to demonstrate their impact on the nucleation and growth of nanoporous platinum and evaluate their electrochemical performance. Additionally, we investigate how the resulting structures affect electrophysiological recordings from cultured neurons. Ultimately, we propose an optimal deposition scheme that balances biocompatibility, electrochemical performance, and electrophysiological performance for use in neuronal recordings.

## Materials and Methods

**Design of Experimental Interfaces.** Designs for all utilized interfaces were created using Clewin 4 (WieWeb Software, Enschede), and are shown in **Figure S1**. To optimize the electrochemical deposition parameters and characterization, 20 electrodes were connected to individual contact pads along the periphery of a 4" wafer (**Figure S1A**). Electrodes with diameters ranging from $10\,\mu m$ to $100\,\mu m$ were used for optimizing deposition parameters, while all electrochemical characterizations were conducted using $30\,\mu m$ diameter electrodes. The metal layer was made $5\,\mu m$ wider than the etching layer to increase alignment tolerance. For electrodes to be tested with neural cell cultures, designs were made compat-

ible with a MEA2100 workstation from Multichannel Systems. These platforms (n = 6) consisted of 59 electrodes with $30\,\mu m$ diameter and $600\,\mu m$ interspace (**Figure S1B**). 1/3 of the electrodes acted as planar controls, 1/3 were electroplated with nanoporous platinum at $-0.4\,V$, and 1/3 were electroplated with microporous platinum at $-0.3\,V$. Each electrode was connected to a contact pad compatible with the recording hardware. Larger contact pads positioned at the periphery of the wafer connected up to 15 electrodes each to the potentiostat during electroplating. These connections were broken once the wafers were diced into 49 x 49 mm substrates compatible with the MEA2100 workstation. $6.0\,mm$ diameter PDMS chambers were used as cell compartments. Samples for scanning electron microscopy were created with 520 planar control electrodes, 520 electrodes electroplated with platinum at $-0.4\,V$, and 520 electrodes electroplated at $-0.3\,V$ (**Figure S1C**).

**Fabrication of Microelectrode Arrays.** The protocol for fabricating MEAs was adapted from our previous work (27, 28) and modified to support electrochemical depositions of platinum. An illustration of the fabrication steps is shown in **Figure 1A**.

MEAs were fabricated on $1\,mm$ thick 4-inch borosilicate wafers ($100\,mm$ Borofloat33, Plan Optik). First, the wafers were washed in acetone and IPA for $1\,min$ each to remove organic contaminants, followed by a $5\,min$ plasma clean in $100\,sccm$ $O_2$ plasma at $20\,kHz$ generator frequency (Femto Plasma Cleaner, Diener Electronics). The wafers were then dehydration baked at $100\,°C$ for $2\,min$ to remove moisture. A $4\,\mu m$ thick layer of the photoresist ma-N 440 (micro resist Technology GmbH) was spin coated onto the substrates at $3000\,rpm$ for $42\,s$ with a ramp rate of $500\,rpm/min$ (spin150, SPS-Europe B.V.). The films were left to rest for $10\,min$ before a soft bake was conducted at $95\,°C$ for $5\,min$. For exposures of the design, a maskless aligner (MLA150, Heidelberg) with a $405\,nm$ laser at $1800\,mJ/cm^2$ was used. Development was conducted in ma-D332/s (micro resist Technology GmbH) for $90 \pm 10\,s$, followed by thorough rinsing in deionized (DI) water. Next, a short descum was performed using $100\,sccm$ $O_2$ plasma for $1\,min$ at $20\,kHz$ generator frequency. A $50\,nm$ titanium adhesion layer was then evaporated onto the substrates at $5\,Å\,s^{-1}$, followed by $100\,nm$ platinum at $2\,Å\,s^{-1}$ (E-beam Evaporator, Pfeiffer Vacuum Classic 500). Finally, a lift-off step was conducted in acetone, followed by a thorough rinse in IPA.

Another $1\,min$ descum was conducted prior to the deposition of a passivation layer. Subsequently, $470\,nm$ silicon nitride ($Si_3N_4$) was deposited on the substrates using plasma-enhanced chemical vapour deposition (PECVD) at $300\,°C$ for $30\,min$ with $20.0\,sccm$ $SiH_4$, $20.0\,sccm$ $NH_3$, and $980\,sccm$ $N_2$ gas (PlasmaLab System 100-PECVD, Oxford Instruments). Thereafter, an etch mask was created using a second layer of ma-N 440, following the same protocol as previously described. Finally, the silicon nitride above the electrodes and contact pads was dry etched using inductively coupled plasma (ICP) with $50.0\,sccm$ $CHF_3$, $10.0\,sccm$ $CF_4$, and $7.0\,sccm$ $O_2$ gas for $6.5\,min$ (Plasmalab System 100 ICP-

RIE 180, Oxford Instruments).

**Electroplating of Porous Platinum.** A PP-Type Wafer Plating Laboratory System from Yamamoto was used for electrodepositions. The electrolyte solution consisted of aqueous $2.5\,\mathrm{mmol}$ chloroplatinic acid ($H_2PtCl_6$, $8\,\mathrm{wt\%}$ $H_2O$, Sigma-Aldrich, 262587). In some experiments, $1.5\,\mathrm{mmol}$ formic acid (HCOOH, $95\%$, Sigma-Aldrich, W248703) was added to the bath as an additive. A custom-built wafer holder was used to position the wafer in the electrolyte bath so that the liquid covered the working electrodes but not the contact pads (**Figure 1A**). A Red Rod REF201 Ag/AgCl electrode (Hatch) was used as the reference electrode, and a platinized titanium plate served as the counter electrode. An external temperature controller maintained the temperature at $30\,^{\circ}\mathrm{C}$. A paddle agitator, placed between the working electrode and the counter electrode, was kept at $60.0\,\mathrm{rpm}$ to reduce the diffusion layer thickness. A PalmSens 4 potentiostat (PalmSens) was used in various modes, including chronoamperometric, chronopotentiometric, linear sweep voltammetry, and cyclic voltammetry, for all depositions.

**Preparation of PDMS Compartments for Cell Experiments.** To prepare PDMS compartments for the cell cultures, silicon elastomer and curing agent (SYLGARD®184 elastomer kit, Dow Corning) were mixed, degassed, and cast at a ratio of 10:1 on top of a precleaned 4-inch silicon wafer (Siltronix). The PDMS was then cured at $65\,^{\circ}\mathrm{C}$ for $4\,\mathrm{h}$ (TS8056, Termaks). After curing, the PDMS was peeled from the mold, and a $6\,\mathrm{mm}$ diameter punch was used to cut out the cell compartments. Debris was removed from the PDMS chips using scotch tape, and the chips were washed successively in acetone, $96\%$ ethanol, and DI water for $1\,\mathrm{min}$ each. Prior to bonding, the chips were left to dry overnight in a fume hood.

**Assembly of Microdevices.** The MEAs were cut into 49 x 49 mm substrates compatible with the Multichannel head stage using a wafer saw (DAD323, DISCO). Following this, the ma-N 440 layer was removed using acetone and IPA. A $10\,\mathrm{min}$ plasma clean was conducted using $160\,\mathrm{sccm}$ $O_2$ at $32\,\mathrm{kHz}$ generator frequency to remove hardened photoresist and oxidize the top nanometers of the silicon nitride layer into silicon dioxide ($SiO_2$). To activate the surfaces of the PDMS device and MEA for bonding, an $O_2$ plasma treatment was conducted using $200\,\mathrm{sccm}$ $O_2$ plasma at $40\,\mathrm{kHz}$ generator frequency for $1\,\mathrm{min}$. Subsequently, two drops of $70\%$ ethanol were placed between the MEA and the PDMS chip, facilitating alignment of the PDMS compartment above the microelectrodes under a stereomicroscope. The bonding was completed on a hotplate at $100\,^{\circ}\mathrm{C}$ for $90\,\mathrm{s}$, followed by $5\,\mathrm{min}$ at room temperature under gentle pressure. DI water was used to wash out any remaining traces of ethanol and to keep the surfaces of the MEAs hydrophilic. Prior to cell culturing, the devices were sterilized under UV light in a biosafety cabinet for at least $60\,\mathrm{min}$.

**Electrochemical Characterization.** As the electrolyte, $0.1\,\mathrm{M}$ Dulbecco's Phosphate Buffered Saline (DPBS)

(Sigma-Aldrich, D8537) was used. A custom-built wafer holder was employed to position the wafer in the electrolyte bath, ensuring the liquid covered the working electrodes but not the contact pads. A Red Rod REF201 Ag/AgCl electrode (Hatch) was used as the reference electrode, and a platinized titanium plate served as the counter electrode. A PalmSens 4 potentiostat (PalmSens) was used to perform electrochemical impedance spectroscopy (EIS) measurements. Nine electrodes of each condition were analyzed, and the average curve of the nine electrodes was plotted. An equilibration time of $8\,\mathrm{ms}$ was set. Measurements were performed against the open circuit potential (OCP), with the constant potential (E dc) set to $0\,\mathrm{V}$. An alternating sine wave of $100\,\mathrm{mV}$ was superimposed on the constant potential. This amplitude was set high to avoid issues with noise at low frequencies and was confirmed not to impact the linearity of the system. The OCP was measured prior to the EIS scan with a maximum time of $3\,\mathrm{s}$. A stability criterion of $0.5\,\mathrm{mV\,s^{-1}}$ was chosen. Impedance was measured in the range from 100,000 to $0.1\,\mathrm{Hz}$ with 10 measurement points per decade on a logarithmic scale. Data from the EIS measurements were validated using the Lin-KK method, based on the Kramers-Kronig (KK) compliant equivalent circuit (29).

**Coating, Cell Plating and Maintenance.** An overview of the timeline for the cell experiments can be seen in **Figure 1B**. After sterilization and prior to coating the surfaces, the samples were soaked in DMEM, low glucose (Gibco™, 11885084) for at least $48\,\mathrm{h}$ to remove any potential uncured PDMS. The cell medium was then replaced with $0.1\,\mathrm{mg/mL}$ Poly-L-Ornithine (PLO) solution (Sigma-Aldrich, A-004-C), and the chips were incubated in a refrigerator at $4\,^{\circ}\mathrm{C}$ overnight. The following day, the chambers were washed three times with MQ water before being filled with laminin solution consisting of $16\,\mathrm{\mu g/mL}$ natural mouse laminin (Gibco™, 23017015) in phosphate-buffered saline (PBS, Sigma-Aldrich, D8537). The samples were then incubated at $37\,^{\circ}\mathrm{C}$ with $5\%$ $CO_2$ for $2\,\mathrm{h}$.

Following coating, the laminin solution was replaced with pre-warmed astrocyte medium consisting of DMEM, low glucose, supplemented with $15\%$ Fetal Bovine Serum (Sigma-Aldrich, F9665) and $2\%$ Penicillin-Streptomycin (Sigma-Aldrich, P4333). Rat astrocytes (Gibco™, N7745100) were then plated at a density of $100\,\mathrm{cells/mm^2}$, equalling 4000 cells per culturing chamber. After two days of expansion, the astrocyte medium was replaced with neuronal medium consisting of Neurobasal Plus Medium (Gibco™, A3582801), supplemented with $2\%$ B27 Plus (Gibco™, A358201), $1\%$ GlutaMax (Gibco™, 35050038), and $2\%$ Penicillin-Streptomycin (Sigma-Aldrich, P4333). Additionally, Rock Inhibitor (Y-27632 dihydrochloride, Y0503, Sigma-Aldrich) was added at a concentration of $0.1\%$ during plating to increase the survival rate. Rat cortical neurons from Sprague Dawley rats (Gibco, A36511) were plated at a density of $1000\,\mathrm{cells/mm^2}$, equalling 40,000 cells per chamber. Half of the cell medium was replaced with fresh medium $4\,\mathrm{h}$ after plating, and again after $24\,\mathrm{h}$. From then on, half of the cell medium was replaced every second

day until the cultures were ended at 28 days *in vitro* (DIV). All astrocytes and neurons were from the same batch and cell vials to avoid biases caused by batch-to-batch variability.

**Electron Microscopy.** To prepare biological samples for imaging, the cells were fixed using $2.5\%$ glutaraldehyde (G5882, Sigma-Aldrich) in Sorensen's phosphate buffer ($0.1$ M, pH 7.2) for at least $24$ h. Initially, the cells were left in the fixative at room temperature for the first $2$ h, followed by storage at $4\,°C$ until chemical dehydration. Subsequently, a chemical serial dehydration was conducted using $25\%$, $50\%$, $70\%$, $80\%$, $90\%$, and $100\%$ (x2) ethanol for $5$ min each. The ethanol was then replaced by $CO_2$ with critical point drying (EM CPD300 Critical Point Dryer, Leica). For this process, the delay time was set to $120$ s, the exchange speed to 1, the number of cycles to 18, and the gas outflow speed to $50\%$ (slow). To make the samples conductive, $15$ nm of platinum/palladium was deposited on the samples using a 208 HR B Sputter Coater from Cressington. These depositions were conducted cyclically from $-45°$ to $45°$ with a period of $20$ s. All electron microscopy imaging was performed using an APREO Field Emission Scanning Electron Microscope from FEI. The samples were connected to the stage using copper tape. Imaging was conducted using secondary electrons detected with an EDT detector, with the beam current set between $25$–$50$ pA, and the acceleration voltage between $4.0$–$10.0$ kV.

**Electrophysiological Recordings.** A MEA2100 workstation (Multichannel Systems) was used for recordings of neuronal activity, with the sampling rate set to $25\,000$ Hz. Furthermore, the temperature was maintained at $37\,°C$ using a temperature controller (TC01, Multichannel Systems). To maintain sterility during recordings, a 3D-printed plastic cap with a gas-permeable membrane was employed. Prior to recordings, the neuronal networks were allowed to equilibrate for $5$ min at the recording stage. Subsequently, neuronal activity was recorded for $15$ min. All recordings were conducted $24$ h following media changes.

**Data Analysis and Statistical Analysis.** Data analysis was performed using Matlab R2021b. To preprocess the data, a 4th order Butterworth bandpass filter was applied to eliminate frequencies below $300$ Hz and above $3000$ Hz. Additionally, noise originating from the power supply mains at $50$ Hz was attenuated using a notch filter. These filters were implemented using zero-phase digital filtering to mitigate group delay in the output signal. For spike detection, the Precise Timing Spike Detection (PTSD) algorithm developed by Maccione *et al.* (30) was employed. The data was thresholded at 9 times the standard deviation of the noise, with the maximum peak duration and refractory time set to $1$ ms and $1.6$ ms, respectively. Color maps for plotting were generated using the Matlab function *linspecer* (31), which is based on the web tool colorBrewer developed by Brewer *et al.* (32). All statistical analyses were conducted in Matlab R2021b using a two-sided Wilcoxon rank sum test.

## Results

**Applied Deposition Potential Determines the Electrode Porosity.** To evaluate the impact of the applied deposition potential on the porosity of platinum microelectrodes, chronoamperometric depositions were conducted in the range from $0$ V to $-0.4$ V. The porosity increased with reduced deposition potential down to $-0.3$ V, as indicated by the darker color and more discernible thickness variations at the electrode periphery when viewed under a microscope (**Figure 2A**). While the amount of deposited platinum was highest at $-0.4$ V, the light absorbance was less pronounced, indicating lower porosity than at $-0.2$ V and $-0.3$ V (**Figure 2A**). SEM imaging was used to further compare the nano- and microstructures of the electrodes. Planar control electrodes had a flat surface (**Figure 2B**), whereas electrodes electroplated at $0$ V displayed a substantial number of evenly dispersed globular nuclei (**Figure 2C**). At $-0.1$ V, larger globular nuclei up to $300$ nm formed with clearly distinguishable grain boundaries (**Figure 2D**). As the deposition potential was further reduced to $-0.2$ V and $-0.3$ V, scattered secondary nuclei resulted in more ramified and heterogeneous structures with significantly taller platinum deposits at the edges than at the centers (**Figures 2E** and **2F**). At $-0.4$ V, significant nucleation and growth still occurred, but with smaller, more evenly dispersed dendrites, producing nanoscale pores (**Figure 2G**). The variations in deposit morphology at different electroplating potentials can be explained by a transition from a charge transfer-limited regime at lower potentials to a more mass transport-limited regime with increased overpotential (**Figure 2H**) (16).

To characterize the impact of the formed structures on the electrodes´ impedance, EIS measurements were conducted in PBS solution over a range from $100$ kHz to $0.1$ Hz. All the nano- and microporous electrodes exhibited impedances´ one to two orders of magnitude lower than the control electrodes (**Figure 2I**). At the lowest frequency, $0.1$ Hz, the electrodes electroplated at $-0.2$ V and $-0.3$ V performed the best, with 63 and 35 times lower impedances compared to the planar controls, respectively. Among the porous electrodes, those deposited at $-0.4$ V had the highest impedance, yet still 11 times lower than the control electrodes. At higher frequencies, where spikes are typically detected ($300$ Hz to $3000$ Hz), the electrodes electroplated at $-0.3$ V had the lowest overall impedance, with at least 9.7 times lower impedance than the controls. The electrodes electroplated at $-0.4$ V had at least 5.3 times lower impedance than the controls in this frequency range. Combined with the imaging results, these findings clearly show that all the porous electrodes had a significantly larger electroactive surface area compared to the controls, leading to substantially reduced impedances.

**Chronoamperometric Depositions Yield Consistent Porosity Irrespective of the Electrode Size.** An important consideration when designing microelectrodes for neuronal recordings is the electrode size. Larger electrodes increase the likelihood of neurons positioning themselves on or near the electrodes, while smaller electrodes provide higher

**Figure 1 | Experimental Setup.** **(A.)** Illustration of the fabrication procedure for creating microelectrode arrays with electroplated porous platinum. **(B.)** Experimental timeline for cell experiments with co-cultures of primary rat cortical neurons and astrocytes. Each utilized platform had 1/3 planar control electrodes, 1/3 highly microporous, heterogeneous electrodes electroplated at $-0.3\,V$, and 1/3 highly nanoporous, evenly layered electrodes electroplated at $-0.4\,V$. Electrophysiological recordings were conducted at 14 and 28 *days in vitro* (DIV) for $15\,min$ each.

**Figure 2 | Nano- and microporous platinum electroplated using chronoamperometry**. **(A.)** Optical microscopy images showing the increase in porosity, and hence light absorbance, of the electroplated electrodes with decreasing voltage down to $-0.3\,V$. Although the amount of deposited platinum increased with further reduction in deposition potential, the porosity appeared to decrease beyond $-0.3\,V$. **(B.)** Control electrode prior to electrochemical deposition of platinum. **(C.) - (G.)** SEM micrographs of $30\,\mu m$ diameter electrodes electroplated at $0\,V$, $-0.1\,V$, $-0.2\,V$, $-0.3\,V$ and $-0.4\,V$, respectively. The micrographs reveal that electroplating at $-0.2\,V$ and $-0.3\,V$ produced the most porous electrodes with noticeable edge effects. Electroplating at $-0.4\,V$ resulted in evenly layered, highly nanoporous structures. **(H.)** Illustration depicting the mass transport limited nucleation and growth of platinum on the microelectrodes, with local and global depletion zones forming around the nucleation sites, promoting high porosity. **(I.)** Electrochemical Impedance Spectroscopy (EIS) measurements confirmed that increased electrode porosity, due to a higher electroactive surface area, resulted in lowered impedance.

selectivity by recording from fewer neurons. Establishing a reliable fabrication protocol is crucial for ensuring that the electrochemical deposition process creates porous structures with consistent thickness and without discernible edge effects, regardless of the working electrode size. In this study, different deposition parameters were tested on electrodes of various sizes relevant for electrophysiological recordings, ranging from $10\,\mu m$ to $100\,\mu m$. When chronoamperometric depositions were performed at $-0.4\,V$, evenly layered nanoporous platinum was formed regardless of electrode size (**Figures 3A** - **3D**). The electroplated structures were also consistent and independent of electrode size for depositions at $-0.2\,V$ and $-0.3\,V$, producing the most microporous electrodes (**Figure S2**). However, compared to electrodes plated at $-0.4\,V$, these electrodes exhibited more distinct edge effects, particularly for the smallest electrodes between $10\,\mu m$ to $30\,\mu m$ in diameter. In contrast, chronopotentiometric depositions resulted in electrode porosity that was clearly dependent on electrode size (**Figures 3E** - **3H**). This can be attributed to the continuously increasing surface area over time, which disperses the applied constant current over a larger total surface area. This made smaller electrodes ($10\,\mu m$ to $30\,\mu m$ in diameter) more prone to extensive platinum growth of along their edges compared to their centers (**Figures 3E** and **3F**). These results demonstrate that chronoamperometry facilitates more reproducible and consistent electroplating independent of electrode size compared to chronopotentiometry.

To assess the impact of electrode size on performance in electrophysiological recordings of neurons, cells were plated on MEAs with electrodes electroplated at $-0.4\,V$ ranging from $10\,\mu m$ to $100\,\mu m$ in diameter, randomly distributed across the interfaces. Recordings conducted during early maturation at 14 DIV indicated a clear dependence of electrode size on the percentage of active electrodes, i.e., electrodes showing strong coupling with one or several neurons (**Figure 4A**). Electrodes with a $100\,\mu m$ diameter had over $90\,\%$ active electrodes, while those $50\,\mu m$ or smaller had less than $60\,\%$ active electrodes at this time point. By 26 DIV, when the networks had matured, electrodes $30\,\mu m$ or larger approached $100\,\%$ active electrodes, whereas electrodes of $10\,\mu m$ and $20\,\mu m$ in diameter had above $60\,\%$ active electrodes. The SNR followed a similar trend, with significantly higher SNR for larger electrodes at 14 DIV, and a non-significant but higher SNR at 26 DIV (**Figure 4B**). Conversely, the median spike amplitude and variance in the noise band showed higher amplitudes and lower noise variance for smaller electrodes (**Figures 4C** and **4D**, respectively). These findings underscore the importance of balancing selectivity and electrochemical performance when selecting electrode size.

**Chronoamperometric Depositions Yield Consistent Porosity Irrespective of Deposition Time.** In addition to the applied voltage or current amplitude, deposition time is a crucial parameter in electrochemical depositions. To evaluate its impact on the final nano- and microstructures, chronoamperometric and chronopotentiometric depositions were conducted for varying durations. Chronoamperometric deposi-

tions at $-0.4\,V$ were performed for periods ranging from $2\,min$ to $10\,min$. These depositions produced evenly layered, nanoporous structures without discernible edge effects on the electrodes, irrespective of the deposition time (**Figures 5A** and **5B**). Conversely, chronopotentiometric depositions resulted in larger, globular structures as the deposition time increased (**Figures 5C** - **5F**). After $30\,min$ of electroplating, the initial nuclei had merged into a homogeneously layered surface with distinguishable grain boundaries (**Figure 5F**). Additionally, edge effects became significantly more prevalent with longer deposition times for these electrodes. These findings underscore the versatility of chronoamperometric depositions, as the process yields the same electrode porosity independent of deposition time and electrode size.

**Addition of Formic Acid and Application of Dynamic Deposition Schemes Decrease Reproducibility of the Electroplating.** Additives such as lead acetate or formic acid are commonly added to the electrolyte bath to facilitate nucleation and improve the adhesion of the porous platinum deposits (8, 33). To evaluate the impact of additives in the electrolyte bath, formic acid (HCOOH) was included in the electrolyte solution prior to performing chronoamperometric depositions between $0\,V$ to $-0.4\,V$. While the addition of HCOOH promoted the growth of highly porous platinum structures, it also led to significant edge effects at all deposition potentials (**Figure S3**). To mitigate edge effects and reduce the formation of heterogeneous and ramified structures, various dynamic deposition protocols were tested, including linearly decreasing voltages, cyclic voltammetry, and pulsed depositions. These depositions were performed both with and without the addition of formic acid to assess their impact on the resulting nano- and microstructures (**Figures S4** and **S5**). Although these methods produced a variety of electrode morphologies, they did not significantly reduce edge effects or the presence of heterogeneous microstructures. Consequently, the reproducibility of these approaches was lower than that of chronoamperometry, leading to their exclusion from further electrochemical and electrophysiological performance testing.

**Heterogeneous, Microporous Electrodes Yield Lower Noise Bands, While Evenly Layered, Nanoporous Electrodes Yield Higher Spike Amplitudes.** To evaluate the effect of electrode porosity on the data quality obtained from electrophysiological recordings, MEAs were designed to include a mixture of planar control electrodes and electrodes electroplated at either $-0.3\,V$ or $-0.4\,V$. 6 MEAs were used for these experiments, each containing 20 electrodes of the different types. By including different electrode types on the same MEAs, potential biases from differences between distinct neuronal networks were avoided. The chosen deposition parameters allowed for a comparison between the most microporous electrodes, having the lowest impedance, and the evenly layered, nanoporous electrodes. Microscopic examination showed no apparent differences in biocompatibility across the electrode types, with prominent neuronal growth observed on all platforms (**Figure 6A**).

**Figure 3 | Dependence of electrode size on electrode porosity when applying chronoamperometric and chronopotentiometric depositions**. **(A.)** - **(D.)** Micrographs demonstrating that electrodes with diameters ranging from $10\,\mu m$ to $100\,\mu m$ exhibited evenly layered, nanoporous platinum deposits without discernible edge effects, irrespective of electrode size, when performing chronoamperometric depositions at $-0.4\,V$ for $3\,min$. **(E.)** - **(F.)** Micrographs illustrating the gradual transition into smaller and more evenly dispersed dendrites as the electrode size increased from $10\,\mu m$ to $100\,\mu m$ when applying chronopotentiometric depositions at $0.1\,nA/\mu m$ for $5\,min$.

Electron microscopy further revealed that even the most porous electrodes supported significant neurite meshes extending across their surfaces (**Figure 6B**). All electrode types exhibited prominent activity, with spike amplitudes ranging from $20\,\mu V$ to well above $300\,\mu V$ (**Figure 6C**), which is typical for extracellular action potentials ([1]).

When comparing the electrophysiological activity of the cells at 14 and 28 DIV, a higher percentage of electrodes electroplated at $-0.3\,V$ were active compared to electrodes electroplated at $-0.4\,V$ and planar controls (**Figure 6D**). The most porous electrodes showed significantly lower median spike amplitudes but also lower variance in the noise band compared to the other electrodes (**Figures 6E** - **6F**). Despite the

lower median spike amplitudes, the low noise contributed to a significantly higher SNR for these electrodes (**Figure 6G**). The difference in firing rate detected by the three electrode types, indicating electrode sensitivity, was non-significant at 14 DIV but significantly higher for the electrodes electroplated at $-0.3\,V$ at 28 DIV compared to the electrodes electroplated at $-0.4\,V$ and the planar controls (**Figure 6H**). The maximum spike amplitudes detected by each electrode were, on average, significantly higher for both the electrodes electroplated at $-0.4\,V$ and the planar controls compared to the more porous electrodes electroplated at $-0.3\,V$ (**Figure 6I**). While the most microporous electrodes had significantly higher SNR, the higher spike amplitudes of the evenly lay-

**Figure 4 | Impact of electrode size on electrophysiological performance of porous platinum electrodes**. **(A.)** At 14 days *in vitro* (DIV), the electrode size significantly influenced the percentage of electrodes detecting neuronal activity. Less than $10\,\%$ of the $10\,\mu m$ diameter electrodes were able to detect activity, while more than $90\,\%$ of the $100\,\mu m$ diameter electrodes were active. By 26 DIV, over $60\,\%$ of electrodes of all sizes were active, with more than $95\,\%$ of electrodes $30\,\mu m$ in diameter or larger detecting activity. **(B.)** At 14 DIV, the Signal-To-Noise (SNR) ratio showed a clear dependence on electrode size, with $100\,\mu m$ diameter electrodes having three times higher SNR than $10\,\mu m$ electrodes. At 26 DIV, the differences in SNR between electrode sizes were less pronounced. **(C.)** The median spike amplitude displayed an opposite trend, with $10\,\mu m$ diameter electrodes showing the highest amplitudes at 14 DIV. By 26 DIV, no significant differences in spike amplitudes were observed across electrode sizes. **(D.)** The variance in the noise band was significantly lower for the largest electrodes at 14 DIV, but the differences across electrode sizes were less pronounced at 26 DIV.

ered, nanoporous electrodes indicate that the neurons may have had better positioning in relation to the electrodes, contributing to better signal acquisition.

It is worth noting that several factors, in addition to electrode morphology, can influence the signal quality of the electrodes. For instance, planar electrodes were found to be more prone to astrocyte coverage, which can shiel the electrodes from the neurons (**Figure S6A**). Scanning electron microscopy revealed astrocytes covering the electrodes, potentially undergoing astrogliosis (**Figure S6B**) (34–36). Another issue was the high fasciculation and formation of thick axonal bundles, which detached from the substrate as the networks matured, leaving a significant gap between the neurons and the electrodes (**Figure S6C**). These results highlight the importance of evaluating biocompatibility and cell-electrode interactions when analyzing electrode performance, in addition to their electrochemical properties.

## Discussion

As shown in both this and previous studies, the electrodeposition of nanoporous platinum is a versatile process that can be fine-tuned to create a variety of nano- and microstructures (33, 37). Numerous parameters influence the characteristics of the formed deposits, including the choice of additives, working electrode material, temperature of the elec-

trochemical bath, deposition current/voltage, and deposition time (16, 17, 38). Although the exact mechanisms behind the nucleation and growth of such structures are not fully understood, our findings support the work of Boehler *et al.*, which suggest that electroplating without additives promotes a more predictable and reproducible deposition process (10). Additionally, our results indicate that chronoamperometric depositions produce more consistent structures regardless of electrode size and deposition time. While low overpotentials resulted in globular structures connected by grain boundaries, higher overpotentials led to more dispersed secondary nucleation from depletion zones forming around the primary nuclei, consistent with previous studies (16). By fine-tuning the overpotential to $-0.4\,V$, we achieved highly nanoporous structures without discernible edge effects on hundreds of electrodes in parallel.

When designing microelectrodes for biosensor applications, it's crucial to consider their biocompatibility (39, 40). While many studies assess biocompatibility solely through cell viability, the impact of electrode morphology on neuron positioning relative to the electrodes is often overlooked. Although higher porosity typically improves electrochemical performance, it can lead to significant edge effects and rough electrode morphologies, affecting interactions with neurons and glial cells. Moreover, these protruding structures are fragile and may break off during cell culturing, potentially

**Figure 5 | Dependence of deposition time on the electrode porosity for chronoamperometric and chronopotentiometric electrodepositions.** **(A.) - (B.)** Chronoamperometric depositions at $-0.4\,\mathrm{V}$ resulted in evenly layered, nanoporous platinum structures, irrespective of the deposition time. The defect in the electrode after a $10\,\mathrm{min}$ deposition reveals clearly defined layers of nanoporous platinum throughout the cross-section of the electrode. **(C.) - (F.)** Chronopotentiometric depositions showed a growth of nuclei into larger, globular structures as the deposition time extended beyond $2\,\mathrm{min}$, eventually merging into a homogeneous layer after $30\,\mathrm{min}$.

being engulfed by cells. Our study found that the most microporous electrodes, electroplated at $-0.3\,\mathrm{V}$, exhibited higher activity and signal-to-noise ratio (SNR) compared to more evenly layered nanoporous electrodes at $-0.4\,\mathrm{V}$ and planar controls. This higher SNR was primarily attributed to lower noise variance, as the less porous electrodes detected higher median and maximum spike amplitudes. Theoretically, the highest spike amplitudes are detected at the perisomatic area, and the amplitude will primarily be determined by the proximity between the neuron and the electrode (1). While the most porous electrodes may better detect low-amplitude signals from neurons farther away, their tall edges and large protrusions may increase the distance between neurons and electrodes. Conversely, less microporous electrodes may not detect signals from distant cells but may promote neuron positioning closer to or on the electrodes. This may contribute to subsampling due to fewer active electrodes (41), but it could also simplify spike sorting as electrodes are more selective to individual neurons (42). Therefore, while microelectrodes with large edge effects exhibit high SNR, using homogeneously layered nanoporous electrodes may generally be advantageous.

## Conclusion

Nano- and microporous electrodes offer enhanced signal-to-noise ratio, making them appealing for electrophysiological applications. In this study, we manipulated the electrochemical deposition of platinum to generate varied electrode morphologies at nano- and micrometer scales. While higher porosity improved electrochemical electrode performance, rougher morphology negatively affected neuron-electrode coupling, likely due to prominent edge effects. Evenly layered, nanoporous electrodes exhibited higher median and maximum spike amplitudes, suggesting closer proximity to perisomatic neuronal areas. These results highlight the importance of considering not only electrochemical characteristics and cell viability when assessing electrode performance, but also the impact of the morphology on the neuron-electrode junction. In conclusion, we have demonstrated a highly versatile fabrication protocol for creating evenly layered, nanoporous platinum microelectrodes with an optimal trade-off between biocompatibility, electrochemical, and electrophysiological performance.

**Figure 6 | Electrophysiological performance and biocompatibility of porous platinum electrodes in neural cell cultures**. **(A.)** Micrographs showing the high biocompatibility of the microelectrodes independent of porosity, with extensive neuronal processes across all electrodes. **(B.)** Scanning electron microscopy (SEM) image showing extensive neurite branching throughout a highly porous electrode electroplated at $-0.3\,\text{V}$. **(C.)** Representative voltage traces demonstrating high signal-to-noise (SNR) ratios for electrodes electroplated at $-0.3\,\text{V}$, $-0.4\,\text{V}$, and planar controls, respectively. Pink specks represent spikes detected using the precise timing spike detection (PTSD) algorithm. **(D.)** A significantly higher proportion of the nano- and microporous electrodes were active throughout the experimental period compared to planar control electrodes. **(E.)** - **(F.)** Both median spike amplitudes and variance in the noise bands were significantly lower for electrodes electroplated at $-0.3\,\text{V}$ compared to electrodes electroplated at $-0.4\,\text{V}$ and planar controls. **(G.)** The SNR followed an opposite trend, with the highest SNR for the most microporous electrodes and the lowest SNR for the planar controls. **(H.)** Firing rates, indicating the sensitivity of the electrodes, were comparably high for all electrode types at 14 days *in vitro* (DIV), but were significantly higher for the most microporous electrodes at 28 DIV. **(I.)** The maximum spike amplitudes were significantly higher for the nanoporous electrodes electroplated at $-0.4\,\text{V}$ at 14 DIV, and non-significantly higher at 28 DIV.

**AUTHOR CONTRIBUTIONS**

The author contributions follow the CRediT system. **NWH**: Conceptualization, Methodology, Software, Investigation (chip design & manufacturing, cell experiments, electrophysiology, SEM and bioSEM imaging, formal analysis), Writing – Original Draft, Visualization. **LI**: Methodology, Investigation (chip manufacturing, SEM imaging), Writing – Review & Editing. **PAK**: Methodology, Writing – Review & Editing. **AS, IS**: Conceptualization, Writing – Review & Editing, Resources, Funding Acquisition. **PS**: Conceptualization, Methodology, Writing – Review & Editing, Resources, Funding Acquisition.

**FUNDING**

This work was supported by NTNU Enabling technologies and the Central Norway Regional Health Authority. The Research Council of Norway is acknowledged for the support to the Norwegian Micro- and Nano-Fabrication Facility, NorFab, project number 295864.

**ACKNOWLEDGEMENTS**

We would like to thank engineers Mark Chiappa, Martijn de Roosz and Mathilde Barriet at NTNU NanoLab for technical assistance. Furthermore, we acknowledge Nan Tostrup Skogaker for training and access to the electron microscopy core facility, NTNU. Prof. Michela Chiappalone and Prof. Sergio Martinoia, University of Genova are acknowledged for generously providing the scripts for the Precise Timing Spike Detection algorithm. We would also like to thank professor Svein Sunde for insights and valuable discussions on the electrochemical characterization.

**COMPETING FINANCIAL INTERESTS**

The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

# Bibliography

1. M. E. J. Obien, K. Deligkaris, T. Bullmann, D. J. Bakkum, and U. Frey. Revealing neuronal function through microelectrode array recordings. *Front. Neurosci.*, 8:423, 1 2015. doi: 10.3389/fnins.2014.00423.
2. C. M. Didier, A. Kundu, D. DeRoo, and S. Rajaraman. Development of in vitro 2D and 3D microelectrode arrays and their role in advancing biomedical research. *J. Micromech. Microeng.*, 30:103001, 7 2020. doi: 10.1088/1361-6439/ab8e91.
3. M. E. Spira and A. Hai. Multi-electrode array technologies for neuroscience and cardiology. *Nat. Nanotechnol.*, 8:83–94, 2 2013. doi: 10.1038/nnano.2012.265.
4. S. A. Desai, J. D. Rolston, L. Guo, and S. M. Potter. Improving Impedance of Implantable Microwire Multi-Electrode Arrays by Ultrasonic Electroplating of Durable Platinum Black. *Front. Neuroeng.*, 3:1–11, 2010. doi: 10.3389/FNENG.2010.00005.
5. N. Azim, C. Hart, F. Sommerhage, M. Aubin, J. J. Hickman, and S. Rajaraman. Precision Plating of Human Electrogenic Cells on Microelectrodes Enhanced With Precision Electrodeposited Nano-Porous Platinum for Cell-Based Biosensing Applications. *J. Microelectromech. Syst.*, 28(1):50–62, 2 2019. doi: 10.1109/jmems.2018.2879577.
6. F. Criscuolo, I. Taurino, V. A. Dam, F. Catthoor, M. Zevenbergen, S. Carrara, and G. De Micheli. Fast Procedures for the Electrodeposition of Platinum Nanostructures on Miniaturized Electrodes for Improved Ion Sensing. *Sensors*, 19(10):2260, 5 2019. doi: 10.3390/s19102260.
7. R. Y. Tang, W. H. Pei, S. Y. Chen, H. Zhao, Y. F. Chen, Y. Han, C. L. Wang, and H. D. Chen. Fabrication of strongly adherent platinum black coatings on microelectrodes array. *Sci. China Inf. Sci.*, 57:042402, 7 2014. doi: 10.1007/s11432-013-4825-6.
8. C. Boehler, T. Stieglitz, and M. Asplund. Nanostructured platinum grass enables superior impedance reduction for neural microelectrodes. *Biomater.*, 67:346–353, 10 2015. doi: 10.1016/j.biomaterials.2015.07.036.
9. J. Abbott, T. Ye, K. Krenek, R. S. Gertner, S. Ban, Y. Kim, L. Qin, W. Wu, H. Park, and D. Ham. A nanoelectrode array for obtaining intracellular recordings from thousands of connected neurons. *Nat. Biomed. Eng.*, 4:232–241, 9 2020. doi: 10.1038/s41551-019-0455-7.
10. C. Boehler, D. M. Vieira, U. Egert, and M. Asplund. NanoPt - A Nanostructured Electrode Coating for Neural Recording and Microstimulation. *ACS Appl. Mater. Interfaces.*, 12(13): 14855–14865, 4 2020. doi: 10.1021/acsami.9b22798.
11. Y. Wang, E. S. Graham, and C. P. Unsworth. Superior galvanostatic electrochemical deposition of platinum nanograss provides high performance planar microelectrodes for in vitro neural recording. *J. Neural Eng.*, 18:0460d8, 8 2021. doi: 10.1088/1741-2552/ac1bc1.
12. A. M. Feltham and M. Spiro. Platinized platinum electrodes. *Chem. Rev.*, 71(2):177–193, 1971. doi: 10.1021/cr60270a002.
13. M. E. Baumgärtner and Ch. J. Raub. The Electrodeposition of Platinum and Platinum Alloys. *Platin. Met. Rev.*, 32(4):188–197, 1 1988. doi: 10.1595/003214088X324188197.
14. A. Kloke, F. von Stetten, R. Zengerle, and S. Kerzenmacher. Strategies for the Fabrication of Porous Platinum Electrodes. *Adv. Mater.*, 23(43):4976–5008, 11 2011. doi: 10.1002/adma.201102182.
15. R. A Green, H. Toor, C. Dodds, and N. H. Lovell. Variation in Performance of Platinum Electrodes with Size and Surface Roughness. *Sens. Mater.*, 24(4):165–180, 2012. doi: 10.18494/sam.2012.821.
16. L. M. Plyasova, I. Yu. Molina, A. N. Gavrilov, S. V. Cherepanova, O. V. Cherstiouk, N. A. Rudina, E. R. Savinova, and G. A. Tsirlina. Electrodeposited platinum revisited: Tuning nanostructure via the deposition potential. *Electrochim. Acta*, 51(21):4477–4488, 6 2006. doi: 10.1016/j.electacta.2005.12.027.
17. S. E. Stanca, F. Hänschke, A. Ihring, G. Zieger, J. Dellith, E. Kessler, and H.-G. Meyer. Chemical and Electrochemical Synthesis of Platinum Black. *Sci. Rep.*, 7:1074–8, 4 2017. doi: 10.1038/s41598-017-01040-8.
18. J. Rothe, O. Frey, R. Madangopal, J. Rickus, and A. Hierlemann. Robust Functionalization of Large Microelectrode Arrays by Using Pulsed Potentiostatic Deposition. *Sensors*, 17(1): 22, 12 2017. doi: 10.3390/s17010022.
19. A. Zátonyi, F. Fedor, Z. Borhegyi, and Z. Fekete. In vitro and in vivo stability of black-platinum coatings on flexible, polymer microECoG arrays. *J. Neural Eng.*, 15:054003, 8 2018. doi: 10.1088/1741-2552/aacf71.
20. H. M. Yasin, G. Denuault, and D. Pletcher. Studies of the electrodeposition of platinum metal from a hexachloroplatinic acid bath. *J. Electroanal. Chem.*, 633(2):327–332, 8 2009. doi: 10.1016/j.jelechem.2009.06.020.
21. C. Bernard. Etude de l'activite electrochimique du platine platine-II. conditions de preparation des electrodes. *Electrochim. Acta*, 15(2):271–282, 2 1970. doi: 10.1016/0013-4686(70)80020-2.
22. A. R. Layson and M. R. Columbia. The Morphology of Platinum Black Electrodeposited on Highly Oriented Pyrolytic Graphite Studied with Scanning Electron Microscopy and Scanning Tunneling Microscopy. *Microchem. J.*, 56(1):103–113, 5 1997. doi: 10.1006/mchj.1996.1440.
23. G. Samjeské, A. Miki, S. Ye, and M. Osawa. Mechanistic study of electrocatalytic oxidation of formic acid at platinum in acidic solution by time-resolved surface-enhanced infrared absorption spectroscopy. *J. Phys. Chem. B.*, 110(33):16559–16566, 8 2006. doi: 10.1021/jp0618911.
24. A. Cowley and B. Woodward. A healthy future: Platinum in medical applications platinum group metals enhance the quality of life of the global population. *Platin. Met. Rev.*, 55(2): 98–107, 4 2011. doi: 10.1595/147106711X566816.
25. M. Gulino, S. D. Santos, and A. P. Pêgo. Biocompatibility of Platinum Nanoparticles in Brain ex vivo Models in Physiological and Pathological Conditions. *Front. Neurosci.*, 15:787518, 12 2021. doi: 10.3389/fnins.2021.787518.
26. G. Bernocchi, F. P. Fanizzi, S. A. De Pascali, V. M. Piccolini, C. Gasperini, V. Insolia, and M. G. Bottone. Neurotoxic Effects of Platinum Compounds: Studies in vivo on Intracellular Calcium Homeostasis in the Immature Central Nervous System. *Toxics 2015*, 3(2):224–248, 6 2015. doi: 10.3390/toxics3020224.
27. R. van de Wijdeven, O. H. Ramstad, V. D. Valderhaug, P. Köllensperger, A. Sandvig, I. Sandvig, and Ø. Halaas. A novel lab-on-chip platform enabling axotomy and neuromodulation in a multi-nodal network. *Biosens. Bioelectron.*, 140:111329, 9 2019. doi: 10.1016/j.bios.2019.111329.
28. N. Winter-Hjelm, Å. B. Tomren, P. Sikorski, A. Sandvig, and I. Sandvig. Structure-function dynamics of engineered, modular neuronal networks with controllable afferent-efferent connectivity. *J. Neural Eng.*, 20:046024, 8 2023. doi: 10.1088/1741-2552/ace37f.
29. M. D. Murbach, B. Gerwe, N. Dawson-Elli, and L.-k. Tsui. impedance.py: A Python package for electrochemical impedance analysis. *J. Open Source Softw.*, 5(52):2349, 8 2020. doi: 10.21105/joss.02349.
30. A. Maccione, M. Gandolfo, P. Massobrio, A. Novellino, S. Martinoia, and M. Chiappalone. A novel algorithm for precise identification of spikes in extracellularly recorded neuronal signals. *J. Neurosci. Methods*, 177(1):241–249, 2 2009. doi: 10.1016/j.jneumeth.2008.09.026.
31. J. C. Lansey. Beautiful and distinguishable line colors + colormap, 2021.
32. C. A. Brewer, G. W. Hatchard, and M. A. Harrower. ColorBrewer in Print: A Catalog of Color Schemes for Maps. *Cartogr. Geogr. Inf. Sci.*, 30(1):5–32, 1 2003. doi: 10.1559/152304003100010929.
33. B. Ilic, D. Czaplewski, P. Neuzil, T. Stanczyk, J. Blough, and G. J. Maclay. Preparation and characterization of platinum black electrodes. *J. Mater. Sci.*, 35(14):3447–3457, 7 2000. doi: 10.1023/A:1004884723515.
34. V. S. Polikov, M. L. Block, J.-M. Fellows, J.-S. Hong, and W. M. Reichert. In vitro model of glial scarring around neuroelectrodes chronically implanted in the CNS. *Biomater.*, 27(31): 5368–5376, 11 2006. doi: 10.1016/j.biomaterials.2006.06.018.
35. C. A. R. Chapman, H. Chen, M. Stamou, J. Biener, M. M. Biener, P. J. Lein, and E. Seker. Nanoporous Gold as a Neural Interface Coating: Effects of Topography, Surface Chemistry, and Feature Size. *ACS Appl. Mater. Interfaces.*, 7(13):7093–7100, 4 2015. doi: 10.1021/acsami.5b00410.
36. M. Ferguson, D. Sharma, D. Ross, and F. Zhao. A Critical Review of Microelectrode Arrays and Strategies for Improving Neural Interfaces. *Adv. Healthc. Mater.*, 8(19):1900558, 10 2019. doi: 10.1002/adhm.201900558.
37. S.-E. Stanca, O. Vogt, G. Zieger, A. Ihring, J. Dellith, A. Undisz, M. Rettenmayr, and H. Schmidt. Electrochemical growth mechanism of nanoporous platinum layers. *Commun. Chem.*, 4:98, 6 2021. doi: 10.1038/s42004-021-00535-w.
38. Y. Xu and B. Zhang. Recent advances in porous Pt-based nanostructures: synthesis and electrochemical applications. *Chem. Soc. Rev.*, 43(8):2439–2450, 3 2014. doi: 10.1039/C3CS60351B.
39. C. Marin and E. Fernández. Biocompatibility of Intracortical Microelectrodes: Current Status and Future Prospects. *Front. Neuroeng.*, 3:8, 5 2010. doi: 10.3389/fneng.2010.00008.
40. Y. Liu, S. Xu, Y. Yang, K. Zhang, E. He, W. Liang, J. Luo, Y. Wu, and X. Cai. Nanomaterial-based microelectrode arrays for in vitro bidirectional brain–computer interfaces: a review. *Microsyst. Nanoeng.*, 9:13, 1 2023. doi: 10.1038/s41378-022-00479-8.
41. A. Levina and V. Priesemann. Subsampling scaling. *Nat. Commun.*, 8:15140, 5 2017. doi: 10.1038/ncomms15140.
42. A. P. Buccino, S. Garcia, and P. Yger. Spike sorting: new trends and challenges of the era of high-density probes. *Prog. Biomed. Eng.*, 4:022005, 5 2022. doi: 10.1088/2516-1091/ac6b96.