Entropy-driven Denaturation for Sustainable Regeneration of Protein Waste

Yichong Wang[1,2,4], Junlang Liu[1,4], Michael Peters[2], Ryoma Ishii[2,3], Dianzhuo Wang[1], Sourav Chowdhury[1], Kevin Kit Parker[2,5*], Eugene I. Shakhnovich[1,5*]

Affiliations

[1] Department of Chemistry and Chemical Biology, Harvard University, Cambridge, MA, 02138 USA

[2] Disease Biophysics Group, John A. Paulson School of Engineering and Applied Sciences, Harvard University, Boston, MA, 02134 USA

[3] Medical & Health Informatics Laboratories, NTT Research, Inc., Sunnyvale, CA, 94085 USA

[4] These authors contributed equally: Yichong Wang, Junlang Liu

*Corresponding authors:

Kevin Kit Parker
Science and Engineering Complex 6.307
150 Western Ave, Boston, MA 02134
Email: kkparker@seas.harvard.edu
Phone: 617-496-1793

Eugene I. Shakhnovich
12 Oxford Street
Cambridge, MA 02138
Email: shakhnovich@chemistry.harvard.edu
Phone: 617-495-4130

Keywords: Indirect Solute Effect, Entropy-driven, Protein Denaturation, Sustainability, Waste Recycling

Abstract (197/200 words)

Electrolytes are essential parts of the environment for all life forms, where proteins, water, and solutes interplay to support vital activities. However, a fundamental understanding of the effect of ionic solutes on proteins remains elusive for more than a century[1–3]. Here we show how some ionic solutes can serve as potent denaturants despite the absence of direct protein-ion interactions. We demonstrate dramatic differences between denaturation potency of different ionic solutes with lithium bromide (LiBr) being the strongest denaturant and sodium bromide (NaBr) being the least potent. Experiments and simulations indicate the presence of certain ions disrupts the structure of water network, thereby induce protein denaturation indirectly via an entropy-driven mechanism. We further introduce a scalable strategy for protein waste revalorization, distinguished by the closed-loop recycling of denaturants, straightforward protein separation, and facile manufacturing, all enabled by the entropy-driven denaturation by LiBr. Through successful isolation and systematic study of indirect solute effects, our findings suggest a unified and generally applicable framework for decoding of the protein-water-solute nexus, where all current studies can be easily incorporated. Besides, our regeneration approach underscores the feasibility of repurposing protein waste into valuable biomaterials in a sustainable way with wide-reaching application potential.

Introduction

The intricate interactions between proteins, water and solutes determine not only protein structure, but also protein folding and function. Initial observations in the 19[th] century[1,2] yielded the 'Hofmeister Series', evaluating protein solubility in relation to ionic solutes. Property changes of proteins in concentrated ionic solutions[4–6] and protein denaturation induced by lithium salts[3,7] have been reported since the 1940s. More recently, there has been significant progress in understanding the importance of direct interactions between proteins or water and solutes[8–11], the origin of hydrophobicity[12] and related effects on protein folding[13]. However, a unified framework to understand triadic relationship between proteins, water, and solutes, has remained elusive[14].

This knowledge gap limits our ability to control, mass-produce, and utilize sustainable protein-based materials from renewable resources[15,16]. Due to our limited understanding of protein-water-solute interactions, current protein extraction processes heavily rely on non-recyclable organic chemicals (e.g., urea, guanidine hydrochloride), resulting in pollution, increased costs, and difficulties in further processing and manufacturing[17]. As a result, over ten million tons of keratin-rich waste generated annually, typically disposed through incineration or landfilling instead of being repurposed[18,19]. Such waste is unfortunate as keratin materials possess various desirable properties including biodegradability, biocompatibility, mechanical strength, and chemical modifiability, thereby endowing them with promising potential for versatile applications from sustainable textiles to tissue engineering scaffolds[20,21].

A plausible mechanism of indirect solute effects on protein stability is modulation of hydrophobic effect via water hydrogen bond network changes. To test this hypothesis, we selected a simple monovalent ion pair—lithium bromide (LiBr) as the model solute. Among all the monovalent ion pairs, LiBr has the second largest solubility of all common solvents (e.g., water,

methanol, ethanol, etc.)[9] and stability in water in contrast to lithium iodide (LiI). Despite the

potential promise of LiBr as a versatile protein denaturant[4], the lack of mechanistic understanding

of its action as a denaturant has largely limited its further industrial applications. Here, we

systematically explored LiBr's effects on protein structure and denaturation through comparison

with both lithium chloride (LiCl) and sodium bromide (NaBr). The capability of LiBr as a universal

denaturant has been confirmed by testing three proteins spanning different levels of structure

complexity. We further confirmed, both experimentally and theoretically, that the indirect solute

effects of LiBr can significantly affect protein structure and stability through altering the structure

of water network. Finally, we demonstrated that entropic mechanisms of denaturation, which lacks

direct interaction between protein and denaturant, is highly advantageous for scalable protein

waste regeneration strategy as it enables closed-loop recycling of LiBr, easy separation of proteins

and facile manufacturing.

Universal denaturation capacity of LiBr

To systematically investigate solute effects on protein conformation, we selected three proteins

representing different levels of structural complexity (Fig. 1a), along with three different ionic

solutes including LiBr, LiCl, and NaBr. We found markedly distinct solute effects for different

proteins and salts across various concentrations, as evidenced by aggregation of denatured protein

during turbidity measurements at 405 nm (Fig. 1b-d). As the smallest protein tested, dihydrofolate

reductase (DHFR) shows significant aggregation at 1 M LiBr and 5 M LiCl, but remains soluble

at all NaBr concentrations (Fig. 1b). Since both salt-induced precipitation and denaturation can

result in protein aggregation, we used Fourier-transform infrared spectroscopy (FTIR) to further

distinguish the underlying mechanisms (Fig. 1e-g, Extended Data Fig. 2a-d). Starting from 2 M

LiBr, we observed a gradual loss of secondary structure of DHFR such as α-helix (1650-1655 cm^{-}

^{1}) and β-sheet/turns (1660-1690 cm^{-1}), along with an increase in aggregated β-like random

structures (1620-1630 cm^{-1}) (Fig. 1e). The secondary structure loss of DHFR in 2 M LiBr was

further confirmed by conformational kinetics measurement using quantitative Raman

spectroscopy, where less-stable β-sheet disappeared first, followed by α-helix, with obvious

accumulation of aggregated random structures (Fig. 1h). Both FTIR (Extended Data Fig. 2a) and

tryptophan fluorescence measurement (Extended Data Fig. 2e) confirmed DHFR unfolding

starting from ~5 M LiCl. In contrast, DHFR stays well-folded for all concentrations of NaBr

(Extended Data Fig. 2b).

To elucidate whether solutes can affect conformations of proteins with more complex,

hierarchically-ordered structures, we examined fibronectin. This protein, a critical component for

cell-extracellular matrix interactions[22] has more recently been explored as a synthetic building

material[23–25] because of its unique structure-function relationships. Fibronectin is comprised of

two covalently linked extensible arms formed by β-sheet domains that can undergo quaternary

structure changes from globular to extended state[26] (Fig. 1a middle). With the increase of protein

structural complexity, higher concentrations of LiBr and LiCl (7 M and 8 M, respectively) were

required to induce aggregation of fibronectin (Fig. 1c), where secondary structure loss was also

confirmed by FTIR spectra (Fig. 1f, Extended Data Fig. 2c-d). Before denaturation, protein

conformational changes were observed through dynamic light scattering (DLS) measurements of

the hydrodynamic radius R_h (Fig. 1i), where fibronectin transitions from the globular state (R_h ~8

nm) to the extended state (R_h ~23 nm) at a lower concentration of LiBr around 2 M. Combining

the secondary and tertiary structure loss observed in FTIR and the quaternary structure extension

shown via DLS, we can identify sequential changes in protein structure as the concentration of

LiBr increases (Extended Data Fig. 2f).

We also tested keratin structural transformation in LiBr solution as observed by

Feughelman et al.[4]. In contrast to DHFR and fibronectin, keratin possesses hierarchical structure

ranging from α-helices at the nanometer scale to protofibrils and filaments at the micrometer scale.

A turbidity map generated from 24-hour soaking of wool in salt solutions showed that visible

signal can only be observed at high concentrations of LiBr (Fig. 1d). FTIR spectra further indicated

complete denaturation of both α-keratin from wool and β-keratin from goose feathers, irrespective

of their different native configurations (Fig. 1g). Finally, scanning electron microscope (SEM)

images of wool before and after treatment with 8 M LiBr, LiCl, and NaBr also corroborate our

turbidity measurement findings (Fig. 1d), where only concentrated LiBr induces denaturation of

keratin (Fig. 1j, Extended Data Fig. 2g).

Indirect solute effects

Thermodynamically, protein conformational change or denaturation is a complex process where

entropy and enthalpy contribute to the overall free energy balance. At lower concentrations of

denaturants, entropy and enthalpy balance to favor the native state; however, at higher

concentrations, they tend towards the unfolded state[27]. To elucidate the thermodynamic

mechanisms of protein denaturation by LiBr, we conducted isothermal titration calorimetry (ITC)

experiments to measure the enthalpic contribution from direct LiBr solute-protein interactions,

with commonly used denaturants urea and guanidine hydrochloride (GdnHCl) as a control.

Pronounced heat release has been detected upon injection of urea or GdnHCl into samples

containing DHFR and fibronectin (Fig. 2a,b). Enthalpy changes, dependent on protein sizes and

exposures of hydrophobic domains ($\sim$-7 kCal mol^{-1} for DHFR and $\sim$-14 kCal mol^{-1} for fibronectin),

correspond to the formation of 1-2 or 3-4 hydrogen bonds per organic denaturant molecule,

respectively. These results are highly consistent with previous studies[28,29], where enthalpy-driven

mechanisms of protein denaturation by urea or GdnHCl were established. In contrast, no enthalpy

change from direct interaction with proteins was detected when LiBr solution was injected into

protein samples under identical protocols, suggesting that solute ions here do not engage in

noticeable direct interactions with proteins. Given that LiBr, being a universal and potent

denaturant, does not contribute enthalpically to protein free energy in solution, we conclude that

LiBr shifts the free energy landscape of proteins towards denatured state by affecting its entropy.

Mechanism of entropy-driven protein denaturation

To further test the hypothesis of entropy-driven denaturation by LiBr, molecular dynamics (MD)

simulations were employed to provide experimentally inaccessible atomistic-level insights. First,

we confirmed that local water density around ions (Extended Data Fig. 3a,b) in our simulations

agrees well with previous X-ray and neutron diffraction experimental results[30]. The cooperativity

of ion hydration[31] was also observed, where local water structures are determined by both ions and

their counterions. Molecular water entropy, encompassing both translational and rotational entropy

of water molecules, was calculated based on TIP3P[32] water model using Two-Phase

Thermodynamic (2PT) method, the combination of which have been validated as the most accurate

for replicating experimental entropy values[33]. In both LiBr and LiCl solutions, two distinct

populations of water molecules are detectable (Fig. 2c, Extended Data Fig. 3d,e). As suggested by

experimental evidence of local effects of Li^+ ions[34] (Extended Data Fig. 3a,b, and c left), the subset

characterized by lower average entropy is identified as ion-bound water, whereas the other,

possessing higher entropy, is identified as free water that constitutes the hydrogen bonded water

network. LiBr solution also demonstrates a higher proportion of ion-bound water compared to LiCl

solution (see Fig. 2c, Extended Data Figs. 3d,e). This enhanced capacity of Li^+ ions to sequester

water in LiBr could stem from the more effective separation between Li^+ and Br^- ions, attributable

to the lower charge density of Br^- ions and the substantial size disparity between Li^+ and Br^- ions.

In contrast, the NaBr solution exhibits a single population akin to the intact hydrogen bond network

of pure water (Fig. 2c, Extended Data Fig. 3f), which could potentially be explained by the absence

of localized high charge density[12,31] (Extended Data Fig. 3c right).

The prominent differences in both water network size and denaturation capability between

LiBr, LiCl, NaBr, and pure water, point out to water network entropy as a possible culprit. To

further highlight this concept, we established an analytical model of entropy penalty decrease

($\Delta\Delta S$), which drives the overall free energy balance towards the denatured state.

$$\Delta\Delta S = \Delta\Delta S^{\text{translation}} + \Delta\Delta S^{\text{rotation}} + \Delta\Delta S^{\text{vibration}} - 4k_{\text{B}} \ln \phi \qquad (1)$$

Here, $\Delta\Delta S^{\text{translation}}$, $\Delta\Delta S^{\text{rotation}}$, and $\Delta\Delta S^{\text{vibration}}$ represent the contributions of water

molecular entropy and $-4k_{\text{B}}\ln\phi$ denotes the contribution of water network entropy, with ϕ

representing the ratio of water network sizes in ionic solutions and pure water (see **Methods** for

derivation of Eq(1) and further details).

Notably, the numerical estimates of water entropy penalty decrease, calculated using Eq.(1)

with values of individual contributions obtained from molecular dynamics simulation (Fig. 2d,f),

align well with our experimental observations regarding the order of denaturation capacities of

different salts. For example, ~3 M LiBr and ~5 M LiCl show comparable degree of entropy penalty

reduction and exhibit similar protein denaturation capacity as shown by FTIR (Fig. 1e and

Extended Data Fig. 2a), while 6 M NaBr exhibits lower entropy penalty reduction than 2 M LiBr

and thus cannot denature DHFR (Extended Data Fig. 2b). Furthermore, the decrease in network

entropy penalty appears to be the predominant factor over that of rotational and translational

entropy of individual water molecules. This key factor has been overlooked in several previous

studies leading to considerable controversy regarding the effects of solutes on water dynamics and

protein unfolding[35,36].

Finally, protein free energy landscapes in different LiBr concentrations were constructed

using well-tempered metadynamics simulation[37] (See **Methods** for details), where a stable α-helix

peptide of 20 amino acids was adopted as a model protein (Fig. 2e). The increase of concentrations

shifts the free energy landscapes and lowers the energy barrier for unfolding, which lend further

confirmation of the universal denaturation capacity of LiBr. In conclusion, solute-induced water

network disruption potentiates the reduction of entropy penalty when proteins sequester water

molecules from bulk water network during unfolding, and thus facilitates the unfolding process

and leads to large-scale protein conformational changes and denaturation (Fig. 2g).

Sustainable keratin regeneration with facile manufacturing

In contrast with conventionally applied enthalpy-driven denaturants (e.g., urea, GdnHCl), the entropy-driven denaturation mechanism can address limitations in protein regeneration, including the waste and pollution from single-use organic chemicals and the complexity of fabrication. Hereby, we developed an economic and sustainable protocol for keratin-rich waste regeneration with closed-loop recycling of LiBr solution followed by facile manufacturing (Fig. 3a). Protein resources such as animal fragments or wool-based textiles are denatured by an aqueous solution of 8 M LiBr, with heat applied to accelerate reaction kinetics and prevent aggregation during extraction. A small amount of 1,4-dithiothreitol (DTT) is added as a reductant to break down the dense disulfide matrix in keratin. After extraction, the mixture is hot filtered, cooled down and separated into a subnatant of denatured keratin gel and a supernatant of LiBr solution driven by spontaneous aggregation (Extended Data Fig. 4b,c). Since the LiBr does not induce denaturation via direct interactions, the resulting solution can be continuously recycled in a closed loop, which not only eliminates pollution from waste organics but also significantly reduces the consumption and cost of denaturants.

To test the cyclic stability of the closed-loop recycling protocol, we performed multiple iterations of extraction using both α-keratin from wool and β-keratin from goose feathers. The yield remains consistently around 40% after five cycles of extraction (Fig. 3b), while the first cycle exhibits a slightly lower yield possibly due to a small amount of keratin remaining in the solution after separation. Unchanged composition of the recycled LiBr solution is further confirmed with thermogravimetric analysis (TGA) and coupled Fourier transform infrared spectroscopy (TG-FTIR) of the emerging gas (Fig. 3c, Extended Data Fig. 4d,e).

Notably, in the absence of direct binding to denaturants, the spontaneous aggregation of

denatured keratin enables a simple separation of condensed gel from the solution, alleviating

difficulties with conventional organic reagents (Fig. 3d), which usually involves dialysis and

lyophilization. Additionally, the separated keratin can undergo a fast phase transition from

denatured gel state to renatured solid state when transferring back into water (Fig. 3e,

Supplementary Video 1), while keratin extracted with organic denaturants remains non-

processable until fully dialyzed. The viscous property of the gel and the fast phase transition

process enable a wide array of manufacturing modalities including injection molding, film casting,

dip coating, fiber spinning, and 3D printing (Fig. 3f) without any additional usage of organic

solvents.

Mechanical tunability and shape-memory of regenerated keratin

Keratins, particularly α-keratins, contain multiple cysteine residues, which form a dense network

of intermolecular disulfide bonds. After extraction, these disulfide bonds are reduced to thiol

groups, thereby endowing the regenerated keratin material with adjustable covalent crosslinking

through oxidation. For instance, low level of crosslinking allows the α-helices to rearrange more

freely under stress (Fig. 4a, Extended Data Fig. 5a). As a result, reduced keratin preserves a high

flexibility with a modulus of 124.3 ± 18.8 kPa and a yield strain of $435 \pm 61\%$. On the contrary,

formation of multiple disulfide bonds can significantly increase the elastic modulus of oxidized

keratin by an order of magnitude to 1.35 ± 0.11 MPa and decrease the fracture strain to $95 \pm 9\%$

(Fig. 4b,e, Extended Data Fig. 5b-e). Raman spectroscopy of keratin samples under 50% strain

suggests that most secondary structure remain unchanged within reduced keratin upon stretching,

whereas a more discernible loss of α-helix domains and an increase of β/random structures can be

observed in oxidized keratin (Fig. 4c). Differences between the two conditions reveal the effect of

disulfide crosslinking on the α-helix network of regenerated keratin, providing the material with

tunable mechanical properties from ductile to elastic (Fig. 4f).

In addition to enhancing the mechanical strength, disulfide crosslinking can also provide

the keratin material with a hydration-responsive shape-memory property. Prior studies of Miserez

et al.[38] and Cera et al.[39] revealed that uniaxial strain can induce reversible uncoiling of α-helix into

metastable β-like structures within anisotropic bio-based elastomer. Similarly, in the crosslinked

keratin network, the transition between coiled helix and uncoiled strands was also observed (Fig.

4d), leading to a shape-memory effect facilitated by formation and decay of hydrogen bonds. In a

hydrated environment, dynamic reformation of hydrogen bonds enables the uncoiling of helices

under external stress, allowing the material to be deformed into a temporary shape. Upon

dehydration, the formation of intermolecular hydrogen bonds then locks the uncoiled chains,

thereby fixing the network in the temporary shape. Finally, upon rehydration, presence of free

water molecules can unlock the hydrogen bonds again, facilitating the recovery of native α-helix

structures and returning the material to its permanent shape (Fig. 4g). The shape-memory

capability of regenerated keratin is demonstrated both as a standalone object and as components

of a more complex tensegrity structure (Fig. 4h, Supplementary Video 2-4). Sustainable keratin

materials may show promise in a variety of applications, including areas such as smart textiles or

biomedical implants, due to their biocompatible nature, tunable mechanical properties, and shape-

memory capability.

Discussion

The effect of water networks on conformations and stability of proteins has been a subject of

extensive debate. We investigated the molecular mechanism of the hierarchical protein

conformational change in the presence of three monovalent salts—LiBr, LiCl, and NaBr. Most

surprisingly we found no direct interactions between proteins and ionic solutes despite the

significant potency of LiBr as a universal denaturant. Thermodynamic and spectroscopic analyses,

in combination with atomistics molecular simulations, have shown that large-scale protein

conformational changes and denaturation by LiBr and other ionic solutes are mediated by

reduction of entropy penalty. Localized strong solute-water interactions for LiBr, and, to a lesser

extent, LiCl, disrupt the water network and reduce the entropy penalty that proteins incur when

sequestering water molecules from bulk water phase during denaturation. In contrast, water

network is largely preserved in NaBr solution, thereby consistently retaining protein native

structures across varying concentrations. With the confirmation of entropic effect of ionic solutes

on protein-water interactions, our study provides a comprehensive understanding of protein-water-

solute nexus, offering potentially valuable insights into the crucial role that water plays in protein

folding, functions, and evolution.

Leveraging the distinctive advantages of this entropy-driven mechanism, we have

developed a regeneration strategy for protein waste featuring closed-loop recycling of LiBr

solution, simple protein separation, and diverse manufacturing pathways. The resulting keratin

material demonstrates tunable mechanical properties and hydration triggered shape-memory

capability. This interdisciplinary study, where clear illustration of molecular-level mechanism

meets scalable novel applications, opens promising avenues for future valorization of mistreated

wastes and development of protein-based smart materials, and offers practical strategies for

advancing towards a sustainable economy.

Figures

Fig. 1 | Concentrated LiBr solutions induce universal protein conformational change and cause denaturation. a, Schematics of DHFR, fibronectin, and α-keratin (wool), representing three levels of structural complexity. **b-d**, Turbidity assay of three respective proteins measured by OD_{405}, suggesting different denaturation capabilities of LiBr, LiCl, and NaBr. Data are normalized by the highest OD_{405} values of respective proteins and presented as mean (n = 4). **e-g**, FTIR of the amide I band indicate a gradual loss of secondary structure upon increasing of LiBr concentration. **h**, Percentage change of the secondary structure in DHFR in 2 M LiBr, deconvoluted from the amide I band of Raman spectra. **i**, DLS measurement of the hydrodynamic radius of fibronectin with increasing LiBr concentration, indicating an extension of quaternary structure followed by aggregation. Data are presented as mean ± 1.5 s.d. (n = 6). **j**, SEM image of wool prior (i) and after (ii) denaturation with 8 M LiBr. Scale bars, 50 µm.

299
Fig. 2 | Protein conformational changes come from indirect solute effects manifested as water network
entropy. a-b, Reaction enthalpy of interactions between proteins (**a,** DHFR, **b,** fibronectin) and
denaturants (LiBr, urea, and GdnHCl) as measured by isothermal titration calorimetry. Data are presented
as mean ± s.d. (n = 3). **c,** Distributions of molecular entropy of water molecules in 7 M LiBr, LiCl, and
NaBr from MD simulations. **d,** Total entropy penalty decrease in different concentrations of LiBr, LiCl,
and NaBr solutions. Data are obtained from MD simulations and calculated via the analytical model (Eq.
1). Data are presented as mean ± s.d. (n = 3), however, the error bars are smaller than the data point size. **e,**
Free energy landscape of an α-helix peptide (20 amino acids) in pure water and 1, 4, 7 M LiBr from MD
simulations. **f,** Decomposition of the total entropy penalty decrease presented in **d**. **g,** Mechanistic
comparison of protein unfolding driven by direct interaction and indirect solute effects.

310
Fig. 3 | Sustainable regeneration of keratin waste with facile manufacturing. a, Schematic showing the
regeneration protocol of keratin waste with closed-loop recycling of LiBr solution. **b**, Extraction yield of
α-keratin from wool and β-keratin from goose down. Data are presented as mean ± s.d. (n = 7 for α-keratin,
n = 3 for β-keratin). **c**, Comparison of the TGA profile shows no major change in the LiBr solution after 5
cycles of extraction. **d**, Keratin solution extracted with LiBr undergoes spontaneous aggregation upon
cooling, and can be easily separated into condensed gel after centrifuging (i). Keratin solution extracted
with urea remains homogenous after the same process, requiring dialysis for separation (ii). **e**, Immersing
extracted keratin on coverslips with transparent well spacers in water. Keratin gel from LiBr extraction
quickly turns into a white solid phase, while keratin solution from urea extraction remains soluble. **f**, Facile
manufacturing strategies including injection molding, film casting, dip coating, fiber spinning, and 3D
printing. Scale bars, 1 cm.
322

323
324
Fig. 4 | Tunable mechanical properties and shape-memory effect of regenerated keratin. a, Schematic
of the α-keratin in reduced state and directional rearrangement of α-helices induced by stretching. **b**, Cyclic
loading of reduced keratin to 50% strain. **c**, Change of secondary structure percentage under 50% strain
quantified from Raman deconvolution of amide I band. A more significant decrease of α-helix can be
observed within oxidized sample, indicating the uncoiling of helices into metastable β-sheets (n = 3). **d**,
Schematic of the α-keratin in oxidized state and uncoiling of helices upon stretch. **e**, Cyclic loading of
oxidized keratin to 50% strain. **f**, Stress-strain curves of reduced and oxidized keratin until fracture. Scale
bars, 2 mm. **g**, Schematic of the shape memory effect triggered by hydration signal. **h**, Demonstration of
shape memory effect with a badge model and a tensegrity structure. Scale bars: 3 cm.

References

1. Hofmeister, F. Zur Lehre von der Wirkung der Salze. *Archiv f. experiment. Pathol. u. Pharmakol* **24**, 247–260 (1888).

2. Jungwirth, P. & Cremer, P. S. Beyond Hofmeister. *Nature Chem* **6**, 261–263 (2014).

3. Bello, J. & Bello, H. R. Evidence from model peptides relating to the denaturation of proteins by lithium salts. *Nature* **194**, 681–682 (1962).

4. Feughelman, M., Haly, A. R. & Mason, P. Contraction of Keratin Fibres in Aqueous Lithium Bromide. *Nature* **196**, 957–958 (1962).

5. Carpenter, D. C. & Lovelace, F. E. The Influence of Neutral Salts on the Optical Rotation of Gelatin. III. Effect of the Halides of Lithium, Sodium, Rubidium and Cesium1. *J. Am. Chem. Soc.* **57**, 2337–2342 (1935).

6. Mandelkern, L., Halpin, J. C., Diorio, A. F. & Posner, A. S. Dimensional Changes in Fibrous Macromolecules: The System α-Keratin-Lithium Bromide. *J. Amer. Chem. Soc.* **84**, 1383–1391 (1962).

7. Bello, J. & Bello, H. R. Interaction of Model Peptides with Water and Lithium Bromide. *Nature* **190**, 440–441 (1961).

8. Balos, V. *et al.* Time-resolved terahertz–Raman spectroscopy reveals that cations and anions distinctly modify intermolecular interactions of water. *Nat. Chem.* **14**, 1031–1037 (2022).

9. Mazzini, V. & Craig, V. S. J. Volcano Plots Emerge from a Sea of Nonaqueous Solvents: The Law of Matching Water Affinities Extends to All Solvents. *ACS Cent. Sci.* **4**, 1056–1064 (2018).

10. Bellissent-Funel, M.-C. *et al.* Water Determines the Structure and Dynamics of Proteins. *Chem. Rev.* **116**, 7673–7697 (2016).

11. Levy, Y. & Onuchic, J. N. Water mediation in protein folding and molecular recognition. *Annu Rev Biophys Biomol Struct* **35**, 389–415 (2006).

12. Dill, K. A., Truskett, T. M., Vlachy, V. & Hribar-Lee, B. Modeling Water, the Hydrophobic Effect, and Ion Solvation. *Annual Review of Biophysics* **34**, 173–199 (2005).

13. Shakhnovich, E. Protein Folding Thermodynamics and Dynamics: Where Physics, Chemistry, and Biology Meet. *Chem. Rev.* **106**, 1559–1588 (2006).

14. Xie, W. J. & Gao, Y. Q. A Simple Theory for the Hofmeister Series. *J. Phys. Chem. Lett.* **4**, 4247–4252 (2013).

15. Ashworth, C. Plastics from proteins. *Nat Rev Chem* **6**, 165–165 (2022).

16. Rosenboom, J.-G., Langer, R. & Traverso, G. Bioplastics for a circular economy. *Nat Rev Mater* **7**, 117–137 (2022).

17. Senthilkumar, N., Chowdhury, S. & Sanpui, P. Extraction of keratin from keratinous wastes: current status and future directions. *J Mater Cycles Waste Manag* **25**, 1–16 (2023).

18. Niinimäki, K. *et al.* The environmental price of fast fashion. *Nat Rev Earth Environ* **1**, 189–200 (2020).

19. Sun, J. *et al.* Bioinspired Processing of Keratin into Upcycled Fibers through pH-Induced Coacervation. *ACS Sustainable Chem. Eng.* **11**, 1985–1994 (2023).

20. Fang, W., Fan, R., Aranko, A. S., Hummel, M. & Sixta, H. Upcycling of Keratin Wastes in Sustainable Textile Fiber Applications. *ACS Sustainable Chem. Eng.* **11**, 14807–14815 (2023).

21. Zhu, S. *et al.* Using Wool Keratin as a Structural Biomaterial and Natural Mediator to Fabricate Biocompatible and Robust Bioelectronic Platforms. *Adv Sci (Weinh)* **10**, e2207400 (2023).

22. Dalton, C. J. & Lemmon, C. A. Fibronectin: Molecular Structure, Fibrillar Structure and
Mechanochemical Signaling. *Cells* **10**, 2443 (2021).
23. Feinberg, A. W. & Parker, K. K. Surface-Initiated Assembly of Protein Nanofabrics. *Nano*
Lett. **10**, 2184–2191 (2010).
24. Ahn, S. *et al.* Self-Organizing Large-Scale Extracellular-Matrix Protein Networks. *Advanced*
Materials **27**, 2838–2845 (2015).
25. Ahn, S., Lee, K. Y., Parker, K. K. & Shin, K. Formation of Multi-Component Extracellular
Matrix Protein Fibers. *Sci Rep* **8**, 1913 (2018).
26. Deravi, L. F. *et al.* Differential Contributions of Conformation Extension and Domain
Unfolding to Properties of Fibronectin Nanotextiles. *Nano Lett.* **12**, 5587–5592 (2012).
27. Privalov, P. L. Stability of proteins: small globular proteins. *Adv Protein Chem* **33**, 167–241
(1979).
28. O'Brien, E. P., Dima, R. I., Brooks, B. & Thirumalai, D. Interactions between Hydrophobic
and Ionic Solutes in Aqueous Guanidinium Chloride and Urea Solutions: Lessons for
Protein Denaturation Mechanism. *J. Am. Chem. Soc.* **129**, 7346–7353 (2007).
29. Stumpe, M. C. & Grubmüller, H. Interaction of Urea with Amino Acids: Implications for
Urea-Induced Protein Denaturation. *J. Am. Chem. Soc.* **129**, 16126–16131 (2007).
30. Skipper, N. T. & Neilson, G. W. X-ray and neutron diffraction studies on concentrated
aqueous solutions of sodium nitrate and silver nitrate. *J. Phys.: Condens. Matter* **1**, 4141
(1989).
31. Tielrooij, K. J., Garcia-Araez, N., Bonn, M. & Bakker, H. J. Cooperativity in Ion Hydration.
Science **328**, 1006–1009 (2010).
32. Jorgensen, W. L., Chandrasekhar, J., Madura, J. D., Impey, R. W. & Klein, M. L.
Comparison of simple potential functions for simulating liquid water. *The Journal of*
Chemical Physics **79**, 926–935 (1983).
33. Lin, S.-T., Maiti, P. K. & Goddard, W. A. I. Two-Phase Thermodynamic Model for Efficient
and Accurate Absolute Entropy of Water from Molecular Dynamics Simulations. *J. Phys.*
Chem. B **114**, 8191–8198 (2010).
34. Roget, S. A., Heck, T. R., Carter-Fenk, K. A. & Fayer, M. D. Ion/Water Network Structural
Dynamics in Highly Concentrated Lithium Chloride and Lithium Bromide Solutions Probed
with Ultrafast Infrared Spectroscopy. *J. Phys. Chem. B* **127**, 4532–4543 (2023).
35. Harano, Y. & Kinoshita, M. Translational-Entropy Gain of Solvent upon Protein Folding.
Biophys. J. **89**, 2701–2710 (2005).
36. Okur, H. I. *et al.* Beyond the Hofmeister Series: Ion-Specific Effects on Proteins and Their
Biological Functions. *J. Phys. Chem. B* **121**, 1997–2014 (2017).
37. Fiorin, G., Klein, M. L. & Hénin, J. Using collective variables to drive molecular dynamics
simulations. *Molecular Physics* **111**, 3345–3362 (2013).
38. Miserez, A., Wasko, S. S., Carpenter, C. F. & Waite, J. H. Non-entropic and reversible long-
range deformation of an encapsulating bioelastomer. *Nat Mater* **8**, 910–916 (2009).
39. Cera, L. *et al.* A bioinspired and hierarchically structured shape-memory material. *Nat Mater*
20, 242–249 (2021).

Methods

Additional methods

Additional methods, along with additional analyses and discussions, can be found in supplementary materials.

Escherichia coli dihydrofolate reductase expression

Cell culture. *E. coli* dihydrofolate reductase (DHFR, UniProt: P0ABQ4) (wild-type or W30C mutant) was overexpressed in BL21(DE3) *E. coli* cells. The plasmid was synthesized by GenScript Biotech with pET-28a(+) vector and C-terminus 6xHis-tag. All the cell culture were conducted in Terrific Broth (TB) medium (BD Difco™), supplemented with 0.4% (v/v) glycerol (RPI), 4 g L^{-1} glucose (Sigma-Aldrich), 25 mM MOPS (Sigma-Aldrich, pH=7.2), 0.4 mM citric acid (VWR Chemicals BDH®), 40 µl L^{-1} 1% (w/v) ferric ammonium citrate (AMRESCO) solution, and 50 µg ml^{-1} kanamycin (Millipore-Sigma). All the concentrations denoted here are final concentrations. 2% (v/v) frozen cell stock solution of BL21(DE3) *E. coli* cells transformed with DHFR (wild-type or W30C mutant) plasmid was used for a small overnight (~12 h) culture at 37 °C with shaking at 250 rpm. 2% (v/v) overnight culture solution was used to start the production culture, initially at 37 °C with shaking at 250 rpm. After 3.5 hours at which the cell growth started the mid-log phase with an optical density of around 0.6 at 600 nm, isopropyl β-D-thiogalactopyranoside (IPTG, RPI) was added to a final concentration of 100 µM to induce the protein overexpression. The temperature was decreased to 18 °C, with shaker speed kept as 250 rpm. The cell pellets were harvested after 12-hour low-temperature protein overexpression through centrifugation.

Protein purification. Three different buffers were used in DHFR protein purification: Lysis buffer [100 mM bicine (Sigma-Aldrich), 5 mM imidazole (Millipore-Sigma OmniPur®), 250 mM NaCl (VWR Chemicals BDH®), pH=9]; Buffer A [20 mM Tris (J.T. Baker™), 5 mM imidazole, 250 mM

441
442
443

NaCl, pH=8.5]; Buffer B [20 mM Tris, 50 mM imidazole, 250 mM NaCl, pH=8]. Every 1 g cell

pellet (from 50 ml cell culture solution) was resuspended in 1.5 ml lysis buffer, supplemented with

0.01% (v/v) Nuclease (Millipore-Sigma Benzonase®), 1% (v/v) Protease Inhibitor Cocktail Set II

(Millipore-Sigma Calbiochem®), and 1 mg ml^{-1} lysozyme (Thermo Fisher Scientific). All the

concentrations denoted here are final concentrations. The resuspended solution was then sonicated,

centrifuged with supernatant collected. cOmplete™ His-Tag Purification Resin (Roche) was used

to further isolate DHFR protein from supernatant in gravity flow columns (Bio-Rad). Buffer A

was first used to wash away non-bound proteins and other cell debris, followed by elution of Buffer

B, where DHFR was washed out and collected. Only the fractions with $A_{280}/A_{260} > 1.7$ were pooled

based on the absorbance measurement with a NanoDrop spectrophotometer (Thermo Fisher

Scientific). DHFR was then washed into 20 mM Tris buffered saline (pH=7.0, with 250 mM NaCl)

and concentrated into a final concentration of 3 mg ml^{-1} using ultrafilter (Sartorius Vivaspin®).

Mass spectrometry (Bruker Impact II q-TOF) was used to confirm that DHFR (both wild-type and

W30C mutant) was successfully synthesized and purified, after which protein solution was

aliquoted and stored in -70 °C.

Turbidity assay

Turbidity measurements at OD_{405} were performed using a Biotek PowerWave HT 340 microplate

reader. For each condition, protein solutions was mixed with solutions of LiBr, LiCl, and NaBr

(Sigma-Aldrich) to a final concentration of 0.4 mg ml^{-1} for DHFR or 0.1 mg ml^{-1} for human

fibronectin (BD Biosciences), with a total volume of 100 µl in a 96-well plate. Samples were then

immediately placed into the microplate reader and OD_{405} was continuously measured for 1 h at

room temperature. For keratin, 80 mg of cleaned wool (R. H. Lindsay Wool Company) was soaked

into 4 ml of salt solutions with 0.1 M DTT (Sigma-Aldrich) in quartz cuvettes, then heated to 70 °C

to accelerate the denaturation kinetics. Samples of the solutions were taken at 24 h and 48 h, added

into 96-well plate, and cooled at room temperature before OD_{405} measurement. Photos recording

the condition of the solution were taken after cooling the cuvette at room temperature for 1h.

FTIR and TG-FTIR

All FTIR measurements were conducted using a Nicolet iS50 FTIR spectrometer. Protein solutions

with final concentrations of 1 mg ml^{-1} DHFR, 0.5 mg ml^{-1} fibronectin, and 1 mg ml^{-1} keratin (α-

keratin from Angora wool, R. H. Lindsay Wool Company; β-keratin from goose down, Dream

Solutions USA), respectively, were prepared with a gradient of LiBr concentrations ranging from

0 to 8 M, then stabilized for at least 3 h prior to measurements. During acquisition, background

information was initially recorded by applying pure LiBr solutions onto the ATR crystal, which

was then replaced by the corresponding protein solutions, with a total of 64 scans collected for

each sample. Solid samples, including regenerated keratins and raw materials, were measured

using the same ATR-FTIR setup. Gas phase FTIR coupled with TGA was collected using the same

equipment connected to the Discovery TGA 550. Data analysis and background subtraction were

carried out with OMNIC v.9.2.86 software.

Raman and polarized Raman

Raman experiments were performed with a Horiba LabRam HR Evolution Raman confocal system

(633nm excitation, 50x, 0.5NA, 13mW). For DHFR experiment, a customized imaging chamber

made by sandwiching a 1 mm thick PDMS (Sylgard™ 184, Dow Corning) well between two glass

slides (Supplementary Fig. 4) was loaded with a solution of 3 mg ml^{-1} DHFR and 2 M LiBr. Each

spectrum was collected with 600 gr mm^{-1}, 180 s acquisition time and 2 accumulations. For solid

samples, 1800 gr mm^{-1}, 60 s acquisition and 4 accumulations were used. For polarized Raman, an

additional increment of 6° per step were applied with the highest intensity tracked around 1650

cm^{-1}. Data collection and analysis were carried out with Labspec v.6.5.1 software.

Dynamic light scattering

DLS experiments were performed using a Malvern Zeitasizer Pro system. Fibronectin in LiBr

solutions were prepared with a final concentration of 0.5 mg ml^{-1}, stabilized for at least 3 h, and

filtered through a 0.22 μm PTFE filter (VWR) before transferred into 40 μl cuvettes (Malvern

Panalytical) for measurement. Keratin solutions after extraction were diluted to approximately 1

mg ml^{-1}, filtered, then transferred into 1 ml cuvettes (Malvern Panalytical). Samples were heated

to 70 °C for 30 min, then stabilized at designated temperature for 10 min before measurement. A

reversible transition between smaller diameters at high temperature and larger diameters at low

temperature can be observed within individual samples. Data collection and analysis were carried

out with ZS Xplorer v.3.0.0.53 software.

Scanning electron microscopy

502 Samples were mounted on a 12.5 mm diameter SEM stub covered with carbon tape, then sputtered-

503 coated with Pt/Pd with an EMS 150T ES sputter coater with 10 nm thickness. SEM images were

504 taken with a Zeiss Gemini 360 field emission scanning electron microscope with an electric high

505 tension of 3 kV and SE2 detector.

Isothermal titration calorimetry

ITC experiments were conducted using a Malvern Panalytical MicroCal VP-ITC. During the

experiments, the sample chamber was filled with 1.8 ml of 1 mg ml^{-1} DHFR (W30C mutant)

solution or 0.5 mg ml^{-1} fibronectin solution, while the syringe was loaded with 100 μM solution

of LiBr, urea, or GdnHCl (Sigma-Aldrich). Corresponding control experiments were performed

by titrating milli-Q water into the same concentration of protein solution to measure and subtract

the dilution heat of proteins. Additionally, parallel control groups were also performed by titrating

100 μM ligands into a chamber filled with milli-Q water to measure the dilution heat of ligands,

which were found to be significantly smaller than the detectable binding enthalpy between proteins

and ligands (Supplementary Fig. 6). Each individual run comprised titrating 7 μl ligand solution

25 times into the chamber, with a duration of 12 s, and interval of 240 s, a filter period of 2 s, a stir

speed of 309, and temperature controlled at 30 °C. Data collection and analysis including baseline

adjustment and integration of enthalpy were carried out with VPViewer2000 v.1.29.1 software.

Molecular dynamics simulations

General simulation setup. All the molecular dynamics simulations were conducted with NAMD

2.14[40] and analyzed and visualized with VMD 1.9.3[41], unless otherwise denoted. Amber ff14SB

force field[42] were used for atomistic protein simulation, combined with TIP3P water model[43] for

explicit solvation and Li/Merz ion parameters[44] for monovalent ions. All initial configurations of

simulation box were prepared using tLEaP program[45], followed by minimization, heating, constant

pressure (NPT) equilibration, and constant volume (NVT) equilibration. All the production

simulations were run under constant particle number, constant volume, and constant temperature

(i.e., canonical ensemble (NVT)). Periodic boundary condition was applied to prevent the

boundary effect. Langevin thermostat with damping coefficient of 1 ps^{-1} was used to control

simulation temperature as 298 K, without coupling hydrogen atoms. Electrostatic and van der

Waals interactions were cut off beyond 12 Å. Particle Mesh Ewald (PME) method was employed

to deal with long-range electrostatic interactions. Rigid bond constraints between hydrogen and

any other atoms were applied through SHAKE/RATTLE algorithm. The integration time step was

set as 2 fs with short-range nonbonded forces updated every 2 fs and long-range electrostatic forces

updated every 4fs.

Initial configuration preparation and equilibration. To ensure that total number of ions and

water molecules are correctly determined for all salts and concentrations, we first decided the

simulation box sizes and thus ion numbers. All the simulation boxes were fixed to the size with

three dimensions around 50 Å. Water molecules were initially placed using tLEaP program[45], the

numbers of which were then adjusted according to volume changes after 100 ps minimization, 200

ps heating, and 2 ns constant pressure (NPT) equilibration. After the water molecule number

corrections, another round of 100 ps minimization, 200 ps heating, 2 ns constant pressure (NPT)

equilibration, plus 2 ns constant volume (NVT) equilibration, were conducted to ensure the correct

setup and complete equilibration of simulation systems.

Water structure characterization. The equilibrated initial configurations containing water

molecules and ions were prepared as stated above. The production simulations for water structure

characterization were run for 100 ns with trajectories recorded every 10 ps. The radial distribution

function *g(r)* between cations (or anions) and oxygen atoms of water can be used to characterize

local water structure around ions. It was calculated via VMD and averaged among all cations (or

anions) and all trajectory frames with the definition as

$$g(r) = \frac{dn_r}{4\pi r^2 \cdot dr \cdot \rho_{\text{bulk}}} \tag{2}$$

where dn_r is the number of oxygen atoms of water within the shell of thickness at the distance r,

$4\pi r^2 \cdot dr$ is the volume of the shell, ρ_{bulk} is the bulk average density of oxygen atoms of water in

the simulation box.

Water entropy calculation. The equilibrated initial configurations containing water molecules

and ions were prepared as stated above. The production simulations for water entropy calculation

were run for 20 ps[33] with trajectories recorded every 2 fs. All the water entropy calculations were

conducted based on Two-Phase Thermodynamic (2PT) model[33,46] using corresponding open

source program[47].

The resulting histograms were fit with two Gaussian distributions with no boundary

conditions. Initial values of peak centers were determined using local minimums of 2^{nd} derivative.

For LiBr and LiCl, fitting achieved convergence with Chi-Square tolerance value of 10^{-6}. For NaBr,

one peak will collapse to zero and only a single peak remained upon convergence.

Protein free energy landscape construction. To examine changes in free energy that drives

denaturation, we used metadynamics simulation to explore the free energy landscape of the

complex molecular system including water, ions, and protein. A short alanine-based peptide with

20 amino acids (AAAAKAAAAKAAAAKAAAAK), which has been confirmed experimentally[48]

to be a stable alpha helix structure in pure water, was adopted as the model protein to study the

difference of protein free energy landscapes under different concentrations of LiBr. We used

ColabFold v1.5.5[49] to obtain the initial atomistic protein structure, with N-terminus acetylated and

C-terminus amidated using PyMOL 2.5.5. The equilibrated initial configurations containing

protein, water molecules and ions were prepared as stated above. Well-tempered metadynamics

simulations were implemented for protein free energy landscape construction using Colvars

module[37] on top of standard molecular dynamics simulations as stated above. Root mean square

displacement (RMSD) from the backbone of native alpha helix protein structure was selected as

the collective variable to guide the sampling of unfolded confirmations. After the first run of

metadynamics simulation, two more protein confirmations (Supplementary Fig. 7a) with medium

RMSD (6 Å) and large RMSD (12 Å) respectively, were chosen as two other start structures. In

total, nine metadynamics simulations for each LiBr concentration, started from three different

initial protein conformations, were conducted. Each simulation was run for around 2 μs with

trajectory recorded every 100 ps (Supplementary Fig. 7b,c). Convergence of metadynamics

simulations was examined using block analysis via the open-source, community-developed

PLUMED library, version 2.8.3[50]. Six converged simulations out of nine for each LiBr

concentration were used for final protein free energy landscape construction (Supplementary Fig.

8-11).

Analytical model of entropy penalty decrease

The protein unfolding reaction is defined as

$$F \leftrightarrows U \tag{3}$$

where F is the folded state and U is the unfolded state. For folded proteins, since they can maintain

stable structures in pure water solution (or very low concentration NaCl solution), the free energy

change ΔG_{water} of the unfolding reaction in pure water should be positive, i.e.,

$$\Delta G_{\text{water}} > 0 \tag{4}$$

According to the unfolding experiments presented in this work, LiBr has the strongest

capability of unfolding (denaturing) proteins, followed by LiCl. NaBr cannot denature those tested

proteins in this work. Therefore, the free energy changes of the unfolding reaction in different

solution environments can be ranked as follow,

$$\Delta G_{\text{LiBr}} < \Delta G_{\text{LiCl}} < \Delta G_{\text{NaBr}} < \Delta G_{\text{water}} \tag{5}$$

where ΔG_{LiBr} and ΔG_{LiCl} for some proteins in high concentration salt solutions are negative (i.e.,

the unfolding reaction is favored).

The difference between free energy changes of the unfolding reaction in salt solutions

ΔG_{salt} and that in pure water ΔG_{water} can be written as

$$\begin{aligned}\Delta\Delta G &= \Delta G_{\text{salt}} - \Delta G_{\text{water}} < 0 \\ &= \Delta H_{\text{salt}} - \Delta H_{\text{water}} - T\Delta S_{\text{salt}} - (-T\Delta S_{\text{water}}) \\ &= \Delta\Delta H - T\Delta\Delta S\end{aligned} \tag{6}$$

where enthalpy change difference $\Delta\Delta H$ equals to 0 given the ITC data (Fig. 2a-b) that no direct

interaction between proteins and ions was observed. Thus, we have

604
$$\Delta\Delta G = -T\Delta\Delta S < 0 \tag{7}$$

605   where $\Delta\Delta S$ is the entropy penalty decrease due to high concentration salts and should be positive.

606   Entropy penalty decrease caused by high concentration salts can be written as

607
$$\begin{aligned} \Delta\Delta S &= \Delta S_{\text{salt}} - \Delta S_{\text{water}} > 0 \\ &= \Delta S_{\text{salt}}^{\text{protein}} + \Delta S_{\text{salt}}^{\text{solution}} - \left(\Delta S_{\text{water}}^{\text{protein}} + \Delta S_{\text{water}}^{\text{solution}} \right) \\ &= \Delta S_{\text{salt}}^{\text{solution}} - \Delta S_{\text{water}}^{\text{solution}} \end{aligned} \tag{8}$$

where protein conformational entropy changes $\Delta S^{\text{protein}}$ during unfolding is independent of

solutions and thus cancel with each other, $\Delta S^{\text{solution}}$ is the solution entropy change.

The solution entropy S^{solution} is composed of two parts, i.e., molecular entropy and network

entropy. Molecular entropy is composed of translational, rotational, and vibrational entropy of

water molecules themselves. Network entropy comes from the collective behavior of water

network, which considers different combinations water molecules can have to form a network.

Therefore, the solution entropy change during protein unfolding can be expressed as

615
$$\Delta S^{\text{solution}} = \Delta S^{\text{translation}} + \Delta S^{\text{rotation}} + \Delta S^{\text{vibration}} + \Delta S^{\text{network}} \tag{9}$$

616   Consider a water network with N water molecules (so-called *free* water molecules since

617   they are not bound by either proteins or ions), the number of microstates for each water molecule

618   inside the network can be expressed as

619
$$\Omega = \left(N^{\text{free}} - 1 \right)\left(N^{\text{free}} - 2 \right)\left(N^{\text{free}} - 3 \right)\left(N^{\text{free}} - 4 \right) \tag{10}$$

620   given one water molecule can form four hydrogen bonds with other water molecules in the network.

621   Then the network entropy of each water molecule is

622
$$S^{\text{network}} = k_{\text{B}} \ln(\Omega) = k_{\text{B}} \ln\left(\left(N^{\text{free}} - 1 \right)\left(N^{\text{free}} - 2 \right)\left(N^{\text{free}} - 3 \right)\left(N^{\text{free}} - 4 \right) \right) \tag{11}$$

623   where

624
$$\Delta S^{\text{network}} = -k_{\text{B}} \ln\left((N^{\text{free}} - 1)(N^{\text{free}} - 2)(N^{\text{free}} - 3)(N^{\text{free}} - 4)\right) \qquad (12)$$

625   The entropy penalty decrease originated from the shrinkage of intact water network size in

626   high salt concentration systems can be expressed as

627
$$\begin{aligned}
\Delta\Delta S^{\text{network}} &= \Delta S_{\text{salt}}^{\text{network}} - \Delta S_{\text{water}}^{\text{network}} \\
&= -k_{\text{B}} \ln\left(\frac{(N_{\text{salt}}^{\text{free}} - 1)(N_{\text{salt}}^{\text{free}} - 2)(N_{\text{salt}}^{\text{free}} - 3)(N_{\text{salt}}^{\text{free}} - 4)}{(N_{\text{water}}^{\text{total}} - 1)(N_{\text{water}}^{\text{total}} - 2)(N_{\text{water}}^{\text{total}} - 3)(N_{\text{water}}^{\text{total}} - 4)}\right) \\
&\doteq -4k_{\text{B}} \ln\left(\frac{N_{\text{salt}}^{\text{free}}}{N_{\text{water}}^{\text{total}}}\right) \\
&= -4k_{\text{B}} \ln \phi
\end{aligned} \qquad (13)$$

628   where $N_{\text{water}}^{\text{total}}$ is the total number of water molecules in pure water systems as all water molecules

629   here are considered as *free* , both $N_{\text{salt}}^{\text{free}}$ and $N_{\text{water}}^{\text{total}}$ are normally much larger than 1 (i.e., $\gg 1$), $\phi =$

630    $\frac{N_{\text{salt}}^{\text{free}}}{N_{\text{water}}^{\text{total}}}$ is the ratio of free water number in salt solution to that of pure water system.

631   Finally, we have

632
$$\begin{aligned}
\Delta\Delta S &= \Delta S_{\text{salt}}^{\text{solution}} - \Delta S_{\text{water}}^{\text{solution}} \\
&= \Delta\Delta S^{\text{translation}} + \Delta\Delta S^{\text{rotation}} + \Delta\Delta S^{\text{vibration}} + \Delta S^{\text{network}} \\
&= \Delta\Delta S^{\text{translation}} + \Delta\Delta S^{\text{rotation}} + \Delta\Delta S^{\text{vibration}} - 4k_{\text{B}} \ln \phi
\end{aligned} \qquad (14)$$

633   where $\Delta\Delta S^{\text{translation}}$, $\Delta\Delta S^{\text{rotation}}$, and $\Delta\Delta S^{\text{vibration}}$ can be expressed as follows,

634
$$\begin{aligned}
\Delta\Delta S^{\text{j}} &= \Delta S_{\text{salt}}^{\text{j}} - \Delta S_{\text{water}}^{\text{j}} \\
&= \left(S_{\text{salt}}^{\text{j-bound}} - S_{\text{salt}}^{\text{j-free}}\right) - \left(S_{\text{water}}^{\text{j-bound}} - S_{\text{water}}^{\text{j-free}}\right) \\
&= S_{\text{water}}^{\text{j-free}} - S_{\text{salt}}^{\text{j-free}}
\end{aligned} \qquad (15)$$

635   where j denotes translational or rotational or vibrational components of solution entropy, the S^{j} of

636   bound water molecules by proteins are assumed to be independent of their solution environments

637   and thus cancel out each other. All the parameters in above equation ($\Delta\Delta S^{\text{translation}}$, $\Delta\Delta S^{\text{rotation}}$,

638    $\Delta\Delta S^{\text{vibration}}$, and ϕ) can be obtained through molecular dynamics simulation and Two-Phase

639   Thermodynamic (2PT) calculation[33,46].

Keratin extraction protocol

The pretreatment of keratin-rich sources (Angora wool, Merino wool shirt, and goose down from

the R. H. Lindsay Wool Company, Merino Tech, and Dream Solutions USA, respectively)

involves washing with ethanol (VWR 200 proof) in a Soxhlet extractor for 48 h to remove organic

residues, followed by rinsing with water and allowing the material to dry at room temperature

overnight. Subsequently, long wool fibers were cut into smaller fragments (less than 1 cm in length)

to facilitate dispersion in solution. During the extraction process, 10 g of keratin fragments were

suspended in a 150 ml aqueous solution containing 8 M LiBr and 0.1 M DTT. The suspension was

stirred for 36 h in an insulated environment at 90°C. Afterwards, insoluble residues were filtered

through cotton cloth with 80/180 μm mesh size while still hot, then stored at 4°C overnight. A

viscous, gel phase of aggregated keratin was observed, and centrifugation (3,000 r.p.m., 4°C)

further separated the mixture into an upper phase of LiBr solution and a lower phase of keratin gel.

The LiBr solution could then be easily collected and reused in the following extraction cycle along

with a new batch of keratin source and DTT. A small amount of 8 M LiBr stock solution were

added to compensate the solution loss from filtration process in order to maintain the total volume

at 150 ml.

The keratin content of the aggregated gel was measured by taking 1 ml of gel and allowing

it to fully solidify in water, freeze-dried, then lyophilized to obtain a dehydrated solid and measure

its weight. It was found that 1 ml of keratin gel contains 392.8 ± 18.6 mg of α-keratin or $347.9 \pm$

23.7 mg of β-keratin (n = 6). To calculate the extraction yield, the volume of the keratin gel

obtained from each batch was measured, multiplied by the corresponding content, and divided by

the initial weight of keratin fragments. The denatured keratin gel could be stably stored at 4°C in

the absence of oxygen, with a shelf life longer than 6 months.

Thermogravimetric analysis

TGA of the LiBr solution prior to the 1st cycle and the recycled LiBr solution after the 5th cycle were conducted with a Discovery TGA 550. Around 30 mg of solution was loaded onto a platinum HT sample pan, stabilized under nitrogen flow for 10 min before measurement. Experiments were performed by heating samples to 100 °C at a rate of 5 °C min^{-1}, then to 600 °C at a rate of 10 °C min^{-1} in an air flow of 90 ml min^{-1}. The mass of the sample was continuously measured while the evolving gas from the sample was analyzed simultaneously by TG-FTIR. Data collection and analysis were carried out with TRIOS v.5.2.2 software.

Sample preparation

All samples were regenerated using α-keratin gel unless otherwise noted. The reverse mold for injection molding was created by casting PDMS (Sylgard™ 184, Dow Corning) around a 3D printed logo. Keratin gel was injected into the mold and transferred into a water bath until solidified. Film casting and dip coating followed a similar process by casting a layer of gel on glass coverslip or coating targets, then transferred into a water bath. Fiber spinning was achieved by injecting the gel through a 21 gauge needle (BD PrecisionGlide™) at a constant rate of 0.1 ml min^{-1} into a bath of 0.4 M NaH$_2$PO$_4$ (Sigma-Aldrich) solution to accelerate the phase transition process. 3D printing was carried out using a Cellink BIO X 3D printer. The keratin gel was extruded into a supporting bath of 25% w/v Pluronic F127 (BASF) under an absolute pressure of 50 kPa and through a 22 gauge needle (Nordson EFD Precision Tips) that was moving at a speed of 4 mm s^{-1}. The Pluronic bath was then removed by cooling and rinsing with water.

Keratin samples for mechanical tests, Raman and polarized Raman spectra were prepared by film casting a layer of keratin gel onto glass coverslips with a thickness around 0.4 mm, then transferred into a water bath to solidify the gel. Oxidized samples were fabricated by further

transferring into a solution of 1% H_2O_2 for 1 h to reconnect the disulfide bonds. Finally, samples

were sectioned into 5 × 20 mm rectangles and stored in water prior to measurements.

The tensegrity structure for the shape memory demonstration was created by oxidizing keratin

films in a curled permanent state to form columns as compression units. These units were then

interconnected with nylon threads (Singer®) to serve as tension units. Samples were fixed in a

distorted temporary state by desiccating for 90 min with addition of external stress.

Mechanical tests

Mechanical tests were performed with a CellScale biaxial tester with 2.5 N load cells. For cyclic

stretching curves, samples were tested at a strain rate of 5% per second to a maximum of 50% for

10 cycles. For yield strain measurements, samples were tested at a strain rate of 5% until fracture.

Sample thickness was measured with a Mitutoyo Absolute Digimatic digital caliper. The modulus

of reduced and oxidized samples was calculated within the 0-50% strain region.

Data availability

700   All the source data can be readily accessed via

701   https://osf.io/kwmqg/?view_only=62f20b64abb24c4c9ca6e0518f99eecb

Code availability

704   All the customized codes used for data analysis are available at

705   https://github.com/junlang-liu/Entropy_code.

Methods Section References

40. Phillips, J. C. *et al.* Scalable molecular dynamics on CPU and GPU architectures with NAMD. *J Chem Phys* **153**, 044130 (2020).

41. Humphrey, W., Dalke, A. & Schulten, K. VMD: Visual molecular dynamics. *Journal of Molecular Graphics* **14**, 33–38 (1996).

42. Maier, J. A. *et al.* ff14SB: Improving the Accuracy of Protein Side Chain and Backbone Parameters from ff99SB. *J. Chem. Theory Comput.* **11**, 3696–3713 (2015).

43. Price, D. J. & Brooks, C. L. A modified TIP3P water potential for simulation with Ewald summation. *J Chem Phys* **121**, 10096–10103 (2004).

44. Li, P., Song, L. F. & Merz, K. M. Jr. Parameterization of Highly Charged Metal Ions Using the 12-6-4 LJ-Type Nonbonded Model in Explicit Water. *J. Phys. Chem. B* **119**, 883–895 (2015).

45. Case, D. A. *et al.* The Amber biomolecular simulation programs. *Journal of Computational Chemistry* **26**, 1668–1688 (2005).

46. Lin, S.-T., Blanco, M. & Goddard, W. A., III. The two-phase model for calculating thermodynamic properties of liquids from molecular dynamics: Validation for the phase diagram of Lennard-Jones fluids. *The Journal of Chemical Physics* **119**, 11792–11805 (2003).

47. https://github.com/atlas-nano/2PT.

48. Marqusee, S., Robbins, V. H. & Baldwin, R. L. Unusually stable helix formation in short alanine-based peptides. *Proc Natl Acad Sci U S A* **86**, 5286–5290 (1989).

49. Mirdita, M. *et al.* ColabFold: making protein folding accessible to all. *Nat Methods* **19**, 679–682 (2022).

50. Tribello, G. A., Bonomi, M., Branduardi, D., Camilloni, C. & Bussi, G. PLUMED 2: New feathers for an old bird. *Computer Physics Communications* **185**, 604–613 (2014).

Acknowledgements We thank M. Rosnach for photography and illustrations, S. Mondal for
suggestions on molecular simulations, K. Park, E. Serebryany and A. Bitran for discussions on
water structure and protein denaturation mechanisms, H. Chang and J. F. Zimmerman for
discussions on material properties. K. Shani and Y. Jang for discussions on biological properties
and tissue engineering potential of keratin. This work was sponsored by National Institutes of
Health (R35GM139571 and R01EY030444 to E.I.S), the John A. Paulson School of Engineering
and Applied Sciences at Harvard University (K.K.P.), the National Science Foundation through
the Harvard University Materials Research Science and Engineering Center (DMR-2011754 to
K.K.P.), the Health@InnoHK program of the Innovation and Technology Commission of the Hong
Kong SAR Government, and the Medical & Health Informatics Laboratories at NTT Research,
Inc. This work was performed in part at the Harvard University Center for Nanoscale Systems
(CNS), a member of the National Nanotechnology Coordinated Infrastructure Network (NNCI),
which is supported by the National Science Foundation under NSF award no. ECCS-2025158. The
content is solely the responsibility of the authors and does not necessarily represent the official
views of NTT Research, Inc.

Author contributions Y.W., J.L., K.K.P., and E.I.S. designed and developed the project. Y.W.
and J.L. performed turbidity measurements, tryptophan fluorescence, and FTIR. Y.W., J.L., and
D.W. performed ITC experiments. Y.W., J.L., and S.C. performed Raman experiments. J.L. did *E.*
coli cell culture, DHFR protein purification and quality control. J.L. conceived the entropy-driven
model and developed the analytical model. J.L. conducted all the simulations and related data
analysis. Y.W. performed TG-FTIR, polarized Raman, DLS, and TGA measurements. Y.W.
performed keratin extraction, demonstrations, and mechanical tests. Y.W. and M.M.P. fabricated
keratin fibers and performed SEM imaging. Y.W. and R.I. did SDS-PAGE. Y.W. and J.L. prepared
the initial manuscript. Y.W., J.L., K.K.P., and E.I.S. revised the manuscript, with contributions
from all the other authors. K.K.P. and E.I.S. supervised the research.

Competing interests A US patent application on the methods for extraction and regeneration of
protein wastes has been filed by Harvard University (assignors: Y.W., J.L., K.K.P., and E.I.S.).

Additional information
Supplementary information Supplementary Information is available for this paper.
Correspondence and requests for materials should be addressed to Eugene I. Shakhnovich or
Kevin Kit Parker
Peer review information
Reprints and permissions information

Extended Figures

768
Extended Data Fig. 1 | Sustainable regeneration of protein waste empowered by entropy-driven
protein denaturation. Upper, Traditional denaturation methods using urea or guanidine hydrochloride
involve direct protein-denaturant interactions, which not only lead to difficulties in protein separation and
further applications but also result in plenty of waste and pollution. **Lower,** Due to the absence of direct
protein-denaturant interactions, entropy-driven protein denaturation via LiBr enables the sustainable
regeneration of protein waste, featured by closed-loop LiBr recycling, simple protein separation, and facile
further manufacturing.

776
Extended Data Fig. 2 | LiBr, LiCl, and NaBr exhibit different levels of protein conformational change
and denaturation capability. a-b, FTIR of the amide I band of DHFR in different concentrations of LiCl
(a) and NaBr (b). **c-d,** FTIR of the amide I band of fibronectin in different concentrations of LiCl (c) and
NaBr (d). **e,** DHFR unfolding curve in LiCl solution measured by tryptophan fluorescence (dots) and fitted
by two-state model (dash lines). Data are presented as mean ± s.d. (n = 3). **f,** Schematics of fibronectin
conformational changes under different LiBr concentrations as cross-referenced from FTIR and DLS
experiments. Fibronectin conformations start from globular state (0 M), to extended state (~2 M), to
aggregation of extended state (4 M-6 M) until aggregation of denatured state (>6 M). **g**, SEM image of
wool prior (i) and after 48-hour denaturation with 8 M LiBr (ii), 8 M LiCl (iii), and 7 M NaBr (iv). SEM
image of feather prior to (v) and after (vi) 48-hour denaturation with 8 M LiBr. Scale bars, 50 μm.

787
Extended Data Fig. 3 | Local and global effects of ions on water dynamics. a, Radial distribution
function *g(r)* of oxygen atoms of water molecules around respective cations (solid) and anions (dashed) in
7 M LiBr, LiCl, and NaBr solution. **b,** Water density at first hydration shell around respective cations (solid)
and anions (dashed) in different concentrations of LiBr, LiCl, and NaBr. **c,** Schematics of different ion
effects on water dynamics. For LiBr and LiCl, high charge density of Li$^+$ ion results in localized (bound)
water molecules and disrupted water network (left), while NaBr changes water dynamics in a more global
manner without breakingK water networks (right). **d-f,** Water molecular entropy distribution in LiBr, LiCl,
and NaBr, respectively, at different concentrations.

796
797 **Extended Data Fig. 4 | Properties of keratin during regeneration process and TG-FTIR of recycled**
798 **LiBr solution. a,** Keratin content of aggregated gel after separation. Data are presented as mean ± s.d. (n =
799 6). **b-c,** Size distribution of denatured keratin in 8 M LiBr solution suggests a spontaneous aggregation as
800 temperature decrease from DLS. **d-e**, TG-FTIR of the LiBr solution recycled after keratin separation.

801
Extended Data Fig. 5 | Mechanical properties and structural behavior of regenerated keratin under
stress. a, Polarized Raman of reduced keratin sample. The anisotropy of keratin under 50% strain suggests
stretch-induced rearrangement of helices. **b-c,** Stress-strain curve of regenerated keratin in reduced state (b)
and oxidated state (c). Data are presented as mean ± s.d. (n = 4). **d-e**, Fracture strain and fracture stress of
regenerated keratin in reduced state and oxidized state. Data are presented as mean ± s.d. (n = 6). **f,** Raman
spectra of the amide I band of reduced and oxidized keratin under 50% strain. A more significant change
of secondary structures within an oxidized sample indicates the uncoiling of helices.