Opto-Myomatrix: µLED integrated microelectrode arrays for optogenetic activation and electrical recording in muscle tissue

Jiaao Lu[1], *Student Member, IEEE*, Muneeb Zia[1], Danish A. Baig[1], Geyu Yan[1], Jeong Jun Kim[2], Kailash Nagapudi[3], Philip Anschutz[1], Shane Oh[1], *Student Member, IEEE*, Daniel O'Connor[2], Samuel J. Sober[3], and Muhannad S. Bakir[1], *Senior Member, IEEE*

Abstract—Optogenetics is a valuable and widely-used technique that allows precise perturbations of selected groups of cells with high temporal and spatial resolution by using optical systems and genetic engineering technologies. Although numerous studies have been done to investigate optogenetic tools used in the brain and central nervous system (CNS), there has been limited progress in developing similar tools for optogenetic muscle stimulation. This paper introduces Opto-Myomatrix, a novel optogenetic tool designed for precise muscle fiber control and high-resolution recording. Based on a flexible and biocompatible polymer substrate, the device incorporates an integrated µLED that delivers light at 465 nm for optogenetic stimulation and 32 low-impedance electrodes for electromyography (EMG) recording. A reflector is also added to the device to improve optical power output by nearly 100% in the direction of interest. Compared to uncoated electrical contacts, the PEDOT:PSS-coated recording electrodes possess an average impedance that is 85% lower, ensuring high signal-to-noise EMG acquisition. To evaluate the potential risk of thermal tissue damage, we measured and simulated the heat dissipation characteristics of the µLED. This analysis aimed to ensure that the maximum temperature change remains within a safe range. The Opto-Myomatrix device was implanted in transgenetic mice and successfully stimulated targeted jaw muscles, inducing movement while simultaneously capturing EMG signals.

Index Terms—Optogenetics, electromyography (EMG), flexible microelectrode arrays (MEAs), µLED

I. INTRODUCTION

Optogenetics is a unique technique that incorporates genetic engineering and optical systems to control the activity of cells with high precision. This technique employs opsins, which are light-sensitive proteins that can be engineered for expression in cell membranes. These genetically modified cells can then be excited or inhibited using visible light at select wavelengths [1], [2]. One of the key advantages of optogenetics is its ability to precisely control neuronal spiking on a millisecond timescale [3], which is achieved by the rapid response of opsins to light. Such temporal resolution aligns closely with the natural timing of neural activity and is invaluable for studying dynamic neural processes. Additionally, optogenetics can target specific cell types within neural circuits by using cell-type-specific promoters, which direct opsin expression exclusively in designated cells [4]. This enables selective activation of the targeted muscle or nerve cells, avoiding less precise control seen with other neuralmodulation techniques such as deep brain stimulation (DBS) or functional electrical stimulation (FES). Another valuable feature provided by optogenetics is that several opsins can be expressed in a single cell, which allows selective excitation and inhibition at their corresponding wavelengths [5]–[7]. This versatile manipulation of cellular activity further enhances the complexity and detail of cellular behavior studies.

Building on these foundational advantages, applying optogenetic techniques in muscle opens new avenues for understanding muscle function and disorders. The precision and specificity of optogenetics provide distinctive tools for mapping and controlling muscle fibers, thus allowing targeted treatments and rehabilitation strategies [8]. Most current research on optical stimulation in muscle fiber utilize lasers as a light source and separate fine-wire or needle electrodes to record electromyography (EMG) signals [9]–[13]. However, although lasers have high light intensity and low beam divergence, they suffer from high power consumption, bulky size, and tethered optical and communication systems restricting the natural behavior of freely moving animals [1]. Moreover, fine-wire and needle electrodes primarily capture bulk EMG from multiple motor units, while for comprehensive computational analysis, it is crucial to identify signals from single motor units [14], [15]. Hence, in muscle optogenetics, there is a need for devices capable of simultaneous light delivery and electrophysiological recording to investigate the causal relationship between neuronal activation and behavior. A promising alternative light source is µLEDs, which are often chosen in optical neural implants developed for brain tissues, due to their compact size, lightweight design, low power consumption, and rapid modulation capability [16]–[21]. For electrical signal acquisition from muscle, high-density, flexible microelectrode

[1] Jiaao Lu, Muneeb Zia, Danish A. Baig, Geyu Yan, Philip Anschutz, Shane Oh and Muhannad S. Bakir are with the Department of Electrical and Computer Engineering, Georgia Institute of Technology, Atlanta, GA 30332, USA. Contact: `jiaaolu@gatech.edu, mbakir@ece.gatech.edu`

[2] Jeong Jun Kim, and Daniel O'Connor are with Solomon H. Snyder Department of Neuroscience, Johns Hopkins School of Medicine, Baltimore, MD 21218, USA.

[3] Kailash Nagapudi and Samuel J. Sober are with the Department of Biology, Emory University, Atlanta, GA 30322, USA. Contact: `samuel.j.sober@emory.edu`

arrays (MEA) are a recently developed tool positioned directly on muscle fiber that can detect motor units activated by a single motor neuron. Incorporating µLEDs into flexible MEA provides the means to obtain accurate recording of neural activities corresponding to optical stimulation with different spatial distributions. It also alleviates the complexity of the surgery process as only one device needs to be implanted [21].

In this work, we propose Opto-Myomatrix, a µLED-integrated flexible microelectrode array, to realize simultaneous optical stimulation in muscle fiber and high-resolution EMG recording. The device consists of 32-channel recording electrodes and a µLED chip to deliver light stimulation at 465 nm. In order to increase optical intensity in the direction of interest, an aluminum reflector underneath the µLED chip was fabricated, and optical characterization of the device was conducted, demonstrating enhanced optical output power suitable for optogenetics stimulation in skeletal muscle. To further improve electrochemical performance, poly(3,4-ethylenedioxythiophene)-poly(styrenesulfonate) (PEDOT:PSS) was applied on all recording electrodes to achieve lower impedance, hence achieving a high signal-to-noise ratio. Both thermal characterization and finite element simulation of the µLED on a flexible array were presented to verify the temperature rise from the device remains safe for muscle stimulation. Finally, we implanted the Opto-Myomatrix device in transgenic mice to optically stimulate jaw muscles, inducing jaw movement, and to collect EMG signals at the same time.

II. DESIGN AND FABRICATION

A. Design concept

Fig. 1 presents the schematic of the Opto-Myomatrix: one µLED chip for optical stimulation is positioned at the center of an array of 32 electrodes for EMG recording. The µLED chip (CREE® TR2227™, Cree, Inc., USA) has a peak wavelength at 465 nm, which falls within the activation range for Channelrhodopsin-2 (ChR2) [3]. It is connected to two traces for power supply and encapsulated by transparent polydimethylsiloxane (PDMS). Given that the bare µLED chip emits light in every direction, we introduce a reflector placed underneath the µLED (as shown in the blue inset in Fig. 1). This design aims to redirect the light emitted from the backside forward, thereby enhancing the optical power output in the desired direction. The 32 recording electrodes surrounding the µLED each has a footprint of 200×100 µm^2, and are coated with a thin layer of PEDOT:PSS (yellow inset in Fig. 1) to improve electrochemical performance. All the metal traces and electrodes are sandwiched between two layers of flexible and biocompatible polyimide. The thicknesses of the substrate and the encapsulation layers are 10 µm and 5 µm respectively. A shallow trench is etched on the top polyimide layer to place the µLED. The size of the trench is designed to appropriately fit the chip with a footprint of 220×270 µm^2 and a thickness of 50 µm.

B. Fabrication process

The fabrication process for Opto-Myomatrix is adapted from previous works on flexible MEAs [22]–[24] and is

Fig. 1. 3D schematic of the Opto-Myomatrix. The device consists of 32 recording electrodes coated with PEDOT:PSS and a µLED chip at the center.

summarized in Fig 2. A detailed fabrication procedure is described in the following sections.

1) Flexible microelectrode array: A 4-inch silicon wafer was utilized as the carrier substrate. After cleaning by acetone, methanol and isopropanol consecutively, and drying by compressed nitrogen, the wafer was spin-coated with a layer of polyimide (Pyralin 2611, HD MicroSystems™ L.L.C., USA) (Fig. 2(a)). The spin speed was set at 1500 RPM to precisely control the thickness of the bottom layer to be 10 µm. This specific thickness ensures the polymer substrate maintains both flexibility and durability through out the *in vivo* implantation process. The polyimide was then cured in a programmable oven at a maximum temperature of 320°C for 45 minutes. To form the traces and electrodes on the polyimide layer, negative photoresist (AZ® nLOF 2020, Microchemicals GmbH, Germany) was patterned, followed by thermal evaporation of titanium (20 nm) and gold (300 nm), and lift-off of the films in acetone (Fig. 2(b)). Subsequently, another layer of polyimide was formed by spinning at 4000 RPM and curing in an oven, serving as the top insulation layer. The top polyimide layer was etched with a reactive ion etching (RIE) process using a photoresist mask (MICROPOSIT™ S1827®, Kayaku Advanced Materials, Inc., USA), to expose the recording electrodes, contact pads for µLED, and connector pads (Fig. 2(d)). Next, an aqueous solution of PEDOT:PSS (PH 1000 PEDOT:PSS, Oscilla, UK) was spin-coated on the wafer and patterned via a lift-off process (Fig. 2(e)). This step selectively coats PEDOT:PSS only on recording electrodes to achieve lower impedance.

2) Reflection layer: As stated in Section II-A, the µLED chips have a colorless SiC substrate and emit light from all directions. However, in skeletal muscle stimulation, it is critical to maximize optical power output normal to the same face as the recording electrodes. Thus, we added a "mirror" layer underneath the LED chip to reflect back the light emitted towards the substrate of the device. The reflection layer consists of 100 nm of aluminum that was deposited and patterned via a lift-off process (Fig. 2(c)). A gap of 5µm was designed between the reflector and metal trace, to avoid a short circuit path through aluminum. Reflectors with different

shapes and sizes were fabricated and tested to investigate the most efficient geometry.

3) µLED chip bonding and encapsulation: During the RIE process of the top polyimide layer (Fig. 2 (d)), shallow trenches of 230×280 µm^2 were formed at the center of 32 electrode array. This process also exposed the contact pads to connect to the anode and cathode of µLED chip. The µLED chip was then attached to the wafer using a flip-chip bonder (FINEPLACER® Lambda 2, Finetech GmbH & Co. KG, Germany) (Fig. 2(f)). Thermocompression bonding was conducted by heating the chip to 290°C for 5 minutes and applying 8 N of force uniformly at the same time. Consequently, atomic interactions between the gold surface of the traces on the wafer and the anode/cathode on the µLED chip created metallic bonds at the interface, forming a strong and durable ohmic contact.

To encapsulate the µLED chips and to enhance the mechanical stability of the device, we carefully applied a thin layer of optically transparent PDMS only to cover the µLED chips (Fig. 2(g)). This is vital in preventing corrosion of the chips or deformation of the bonding due moisture from tissue fluids when implanted *in vivo*.

4) Device release and assembly: After µLED bonding, the outline of device was precisely cut through the polyimide layer using a femtosecond laser (OPTEC WS-Flex USP, OPTEC S.A., Belgium). Finally, the array was peeled off the silicon wafer to complete the release. A 32-channel Omnetics connector was assembled with anisotropic conductive film (ACF) tape for multichannel neural recording, while the µLED power would be supplied by wires connected by conductive epoxy (Fig. 2(i)).

C. Fabricated device

Fig. 3(a) and (c) show microscope and SEM images of the fabricated Opto-Myomatrix. The µLED chip is successfully flip-chip bonded on flexible MEA in the shallow trench on polyimide layer. When activated by current (Fig. 3(a)), the µLED emits blue light at 465 nm, aligning with the activation wavelength for ChR2, thereby enabling targeted optogenetic stimulation. The blue inset in Fig. 3(a) presents the circular reflector with diameter of 500 µm that is added underneath the µLED chip to enhance optical intensity of the Opto-Myomatrix device. The SEM image also shows that the top surface of the PDMS layer is above the surface of polyimide substrate while the PEDOT:PSS layer of electrodes is slightly below the surface. This is due to the geometry of µLED chip we selected and the etching process of top polyimide layer to expose recording electrodes. The surface profile of µLED chip covered by PDMS is captured using surface profilometry (Fig. 3(b)). The maximum height at the center of the µLED chip is less than 60 µm. Considering that the thickness of the µLED chip is 50 µm, this maximum height indicates that the µLED chip is completely encapsulated by the PDMS layer, which has a thickness of less than 10 µm. The total thickness has been validated through *in vivo* experiments, ensuring that all electrodes can establish contact with muscle fibers and effectively record EMG signals (see Section IV). The released

Fig. 2. Fabrication process of Opto-Myomatrix. (a) Bottom polyimide coating. (b) Trace and electrode metal deposition. (c) Reflector metal deposition. (d) Top polyimide coating and patterning. (e) PEDOT:PSS coating and patterning. (f) µLED flip-chip bonding. (g) PDMS encapsulation. (h) Laser dicing. (i) Device release and connectorization.

Opto-Myomatrix is shown in Fig. 3 (d), where the curve of the subsrate was formed by applying a bending force manually, demonstrating the device's flexibility. As shown in the figure, the µLED is turned on with no loss in optical power. This indicates that the bending stress results in very little or no piezoelectric field change [25] and does not affect the bonding strength of the µLED chip, exhibiting a great potential for minimally invasive optical stimulation and physiological recording.

III. RESULTS AND DISCUSSION

A. Optical characterization

In order to evaluate the optical performance of fabricated Opto-Myomatrix and to assess the improvement from reflector design, optical power output from µLEDs was measured at a wavelength of 465 nm with a power meter (PM100A, Thorlabs, Inc., USA) and a photodiode sensor (S120VC, Thorlabs, Inc., USA). Three types of reflectors were tested: circular shape with diameter of 500 and 1000 µm, and square shape with side length of 1000 µm. The µLED encapsulated in PDMS was placed as close as possible to the surface of the sensor, while a controlled DC power supply (E3610A 30-Watts DC Power Supply, HP Development Company, L.P., USA) was connected to supply current to the anode and cathode of the

Fig. 3. Fabricated Opto-Myomatrix. (a) A microscope image of all recording electrodes and µLED of Opto-Myomatrix on wafer; the inset shows the circular reflector with diameter of 500 µm. (b) Surface profilometry results for the µLED chip covered with a thin layer of PDMS on a flexible substrate. (c) An SEM image of the electrodes and µLED chip encapsulated in PDMS. (d) An optical image of released Opto-Myomatrix device under bending stress.

µLED. This setup aims to replicate the effect of stimulating muscle tissue, with the Opto-Myomatrix directly in contact with the muscle. The experiment setup was placed in air at room temperature and the optical intensity was calculated by dividing the measured power by total surface area of µLED (220×270 µm^2).

Fig. 4. Optical measurement results. (a) Driving current vs. optical power output at 465 nm from the µLED with three types of reflectors (n=4). (b) Optical power output measured from front and back side at 10 mA of supplied current with and without reflectors (n=4).

As shown in Fig. 4(a), the Opto-Myomatrix with bare µLED can achieve optical intensity of 5.93 to 66.20 mW/mm^2 with supplied current from 1 to 20 mA. This indicates that at very low driving currents, our device exceeds the optical intensity typically required to activate ChR2 (1 mW/mm^2) [26]. Additionally, the reflector design further increased the optical intensity. With the smallest reflector (500 µm dia.), the optical power is enhanced by at least 1.5x. Moreover, the larger circular reflector (1000 µm in diameter) even intensified the optical power by approximately 2x, with the highest intensity of 129.46 mW/mm^2. Although the square reflector with 1000 µm side length has a larger footprint area, the average optical power measured is slightly lower than that with circular design.

As stated in Section II-A, the µLED chip employed in this work emits light in all directions. Hence, we conducted another set of measurements to obtain the optical power "leakage" from the backside of the device to further ensure the reflector design effectively prevents light leakage. In Fig. 4 (b), constant current of 10 mA was supplied to the µLED with three different reflector designs, and the optical power output was read with the frontside and backside placed towards the photo-diode sensor, respectively. We also measured a µLED without reflector as the baseline result. The 1000 µm circular reflector gives the best frontside optical intensity ($\sim$2x baseline), and all reflector designs significantly reduce the optical power leaking from the backside ($\sim$5x baseline). Interestingly, the variation in the size of the reflector does not significantly affect its improvement on backside leakage, indicating that all reflectors are effective in redirecting light and enhancing the light intensity towards the targeted tissue.

B. Electrochemical characterization

Electrochemical properties of the fabricated Opto-Myomatrix was evaluated by electrochemical impedance spectroscopy (EIS). Specifically, the recording electrodes with a bare gold surface and with PEDOT:PSS coating were tested, respectively, to evaluate the improvement in impedance from the conductive polymer layer. NanoZ impedance tester (White Matter LLC, USA) was employed to measure impedance from all 32 channels over the frequency range from 1 Hz to 5 kHz. The impedance data was obtained with a 2-electrode setup in physiological saline solution (0.9% NaCl), where the recording electrodes of Opto-Myomatrix acted as a working electrode (WE) and an Ag/AgCl wire served as reference electrode (RE) and counter electrode (CE).

Fig. 5 provides the EIS results measured from electrodes with both gold and PEDOT:PSS finishing. In line with our previous work [23], PEDOT:PSS has once again demonstrated its significant utility. Over the whole testing frequency range, PEDOT-coated electrodes consistently outperform the gold ones. Specifically, at 1 kHz, PEDOT-coated electrodes exhibit an average impedance as low as 3.4 kΩ, which represents an approximately 85% reduction compared with bare gold electrodes. This significant reduction in impedance suggests that PEDOT-coated electrodes can achieve a lower noise level, resulting in a higher signal-to-noise ratio in electrophysiology

Fig. 6. Temperature measurement of μLED chip operating with 20 ms current pulse at different amplitudes (n=3), along with finite element simulation results of the experiment.

circular reflectors (500 and 1000 μm in diameter). All μLEDs used in the tests were covered with a PDMS layer and the temperature variation was obtained from the surface of PDMS.

Fig. 6 (experiment) shows measured meaximum temperature increase from different designs as a function of supplied current. For all device configurations, as the supplied current increases, more heat is generated and dissipated, and thus the higher the temperature increase. It is noted that the aluminum reflector assists in heat dissipation, thereby contributing to a lower temperature increase. The larger reflector has a larger surface area that facilitates more efficient thermal transfer to the surrounding environment, and consequently leads to the lowest temperature increase across all supplied currents. At supplied current of 5 mA, both reflectors successfully spread out the heat and obtained a controlled temperature increase of 2.08°C and 2.68°C respectively, while the maximum temperature increase from bare μLEDs covered with PDMS reached 4.14°C. Although previous research indicates that a temperature increase of 2°C can potentially damage brain tissue [17], [27], [28], muscle tissue has a higher tolerance for temperature fluctuations compared to neural tissue, allowing it to withstand up to 3°C without sustaining damage [29], [30]. In this scenario, only using the highest current (5 mA) without a reflector surpasses the safe limit. It is important to mention that the measurements here were conducted in air, which has a much lower thermal conductivity than muscle tissue [31]. Consequently, when the Opto-Myomatrix is implanted *in vivo*, the surrounding muscle tissue is expected to more effectively dissipate the heat generated by the μLED chip. This will likely allow for the safe operation of the Opto-Myomatrix with a higher supplied current than used in these experiments.

The experiment setup of thermal measurement was also modeled in finite element analysis (FEA) simulation using COMSOL Multiphysics® (Version COMSOL 6.2). The simulated maximum temperature increase is presented in Fig. 6 (simulation) for comparison. It is noted that while the simulated values follow the same trend as the experimental results, they are consistently higher. This discrepancy could

Fig. 5. Electrochemical impedance spectroscopy (EIS) results of the recording electrodes on Opto-Myomatrix. Both bare gold and PEDOT:PSS coated electrodes were measured (n=32).

recordings. Since the μLEDs were attached to the Opto-Myomatrix device after coating PEDOT:PSS layer, the measurement also confirms that the heat from the flip-chip bonding process does not compromise the integrity of the PEDOT:PSS layer.

C. Thermal measurement

Temperature management is a critical consideration in muscle optogenetics stimulation to avoid adverse effects in muscle tissue [8]. The temperature profile of a single μLED on polyimide substrate was obtained using a thermal camera (A6701 MWIR, Teledyne FLIR LLC, USA) with a resolution of 640×512 and pixel size of 15 μm. A 1x microscope lens (3-5 μm, f/2.5 MWIR FPO Manual Bayonet Lens, Teledyne FLIR LLC, USA) was utilized. The system has a sensitivity of less than 0.02°C. This experiment was conducted in a controlled setting at room temperature (20°C) with adequate ventilation to prevent heat accumulation, thus guaranteeing accurate thermal measurements. High-speed videos at 300 frames per second were recorded when a square-wave pulse current was supplied to the μLED with a duration of 20 ms and varying amplitude from 1 mA to 5 mA. To study the impact of reflector design on thermal performance, we conducted tests with three different device configurations: a bare μLED on the polymer substrate, and μLEDs with two different sizes of

	Density (kg/m^3)	Heat capacity (J/kg·K)	Thermal conductivity (W/m·K)
Silicon carbide	3200	1200	450
Gold	19300	129	317
Polyimide	1300	1100	0.15
PDMS	970	1460	0.16
Aluminum	2700	904	237
Muscle	1090	3421	0.49

be due to the actual heat generated by the μLEDs being lower than the values entered in the model. Another possible reason is that there might have been a ramping up step when the power source supplied current to the μLEDs, resulting in lower total power.

D. Thermal finite element simulation

Since it is challenging to obtain the temperature profile from muscle when the opto-Myomatrix is implanted *in vivo*, finite element analysis (FEA) of heat dissipation in muscle tissue is conducted in COMSOL Multiphysics® (Version COMSOL 6.2) to further understand the heat transfer process in real scenarios. To reduce computing complexity, the model is simplified to contain the main components: the μLED chip made of silicon carbide, the anode and cathode of μLED made of gold with a size of 80 μm diameter, the polyimide substrate with a size of 1.1×1.1 mm^2, the PDMS covering μLED chip with a thickness of 10 μm, and a substantial volume of muscle tissue with a volume of 5×5×5 cm^3. The physical properties of the materials used in the simulated models are detailed in Table I (sourced from the COMSOL Multiphysics® material library). The PDMS and polyimide surfaces are in contact with muscle to replicate *in vivo* experiment setup. The muscle boundaries are set at constant body temperature (37°C) except for surfaces in contact with air, assuming the volume for analysis is adequately large. All the other boundaries that are exposed to air are configured for natural convection in air, with a heat transfer coefficient of 5 W/(m^2·K) at room temperature (20°C) [32]. The heat source is applied at the bottom side of the μLED chip to mimic the heat generated at p-n junctions and the value is calculated from the I-V curve of the chip, with optical efficiency assumed to be 40% ($Q_0 = I \cdot V \times (1-40\%)$) [33]. We selectively simulated square-wave current pulse with a duration of 5, 10, and 15 ms and amplitude from 1 to 5 mA, and studied the transient response to extract the highest temperature increase at the surface of muscle in contact with the μLED. Similar to the thermal measurement experiment, the reflector is taken into account as well to investigate its potential function as a heat sink.

The simulation results are presented in Fig. 7(a) and (b), along with an example plot of the cross-sectional and bottom views of the simulated μLED and muscle (Fig. 7(c)). Highest temperature increase at muscle surface with different configurations of device is presented in Fig. 7(a). In this model, all three pulse widths result in a temperature increase of less than 3°, indicating that the device is safe for muscle optogenetics

Fig. 7. Thermal finite element analysis of the μLED on an Opto-Myomatrix device. (a) Maximum temperature increase simulated with current pulses with different pulse width and amplitude. (b) Temperature change over time when the μLED is supplied with current of 3 mA for 15 ms. (c) Temperature profile of the cross-sectional and bottom views of the simulated model.

stimulation. As shown in the cross-sectional view (Fig. 7(c) top), when the temperature inside μLED chip rises, the PDMS layer acts as a barrier to prevent heat from reaching the muscle tissue. It is noted that the heat impact is highly localized, affecting only a very small area – specifically tissue within 100 μm of the Opto-Myomatrix device (Fig. 7(c) bottom). Additionally, when the supplied current has a duration of 15 ms and amplitude of 5 mA, both reflector configurations limit the maximum temperature rise to below 2°C. This confirmed that the design of the reflector effectively serves as a heat sink and significantly reduces the temperature variations. The aluminum reflector has a high thermal conductivity, allowing rapid heat transfer into the air [34]. This property enables the reflector to quickly disperse heat, leading to a lower peak temperature (Fig. 7(b)). While the design without the reflector remains safe for muscle stimulation, the addition of the reflector offers improved heat management, enhancing overall performance [29], [30]. To investigate temperature change at muscle surface over time, we studied the transient

response using a supplied current with a 15-ms pulse duration and a 3-mA amplitude, sustained for 100 ms (Fig. 7(b)). After 15 ms, devices with all three configurations reach their maximum temperature. Once the current is turned off, the temperature declines more rapidly and to lower levels with an increasing reflector footprint. This is again attributed to the heat sink properties of the reflector, which helps dissipate heat more efficiently by conducting it away from the device and increasing surface area exposure to air.

IV. *In vivo* EXPERIMENTS

The fabricated Opto-Myomatrix device was utilized in an acute electrophysiological recording in mice to optically stimulate temporalis muscle and record EMG signals (Fig. 8(a)). All procedures were approved by the Johns Hopkins University Institutional Animal Care and Use Committee.

Emx1-Cre/Ai32 offspring were generated by crossing Emx1-IRES-Cre knock-in homozygotes (Stock no. 005628, Jackson Laboratory) with Ai32 (RCL-ChR2H134R-EYFP) reporter homozygotes (Stock no. 024109, Jackson Laboratory). The mice were anesthetized using 0.9-1.5% isoflurane at a flow rate of 1 L/min and the anesthesia was maintained consistently throughout the surgical procedure and data collection. 30 μL of physiological saline was injected subcutaneously, followed by opening a skin flap at the chin to expose the temporalis and masseter muscles. The Opto-Myomatrix devices were then placed on the surface of the temporalis muscles while the temporalis muscle was kept moist with saline. A high-speed CMOS camera (DR1-D1312-200-G2-8, PhotonFocus, Switzerland) in a 0.25x telecentric lens (Edmund Optics, USA) captured jaw kinematics at 400 frames per second using IR illumination at 850 nm and an angled mirror to collect side and bottom views simultaneously. Light pulses of varying power (0-1 mW) and pulse duration (5, 50, 100 ms) were delivered via the integrated μLED component. Stimuli parameters were controlled by a National Instruments DAQ system (BNC-2090A, National Instruments Corp., USA) with WaveSurfer. EMG signals were amplified and digitized with an Intan RHD2216 bipolar amplifier chip (Intan Technologies, USA) and bandpass filtered at 300–7500Hz.

The collected raw EMG signals were rectified and then smoothened with a Gaussian kernel of 2.5 ms. To quantify the optically evoked jaw movement, eleven keypoints were traced along the jaw in captured video using DeepLabCut to quantify the movement [36]. The illumination of ChR2-expressing temporalis muscles, a jaw closing muscle, leads to elevation and deviation of the mandible away from the midline [37]. As shown in Fig 8(b), short (5 ms) light pulses of <1 mW power is sufficient to drive overt jaw movements. Increasing light power drives increasing amplitude in jaw movements. Correspondingly, the higher light power also results in higher peak EMG amplitude and lower latency in EMG activity, suggesting greater activation of muscle fibers and decreased time to depolarization.

The multi-contact layout of Opto-Myomatrix (Fig. 9(a)) permits measurement of the spatial extent of optical depolarization of muscle. The space constant was derived via a

(a) Emx-Cre; Ai32 (ChR2 in orofacial muscles)

Fig. 8. *In vivo* optical stimulation. (a) Experiment setup. Optical stimulation of the temporalis muscle in an anesthetized mouse expressing channelrhodopsin-2 (ChR2) in orofacial muscle fibers. (b) Optical activation evokes muscle activation and lateral movement of the jaw. The latency of EMG response (red arrow) is consistent with published values for optical stimulation of muscle fibers [35].

single-term exponential fit using the equation $y = ae^{-x/\lambda}$, where y represents the peak EMG amplitude, x the distance from the μLED, and λ the space constant. As shown in Fig. 9(b), the peak amplitude of EMG activity decayed with distance from centrally placed μLED with a space constant of approximately 1111 um. The space constant reflects the spread of depolarization across muscle fibers. The spatial profile of EMG activity was notably inhomogeneous, likely reflecting the underlying orientation of muscle fibers and variability in electrode contact with the underlying muscle. In addition, the spatial profile of latency in EMG activity showed increasing latency with distance from μLED.

V. CONCLUSION

Opto-Myomatrix is a flexible and biocompatible microelectrode array with an integrated μLED chip for simultaneous optogenetic stimulation and EMG recording from muscle tissue. In this work, we present the design concept, fabrication process and characterization of Opto-Myomatrix, and proof-of-concept *in vivo* experiments to validate its capability of precisely controlling and monitoring muscle activity. The

Fig. 9. Sample EMG signals. (a) Layout of 32-channel recording electrodes paired for bipolar recording and μLED on Opto-Myomatrix. (b) EMG signals recorded using the Opto-Myomatrix in bipolar mode during optical stimulation. The pulse is 50 msec in duration and each plot spans from -0.5 to +0.5 mV. Variations in amplitude and latency across the channels are illustrated, highlighting their correlation on the varying distances from the μLED.

fabrication process can be adapted to fit various muscle types, enhancing the versatility of the device. Featuring an embedded reflector design, the Opto-Myomatrix achieves an optical intensity of up to 129.46 mW/mm^2 at wavelength of 465 nm with a 20 mA driving current, significantly surpassing the activation threshold for ChR2. Additionally, the reflector plays a crucial role in minimizing light leakage from the backside, redirecting the light to the targeted area. The electrochemical characterization shows that the PEDOT:PSS-coated recording electrodes of Opto-Myomatrix possess low impedance, consistently outperforming the benchmark device with gold finishing over the testing frequency range. The observed impedance improvement aligns with the consistent findings of reduced impedance demonstrated in our previous work [23], enabling recordings with a high signal-to-noise ratio and thereby enhancing both data quality and reliability. We also conducted thermal measurements and simulated the heat dissipation process of the μLED chip and confirmed that the maximum temperature increase stays within safe limits for muscle stimulation. The fabricated Opto-Myomatrix was implanted in transgenic mice and successfully stimulated temporalis muscle with light at 465 nm. The induced EMG signals and jaw movement were collected and analyzed to demonstrate the device's functionality and the precision of optogenetic muscle control. The multi-contact layout of Opto-Myomatrix also allowed quantification of optical depolarization across muscle fibers, showing a space constant of 1111 um and a distance-related variation in EMG activity and latency.

ACKNOWLEDGMENT

This work was funded by National Institutes of Health Grant R01 NS109237 and U24 NS126936, the McKnight Foundation and the Simons Foundation as part of the Simons-Emory International Consortium on Motor Control, and was performed in part at the Georgia Tech Institute for Electronics and Nanotechnology (IEN) and Materials Characterization Facility (MCF); JJK was supported by NIH Award 1F31DE033256-01.

REFERENCES

[1] B. Fan and W. Li, "Miniaturized optogenetic neural implants: a review," *Lab on a Chip*, vol. 15, no. 19, pp. 3838–3855, 2015.

[2] E. A. Ferenczi and C. L.-H. Huang, "Principles of optogenetic methods and their application to cardiac experimental systems," *Frontiers in physiology*, vol. 10, p. 465253, 2019.

[3] E. S. Boyden, F. Zhang, E. Bamberg, G. Nagel, and K. Deisseroth, "Millisecond-timescale, genetically targeted optical control of neural activity," *Nature neuroscience*, vol. 8, no. 9, pp. 1263–1268, 2005.

[4] A. Roy, J. J. Osik, N. J. Ritter, S. Wang, J. T. Shaw, J. Fiser, and S. D. Van Hooser, "Optogenetic spatial and temporal control of cortical circuits on a columnar scale," *Journal of neurophysiology*, vol. 115, no. 2, pp. 1043–1062, 2016.

[5] F. Zhang, L.-P. Wang, M. Brauner, J. F. Liewald, K. Kay, N. Watzke, P. G. Wood, E. Bamberg, G. Nagel, A. Gottschalk *et al.*, "Multimodal fast optical interrogation of neural circuitry," *Nature*, vol. 446, no. 7136, pp. 633–639, 2007.

[6] V. Gradinaru, F. Zhang, C. Ramakrishnan, J. Mattis, R. Prakash, I. Diester, I. Goshen, K. R. Thompson, and K. Deisseroth, "Molecular and cellular approaches for diversifying and extending optogenetics," *Cell*, vol. 141, no. 1, pp. 154–165, 2010.

[7] D. J. Rindner and G. Lur, "Practical considerations in an era of multicolor optogenetics," *Frontiers in Cellular Neuroscience*, vol. 17, p. 1160245, 2023.

[8] L. A. Gundelach, M. A. Hüser, D. Beutner, P. Ruther, and T. Bruegmann, "Towards the clinical translation of optogenetic skeletal muscle stimulation," *Pflügers Archiv-European Journal of Physiology*, vol. 472, pp. 527–545, 2020.

[9] H. Watanabe, H. Sano, S. Chiken, K. Kobayashi, Y. Fukata, M. Fukata, H. Mushiake, and A. Nambu, "Forelimb movements evoked by optogenetic stimulation of the macaque motor cortex," *Nature communications*, vol. 11, no. 1, p. 3253, 2020.

[10] E. S. Benevides, M. D. Sunshine, S. Rana, and D. D. Fuller, "Optogenetic activation of the diaphragm," *Scientific reports*, vol. 12, no. 1, p. 6503, 2022.

[11] C. Towne, K. L. Montgomery, S. M. Iyer, K. Deisseroth, and S. L. Delp, "Optogenetic control of targeted peripheral axons in freely moving animals," *PloS one*, vol. 8, no. 8, p. e72691, 2013.

[12] J. J. Williams, A. M. Watson, A. L. Vazquez, and A. B. Schwartz, "Viral-mediated optogenetic stimulation of peripheral motor nerves in non-human primates," *Frontiers in neuroscience*, vol. 13, p. 440264, 2019.

[13] E. Ganji, C. S. Chan, C. W. Ward, and M. L. Killian, "Optogenetic activation of muscle contraction in vivo," *Connective tissue research*, vol. 62, no. 1, pp. 15–23, 2021.

[14] S. J. Sober, S. Sponberg, I. Nemenman, and L. H. Ting, "Millisecond spike timing codes for motor control," *Trends Neurosci.*, vol. 41, no. 10, pp. 644–648, 2018.

[15] K. H. Srivastava, C. M. Holmes, M. Vellema, A. R. Pack, C. P. Elemans, I. Nemenman, and S. J. Sober, "Motor control by precisely timed spike patterns," *PNAS*, vol. 114, no. 5, pp. 1171–1176, 2017.

[16] T. Abaya, M. Diwekar, S. Blair, P. Tathireddy, L. Rieth, G. Clark, and F. Solzbacher, "Glass optrode array for optogenetic stimulation," in *Optogenetics: Optical Methods for Cellular Control*, vol. 8586. SPIE, 2013, pp. 89–93.

[17] B. Ji, Z. Guo, M. Wang, B. Yang, X. Wang, W. Li, and J. Liu, "Flexible polyimide-based hybrid opto-electric neural interface with 16 channels of micro-leds and electrodes," *Microsystems & nanoengineering*, vol. 4, no. 1, p. 27, 2018.

[18] B. Ji, C. Ge, Z. Guo, L. Wang, M. Wang, Z. Xie, Y. Xu, H. Li, B. Yang, X. Wang *et al.*, "Flexible and stretchable opto-electric neural interface for low-noise electrocorticogram recordings and neuromodulation in vivo," *Biosensors and Bioelectronics*, vol. 153, p. 112009, 2020.

[19] F. Wu, E. Stark, P.-C. Ku, K. D. Wise, G. Buzsáki, and E. Yoon, "Monolithically integrated μleds on silicon neural probes for high-resolution optogenetic studies in behaving animals," *Neuron*, vol. 88, no. 6, pp. 1136–1148, 2015.

[20] A. M. Clark, A. Ingold, C. F. Reiche, D. Cundy III, J. L. Balsor, F. Federer, N. McAlinden, Y. Cheng, J. D. Rolston, L. Rieth *et al.*, "An optrode array for spatiotemporally-precise large-scale optogenetic stimulation of deep cortical layers in non-human primates," *Communications Biology*, vol. 7, no. 1, p. 329, 2024.

[21] H. Cao, L. Gu, S. Mohanty, and J.-C. Chiao, "An integrated μled optrode for optogenetic stimulation and electrical recording," *IEEE Transactions on Biomedical Engineering*, vol. 60, no. 1, pp. 225–229, 2012.

[22] B. Chung, M. Zia, K. A. Thomas, J. A. Michaels, A. Jacob, A. Pack, M. J. Williams, K. Nagapudi, L. H. Teng, E. Arrambide *et al.*, "Myomatrix arrays for high-definition muscle recording," *Elife*, vol. 12, p. RP88551, 2023.

[23] J. Lu, M. Zia, M. J. Williams, A. L. Jacob, B. Chung, S. J. Sober, and M. S. Bakir, "High-performance flexible microelectrode array with pedot: Pss coated 3d micro-cones for electromyographic recording," in *2022 44th Annual International Conference of the IEEE Engineering in Medicine & Biology Society (EMBC)*. IEEE, 2022, pp. 5111–5114.

[24] M. Zia, B. Chung, S. Sober, and M. S. Bakir, "Flexible multielectrode arrays with 2-d and 3-d contacts for *invivo* electromyography recording," *IEEE Transactions on Components, Packaging and Manufacturing Technology*, vol. 10, no. 2, pp. 197–202, 2020.

[25] M. Asad, Q. Li, M. Sachdev, and W. S. Wong, "Thermal and optical properties of high-density gan micro-led arrays on flexible substrates," *Nano Energy*, vol. 73, p. 104724, 2020.

[26] E. Stark, T. Koos, and G. Buzsáki, "Diode probes for spatiotemporal optical control of multiple neurons in freely moving animals," *Journal of neurophysiology*, vol. 108, no. 1, pp. 349–363, 2012.

[27] T.-i. Kim, J. G. McCall, Y. H. Jung, X. Huang, E. R. Siuda, Y. Li, J. Song, Y. M. Song, H. A. Pao, R.-H. Kim *et al.*, "Injectable, cellular-scale optoelectronics with applications for wireless optogenetics," *Science*, vol. 340, no. 6129, pp. 211–216, 2013.

[28] M. M. Elwassif, Q. Kong, M. Vazquez, and M. Bikson, "Bio-heat transfer model of deep brain stimulation-induced temperature changes," *Journal of neural engineering*, vol. 3, no. 4, p. 306, 2006.

[29] J. W. Castellani, E. J. Zambraski, M. N. Sawka, and M. L. Urso, "Does high muscle temperature accentuate skeletal muscle injury from eccentric exercise?" *Physiological reports*, vol. 4, no. 9, p. e12777, 2016.

[30] M. Locke and C. Celotti, "The effect of heat stress on skeletal muscle contractile properties," *Cell Stress and Chaperones*, vol. 19, no. 4, pp. 519–527, 2014.

[31] H. F. Bowman, E. G. Cravalho, and M. Woods, "Theory, measurement, and application of thermal properties of biomaterials," *Annual review of biophysics and bioengineering*, vol. 4, no. 1, pp. 43–80, 1975.

[32] S. Kim, P. Tathireddy, R. A. Normann, and F. Solzbacher, "Thermal impact of an active 3-d microelectrode array implanted in the brain," *IEEE Transactions on Neural Systems and Rehabilitation Engineering*, vol. 15, no. 4, pp. 493–501, 2007.

[33] E.-L. Hsiang, Z. He, Y. Huang, F. Gou, Y.-F. Lan, and S.-T. Wu, "Improving the power efficiency of micro-led displays with optimized led chip sizes," *Crystals*, vol. 10, no. 6, p. 494, 2020.

[34] M. Krstic, L. Pantic, S. Djordjevic, I. Radonjic, V. Begovic, B. Radovanovic, and M. Mancic, "Passive cooling of photovoltaic panel by aluminum heat sinks and numerical simulation," *Ain Shams Engineering Journal*, vol. 15, no. 1, p. 102330, 2024.

[35] P. Magown, B. Shettar, Y. Zhang, and V. F. Rafuse, "Direct optical activation of skeletal muscle fibres efficiently controls muscle contraction and attenuates denervation atrophy," *Nature communications*, vol. 6, no. 1, p. 8506, 2015.

[36] A. Mathis, P. Mamidanna, K. M. Cury, T. Abe, V. N. Murthy, M. W. Mathis, and M. Bethge, "Deeplabcut: markerless pose estimation of user-defined body parts with deep learning," *Nature neuroscience*, vol. 21, no. 9, pp. 1281–1289, 2018.

[37] H. Baverstock, N. S. Jeffery, and S. N. Cobb, "The morphology of the mouse masticatory musculature," *Journal of Anatomy*, vol. 223, no. 1, pp. 46–60, 2013.