Biomechanical Evaluation of Temporomandibular Joint Implants Under Complete Mastication Cycle

Rajdeep Ghosh, Ph.D.[1,2,3], Girish Chandra, Ph.D.[1], Vivek Verma, Ph.D.[1], Kamalpreet Kaur, MDS[4], Ajoy Roychoudhury, MDS[4], Sudipto Mukherjee, Ph.D.[1], Anoop Chawla, Ph.D.[1], Kaushik Mukherjee, Ph.D.[1, *]

[1]*Department of Mechanical Engineering, Indian Institute of Technology Delhi, New Delhi 110 016, Delhi, India*

[2]*Department of Mechanical Engineering, University of Sheffield, Sheffield S1 3JD, United Kingdom*

[3]*INSIGNEO Institute for in silico Medicine, University of Sheffield, Sheffield S1 3JD, United Kingdom*

[4]*Department of Oral & Maxillofacial Surgery CDER, All India Institute of Medical Sciences, New Delhi 110029, Delhi, India*

*Corresponding author:

Dr. Kaushik Mukherjee

Department of Mechanical Engineering

Indian Institute of Technology Delhi

New Delhi, 110 016

Tel: +91 – (0) 3612 – 583211

Email: kmukherjee@mech.iitd.ac.in

Keywords: *Temporomandibular joint (TMJ) implant; Mandible; Mastication cycle; FE analysis*

Word Count: Abstract 252; Manuscript 3519
Number of Tables: 2; Number of Figures: 7

Abstract

Background: To ensure the long-term success of temporomandibular joint implants, it is

imperative to understand their biomechanical performances under the mastication cycle.

Purpose: This study aims to compare the biomechanical performance of two commercially

available stock implants under a complete mastication cycle. This study has been further

extended to understand the influence of bone-implant interface conditions on pre-clinical

testing of implants.

Methods: In the present study, patient-specific QCT-based finite element models of a human

mandible were developed. The left temporomandibular joint was virtually replaced by stock

implants (narrow and standard). A complete mastication cycle involving six clenching tasks

was simulated. A comparative biomechanical assessment between the intact and the implanted

mandibles was performed based on maximum principal stress and strain distributions on the

mandible.

Results: As compared to contralateral occlusion, ipsilateral clenching resulted in higher

strains in the mandible. However, contralateral occlusion produced a larger von Mises stress

on the implant than ipsilateral occlusion. Furthermore, intercuspal biting was found to have

produced the highest strain (1750-1880 $\mu\varepsilon$) and stress (16.02-16.54 MPa) in the mandible. As

compared to immediate post-operative non-osseointegrated conditions, an overall reduction of

stress (narrow implant: 0.14 MPa; standard implant: 0.12 MPa) and strain (narrow implant: 30

$\mu\varepsilon$; standard implant: 20 $\mu\varepsilon$) was observed in post-operative osseointegrated phase.

Conclusions: Although stresses and strains in mandible and implants are reduced in

osseointegrated condition, standard temporomandibular joint implant produced higher stresses

in cortical bone compared to narrow implant during non-osseointegrated conditions, which

suggests the possible preference of narrow implant over standard ones.

1. Introduction

A wide range of disorders, primarily intra-articular pathologies, and trauma [1–3], can affect the temporomandibular joint (TMJ), causing clinical symptoms such as pain, restricted joint movement, malocclusion, and functional difficulty during deglutition and speech [4,5]. TMJ replacement with an alloplastic joint may be required for patients who do not respond well to conservative and non-surgical treatment [1]. Despite the short-term successes associated with the use of TMJ implants, the long-term implications of these commercially available stock TMJ implants are still not clear to the scientific community and clinicians [6–9].

The patient-specific TMJ Concepts system (Stryker, Ventura, CA, USA) and the stock Zimmer Biomet Microfixation systems (Jacksonville, FL, USA) are the two primary US-FDA-approved TMJ replacement systems now available globally. Patient-specific implants are designed to match the anatomical periphery of the host bone for better stability and ease of implantation [10,11]. However, the use of patient-specific implants is not as prevalent as the stock ones due to higher cost and longer delivery times [12]. Biomet Microfixation system® designed stock mandibular prosthesis comes in two shapes viz. standard (45 mm, 50 mm and 55 mm) and narrow (45 mm and 50mm) with varying sizes depending on the length of the mandibular body. The choice between standard and narrow implants depends on factors such as patient anatomy, surgical requirements, and the extent of joint reconstruction needed. A report from a recent meta-analysis by Zou et al.[13] revealed comparable outcomes between stock and patient-specific prostheses in terms of reduced pain score and improvement in function score, diet score, and maximum incisal opening. However, these implants (especially stock implants) are vulnerable to long-term failure risks primarily owing to implant design, poor material

selection, improper surgical techniques etc.[7,8]. Therefore, further research is needed to

achieve a longer life span for existing TMJ implants [6,13].

The human mandible experiences different physiological loads throughout its lifetime.

Although there have been several *in silico* studies on biomechanical assessment of healthy [14–

20] and reconstructed human mandibles [21–29], only a few studies have investigated

reconstructed human mandibles with TMJ implants [24,26,27]. Notable among them is the study

by Pinheiro et al. [26] which reported the strain and deformation across the human mandible

implanted with a patient-specific TMJ implant under three clenching tasks. Their study

considered a frictionless interface between the bone-implant and condyle-fibrocartilage. A

frictionless interface typically indicates an extremely smooth interface which offers no resistance

against relative movement. While this might be true for the condyle-fibrocartilage joint, the

bone-implant interfaces are typically modelled as frictional [30] or bonded [31]. Additionally,

such simplified bone-implant interface modelling would also influence the stress-strain

behaviour across the mandible and TMJ implant.

To the authors' knowledge, none of the studies reported the influence of different stock

TMJ implants on load transfer across the human mandible under both unilateral and bilateral

clenching activities. The present study is thus aimed at gaining an insight into the biomechanical

performance of two stock TMJ implants (standard and narrow types by Zimmer Biomet

Microfixation systems®) under unilateral and bilateral clenching tasks representing a complete

mastication cycle. In addition, the influences of bone-implant interface conditions, representing

an osseointegrated and non-osseointegrated conditions, on stresses and strains in implanted

mandible were also investigated.

2. Materials and Methods

Quantitative computed tomography (QCT)- dataset (512 x 512 pixels; voxel size of $0.439 \times 0.439 \times 0.75$ mm^3) of an anonymized 20-year-old healthy male subject was obtained to develop the model of the intact mandible. Ethical approval was obtained from the Institute Ethics Committee of All India Institute of Medical Sciences, New Delhi, India. A 3-D surface model of the intact mandible was reconstructed in Materialise Mimics v25.0 (Materialise Inc., Leuven, Belgium). Finite element (FE) mesh was generated in Hypermesh v2022 (Altair Engineering Inc., Troy, MI, USA), whereas FE simulation and further post-processing were performed in Ansys APDL v2022 R2 (ANSYS Inc., Canonsburg, PA, USA).

2.1 Development of Intact FE model

The human mandible (Figure 1) has the following major components: cortical, cancellous, periodontal ligament (PDL), teeth, articular fibrocartilage, and temporal bone (represented by cubic block). Due to considerable influence of PDL layer on stress-strain distribution in human mandible [16], it was decided to model the PDL (~ 0.3 mm thickness) and this was achieved by offsetting the interface between the cancellous bone and the teeth. PDL was further divided into three subcomponents along the root length: coronal, middle, and apical thirds. All components were meshed with 10-noded tetrahedral elements (with edge lengths from 0.3 mm to 2 mm) by fulfilling appropriate mesh quality parameters such as aspect ratio (<5), Jacobian ratio (>1), etc. A mesh convergence study was performed with an ascending number of elements from coarse (305,774 elements), to medium (3,403,988 elements), to fine (7,054,373 elements) element sizes on the intact model. However, difference in maximum principal stress in the mandible was predicted to be 5% between coarse and medium meshed models, while 0.4% between the medium and fine meshes. Therefore, the medium meshed model with element sizes ranging

134 between 0.5 mm to 1.5 mm (3,403,988 elements) was chosen as the optimum FE model for

135 further investigation in this study. -

2.2 Development of Implanted FE models

The 3D models of the mandibular components of TMJ implants (Figure 2 - a & b) were

developed from the micro-CT images (Xtreme CT II, Scanco Medical AG, Switzerland, with

scanning parameters: 491 x 256 pixels; isometric voxel size of 60 μm) of narrow and standard

stock implants of size 45 mm (Zimmer Biomet Microfixation system, Jacksonville, FL, USA).

Based on Biomet mandibular screws [32], bi-cortical screws were modelled as simplified

cylinders (Φ2.7 mm) with lengths ranging from 8 – 12 mm. The models of the intact mandible

and TMJ implant were imported into Rhinoceros® software (Rhinoceros V7.0, Robert McNeel &

Associates, Seattle, USA) for osteotomy and virtual implantation based on clinical

recommendations. A medium mesh (edge length between 0.5 – 1.5 mm) was used for TMJ

implants (Figure 2 - c & d).

2.3 Material Properties

In this study, linear elastic orthotropic material properties were assigned to different regions of

mandible. Cortical bone was modelled as a region-specific orthotropic material [14]. Cancellous

bone, however, was modelled as homogeneous orthotropic material [14]. All other components

such as teeth, PDL, fibrocartilage and implant were modelled as linear elastic isotropic material

[21,28] Temporal bone was modelled as a rigid body [21]. Table 1 shows the material properties

used in this study for different components. For the implanted mandible, the mandibular

component and the screws were assumed to be made of medical grade Ti-6Al-4V extra-low

interstitial (ELI).

2.4 Loading and Boundary Conditions

The following six biting tasks (Table 2) were considered in this study: incisal (INC), intercuspal (ICP), right molar (RMOL), left molar (LMOL), right group (RGF), and left group (LGF) biting. Muscle activity of seven muscles (Figure 2-e) [33] namely, two masseter (SM/DM), two pterygoid (MP/LP), and three temporalis muscles (AT/MT/PT) were considered in this study. However, the influence of lateral pterygoid was neglected on the implanted side of the implanted model as total joint replacement requires excision of condyle where the lateral pterygoid muscle is attached. In addition, the present study hypothesized that all the muscles reattached successfully post-implantation. The top surface of temporal bone blocks was fixed in all directions [14,33]. The bite points corresponding to each biting tasks were constrained in Z-direction [26]. To investigate the influence of bone-implant interface conditions on stress-strain distribution across the bone and implant, both osseointegrated (OI) and non-osseointegrated (NOI) bone-implant interface conditions have been considered here. To model the osseointegrated (OI) condition, the interface between mandibular component and cortical bone was bonded whereas a frictional interface between mandibular component and cortical bone was considered to mimic the non-osseointegrated (NOI) condition. Furthermore, the frictional contact between articular fibrocartilage and mandibular condyle was defined in the intact and implanted mandibles. Frictional contact was also considered between the head of the mandibular component and temporal bone block in the implanted mandible. All the other contact pairs were defined as bonded. An 'Augmented Lagrangian Algorithm' was defined for all surface-to-surface frictional contact pairs ($\mu = 0.3$).

2.5 Interpretation of Results

Mandible exhibits a sandwich structure wherein the cortical bone bears most of the clenching load. Cortical bone being brittle in nature, prior studies considered maximum principal strains as failure criterion [34,35]. Therefore, in the current study, maximum principal strains and stresses in the mandible were considered for biomechanical comparisons between the intact and implanted mandibles. To exclude singular values, owing to constrained regions in the FE models in both intact and implanted mandibles, 99th percentile values of principal stresses and strains of cortical bone were considered for comparison. Conversely, implants being made of Ti6Al4V which exhibits ductile material behaviour, von Mises stress was considered for investigating the load transfer through narrow and standard TMJ implants under complete mastication cycle.

2.6 Verification of Intact FE model

Since the CT-scan dataset was derived from a living subject, the FE model developed in the present study could not be directly validated by a one-to-one experiment. However, a qualitative and quantitative verification of the FE model was performed by comparing the results with those from earlier studies [14,18,26,36]. The present study observed a maximum principal stress of 11.87 MPa around the biting surfaces of the right molar teeth which corroborates a similar finding (15 MPa to 25 MPa) reported in a previous study by Korioth et al. [14] during a right molar clenching. The present study observed high maximum principal strains [700-1750 $\mu\varepsilon$] in all the load cases in healthy mandible. The magnitude of the principal strain observed near the anterior ramus surface of the mandible during the RMOL case in the present study was 1250 $\mu\varepsilon$, which closely matches the strain (1260 $\mu\varepsilon$) observed earlier [26]. Similar to the study by [36] high tensile strains below the mandibular notch and anterior surface of the condylar neck were also observed here (Fig 3). Gröning et al. [18] reported highest principal strains around the *pars*

alveolaris below the molars, oblique line, *basis mandibulae,* and posterior ramus inferior to

condyle during INC, ICP and molar bites (RMOL/LMOL). Similar strain distributions were

observed in the present study for INC, ICP, and molar bites. The quantitative difference in results

in maximum principal stresses and strains between this study and the erstwhile works [14,26]

might be attributed to the difference in bone morphology, choice of bone material properties, and

in muscle attachment sites. Notwithstanding subtle differences, the results from the present study

provide confidence in the developed FE models.

3. Results

The principal stress and strain on the intact and implanted mandibles along with von Mises stress

in the TMJ implants (mandibular component and screws) during immediate post-operative non-

osseointegrated (NOI) condition are discussed first (section 3.1 and 3.2). Thereafter, influence of

osseointegration on stresses and strains has been investigated by comparing the non-

osseointegrated results with those of the osseointegrated (OI) models (section 3.3).

3.1 Maximum Principal Stress and Strain Distribution in Intact and Implanted Mandibles

Figure 3 and 6a shows the magnitude and distribution of maximum principal stress around intact

and implanted mandibles under six different biting tasks representing a complete mastication

cycle respectively. The maximum tensile stress (Fig. 6a) in the intact mandible ranges between

5.85 MPa (LGF) and 16.02 MPa (ICP). Higher stress regions were observed along the oblique

line, anterior ramus, and across lateral alveolar regions in discrete patches for the molar (RMOL)

and intercuspal (ICP) occlusion. For the rest of the load cases (INC/LGF/RGF), higher stresses

were observed mostly near the molars in the alveolar region and around the medial mandibular

notch (Fig. 3). Minor difference in stress magnitude (narrow TMJ: 1.02 MPa; standard TMJ: 0.75

MPa) was observed between the intact and the implanted mandibles. However, marginally higher

stress (maximum difference of 0.32 MPa) was observed in mandible with standard TMJ implant

as compared to the one with narrow TMJ implant. Moreover, an overall increase in stress was

observed in case of contralateral clenching (RMOL and RGF) as compared to ipsilateral ones

(LMOL and LGF).

Figure 4 and 6b shows the distribution and magnitude of maximum principal strain in the

intact and reconstructed mandibles in a mastication cycle respectively. The strain in the intact

mandible over the full mastication cycle ranges from 700 $\mu\varepsilon$ to 1750 $\mu\varepsilon$ (Fig. 6b). Higher strains

(1150 $\mu\varepsilon$ to 1750 $\mu\varepsilon$) were observed during molar biting (RMOL and LMOL) and ICP cases

across the ramus primarily around the lower condyles, coronoid process, oblique line and lateral

surfaces of alveolar and body (Fig. 4). However, INC and group function tasks (RGF/LGF)

resulted in lower strains (700 $\mu\varepsilon$ to 730 $\mu\varepsilon$) mostly around medial surfaces of mandibular notch

and alveolar region on lateral sides. The ICP clenching caused the highest tensile strain (1750 $\mu\varepsilon$

to 1880 $\mu\varepsilon$) among all the load cases.

An overall reduction in the magnitude of peak strain was observed in implanted

mandibles (narrow TMJ: 80 $\mu\varepsilon$; standard TMJ: 120 $\mu\varepsilon$) as compared to those in intact mandible.

However, higher strains (up to 80%) were observed around the screw holes in the implanted ones

as compared to the intact mandible. Unlike intact mandibles, maximum principal strains in

implanted mandibles increased under ipsilateral clenching (up to 14.75%) than contralateral ones

(Figure 6b). However, an opposite trend was observed for ipsilateral gonial angle region wherein

strains under ipsilateral loading was higher (by 11.9%) than those under contralateral loading.

3.2 Stresses in Implants

Figure 5 and 7 shows the von Mises stress distribution and peak von Mises stress across the

implants and screws under different biting conditions respectively. Among all the loading

conditions, peak von Mises stress in the mandibular component (Fig. 7a) of ramus standard TMJ

was the highest (150.76 MPa) under RMOL, whereas the lowest (57.53 MPa) under LMOL. In

comparison, for narrow TMJ implant, the highest (131.97 MPa) and lowest (87.21 MPa) von

Mises stresses in mandibular component were observed under RGF and LGF, respectively. In

general, ipsilateral clenching (LMOL/LGF) resulted in reduced von Mises stresses (standard

TMJ: 93.23 MPa; narrow TMJ: 44.76 MPa) in mandibular component as compared to

contralateral clenching (RMOL/RGF). Regions near the base of the mandibular component

experienced negligible stresses (≤5MPa in standard TMJ implants (Fig. 5). Peak von Mises

stresses in the screws (Fig. 7b) were minimum during LMOL (narrow TMJ: 49.90 MPa; standard

TMJ: 52.25 MPa). In comparison, higher stresses in the screws were observed during INC

(narrow TMJ: 114.57 MPa; standard TMJ: 128.1 MPa) and RGF (narrow TMJ: 108.55 MPa;

standard TMJ: 129.49 MPa). Additionally, stresses in the screws were higher in standard TMJ

implant as compared to narrow TMJ implant during immediate post-operative non-

osseointegrated condition. Overall stress patterns in the screws under all the loading conditions

were similar.

3.3 Influence of osseointegration on stresses and strains in implanted mandible

The present study investigated both immediate post-operative non-osseointegrated (NOI) and

long-term post-operative osseointegrated (OI) conditions. The interfacial conditions were found

to influence the stresses (Figure 3 and 6a) and strains (Figure 4 and 6b) in the mandible and

implant. Overall reduction in stress (narrow TMJ: 0.14 MPa; standard TMJ: 0.12 MPa) and

strains (narrow TMJ: 30 $\mu\varepsilon$; standard TMJ: 20 $\mu\varepsilon$) were observed due to osseointegration.

However, in mandibular component, an increase in stress was observed under contralateral

loading as compared to ipsilateral loading for both NOI and OI conditions. During NOI

condition, von Mises stresses in mandibular component during LMOL (narrow TMJ: 92.65 MPa;

standard TMJ: 57.53 MPa) and LGF (narrow TMJ: 87.21 MPa; standard TMJ: 86.17 MPa) were

found to be much lower than those during RMOL (narrow TMJ: 131.20 MPa; standard TMJ:

150.76 MPa) and RGF (narrow TMJ: 131.97 MPa; standard TMJ: 110.77 MPa) loading

conditions. A similar observation was noted for OI condition as well (Figure 7). Although there

was an overall reduction in stress in the standard TMJ implants as compared to the narrow ones

in the OI condition, stresses in the implants (Fig. 7a) during both OI and NOI conditions were

much below the yield limit of the implant material (~955 MPa) [37]. In addition, reduction in

stresses (up to 5.24 MPa) on the screws (Fig. 7b) were also found in the standard TMJ implant

compared to that on the narrow ones in the OI condition. Conversely, stresses in the screws

increased (up to 22.87 MPa) in the standard TMJ implants in the NOI conditions (Fig. 7b).

4. Discussion

The present study is aimed to assess biomechanical performance of two widely used stock

mandibular TMJ implants (standard and narrow) under the complete mastication cycle including

both unilateral and bilateral clenching activities. In addition, influences of osseointegration on

the stresses and strains in mandible and TMJ implants have also been investigated.

Minor difference in stress magnitude across the mandible between the intact and

implanted mandibles was observed in this study. Although mandibles implanted with standard

TMJ implants resulted in slightly higher stresses (0.05-0.34 MPa) in cortical bone, the overall

spatial distribution of cortical bone stresses were similar in all the cases. Higher cortical bone

strains were, however, observed around the screw holes. This might cause fibrous tissue

formation at the bone-implant interface [38], [39] in the long term. Similar observation was also

reported in earlier clinical study [40]. Sugiura et al.[41] reported a threshold compressive strain

(3600 µε) for inducing bone resorption in human mandibles. The peak strain reported in the

present study in implanted mandibles with both implants is much below the critical threshold

limit for bone resorption which ensures the suitability of these implants in the present scenario.

Higher strains (up to 14.75%) on implanted bone were observed under ipsilateral loading as

compared to the contralateral ones, which is in contrast with the observations for intact bone. A

similar trend of strains under ipsilateral and contralateral loading was also reported earlier [26].

Bone-implant interface condition was found to influence load transfer through

mandibular component. An overall reduction in stresses were observed due to osseointegration

similar to a recent study on dental implants [42]. During the initial NOI condition, screws act as

mechanism to transfer loads from the mandible to the mandibular component and vice versa. On

the contrary, during the OI condition, the entire bone-implant interface becomes osseointegrated

and therefore, load-sharing happens through a larger interfacial area. Hence, a reduction in peak

von Mises stress in implant and screws due to osseointegration is observed. Although implant

and screw stresses remained within the corresponding yield limit during both nonosseointegrated

and osseointegrated (OI) conditions, during nonosseointegrated condition, screw stresses were

higher in standard TMJ implant than those of the narrow TMJ implant. Therefore, based on this

study, although both the stock implants were found to be safe, narrow TMJ is preferred over

standard TMJ for joint replacement.

There were certain limitations of the present study. Even though the bone is

heterogeneous anisotropic, the material property of cortical and cancellous bone was considered

as a region-specific orthotropic material in the current work[14]. Modelling screws as cylindrical

entities, while neglecting its threads, is another limitation of the present study. However, detailed

thread modelling is primarily necessary when the focus is on understanding the stress-strain

distribution at the screw thread interface [43,44] and, therefore, this assumption will not

influence the overall prediction of this current study. In addition, inter-patient anatomical and

muscle force variations of the human mandible were neglected in this study. Despite these

limitations, this study on stock TMJ implants provide a thorough understanding on the

performance of different stock implants under clenching loads and is expected to assist clinicians

to choose a proper design of patient-specific TMJ implant.

5. Conclusion

To summarize, the present study investigated the biomechanics of narrow and standard TMJ

implants on a patient-specific human mandible under different biting tasks representing a

complete mastication cycle. Ipsilateral clenching resulted in higher strains in implant as

compared to contralateral clenching. Overall, stresses and strains in the cortical bone, TMJ

implants and screws were well below the corresponding failure limits for all the models. While

osseointegration reduced stresses and strains in cortical bone for both the stock implants, a

standard TMJ implant induced higher stress in cortical bone and higher strains in screws as

compared to narrow TMJ implant during immediate post-operative non-osseointegrated

condition. Therefore, this study suggests that although both standard and narrow TMJ implants

were found to be safe for joint replacements, narrow TMJ implant should perhaps be preferred

over the standard ones.

Funding

The study was supported by the Indo–German Science & Technology Centre (IGSTC) project:

"add-bite: Development of patient specific additively manufactured mandibular implants with

biotechnology inspired functional lattice structures" under grant no. IGSTC/Call 2020/add-
bite/48/2021-22/260.

CRediT authorship contribution statement

Rajdeep Ghosh: Conceptualization, Data Curation, Formal Analysis, Investigation,
Methodology, Software, Validation, Visualization, Writing – original draft, Writing – review &
editing. **Girish Chandra:** Conceptualization, Data Curation, Formal Analysis, Methodology,
Visualization, Writing – review & editing. **Vivek Verma:** Data Curation, Visualization, Writing
– review & editing. **Kamalpreet Kaur:** Writing – review & editing. **Ajoy Roychoudhury:**
Funding acquisition, Project Administration, Resources, Supervision. **Sudipto Mukherjee:**
Conceptualization, Funding acquisition, Methodology, Project Administration, Resources,
Supervision, Writing – review & editing. **Anoop Chawla:** Conceptualization, Funding
acquisition, Methodology, Project Administration, Resources, Supervision, Writing – review &
editing. **Kaushik Mukherjee:** Conceptualization, Funding acquisition, Methodology, Project
Administration, Resources, Supervision, Writing – review & editing.

Declaration of competing interest

There are no possible conflicts of interest for the authors in terms of funding support, research,
authorship, or publishing of this paper.

References:

[1]   A. Roychoudhury, P. Yadav, O. Bhutia, R. Mane, R. Yadav, D. Goswami, A. Jose,
Alloplastic total joint replacement in management of temporomandibular joint ankylosis,
J.   Oral   Biol.   Craniofacial   Res.   11   (2021)   457–465.
https://doi.org/10.1016/j.jobcr.2021.05.006.

[2]   K. Bhatt, A. Roychoudhury, O. Bhutia, R.M. Pandey, Functional outcomes of gap and

359   interposition arthroplasty in the treatment of temporomandibular joint ankylosis, J. Oral

360   Maxillofac. Surg. 72 (2014) 2434–2439. https://doi.org/10.1016/j.joms.2014.08.012.

361   [3]   T. Yoda, N. Ogi, H. Yoshitake, T. Kawakami, R. Takagi, K. Murakami, H. Yuasa, T.

362   Kondoh, K. Tei, K. Kurita, Clinical guidelines for total temporomandibular joint

363   replacement, Jpn. Dent. Sci. Rev. 56 (2020) 77–83.

364   https://doi.org/10.1016/j.jdsr.2020.03.001.

365   [4]   J. Durham, T.R.O. Newton-John, J.M. Zakrzewska, Temporomandibular disorders, BMJ

366   350 (2015) 1–9. https://doi.org/10.1136/bmj.h1154.

367   [5]   S. Kanatsios, O. Breik, G. Dimitroulis, Biomet stock temporomandibular joint prosthesis:

368   Long-term outcomes of the use of titanium condyles secured with four or five condylar

369   fixation screws, J. Cranio-Maxillofacial Surg. 46 (2018) 1697–1702.

370   https://doi.org/10.1016/j.jcms.2018.07.002.

371   [6]   H.E. Giannakopoulos, D.P. Sinn, P.D. Quinn, Biomet microfixation temporomandibular

372   joint replacement system: A 3-year follow-up study of patients treated during 1995 to

373   2005, J. Oral Maxillofac. Surg. 70 (2012) 787–794.

374   https://doi.org/10.1016/j.joms.2011.09.031.

375   [7]   S. Kerwell, M. Alfaro, R. Pourzal, H.J. Lundberg, Y. Liao, C. Sukotjo, L.G. Mercuri,

376   M.T. Mathew, Examination of failed retrieved temporomandibular joint (TMJ) implants,

377   Acta Biomater. 32 (2016) 324–335. https://doi.org/10.1016/j.actbio.2016.01.001.

378   [8]   J.N.A.R. Ferreira, C.C. Ko, S. Myers, J. Swift, J.R. Fricton, Evaluation of Surgically

379   Retrieved Temporomandibular Joint Alloplastic Implants: Pilot Study, J. Oral Maxillofac.

Surg. 66 (2008) 1112–1124. https://doi.org/10.1016/j.joms.2007.09.013.

[9]   L.G. Mercuri, Temporomandibular joint replacement devices - dark past to challenging

future, Stomatol. Dis. Sci. 2019 (2019). https://doi.org/10.20517/2573-0002.2018.25.

[10] J. Zhao, L. Zou, D. He, E. Ellis, Comparison of bone adaptation after modification in

biomet standard alloplastic temporomandibular joint prostheses, J. Cranio-Maxillofacial

Surg. 46 (2018) 1707–1711. https://doi.org/10.1016/j.jcms.2018.07.024.

[11] L.G. Mercuri, Alloplastic temporomandibular joint replacement: Rationale for the use of

custom devices, Int. J. Oral Maxillofac. Surg. 41 (2012) 1033–1040.

https://doi.org/10.1016/j.ijom.2012.05.032.

[12] L.M. Wolford, M.C. Pitta, O. Reiche-Fischel, P.F. Franco, TMJ concepts/techmedia

custom-made TMJ total joint prosthesis: 5-year follow-up study, Int. J. Oral Maxillofac.

Surg. 32 (2003) 268–274. https://doi.org/10.1054/ijom.2002.0350.

[13] L. Zou, D. He, E. Ellis, A Comparison of Clinical Follow-Up of Different Total

Temporomandibular Joint Replacement Prostheses: A Systematic Review and Meta-

Analysis, J. Oral Maxillofac. Surg. 76 (2018) 294–303.

https://doi.org/10.1016/j.joms.2017.08.022.

[14] T.W.P. Korioth, D.P. Romilly, A.G. Hannam, Three‐dimensional finite element stress

analysis of the dentate human mandible, Am. J. Phys. Anthropol. 88 (1992) 69–96.

https://doi.org/10.1002/ajpa.1330880107.

[15] T.W. Korioth, A.G. Hannam, Mandibular forces during simulated tooth clenching., J.

Orofac. Pain 8 (1994) 178–189.

https://doi.org/https://pgocclusion.com/files/KoriothHannam01.pdf.

[16] I. Ichim, M. V. Swain, J.A. Kieser, Mandibular stiffness in humans: Numerical predictions, J. Biomech. 39 (2006) 1903–1913. https://doi.org/10.1016/j.jbiomech.2005.05.022.

[17] F. Gröning, M.J. Fagan, P. O'Higgins, The effects of the periodontal ligament on mandibular stiffness: A study combining finite element analysis and geometric morphometrics, J. Biomech. 44 (2011) 1304–1312. https://doi.org/10.1016/j.jbiomech.2011.01.008.

[18] F. Gröning, M. Fagan, P. O'higgins, Comparing the Distribution of Strains with the Distribution of Bone Tissue in a Human Mandible: A Finite Element Study, Anat. Rec. 296 (2013) 9–18. https://doi.org/10.1002/ar.22597.

[19] A.H. Choi, B. Ben-Nissan, R.C. Conway, Three-dimensional modelling and finite element analysis of the human mandible during clenching, Aust. Dent. J. 50 (2005) 42–48. https://doi.org/10.1111/j.1834-7819.2005.tb00084.x.

[20] R.T. Hart, V. V. Hennebel, N. Thongpreda, W.C. Van Buskirk, R.C. Anderson, Modeling the biomechanics of the mandible: A three-dimensional finite element study, J. Biomech. 25 (1992) 261–286. https://doi.org/10.1016/0021-9290(92)90025-V.

[21] A. Dutta, K. Mukherjee, V.S. Seesala, K. Dutta, R.R. Paul, S. Dhara, S. Gupta, Comparative evaluation of a patient-specific customised plate designs and screws for partial mandibular reconstruction, Med. Eng. Phys. 111 (2023) 103941. https://doi.org/10.1016/j.medengphy.2022.103941.

[22] A. Kashi, A.R. Chowdhury, S. Saha, Finite element analysis of a TMJ implant, J. Dent.

Res. 89 (2010) 241–245. https://doi.org/10.1177/0022034509357716.

[23] J. Huo, P. Dérand, L.E. Rännar, J.M. Hirsch, E.K. Gamstedt, Failure location prediction

by finite element analysis for an additive manufactured mandible implant, Med. Eng.

Phys. 37 (2015) 862–869. https://doi.org/10.1016/j.medengphy.2015.06.001.

[24] M. Mesnard, A. Ramos, Experimental and numerical predictions of Biomet® alloplastic

implant in a cadaveric mandibular ramus, J. Cranio-Maxillofacial Surg. 44 (2016) 608–

615. https://doi.org/10.1016/j.jcms.2016.02.004.

[25] B. Bekcioglu, E. Bulut, B. Bas, The Effects of Unilateral Alloplastic Temporomandibular

Joint Replacement on the Opposite-Side Natural Joint: A Finite-Element Analysis, J. Oral

Maxillofac. Surg. 75 (2017) 2316–2322. https://doi.org/10.1016/j.joms.2017.05.017.

[26] M. Pinheiro, R. Willaert, A. Khan, A. Krairi, W. Van Paepegem, Biomechanical

evaluation of the human mandible after temporomandibular joint replacement under

different biting conditions, Sci. Rep. 11 (2021) 1–12. https://doi.org/10.1038/s41598-021-

93564-3.

[27] S.M. Ingawale, T. Goswami, Design and Finite Element Analysis of Patient-Specific Total

Temporomandibular Joint Implants, Materials (Basel). 15 (2022).

https://doi.org/10.3390/ma15124342.

[28] A. Gupta, A. Dutta, K. Dutta, K. Mukherjee, Biomechanical influence of plate

configurations on mandible subcondylar fracture fixation: a finite element study, Med.

Biol. Eng. Comput. 61 (2023) 2581–2591. https://doi.org/10.1007/s11517-023-02854-7.

[29] P. Ruf, V. Orassi, H. Fischer, C. Steffen, K. Kreutzer, G.N. Duda, M. Heiland, S. Checa,

C. Rendenbach, Biomechanical evaluation of CAD/CAM magnesium miniplates as a

fixation strategy for the treatment of segmental mandibular reconstruction with a fibula

free flap, Comput. Biol. Med. 168 (2024) 107817.

https://doi.org/10.1016/j.compbiomed.2023.107817.

[30] K. Mukherjee, S. Gupta, Bone ingrowth around porous-coated acetabular implant: a three-

dimensional finite element study using mechanoregulatory algorithm, Biomech. Model.

Mechanobiol. 15 (2016) 389–403. https://doi.org/10.1007/s10237-015-0696-7.

[31] R. Ghosh, S. Chanda, D. Chakraborty, Qualitative predictions of bone growth over

optimally designed macro-textured implant surfaces obtained using NN-GA based

machine learning framework, Med. Eng. Phys. 95 (2021) 64–75.

https://doi.org/10.1016/j.medengphy.2021.08.002.

[32] BIOMET Microfixation, Mandibular Joint Replacement System by Zimmer Biomet, 2007.

https://doi.org/http://www.wlorenz.com.co/sites/default/files/documentos_producto/TMJ.p

df.

[33] L. Hijazi, W. Hejazi, M.A. Darwich, K. Darwich, Finite element analysis of stress

distribution on the mandible and condylar fracture osteosynthesis during various clenching

tasks, Oral Maxillofac. Surg. 20 (2016) 359–367. https://doi.org/10.1007/s10006-016-

0573-2.

[34] R. Fan, J. Liu, Z. Jia, Biomechanical evaluation of different strain judging criteria on the

prediction precision of cortical bone fracture simulation under compression, Front.

Bioeng. Biotechnol. 11 (2023) 1–9. https://doi.org/10.3389/fbioe.2023.1168783.

[35]   E. Schileo, E. Dall'Ara, F. Taddei, A. Malandrino, T. Schotkamp, M. Baleani, M.

466   Viceconti, An accurate estimation of bone density improves the accuracy of subject-

467   specific finite element models, J. Biomech. 41 (2008) 2483–2491.

468   https://doi.org/10.1016/j.jbiomech.2008.05.017.

469   [36]   C. Meyer, J.L. Kahn, P. Boutemi, A. Wilk, Photoelastic analysis of bone deformation in

470   the region of the mandibular condyle during mastication, J. Cranio-Maxillofacial Surg. 30

471   (2002) 160–169. https://doi.org/10.1054/jcms.2002.0297.

472   [37]   M.U. Farooq, M.P. Mughal, N. Ahmed, N.A. Mufti, A.M. Al-Ahmari, Y. He, On the

473   investigation of surface integrity of Ti6Al4V ELI using si-mixed electric discharge

474   machining, Materials (Basel). 13 (2020). https://doi.org/10.3390/ma13071549.

475   [38]   L.E. Claes, C.A. Heigele, Magnitudes of local stress and strain along bony surfaces

476   predict the course and type of fracture healing, J. Biomech. 32 (1999) 255–266.

477   https://doi.org/10.1016/S0021-9290(98)00153-5.

478   [39]   D.R. Carter, G.S. Beaupré, N.J. Giori, J.A. Helms, Mechanobiology of Skeletal

479   Regeneration, Clin. Orthop. Relat. Res. 355 (1998).

480   https://doi.org/https://journals.lww.com/clinorthop/fulltext/1998/10001/mechanobiology_

481   of_skeletal_regeneration.6.aspx.

482   [40]   J.-P. van Loon, L.G.M. de Bont, F.K.L. Spijkervet, G.J. Verkerke, R.S.B. Liem, A short-

483   term study in sheep with the Groningen temporomandibular joint prosthesis, Int. J. Oral

484   Maxillofac. Surg. 29 (2000) 315–324. https://doi.org/10.1034/j.1399-0020.2000.290501.x.

485   [41]   T. Sugiura, K. Horiuchi, M. Sugimura, S. Tsutsumi, Evaluation of threshold stress for

486   bone resorption around screws based on in vivo strain measurement of miniplate., J.

Musculoskelet. Neuronal Interact. 1 (2000) 165–70.

http://www.ncbi.nlm.nih.gov/pubmed/15758514.

[42] M.R. Niroomand, M. Arabbeiki, Implant stability in different implantation stages:

Analysis of various interface conditions, Informatics Med. Unlocked 19 (2020) 100317.

https://doi.org/10.1016/j.imu.2020.100317.

[43] R. Ghosh, S. Chanda, D. Chakraborty, The influence of macro-textural designs over

implant surface on bone on-growth: A computational mechanobiology based study,

Comput. Biol. Med. 124 (2020) 103937.

https://doi.org/10.1016/j.compbiomed.2020.103937.

[44] J.A. Inzana, P. Varga, M. Windolf, Implicit modeling of screw threads for efficient finite

element analysis of complex bone-implant systems, J. Biomech. 49 (2016) 1836–1844.

https://doi.org/10.1016/j.jbiomech.2016.04.021.

514   **Tables**

515   Table 1: Material properties of the components of the FE model [14]

Components	Young's Modulus			Poisson's Ratio			Shear Modulus		
	(GPa)						(GPa)		
	E_x	E_y	E_z	ν_{xy}	ν_{yz}	ν_{xz}	G_{xy}	G_{yz}	G_{xz}
Cortical									
Symphyseal and mental	23	10	15	0.3	0.3	0.3	4.8	3.6	6.2
Gonial angle region	20	11	12	0.3	0.3	0.3	4.8	5.3	6.0
Rest of the cortical	17	6.9	8.2	0.3	0.3	0.3	2.8	2.9	4.6
Cancellous	0.96	0.32	0.39	0.3	0.3	0.3	0.09	0.13	0.17
Enamel	80	-	-	0.3	-	-	-	-	-
Dentin	17.6	-	-	0.25	-	-	-	-	-
Periodontal ligament									
Coronal third	0.0032	-	-	0.45	-	-	-	-	-
Middle third	0.0027	-	-	0.45	-	-	-	-	-
Apical third	0.0025	-	-	0.45	-	-	-	-	-

Fibrocartilage	0.006	-	-	0.47	-	-	-	-	-
Mandibular component and Screws (Ti-6Al-4V ELI)	113.8	-	-	0.342	-	-	-	-	-

519 Table 2: Muscle forces and boundary conditions simulating different clenching activities [21,33]

Clenching tasks	Side	Direction	Muscular force (N)							Boundary Condition
			SM	DM	MP	AT	MT	PT	LP	
INC	Right	Force	76.2	21.2	136.4	12.6	5.7	3.0	47.5	Constrained the incisor regions
		F_x	−15.8	−11.6	66.3	−1.9	−1.3	−0.6	29.9	
		F_y	−31.9	7.6	−50.9	−0.6	2.9	2.6	−36.0	
		F_z	67.3	16.1	107.8	12.5	4.8	1.4	−8.3	
	Left	Force	76.2	21.2	136.4	12.6	5.7	3.0	47.5	
		F_x	15.8	11.6	−66.3	1.9	1.3	0.6	−29.9	
		F_y	−31.9	7.6	−50.9	−0.6	2.9	2.6	−36.0	
		F_z	67.3	16.1	107.8	12.5	4.8	1.4	−8.3	
ICP	Right	Force	190.4	81.6	132.9	154.9	91.8	71.0	18.1	Constrained the canine and premolars
		F_x	−39.4	−44.6	64.6	−23.1	−20.4	−14.8	11.4	
		F_y	−79.80	29.2	−49.61	−6.8	45.9	60.8	−13.7	
		F_z	168.3	61.9	105.1	153.0	76.8	33.7	−3.1	
	Left	Force	190.4	81.6	132.9	154.9	91.8	71.0	18.1	
		F_x	39.4	44.6	−64.6	23.1	20.4	14.8	−11.4	
		F_y	−79.8	29.2	−49.6	−6.8	45.9	60.8	−13.7	
		F_z	168.3	61.9	105.1	153.0	76.8	33.7	−3.1	

RMOL	Right	Force	137.1	58.8	146.9	115.4	63.1	44.6	20.1	Constrained the right molars
		F_x	−28.4	−32.1	71.4	−17.2	−14.0	−9.3	12.6	
		F_y	−57.4	21.0	−54.8	−5.1	31.5	38.1	−15.2	
		F_z	121.2	44.5	116.1	114.0	52.8	21.1	−3.5	
	Left	Force	114.2	49.0	104.9	91.7	64.0	29.5	43.5	
		F_x	23.6	26.7	−51.0	13.7	14.2	6.1	−27.4	
		F_y	−47.9	17.5	−39.1	−4.0	32.0	25.2	−32.9	
		F_z	101.0	37.1	83.0	90.5	53.6	14.0	−7.6	

LMOL	Right	Force	114.2	49.0	104.9	91.7	64.0	29.5	43.5	Constrained the left molars
		F_x	−23.6	−26.7	51.0	−13.7	−14.2	−6.1	27.4	
		F_y	−47.9	17.5	−39.1	−4.0	32.0	25.2	−32.9	
		F_z	101.0	37.1	83.0	90.5	53.6	14.0	−7.6	
	Left	Force	137.1	58.8	146.9	115.4	63.1	44.6	20.1	
		F_x	28.4	32.1	−71.4	17.2	14.0	9.3	−12.6	
		F_y	−57.4	21.0	−54.8	−5.1	31.5	38.1	−15.2	
		F_z	121.2	44.5	116.1	114.0	52.8	21.1	−3.5	
RGF	Right	Force	34.3	29.4	12.2	104.3	61.2	46.8	39.5	Constrained the right canine, premolars and molars
		F_x	−7.1	−16.0	5.9	−15.5	−13.6	−9.7	24.9	
		F_y	−21.5	7.6	−49.6	−0.5	2.9	3.9	−7.1	
		F_z	45.4	16.1	105.1	10.9	4.8	2.2	−1.6	
	Left	Force	51.4	21.2	132.9	11.1	5.7	4.5	9.4	
		F_x	10.6	11.6	−64.6	1.6	1.3	0.9	−5.9	
		F_y	−21.5	7.6	−49.6	−0.5	2.9	3.9	−7.1	
		F_z	45.4	16.1	105.1	10.9	4.8	2.2	−1.6	
LGF	Right	Force	51.4	21.2	132.9	11.1	5.7	4.5	9.4	Constrained the left canine, premolars and molars
		F_x	−10.6	−11.6	64.6	−1.6	−1.3	−0.9	5.9	

	F_y	−21.5	7.6	−49.6	−0.5	2.9	3.9	−7.1
	F_z	45.4	16.1	105.1	10.9	4.8	2.2	−1.6
Left	Force	34.3	29.4	12.2	104.3	61.2	46.8	39.5
	F_x	7.1	16.0	−5.9	15.5	13.6	9.7	−24.9
	F_y	−21.5	7.6	−49.6	−0.5	2.9	3.9	−7.1
	F_z	45.4	16.1	105.1	10.9	4.8	2.2	−1.6

521
522

Figures

Figure 1 Different components of the developed mandible model: (a) teeth with enamel and

dentin; (b) periodontal ligament (PDL) comprising of upper, middle, and basal PDL; (c)

cancellous bone; (d) blocks representing temporal bone; (e) articular fibrocartilage; (f) cortical

bone with three major regions: symphyseal and mental, gonial, rest of the mandible; and (g) the

complete mandible model.

555   **Figure 2** Developed FE models of implanted mandibles: (a, c) Narrow TMJ Implant (b, d)

556   Standard TMJ Implant (e) muscle attachment sites and representative boundary conditions for

557   incisor (INC) loading condition.

Figure 3 Maximum principal stress distributions across intact and implanted mandibles under complete mastication cycle. For implanted mandibles, stress distributions for both non-osseointegrated (NOI) and osseointegrated (OI) conditions are shown.

Figure 4 Maximum principal strain distribution across the intact and implanted mandibles under complete mastication cycle. For implanted mandible, strain distributions during both non-osseointegrated (NOI) and osseointegrated (OI) conditions are shown.

595   **Figure 5** von Mises stress distribution in narrow and standard TMJ implants and screws under

596   complete mastication cycle during non-osseointegrated (NOI) and osseointegrated (OI)

597   conditions.

Figure 6 (a) Maximum principal stress, and (b) maximum principal strain in the cortical bone of

intact and implanted (with narrow/standard mandibular component) mandible.

641 **Figure 7** Maximum von Mises stresses in (a) mandibular component and (b) screws.