Modular Nano-Scaffold Biocatalysis for Superior PET Depolymerization and Valorization

Yujia Zhang[1,2], Chongsen Li[1,2], Ehsan Hashimi[2], Enting Xu[3], Xuemei Yang[3], Yanbing Lin[1], Hui Gao[2,*], Zhuobin Liang[2,*,+]

[1] College of Life Sciences, Northwest A&F University, Yangling, Shaanxi 712100, China

[2] Institute of Molecular Physiology, Shenzhen Bay Laboratory, Shenzhen 518132, China

[3] School of Science, Harbin Institute of Technology (Shenzhen), Shenzhen 518055, China

[+] Lead Contact

[*] Correspondence addressed to: ZL (zbliang@szbl.ac.cn) or HG (gaohui@szbl.ac.cn)

Abstract

The global crisis of polyethylene terephthalate (PET) waste demands innovative solutions for sustainable management. Current approaches are often inefficient, energy-intensive, and result in incomplete depolymerization. Here, we introduce SPEED (Scaffold-enabled PET Enzyme Ensemble-augmented Degradation), a transformative biocatalytic platform engineered for the superior degradation across diverse PET substrates. Through the strategic combination of complementary PET hydrolases on a tailored protein nano-scaffold and extensive optimization, SPEED achieves near-complete depolymerization of PET into its constituent monomers, exceeding existing biocatalytic systems' efficiency by up to two orders of magnitude. The platform's versatility and industrial relevance are further demonstrated through successful integration with metal-organic frameworks (MOFs) for enhanced stability and reusability, enabling PET upcycling into valuable products, and its compatibility with a yeast-based live cell system for surface display. SPEED's high efficiency, adaptability, and cost-effectiveness position it as a powerful technology to accelerate sustainable plastic waste management and drive a circular PET economy.

Main

Polyethylene terephthalate (PET), a ubiquitous polyester valued for its durability and versatility, poses a major sustainability crisis due to its environmental persistence and the limitations of traditional recycling. Its vast global production, exceeding 30 million tons annually, leads to widespread plastic pollution, harming terrestrial and marine ecosystems [1], releasing hazardous microplastics [2], and posing risks to human health [3,4]. Traditional mechanical recycling requires extensive sorting, often yields low-value products due to incomplete degradation [5], and can further exacerbate microplastic pollution [6]. Chemical recycling, while promising, can be energy-intensive and produce undesirable byproducts [7,8].

Biocatalytic degradation, harnessing enzymes from microorganisms to break down PET polymers, offers a promising and sustainable alternative [9]. This approach is attractive due to its potential for complete degradation, lower environmental impact, and the generation of valuable products through recycling and upcycling, as showcased in early-phase industrial demonstrations [10]. Several PET hydrolases, including TfH [11], leaf-branch cutinase (LCC) [12], and *Is*PETase [13], have been identified and further engineered [14,15] (**Supplementary Table 1**). However, existing biocatalytic systems still face major hurdles such as incomplete conversion [16], intermediate inhibition [17], limited efficiency on high-crystallinity PET, and cost-effectiveness [18], hindering their widespread industrial implementation.

Recent efforts to address these limitations have focused on multi-enzyme systems that leverage the synergistic action of different PET hydrolases [19–25] (**Table 1**). While these systems have shown promise, challenges in achieving complete depolymerization and overcoming intermediate inhibition persist. Moreover, they often lack the modularity and adaptability needed to incorporate diverse enzyme functionalities for optimal PET degradation across various substrates and conditions, and to expand into applications such as monomer upcycling and live cell systems, underscoring the need for innovative designs.

In this study, we introduce Scaffold-enabled PET Enzyme Ensemble-augmented Degradation (SPEED), a modular biocatalytic platform designed to address the PET waste crisis and promote a shift towards a circular economy (**Fig. 1**). SPEED strategically combines multiple complementary PET hydrolases with a flexible nanometric protein scaffold, fostering their synergistic action to ensure complete intermediate conversion across diverse substrates under mild conditions. Through iterative optimization, SPEED significantly outperforms existing biocatalytic systems. The platform's versatility and industrial relevance are further showcased through successful applications in MOF-immobilization, PET upcycling, and a yeast-based live cell system, highlighting its transformative potential for sustainable plastic waste management.

58
Fig. 1: Schematic overview of PET recycling pathways, highlighting SPEED's role in promoting a circular
PET economy. Arrows depict the mechanical, chemical and biological PET recycling processes. The SPEED system
(central circle) utilizes a modular enzyme-scaffold complex to achieve complete depolymerization of various PET
substrates with a broad range of crystallinity into valuable monomers, terephthalate (TPA) and ethylene glycol (EG).
Key advantages of SPEED at different stages of the recycling and upcycling processes are highlighted. The enzyme-
scaffold complex structure was constructed by integrating PETase structures from the PDB with an AlphaFold2-
predicted scaffold model. Abbreviations: MA, *cis*-muconic acid; PHA, polyhydroxyalkanoate; SA, succinic acid;
ICA, isocinchomeronic acid; GA, gallic acid; VA, vanillic acid.

 Table 1. Current multi-enzyme systems for biodegradation of PET plastics

System	PET substrate*	Reaction condition	Enzymes	Total products (mM)	Reaction volume (mL)	Degradation efficiency (mol total products /mmol enzyme)	Efficiency fold-change (SPEED vs. other systems)	Reference
HiC+CALB	Bottle-H	60℃, 14 days, pH 7	225 nmol HiC + 24.24 nmol CALB	2.247	5	0.045	133.8 (SPEED★)	19
HiC+CALB	Bottle-H	60℃, 14 days, pH 7	62.5 nmol HiC + 60.61 nmol CALB	0.728	10	0.06	102.0 (SPEED★)	20
TfCa+LCC	Film-L	60℃, 24 h, pH 9	21.7 nmol TfCa (immobilized) + 13.85 nmol LCC	10.42 (TPA: 6.71, M/BHET: 3.71)	40	11.72	4.7 (total) 13.0 (TPA) (SPEED♠)	22
PETase+ MHETase	Film-L	30℃, 96 h, pH 7.5	0.33 nmol PETase + 0.081 nmol MHETase	2.87	0.5	3.47	28.6 (SPEED♣)	21
cPETase+ cCALB+ mCbpA (scaffold)	Waste-H	30℃, 96 h pH 7	10 nmol cPETase + 10 nmol cCALB	0.04	40⁺	0.08	26.9 (SPEED♦)	25
	Film-H			0.089		0.18	12.1 (SPEED♦)	
LCC+TTCE	Film-L	60℃, 96 h, pH 8	1 nmol LCC + 1 nmol TTCE	17.97	0.5	4.49	22.1 (SPEED♣)	23
TfCaWA+ *Is*PETasePM	Film-L	45℃, 24 h, pH 7.5	0.05 nmol PETase + 0.55 nmol TfCa	1.68	1	2.80	19.7 (SPEED♠)	24
SPEED (FAST-PETase+ MHETase+ ICCG+Scaffold)	Film-L	40℃, 24 h, pH 7	0.25 nmol FAST + 0.25 nmol MHETase + 0.25 nmol ICCG	82.87	0.5	55.25 (♠)	-	This study (**Fig. 5**)
	Powder-H	40℃, 96 h, pH 7		143.76		95.84 (♥)	-	
	Film-L			148.82		99.21 (♣)	-	
	Film-H			3.23		2.15 (♦)	-	
	Film-L	40℃, 14 days, pH 7		189.85		126.57 (■)	-	
	Film-H			9.05		6.03 (★)	-	

68 Note: **a.** * Substrates can vary in different studies. To facilitate their comparison, we define substrates as follows: L:

69 low crystallinity (< 20%), H: high crystallinity (> 20%). **b.** ⁺ Where reaction volume was not specified in the original

70 publication nor provided by the corresponding author, a reaction volume of 40 mL was assumed for efficiency

71 calculations, based on the largest volume reported in similar studies listed in Table 1. **c.** Total products include TPA,

72 MHET, and BHET. **d.** Extended details associated of this table is provided in **Supplementary File 1**.

Results

Synergistic enzyme-scaffold system for enhanced PET degradation

To harness the complementary properties of different PET hydrolases and promote their synergy, we utilized the established dockerin-cohesin (doc-coh) pairs [26] to assemble multiple PET hydrolases onto a tailored scaffold. We initially selected FAST-PETase [15], for its potent PET hydrolysis at ambient conditions, and MHETase [13] for its ability to convert hydrolysis intermediates bis-(2-hydroxyethyl) terephthalate (BHET) and mono-(2-hydroxyethyl) terephthalate (MHET) into valuable monomers terephthalic acid (TPA) and ethylene glycol (EG) (**Fig. 2a**).

Fig. 2: Enzyme-scaffold complexes enhance PET degradation efficiency. a Schematic of enzymatic PET hydrolysis. Hydrolysis intermediates MHET and BHET can inhibit PETase activity, which is mitigated by MHETase. **b** Schematic of enzyme-scaffold complexes. Enzymes with complementary PET degradation activities are fused with dockerin domains, enabling co-assembly with a cohesin-containing scaffold. **c-d** Binding analysis of MHETase-CelF **(c)** and FAST-PETase-CelK **(d)** to Scaf.2 (CipA-CBM-CipC). **e** Binding affinity of scaffolds to PET substrates. **f-h** PET degradation assays comparing various enzyme and scaffold combinations on different substrates: PET powder (40.8% crystallinity) **(f)**, low crystallinity PET film (film-L, 18.0% crystallinity) **(g)**, and high crystallinity PET film (film-H, 43.3% crystallinity) **(h)**; reactions were performed at 30°C, pH 7.0, for 96 hours using 100 mg PET substrate, 0.2 nmol individual enzymes, with an enzyme:scaffold molar ratio of 0.2:1. Data are presented as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA (ns: not significant, *$p < 0.1$, **$p < 0.01$, ***$p < 0.001$, ****$p < 0.0001$).

PET biodegradation assays confirmed the synergistic effects of FAST and MHETase in hydrolyzing PET with different crystallinity (**Fig. 2f-h** and **Supplementary Fig. 3**). Consistent with previous findings [13], FAST alone readily hydrolyzed PET, while MHETase exhibited no independent activity. While combining these enzymes enhanced degradation, particularly for high-crystallinity substrates, further improvements were achieved by assembling them onto Scaf.1 (Complex-A). This resulted in over two-fold increases in total PET hydrolysis compared to FAST alone for all tested substrates, and a two-fold increase for PET powder and low-crystallinity film (film-L) compared to

102 the enzyme mixture without scaffold. Notably, complexes with Scaf.2 (Complex-B) slightly

103 outperformed those with Scaf.1, yielding 22.11 mM (PET powder), 17.29 mM (film-L), and 0.73

104 mM (film-H) total products after 96 hours.

Optimization of MHETase expression, assembly, and activity

The above results highlight the importance of MHETase in mitigating the competitive inhibition of

intermediates to PET hydrolases (**Fig. 2a**). However, the extremely low expression level of

recombinant MHETase in *E.coli*, hindered our further development (**Supplementary Fig. 4a**,**b**). To

address this bottleneck, we pursued a multi-pronged optimization strategy focusing on host strain

selection, induction conditions, codon usage, and protein domain fusions (**Fig. 3a**,**b** and

Supplementary Fig. 4,5). This led to the creation of SH3$_L$-optiMHETase and a redesigned scaffold,

CipA-CBM-SH3$_D$ (Scaf.3). Importantly, SH3$_L$-optiMHETase demonstrated significantly improved

binding affinity to Scaf.3 (an 80-fold enhancement compared to MHETase-CelF (**Fig. 3c** vs. **Fig.**

2c), reaching a level comparable to FAST (**Fig. 3c-e**). These modifications enabled the successful

assembly of Complex-C (**Fig. 3a**).

Degradation assays across various PET substrates revealed significant improvements (**Fig. 3f-**

h). Complex-C yielded 22.37 mM, 23.22 mM and 0.83 mM TPA production with PET powder, film-

L and film-H, respectively. This represents a 3-fold increase over FAST-only groups and a 22.2%

average increase over Complex-B (**Fig. 3f-h** vs. **Fig. 2f-h**). These results confirm Complex-C's

effectiveness in promoting PET recycling, highlighting SPEED's adaptability and potential for cost

reduction in complex construction.

Modular scaffold expansion to boost PET degradation capacity

Our optimization from Complex-A to Complex-C exemplifies the power of SPEED's modular

scaffold design, allowing for tailored enzyme combinations for diverse substrates. To broaden

substrate range, we incorporated ICCG, an enzyme active towards higher-crystallinity substrates

(6%-40%) [27], complementing the preference of FAST-PETase for lower-crystallinity PET (1%-30%)

[15]. Using the doc-coh pair ScaA-ScaB [28] we successfully integrated ICCG into a new scaffold, CipA-

CBM-SH3$_D$-ScaB (Scaf.4), forming Complex-D (**Fig. 4a** and **Supplementary Fig. 6**).

Degradation assays revealed several key insights (**Fig. 4b-d**). The result showed ICCG has

slightly higher activity towards PET substrates compared to FAST at 30°C. Notably, inclusion of

MHETase with ICCG led to near-complete conversion of MHET and BHET intermediates into TPA,

and EG by implication. Moreover, combining ICCG, FAST, and MHETase greatly increased TPA

productions to 33.07 mM (powder), 36.09 mM (film-L) and 0.93 mM (film-H). Importantly, Scaf.4

further boosted the efficiency to 44.66 mM (powder), 49.03 mM (film-L) and 1.32 mM (film-H).

Finally, we confirmed the strong binding of all three enzymes (FAST, MHETase, and ICCG) to the

scaffold, demonstrating stability of Complex-D (**Fig. 4e-g**). Overall, Complex-D further enhanced

PET biodegradation efficiency and achieved complete monomer conversion.

Fig. 3: MHETase optimization for enhanced expression, scaffold binding, and PET degradation. a Schematic illustration of MHETase optimization strategy and the assembly of Complex-C with Scaf.3 (CipA-CBM-SH3$_D$). **b** Purification efficiency of different MHETase variants. M-CelF: MHETase-CelF; optiM-CelF: codon optimized M-CelF; M-optiSH3$_L$: optiMHETase-SH3$_L$; SH3$_L$-optiM: SH3$_L$-optiMHETase; optiM: codon optimized MHETase (as control); **c-e** Binding analysis of SH3$_L$-optiMHETase **(c)**, optiMHETase-SH3$_L$ **(d)**, and FAST-PETase-CelK **(e)** to Scaf.3. **f-h** PET degradation assays using FAST and SH3$_L$-optiM, assembled with Scaf.3, on various substrates: PET powder **(f)**, film-L **(g)**, and film-H **(h)**. All reactions were performed at 30°C, pH 7.0, for 96 hours using 100 mg PET substrate, with an enzyme:scaffold molar ratio of 0.2:1. Data are presented as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA (ns: not significant, *$p < 0.1$, **$p < 0.01$, ***$p < 0.001$, ****$p < 0.0001$).

Fig. 4: Scaffold engineering further enhances PET degradation with a three-enzyme complex. a Schematic illustration of Complex-D, formed by the assembly of three hydrolases (FAST-CelK, SH3L-optiMHETase, ICCG-ScaA) onto the modular scaffold Scaf.4 (CipA-CBM-SH3D-ScaB). **b-d** PET degradation assays comparing the activity of individual hydrolases and Complex-D on different substrates: PET powder **(b)**, film-L **(c)**, and film-H **(d)**. All reactions were performed at 30°C, pH 7.0, for 96 hours using 100 mg PET substrate, with an enzyme:scaffold molar ratio of 0.2:1. Data are presented as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA (ns: not significant, *p < 0.1, **p < 0.01, ***p < 0.001, ****p < 0.0001). **e-g,** Binding analysis of SH3L-optiMHETase **(e)**, FAST-CelK **(f)**, and ICCG-ScaA **(g)** to Scaf.4.

Improve SPEED performance through reaction optimization

To optimize the performance of the three-enzyme Complex-D and improve enzyme cost-effectiveness, we systematically investigated its PET degradation efficiency under various reaction conditions (**Fig. 5a**), beginning with the impact of enzyme-scaffold ratio (**Fig. 5b**). While increasing enzyme concentration enhanced product release (**Fig. 5b**, bar graph), ratios exceeding 0.5:1 (enzyme:Scaf.4) led to diminishing benefits from the scaffold (**Fig. 5b**, dot graph and **Supplementary Fig. 7**). This suggests that excessive enzymes may not only increase costs but also hinder substrate channeling due to limited scaffold availability. Consequently, we adopted the 0.5:1

enzyme-to-scaffold ratio for subsequent optimizations.

Next, we investigated the influence of temperature and PH on Complex-D performance (**Fig.**
5c,d). According to previous findings [29], the optimal temperatures for FAST and ICCG were
approximately 40°C and 60°C, respectively. Our results showed that further temperature increases
above 40°C resulted in elevated levels of intermediates and reduced TPA production, likely due to
adverse effects on enzyme activity of MHETase (**Supplementary Fig. 8**). The highest total product
yield (176.40 mM with 174.71 mM TPA) was achieved at 40°C and pH 7.0, which consists with the
optimal conditions for MHETase activity [30]. Next, the robustness of Complex-D under these optimal
conditions was validated across diverse PET substrates, including PET powder, films and
commercial bottles, confirming its outstanding ability to mediate complete PET degradation
(**Supplementary Fig. 9**).

The catalytic stability and substrate versatility of Complex-D, were assessed through long-term
PET degradation experiments under optimal conditions (40°C, pH 7.0, 0.5:1 Enz.:Scaf. ratio). This
complex exhibited robust and sustained hydrolysis across diverse PET substrates (**Fig. 5e-g**).
Scanning electron microscopy (SEM) revealed that treatment with the optimized Complex-D
(optiComplexD) induced significantly greater surface erosion and pore formation on PET film after
96 hours, compared to individual enzymes (FAST, ICCG, or MHETase) (**Fig. 5h**).

MOF immobilization enhances SPEED performance and reusability

To enhance the system's stability and reusability for industrial translation, we immobilized
optiComplex-D onto the metal-organic framework ZIF-8 [31] (**Fig. 6a**). The successful synthesis of
enzyme complex-conjugated ZIF-8 (optiComplex-D@ZIF-8) was characterized by SEM,
fluorescent microscopy, and further confirmed by XRD analysis, which showed strong peaks
matching the simulated ZIF-8 with a high loading efficiency of 92.8% (**Fig. 6a,b** and
Supplementary Fig. 10). Indeed, MOF immobilization further enhanced PET biocatalysis (**Fig.**
6d). Notably, optiComplex-D@ZIF-8 exhibited a 151% increase in PET degradation efficiency
compared to the enzyme mixture without the scaffold (Enz.3@ZIF-8), underscoring the importance
of the scaffold design even after the immobilization. Furthermore, immobilization significantly
improved the complex's stability across a wider pH range, with optiComplex-D@ZIF-8 showing
2.1-fold and 1.6-fold higher activity at pH 5.0 and 9.0, respectively, compared to the free
optiComplex-D (**Fig. 6e**). The reusability of optiComplex-D@ZIF-8 was also remarkable, retaining
52.2% activity after four 4-day cycles, significantly surpassing the 24.4% retained activity of
optiComplex-D without immobilization (**Fig. 6f**). Critically, the inclusion of the nano-scaffold
remained crucial even after ZIF-8 immobilization, as it exhibited superior long-term degradation
activity (**Fig. 6g**). This enhanced stability and reusability, coupled with the superior degradation
efficiency, underscore the potential of SPEED for cost-effective and sustainable PET recycling by
reducing enzyme consumption and improving process efficiency.

Fig. 5: Optimization of SPEED reaction conditions. a Overview of the optimization strategy. **b** Effect of enzyme-
to-scaffold molar ratio on PET degradation efficiency (30°C, pH 7.0, 96 hours, 100 mg PET powder, with a constant
1 mM scaffold concentration). Total product release (bar graph, left Y axis) and fold-change in efficiency with vs.
without Scaf.4 (dot graph, right Y axis) are shown. **c** Influence of temperature on PET degradation efficiency and
final products (0.5:1 enzyme:scaffold ratio, pH 7.0, 96 hours, 100 mg PET powder). **d** Impact of pH on PET
degradation efficiency and final products (0.5:1 enzyme:scaffold ratio, 40°C, 96 hours, 100 mg PET powder). **e-g**
Time-course analysis of PET degradation by optiComplex-D (40°C, pH 7.0, 0.5:1 enzyme:scaffold ratio) on different
substrates: PET powder **(e)**, film-L **(f)**, and film-H **(g)**. **h** SEM images of film-L after 96 hours of treatment at 40°C,
pH 7.0, with no enzyme (Control), single enzyme (MHETase, FAST, ICCG), and optiComplex-D. Data are presented
as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA (ns: not significant, *p < 0.1, **p
< 0.01, ***p < 0.001, ****p < 0.0001).

Fig. 6: MOF immobilization enhances SPEED performance and reusability. a Schematic illustration of optiComplex-D immobilized on ZIF-8 (optiComplex-D@ZIF-8). **b** SEM images of ZIF-8, Enz.3@ZIF-8 and optiComplex-D@ZIF-8. **c** Confocal microscope images of ZIF-8, Enz.3@ZIF-8 and optiComplex-D@ZIF-8. Alexa Fluor® 488 was used to detect His-tagged proteins. **d** PET degradation assays with PET powder at 40°C, pH 7.0, for 96 hours. **e** Impact of pH on TPA release at 40°C for 96 hours, with 1 M BHET as substrate. **f** Relative PET catalysis activity in each of the 4-day cycles normalized to the initial cycle. **g** Time-course analysis of PET degradation at 40°C, pH 7.0, with 0.5:1 enzyme:scaffold ratio on PET powder. Enz.3 represents a mixture of FAST-PETase, ICCG, and MHETase (0.25 nmol of each enzyme). Data are presented as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA (ns: not significant, *p < 0.1, **p < 0.01, ***p < 0.001, ****p < 0.0001).

PET upcycling through SPEED-enabled biocatalysis

The efficient depolymerization of PET by optiComplex-D provides an opportunity for coupling the upcycling of the resulting monomers into high-value chemicals [32–34]. To showcase this capability, we leveraged the SPEED platform's modularity to engineer a multi-enzyme assembly (Complex-E) capable of converting PET degradation product ethylene glycol (EG) to gallic acid (GA), a valuable compound with applications in in inflammation treatment and pathogen resistance [35–37]. The

conversion pathway we designed involves the sequential action of 1,2-propanediol oxidoreductase

(FucO) [38] and glycolaldehyde dehydrogenase (AldA) [39], with *Lactobacillus reuteri* NADH oxidase

(LrNox) [40] regenerating the required NAD^+ cofactor, a similar strategy builds upon our prior work

(**Fig. 7a,b**).

We explored two reaction designs to evaluate GA production efficiency. First, adding

Complex-E to the PET degradation products generated by Complex-D resulted in 2.65 mM GA in

4 days (**Fig. 7c**). Next, simultaneous addition of Complex-D and E further promoted GA production

to 4.61 mM in 4 days, a 1.74-fold increase (**Fig. 7d**), which likely stems from the synergistic action

of both complexes, enabling real-time conversion of the intermediate EG. Interestingly, the

simultaneous addition of free upcycling enzymes initially reduced Complex-D's PET degradation

rate (**Fig. 7e**), likely due their competition for Scaf.4 binding sites. However, pre-incubating the

upcycling enzymes with Scaf.4 before adding to Complex-D eliminated this competition,

highlighting the scaffold's ability to promote synergistic interactions while preventing interference

between different enzyme complexes.

Overall, the successful upcycling of PET waste into GA showcases the SPEED platform's

effectiveness in assembling diverse enzymes, improving reaction efficiency, and enabling a

promising strategy for multi-enzyme biocatalysis towards a circular PET economy.

Fig. 7: Valorization of PET waste via SPEED-enabled upcycling. a Schematic of the enzymatic synthesis pathway

for gallic acid (GA). **b** Schematic illustration of Complex-E. **c-d** GA production assays after 4-day, , using either

sequential addition of Complex-D (for PET degradation) followed by Complex-E (for GA production) **(c)** or

simultaneous addition of both complexes to the PET substrate **(d)**. **e** PET degradation performance under different

enzyme and scaffold combinations. All reactions were performed at 40°C, pH 7.0, for 96 hours, with 0.5 nmol of

each individual enzyme and enzyme:scaffold molar ratios of 0.5:1 for optiComplex-D and 1:1 for Complex-E. ND,

not detected. Data are presented as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA

(ns: not significant, *p < 0.1, **p < 0.01, ***p < 0.001, ****p < 0.0001).

Cell surface display expands SPEED to live cell systems

To further demonstrate the adaptability of SPEED for industrial PET biorecycling, we explored its integration with cell surface display technology, aiming to create a cost-effective live cell system compatible with large-scale fermentation processes [41]. We selected the industrial yeast *Pichia pastoris* for its ability to achieve high-yield protein production, attributed to its high growth density and secretion capacity [42,43]. Among various *P. pastoris* strains, we chose the SMD1168 strain for its superior capacity to display the scaffold on the cell surface and secrete PETases (**Fig. 8a** and **Supplementary Fig. 11**). The scaffold expressed by the engineered strain was displayed to the cell surface using the SED1 protein, which demonstrated the highest efficiency among the tested anchors (**Fig. 8b**). Confocal microscopy and flow cytometry confirmed the successful assembly of the multi-enzyme complex on the engineered *P. pastoris* cell surface (**Fig. 8c,d**). The surface-displayed SPEED Complex-B, facilitated by the scaffold, exhibited a remarkable increase in PET degradation efficiency, up to 3.05-fold higher than the secreted enzyme group [42,43] (**Fig. 8e**). This result underscores the advantage of enzyme synergy enabled by our SPEED design in accelerating PET degradation, both *in vitro* and *in vivo*.

Fig. 8: SPEED-enabled live cell system for PET degradation. a Schematic of the engineered *P. pastoris* SMD1168 system for cell-surface display of the enzyme complex. **b** Cell surface display efficiency of the scaffold using different anchor proteins. The relative efficiency was calculated by taking the maximum display efficiency as 100%. NC, negative control (scaffold fused with no anchor). **c-d** Characterization of engineered strains by confocal microscopy (**c**) and flow cytometry (**d**). **e** PET degradation assays using the engineered *P. pastoris* strains. Expression and reactions were performed at 30°C, pH 7.0, for 96 h (induction) and 48 h (reaction) with 100 mg PET powder substrate. The ratio of enzyme-secreting strains to the scaffold-displaying strain was 10:1. Statistical significance was determined by one-way ANOVA (ns: not significant, *p < 0.1, **p < 0.01, ***p < 0.001, ****p < 0.0001).

Discussion

Our study demonstrates SPEED's potential to transform current PET waste management. By achieving unprecedented efficiency across diverse PET waste substrates, SPEED offers significant advances over existing biocatalytic systems. This superior performance stems from several factors. The modular design of the nano-scaffold enables the integration of multiple enzymes with complementary activities, facilitating synergistic PET degradation and complete conversion to high-value monomers (TPA and EG). This complete depolymerization, evident in the minimal accumulation of intermediates, not only reduces environmental impact but also enhances the economic viability of biorecycling by generating products suitable for direct upcycling. Additionally, the strategic selection of enzymes with optimal activity at 40°C and pH 7.0, as well as the optimization of the enzyme-to-scaffold ratio, further contribute to SPEED's exceptional efficiency. These factors, along with the resolution of the MHETase expression and assembly bottleneck [44], collectively address the limitations of previous biocatalytic systems, such as incomplete conversion and intermediate inhibition, and pave the way for its industrial adoption.

Furthermore, SPEED's significant efficiency gains, the modular flexibility and the lower enzyme requirement for comparable performance highlight its cost-effectiveness. This addresses one of the major hurdles to large-scale adoption of biocatalytic PET recycling [29,45]. The modularity of SPEED also opens up opportunities for customization, potentially enabling the degradation of diverse PET waste streams with tailored enzyme cocktails.

Beyond its immediate impact on PET recycling, SPEED offers a broader contribution to sustainable materials management. The successful upcycling of PET waste into high-value compounds like gallic acid, exemplifies the platform's potential to drive a circular economy. Additionally, SPEED's compatibility with other strategies, such as cell surface display and enzyme immobilization, further enhances its efficiency and broadens its applicability. The SPEED-enabled live cell system offers additional benefits such as eliminating the need for antibiotics, ensuring stable enzyme production, and reducing plastic degradation costs. The integration of SPEED into existing industrial processes could reduce reliance on fossil fuels for PET production, while promoting circularity by closing the loop on plastic waste.

While our work demonstrates the promise of SPEED, challenges remain in scaling up the technology and ensuring its economic viability at an industrial level. Further research is needed to optimize enzyme production costs and explore the potential for incorporating additional upcycling enzymes [33]. Nevertheless, the results presented here underscore the transformative potential of nano-scaffolded enzyme complex platform such as SPEED in addressing the global plastic waste crisis and accelerating the transition towards a circular economy model. With its proven efficiency and promising scalability, SPEED has great potential to revolutionize waste management practices, reducing environmental harm and promoting a more sustainable future.

Methods

Plasmid construction

Genes encoding enzymes and scaffolds were obtained from commercial synthesis (Tsingke, China). Standard cloning techniques were employed using *E. coli* DH5α. Briefly, FAST-PETase, ICCG, FucO, AldA, LrNox and scaffold variants were cloned into pET28a vectors, while MHETase constructs utilized pET28a and pColdII vectors. Synthesized genes and pET28a vectors were digested with NdeI and XhoI (37°C, 1h), followed by T4 DNA ligase-mediated ligation (room temperature, 2h). This generated plasmids pET28a-FAST-PETase-CelK, pET28a-MHETase-CelF, pET28a-ICCG-ScaA, pET28a-FucO-CelF, pET28a-SH3$_L$-AldA, pET28a-LrNox-ScaA, pET28a-CipA-CBM-CipC, pET28a-CipA-CBM-SH3$_D$, and pET28a-CipA-CBM-SH3$_D$-ScaB.

To construct the living cell PET degradation system, *Pichia pastoris* SMD1168 was employed. The pPIC9K vector was utilized for the insertion and expression of MHETase, and Scaf.3. To engineer strain with exogenous gene insertion, primer pairs pScf-F/pScf-R were employed to amplify CipA-CBM-CipC-SED1, while primer pairs pF-F/pF-R and pM-F/pM-R were utilized to amplify FAST and MHETase, respectively. Additionally, primers pPIC9K-F/pPIC9K-R was used to amplify pPIC9K linearized vector. The pPICZC vector was utilized for the insertion of MHETase. MHETase and pPICZC linearized vector were amplified using primer pairs pZM-F/pZM-R and pPICZC-F/pPICZC-R. The linearized gene and vector were connected by seamless cloning to form the expression vectors pPICZC-FAST, pPIC9K-MHETase, pPIC9K-CipA-CBM-CipC-SED1, and pPICZC-MHETase. The expression vectors were linearized by SacI digestion and transformed into *P. pastoris* SMD1168. The transformants were cultured in histidine-deficient (SD-his) plates and screened for strains with high copies of the exogenous gene insertion by SD-his plates containing 5 mg/mL G418.

To reposition SH3$_L$ from the C-terminus to the N-terminus of optiMHETase, sequential PCR was performed with primer pairs M1-F/M-R, M2-F/M-R, and M3-F/M-R. To remove SH3$_L$ from SH3$_L$-optiMHETase (as control), PCR was performed with primer pairs M1-F/Md-R. For C-terminal His-tag of MHETase, PCR was conducted using primers his-F/his-R. Subsequent digestion with NdeI and XbaI, followed by T4 DNA ligase-mediated recombination, generated plasmids pColdII-MHETase-CelF, pColdII-optiMHETase-CelF, pColdII-optiMHETase-SH3$_L$, pColdII-SH3$_L$-optiMHETase, and pColdII-optiMHETase. All protein constructs were designed with both N- and C-terminal His tags.

Exogenous gene insertion analysis

The insertion copy number of exogenous genes was determined by quantitative real-time PCR (qPCR). The genomic DNA of engineered *P. pastoris* SMD1168 was extracted by the Yeast Genomic DNA Extraction Kit (TIANGEN, DP307). Genomic DNA of *P. pastoris* SMD1168$_{His4::CipA-CBM-CipC-SED1}$, *P. pastoris* SMD1168$_{His4::FAST}$, *P. pastoris* SMD1168$_{His4::MHETase}$ and *P. pastoris* SMD1168$_{His4::FAST-MHETase}$ were used as templates, respectively, for the amplification

359   of the genes CipA-CBM-CipC, FAST, MHETase with the primer pairs qC-F/qC-R, qF-F/qF-R, and

360   qM-F/qM-R; the housekeeping gene GAPDH was amplified with the primer pairs qGAPDH-

361   F/qGAPDH-R to obtain the copy number of the exogenous protein inserted in the engineered strains.

Recombinant protein expression and purification

For living cell systems, surface-displaying and secretory-expressing engineered bacteria were

individually pre-cultured in BMGY (1% yeast extract, 2% peptone, 100 mM potassium phosphate

buffer, 1.34% amino acid-free yeast nitrogen source, and 1% (v/v) glycerol, pH 6.0) at 30°C for 12

h, after which the number of cells was measured in the pre-cultured products. *P. pastoris*

SMD1168$_{His4::enzyme}$ was mixed with *P. pastoris* SMD1168$_{His4::scaffold}$ in a 10:1 ratio, resulting in a

final system comprising $2×10^7$ *P. pastoris* SMD1168$_{His4::scaffold}$. The expression medium BMMY (1%

yeast extract, 2% peptone, 100 mM potassium phosphate buffer, 1.34% amino acid-free yeast

nitrogen, and 1% (v/v) methanol, pH 6.0) was employed for protein expression and enzyme-scaffold

assembly. Expression was conducted at 30°C, with the medium augmented with 0.5% methanol at

24-hour intervals over a period of 96 hours.

For in vitro protein expression, *E. coli* C41 (DE3) cells were transformed with pColdII-based

plasmids, while *E. coli* BL21 (DE3) and *E. coli* Rosetta (DE3) cells were used for pET28a constructs.

Transformants were grown in LB media supplemented with appropriate antibiotics (100 μg/mL

ampicillin for pColdII, 500 μg/mL kanamycin for pET28a) at 37°C until OD_{600} reached 0.6-0.7.

IPTG (0.5 mM or 1.0 mM final concentration for MHETases, 1.0 mM for others) induced expression

overnight (at 16°C or 37°C for MHETases, 16°C for others). Cells were harvested by centrifugation

and stored at -80°C.

Cells were resuspended in lysis buffer (50 mM sodium phosphate, 300 mM NaCl, pH 8.0),

disrupted by sonication, and the supernatant was collected by centrifugation. HisTrap HP column

purification employed an ÄKTA pure system (Cytiva, China). Bound protein was washed with 85%

binding buffer (20 mM sodium phosphate, 30 mM imidazole, 500 mM NaCl, pH 7.4) with 15%

elution buffer (20 mM sodium phosphate, 500 mM imidazole, 500 mM NaCl, pH 7.4) and eluted

with a linear gradient of 15-100% elution buffer. Eluates were concentrated (Amicon Ultra, Merck

Millipore, China), buffer-exchanged to 50 mM sodium phosphate (SP buffer, pH 7.0), and assessed

for purity/concentration by NanoDrop™ One/One^C (Thermo Fisher, U.S.A.). Proteins were stored

in storage buffer (50% glycerol in SP buffer, pH 7.0) at -80°C.

Binding assay of scaffold protein to PET

Following previously established protocols [25], PET powder (crystalline, Xing-xiang new materials,

China) or PET film (amorphous, Goodfellow, UK) were washed with 10% SDS, water, and SP

buffer (pH 7.0). CipA-CipC (Scaf.1) or CipA-CBM-CipC (Scaf.2) were incubated at 2.5, 5, and 7.5

μM with 100 mg PET powder in 200 μL SP buffer (pH 7.0) overnight at 4°C. Samples were

centrifuged (12000 g, 1 min), washed twice with SP buffer (pH 7.0), and residual protein in solution

was quantified using a BCA Protein Quantification Kit (Yeason, China). Binding protein

concentration was calculated as follows (C, concentration; before, before incubation with PET; after,

after incubation with PET):

$$Binding\ protein\ concentration = C_{(before)} - C_{(after)}$$

399 Binding assay of enzymes to scaffolds

Enzyme-scaffold protein interactions were analyzed by MicroCal PEAQ-ITC Automated (Malvern

Panalytical, Netherland). Enzymes were placed in the reaction cell, and scaffold protein titrations

were performed at 25°C with 18 injections of 2 μL substrate (details in Fig. legends). Dilution heats

were corrected, and data were analyzed using the MicroCal PEAQ-ITC Analysis Software (one set

of sites model).

For living cell system, flow cytometry was used to analyze enzyme-scaffold protein

interactions. After a 96-hour induction at 30°C, the yeast cells were collected by centrifugation at

4000 g for 10 min at 4°C, then washed and diluted with DPBS. Subsequently, $1×10^7$ cells and 0.1

μL of each antibody (V5 tag antibody, Invitrogen 451098; His tag antibody, Cell Signaling

Technology 14930; or Myc tag antibody, R&D Systems IC3696P) were incubated (for 45 min)

washed, and detected through flow cytometry.

411 Characterization of crystallinity of PET substrates

Thermal crystallinity of PET substates was determined by differential scanning calorimetry (DSC

8000, PerkinElmer). PET substrates (75 μm powder; low crystallinity PET film, film-L; high

crystallinity PET film, film-H; Nongfu Spring water bottle, NFbottle) were heated from 30°C to

300°C at a heating rate of 30°C/min, kept at 300°C for 1 min, and then cooled to 0°C at 5 min with

same rate of 30°C/min. The theoretical heat of melting value (ΔHm°) of 100% crystallized PET was

140.1 J/g. Percentage crystallinity was calculated with the heat of melting (ΔHm) and cold

crystallization (ΔHc) values, as the following equation:

$$Crystallinity\ (\%) = \frac{\Delta Hm - \Delta Hc}{\Delta Hm°} \times 100\%$$

420 Synthesis and characterization of MOF-immobilized enzyme complexes

For synthesis of Complex-D@ZIF-8 and Enz.3@ZIF-8, 1.75 mL of 2-methylimidazole (2-MI,

790 mM), a certain amount of proteins (0.25 nmol individual enzyme of FAST, MHETase and ICCG

with/without scaffold to form Complex-D/Enz.3), and 0.25 mL $Zn(NO_3)_2·6H_2O$ (97.5 mM) was

stirred at 500 g for 5 min. To synthesize ZIF-8, the same volume of 2-MI and $Zn(NO_3)_2·6H_2O$ was

stirred. Subsequently, the mixture was left undisturbed for 3 h at 4°C. Finally, the prepared

Complex-D@ZIF-8, Enz.3@ZIF-8 and ZIF-8 were collected by centrifugation at 3500 g for 10

minutes and dispersed into 0.5 mL SP buffer.

For characterizations, confocal microscopy images were recorded by Nikon confocal laser

scanning microscope with his-tag antibody (14930, Cell signaling technology); XRD (Bruker D8

Advance) and SEM (ZEISS GeminiSEM 300) were used to measure the immobilized samples.

Characterization of living cell PET biodegradation systems

Confocal microscopy images and flow cytometry assays were recorded by Nikon confocal laser

scanning microscope His Tag Alexa Fluor® 488-conjugated Antibody (IC0501G, R&D Systems),

V5 Tag Monoclonal Antibody (451098, Invitrogen), Human c-Myc PE-conjugated Antibody

(IC3696P, R&D Systems) to detect MHETase and/or FAST with his tag, FAST with myc tag,

scaffold with V5 tag, separately.

For surface displaying assays mediated by different anchors, displaying efficiency was

calculated with median florescence intensity (MFI) and copy number by flow cytometry and qPCR,

as the following equation:

440
$$Relative\ display\ efficiency = \frac{MFI_{V5\ positive}}{Copy\ number\ of\ the\ scaffold}$$

Degradation assay of PET plastics

Standard reactions contained 100 mg PET (powder, low or high crystallinity PET films), 0.2 mM

enzyme, 500 µL reaction buffer (50 mM sodium phosphate, 0.5 mM $CaCl_2$, 10% DMSO, pH 7.0).

For complex assembly, enzymes (0.2 mM) were pre-mixed with scaffold (1 mM) for 40 min at room

temperature. Unless otherwise stated, degradations proceeded for 96 h at 30°C.

To optimize the enzyme:scaffold ratio within SPEED, ratios ranged from 0.2:1 to 1:1 (constant

scaffold protein 1 mM). Effects of pH (5.0-9.0, 30°C), temperature (30-70°C, pH 7.0), and PET

substrate type (PET powder, low and high crystallinity PET films, commercial bottle) were also

analyzed.

For PET upcycling reaction, PET degrading enzymes (FAST, MHETase, ICCG) were

combined with Scaf.4 (1 mM, CipA-CBM-SH3$_D$-ScaB) in an optimized ratio. Similarly, the

upcycling enzymes (FucO, AldA, LrNox), which facilitate the synthesis of valuable products from

PET, were mixed with Scaf.4 (0.5 mM) in a molar ratio of 1:1. The mixed proteins were incubated

at room temperature for 40 minutes to achieve complex assembly. Following assembly, the

upcycling complex was incorporated into the PET degradation product, which was reacted for four

days under optimal conditions. Alternatively, the PET degradation complex was mixed with the

upcycling complex and 100 mg PET Film-L for further conversion. The reactions were conducted

in 500 µL systems for 2 to 4 days in SP buffer (with 1 mM additional NADH).

For living cell PET degradation, a mixture of 1×10^9 induced *Pichia pastoris* SMD1168 was

collected, then placed in 400 µL of sterile glycine-NaOH buffer (pH 7.0) containing 100 mg PET

powder to facilitate the degradation reaction. The degradation reaction was conducted at 30°C for

48 h.

All reactions were terminated at 95°C for 10 min, supernatants were 0.22 µm filtered, and

released products were quantified by HPLC (High Performance Liquid Chromatography).

MHETase degradation assay

To assess the intermediates degradation ability of MHETase, 0.5 mM SH3$_L$-optiMHETase was combined with 5 mM MHET and BHET in 500 μL reaction buffer (50 mM sodium phosphate, 0.5 mM CaCl2, 10% DMSO, pH 7.0). The reactions were constructed at varying temperatures (30°C, 40°C, 50°C, 60°C, 70°C) for 96 h and terminated by heating to 95°C for 10 min. Supernatants were 0.22 μm filtered, and released products were quantified by HPLC.

HPLC analysis

TPA, GA, MHET, and BHET standards were obtained from Aladdin (China). Samples were analyzed using an Agilent 1260 LC system with G1315A diode array detector (DAD) and ZORBAX StableBond C18 column (Agilent), refractive index detector (RID) and Xtimate® Sugar-H column (Welch Materials). For TPA, MHET and BHET detection, the mobile phase consisted of 0.1% formic acid (A) and acetonitrile (B); separation used a flow rate of 1 mL/min (80% A / 20% B, 10 min); detection was performed at 240 nm with C18 column. For GA detection, the mobile phase consisted of 5 mM H$_2$SO$_4$ (Solvent as ddH$_2$O); separation used a flow rate of 1 mL/min (15 min); detection was performed with Sugar-H column. Analyte concentrations were determined using calibration curves (10-500 mM). Samples were adaptively diluted with ultrapure water prior to analysis.

Scanning electron microscopy (SEM)

Low-crystallinity PET film samples (6 mm diameter) were analyzed by SEM (HuaSuan Technolygy, China) after degradation (40°C, 96 h, pH 7.0). Samples were washed (10% SDS, water, ethanol), dried, gold-coated, and imaged.

Scaffold-enzyme Structural prediction

In this study, the three enzymes structures were obtained from the Protein Data Bank (https://www.rcsb.org/. FAST-PETase: 6IJ6, MHETase: 6QZ4, ICCG: 8JMP, CelK: 3P6B, SH3$_L$: 1PRM, ScaA: 5N5P). The structure of the scaffold was predicted by AlphaFold2. After running the standard AlphaFold2 MSA generation pipeline against UniRef, MGnify, PDB, and BFD, the sequence with highest pLDDT greater than 0.9 is chosen as the final model prediction. The prediction of enzyme-scaffold complex was visualized by BioRender (https://www.biorender.com/).

Statistical analysis

One-way analysis of variance (ANOVA) followed by normality test was employed to evaluate the significance of differences among different treatments. Statistical analysis were conducted using GraphPad Prism 9.0 software. ns: not significant, *$p < 0.1$, **$p < 0.01$, ***$p < 0.001$, ****$p < 0.0001$.

Declaration of Competing Interest

The authors have two patent applications related to this work.

Data Availability

All data are available in the main text or supplementary information. Additional information related to this study is available from the corresponding author upon reasonable request.

Acknowledgements

This study was supported by funding from the Shenzhen Bay Laboratory Startup Fund, the Shenzhen Outstanding Talents Training Fund, Shenzhen Research Funding for Postdocs and the Key Research and Development Program of Shaanxi Province, China (Grant Numbers: 2022NY-055 and 2019NY-187). We acknowledge the intellectual and experimental contributions of all authors for this study and its manuscript preparation. We are particularly grateful for the insights gained from discussions with lab members in the Zhuobin Liang and Yanbin Lin labs. We would like to acknowledge Ziwei Luo for her technical assistance in the illustration of Figure. 1. We also extend our gratitude to the Haizhen Long and Jianchuan Wang lab at Shenzhen Bay Laboratory for their assistance in experiment setup. Finally, we thank the Research Core Facility of Shenzhen Bay Laboratory for their technical support, especially for the use of ÄKTA and HPLC instruments.

References

1. Lau, W. W. Y. *et al.* Evaluating scenarios toward zero plastic pollution. *Science (1979)* **369**, 1455–1461 (2020).

2. Xu, C. *et al.* Are we underestimating the sources of microplastic pollution in terrestrial environment? *J Hazard Mater* **400**, 123228 (2020).

3. Blackburn, K. & Green, D. The potential effects of microplastics on human health: What is known and what is unknown. *Ambio* **51**, 518–530 (2022).

4. Gao, R., Pan, H., Kai, L., Han, K. & Lian, J. Microbial degradation and valorization of poly(ethylene terephthalate) (PET) monomers. *World J Microbiol Biotechnol* **38**, 89 (2022).

5. Ragaert, K., Delva, L. & Van Geem, K. Mechanical and chemical recycling of solid plastic waste. *Waste Management* **69**, 24–58 (2017).

6. Suzuki, G. *et al.* Global discharge of microplastics from mechanical recycling of plastic waste. *Environmental Pollution* **348**, 123855 (2024).

7. Zeng, W. *et al.* A general strategy for recycling polyester wastes into carboxylic acids and hydrocarbons. *Nat Commun* **15**, 160 (2024).

8. Sullivan, K. P. *et al.* Mixed plastics waste valorization through tandem chemical oxidation and biological funneling. *Science (1979)* **378**, 207–211 (2022).

9. Kushwaha, A., Goswami, L., Singhvi, M. & Kim, B. S. Biodegradation of poly(ethylene terephthalate): Mechanistic insights, advances, and future innovative strategies. *Chemical Engineering Journal* **457**, 141230 (2023).

10. Amalia, L., Chang, C.-Y., Wang, S. S.-S., Yeh, Y.-C. & Tsai, S.-L. Recent advances in the biological depolymerization and upcycling of polyethylene terephthalate. *Curr Opin Biotechnol* **85**, 103053 (2024).

11. Müller, R., Schrader, H., Profe, J., Dresler, K. & Deckwer, W. Enzymatic Degradation of Poly(ethylene terephthalate): Rapid Hydrolyse using a Hydrolase from *T. fusca*. *Macromol Rapid Commun* **26**, 1400–1405 (2005).

12. Sulaiman, S. *et al.* Isolation of a Novel Cutinase Homolog with Polyethylene Terephthalate-Degrading Activity from Leaf-Branch Compost by Using a Metagenomic Approach. *Appl Environ Microbiol* **78**, 1556–1562 (2012).

13. Yoshida, S. *et al.* A bacterium that degrades and assimilates poly(ethylene terephthalate). *Science (1979)* **351**, 1196–1199 (2016).

14. Tournier, V. *et al.* An engineered PET depolymerase to break down and recycle plastic bottles. *Nature* **580**, 216–219 (2020).

15. Lu, H. *et al.* Machine learning-aided engineering of hydrolases for PET depolymerization. *Nature* **604**, 662–667 (2022).

16. Bååth, J. A., Borch, K., Jensen, K., Brask, J. & Westh, P. Comparative Biochemistry of Four Polyester (PET) Hydrolases**. *ChemBioChem* **22**, 1627–1637 (2021).

17. Brizendine, R. K. *et al.* Particle Size Reduction of Poly(ethylene terephthalate) Increases the Rate of Enzymatic Depolymerization But Does Not Increase the Overall Conversion Extent. *ACS Sustain Chem Eng* **10**, 9131–9140 (2022).

18. Chow, J., Perez-Garcia, P., Dierkes, R. & Streit, W. R. Microbial enzymes will offer limited solutions to the global plastic pollution crisis. *Microb Biotechnol* **16**, 195–217 (2023).

19. Carniel, A., Valoni, É., Nicomedes, J., Gomes, A. da C. & Castro, A. M. de. Lipase from Candida antarctica (CALB) and cutinase from Humicola insolens act synergistically for PET

hydrolysis to terephthalic acid. *Process Biochemistry* **59**, 84–90 (2017).

20. de Castro, A. M., Carniel, A., Nicomedes Junior, J., da Conceição Gomes, A. & Valoni, É.
Screening of commercial enzymes for poly(ethylene terephthalate) (PET) hydrolysis and
synergy studies on different substrate sources. *J Ind Microbiol Biotechnol* **44**, 835–844
(2017).

21. Knott, B. C. *et al.* Characterization and engineering of a two-enzyme system for plastics
depolymerization. *Proceedings of the National Academy of Sciences* **117**, 25476–25485
(2020).

22. Barth, M. *et al.* A dual enzyme system composed of a polyester hydrolase and a
carboxylesterase enhances the biocatalytic degradation of polyethylene terephthalate films.
Biotechnol J **11**, 1082–1087 (2016).

23. Mrigwani, A., Thakur, B. & Guptasarma, P. Conversion of polyethylene terephthalate into
pure terephthalic acid through synergy between a solid-degrading cutinase and a reaction
intermediate-hydrolysing carboxylesterase. *Green Chemistry* **24**, 6707–6719 (2022).

24. von Haugwitz, G. *et al.* Structural Insights into (Tere)phthalate-Ester Hydrolysis by a
Carboxylesterase and Its Role in Promoting PET Depolymerization. *ACS Catal* **12**, 15259–
15270 (2022).

25. Hwang, D.-H. *et al.* Enhanced biodegradation of waste poly(ethylene terephthalate) using a
reinforced plastic degrading enzyme complex. *Science of The Total Environment* **842**,
156890 (2022).

26. Oliveira, C., Carvalho, V., Domingues, L. & Gama, F. M. Recombinant CBM-fusion
technology — Applications overview. *Biotechnol Adv* **33**, 358–369 (2015).

27. Makryniotis, K., Nikolaivits, E., Gkountela, C., Vouyiouka, S. & Topakas, E. Discovery of
a polyesterase from Deinococcus maricopensis and comparison to the benchmark
LCCICCG suggests high potential for semi-crystalline post-consumer PET degradation. *J
Hazard Mater* **455**, 131574 (2023).

28. Duarte, M. *et al.* Structure-function studies can improve binding affinity of cohesin-dockerin
interactions for multi-protein assemblies. *Int J Biol Macromol* **224**, 55–67 (2023).

29. Arnal, G. *et al.* Assessment of Four Engineered PET Degrading Enzymes Considering
Large-Scale Industrial Applications. *ACS Catal* **13**, 13156–13166 (2023).

30. Zhang, J. *et al.* Computational design of highly efficient thermostable MHET hydrolases
and dual enzyme system for PET recycling. *Commun Biol* **6**, 1135 (2023).

31. Wang, X., Lan, P. C. & Ma, S. Metal–Organic Frameworks for Enzyme Immobilization:
Beyond Host Matrix Materials. *ACS Cent Sci* **6**, 1497–1506 (2020).

32. Kim, H. T. *et al.* Biological Valorization of Poly(ethylene terephthalate) Monomers for
Upcycling Waste PET. *ACS Sustain Chem Eng* **7**, 19396–19406 (2019).

33. Weiland, F., Kohlstedt, M. & Wittmann, C. Biobased de novo synthesis, upcycling, and
recycling — the heartbeat toward a green and sustainable polyethylene terephthalate
industry. *Curr Opin Biotechnol* **86**, 103079 (2024).

34. Wongsatit, T., Srimora, T., Kiattisewee, C. & Uttamapinant, C. Enzymes, auxiliaries, and
cells for the recycling and upcycling of polyethylene terephthalate. *Curr Opin Syst Biol* **38**,
100515 (2024).

35. Jin, L. *et al.* Gallic acid improves cardiac dysfunction and fibrosis in pressure overload-
induced heart failure. *Sci Rep* **8**, 9302 (2018).

36.   Ojo, O. A., Rotimi, D. E., Ojo, A. B., Ogunlakin, A. D. & Ajiboye, B. O. Gallic acid abates
cadmium chloride toxicity via alteration of neurotransmitters and modulation of
inflammatory markers in Wistar rats. *Sci Rep* **13**, 1577 (2023).

37.   Mahboob, T. *et al.* PLGA nanoparticles loaded with Gallic acid- a constituent of Leea indica
against Acanthamoeba triangularis. *Sci Rep* **10**, 8954 (2020).

38.   Montella, C. *et al.* Crystal Structure of an Iron-Dependent Group III Dehydrogenase That
Interconverts l -Lactaldehyde and l -1,2-Propanediol in
Escherichia coli. *J Bacteriol* **187**, 4957–4966 (2005).

39.   Pandit, A. V., Harrison, E. & Mahadevan, R. Engineering Escherichia coli for the utilization
of ethylene glycol. *Microb Cell Fact* **20**, 22 (2021).

40.   Gao, H. *et al.* NADH oxidase from Lactobacillus reuteri: A versatile enzyme for oxidized
cofactor regeneration. *Int J Biol Macromol* **123**, 629–636 (2019).

41.   Heyde, S. A. H., Arnling Bååth, J., Westh, P., Nørholm, M. H. H. & Jensen, K. Surface
display as a functional screening platform for detecting enzymes active on PET. *Microb Cell
Fact* **20**, 93 (2021).

42.   Chen, Z. *et al.* Biodegradation of highly crystallized poly(ethylene terephthalate) through
cell surface codisplay of bacterial PETase and hydrophobin. *Nat Commun* **13**, 7138 (2022).

43.   Chen, Z. *et al.* Enhanced in situ biodegradation of microplastics in sewage sludge using
hyperthermophilic composting technology. *J Hazard Mater* **384**, 121271 (2020).

44.   Sagong, H.-Y. *et al.* Decomposition of the PET Film by MHETase Using Exo-PETase
Function. *ACS Catal* **10**, 4805–4812 (2020).

45.   Oda, K. & Wlodawer, A. Development of Enzyme-Based Approaches for Recycling PET on
an Industrial Scale. *Biochemistry* (2024) doi:10.1021/acs.biochem.3c00554.

46.   Cui, Y. *et al.* Computational Redesign of a PETase for Plastic Biodegradation under Ambient
Condition by the GRAPE Strategy. *ACS Catal* **11**, 1340–1350 (2021).

47.   Zhong-Johnson, E. Z. L., Voigt, C. A. & Sinskey, A. J. An absorbance method for analysis
of enzymatic degradation kinetics of poly(ethylene terephthalate) films. *Sci Rep* **11**, 928
(2021).

48.   Bell, E. L. *et al.* Directed evolution of an efficient and thermostable PET depolymerase. *Nat
Catal* **5**, 673–681 (2022).

49.   Liu, Y. *et al.* Enhancement of the degradation capacity of IsPETase for PET plastic
degradation by protein engineering. *Science of The Total Environment* **834**, 154947 (2022).

50.   Liu, Z., Zhang, Y. & Wu, J. Enhancement of PET biodegradation by anchor peptide-cutinase
fusion protein. *Enzyme Microb Technol* **156**, 110004 (2022).

51.   Hayes, H. C. & Luk, L. Y. P. Investigating the effects of cyclic topology on the performance
of a plastic degrading enzyme for polyethylene terephthalate degradation. *Sci Rep* **13**, 1267
(2023).

52.   Cui, Y. *et al.* Computational redesign of a hydrolase for nearly complete PET
depolymerization at industrially relevant high-solids loading. *Nat Commun* **15**, 1417 (2024).

Author information

Authors and Affiliations

College of Life Sciences, Northwest A&F University, Yangling, Shaanxi, China

Yujia Zhang, Chongsen Li, Yanbing Lin

Institute of Molecular Physiology, Shenzhen Bay Laboratory, Shenzhen, China

Yujia Zhang, Chongsen Li, Ehsan Hashimi, Hui Gao, Zhuobin Liang

School of Science, Harbin Institute of Technology (Shenzhen), Shenzhen, China

Enting Xu, Xuemei Yang

Contributions

Yujia Zhang: Methodology, Investigation, Data Curation, Formal Analysis, Visualization, Writing – Original Draft. **Chongsen Li:** Investigation, Data Curation, Validation. **Ehsan Hashimi**: Investigation, Data Curation, Validation. **Enting Xu:** Investigation, Validation. **Xuemei Yang:** Methodology, Supervision, **Yanbing Lin:** Resources, Supervision. **Hui Gao:** Conceptualization, Methodology, Investigation, Data Curation, Formal Analysis, Writing – Original Draft, Funding acquisition. **Zhuobin Liang:** Conceptualization, Methodology, Supervision, Writing – Original Draft, Project administration, Funding acquisition.

Corresponding authors

Correspondence to Zhuobin Liang or Hui Gao.

Extended Data

Source Data

Supplementary information

Supplementary Tables 1-3

Supplementary Figure 1-11

Supplementary File 1

Supplementary Methods

Supplementary Table 1. Key degradation parameters and efficiency of major PET hydrolases

PET hydrolase	Substrate*	Reaction condition	Enzyme usage (nmol)	Total products (mM)	Degradation efficiency (mol total products /mmol enzyme)	Reference
IsPETase	Film-L	30°C, 18 h, pH 7.0	0.015	0.30	6.00	13
TfH			0.015	0.00079	0.016	
LCC			0.015	0.0063	0.13	
FsC			0.015	0.00075	0.015	
LCC	Post-consumer colored-flake PET waste-H	72°C, 20 h, pH 8.0	690.00	552.09	64.01	14
ICCG (LCC$^{F243I/D238C/S283C/Y127G}$)		72°C, 15 h, pH 8.0	690.00	854.17	99.03	
WCCG (LCC$^{F243W/D238C/S283C/Y127G}$)		72°C, 20 h, pH 8.0	690.00	885.42	102.66	
FAST-PETase (*Is*PETase$^{S121E/D186H/R224Q/N233K/R280A}$)	Film-H	50°C, 96 h, pH 8.0	0.12	33.80	169.00	15
			0.12	29.50	147.50	
ICCM (LCC$^{F243I/D238C/S283C/N246M}$)		40°C, 96 h, pH 8.0	0.12	14.75	73.75	
DuraPETase (*Is*PETase$^{S214H/I168R/W159H/S188Q/R280A/A180I/G165A/Q119Y/L117F/T140D}$)	Film-H	50°C, 72 h, pH 9.0	0.17	2.63	7.56	46
		37°C, 72 h, pH 9.0	0.17	1.76	5.06	
LCC		pH 9.0	0.17	1.04	3.00	
TS-PETase (*Is*PETase$^{S121E/D186H/R280A}$)	Film-L	30°C, 6 days, pH 9.0	0.40	0.05	0.13	47
fvThermobifida fusca cutinase$^{H184S/Q92G/F209I/I213K}$	Bottle-H	60°C, 96 h, pH 8.0	1461.18	N/A (3542.00 nmol)	2.42	42
LCC$^{H184S/Q92G/F209I/I213K}$			1742.22	N/A (1354.00 nmol)	0.78	
BhrPETase$^{H184S/Q92G/F209I/I213K}$			1724.14	N/A (3802.00 nmol)	2.21	
HotPETase	Powder-H	60°C, 5 h, pH 9.2	0.21	6.07	146.52	48
DuraPETase-4M (DuraPETase$^{N233C/S282C/H214S/S245R}$)	Powder-H	60°C, 96 h, pH 9.0	0.01	15.80	45.48	49
DuraPETase			0.01	5.70	16.39	
DSI- *Tf*cutinase$^{D204C/E253C}$ (Tfuc2 fusing with the anchor peptide Dermaseptin SI)	Particle-L	70°C, 96 h, pH 8.0	7.00	300.00	42.86	50
IsPETase-Spy (Cyclic monomer)	Powder-H	30°C, 24 h, pH 7.5	0.10	0.40	4.03	51
IsPETase-Dimer (Cyclic dimer)			0.05	0.46	9.16	
IsPETase-Cat (Catenane)			0.05	0.50	9.95	
***Is*PETase**			0.10	0.40	3.95	
TurboPETase	Film-L	65°C, 12 h, pH 8.0	0.16	130.00	401.04	52
BhrPETase			0.16	6.00	18.54	
LCC^{ICCG}			0.16	34.00	104.41	
FAST-PETase			0.15	2.00	6.89	

669 Note: **a**. * Substrates can vary in different studies. To facilitate their comparison, we define substrates as follows L:

670 low crystallinity (< 20%), H: high crystallinity (> 20%). **b**. Total products include TPA, MHET, and BHET. 3.

671 Extended details associated of this table is provided in **Supplementary File 1**. **c**. N/A: information not available

672 from the corresponding publication.

Supplementary Table 2. Information of genes and primers

Type	Gene	Sequence
Enzyme	FAST-PETase-CelK	catatgcagacaaatccctatgcccgtgggccaaatcccactgcggcgagtttagaagccagtgccggtccgtttaccgtccgttcttttactgtaagccgcccgtccggata cggggcggggacggttttattatcccacgaatgccggaggcaccgtgggtgctattgcaattgttccaggctatacagcgcgccaatcatctatcaaatggtggggaccgcg tctggcttcgcacggattcgtagttattacgattgacacaaacagcacgttagaccagcccgaaagtcgcagcagtcaacaaatggcggcgttacgtcaggtcgcaagctta aacgggacatcaagcagtccatctatggaaaagtcgatacagcgcgcatgggtgtcatgggctggtccatgggaggcggggggtctttgatttctgctgctaataatccta gtttaaaagccgccgccccgcaggcaccgttggcattcgtccaccaactttttcatcggtaacggtccccactcttatttttgcgtgtgagaacgactcgatcgcaccggttaatt cttctgctctgccgatttacgactcaatgtcgcaaaatgcaaagcaattccttgaaattaaaggtggctcccattcttgtgccaactcaggtaacagtaatcaagcccttattgga aagaaaggtgtcgcatggatgaaacgttttatggataatgacacccgctattctaccttcgcctgcgaaaacccgaacagcaccgctgtatcagatttccgcactgccaactg tagcttaataacaccgccaggaggagtagacccagaagaaccggaggttatttatggtgactgcaatggcgacggaaaagttaattcaactgacgctgtggcattgaagag atatatcttgagatcaggtataagcatcaacactgataatgctgatgtaaatgctgatggcagagttaactctacagacttggcaatattgaagagatatattcttaaagagatag atgtattgccacataaaactcgag
Enzyme	MHETase-CelF	catatgcagaccacagtaacgacgatgttgcttgcaagcgtagccttagccgcctgtgcgggtggtggcagcaccccattaccgttaccgcaacaacagccgccccagca agaaccaccccaccgcctgtcccgttagcgtcacgcgcagcatgtgaggcactgaaagacggcaatggcgacatggtatggccgaatgccgctaccgtggtcgaagtc gctgcctggcgcgacgcggcaccagctacagcaagtgctgctgcctcgaacactgcgaagtgtcgggcgcgatcgcgaaacgcacgggcattgatggctacccg tacgaaattaaatttcgtcttcgtatgccagccgaatggaatggacgtttcttcatcgatgagggccggctcggggacaaatggttcattgtcagcgactacaggttcgattggggggt ggtcaaattgcatctgccttgagccgcaacttcgccaccatcgctaccgacgagaggcatgataacgcggttaatgacaacccggatgcattgggaacagttgcctttggttt agatccccaggctcgtctggacatgggctacaatagttacgaccaggtcacgcaagctggcaaggctgcggttgctcgtttctatggacgtgcggcagacaaatcgtatttc attggatgcagtgagggaggacgcgagggcatgatgctgagccagcgcttccatcacactacgatggcattgtcgccggtgcccctgggtatcagctgcaaaagccg ggatttccggtgcctggacgacgcaatccttggcaccagcccagtcgagttgagtttagatgccgcaaggggtgcctctgattaataagtccttctcggatgctgatttgcaccttctgt cacaagctatcttaggaacatgtgacgctctcggatggattggcagatggaattgttgacaactaccgcgcctgtcaggcagcgttcgatcccgctacagctgcgaatccggc taacggtcaggccttgcaatgtgtcggggcaaagacagcagactgcctgtctcctgtgcaggtgaccgctatcaaacgcgcgatggcagggccagtgaattctgcaggca ccccctgtataatcgttgggcgtgggacgctggtatgagtgagcttgtcagggacaacgtataatcagggatggcgcagctggtggttggggtctttcaacagctctgcgaa taacgcgcaaaagtcagcggcttcgcggctcgttcctggctggtggatatcgcaactccaccagagcccatgcctatgacccaggttgctgcacgcatgatgaaattcga cttcgatattgatccgctgaaaatttgggcgacatctgggcaatttacacaaaagctctatggactggcacggcgctacttcgaccgatttagcgtctttcgtgaccgtggagg caagatgatcttgtatcacggtatgagtgatgcggccttcagtgcattagatacggcggattattacgagcgtctcgggagcggctatgcctggggctgccggtttcgctcgcc ttttttttagtaccagggatgaaccattgctcaggcgggcctggaacggaccgttttgacatgttgactccttttagtggcctgggttgagcgtggcgaggcgcctgatcaaatttc cgcatggtccgggacccaggtattcggtgttgcagcaccgcacccgcccgtgttgtcatatccacaaatcgcgcgttataaaaagggtccgggagacattaatacggaagc gaattttgcttgcgcagccccccccttcccagatcaaggtccagaaaaattattgggtgatgtaaacggtgacgaaactgtagacgctattgaccttgctatacttaaaaaatat cttttaaacagcagtactacaataaaatactgcaaatgcagatatgaatagtgataatgctattgacgctattgactatgctctttaaagaaagcacttctttctatccaactcgag
Enzyme	optiMHETase-CelF	ggtggtggtagtacaccgctgccgctgcctcagcagcagcagcctccgcagcaagaaccgcctccgcctccggttccgctggcaagccgtgcagcatgtgaagcactgaaa gatggtaatggtgatatggtttggccgaatgcagcaaccgttgttgaagttgcagcatggcgtgatgcagcaccggcaaccgcaagcgcagcagcactgccgggaacattg tgaagttagcggtgcaattgccaaacgtaccggtattgatggttatccgtatgaaatcaaatttcgtctgcgtatgcctgaatggaatggtcgtttctttatcgatgagggtcggta gcggcaccaatggtagcctgagcgcagccaccggtagcattggtggtggtcagattgcaagcgcactgagccgtaattttgcaaccattgcaaccgatggtggtcatgata atgccgttaatgataatccggatgcactgggcaccgttgcatttggtctggatccgcaggcacgtctggatatgggttataatagctatgatcaggttacccaggcaggtaaa gcagcagttgcacgttttatggtcgtgcagcagataaaagctattttatccggttgtagcgaaggtggtcgtgaaggtatgatgctgagccagcgttttccgagccattatgatg gtattgttgcgggtgcaccgggttatcagctgccgaaagcaggtatttgtggtgtgagcgaaggtggtcgtgaaggtatgatgctgagccagcgttttccgagccattatgatg ccgctgattaacaaaagctttagtgatgccgatctgcatctgctgagtcaggcaattctgggcacctgtgatgccctggatggtctggcagatggcattgttgataactatcgtg catgtcaggcagcatttgatccggcaacagcagcaaatccggcaaatggtcaggccctgcagtgtgttggtcaaaaaccgcagattgtctgagtccggttcaggtgaccg caattaaacgcgcaatggcaggtccggttaatagcgcaggcacaccgctgtataatcgttgggcatgggatgcaggtatgagcggtctgagcggtacaacctataatcaag gttggcgtagttggtggctgggtagctttaatagcagcgcaaataatgcccagcgtgttagcggttttagcgcacgtagctggctggctggttgattttgcgaccctccggaaccg atgccgatgacacaggttgcagcacgcatgatgaaattcgattttgatattgacccgctgaaaatttgggcaaccagcggtcagtttacccagagtagcatggattggcatgg tgcaaccagcaccgatctggcagcctttcgtgatcgtggtggtaaaatgattctgtatcatggtatgtcagatgcagcctttagtgcactggatacagcagattattatgaacgt ctgggtgcagcaatgcctggtgcagcaggttttgcacgtctgtttctggttccgggtatgaatcattgtagcggtggtccgggtacagatcgtttgatatgctgacccctctgg ttgcatgggttgaacgtggtgaagcaccggatcagattagcgcatggtactccgggttatttttggtgttgccgcacgtacccgtccgctgtgtccgatccgcagatc gcacgttataaaggtagcggtgatattaacaccgaagccaattttgcatgtgcagcacctccgttcccagatcaaggtccagaaaaattattgggtgatgtaaacggtgacga aactgtagacgctattgaccttgctatacttaaaaaatatcttttaaacagcagtactacaataaaatactgcaaatgcagatatgaatagtgataatgctattgacgctattgactat gctctttaaagaaagcacttctttctatccaa
Enzyme	SH3L-optiMHETase	cctcctcctgctctgccaccaaaaaggagaagacatcatcatcatcatcacagcagcggcctggtgccgcgcggcagcggtggtggtagtacaccgctgccgctgcctca gcagcagcctccgcagcaagaaccgcctccgcctccggttccgctggcaagccgtgcagcatgtgaagcactgaaagatggtaatggtgatatggtttggccgaatgca gcaaccgttgttgaagttgcagcatggcgtgatgcagcaccggcaaccgcaagcgcagcagcactgccgggaacattgtgaagttagcggtgcaattgccaaacgtaccg gtattgatggttatccgtatgaaatcaaatttcgtctgcgtatgcctgcagaatggaatggtcgtttctttatggaaggtggtagcggcaccaatggtagcctgagcgcagcca ccggtagcattggtggtggtcagattgcaagcgcactgagccgtaattttgcaaccattgcaaccgatggtggtcatgataatgccgttaatgataatccggatgcactgggc accgttgcatttggtctggatccgcaggcacgtctggatatgggttataatagctatgatcaggttacccaggcaggtaaagcagcagttgcacgttttatggtcgtgcagca gataaaagctattttatcggttgtagcgaaggtggtcgtgaaggtatgatgctgagccagcgttttccgagccattatgatggtattgttgcgggtgcaccgggttatcagctgc cgaaagcaggtattagtggtgcatggaccacacagagcctggcaccggcagccgttggcctggatgcacagggtgttccgctgattaacaaaagctttagtgatgccgatc tgcatctgctgagtcaggcaattctgggcacctgtgatgccctggatggtctggcagatggcattgttgataactatcgtgcatgtcaggcagcatttgatccggcaacagca gcaaatccggcaaatggtcaggccctgcagtgtgttggtcaaaaaccgcagattgtctgagtccggttcaggtgaccgcaattaaacgcgcaatggcaggtccggttaat agccaggcacaccgctgtataatcgttgggcatgggatgcaggtatgagcggtctgagcggtacaacctataatcaaggttggcgtagttggtggctgggtagctttaata gcagcgcaaataatgcccagcgtgttagcggttttagcgcacgtagctggctggcttggttgattttgcgaccctccggaaccgatgccgatgacacaggttgcagcacgcatga tgaaattcgattttgatattgacccgctgaaaatttgggcaaccagcggtcagtttacccagagtagcatggattggcatggtgcaaccagcaccgatctggcagcctttcgtg atcgtggtggtaaaatgattctgtatcatggtatgtcagatgcagcctttagtgcactggatacagcagattattatgaacgtctgggtgcagcaatgcctggtgcagcaggtttt gcacgtctgtttctggttccgggtatgaatcattgtagcggtggtccgggtacagatcgtttgatatgctgacccctctggttgcatgggttgaacgtggtgaagcaccggatc agattagcgcatggtcaggtactccgggttattttggtgttgccgcacgtacccgtccgctgtgtccgatccgcagatcgcacgttataaaggtagcggtgatattaacaccg aagccaattttgcatgtgcagcacctccg
Enzyme	OptiMHETase-SH3L	ggtggtggtagtacaccgctgccgctgcctcagcagcagcagcctccgcagcaagaaccgcctccgcctccggttccgctggcaagccgtgcagcatgtgaagcactgaaa gatggtaatggtgatatggtttggccgaatgcagcaaccgttgttgaagttgcagcatggcgtgatgcagcaccggcaaccgcaagcgcagcagcactgccggaacattg tgaagttagcggtgcaattgccaaacgtaccggtattgatggttatccgtatgaaatcaaatttcgtctgcgtatgcctgcagaatggaatggtcgtttctttatggaaggtggta gcggcaccaatggtagcctgagcgcagccaccggtagcattggtggtggtcagattgcaagcgcactgagccgtaattttgcaaccattgcaaccgatggtggtcatgata atgccgttaatgataatccggatgcactgggcaccgttgcatttggtctggatccgcaggcacgtctggatatgggttataatagctatgatcaggttacccaggcaggtaaa gcagcagttgcacgttttatggtcgtgcagcagataaaagctattttatcggttgtagcgaaggtggtcgtgaaggtatgatgctgagccagcgttttccgagccattatgatg gtattgttgcgggtgcaccgggttatcagctgccgaaagcaggtattagtggtgcatggaccacacagagcctggcaccggcagccgttggcctggatgcacagggtgtt ccgctgattaacaaaagctttagtgatgccgatctgcatctgctgagtcaggcaattctgggcacctgtgatgccctggatggtctggcagatggcattgttgataactatcgtg catgtcaggcagcatttgatccggcaacagcagcaaatccggcaaatggtcaggccctgcagtgtgttggtcaaaaaccgcagattgtctgagtccggttcaggtgaccg caattaaacgcgcaatggcaggtccggttaatagcgcaggcacaccgctgtataatcgttgggcatgggatgcaggtatgagcggtctgagcggtacaacctataatcaag gttggcgtagttggtggctgggtagctttaatagcagcgcaaataatgcccagcgtgttagcggttttagcgcacgtagctggctggcttggttgattttgcgaccctccggaaccg atgccgatgacacaggttgcagcacgcatgatgaaattcgattttgatattgacccgctgaaaatttgggcaaccagcggtcagtttacccagagtagcatggattggcatgg tgcaaccagcaccgatctggcagcctttcgtgatcgtggtggtaaaatgattctgtatcatggtatgtcagatgcagcctttagtgcactggatacagcagattattatgaacgt ctgggtgcagcaatgcctggtgcagcaggttttgcacgtctgtttctggttccgggtatgaatcattgtagcggtggtccgggtacagatcgtttgatatgctgacccctctgg ttgcatgggttgaacgtggtgaagcaccggatcagattagcgcatggtactccgggttatttttggtgttgccgcacgtacccgtccgctgtgtccgatccgcagatc gcacgttataaaggtagcggtgatattaacaccgaagccaattttgcatgtgcagcacctccgcaccaccaccaccaccaccctcctcctgctctgccaccaaaaaggaga aga

Type	Gene	Sequence
Enzyme	ICCG-ScaA	agcaacccgtaccagcgtggccccgaatccgacccgcagcgcactgaccgcagatggcccgtttagcgtggcaacctacaccgtctcacgcctgtcagtctcgggttttgg cggtggcgtgatttattacccgaccggcacgtctctgacgttcggtggcatcgcgatgagtccgggttataccgcagatgctagctctctggcatggctgggtcgtcgcctg gcttcccatggctttgtggttctggtgattaacacagaattcacgtttcgatggcccggacagccgcgcctctcagctgagtgccgccctgaactacctgcgtaccagttcccc gagcgccgttcgcgcacgtctgatgcaaatcgtctggccgtttgccggtcattctatgggtggcggtggcaccctgcgtattgcagaacaaaacccgagcctgaaagcgg ctgtccccgctgaccccgtggcacaccgataaaacgtttaataccagtgtccccgtgctgattgttggcgcagaagctgacaccgtggcgccggtttcgcagcatgccatcc cgtttttatcaaaacctgccgagcaccacgccgaaagtttacgtcgaactgtgcaacgcatcgcacattgtccgaacagcaacaatgcggccatttccgtttatacgatctcat ggatgaaactgtgggtcgataatgacacccgttaccgccagttcctgtgtaatgtgaacgacccggctctgtgcgacttccgcaccaataatcgccactgccagtaacaac tcctcagcccggcacaaagctccgttcctacatggggcgatacaaactgcgacggccgttgtaaatgttgctgacgtagtagttcttaacagattcctcaacgatcctacatattct aacattactgatcagggtaaggttaacgcagacgttgttgatcctcaggataagtccggcgcagcagttgatcctgcaggcgtaaagctcacagtagctgactctgaggcaa tcctcaaggcatccgttgaa
Enzyme	FucO-CelF	atgatggctaacagaatgctggtgaacgaaacggccatggtttggtcgaggtgctgttggagctttaaccgatgaagtgaaacgccgtggttatcagaaggcgctgatcgtca ccgataaaacgctggtgcaatgcggccgtggtggcgaaagtgaccgacaagatggatgccgcaggactggcatggccgatttacgacggcgtagtacctaacccaacaat tactgtcgtcaaagaagggctcgatgtattccagaatagcggccgcggattacctgatcgctattggttggtggttctccacagatacgttaaagcgattatcagca acaacccggagtttgccgatgtgcgtagcctggaaagggctttccccgaccaataaacccagtgtaccgattctggcaatcccaccacagcaggcactgcggcagaagtg accattaactacgtgatcactgacgaagagaaacggccgcaagtttgtttgcgttgatccgcatgatatcccgcaggtggcgtttattgacgctgacatgatggatggtatgcct ccagcgctgaaagctgcgacgggtgtcgatgcgctcactcatgctcattgaggggtatattacccgtggcgcgtgggcgctaaccgatgcactgcacattaaagcgattgaa atcattgctggggcgctgcgaggatcggttgctggtgataaggatgccggagaagaaatggcgctcgggcagtatgttgcgggttctcgaatgttgggttaggg ttggtgcatggtatggcgcatccactgggcgcgtttttataacactccacacggtgttgcgaacgccatcctgttaccgcatgtcatgcgttataacgctgactttaccggtgag aagtaccgcgatatcgcgcgcgttatgggcgtgaaagtggaaggtatgagcctggaagaggcgcgtaatgccgccgttgaagcggtgtttgctctcaaccgtgatgtcggt attccgccacatttacgtgatgttggtgtacgcaaggaagacattccggcactggcgcaggcggcactggatgatgtttgtaccggtggcaacccgcgtgaagcaacgctt gaggatattgtagagctttaccataccgcctggtctgaggtgaaggctcaggaggtggaggctctggaggtggaggctcaccttaggttcccag atcaaggtccagaaaaattattgggtgatgtaaacggtgacgaaactgtagacgctattgaccttgctataacttaaaaaatatctttaaacagcagtactacaataaatactgca aatgcagatatgaatagtgataatgctattgacgctattgactatgctcttttaaagaaagcacttctttctatccaactcgag
Enzyme	SH3L-AldA	cctcctcctgctctgccaccaaaaaggagaagatctggaggtggaggctcaggaggtggaggctccggaggtggaggctcacatatgtcagtacccgttcaacatcctat gtatatcgatggacagtttgtacctggcgtgtggagacgcatggattgatgtgtgtaaaaccctgctacagaggctgtcattccccgcatacccgatggtcaggccgaggatgcc cgtaaggcaatcgatgcagcagaacgtgcacaaccagatgggaagcgttgcctgctattgaacgcgccagttggttgcgcaaaatctccgccgggatccgcgaacgcg ccagtgaaatcagtgcgctgattgttgaagaaggggggcaagatccagcagctggctgaagtcgaagtggctttttactgccgactatatgcattacatggcggagtgggcac ggcgttacgagggcgagattattcaaagcgatcgtccaggagaaaatattctttttgtttaaacgtgcgcttggtgtgactaccggcattctgccgtggaacttcccgttcttcctc attgcccgcaaaatggctcccgctcttttgaccggtaataccatcgtcattaaacctagtgaatttacgccaaacaatgcgattgcattcgacaggcagcgtctctgca cttccgccggcgtgtttaaccttgtactgaggcgctggtgaaacgttgggcaagaactggcgggtaacccaaagtgccaatggtcagtatgacaggcagcgtctctgca ggtgagaagatcatggcgactgcgcgaaaaacatcaccaaagtgtgtctggaattgggggtaaagcaccagctatcgtaatggacgatgccgatcttgaactggcagt caaagccatcgttgattcacgcgtcattaataagtgggcaagtgtgtaactgtgcagaacgtgtttatgtacagaaaggcatttatgatcagttcgtcaatcggctgggtgaagc gatgcaggcggttcaatttggtaaccccgctgaacgcaacgacattgcgatgggggccgttgattaacgccgcggcgctggaaaggtcgagcaaaaagtggcgcgcgc agtagaagaaggggcgaagctggccgttcggtggcaaagcgggtagaggggaaaagatatttattatccgccgacattgctcgtggatgttcgccaggaaatgtcgattatgc atgaggaaacctttggcccggtgctgccagttgtcgcatttgacacgctggaagatgctatctcaatgggctaatgacagtgattacggcctgacctcatcaatctatacccaaa atctgaacgtcgcgatgaaagccattaaagggctgaagtttggtgaaacttacatcaaccgtgaaaacttcgaagctatgcaaggcttccacgccggatgcgtaaatccgg tattggcggcgcagatggtaaacatggcttgcatgaatatctgcagacccaggtggtttatttacagtcgctcgag
Enzyme	LrNox-ScaA	atgaaagttattattgttggttgtacacatgcgggaacaattactgccactcaaatttacagaatcatccagaaacagaagtcacaatttatgaacggaatgataacgtttcattc ctctcatgtggggattgcagtttacttgagcggtgatgttggtaatccagatgcgatgtttttattcaagccctgaacaacttgctgccatgggtgcaacagttcatatgcaacataat gtaactgatattgaccctaagactaagacagtcacagtgacagaccttgtgacaggcgaaacaaagaccgaccattatgataagttagttgatactactggttcttggccagta attccaccaattgaaggtgtagatggccctcatgtttatttgtgtgcaagaattaccatcatgctaaagaattatttaacgttgctaaagatgcgcaacgaattgttgtgattggtgga ggttatattggggttgaattagtagaagcttacactcgtcaaaataaggacgtattggttgggtctccacgatgggctgcttcataaatactttgacccgcagtatacggatcg aattcaacaggaatttgtagatcacgggcgcccactttgctttgaccaacgcgtaactggatttgaaaaccacgaaaatggtgtaaccgttaagacgataagggcaactacg aggcagatattgctatcctctgtgttggctccgtcctaatactgatctcttaaaaggtaaagttaagatgcatgataatggggcaatcattacgaacgaatacatgcaatcatct gatccagatattttacgctgccggagattcaacggctgttcactataacccaactggcaaggatgcatacattccattagctactaacgctattcggcaaggaacaattgttgga acaaatctctttggtaataacaatgcgcgatatgggaacccaatctagttctggcttaaacttatatgaacaacgatggtatcatctggcttaacttttggagaatgccaaagaag cgggctttgatgcagctgcggtgacagttgaagacaactaccgtccagaatttatgccgacaacaactcctgtattaatgacattggtgtgtgggataagaaagactcggcaaatt cttggtgggacagtttatgagtaagcatgatgtttctcaatctgctaacattatttccttatgtatccaggataagcacacgattgattatttcatttgttgatatgctttccaaccac actttgatcgtccatttaactatgtaaatattcttggccaagcggcggtaaagaaacaagctgaattagaaaaatctggaggtggaggctcaggaggtggaggctccggagg tggaggctcacctaggtaacaactcctcagcccggcacaaagctcgttcctacatggggcgatacaaactgcgacggccgttgtaaatgttgctgacgtagtagttcttaac agattcctcaacgatcctacatattctaacattactgatcagggtaaggttaacgcagacgttgttgatcctcaggataagtccggcgcagcagttgatcctgcaggcgtaaag ctcacagtagctgactctgaggcaatcctcaaggcatccgttgaactcatcacacttcctcagctcgag
Scaffold	CipA-linker-CipC	ggtgtggtagtagaaattggcaaagttacgggatctgttggaactacagttgaaatacctgtatatttcagaggagttccatccaaaggaatagcaaactgcgactttgtgttca gatatgatccgaatgtattggaaattataggaatagatcccgagacataataagttgacccgaatcctaccaagagctttgatactgcaatatatcctgacagaaagataatag tattcctgtttgcggaagacagcggaacaggagcgtatgcaataactaaagacgagatgattgcaaaaataagctgaactgtaaaatcaagtgctccgggctatattactttc gacgaagtaggtggatttgcagataatgacctggtagaacagaaggtatcatttatagacggtggtgttaacgttggcaatgcaacaccgaccaagggagcaacaccaaca aatacagctacgccgacaaaatcagctacggctacgcccaccaggccatcggtaccgacaaacacaccgacaaacacaccggcaaatacaccggcagtgtagtacca tcaacacagccgtgtaacaacaccacctgcaacaacaaaaccacctgcaacaacaaaaccacctgcaacaacaataaccgccgtgcagatgatccgggcgattctcttaaagtt acagtaggaacagctacgactgcgctgcggatacagtaacagtacatttgctgatgtagcaacagatgaaaacgtaggaacatgtaatttctatcttggatatgatg caagcctgttagaggtagtatcagtagatgcaggtccaatagttaagaatgcagcagttaacttctcaagcagtgcaagcaacggaacaatcagcttcctgttcttggataac acaattacagacgaattgataactgcagacggtgtgtttgcaaatattaagttcaaattaaagagtgtaacggctaaaactacaacaccagtaacatttaaagatggtggagctt ttggtgacggaactatgtcaaagatagcttcagttactaagacaaacggtagtgtaactatagatcctggtactcaa
Scaffold	CipA-linker-CBM-linker-CipC	ggtgtggtagtagaaattggcaaagttacgggatctgttggaactacagttgaaatacctgtatatttcagaggagttccatccaaaggaatagcaaactgcgactttgtgttca gatatgatccgaatgtattggaaattataggaatagatcccgagacataataagttgacccgaatcctaccaagagctttgatactgcaatatatcctgacagaaagataatag tattcctgtttgcggaagacagcggaacaggagcgtatgcaataactaaagacgagatgattgcaaaaataagagcaactgtaaaatcaagtgctccgggctatattactttc gacgaagtaggtggatttgcagataatgacctggtagaacagaaggtatcatttatagacggtggtgttaacgttggcaatgcaacaccgaccaagggagcaacaccaaca aatacagctacgccgacaaaatcagctacggctacgcccaccaggccatcggtaccgacaaacacaccgacaaacacaccggcaaatacaccggtatcaggcaatttga aggttgaattctacaacagcaatccttcagatactactaactcaatcaatctcagttcaaggttactaataccgaagcagtgcaattgatttgtccaaactcacattgagatatt attatacagtagacggacagaaagatcagaccttctggtgtgaccatgctgcaataatcggcagtaacggcagctacaacggaattacttcaaatgtaaaaggaacatttgta aaaatgagttcctcaacaaataacgcagacacctaccttgaaataagctttcaggcggaactcttgaaccgggtgcacatgttcagatacaaggtagatttgcaaagaatga ctggagtaactatacacagtcaaatgactactcattcaagtctgcttcacagtttgttgaatgggatcaggtaacagcatacttgaacggtgttcttgtatgggggtaaagaaccc ggtgcagtgtagtaccatcaacacaggcctgtaacaacaccacctgcaacaacaaaaccacctgcaacaacaataaccgccgtgcagatgatc cgggcgattctcttaaagttacagtaggaacagctacgactgcgctgcggatacagtaacagtacatttgctgatgtagcaacagatgaaaacgtaggaacatgta atttctatcttggatatgatgcaagcctgttagaggtagtatcagtagatgcaggtccaatagttaagaatgcagcagttaacttctcaagcagtgcaagcaacggaacaatca gcttcctgttcttggataacacaattacagacgaattgataactgcagacggtgtgtttgcaaatattaagttcaaattaaagagtgtaacggctaaaactacaacaccagtaac atttaaagatggtggagctttttggtgacggaactatgtcaaagatagcttcagttactaagacaaacggtagtgtaactatagatcctggtactcag
Scaffold	CipA-linker-CBM-linker-CipC-SED1	ggtgtggtagtagaaattggcaaagttacgggatctgttggaactacagttgaaatacctgtatatttcagaggagttccatccaaaggaatagcaaactgcgactttgtgttca gatatgatccgaatgtattggaaattataggaatagatcccgagacataataagttgacccgaatcctaccaagagctttgatactgcaatatatcctgacagaaagataatag tattcctgtttgcggaagacagcggaacaggagcgtatgcaataactaaagacgagatgattgcaaaaataagagcaactgtaaaatcaagtgctccgggctatattactttc gacgaagtaggtggatttgcagataatgacctggtagaacagaaggtatcatttatagacggtggtgttaacgttggcaatgcaacaccgaccaagggagcaacaccaaca aatacagctacgccgacaaaatcagctacggctacgcccaccaggccatcggtaccgacaaacacaccgacaaacacaccggcaaatacaccggtatcaggcaatttga aggttgaattctacaacagcaatccttcagatactactaactcaatcaatcctcagttcaaggttactaataccggaagcagtgcaattgatttgtccaaactcacattgagatatt attatacagtagacggacagaaagatcagaccttctggtgtgaccatgctgcaataatcggcagtaacggcagctacaacggaattacttcaaatgtaaaaggaacatttgta aaaatgagttcctcaacaaataacgcagacacctaccttgaaataagctttcaggcggaactcttgaaccgggtgcacatgttcagatacaaggtagatttgcaaagaatga

		ctggagtaactatacacagtcaaatgactactcattcaagtctgcttcacagtttgttgaatgggatcaggtaacagcatacttgaacggtgttcttgtatggggtaaagaaccc**ggtg**gcagtgtagtaccatcaacacagcctgtaacaacaccacctgcaacaacaaaaccacctgcaacaacaataccgccgtcagatgatcc**ggg**cgattctcttaaagttacagtaggaacagctaatggtaagcctggcgatacagtaacagttcctgttacatttgctgatgtagcaaagatgaaaaacgtaggaacatgtaatttctatcttggatatgatgcaagcctgttagaggtagtatcagtagatgcaggtccaatagttaagaatgcagcagttaacttctcaagcagtgcaagcaacggaacaatcagcttcctgttcttggataacacaattacagacgaattgataactgcagacggtgtgtttgcaaatattaagttcaaattaaagagtgtaacggctaaaactacaacaccagtaacatttaaagatggtggagcttttggtgacggaactatgtcaaagatagctcagttactaagacaaacggtagtgtaactatagatcctggtactcaactcgaggggtggtggaggtagtggaggaggtggtagtcaattttccaacagtacatctgcttcttccaccgatgtcacttcctcctcttccatctccacttcctctggctcagtaactatcacatcttctgaagctccagaatccgacaacggtaccagcacagctgcaccaactgaaacctcaacagaggctccaaccactgctatcccaactaacggtacctctactgaagctccaaccactgctatcccaactaacggtacctctactgaagctccaactgatactactactgaagctccaaccaccgctcttccaactaacggtacttctactgaagctccaactgatactactactgaagctccaaccaccggtctccaacaacgttactaccttcagctttccaccaactacatctttgccaccaagcaacactaccaccactcctccttacaacccatctactgactacaccactgactacactgtagtcactgaatatactacttactgtccagaaccaaccacttttcaccacaaacggtaagacttacaccgtcactgaaccaaccacattgactatcactgactgtccatgcaccattgaaaagccaacaaccacatcaacccaccgaatacactgtagtcactgaatatactacttactgtccagaaccaaccacttttcaccacaaacggtaagacttacaccgtcactgaaccaaccacatcaaccaccatcatctttgactatcactgactgtccatgtactattgaaaagagcgaagcccctgagtcttctgtcccagttaccgaatctaagggcaccaccaaagaaacaggtgttactaccaaacaaacacacgccaacaagtctaaccgtctccacagtcgtcccagtttcatcctctgcttcttctcattccgttgtcatcaacagtaacggtgctaacgtcgtcgttccaggtgcttaggtttggctggtggtgttgctatgttattcttataa
Scaffold	CipA-linker- CBM-linker- SH3_D	ggtgtggtagtagaaattggcaaagttacgggatctgttggaactacagttgaaatacctgtatatttcagaggagttccatccaaaggaatagcaaactgcgactttgtgttcagatatgatccgaatgtattggaaattatagggatagatcccgggagacataatagttgacccgaatcctaccaagagctttgatactgcaatatatcctgacagaaagataatagtattcctgtttgcggaagacagcggaacaggagcgtatgcaataactaaagacggagtatttgcaaaaataagagcaactgtaaaatcaagtgctccgggctatattactttcgacgaagtaggtggatttgcagataatgacctggtagaacagaaagggtatcatttatagacggtggtgttaacgttggcaatgcaacaccgacccaagggagcaacaccaacaaatacagctacgccgacaaaatcagctacggctacgcccaccaggccatcggtaccgacaaacacaccgacaaacacacggcaaatacaccg**gtatcaggcaatttga**aggttgaattctacaacagcaatccttcagatactactaactcaatcaatcctcagttcaaggttactaataccggaagcagtgcaattgatttgtccaaactcacattgagatattattatacagtagacggacagaaagatcagaccttctggtgtgtgaccatgctgcaataatcggcagtaacggcagctacaacgggaattacttcaaatgtaaaaggaacatttgtaaaatgagttcctcaacaaataacgcagcacctacctttgaaataagctttacaggcgtaactcttgaaccgggtgcacatgttcagataacaaggtagatttgcaaagaatga**ctggagtaactatacacagtcaaatgactactcattcaagtctgcttcacagtttgttgaatgggatcaggtaacagcatacttgaacggtgttcttgtatggggtaaagaaccc**ggt**ggcagtgtagtaccatcaacacagcctgtaacaacaccacctgcaacaacaaaaccacctgcaacaacaataccgccgtcagatgatccggaagaggcagaatgttcgtgccctgtttgattttaatggcaacgatgaagaagatctgccgtttaaaaagggtgatattctgcgtattcgtgacaaaccggaagaacagtggtggaatgcagaagatagcgaaggtaaacgtggtatgattccggttccgtatgttgaaaaaatatcgtccg
Scaffold	CipA-linker- CBM-linker- SH3_D -ScaB	ggtgtggtagtagaaattggcaaagttacgggatctgttggaactacagttgaaatacctgtatatttcagaggagttccatccaaaggaatagcaaactgcgactttgtgttcagatatgatccgaatgtattggaaattatagggatagatcccgggagacataatagttgacccgaatcctaccaagagctttgatactgcaatatatcctgacagaaagataatagtattcctgtttgcggaagacagcggaacaggagcgtatgcaataactaaagacggagtatttgcaaaaataagagcaactgtaaaatcaagtgctccgggctatattactttcgacgaagtaggtggatttgcagataatgacctggtagaacagaaagggtatcatttatagacggtggtgttaacgttggc**aatgcaacaccgacccaagggagcaacaccaaca**aatacagctacgccgacaaaatcagctacggctacgcccaccaggccatcggtaccgacaaacacaccgacaaacacacggcaaatacaccg**gtatcaggcaatttga**aggttgaattctacaacagcaatccttcagatactactaactcaatcaatcctcagttcaaggttactaataccggaagcagtgcaattgatttgtccaaactcacattgagatattattatacagtagacggacagaaagatcagaccttctggtgtgtgaccatgctgcaataatcggcagtaacggcagctacaacggaattacttcaaatgtaaaaggaacatttgtaaaatgagttcctcaacaaataacgcagcacctaccttgaaccgggtgcacatgttcagataacaaggtagatttgcaaagaatga**ctggagtaactatacacagtcaaatgactactcattcaagtctgcttcacagtttgttgaatgggatcaggtaacagcatacttgaacggtgttcttgtatggggtaaagaaccc**ggt**ggcagtgtagtaccatcaacacagcctgtaacaacaccacctgcaacaacaaaaccacctgcaacaacaataccgccgtcagatgatccggaagaggcagaatgttcgtgccctgtttgattttaatggcaacgatgaagaagatctgccgtttaaaaagggtgatattctgcgtattcgtgacaaaccggaagaacagtggtggaatgcagaagatagcgaaggtaaacgtggtatgattccggttccgtatgttgaaaaaatatcgtccgggatccgccggtggtttatccgctgtgcagcctaatgttagttaggcgaagtactggatgtttctgctaacagaaccgctgctgacggaatggtttatcccaacagtaactgcagctccaggcccagaccggcgacaggcgtacgttattcgtccaagacggacggtgacgcttacggttcaggcattgtgtacaataatagtaagtatgctttggacagggtgcaggtagaggaatagttgcagctgatgattccggttgtgcttactcttgcatatacagtcccgctgattgtgctgaaggtacatatgatgtcaagtggtctgatgcgtttgtaagtgatacagacggacagaatatcacaagtaaggttactcttactgatggcgctatcattgttaag
Primer	M1-F	ggaggctcaggaggtggaggctccggaggtggaggctcaggtggtggtagtacaccgct
Primer	M2-F	caccaaaaaggagaagatctggaggtggaggctcaggaggtggaggct
Primer	M3-F	catcatatgcctcctcctgctctgccaccaaaaaggagaagatct
Primer	M-R	gaattcggatccctcgagcggaggtgctgcacatgcaaaattg
Primer	Md-R	gcagagattacctatctagacggaggtgctgcacatgc
Primer	his-F	ggtaatacaccatgaatcacaaag
Primer	his-R	ctatctagagtggtggtggtggtggtggtcgacaagcttgaattcgg
Primer	pScf-F	cctcagatgggcagcagcggtaagcctatccctaaccctctcctc
Primer	pScf-R	gagaccttaattcgcttataagaataacatagcaacaccagc
Primer	pF-F	gacctcagatgggcagcagccatatgcagacaaatccctatgccc
Primer	pF-R	gtcagagagaccttaattcgctcacaagtcctcttcagaaatgagc
Primer	pM-F	ccatcagagacctcagatgggcagcagccatcatcatcatcatcacagc
Primer	pM-R	cagagagaccttaattcgctcagtggtggtggtggtggtgctcgag
Primer	pZM-F	ggcggccgccagcttacgtacatcatcatcatcacagcagcggcc
Primer	pZM-R	gtctaaggctacaaactcagtggtggtggtggtggtgctcgagttgg
Primer	pPIC9K-F	gcgaattaaggtctctctgacttagacatgactgttcctcagttcaag
Primer	pPIC9K-R	tgaggtctctgatggctgctgcccatgaattctacgtaagcttcagc
Primer	pPICZC-F	tgagtttgtagccttagacatgactgttcctcagttcaag
Primer	pPICZC-R	tacgtaagctggcggccgccgcggctcgaggtaccgatcc
Primer	qC-F	tcctgtttgcggaagacagcg
Primer	qC-R	tgttggtgttgctcccttggtc

Primer	qF-F	gtccgtttaccgtccgttct
Primer	qF-R	gcgctgtatagcctggaaca
Primer	qM-F	gcagaccacagtaacgacga
Primer	qM-R	cattgccgtctttcagtgcc
Primer	qGAPDH-F	gtggtcatcaaaccggactca
Primer	qGAPDH-R	caagaaggtcgtcatcactgctc

675 **Supplementary Table 3. Insertion copy number of genes of engineered *Pichia pastoris* SMD1168**

Strain	Gene	Copy number
P. pastoris **SMD1168**_{His4::CipA-CBM-CipC-SED1}	CipA-CBM-CipC-SED1	22.13±1.14
P. pastoris **SMD1168**_{His4::MHETase}	MHETase	17.71±0.99
P. pastoris **SMD1168**_{His4::FAST}	FAST	15.20±0.38
P. pastoris **SMD1168**_{His4::FAST-MHETase}	MHETase	18.19±0.72
P. pastoris **SMD1168**_{His4::FAST-MHETase}	FAST	14.54±0.77

678 **Supplementary Fig. 1. SDS-PAGE of purified recombinant enzymes and protein scaffolds used in this study.**

679 **(A)** M-CelF: MHETase-CelF; optiM: codon optimized MHETase (as control); M-SH3$_L$: optiMHETase-SH3$_L$; SH3$_L$-

680 M: SH3$_L$-optiMHETase; ICCG: ICCG-ScaA; FAST: FAST-PETase-CelF. **(B)** Scaf.1: CipA-CipC; Scaf.2: CipA-

681 CBM-CipC; Scaf.3: CipA-CBM-SH3$_D$; Scaf.4: CipA-CBM-SH3$_D$-ScaB. **(C)** LrNox: LrNox-ScaA; FucO: FucO-

682 CelF; AldA: SH3$_L$-AldA. All proteins were Coomassie stained.

Supplementary Fig. 2. Purification of enzymes and protein scaffolds. (A)-(F) SDS-PAGE and Fast Protein Liquid Chromatography (FPLC) results of enzymes and scaffolds, followed by binding to HisTrap column and eluting the protein with high concentration of imidazole. **(A)** FAST-PETase-CelK. **(B)** ICCG-ScaA. **(C)** CipA-CipC (Scaf.1). **(D)** CipA-CBM-CipC (Scaf.2). **(E)** CipA-CBM-SH3$_D$ (Scaf.3). **(F)** CipA-CBM-SH3$_D$-ScaB (Scaf.4). M, marker; #4-#44, numbers of elution fractions from the HisTrap column.

Supplementary Fig. 3. Crystallinity characterization of PET substrates used in this study. Differential scanning calorimetry (DSC) thermograms of different substrates: **(A)** PET powder (40.82% crystallinity). **(B)** NFbottle (61.33% crystallinity). **(C)** Film-L (17.99% crystallinity). **(D)** Film-H (43.31% crystallinity). ΔHm, heat of melting; ΔHc, heat of cold crystallization. Data are presented as mean ± s.d. (n = 3).

Supplementary Fig. 4. Optimizations of MHETase expression. (A) Optimization of strains for MHETase-CelF

expression at 4°C, induced by 1 mM IPTG for 12 hours. SDS-PAGE result indicates the best strain *E.coli* C41(DE3)

for MHETase expression. **(B)** Optimization of inducing conditions for MHETase-CelF expression. SDS-PAGE result

indicates the best inducing condition, at 16°C, induced by 1 mM IPTG, for MHETase expression. M, Marker. **(C)-**

(D) Condon quality distributions (top) and codon quality plot (bottom) of MHETases in *E.coli*. Results were

calculated by GeneArt™ GeneOptimizer™ (Thermo Fisher). **(C)** MHETase-CelF (blue). **(D)** Codon optimized

MHETase-CelF (optiMHETase-CelF, yellow).

Supplementary Fig. 5. Purification of MHETases by Fast Protein Liquid Chromatography (FPLC). (A) Fast

Protein Liquid Chromatography (FPLC) overlay results of MHETases. **(B)-(F)** SDS-PAGE of MHETases. M, marker;

#3-#22, numbers of elution fractions from the HisTrap column.

Supplementary Fig. 6. Predicted structure of enzyme-scaffold complex D. Structure of the scaffold, containing

CipA (orange), CBM (brown), SH3$_D$ (green), ScaB (blue), was predicted by AlphaFold2.

Supplementary Fig. 7. Optimization of enzyme-to-scaffold molar ratio in SPEED system. Effect of enzyme-

to-scaffold molar ratio on PET degradation efficiency with fixed amount of enzyme (0.25 nmol individual

enzymes). All reactions were performed at 30°C, pH 7.0, for 96 hours using 100 mg PET powder, with Scaf.4-to-

enzyme molar ratio of .0:1/0.5:1/1:1/2:1/3:1/4:1/5:1/10:1.

Supplementary Fig. 8. Assessment of optimal temperature of SH3$_L$-optiMHETase. The reaction was carried

out by 0.5 mM enzyme with 5 mM MHET and BHET at pH 7.0 for 96 hours. The elevated TPA release observed

in the 70°C group may be attributed to the self-degradation of the monomers under high temperatures (**Source**

Data). Data are presented as mean ± s.d. (n = 3). Statistical significance was determined by one-way ANOVA (ns:

not significant, *$p < 0.1$, **$p < 0.01$, ***$p < 0.001$, ****$p < 0.0001$).

Supplementary Fig. 9. PET degradation by SPEED Complex-D under optimal conditions. PET degradation
assays of optimized Complex-D on different substrates: PET powder (A), film-L (B), film-H (C) and NFbottle (D).
All reactions were performed at 40°C, pH 7.0, for 96 hours using 100 mg PET substrate, 0.5 nmol individual enzymes,
with an enzyme:scaffold molar ratio of 0.5:1. Data are presented as mean ± s.d. (n = 3). Statistical significance was
determined by one-way ANOVA (ns: not significant, *p < 0.1, **p < 0.01, ***p < 0.001, ****p < 0.0001).

Supplementary Fig. 10. XRD spectra of immobilized samples. (A) XRD pattern simulated from CIF file of ZIF-

8 (bottom, No. 00-062-1030), XRD patterns of synthesized ZIF-8, optiComplex-D@ZIF-8, and Enz.3@ZIF-8,

respectively. **(B)** XRD patterns of simulated NaZn(PO$_4$)·H$_2$O (bottom), Enz.3@ZIF-8 and optiComplex-D@ZIF-8,

respectively. Enz.3, FAST-PETase with ICCG and MHETase (0.25 nmol individual enzymes); optiComplex-D,

Enz.3 with Scaf.4 (5 nmol).

Supplementary Fig. 11. Scaffold expression and enzyme secretion assays in different *Pichia pastoris* strains.

The scaffold (with V5 tag) displaying strain and enzyme (with His tag) secreting strains were pre-mixed and then

induced at 30°C in BMMY medium. Scaf., *P. pastoris*His4::CipA-CBM-CipC-SED1, M, *P. pastoris*His4::MHETase, F, *P.*

*pastoris*His4::FAST. The scaffold was fused with V5 tag; MHETase and FAST were fused with his tag for detection. *P.*

*pastoris*His4::enzyme was mixed with *P. pastoris*His4::scaffold in a 1:1 ratio, resulting in a final system comprising 2×10^7

*P. pastoris*His4::scaffold.

Supplementary Methods

Calculation of total enzymes

Weight or the concentration of enzymes was got from corresponding paper (**Supplementary File**
1). Total enzymes amount was calculated with the sum of corresponding molar amount of single
enzyme. For known weight of enzymes, molar amount of single enzyme was calculated with the
formula below (molecular weight of each enzyme was calculated on
https://web.expasy.org/protparam/):

$$Molar\ amount\ of\ single\ enzyme\ (nmol) = \frac{Weight\ (\mu g)}{Molecular\ weight\ (kDa)}$$

For known concentration of enzymes, molar amount of single enzyme was calculated with the
formula below:

$$Molar\ amount\ of\ single\ enzyme\ (nmol) = \frac{Concentration\ (nM) \times Volume\ (mL)}{1000}$$

Calculation of total products

Weight loss or concentration of released total products was got from corresponding paper
(**Supplementary File 1**). For known concentration of total products, molar amount was calculated
with the formula below:

$$Molar\ amount\ of\ total\ products\ (\mu mol) = Concentration(mM) \times Volume(mL)$$

For known weight loss of total products, molar amount was calculated with the formula below
(192 is the relative molecular mass of a bulding block of PET):

$$Molar\ amount\ of\ total\ products\ (\mu mol) = \frac{Weight\ loss\ (\%) \times Weight\ of\ PET\ (mg) \times 10}{192}$$

Calculation of degradation efficiency and improved fold-change

Degradation efficiency was calculated based on the above calculations, with the formula below:

$$Degradation\ efficiency\ (mol/mmol) = \frac{Molar\ amount\ of\ total\ products\ (\mu mol)}{Molar\ amount\ of\ single\ enzyme\ (nmol)}$$

Improved fold-change is the ratio of the above calculated degradation efficiencies (this study
vs. previous study).

Calculation of percentage of recyclable monomer release

Percentage of recyclable monomer release was calculated based on the above calculations, with the

formula below:

770
$$Recyclable\ monomer\ release\ (\%) = \frac{Concentration_{TPA+EG}\ (mM)}{Concentration_{TPA+EG+MHET+BHET}\ (mM)} \times 100\%$$