Efficient degradation of oxidized polyethylene containing ester bonds by cutinase

or lipase in aqueous phase

Demin Kong[a,b,c], Lei Wang[a,b,c], Wei Xia[a,b,c], Meng Shi[a,b,c], Jing Wu[a,b,c*]

[a]State Key Laboratory of Food Science and Resources,Jiangnan University, 1800 Lihu

Avenue, Wuxi, 214122, China

[b]School of Biotechnology and Key Laboratory of Industrial Biotechnology Ministry

of Education, Jiangnan University, 1800 Lihu Avenue, Wuxi, 214122, China

[c]International Joint Laboratory on Food Safety, Jiangnan University, 1800 Lihu

Avenue, Wuxi, 214122, China

* Corresponding author:

State Key Laboratory of Food Science and Resources, Jiangnan University, 1800 Lihu

Avenue, Wuxi, Jiangsu 214122, China.

Phone: +86-510-85327802

Fax: +86-510-85326653

E-mail: jingwu@jiangnan.edu.cn

Abstract:

Polyethylene is a widely used plastic that presents challenges in degrading within natural environments. Therefore, the degradation of polyethylene is of utmost importance. Currently, physical or chemical methods are efficient but more dangerous. Conversely, biological methods are safer but less efficient. Combining the two approaches to create entirely new polyethylene degradation pathways is a viable idea. Based on the previous research, it is an effective method to add ester bonds inside polyethylene and degrade using cutinase or lipase. However, the method only detected a decrease in molecular weight and did not observe a rate of weight loss at the macroscopic level. In this research, rapid degradation of polyethylene is achieved by optimizing catalysis conditions and machine learning. Finally, the maximum weight loss up to 80.51% within 24h and a mild catalysis environment (60-80°C). Furthermore, the method's versatility was confirmed for cutinase and lipase. Overall, this research has established an effective, efficient, and mild degradation process of polyethylene, significantly contributing to the progress in polyethylene degradation.

Keywords:

Polyethylene, cutinase, degradation, weight loss

Introduction

Polyethylene, a ubiquitous used plastic[1], is widely used in the agricultural, food, construction and medical industries. However, due to its stable chemical properties, polyethylene is difficult to degrade in the natural environment and is accumulating in large quantities, polluting the environment[2]. Hence, in order to replace traditional incineration and landfill methods, the quest for safe, dependable, and efficient degradation techniques is imperative.

Physical or chemical methods have the advantage of high efficiency. The catalyst $mSiO_2/Pt/SiO_2$ was utilized for polyethylene hydrogenation after 6 h at 300□ under 1.38 MPa of H_2, resulting in the production of alkanes spanning from C_6 to C_{40}[3]. L-$ZrO_2@mSiO_2$ or a comparable material was employed for decomposing polyethylene to generate C_8-C_{40}[4]. Polyethylene can be fully converted into C_6-C_{10} at 70 °C, and the

degradation system was catalysed under Lewis acidic conditions.[5] Microwaves and

$FeAlO_x$ were employed in the degradation of polyethylene to generate H_2 and solid

carbon[6]. The utilization of polyethylene as a substrate for the production of olefins

was achieved through dehydrogenation, which was coupled with tandem isomerizing

ethenolysis for the desaturated chain[7]. Nonetheless, the scalability of the mentioned

catalysts or processes on an industrial level poses a significant challenge, constituting

a critical drawback of physical or chemical methodologies [8].

Biological degradation methods are safer but less efficient than the above methods[8].

When biological methods are combined with physical or chemical methods, the

efficiency and practicality of the methods are effectively enhanced.[9] Yao et al.

reported that the laccase-mediator system can be used to degrade LDPE with UV

treatment, and the weight-average molecular weight (M_w) was reduced by

approximately 40% compared with that of the original PE[10]. Latex clearing protein

from the *Streptomyces* sp. Strain K30 degradation system resulted in a 42.02%

reduction in the Mw of UV-treated LDPE[11]. On the other hand, more and more

enzymes have demonstrated the ability to catalyze the degradation of polyethylene

and yielding carbonyl, hydroxyl or carbon-carbon double bonds. Examples include

laccase from *Psychrobacter* sp. NJ228[12], glutathione peroxidase from *Alternaria*

alternata FB1[13] or *Rhodococcus* sp. C-2[14], and demetra or cere from *Galleria*

mellonella larvae[15]. These enzymes present novel opportunities for the enzymatic

breakdown of polyethylene.

In conclusion, incorporating appropriate functional groups into polyethylene proves to

be a highly effective approach for accelerating its degradation process. Polymers

containing ester bonds exhibit greater susceptibility to degradation compared with

polyolefins, such as poly (ethylene terephthalate)[16] and poly (butylene adipate-co-

terephthalate)[17]. Similarly, ester bonds can be added in polyethylene by using the

Baeyer–Villiger oxidation[18, 19] and be degraded using cutinase from *Thermobifida*

fusca WSH03-11. However, previous research noted that while cutinase degraded the

polymer, the efficiency was limited to molecular weight loss[18]. To address this, the

catalytic system was enhanced by incorporating various surfactants, which helped to

increase the solubility of polyethylene and its oxidation products in water and
increased the degradation rate of the system[20, 21]. Ultimately, the weight loss of
polyethylene after cutinase degradation was up to 80.51%. Moreover, the research
used machine learning to determine the optimal conditions for the degradation system.
The research establishes a gentle and effective method for converting polyethylene to
long-chain fatty acids or fatty alcohols, as well as determining the versatility of the
method in cutinase or lipases.

Materials and methods

Reagents, plasmid, and strain

Polyethylene film (PE_{film}) and pure polyethylene (PE_{pure}) were purchased from
PetroChina Company Limited and Shanghai Macklin Biochemical Technology Co.,
Ltd, respectively. The reagents used to prepare the medium include tryptone, yeast
extract, NaCl, K_2HPO_4, KH_2PO_4, kanamycin (Kan), ampicillin (Amp), and isopropyl-
beta-D-thiogalactopyranoside (IPTG), all of which were purchased from Sinopharm
Chemical Reagent Co., Ltd. Some surfactants, embedding agents, or organic reagents
were used for enhancing the solubility of products in this study, mainly including
sodium dodecyl sulfate (SDS), hexadecyl trimethyl ammonium Bromide (CTAB),
Triton X-100, PEG, betaine, rhamnolipid, cyclodextrin (α, β, γ), and dimethyl
sulfoxide (DMSO), and they were purchased from Sinopharm or Taobao (China)
Software Co., Ltd. Some of the model substrates used for enzyme activity assays were
purchased from Merck KGaA, including 4-nitrophenyl butyrate (pNPB), 4-
nitrophenyl octanoate (pNPO), 4-nitrophenyl laurate (pNPL), 4-nitrophenyl myristic
(pNPM), and 4-nitrophenyl palmitic (pNPP). Four plasmids expressing cutinases or
lipases, which contained the genes of *Thermobifida fusca* cutinase (*Tf*Cut), *Humicola*
insolens cutinase (HiC), *Thermomyces lanuginosus* lipase (TLL), *Ideonella sakaiensis*
cutinase (*Is*PET), were constructed, namely pET-24a(+)-*TfCut*[16], pPIC9K-*HiC*[22],
pPIC9K-*TLL*[23], and pET-21b(+)-*IsPET*[24]. The hosts used to construct plasmids or
express genes in this paper included *Escherichia coli* (*E. coli*) JM109, *E. coli*
BL21(DE3), and *Pichia pastoris* (*P. pastoris*) KM71.

Preparation and properties of cutinase and lipase

*Tf*Cut and *Is*PET were expressed using *E. coli* BL21(DE3), and the expression conditions were 37°C enrichment culture for 2h and 25°C culture for 24h in order to express the target enzyme after the addition of 0.1mM IPTG. Kan or Amp was added throughout with 30 μg/mL or 100 μg/mL. Hic and TLL were expressed using *P. pastoris* KM71, as previously described[22, 23]. In order to exclude interference from the culture medium, all enzymes were subjected to ammonium sulfate precipitation, dialysis and freeze-drying to obtain protein powder. The enzyme active was measured using pNPB as substrate as previously described[22]. When testing the preference of different enzymes for carbon chain length, 4-nitrophenyl ester of different lengths as above are used. The proteins concentration was measured using Bradford protein assay kit, and the distribution of proteins was examined using SDS-PAGE.

Preparation of oxidized polyethylene containing ester bonds

The oxidized polyethylene containing ester bonds was prepared using meta-chloroperoxybenzoic acid (^{m}CPBA) as previously described[18], the process mainly included the dissolution of PE using a mixture of 1,2,4-trichlorobenzene and dichloroethane in the ratio of PE:solution=1g:20mL and the oxidation of PE using ^{m}CPBA in the ratio of 1:5 (PE:^{m}CPBA). PE_{film} and PE_{pure} were used as substrate. For PE_{film}, dissolving step was performed for 12h in order to fully dissolve. For PE_{pure}, the step takes only 2h[19]. In the research, oxidized polyethylene with different ester bond content was prepared and the parameters were shown in Table S1.

Construction of cutinase or lipase degradation system in aqueous phase

Cutinase or lipase degradation contained enzymes, additives (surfactants, embedding agents, or organic reagents), phosphate buffer, and oxidized polyethylene. Different factors were optimized in the system, including the type and concentration of additives, rotational speed, the type and concentration of enzyme, temperature, pH, degradation days, and the characteristic of oxidized polyethylene.

The degradation products were treated as follow. First, the products were filtered using nylon mesh. Second, the solids obtained by filtration were washed twice using 75% ethanol and water, respectively. Lastly, the solids were dried in an oven at 60□

136 for 12h. Optimizations results were judged by weight loss ratio, and the ratio was

137 calculated according to eq.1. Among eq.1, W was weight loss ratio, S was the weight

138 of nylon mesh and products, s was the weight of nylon mesh, M was the weight of

139 substrate, s_0 and s_1 was the weight of empty nylon mesh before and after drying.

140
$$W = \frac{S-s}{M} \times \frac{s0-s1}{s0} \qquad \text{eq1}$$

Test methods on the products of degradation system

For the degradation products, the test methods included Fourier transform infrared

spectroscopy (FT-IR), high-temperature gel permeation chromatography (HT-GPC),

gas chromatography-tandem mass spectrometry (GC-MS), Differential Scanning

Calorimeter (DSC), and dynamic/static laser scattering instrument. FT-IR was used to

analyze the ester bonds content in oxidized polyethylene with a scanning range of

4000 cm^{-1} - 400 cm^{-1} and 32 scans. Ester bond index (EBI) is defined as the ratio of

the peak height at ~1735 cm^{-1} (ester bond) to the peak height at ~1465 cm^{-1}

(methylene). The FT-IR data was treated using Omnic 8.2.0.387. HT-GPC was used to

determine weight average molecular weight (M_w), number average molecular weight

(M_n), and dW/d(LogM)-Log(M) differential distribution curve in oxidized

polyethylene. The sample was dissolved in trichlorobenzene. The detail method

contained detection temperature 145°C, injection volume 300 μL, elution solution

dichlorobenzene, elution time 50 min, and elution flow rate 1.0 mL/min. GC-MS was

used as a tool for the analysis of end products. GC conditions were a DB-5MS column,

injection rate 1.0 ml/min, initial temperature 40°C, ramped up from 40°C to 250°C at

a rate of 10°C min^{-1}, and a 4-minute maintenance. The MS conditions involved

molecular weight detection range 33-450, an ion source temperature 70°C, and an

electron energy 70. DSC was used for achieving melting temperature (T_m). The

temperature ramped form 30°C to 300°C at a rate of 10°C min^{-1}. All data was treated

and drawn using R.

Random forest machine learning optimizes degradation systems

Machine learning was performed using the package randomForest, and GenSA was

used for optimal solution solving in R. Independent variables included EBI, pH,

degradation days, temperature, amount of enzyme addition, rotational speed, the type

and concentration of additives, with the dependent variable being the weight loss rate.

Among them, temperature, amount of enzyme addition, and rotational speed were

taken as a logarithm for a better fit. Analysis of the input data was accomplished

through the use of the vivid package, including Variable Importance, Variable

Interactions, partial dependence plot (PDP), and individual conditional expectation

Curves (ICE) curves[25]. The optimal conditions were analyzed using Shaply. All the

code for random forests has been placed in supporting information.

Result and discussion

The preparation of cutinase and lipase

In order to determine the versatility of the degradation systems, two extensively

researched cutinases and lipases were chosen for this study, mainly including *Tf*Cut,

*Is*PETase, TLL, and HiC. These enzymes were selected due to their distinctive

features, particularly the variance in substrate binding grooves and charge distribution

(shown in Fig. 1). For the former, *Tf*Cut and *Is*PETase prossess open tunnels without

significant site resistance at entry and exit points, making them more suitable for

binding medium- and long-chain substrates. This aligns with their capacity to degrade

ester bonds within the main chains of large molecules such as poly (ethylene

terephthalate) [16, 24] and poly (butylene adipate-co-terephthalate)[17]. Conversely, TLL

and HiC exhibit substrate-binding grooves with greater site resistance, aligning with

the ability to degrade ester bonds in the side chain such as poly (methyl acrylate) and

poly (ethyl acrylate)[22, 26] For the latter, *Is*PET and HiC are predominantly positively

charged near the active site, whereas *Tf*Cut and TLL are characterized by negatively

charged.

The enzymes were produced using *E.coli* BL21(DE3) or *P. pastoris* KM71. All

enzyme were concentrated and analyzed through ammonium sulfate precipitation and

SDS-PAGE. According to pre-laboratory, the concentrations of NH_4SO_4 were

determined to be 30% (w/v), 50%, 50% and 40% for *Tf*Cut, *Is*PETase, TLL and HiC,

respectively. The result of the SDS-PAGE analysis are presented in Fig S1. Greyscale

analysis using Image-J, the percentages of the four enzymes were 73.15%, 41.95%,

63.49%, and 74.61%. The specific enzyme activity (pNPB as substrate) of them were

52.5, 3.5, 456.6, and 5.0U mg^{-1} of enzyme powder for TfCut, IsPETase, TLL, and HiC,

respectively. In comparisons with substrates of different carbon chain lengths (pNPO,

pNPL, pNPM, pNPP), TfCut exhibited enhanced affinity for long-chain substrates

when compared to the other enzymes, as demonstrated in Fig S2.

Preparation and properties of oxidized polyethylene

^{m}CPBA catalysis Baeyer-Villiger oxidation to introduce ester bonds into the main

chain of PE[18, 19]. This reaction transforms the more resistant carbon-carbon single

bonds into readily reactive ester bonds. Subsequent to ^{m}CPBA oxidization, FT-IR

analysis (Fig. 2) indicated that PE_{film} and PE_{pure} can both generate ester bonds, with a

higher ester bonds content in PE_{pure} compared to PE_{film}. However, due to the

stochastic nature of ^{m}CPBA oxidation, different batches of oxidized polyethylene

were used in this study and characterized by EBI value. Table S1 presents the range of

EBI values (1.06-2.11) for the varied batches of oxidized PE examined in this study,

and the FT-IR results of the oxidized PE sample were displayed in Fig S3.

The degradation system for polyethylene film with high molecular weight

To evaluate the feasibility of degradation system, PE_{film} was initially employed as

experimental subjects to establish an aqueous phase system. When utilizing oxidized

PE_{film} as substrate, SDS, PEG400, β-CD, and CTAB were incorporated to enhance the

weight loss ratio. Specifically, the degradation system for PE_{film} comprised 40U mg^{-1}

substrate of TfCut, additive (2% SDS, 10% PEG, 10mM β-CD, or 2% CTAB),

phosphate buffer (pH 8.0), and oxidized PE_{film}. Following an incubating period at 60□

for 7d, the CTAB group exhibited the had highest weight loss at approximately 19.72%

(compared to the control, as illustrated in Fig. 3A). Remarkably, the inclusion of

CTAB in aqueous phase system also resulted in a weight loss of 27.93% in the control

sample. It meant that the phosphate buffer contained CTAB can resolve oxidized

PE_{film}. Compared with other control groups, CTAB demonstrated the most significant

solubilizing impact. The results of particle size distribution (Fig. 3B) revealed that the

CTAB group contained more large particles, consistent with W result. In the FT-IR

results (Fig. 3C and detail data in Fig. S4), the EBIs of the experimental groups were

consistently lower than those of the control group, implying that the presence of TfCut

cleaves the ester bond. Inconsistent with the weight loss rate, the difference in EBI

was not the largest in the CTAB group, possibly due to CTAB's enhanced substrate

solubility. Additionally, the GC-MS results for the enzyme digests dried products

illustrated that the enzyme digests from the experimental groups contained a great

variety of substances, mainly monohydric alcohols, diols, binary acid, and hydroxy

fatty acids, then those of the control group (shown in Fig 3D, and detail data in Table

S2). The results indicated that TfCut catalyzed oxidized PE_{film} into small molecule

fragments. The CTAB group displayed a broader array of substances, underscoring its

efficacy. Overall, incorporating additives enhanced the performance of TfCut, with

CTAB emerging as the most beneficial. It is crucial to emphasize that this section

solely aims to verify the method's capability to process PE_{film} in its pristine state.

Subsequently, the optimization of the degradation system was pursued using PE_{pure} as

W was unsatisfactory with PE_{film} as the substrate. This approach enabled more precise

optimization and eliminated potential interference from plasticizers.[27].

The optimization of degradation system using pure polyethylene with low

molecular weight

To prevent the interference of substances such as plasticisers and antioxidants on the

detection of weight loss[27], PE_{pure} was utilized as the substrate for all subsequent

experiments. The optimization of the degradation system involved refining the type

and concentration of additives, rotational speed, the concentration of enzyme,

temperature, pH, degradation days based on the result of PE_{film}. Additives

encompassed SDS, CTAB, TritonX-100, PEG, betaine, rhamnolipid, α-CD, β-CD, γ-

CD, and DMSO. Following a 7d reaction period, the SDS, CTAB, TritonX-100 group

exhibited the highest weight loss ratio, but the deviation from control group was not

the highest, seeing Fig. 4A. The outcome can be attributed to the superior solubilizing

properties of these surfactants for oxidized PE_{pure} and their impact on TfCut enzyme

activity (particularly SDS and CTAB group, shown in Fig. 4B). In comparison, the

rhamnolipid group displayed the most significant distinction in weight loss rate

compared to the control group, with rhamnolipid exerting a minor influence on the

enzyme activity. Hence, rhamnolipid was identified as an optimal additive for further

enhancement. Subsequently, experiments were conducted to explore the impact of

varying rhamnolipid concentrations from 0.2% (w/v) to 8%. The results (Fig. 4C and

D) showed that a rhamnolipid concentration of 1% yielded the most effective

degradation performance, with minimal influence on *Tf*Cut enzyme activity. To

mitigate the occurrence of the sticky wall phenomenon (seeing Fig S6) and minimize

the impact of shear during the reaction, optimizing the rotational speed during

incubation was deemed essential. Testing rotational speed ranging from 0 rpm to 200

rpm indicated that there was not significant effect on the results, with 200 rpm slightly

increasing the weight loss rate. Subsequently, based reaction factors were optimized,

including temperature (ranging from 50□ to 80□), pH (varied from 7 to 10), enzyme

addition (ranging from 1 U mg^{-1} to 40 U mg^{-1} substrate), and reaction duration

(spanning from 1d to 7d). The results (Fig 5) denoted the optimal conditions as 70□,

pH 9.5, enzyme addition 5 U mg^{-1} substrate, and 1d reaction period. However, it was

observed that *Tf*Cut enzyme activity diminished markedly under the conditions of pH

9.5 or 70°C, with less than 10% enzyme activity retained after reaction. Consequently,

the *W* of oxidized PE did not meet initial expectations under the combined conditions

(Fig 6A). Based on the results of the significance analysis of the machine learning

modelling (see below), the decision was made to lower the temperature instead of

adjusting the pH to ensure optimal weight loss rates. Notably, degradation efficiency

significantly improved using the same substrate at 60°C compared with 70°C (Fig 6B).

Therefore, the optimal degradation parameters encompassed 60□, pH 9.5, enzyme

addition 5 U mg^{-1} substrate, and 1d reaction. The value of *W* was 80.51% under the

optimal degradation conditions.

Machine learning to build models and obtain optimal solutions

Machine learning was utilized to analyze the aforementioned variables and outcomes

through forest simulation[28]. The dataset incorporated details such as the type and

concentration of surfactant EBI, pH, reaction day, temperature, enzyme addition,

rotational speed, and *W*. Certain parameters were logarithmically transformed for

analysis, including temperature, enzyme addition and rotational speed. Before the

modelling stage, the parameters ntree (number of trees to grow) and mtry (number of

variables randomly sampled as candidates at each split) were optimized within ranges

of 200-5000 and 1-8, respectively, through ten sets of repetitions. Following this

screening process (Fig S7), ntree=4600 and mtry=7 was selected as the optimal values.

The model revealed that a correlation coefficient (R^2) of 0.930 for the train set, and

the test set was 0.916 (Fig 7 A-B). Furthermore, importance analyses and optimal

solution calculations (genetic algorithms) were performed. The importance analyses

(Fig. 7C-D, Fig S8) indicted that the surfactant type, EBI values, and pH exerted the

most significant influence on weight loss rate. Notably, temperature is less important

than pH according to importance analyses. This also rationalizes the choice of optimal

conditions in the above process to lower the temperature rather than the pH. The

results of optimal solution calculations aligning with experimental results further

validated this approach (Fig. 7E). Consequently, the identified optimal conditions

were retained for subsequent high-concentration substrate degradation experiments.

Additionally, according to PDP results, EBI and pH have a positive effect on

degrading oxidized PE (Figure S9). The shaply analysis revealed that all variables,

except for ester bond content, had been optimized to enhance degradation efficiency

(as shown in Figure S10). Notably, the uncontrollable nature of ester bond content

highlights the need for further exploration and understanding in future investigations.

Characteristic of degradation products of pure polyethylene at optimum

conditions

After determining the optimal reaction conditions, a higher substrate concentration

(increased from 5g/L to 44g/L oxidized PE$_{pure}$ ID=10) was employed. The value of W

was 60.33%. Various analytical techniques including FT-IR, HT-GPC, GC-MS

(headspace extraction), and DSC were utilized to analyze the composition of the dried

product solids. In Fig. 8A, the products displayed a significant presence of hydroxyl

groups (~3000cm^{-1}), and the ester bond peak was notably lower than oxidized PE$_{pure}$

ID=10(Fig. S3H). Additionally, the weight average molecular weight (Mw) of the

products (Fig. 8B) was found to be reduced to 2522 Da compared to 261564 Da for

PE_{pure}. The melting temperature (T_m) of the products were observed at 51.9 □ and

81.01 □ (Fig. 8C), indicating the presence of both cleaved and uncleaved oxidized

PE_{pure}, significantly below the T_m of PE. For products type, GC-MS results (Fig. 8D)

showed that a higher concentration of dibasic fatty alcohols in both the nylon mesh

intercepts and the enzyme digests dried products. In summary, the results indicated

that oxidized PE_{pure} underwent degraded into smaller molecules, with *Tf*Cut

demonstrating the ability to degrade high concentrations of oxidized PE_{pure}.

Application of other cutinases or lipases in degradation systems

In order to determine the generality of the degradation system, four enzymes were

used to degrade oxidized PE_{pure}, include *Tf*Cut, *Is*PETase, TLL, and HiC. The

rationale behind selecting these enzymes was elucidated in the initial segment of the

results (Fig 1). Each enzyme operated at its optimum temperature during the reactions.

*Tf*Cut and *Is*PETase functioned at 60 □, while TIL and HiC operated at 50 and 60 □.

When degrading oxidized PE_{pure} ID=7, both *Tf*Cut and *Is*PETase exhibited

comparable degradation capabilities. Conversely, TLL and HiC demonstrated inferior

performance to *Tf*Cut at both 50 and 60 □, attributed to the larger active site of *Tf*Cut

and *Is*PETase and the smaller one of the TLL and HiC. Nevertheless, all four enzymes

displayed proficiency in degrading oxidized PE_{pure}, underscoring the effectiveness of

the degradation system.

Conclusion

Building upon previous research, the polyethylene degradation system, which

integrates BV reaction and cutinase hydrolysis reaction, was refined through

optimization. By conducting experimental validation and random forest modelling,

this study identified the optimal degradation conditions parameters: 60 °C, pH 9.5,

enzyme addition 5 U mg^{-1} substrate, and 1d reaction duration. Under these conditions,

the treatment with cutinase resulted in a remarkable weight loss of up to 80.51% of

oxidized polyethylene. Moreover, the functionality of the degradation system was

further refined. For example, validation of its ability to treat up to 44 g/L of

polyethylene oxide with a weight loss of 60.33%, and determination of its versatility

in the face of different types of keratinases or lipases. In conclusion, this research

showcases an effective, efficient and mild degradation process of polyethylene into

long-chain fatty acids or fatty alcohols, with promising implications for polyolefin

biodegradation.

Reference

1. Lear G, *et al.* Microbial abilities to degrade global environmental plastic polymer waste are overstated. *Environ Res Lett* **17**, 043002 (2022).

2. Ali SS, *et al.* Degradation of conventional plastic wastes in the environment: A review on current status of knowledge and future perspectives of disposal. *Sci Total Environ* **771**, 144719 (2021).

3. Tennakoon A, *et al.* Catalytic upcycling of high-density polyethylene via a processive mechanism. *Nat Catal* **3**, 893-901 (2020).

4. Chen SJ, *et al.* Ultrasmall amorphous zirconia nanoparticles catalyse polyolefin hydrogenolysis. *Nat Catal* **6**, 161-173 (2023).

5. Zhang W, *et al.* Low-temperature upcycling of polyolefins into liquid alkanes via tandem cracking-alkylation. *Science* **379**, 807–811 (2023).

6. Jie XY, *et al.* Microwave-initiated catalytic deconstruction of plastic waste into hydrogen and high-value carbons. *Nat Catal* **3**, 902-912 (2020).

7. Conk RJ, *et al.* Catalytic deconstruction of waste polyethylene with ethylene to form propylene. *Science* **377**, 1561–1566 (2022).

8. Chen J, *et al.* How to Build a Microplastics-Free Environment: Strategies for Microplastics Degradation and Plastics Recycling. *Adv Sci (Weinh)* **9**, e2103764 (2022).

9. Sullivan KP, *et al.* Mixed plastics waste valorization through tandem chemical oxidation and biological funneling. *Science* **378**, 207–211 (2022).

10. Yao CY, Xia W, Dou Md, Du Yy, Wu J. Oxidative degradation of UV-irradiated polyethylene by laccase-mediator system. *J Hazard Mater* **440**, 129709 (2022).

11. Lou H, *et al.* Biodegradation of polyethylene by *Meyerozyma guilliermondii* and *Serratia marcescens* isolated from the gut of waxworms (larvae of *Plodia interpunctella*). *Sci Total Environ* **853**, 158604 (2022).

12. Zhang A, Hou Y, Wang Y, Wang Q, Shan X, Liu J. Highly efficient low-temperature biodegradation of polyethylene microplastics by using cold-active laccase cell-surface display system. *Bioresour Technol* **382**, 129164 (2023).

13. Gao R, Liu R, Sun C. A marine fungus *Alternaria alternata* FB1 efficiently

391   degrades polyethylene. *J Hazard Mater* **431**, 128617 (2022).

393 14. Rong Z, Ding ZH, Wu YH, Xu XW. Degradation of low-density polyethylene
394   by the bacterium *Rhodococcus* sp. C-2 isolated from seawater. *Sci Total*
395   *Environ* **907**, 167993 (2024).

397 15. Sanluis-Verdes A*, et al.* Wax worm saliva and the enzymes therein are the key
398   to polyethylene degradation by *Galleria mellonella*. *Nat Commun* **13**, 5568
399   (2022).

401 16. Chen XQ*, et al.* Directional-path modification strategy enhances PET
402   hydrolase catalysis of plastic degradation. *J Hazard Mater* **433**, 128816 (2022).

404 17. Yang Y*, et al.* Complete bio-degradation of poly(butylene adipate-co-
405   terephthalate) via engineered cutinases. *Nat Commun* **14**, 1645 (2023).

407 18. Kong D*, et al.* Chemical-biological degradation of polyethylene combining
408   Baeyer–Villiger oxidation and hydrolysis reaction of cutinase. *Green*
409   *Chemistry* **24**, 2203-2211 (2022).

411 19. Bunescu A, Lee S, Li Q, Hartwig JF. Catalytic Hydroxylation of Polyethylenes.
412   *ACS Cent Sci* **3**, 895-903 (2017).

414 20. Taghavi N, Udugama IA, Zhuang WQ, Baroutian S. Challenges in
415   biodegradation of non-degradable thermoplastic waste: From environmental
416   impact to operational readiness. *Biotechnol Adv* **49**, 107731 (2021).

418 21. Taghavi N, Zhuang W-Q, Baroutian S. Effect of rhamnolipid biosurfactant on
419   biodegradation of untreated and UV-pretreated non-degradable thermoplastics:
420   Part 2. *Journal of Environmental Chemical Engineering* **10**, 107033 (2022).

422 22. Hong R, Su L, Wu J. Cutinases catalyze polyacrylate hydrolysis and prevent
423   their aggregation. *Polymer Degradation and Stability* **159**, 23-30 (2019).

425 23. Zheng Y-Y, Guo X-H, Song N-N, Li D-C. Thermophilic lipase from
426   *Thermomyces lanuginosus*: Gene cloning, expression and characterization.
427   *Journal of Molecular Catalysis B: Enzymatic* **69**, 127-132 (2011).

429 24. Liu Y, Liu Z, Guo Z, Yan T, Jin C, Wu J. Enhancement of the degradation
430   capacity of IsPETase for PET plastic degradation by protein engineering. *Sci*
431   *Total Environ* **834**, 154947 (2022).

433 25. Inglis A, Parnell A, Hurley C. vivid: An R package for Variable Importance
434   and Variable Interactions Displays for Machine Learning Models. *arXiv*,

(2023).

26.   Su L, Hong R, Kong D, Wu J. Enhanced activity towards polyacrylates and
poly(vinyl acetate) by site-directed mutagenesis of *Humicola insolens* cutinase.
Int J Biol Macromol **162**, 1752-1759 (2020).

27.   Krueger MC, Harms H, Schlosser D. Prospects for microbiological solutions
to environmental pollution with plastics. *Appl Microbiol Biotechnol* **99**, 8857-
8874 (2015).

28.   Breiman L. Random Forests. *Machine Learning* **45**, 5-32 (2021).

Fig

Figure 1. The structure analysis of cutinase or lipase, include *Tf*Cut, *Is*PETase,
TLL and HiC. Among of them, A and E was substrate binding groove and charge
distribution of *Tf*Cut, B and F was *Is*PETase, C and G was TLL, D and H was
HiC. The green circle was enzyme active center. For charge distribution, blue
surface was positive charge, and red surface was negative charge. For substrate,
red marked were ester bonds that can be degraded by the above enzyme.

Figure 2. The FT-IR result of PE$_{film}$ and PE$_{pure}$. Among them, figure A was PE$_{film}$,

figure B was PE$_{pure}$, figure C was oxidized PE$_{film}$, and figure D was oxidized

PE$_{pure}$.

**Figure 3. The result of degradation system using oxidized PE$_{pure}$ (ID=3, figure S3
and table S1) as substrate. (A) comparison of weight loss rate of polythene, (B)
changing of average particle size, (C) changing of EBI, and (D) comparison of
products in the enzyme solution. In figure A-C, red column was the control group
and blue column was the experimental group. In figure D, red module was
monoacid, yellow module was binary acid or hydroxy fatty acid, blue module
was diol, and green module was monohydric alcohols. Detail data in Table S2.**

Figure 4. Additive optimization results for degradation systems using oxidized

PE$_{pure}$ (ID=4, figure S3 and table S1) as substrate. Different additives were

screened using weight loss rate (A) and enzyme activity rate (B), and the

concentration of optimal additive (rhamnolipid) was determined using weight

loss rate (C) and enzyme activity rate (D). In figure A and C, red column was the

control group, blue column was the experimental group and the dark blue line

was difference in weight loss rate between control group and experimental group.

In figure D, letters represent analysis of significance using one-way analysis of

variance (ANOVA) followed by SNK (Student-Newman-Keuls; $P \leq 0.05$).

Figure 5. Optimization results for degradation systems using oxidized PE_pure

(ID=5 (red) and 6 (blue), figure S3 and table S1) as substrate about enzyme

addition, temperature, pH, and degradation time. Among them, line represents

weight loss rate and column represents residual enzyme activity.

Figure 6. The oxidized PE_pure degradation results using optimization conditions. The reaction temperature was (A) 70 ℃ or (B) 60 ℃. Among them, red column was weight loss rate and blue column was enzyme activity residual rate. The number in the horizonal coordinate represents EBI value.

Figure 7. Random Forest fit to oxidize PE_{pure} degradation data. The fitting results for the training (A) and test (B) data are shown using R^2. Importance analyses for different factors are shown in C and D. In figure E, optimal degradation conditions were calculated using genetic algorithms.

Figure 8. Characteristic of degradation products of oxidized PE$_{pure}$ (ID=10,

figure S3 and table S1). The result includes FT-IR (A), GPC (B), DSC (C), and

GC-MS (D). In figure A-C, red line and blue line represents PE$_{pure}$ and

degradation products, respectively. In figure D, Blank was a control group liquid,

GT was experimental group solid, and YT was experimental group liquid. red

module was monoacid, yellow module was binary acid or hydroxy fatty acid,

blue module was diol, and green module was monohydric alcohols.

Figure 9. Results of degradation of oxidized PE$_{pure}$ (ID=7, figure S3 and table S1)

using different cutinase or lipases. The number in the horizontal coordinate

represents the reaction temperature.