Upcycling Polyethylene into Poly(3-hydroxybutyrate) via a Chemo-Enzymatic-Microbial Cascade

Demin Kong[a,b,c,d], Wei Xia[a,b,c], Meng Shi[a,b,c], Qisheng Fu[a,b,c], Guiyuan Zheng[a,b,c], Lei Wang[a,b,c*], Jing Wu[a,b,c*]

[a]School of Biotechnology and Key Laboratory of Industrial Biotechnology Ministry

of Education, Jiangnan University, Wuxi, China

[b]State Key Laboratory of Food Science and Resources, Jiangnan University, 1800 Lihu

Avenue, Wuxi, 214122, China

[c]International Joint Laboratory on Food Safety, Jiangnan University, 1800 Lihu Avenue,

Wuxi, 214122, China

[d]School of Food Science and Technology, Jiangnan University, 1800 Lihu Avenue,

Wuxi, 214122, China

* Corresponding author:

State Key Laboratory of Food Science and Resources, Jiangnan University, 1800 Lihu

Avenue, Wuxi, Jiangsu 214122, China.

Phone: +86-510-85327802

Fax: +86-510-85326653

E-mail: jingwu@jiangnan.edu.cn; leiwang_enzyme@jiangnan.edu.cn

Abstract:

Polyethylene (PE) plastics are extensively utilized across agricultural, industrial, and medical sectors owing to their favorable physicochemical properties. However, their chemical stability and escalating production have resulted in severe waste accumulation and environmental pollution. Conventional disposal methods are plagued by resource inefficiency and secondary pollution. While emerging strategies offer promise, physicochemical methods demand harsh operating conditions, and biological routes remain inefficient. This research presents an integrated "chemical pretreatment–biodegradation–upcycling" system that combines the efficiency of chemical catalysis with the sustainability of biological conversion. Ester bonds were introduced into PE via Baeyer–Villiger oxidation, followed by enzymatic hydrolysis using the cutinase from *Thermobifida fusca* WSH03-11 (*Tf*Cut). Specifically, machine learning-aided optimization of reaction conditions and computational redesign of *Tf*Cut enhanced degradation efficiency, yielding a maximum weight loss of approximately 71.19%. The degradation intermediates were bio-converted into poly(3-hydroxybutyrate) (PHB) by the wild-type strain LETBE-HOU, isolated in this study, achieving a concentration of 16.75 mg/L. Multi-omics analysis of LETBE-HOU further revealed the PHB biosynthesis pathway and fatty acid degradation regulation. This work breaks the long-standing reliance on physiochemically-derived degradation intermediates for microbial conversion of PE, establishing a fully circular system that opens new avenues for future research.

Introduction

Polyethylene (PE), the most prevalent member of the polyolefin family, is a high-molecular-weight polymer composed of ethylene monomers connected by carbon-carbon single bonds. Its attractive properties, including abundant availability, low production cost, and favorable physicochemical characteristics, have driven continuous global production expansion. Cumulative output between 1950 and 2017 surpassed 180 million tons, with projections indicating an annual growth rate of 2-5%, potentially exceeding 2.5 billion tons by 2050[1-3]. This escalating production has generated correspondingly large amounts of plastic waste. However, the carbon-carbon bonds in PE exhibit high dissociation energy (about 330-370 kJ/mol), substantially greater than that of natural polymers such as lignin or latex[4, 5]. This exceptional stability renders PE highly persistent in the environment, with estimated degradation timescales of up to 400 years[6]. The convergence of chemical recalcitrance and unabated production growth has intensified waste accumulation and environmental pollution, underscoring the critical need for efficient and sustainable degradation strategies, particularly through advanced biological and catalytic conversion pathways. Current disposal methods for PE predominantly rely on incineration and landfilling, which approaches that present considerable environmental drawbacks. Incineration generates significant secondary pollutants, while landfilling consumes vast tracts of land, requires extended mineralization timelines, and facilitates the continuous release of microplastics. Alternative physicochemical techniques, including pulverization, decrystallization[7], ultraviolet irradiation[8], catalytic cracking[9-11], and microwave-assisted catalysis[9, 10, 12, 13], can decompose PE into alkanes, alkenes, and other chemical products. Despite their high catalytic efficiency, these methods are constrained by operational safety issues and demanding reaction conditions, hindering large-scale implementation. Biological degradation methods, mediated by whole cells[5] or isolated enzymes[14], provide compelling advantages such as mild operating conditions and inherent environmental compatibility. However, they face a fundamental limitation: the recalcitrance of carbon-carbon backbone to direct enzymatic cleavage.

Drawing inspiration from physicochemical processes, where intensive oxidative treatments introduce functional groups and reactive sites into the polymer matrix, a synergistic strategy has emerged(*15*). By combining initial physicochemical pretreatment with subsequent biological conversion, it becomes possible to enhance bioavailability and degradation efficiency of PE(*8, 16-20*). This integrated approach represents a promising and sustainable platform for plastic valorization, aligning degradation performance with green process ideals.

Pretreatment of PE centers on the introduction of polar functional groups into its polymer backbone to enhance degradability. These reactive sites encompass a range of polar moieties, such as hydroxyl, carbonyl, C=C double bonds, and ester bonds(*21*). Among them, ester bonds represent a particularly viable target owing to their well characterized enzymatic cleavage and higher practical feasibility(*21*). Following established approaches(*22, 23*), ester groups can be incorporated into PE via Baeyer–Villiger (BV) oxidation, and subsequent enzymatic hydrolysis by the cutinase from *Thermobifida fusca* WSH03-11 (*Tf*Cut) enables effective depolymerization. Nevertheless, prior studies have not accomplished closed–loop recycling of the resulting degradation intermediates.

Specifically, current research on the valorization of PE degradation products focuses on three main routes: mineralization(*6*), conversion into small molecules(*20*), and biosynthesis of biodegradable polymers(*16, 24*). The microbial conversion of PE degradation intermediates into low-molecular-weight compounds or biodegradable plastics represents a promising route toward efficient and sustainable plastic waste management. However, in most reported cases(*6, 16, 24*), the substrates metabolized by microorganisms are primarily derived from physicochemical degradation processes. To date, the direct reuse of PE biodegradation intermediates remains unreported, underscoring a critical research gap and highlighting the need for integrated processing strategies.

To tackle the challenges outlined above, this work develops an integrated "degradation–upcycling" platform (Fig. 1) that enables the complete biological conversion of PE into the biodegradable plastic poly(3-hydroxybutyrate) (PHB). System performance was

substantially enhanced through machine learning-assisted optimization of reaction

parameters and computational redesign of the key enzyme *Tf*Cut, yielding a notable

weight loss of up to 71.19%. By employing PE degradation intermediates as the sole

carbon source, we isolated a novel wild-type strain, LETBE-HOU, capable of

synthesizing PHB at titers reaching 16.75 mg/L. The degradation efficiency achieved

here exceeds current benchmarks for biological PE degradation systems(*19, 25-28*).

More significantly, this study achieved the first microbial valorization of high-

molecular-weight PE degradation intermediates (>2000 Da), thereby overcoming a

fundamental limitation in a field where only low-molecular-weight fragments from

physicochemical pretreatment were previously considered metabolizable(*6, 16, 24*).

Combined with systematic pathway analysis of PHB synthesis in LETBE-HOU, our

findings provide both mechanistic insights and an engineered platform for sustainable

plastic upcycling.

Result

Pathway for PE conversion to PHB

Prior studies have established that PE can be degraded into fatty acids, fatty alcohols,

α,ω-carboxylic acids, and ω-hydroxycarboxylic acids via BV oxidation and lipase-

catalyzed hydrolysis(*22, 23*). These degradation intermediates serve as precursors for

PHB synthesis(*16*). Building on this foundation, an integrated reaction pathway was

designed for converting PE to PHB, as illustrated in Fig. 1. Previous attempts in this

area have encountered limitations such as marginal weight loss and inability to valorize

degradation intermediates. Specifically, reaction parameters were optimized using

random forest modeling, enzyme stability was improved through virtual screening, and

novel microbial strains capable of transforming PE degradation intermediates into PHB

were isolated. This work establishes a comprehensive and efficient PE recycling system,

successfully demonstrating a bio-based strategy for PE biodegradation and upcycling.

Pre-treatment and degradation of PE via chemo-enzymatic cascade

The BV oxidation of PE was catalyzed by ^{m}CPBA to introduce ester bonds into the

polymer backbone(*22*), converting recalcitrant carbon-carbon single bonds into more

labile ester linkages. Following established procedures(*22, 23*), PE was pretreated with

^{m}CPBA and subsequently degraded using *Tf*Cut. The molecular weight profile and

composition of the resulting degradation products aligned with previous reports(*22, 23*).

Under baseline conditions, $\underline{Tf}$Cut-mediated degradation achieved a weight loss (ΔW) of

approximately 4.34% (Fig. 2a), indicating limited degradation efficiency. However, the

low extent of degradation hindered effective recovery and upcycling of the

intermediates, necessitating strategies to enhance the overall degradation yield.

138 Reaction condition optimization to enhance degradation efficiency

Rational design of enzymatic catalytic systems has been shown to substantially improve

the degradation efficiency of polymeric substrates(*29, 30*). In this study, the TfCut-

based degradation system was optimized through systematic refinement of key

parameters including additive type and concentration, rotational speed, enzyme loading,

temperature, pH, and reaction duration. Single-factor optimization (Fig. 2a,b) identified

the following optimal conditions: 0.60 g/L rhamnolipid (22.04% weight loss), 70°C

(35.37%), pH 9.5 (38.50%), enzyme loading of 5 U/mg substrate (22.14%), and 1-day

reaction time (18.96%).

Random forest modeling was subsequently employed to evaluate the relative

importance of multiple reaction parameters on degradation efficiency, providing a data-

driven foundation for multi-factor optimization. Following dataset preprocessing and

parameter tuning (Fig. S1), the model demonstrated strong predictive performance with

correlation coefficients of 0.930 (training set) and 0.938 (test set) between predicted

and actual values (Fig. S2). SHapley Additive exPlanations analyses (SHAP), variable

importance (vimp), variable interaction (vint), partial dependence plot (PDP), and

individual conditional expectation (ICE) (Fig. 2c and S3) consistently identified pH as

the most significant factor, guiding its prioritization in subsequent experimental designs.

The final optimized system, comprising 0.60 g/L rhamnolipid, 60°C, pH 9.5, 5 U/mg

enzyme loading, and 1-day reaction, achieved a maximum weight loss of approximately

50.04% (Fig. 2d). Macroscopic examination revealed an emulsion-like state in the post-

reaction mixture, indicating substantially improved aqueous solubility of the

degradation products (Fig. 2d).

Comprehensive characterization of the degradation products was performed using

differential scanning calorimetry (DSC), Fourier transform infrared spectroscopy (FT-

IR), high-temperature gel permeation chromatography (HT-GPC), and gas

chromatography–mass spectrometry (GC–MS) (Fig. S4). Compared with previous

reports(*22, 23*), the products exhibited reduced ester bond content, increased hydroxyl

group abundance, lower molecular weight, higher ester bond utilization efficiency, and

greater diversity of liquid-phase compounds. These results indicated that the optimized

*Tf*Cut catalytic system can degrade PE more efficiently, offering greater potential for

recycling.

However, system optimization revealed operational limitations, particularly rapid

inactivation of *Tf*Cut under extreme alkaline conditions (pH 9.5) (Fig. 2 and S5). To

address this constraint, protein engineering was undertaken to enhance *Tf*Cut stability

under high-temperature and high-pH conditions.

Enzyme stability modification for enhancing degradation efficiency

To enhancd enzyme stability, *Tf*Cut was engineered via virtual screening under extreme

conditions (pH 9.5/60°C and pH 9.5/70°C). A combined strategy of static and dynamic

computational analyses (Fig. 3a) was employed to design mutation sites, followed by

iterative combinatorial mutagenesis to characterize mutant properties.

Virtual screening yielded 64 candidate mutants. From static analysis, all PROSS-

proposed mutants were adopted; FIREPROT selected mutants exhibiting lower Rosetta

folding free energy at sites overlapping with PROSS predictions; EMOCPD prioritized

amino acid microenvironment effects, supplementing the design pool with the top 10

highest-scoring mutants not identified by the other methods. This process resulted in

62 single-point mutants. Dynamic analysis results revealed (Fig. S6a,b) that root mean

square fluctuation (RMSF) values for the 173–192 and 203–214 regions were higher

under extreme conditions compared to normal conditions, indicating reduced stability

of these regions in a high-temperature and high-alkaline environment. Virtual saturation

mutagenesis was applied to these regions, and mutants were screened based on reduced

RMSF averages, increased predicted k_{cat}, and decreased ddG, yielding two final

candidates. All single-point mutants from both strategies are listed in Table S1, with

corresponding expression levels validated by SDS-PAGE in Fig. S7.

Experimental screening of single-point mutants (Fig. S8a-c) assessed expression,

specific activity toward *p*-nitrophenylester (*p*NPB), and stability under extreme

conditions. Nine beneficial mutants were obtained, including D174E, D174Q, N28K,

N28P, S197A, E64Q, T89R, P187R, and N212T, with structural representations

provided in Fig. S8d. These were subsequently used for iterative combination

mutagenesis. Screening results (Fig. 3b) and SDS-PAGE analysis (Fig. S9) identified

five advantageous combination mutants: D174E/P187R, D174E/N212T,

D174Q/N212T, D174E/P187R/N212T, and D174Q/P187R/N212T. Enzymatic

properties were summarized in Table S2. Based on comprehensive evaluation of

stability, specific activity, and expression, D174E/N212T and D174Q/N212T mutants

were selected for PE degradation assays.

Degradation performance (Fig. 3c) showed that both mutants exhibited superior activity

under pH 9.5/60°C and pH 9.5/70°C, with D174Q/N212T achieving the highest weight

loss rate of ~66.32%. Furthermore, through more precise temperature and pH control,

the maximum weight loss rate in a 1L reactor was increased to 71.19%.

To elucidate the stability mechanism of the top-performing mutant D174Q/N212T,

constant-pH molecular dynamics (CpHMD) simulations were conducted at

pH 9.5/70°C. Analyses focused on global protein dynamics and local mutation site

effects. Principal components analysis (PCA) and dynamical cross-correlation matrix

(DCCM) analysis of MD trajectories (Fig. 3d-f) indicated that D174Q/N212T adopts a

more compact conformation with enhanced residue–residue correlations, contributing

to its improved structural integrity under extreme conditions. Local analysis revealed

that D174Q lies near the C204–C253 disulfide bond. Dihedral angle analysis (Fig. S10

a,b) indicated enhanced conformational stability of this disulfide in the mutant.

Substitution of Asp with Gln mitigates deamidation and isoaspartate formation under

alkaline conditions, thereby improving stability(*31, 32*). N212T introduces a new

hydrogen bond that remains stable throughout the 100 ns simulation (Fig. S10 c,d),

stabilizing the local α-helix and overall protein fold.

Through systematic enzyme engineering and process optimization, this study achieved

PE degradation efficiency exceeding currently reported biodegradation(*19, 25-28*).

Further work will focus on the upcycling of degradation intermediates.

Screening and assessment of wild-type strains for valorization PE degradation

intermediates

Wild-type strains were screened for their capacity to utilize PE degradation

intermediates as carbon sources. Primary screening employed solid plates

supplemented with Nile red to identify isolates with metabolic activity toward the

intermediates. From this process, 15 wild strains were isolated, with representative plate

cultures shown in Fig. S11. Subsequent liquid culture assays measured OD_{600}, reflecting

growth, and Nile red fluorescence intensity, indicating accumulation of

polyhydroxyalkanoate-like compounds. As summarized in Fig. 4a,b, nine strains

exhibited robust growth, and one isolate (ID 1) showed fluorescence intensity more

than twice that of others. The high-performing strain, designated LETBE-HOU,

demonstrated superior potential for polyhydroxyalkanoate synthesis and was selected

for further analysis. Its growth curve was displayed in Fig. S12.

Polymer production by LETBE-HOU was characterized using confocal laser scanning microscopy (LSCM), transmission electron microscopy (TEM), Fourier-transform infrared spectroscopy (FT-IR), and gas chromatography–mass spectrometry (GC–MS). LSCM (Fig. 4c) revealed bright intracellular fluorescent particles in cells cultivated with PE degradation intermediates (experimental group), indicating enhanced accumulation of lipid-soluble compounds relative to the control group. TEM (Fig. 4d) showed that experimental group cells were larger (1.2 μm) than control group cells (0.5 μm) and contained distinctly visible white granules within the cells, confirming intracellular metabolite accumulation. Microscopic examination revealed that this strain utilized PE degradation intermediates, with metabolic products accumulating intracellularly.

To chemically identify the accumulated product, FT-IR and GC–MS analyses were performed. The FT-IR spectrum (Fig. 4e) displayed a characteristic ester carbonyl absorption at 1730 cm^{-1}, consistent with polyhydroxyalkanoates[33, 34]. GC–MS (Fig. 4f) confirmed the polymer as PHB. Under optimizing conditions (24 h cultivation, 3 g/L degradation intermediates), LETBE-HOU achieved a maximum PHB yield of 15.34 mg/L (Fig. 4g,h), exceeding previously reported values for similar strains[16, 24]. To our knowledge, this is the first reported strain capable of directly converting enzymatically derived PE degradation intermediates into PHB[16, 24]. The strain also efficiently assimilated long-chain fatty acids (Fig. S13), suggesting the presence of specialized transport or metabolic systems—a hypothesis meriting further genomic and transcriptomic investigation.

Genome and transcriptome analysis for LETBE-HOU

To elucidate the PHB biosynthesis mechanism in strain LETBE-HOU, integrated genomic and transcriptomic analyses were conducted. Whole-genome sequencing identified the strain as *Bacillus paranthracis*, with an assembled genome has a total length of 5234090 bp and encodes 5198 genes. The circular genome map and a general summary are provided in Fig. S11 and Table S3, respectively. Functional annotation of the entire genome was subsequently performed using the Kyoto Encyclopedia of Genes and Genomes (KEGG), Gene Ontology (GO), Clusters of Orthologous Groups (COG), Carbohydrate-Active enZYmes Database (CAZy), and Pathogen Host Interactions Database (PHI) databases (Fig. 5a-e). KEGG annotation identified 167 membrane transport-related proteins; GO analysis showed enrichment in Catalytic Activity, Binding, and Transporter Activity within the Molecular Function category; and COG

analysis highlighted numerous genes involved in Carbohydrate transport and metabolism and Cell wall/membrane/envelope biogenesis. These findings indicate a genetic predisposition for efficient transport and catalytic processes. CAZy annotation further identified genes encoding Carbohydrate-Binding Binding Modules (CBMs) and Carbohydrate Esterases (CEs) , which may promote enzyme–substrate association and hydrolyze ester bonds in PE-derived intermediates, respectively. PHI annotation indicated that 13.70% of genes are linked to reduced virulence, supporting the strain's suitability for biotechnological applications. Collectively, multi-database annotation underscores the genomic advantages of LETBE-HOU for PHB production, including efficient transport, catalytic, and binding systems, as well as robust cell envelope biogenesis.

Transcriptomic profiling under PHB-producing conditions revealed 930 upregulated and 1161 downregulated genes in the experimental group (Fig. S15). Gene set enrichment analysis (GSEA) of three PHB-relevant pathways—butyrate metabolism, fatty acid metabolism, and peptidoglycan metabolism—showed upregulation of the butyrate and fatty acid pathways and downregulation of peptidoglycan metabolism (Fig. 5f). Selected gene expression patterns from these pathways are displayed in Fig. 5g. Upregulation of the butyrate pathway, which is directly involved in PHB synthesis, and the fatty acid pathway, supplying key precursors, aligns with elevated PHB production. In contrast, downregulation of peptidoglycan metabolism likely reduces cell wall rigidity, potentially facilitating export of PE degradation intermediates and accommodating cell volume expansion during PHB accumulation. These transcriptomic results corroborate TEM observations and support a model in which LETBE-HOU reprograms its metabolism to efficiently convert PE degradation intermediate into PHB.

Analysis and enhanced of PHB synthesis pathway for LETBE-HOU

Based on genomic and transcriptomic evidence, the PHB biosynthesis pathway in LETBE-HOU was elucidated. Key genes identified include those encoding NADPH-dependent acetoacetyl-CoA reductase (PhaB), 3-hydroxybutyrate polymerase (PhaC), poly-3-hydroxybutyrate inclusion body protein (PhaP), poly-3-hydroxybutyrate-responsive repressor (PhaQ), poly-3-hydroxybutyrate regulator (PhaR), and (R)-specific acyl-CoA hydratase (PhaJ). T Their genomic organization is consistent with previous reports(*35*).Functionally, PhaP and PhaR regulate intracellular PHB stability, while PhaQ modulates PHB metabolic genes. The enzymes PhaB, PhaC, and PhaJ

catalyze PHB biosynthesis.

PHB synthesis primarily occurs through the butyrate metabolism pathway (green region
in Fig. 6a), via two distinct routes: 1) the conventional pathway: acetyl-CoA →
acetoacetyl-CoA → (R)-3-hydroxybutyrate → PHB. Mainly catalyzed by PhaB and
PhaC; 2) the auxiliary pathway: 2-butenyl-CoA → (R)-3-hydroxybutyrate → PHB,
primarily involving the PhaJ and PhaC. Transcriptome analysis revealed that the most
critical gene in this pathway is the PhaC-encoding gene (phaC), showing a 7.33-fold
increase in expression compared to the control group (Fig. S16).

To validate its role, phaC was overexpressed in LETBE-HOU, and PHB production
was evaluated using either untreated or redox enzyme CYP152N1-decarboxylated(36)
PE degradation intermediates. As showed in Fig. 6b,c, phaC overexpression did not
enhance PHB yield with untreated substrates, likely due to insufficient raw material
supply. However, with decarboxylated treatment, the engineered strain produced
approximately 16.75 mg/L PHB, representing a 1.53-fold increase compared to the
wild-type strain. These results confirm that phaC overexpression enhanced PHB
production when precursor availability is sufficient. Further investigation into the
substrate supply pathway (fatty acid metabolism) was required to improve the strain's
utilization efficiency of PE degradation intermediates.

Analysis of fatty acid metabolism for LETBE-HOU

Further analysis of fatty acid metabolism revealed two major inconsistencies. First, a
discrepancy was observed between GC–MS results and the theoretical fatty acid
metabolic pathways. GC–MS analysis confirmed that LETBE-HOU exclusively
produces PHB. In contrast, the canonical fatty acid metabolic pathway suggests that
multiple acyl-CoA products can be converted by PhaJ to 3-hydroxyacyl-CoA, which
PhaC then polymerizes into a mixture of polyhydroxyalkanoates (Fig. 6a). A second
inconsistency was identified between the expression of a key fatty acid metabolism
gene and observed bacterial growth. KEGG annotation identified only one acyl-CoA
hydratase (FadB), whose expression was downregulated by 3.02-fold (Fig. S16). This
downregulation insufficient to support the strain's fatty acid metabolic demands in
oligotrophic media.

Genomic and transcriptomic data mining identified an isoenzyme, acyl-CoA hydratase
YhaR, which shares 27.45% sequence homology with FadB. AlphaFold3-based
structural prediction and hexenyl-CoA docking revealed that that FadB and YhaR adopt
conserved acyl-CoA hydratase folds but differ in active-site geometry (Fig. 7). In FadB,

residue F141 creates a spatial barrier that confers specificity for short-chain acyl-CoAs (carbon chain length <6). In contrast, YhaR possesses an open conformation that accommodates long-chain acyl-CoAs (carbon chain length >6), with residue F137 at the substrate entrance acting as a gatekeeper to preclude short-chain substrates. Transcriptome data (Fig. S16) showed a 3.02-fold downregulation of FadB and a concurrent 7.56-fold upregulation of YhaR. These results support a "dual-enzyme control" model for fatty acid metabolism: YhaR regulates the stepwise conversion of long-chain fatty acids to 2-butenyl-CoA, while FadB precisely controls the degradation flux of 2-butenyl-CoA. This mechanism maintains overall fatty acid degradation rates while channeling 2-butenyl-CoA toward the specific synthesis of PHB.

This dual-enzyme control model provides a theoretical foundation for engineering the fatty acid metabolic. Nevertheless, further validation is required, including validation of the enzymatic functions of YhaR and FadB, investigation of the effects of gene knockout or overexpression on PHB production, and exploring the roles of additional acyl-CoA hydratase isoenzymes.

Discussion

The persistent challenge of PE biodegradation necessitates innovative recycling strategies. While direct microbial or enzymatic degradation of PE remains elusive, this study establishes an integrated, three-stage recycling cascade comprising pretreatment (ester bond introduction), enzymatic degradation (ester bond hydrolysis), and microbial product conversion, thereby achieving the successful upcycling of PE. This system currently exhibits the highest catalytic efficiency reported for biocatalysis(*19, 25-28*). Simultaneously, each stage presents significant opportunities for optimization.

The current pretreatment system, which employs hazardous reagents and operates discontinuously from the subsequent degradation step, is a primary target for improvement. Substituting organic solvents with green alternatives like deep eutectic solvents (DES) and replacing *m*CPBA with enzyme-catalyzed (e.g., CALB) BV oxidation could mitigate environmental and safety concerns.

To address operational discontinuity, further engineering of cutinase—through immobilization, enhancing organic solvent tolerance, and improving stability—could enable a more seamless integration of the pretreatment and degradation stages into a unified, continuous process.

Regarding the PE degradation intermediates conversion stage, the strain LETBE-HOU

requires further optimization to maximize PHB yield. Potential strategies include: engineering cellular morphology and membrane permeability to enhance intracellular PHB accumulation; strengthening substrate transport systems to improve uptake efficiency; expressing exogenous enzymes (e.g., oxidoreductases, esterases) to broaden substrate utilization; and modulating key PHB pathway genes to augment metabolic flux. These modifications are expected to significantly increase the overall conversion efficiency from PE to PHB. Notably, we observed that LETBE-HOU can survive as spores at 60°C, a trait that could be leveraged to facilitate its integration into a consolidated catalytic system encompassing both the pretreatment and degradation stages.

In summary, this work pioneers a novel chemo-enzymatic-microbial pathway for PE upcycling by converting it into the biodegradable polymer PHB, thereby laying a foundational framework for future research in plastic waste management.

Methods

Reagents, strain, and plasmid

Most Chemicals were procured from TCI, Sinopharm or Macklin. The bacterial strains and plasmids used in this study were obtained from previous studies[37] or from our own screening. Detailed information is provided in Supplementary Methods 1.

Enzyme preparation and characterization

The cutinase *Tf*Cut and its mutants were expressed in *Escherichia coli*. The recombinant proteins were purified via Ni-NTA affinity chromatography, and their stability and catalytic efficiency were characterized using model substrates. A detailed protocol is available in Supplementary Methods 2 and 3.

PE Degradation system

The PE degradation process consists of two main stages. The pretreatment stage primarily employs ^{m}CPBA[22, 38], to introduce oxygenated functional groups via simultaneous hydroxylation, carbonylation, and BV oxidation. The subsequent enzymatic degradation stage utilizes *Tf*Cut to hydrolyze the introduced ester bonds. The catalytic conditions for *Tf*Cut, including additive type/concentration, enzyme loading, temperature, pH, reaction duration, and stirring speed, were systematically optimized. Degradation efficiency was primarily quantified by measuring the weight loss of the

402 residual solid material after the reaction. Further details are described in the
403 Supplementary Methods 4 to 6.

Detection of PE degradation products

405 The degradation products were characterized by DSC, FT-IR, HT-GPC, and GC–MS.
406 These techniques were used to determine changes in melting temperature, functional
407 groups, molecular weight, and degradation products, respectively. Detailed
408 methodologies are described in the Supplementary Methods 7 to 11 .

Mutant design and analysis for *Tf*Cut

The computational design of *Tf*Cut mutants was conducted through integrated static
and dynamic analyses. Static analysis was performed using PROSS(*39*),
FIREPROT(*40*), and EMOCPD(*41*). Dynamic analysis combined MD simulations with
virtual screening to identify beneficial mutations. Specifically, CphMD simulations
were first employed to pinpoint structurally unstable regions of *Tf*Cut under operational
conditions (pH 9.5/70°C). These target regions then underwent virtual saturation
mutagenesis. The resulting mutants were evaluated based on root-mean-square
fluctuation (RMSF) analysis, predicted catalytic efficiency (k_{cat}), and folding free
energy changes (*ddG*). To gain deeper mechanistic insights, CphMD simulations were
applied to analyze wild-type *Tf*Cut and its variants, incorporating key interatomic
distance measurements, dihedral angle analysis, principal component analysis (PCA),
and dynamic cross-correlation matrix (DCCM) analysis. Detailed computational
procedures are provided in the Supplementary Methods 12 and 13.

Synthesis, Qualification, and Quantification of PHB

LETBE-HOU was obtained through a screening campaign of wild-type strains to
synthesis PHB. It was pre-cultured in LB medium and subsequently transferred to YSV
medium (containing 1 g/L PE degradation products) for 24-hour cultivation. After
centrifugation, the cell pellet was collected, and PHB was found to be exclusively
accumulated intracellularly. Qualitative analysis of PHB was carried out using FT-IR,
confocal laser scanning microscopy (LSCM), transmission electron microscopy (TEM),
and GC–MS. Quantification was performed by GC–MS. Detailed procedures for
cultivation and analysis are provided in the Supplementary Materials 14 to 18.

Genome and Transcriptome Analysis for LETBE-HOU

Samples for genomic DNA and transcriptomic RNA extraction were prepared by culturing cells in LB and YSV media for 24 h, respectively, followed by centrifugation and immediate flash-freezing. For transcriptomic, the control group was not supplemented with PE degradation products, whereas the experimental group received 1 g/L of these substrates. Both DNA and RNA extraction, as well as quality control, were conducted by Guangzhou GediO.

The genomic data were functionally annotated through GO, KEGG, COG, PHI, and CAZy databases. The complete genome sequence has been deposited in the National Center for Biotechnology Information (NCBI) database under accession number CP176001.

For transcriptome analysis, gene expression levels were quantified using RSEM (v1.2.19)(*42*). Differentially expressed genes were identified and subjected to KEGG pathway annotation and GSEA to elucidate the PHB synthesis pathway and identify key genes involved.

Acknowledgements

This work was supported by the National Key Research and Development Program of China (2019YFA0706900), and Jiangsu Provincial Science and Technology Department Policy Guidance Program-International Cooperation Projects-Innovation cooperation project of "B&R" (No. BZ2020010).

Author contributions

J.W. initiated the project. D.M.K., L.W., W.X., M.S., and G.Y.Z., performed all the experiments, D.M.K. performed the computational work, D.M.K. drafted the manuscript, which was revised and approved by all authors.

Conflicts of interest

The authors declare that they have no conflicts of interests.

References

1. R. Geyer, J. R. Jambeck, K. L. Law, Production, use, and fate of all plastics ever made. *Sci. Adv.* **3**, e1700782 (2017).

2. R. Meys, A. Kätelhön, M. Bachmann, B. Winter, C. Zibunas, S. Suh, A. Bardow, Achieving net-zero greenhouse gas emission plastics by a circular carbon economy. *Science* **374**, 71-76 (2021).

3. A. Mohanty, R. K. Borah, A. P. Fatrekar, S. Krishnan, A. A. Vernekar, Stepping towards benign alternatives: sustainable conversion of plastic waste into valuable products. *Chem. Commun.* **57**, 10277-10291 (2021).

4. C. C. Chen, L. H. Dai, L. X. Ma, R. T. Guo, Enzymatic degradation of plant biomass and synthetic polymers. *Nat. Rev. Chem.* **4**, 114-126 (2020).

5. S. S. Ali, T. Elsamahy, E. Koutra, M. Kornaros, M. El-Sheekh, E. A. Abdelkarim, D. Zhu, J. Sun, Degradation of conventional plastic wastes in the environment: A review on current status of knowledge and future perspectives of disposal. *Sci. Total Environ.* **771**, 144719 (2021).

6. Z. Q. Tang, Y. L. Zhao, Z. S. Wang, X. Liu, Y. Liu, P. Gu, G. Xiao, J. Baeyens, H. Su, Cobalt catalyzed carbonyl functionalization to boost the biodegradation of polyethylene by *Bacillus velezensis* C5. *Chem. Eng. J.* **495**, 153226 (2024).

7. Y. Zhou, J. X. Zhang, Y. X. Zheng, W. Lin, S. You, M. Wang, R. Su, W. Qi, Simple enzymatic depolymerization process based on rapid ball milling pretreatment for high-crystalline polyethylene terephthalate fibers. *Bioresour. Technol.* **416**, 131759 (2024).

8. S. S. Ali, T. Elsamahy, R. Al-Tohamy, D. Zhu, Y. A. Mahmoud, E. Koutra, M. A. Metwally, M. Kornaros, J. Sun, Plastic wastes biodegradation: Mechanisms, challenges and future prospects. *Sci. Total Environ.* **780**, 146590 (2021).

9. W. Zhang, S. Kim, L. Wahl, R. Khare, L. Hale, J. Hu, D. M. Camaioni, O. Y. Gutiérrez, Y. Liu, J. A. Lercher, Low-temperature upcycling of polyolefins into liquid alkanes via tandem cracking-alkylation. *Science* **379**, 807-811 (2023).

10. S. J. Chen, A. Tennakoon, K.-E. You, A. L. Paterson, R. Yappert, S. Alayoglu, L. Fang, X. Wu, T. Y. Zhao, M. P. Lapak, M. Saravanan, R. A. Hackler, Y.-Y. Wang, L. Qi, M. Delferro, T. Li, B. Lee, B. Peters, K. R. Poeppelmeier, S. C. Ammal, C. R. Bowers, F. A. Perras, A. Heyden, A. D. Sadow, W. Huang, Ultrasmall amorphous zirconia nanoparticles catalyse polyolefin hydrogenolysis. *Nat. Catal.* **6**, 161-173 (2023).

11. A. Tennakoon, X. Wu, A. L. Paterson, S. Patnaik, Y. Pei, A. M. LaPointe, S. C. Ammal, R. A. Hackler, A. Heyden, I. I. Slowing, G. W. Coates, M. Delferro, B. Peters, W. Huang, A. D. Sadow, F. A. Perras, Catalytic upcycling of high-density polyethylene via a processive mechanism. *Nat. Catal.* **3**, 893-901 (2020).

12. X. Y. Jie, W. S. Li, D. Slocombe, Y. Gao, I. Banerjee, S. Gonzalez-Cortes, B. Yao, H. AlMegren, S. Alshihri, J. Dilworth, J. Thomas, T. Xiao, P. Edwards, Microwave-initiated catalytic deconstruction of plastic waste into hydrogen and high-value carbons. *Nat. Catal.* **3**, 902-912 (2020).

13. Q. Dong, A. D. Lele, X. Zhao, S. Li, S. Cheng, Y. Wang, M. Cui, M. Guo, A. H. Brozena, Y. Lin, T. Li, L. Xu, A. Qi, I. G. Kevrekidis, J. Mei, X. Pan, D. Liu, Y. Ju, L.

Hu, Depolymerization of plastics by means of electrified spatiotemporal heating. *Nature* **616**, 488-494 (2023).

14. A. Amobonye, P. Bhagwat, S. Singh, S. Pillai, Plastic biodegradation: Frontline microbes and their enzymes. *Sci. Total Environ.* **759**, 143536 (2021).

15. H. Zhou, Y. Wang, Y. Ren, Z. H. Li, X. G. Kong, M. F. Shao, H. H. Duan, Plastic waste valorization by leveraging multidisciplinary catalytic technologies. *ACS Catal.* **12**, 9307-9324 (2022).

16. K. P. Sullivan, A. Z. Werner, K. J. Ramirez, L. D. Ellis, J. R. Bussard, B. A. Black, D. G. Brandner, F. Bratti, B. L. Buss, X. Dong, StefanJ.Haugen, M. A.Ingraham, M. O. Konev, W. E. Michener, J. Miscall, I. Pardo, SeanP.Woodworth, AdamM.Guss, Y. Román-Leshkov, S. S. Stahl, G. T. Beckham, Mixed plastics waste valorization through tandem chemical oxidation and biological funneling. *Science* **378**, 207-211 (2022).

17. N. Taghavi, I. A. Udugama, W. Q. Zhuang, S. Baroutian, Challenges in biodegradation of non-degradable thermoplastic waste: From environmental impact to operational readiness. *Biotechnol. Adv.* **49**, 107731 (2021).

18. J. L. Chen, J. Wu, P. C. Sherrell, J. Chen, H. p. Wang, W. x. Zhang, J. p. Yang, How to build a microplastics-free environment: strategies for microplastics degradation and plastics recycling. *Adv. Sci.* **9**, 2103764 (2022).

19. A. Sanluis-Verdes, P. Colomer-Vidal, F. Rodriguez-Ventura, M. Bello-Villarino, M. Spinola-Amilibia, E. Ruiz-Lopez, R. Illanes-Vicioso, P. Castroviejo, R. Aiese Cigliano, M. Montoya, P. Falabella, C. Pesquera, L. Gonzalez-Legarreta, E. Arias-Palomo, M. Sola, T. Torroba, C. F. Arias, F. Bertocchini, Wax worm saliva and the enzymes therein are the key to polyethylene degradation by *Galleria mellonella*. *Nat. Commun.* **13**, 5568 (2022).

20. R. Wei, W. Zimmermann, Microbial enzymes for the recycling of recalcitrant petroleum-based plastics: how far are we? *Microb. Biotechnol.* **10**, 1308-1322 (2017).

21. D. Kong, L. Wang, Y. Yuan, W. Xia, Z. Liu, M. Shi, J. Wu, Review of key issues and potential strategies in bio-degradation of polyolefins. *Bioresour. Technol.* **414**, 131557 (2024).

22. D. m. Kong, L. Wang, X. Chen, W. Xia, L. Su, F. Zuo, Z. Yan, S. Chen, J. Wu, Chemical-biological degradation of polyethylene combining Baeyer–Villiger oxidation and hydrolysis reaction of cutinase. *Green Chem.* **24**, 2203-2211 (2022).

23. T. Oiffer, F. Leipold, P. Suss, D. Breite, J. Griebel, M. Khurram, Y. Branson, E. de Vries, A. Schulze, C. A. Helm, R. Wei, U. T. Bornscheuer, Chemo-Enzymatic Depolymerization of Functionalized Low-Molecular-Weight Polyethylene. *Angew. Chem. Int. Ed.* **63**, e202415012 (2024).

24. W. A. Wan Mahari, S. H. Kee, S. Y. Foong, T. S. M. Amelia, K. Bhubalan, M. Man, Y. Yang, H. C. Ong, M. Vithanage, S. S. Lam, C. Sonne, Generating alternative fuel and bioplastics from medical plastic waste and waste frying oil using microwave co-pyrolysis combined with microbial fermentation. *Renewable Sustainable Energy Rev.* **153**, 111790 (2022).

25. Z. Rong, Z. H. Ding, Y. H. Wu, X. W. Xu, Degradation of low-density polyethylene by the bacterium *Rhodococcus* sp. C-2 isolated from seawater. *Sci. Total Environ.*

907, 167993 (2024).

26.   S. H.V, R. Bellibatlu, K. M, T. B, Low density polyethylene degrading fungi isolated
from local dumpsite of shivamogga district. *Int. J. Biol. Res.* **2**, 39-43 (2014).

27.   H. Zhang, D. M. Kong, L. Wang, W. Xia, C. Yao, J. Wu, Degradation of UV-
pretreated polyolefins by latex clearing protein from *Streptomyces* sp. Strain K30. *Sci.*
Total Environ. **806**, 150779 (2022).

28.   J. Jin, J. Arciszewski, K. Auclair, Z. Jia, Enzymatic polyethylene biorecycling:
Confronting challenges and shaping the future. *J. Hazard. Mater.* **460**, 132449 (2023).

29.   Y. Zhou, J. X. Zhang, S. P. You, W. Lin, B. Zhang, M. Wang, R. Su, W. Qi, High
terephthalic acid purity: Effective polyethylene terephthalate degradation process
based on pH regulation with dual-function hydrolase. *Bioresour. Technol.* **413**,
131461 (2024).

30.   N. Taghavi, W. Q. Zhuang, S. Baroutian, Effect of rhamnolipid biosurfactant on
biodegradation of untreated and UV-pretreated non-degradable thermoplastics: Part 2.
J. Environ. Chem. Eng. **10**, 107033 (2022).

31.   P. J. Hogg, Disulfide bonds as switches for protein function. *Trends Biochem. Sci.* **28**,
210-214 (2003).

32.   N. E. Robinson, A. B. Robinson, Deamidation of human proteins. *Proc. Natl. Acad.*
Sci. U. S. A. **98**, 12409-12413 (2001).

33.   K. Hong, S. Sun, W. Tian, G. Q. Chen, W. Huang, A rapid method for detecting
bacterial polyhydroxyalkanoates in intact cells by Fourier transform infrared
spectroscopy. *Appl. Microbiol. Biotechnol.* **51**, 523-526 (1999).

34.   Y. Liu, S. B. Huang, Y. Q. Zhang, F. Xu, Isolation and characterization of a
thermophilic *Bacillus shackletonii* K5 from a biotrickling filter for the production of
polyhydroxybutyrate. *J. Environ. Sci.* **26**, 1453-1462 (2014).

35.   J. M. Borrero-de Acuña, I. Poblete-Castro, Rational engineering of natural
polyhydroxyalkanoates producing microorganisms for improved synthesis and
recovery. *Microb. Biotechnol.* **16**, 262-285 (2022).

36.   H. Onoda, O. Shoji, K. Suzuki, H. Sugimoto, Y. Shiro, Y. Watanabe, α-Oxidative
decarboxylation of fatty acids catalysed by cytochrome P450 peroxygenases yielding
shorter-alkyl-chain fatty acids. *Catal. Sci. Technol.* **8**, 434-442 (2018).

37.   X. Q. Chen, Z. Y. Guo, L. Wang, Z. F. Yan, C. X. Jin, Q. S. Huang, D. M. Kong, D.
M. Rao, J. Wu, Directional-path modification strategy enhances PET hydrolase
catalysis of plastic degradation. *J. Hazard. Mater.* **433**, 128816 (2022).

38.   A. Bunescu, S. Lee, Q. Li, J. F. Hartwig, Catalytic hydroxylation of polyethylenes.
ACS Cent. Sci. **3**, 895-903 (2017).

39.   A. Goldenzweig, M. Goldsmith, S. E. Hill, O. Gertman, P. Laurino, Y. Ashani, O.
Dym, T. Unger, S. Albeck, J. Prilusky, R. L. Lieberman, A. Aharoni, I. Silman, J. L.
Sussman, D. S. Tawfik, S. J. Fleishman, Automated structure- and sequence-based
design of proteins for high bacterial expression and stability. *Mol. Cell* **63**, 337-346
(2016).

40.   M. Musil, A. Jezik, J. Horackova, S. Borko, P. Kabourek, J. Damborsky, D. Bednar,
FireProt 2.0: web-based platform for the fully automated design of thermostable
proteins. *Briefings Bioinf.* **25**, 1-10 (2023).

41.   X. Ling, C. Cai, D. Kong, Z. Wei, J. Wu, L. Wang, Z. Deng, EMOCPD: Efficient
Attention-Based Models for Computational Protein Design Using Amino Acid
Microenvironment. *J. Chem. Inf. Model.* **65**, 5758-5770 (2025).
42.   B. Li, C. N. Dewey, RSEM: accurate transcript quantification from RNA-Seq data
with or without a reference genome. *BMC Bioinf.* **12**, 323 (2011).

Fig. 1 | Schematic overview of PE waste upcycling via ester bond activation

The upcycling process comprises four stages: (1) Optimization of TfCut reaction conditions; (2) Enhancement of TfCut stability; (3) Screening of wild-type strains using PE degradation intermediates as the sole carbon source; (4) Functional characterization of the selected strain. Stages 1 and 2 aim to maximize PE degradation efficiency, while stages 3 and 4 enable upcycling of degradation intermediates into value-added products.

Fig. 2 | Optimization of reaction conditions of *Tf*Cut degradation system.

a, Single-factor optimization of additive type and concentration. **b,** Single-factor optimization of temperature, pH, enzyme loading, and reaction time under fixed rhamnolipid concentration (0.60 g/L). **c,** Analysis of random forest modeling for single-factor optimization results via SHAP, vimp, and vint. Independent variables A–F correspond to reaction time, enzyme loading, pH, temperature, rhamnolipid concentration, and additive type, respectively. **d,** Degradation efficiency after multi-factor combinations (left) and macroscopic appearance of the reaction system before and after degradation (right). In the figure, ΔW represents the weight loss rate, and ΔE represents the enzyme activity residual rate, with calculation methods detailed in the Supplementary Methods 7.

Fig. 3 | Computational design and experimental characterization of *Tf*Cut variants with enhanced stability.

a, Integrated computational design combining static analysis (PROSS, FIREPROT, EMOCPD) with dynamic CpHMD simulations (for details, see Supplementary Methods 13 and Fig. S6). **b,** Iterative combinatorial mutagenesis screening. In this figure, point height indicates residual activity after 24 h at pH 9.5 and 70 °C; point size reflects recombinant protein expression level; point color represents specific activity (red, high; blue, low). CM0–CM4 denote combinatorial rounds. **c,** ΔW of pretreated polyethylene by wild-type *Tf*Cut and selected mutants. **d,** Schematic diagram of the D174Q and N212T mutation sites. Among these, D174Q was located near a disulfide bond, affecting its stability, while N212T introduces a new hydrogen bond. For details, see Fig. S10. **e,** CpHMD trajectory analysis (100 ns) of wild-type *Tf*Cut, including PCA and DCCM analysis. **f,** CpHMD analysis of the top-performing mutant D174Q/N212T.

Fig. 4 | Screening of wild-type strains and characterization of metabolites from PE degradation intermediates.

a, Growth status (OD_{600}) of rescreened strains. **b,** Detection of metabolic product yield in strains via Nile red staining fluorescence. **c,** LSCM images of Nile red-stained LETBE-HOU cells. **d,** TEM micrographs of LETBE-HOU cells. In diagram b and c, EG and CG denote experimental and control groups, respectively. **e,** FT-IR spectrum of metabolites extracted from LETBE-HOU. **f,** GC–MS analysis of metabolites: chromatogram showing PHB monomer peak at 4.25 min and internal standard (methyl benzoate) at ~9 min (left) with corresponding mass spectrum (right). **g,** Optimization of cultivation time for PHB production by LETBE-HOU. **h,** Optimization of PE degradation intermediate concentration for PHB synthesis.

Fig. 5 | Genomic and transcriptomic analysis of LETBE-HOU.

a, KEGG pathway annotation. **b,** GO classification. **c,** COG categorization. **d,** CAZy annotation.

e, PHI analysis. **f,** GSEA of selected metabolic pathways: butyrate metabolism (left), fatty acid metabolism (middle), and peptidoglycan metabolism (right). **g,** Expression levels of key genes in butyrate metabolism (left), fatty acid metabolism (middle), and peptidoglycan metabolism (right) pathways. B and S denote the control and experimental group, respectively. All data were detected in triplicate.

Fig. 6 | PHB metabolic pathway in LETBE-HOU and effect of phaC overexpression

a, PHB biosynthesis pathway from KEGG annotation: enzymes encoded by up-, down-, and non-regulated genes are highlighted in red, green, and blue, respectively; heatmap circles show expression levels (green to red: low to high). **b,** PHB production by *phaC*-overexpressing and wild-type strains using untreated PE degradation intermediates. **c,** PHB production by *phaC*-overexpressing and wild-type strains using decarboxylated PE degradation intermediates.

Fig. 7 | Schematic of the "dual-enzyme control" in fatty acid metabolism of LETBE-HOU