Title: A forward-engineered muscle tissue driven soft robotic swimmer

Authors:

W. C. Drennan[1,2]*, O. Aydin[1,2,3], B. Emon[1,2], Z. Li[4], M. S. H. Joy[1,2], A. Barishman[5], Y. Kim[1], M. Wei[5], D. Denham[6], A. Carrillo[5], and M. T. A. Saif [1,2]*

Affiliations:

[1]Department of Mechanical Science and Engineering, University of Illinois at Urbana-Champaign; Urbana, USA.

[2]CZ Biohub Chicago, LLC; Chicago, USA.

[3]Carl R. Woese Institute for Genomic Biology, University of Illinois at Urbana-Champaign; Urbana, USA.

[4]Cullen College of Engineering, Biomedical Engineering, University of Houston; Houston, USA.

[5]Department of Bioengineering, University of Illinois at Urbana-Champaign; Urbana, USA.

[6]Department of Molecular and Cellular Biology, University of Illinois Urbana-Champaign; Urbana, USA.

*wcd2@illinois.edu, saif@illinois.edu

Abstract: The integration of biological actuators with soft scaffolds has led to biohybrid robots including microscale flagellate-like swimmers which generate thrust by waving their flagella-like tails. However, they achieve swimming speeds of only 0.014 body lengths per minute, Reynolds number (Re) $\sim 10^{-3}$, which is much slower than natural flagellates ($O(10^2 - 10^3)$) body lengths per minute). To investigate this, we applied theoretical and experimental methods, including fabrication of a swimmer that converts muscle contractions into large angular tail displacements, reaching swimming speeds of 86.8 μm/s (0.58 body lengths per minute), surpassing low-Re predictions. Swimming dynamics sharply transition from a low-Re ($\sim 10^{-3}$) to an intermediate-Re (~ 0.1) regime when the actuation angle exceeded 4º. We used the swimmer to study the ability of muscle to adapt to mechanical stiffness and the beneficial effects of neuromuscular coculture on muscle development. These insights into mechanical and chemical cues will help optimize future biobots.

Teaser: How are biological flagellate swimmers like *E. coli* and sperm cells so fast? We have built a new biohybrid robot to explore the theory.

MAIN TEXT:
INTRODUCTION

Biohybrid robots have emerged over the past two decades serving as platforms to study the biomechanics of living actuators as well as novel fabrication and control techniques (*1–5*). Several recently developed muscle-actuated robots, ranging in size scale from 10^{-4} to 10^{-2} meters, have allowed for the basic study of locomotion and emergent behaviors (*6–8*). They include biomimetic swimmers resembling jellyfish (*9, 10*), manta rays (*11*), and flagellates (*12, 13*), crawling robots that use structural asymmetry to achieve unidirectional motion (*14–17*), a valveless pumping robot (*18*), and a variety of micromanipulators which function both in (*19*) and out (*20, 21*) of media. They usually consist of cardiac or skeletal muscle interfaced with a soft scaffold (silicone elastomers, hydrogels) and either operate autonomously or receive pacing through electrical or optogenetic stimulation.

Recent studies have focused on the emergence of living tissues in biobots through the introduction of multiple cell types (*3*, *22*), including motor neurons which can interface with skeletal muscle (*12*, *23–26*). A recently developed flagellate-like biohybrid swimmer demonstrated how these cell types can be combined to form a function motor-unit actuator. The skeletal muscle tissue, coupled to the dynamics of on-board motor neurons, was used to actuate the base of a pair of thin tails. Actuation of the tails elicits a propagating wave. The time-asymmetric nature of these waves allows for net thrust at Reynolds number (*Re*) on the order of 10^{-3}. This biobot swam at 0.7 µm/s or 0.014 body lengths per minute, much slower than natural flagellar swimmers, including sperm which swim on the order of 100 body lengths per minute. This motivated us to explore the design space and the associated mechanisms in small-scale biohybrid flagellate-like swimmers that would allow for increased speed. We employ theory, simulation, and experimentation in this work. Note that large scale biohybrid swimmers including a spring-shaped swimmer (*8*) and a cardiac muscle-powered biohybrid stingray (*11*), have been shown to reach relative average velocities of 2.77 and 6.42 body lengths per minute, where the mechanism of thrust generation is different from flagellum-mediated swimming.

Flagellate swimmers operate across a range of flow regimes, including some types of bacteria and algae operating at $Re \sim 10^{-6}$ and sperm operating in the range of $Re \sim 10^{-5} – 10^{-2}$ (*27–31*). These biological swimmers generate thrust by moving their flagella in a planar rowing or three-dimensional corkscrew motion, thereby creating time-asymmetric waves that mediate net propulsion at low *Re*. We are interested in producing a biobot propelled by generating planar waves in a thin elastic tail actuated by periodic, linear and angular displacements at its base. The resultant thrust from these waves can be predicted by a low-*Re*, linearized model of slender body elasto-hydrodynamics (*12*, *32*). Our simulations, using this theory, predict a steep increase in thrust from a boundary condition of large angular displacements at the base of the tail, as compared with increasing translation (*33*). Intuitively, improved speed with increased angular actuation follows from a scaling argument about the bending waves. The amplitude of the bending waves is proportional to the amplitude of the linear displacement of the base of the tail and to the product of the length of the tail and the amplitude of angular displacement. For a muscle tissue that can only contract a fixed percentage of its length, changes to the muscle and swimmer size result in increasing drag which cancels out the benefit from increased translation amplitude. It is possible to introduce a compliant rocking mechanism to translate small amplitude muscle contractions into large amplitude angular displacement of the base of the tail at the expense of a larger force resisting the contraction of the muscle. By doing this, it is possible to increase the amplitude of the bending wave proportional to the length of the tails without changing the size of the muscle.

To take full advantage of an appropriate compliant rocking mechanism, it is also necessary to ensure strong maturation of the muscle tissue. The process by which muscle fibers mature, termed myofibrillogenesis, depends on a number of mechanical and chemical factors (*34*). *Mechanical factors*: During the maturation process, myoblast muscle precursor cells fuse into multinucleated nascent myotubes which stretch out and pull on the surrounding matrix. Based on in vivo study of drosophila abdominal muscles which resemble the cross-striated skeletal muscle of mammals, this pulling generates tension and is necessary for the formation of immature contractile units of actin and myosin (*35*). These immature units undergo spontaneous, calcium dependent twitching, which appears to be necessary for the organization of highly periodic cross-striated sarcomeres, the key force generating units in skeletal muscle. This implies that the mechanical stiffness of the mechanism that serves as an anchor for the muscle needs to be sufficient to allow the muscle tension to develop, and yet compliant enough to allow the muscle to twitch. *Chemical factors*: In vitro studies with the immortalized mouse myoblasts cell line , C2C12, demonstrate that this maturation process requires a reduction in growth factors, which can be achieved by reducing the

94	amount of serum in the media (*36*, *37*). A remarkable finding from in vitro studies of
95	neuromuscular junction (NMJ) formation is that the spontaneous twitching of C2C12 derived
96	skeletal muscle increases in the presence of motor neurons (*23*, *38*). We therefore expect that
97	neurons in the vicinity of a muscle culture will improve muscle maturation as demonstrated by an
98	increase in overall contractility and force, although the underlying mechanism of their cross talk
99	remains unclear as well as the culture conditions necessary to allow for it. We consider both
100	mechanical and chemical factors in the development of our swimming biobot.

101	We present a biohybrid flagellar swimmer that maximizes angular displacement of the base of the
102	tails and improves muscle maturation by offering favorable anchor stiffness and proximity of motor
103	neurons. To our surprise, we find (1) that the speed of the swimmer far exceeds the average velocity
104	(by an order of magnitude) that our model predicts, (2) that the speed shows a transition from low
105	to high values when the tail angle exceeds a threshold value, suggestive of a phase transition, and
106	(3) that muscle maturation is invariant to the history of anchor stiffness such that there seems to be
107	a homeostatic state of the muscle for a given anchor stiffness irrespective of any perturbations in the
108	anchor stiffness during maturation. Our findings offer new insights on biohybrid systems that are
109	essential for their design and an understanding of their emergence.

RESULTS
Biohybrid swimmer design:
Design overview

113	Our novel swimmer is designed to convert muscle contractions into large amplitude angular
114	displacements of a pair of thin tails to generate high amplitude bending waves and propulsion (Fig.
115	1). It is also designed to support muscle maturation through mechanical and chemical cues. The
116	swimmer consists of a soft, polydimethylsiloxane (PDMS) scaffold, a ring of skeletal muscle made
117	from C2C12 mouse myoblasts, and a cluster of mouse embryonic stem cell (mESC) derived motor
118	neurons. The muscle tissue functions as the on-board actuator. The scaffold consists of (*1*) a head
119	with a reservoir for neuron spheroids, (*2*) a compliant mechanism with anchors for a muscle ring,
120	and (*3*) two slender tails. A ring of compacted myoblasts is mounted on the anchors. The ring
121	matures with time while it receives mechanical cues from the compliant mechanism and chemical
122	cues from the nearby neurons on the head. Upon actuation, the muscle contracts, pulling the
123	anchors towards each other which results in translation and angular displacement of the base of the
124	tails. The dynamics of the tails generate net time-averaged thrust ($\langle F_{prop} \rangle$) for the swimmer. For
125	high thrust, we need large amplitude muscle contractions which requires a strong, mature muscle.
126	The compliant mechanism is intended to provide an appropriate mechanical stiffness for optimal
127	muscle maturation and yet sufficient compliance to allow for maximal angular displacement of the
128	tails. The wide head of the swimmer increases drag against swimming but also supports a long
129	muscle strip and minimizes the hydrodynamic interactions between the tails by increasing their
130	separation distance. At low Reynolds numbers, the time averaged velocity of the swimmer, denoted
131	by ($\langle v \rangle$, is the time average of the thrust divided by the total drag on the untethered system γ,
132	given by $\langle v \rangle = \langle F_{prop} \rangle / \gamma$. We approximate the drag on the head (γ_{head}) to be that of a sphere at
133	Stoke's flow with the same projected area in the direction of swimming.

134	At low *Re*, thrust generated by a thin filament comes from the asymmetry between the drag per unit
135	length tangent to the filament ($\zeta_{\parallel}$) and perpendicular to the filament ($\zeta_{\perp}$), such that
136	$F_{prop} \propto (\zeta_{\perp} - \zeta_{\parallel})$ (*32*). From resistive force theory we have that in the limit of the length of the
137	filament to the radius of the filament $L/r \rightarrow \infty$, the perpendicular and parallel drag coefficients are
138	related by $\zeta_{\perp} = 2\zeta_{\parallel}$ (*39*). In our design, where $L/r \approx 90$, we expect $\zeta_{\perp} = 1.6\zeta_{\parallel}$ (*33*). When the tails

are oriented along the direction of swimming, they contribute to the drag of the overall system $\gamma_{tails} = 2L\zeta_{\parallel}$. The overall drag of the system is then $\gamma = \gamma_{head} + \gamma_{tails}$.

Fig. 1. Design for the novel biohybrid swimmer. The amount of curvature in the swimmer tails is exaggerated in these images to convey the idea of a propagating wave. In theory, the optimal speeding speed for a low-*Re* swimmer occurs when the amount of curvature in the tail is approximately one-quarter of a full wave. (**A**) Conceptual design highlighting the role of large angular displacement of the base of the tails for generating large amplitude bending waves and propulsion. The relationship between swimming velocity and tail angle change is derived from numerical simulations of the elastohydrodynamic model of the swimmer. (callout) A conceptual compliant hinge mechanism, whereby the motion of a muscle contracting and relaxing by distance δ creates an angular displacement Δθ at the base of the tail. (**B**) Rendering of the biohybrid implementation of the conceptual design. (callout) The micromolded PDMS realization of the compliant hinge mechanism, whereby the grip is attached to the tail by the thinnest beam which can be fabrication with DRIE and demolded successfully (around 20 μm in our experience).

Muscle tissue design

Anchoring a muscle tissue to a synthetic scaffold requires some type of interface. This could be a direct interface where the muscle fibers and collagen adhere to the scaffold or an indirect interface where the muscle wraps around the scaffold. Forming a direct interface requires providing an anchor for the muscle and collagen to adhere to, which has been achieved with PDMS for various cell types through treatment with oxygen plasma followed by incubation in extracellular matrix (ECM) (*40, 41*). This process of ECM adsorption creates anchorage for the tissue. In our experience, this method is less reliable with muscle tissues, likely because the muscle fibers produce high, localized forces which can overcome the adhesion between the adsorbed ECM and the muscle fibers. In both cases (direct or indirect interface) muscle tissue emerges from a mixture of ECM and myoblasts where the myoblasts collectively compact the matrix around a structure to form a band or a ring (*18, 23, 42, 43*). Muscle maturation is facilitated by spontaneous twitching and tension that are necessary for the formation of cross-striated sarcomeres. Myoblasts compact the gel, approach each other and fuse after contact when multinucleated nascent myotubes emerge. They develop into immature myofibrils with loosely organized actin-myosin structures (*35, 44, 45*). Maturation begins after the tissue compacts. In the case of a muscle ring, the tissue is transferred onto the scaffold before it starts to differentiate. In this study, we opted to form the muscle around pillars since this eliminates the need for a complex system of molds which would go around the scaffold. We found that rings with inner diameter greater than 3 mm could be manually transferred onto the swimmer scaffold consistently.

174	In our scaffold design, the grips are spaced 4 mm apart. For a scaffold thickness of 150 µm, a
175	muscle ring with inner diameter 3 mm will be able to wrap around the grips with only 1.1 mm of
176	slack which gets taken up as the muscle rings continue to compact and mature. Having this slack
177	aids with mounting, whereas too much slack will require more compaction by the tissue before it
178	starts pulling on the grips.

179	For identifying the appropriate stiffness for the muscle grips to support maturation, we recall a
180	previous study that found optimal contractility in muscles anchored between two pillars with an
181	overall stiffness of 2 µN/µm (*23*). The tissues in this study measured around 500 µm in length with
182	a cross-sectional area around 300 μm^2. We hypothesize that this optimal stiffness might scale with
183	the geometry of the tissue. To illustrate, let L_0 be the free distance between the muscle grips. And
184	assume that the muscle shrinks by ΔL while it matures. Also suppose that the grips have a linear
185	spring constant k so that the passive tension in the muscle is $k\Delta L$. The ratio of the tensile stress
186	$\sigma = k\Delta L / A_c$ to the tensile strain $\epsilon = \Delta L / L_0$ is then kL_0 / A_c where A_c is the cross-sectional area of
187	the tissue. Our hypothesis implies that muscles with given kL_0 / A_c will have similar maturity.
188	Keeping this constant with respect to the previous study gives a stiffness of 14 µN/µm per grip for
189	the current swimmer design.

Swimmer tails

191	The swimmer tails attach to the head of the swimmer via a compliant mechanism which translates
192	the muscle contraction into angular displacement. The two tails cancel out each other's thrust
193	normal to the direction of swimming. Like the scaffold head, the tails contribute drag to the system,
194	which at low *Re* can be estimated with resistive force theory (*39*). In the limit $Re \to 0$, and for an
195	arbitrarily slender tail, there exists a difference between the drag per unit length along the tail $\zeta_\parallel$
196	and perpendicular to the tail $\zeta_\perp$. This difference is referred to as drag asymmetry, and it is
197	necessary for the generation of net propulsion at low *Re* (*32*). Because $\zeta_\parallel$ is less than $\zeta_\perp$, the tails
198	contribute the least drag to the overall system when their resting configuration orients along the
199	direction of swimming. During development, the muscle generates tonic tension, pulling the tails
200	towards the middle of the swimmer. To compensate for this, the tails are initially oriented 60º away
201	from the muscle. For a 4 mm long muscle which shortens by *4%* of its length during electrical
202	stimulation (*12*), the absolute displacement for each grip (anchoring the muscle) would be roughly
203	80 µm. This displacement of the grips δ_g is converted by the compliant mechanism into linear
204	displacement δ and angular displacement $\Delta\theta$ of the base of the tails (Fig. 1B). For fixed actuation
205	amplitudes and tail cross section, the propulsion generated by the tails is fully determined by their
206	sperm number, *Sp*, which varies with length, actuation frequency, and flexural rigidity. For low *Re*
207	swimmers, propulsion is negligible for *Sp* < 1 and is at a maximum around an *Sp* of 2.1 (*32*). The
208	present swimmer is designed for an *Sp* of 1.4 during 5 Hz actuation.

Motor neurons contribution to muscle performance

210	Evidence has been emerging that in vitro muscle matures better in coculture with motor neurons,
211	potentially due to interaction mediated by mutual chemical cues. Neurons extend neurites towards
212	the muscle, some of which may form neuro-muscular junctions. A study of the abdominal muscles
213	of drosophila, which resemble the cross-striated skeletal muscle in mammals, found that tension
214	within nascent myotubes precedes and is required for their development into immature myofibrils.
215	These immature myofibrils exhibit calcium dependent twitching, and this twitching appears
216	necessary for the self-assembly of organized, cross-striated sarcomeres (*35*). Studies have found
217	increased spontaneous twitching in skeletal muscle in the presence of motor neurons. Aydin et al.

(2020) developed a platform for the fabrication of C2C12 derived muscle tissues in the presence of mESC derived motor neurons. They observed preferential outgrowth of neurites towards the muscle, higher spontaneous contractility and a 60% higher ratio of cross-striated myofibers to immature myotubes in co-cultured samples. Andersen et al. (2020), developed a system for culturing cortical, spinal, and muscle organoids together. Several times more spontaneous twitching events were observed in the muscle in the presence of the spinal organoid, although the variability was high sample to sample. Transmission electron microscopy images of the multi-organoid samples show highly organized, cross-striated sarcomeres, which is evidence of maturity.

To improve maturity of the swimmer muscle through neuronal signals, we dispense mouse stem cell derived motor neurons on a PDMS holder affixed to the head of the swimmer. The holder also increases the rigidity of the head against bending and buckling out of plane. We fill the holder with mouse embryonic stem cell (mESC) derived motor neuron spheroids.

The holder keeps the motor neurons around 1 mm away from the muscle tissue to avoid any contact between neuron and muscle cell bodies. Studies have shown that spheroids of motor neurons in contact with skeletal muscle tissue form localized, functional neuromuscular junctions (*24*, *46*), resulting in weak, localized muscle activity. In contrast, neurons positioned away from the muscle formed NMJs and exhibited robust tissue-wide contraction (*23*, *47*). In our design, ECM is used to bridge the gap between the motor neuron spheroids and the muscle. Neurites extend through the ECM bridges towards the muscle while the holder prevents the neuron spheroids from slipping onto the muscle during or after placement (Fig. 1B). When ECM is deposited around a muscle tissue, we observe that the muscle tissue pulls the ECM towards itself over several days. In addition, when motor neurons innervate muscle, they build up tension in their axons (*48*). Without mechanical anchorage, this force might pull the neurons into the muscle should innervation occur.

Implementation and characterization:

Scaffold fabrication and calibration

The scaffold is molded in a PTFE coated microfabricated silicon mold. The neuron spheroid holder is cast in a separate SLA printed resin mold and is attached to the scaffold with liquid PDMS. For the purpose of analyzing its deformation response, the swimmer scaffold has been sub-divided into four components: the grip, the coupler, the beam, and the head (Fig. 2A). The mechanical stiffness cue experienced by the muscle is measured by pulling the grip of the swimmer scaffold with a tungsten wire with known spring constant (0.43 µm/s, Fig. 2B). The displacement of the head (x_1), bending of the small segment of the tail connecting the head and the coupler (x_2), the stretching of the coupler (x_3), and deformation of the grip itself (x_4) all contribute to the compliance felt by the muscle. Note that the bending of the tail near the base gives rise to the desired angular displacement (Fig. 2C). Initially, a sacrificial support attaches the grips to the head of the swimmer, resulting in an overall stiffness of 1.83 µN/um per grip, behaving linearly up to 400 µN. When the sacrificial support is removed, stiffness drops to 1.75 µN/µm at each grip at small deformations. The stiffness decreases with increasing deformation, dropping to 0.97 µN/µm at 400 µN, i.e., the grip behaves as a softening spring (Fig. 2D). If the grips are released several days after mounting, then the muscle is subjected to a sudden drop in stiffness during maturation followed by further softening of the grips. We show that muscle reaches similar maturity regardless of when the sacrificial support is released, indicating that muscle maturity is invariant to the stiffness history of the anchor. The effect of such change in stiffness during muscle maturation has never been explored before. We discuss this in detail in a following section. The rate at which the tail undergoes angular displacement with respect to the muscle exhibits slight nonlinearity, beginning at around 0.09°/µm when $x_4 = 0$ and decreasing to 0.05°/µm when $x_4 = 400$ µm (Fig. 2E). This drop in the angular displacement rate works against

the expected swimmer performance, since after maturation muscle already shows a steady grip displacement of $330 \pm 29\,\mu m$ (n = 20, ±SEM). The reason for this appears to be the moment induced by the coupler on the tail hindering its ability to twist with respect to the head.

Fig. 2. Calibration of the PDMS swimmer scaffold. (**A**) Schematic of the swimmer scaffold decomposing the overall system into four compliant components. (**B**) Diagram of the setup for calibrating the PDMS scaffold with respect to the stiffness of a tungsten needle (0.43 µN/µm) with a hypodermic needle acting as a reference. (**C**) Diagram of the compliant components of the scaffold. The head and the beam contribute to the angular displacement of the tail. (**D**) Force-displacement relationships for the components of the scaffold. (E) Tail angle-displacement relationship which applies to contraction of the muscle.

Timeline for biological component assembly

The timeline of the fabrication and assembly of the biological components of the swimmer appears in Fig. 3. The muscle ring fabrication and mounting process (Fig. 3C) are shown in Supplementary Video 1. During mounting, sacrificial supports attach the grips to the head of the swimmer. They offer rigidity against grip displacement and facilitate mounting of the muscle. In order to initiate C2C12 myoblast fusion into nascent myotubes, the concentration of serum in the media is reduced, following the protocol in Olson (1992).

Fig. 3. Timeline for the fabrication and assembly of the biological components of the swimmer. (**A**) Overall timeline for the biological components. Some preparation steps occur beforehand, including the expansion of a culture of C2C12 myoblasts and the differentiation of mouse embryonic stem cells into motor neuron spheroids (see Materials and Methods). (**B**) Ring molds used for casting the muscle tissue rings. (**C**) Renderings of the steps involved in mounting the muscle rings on the scaffold. Callouts show

tweezer placement necessary to put the muscle into the grips without causing damage. (**D**) Renderings of
the steps involved in mounting the motor neuron spheroids in the head of the swimmer. A hydrophobic
parafilm substrate keeps the ECM from flowing away. (**E**) Photograph of the swimmer with callouts
showing the live imaging of the growth of neurites towards the muscle and confocal images of α-actinin
assembled into sarcomeres (white chevron) localized in the middle of the muscle tissue taken after fixing.
The neurite GFP signal indicates expression of the Hb9 motor neuron specific promoter, although other
types of neurons are present in the neurospheres due to imperfect differentiation efficiency. The photograph
of the swimmer was post-processed by darkening the background around the edge of the PDMS scaffold to
help the clear rubber body stand out.

Muscle maturation is unaffected by the history of the stiffness of the anchor

Although the circumference of the muscle is long enough to wrap around the anchors without
deforming the scaffold, in practice, the tissue possesses some rigidity and resists being stretched
out. It exerts around 100 µN of force on the anchors following mounting. On day in vitro (DIV) 2,
the swimmers are placed in low serum (2% HS) differentiation media. Over the following two
weeks, the muscles continue to compact, developing tonic tension against the anchors. In the
presence of the sacrificial supports (Fig. 5A) when the compliance of the head, the tail and the
coupler are turned off, the muscle is subjected to a stiffness of 1.9 µN/µm per grip (Fig. 4A, 4B).
After the supports are cut, the stiffness drops. The amount it drops depends on the force in the
muscle. On DIV 3, cutting the supports drops the stiffness to 1.5 µN/µm per grip. On DIV 6 or 9,
the stiffness drops to 0.8 µN/µm per grip. We wanted to know if the time history of the stiffness felt
by the muscle would have a long-term effect on the rate and extent of the build-up in tension in the
muscles. To test this, three groups of swimmers were prepared with muscle rings (no neurons). The
sacrificial supports were cut 1, 4, and 7 days after starting differentiation media (DIV 3, 6, 9). The
length of the muscle is measured with respect to the points joining the grips and the couplers (x_3 to
x_3) (Fig. 4C).

When the sacrificial supports are cut, the muscles shorten and their tonic force drops (Fig. 4D,E).
The muscles rebuild this tension within a day (Fig. 4Ei,ii). Throughout the development process,
the lengths and tonic force of the muscles in the different groups follow a similar course. Before
DIV 5, the overall stiffness felt by the groups varies by less than 25%, which may contribute to this
similarly. However, even on DIV 8, when the stiffness varies by 90% between the samples with the
without the sacrificial supports, the tonic force in all the samples is insignificantly different. Except
on DIV 4 and on DIV 9 after cutting the supports in the DIV 9 release group, the tonic force in all
the samples is insignificantly different. The different anchor stiffnesses do not appear to affect the
tonic force development, and the variation in the time history of the stiffness felt by each of the
muscles does not appear to have left a lasting effect on tonic force or length of the muscles. This
might be the result of a homeostatic state of tension that the muscle arrives at during maturation,
independent of the support stiffness and corresponding force history. On DIV 11, when the muscles
would be used for swimming, the average tension in all of the muscles was 498 ± 8.5 µN (n = 10,
mean $\pm$ SEM).

Fig. 4. Contraction and tonic force increase of the muscle during development. (A) Schematic showing the change in scaffold geometry following removal of the sacrificial supports. (B) Force-displacement curves showing the stiffness measured from x_3, the junction between the grip and the coupler before and after cutting the sacrificial supports. (C) Diagram defining how the contraction of the muscle is extracted from bright field images. (D,E) Tracking the variation in the contraction and tonic force of the muscles when their sacrificial supports are removed at DIV 3, 6, and 9. Statistics indicate the results of one-way ANOVA statistical tests comparing the percent of initial lengths of the muscle of the three groups (** = p-value < 0.01, * = p-value < 0.05, n.s. = p-value > 0.05). For DIV 6 and 9, statistics reflect length

measurements taken one hour after the removal of the sacrificial supports. By DIV 9, after cutting the sacrificial supports on the last group of samples, large variation among the muscle lengths contributes to the groups being indistinct from one another (p-value > 0.05 by one-way ANOVA). (Ei,ii) insets for change in force following release on DIV 6 and 9. Exponential curve fits give approximate time constants of 4.5 and 5.8 hours for recovery of the force during the first day after release.

Starting between DIV 6 and 8, the muscle rings tend to exhibit small amplitude, spontaneous twitching. This indicates that immature myofibrils or matured cross-striated myofibers have developed. To increase the amount of spontaneous twitching, motor neuron spheroids are added on DIV 8. To do this, the swimmers are placed on wax paper, excess media is aspirated, and the motor neuron spheroids are added to the holder on the swimmer's head (Fig. 3D). Next, the neurons and muscle are covered with ECM. This protects the muscle and neurons from drying out while the ECM polymerizes. When the swimmer is lifted away from the wax paper, some ECM stays attached to the narrow gaps between the muscle and the holder, while excess ECM sticks to the wax paper and tears off. Over the next two days, loose ECM gets pulled into the muscles by the C2C12 cells, and the ECM between the holder and the muscle forms a series of tense bridges. Neurites grow along these bridges towards the muscle (Fig. 3E). By DIV 8, swimmers with neurons tend to exhibit strong, spontaneous twitching on the order of $1.11 \pm 0.27\%$ (n = 9, mean $\pm$ SEM) the length of the muscle. This twitching causes the tails of the swimmer to move enough to see with the naked eye (Supplementary Video 2). As a note, the serum concentration is the same for all samples after DIV 2 (2% HS), but the basal media varies between aneural and cocultured samples with DMEM in the aneural samples and a 50:50 mixture of advanced-DMEM/F-12 and Neurobasal Plus media in the cocultured samples.

Concerning the long term stability of the swimmers, it is found that beyond two weeks, the performance of the swimmers declines until they no longer respond to electrical stimulation. One contributing factor to this decline is likely the persistent proliferation of C2C12 inside the muscle tissue, acting to increase its compressive stiffness without adding to the functional muscle fibers. Another factor may be the excretion of cysteine proteases by the C2C12 cells, leading to the breakdown of the tissue. Previous studies have shown that culturing muscle with E-64, a broad-spectrum cathepsin inhibitor, can extend the lifespan of C2C12 tissues to more than 200 days (*49*).

Motor neurons increase spontaneous and evoked muscle contraction

By DIV 10, swimmers with and without neurons tend to reach their peak dynamic contractility in response to electrical stimulation. Muscle contractility is measured as a percent change in the muscle's resting length (Fig. 5A). The amplitude of spontaneous and evoked twitching is compared between swimmers with and without neurons (Fig. 5B). On DIV 10, only 4 of 11 swimmers without neurons exhibit spontaneous twitching, as compared to all 9 of the swimmers with neurons. During electrical stimulation, the swimmers with neurons contract 4.2 times more than the swimmers without neurons on average. Contractility is observed to increase with increasing voltage up to 5 V/cm (Fig. 5C). However, voltages above 3V/cm are sometimes observed to excite prolonged, spontaneous twitching, which hampers our ability to turn off the movement of the swimmer. Contractility at low frequency is around 2.8% of the muscle length (Fig. 5D). At stimulation frequencies above 4 Hz, the muscle is unable to fully relax before the next pulse, resulting in tonic contraction and decreased actuation amplitude.

We used motor neurons expressing ChR2, a light sensitive ion channel which opens in the presence of blue light (465 nm) and induces the neurons to depolarize (*50*, *51*). At DIV 10, the swimmer samples with neurons were subjected to blue light using the setup from Aydin et al. (2019). In previous studies, stimulation of optogenetic motor neurons has been able to cause global

depolarization of an associated muscle tissue (*12*). In those cases, this may have been due to widespread innervation of the muscle by the neurons or due to gap junction (found in immature skeletal muscle) between the myofibers capable to transmitting the wave of depolarization (*52*, *53*). In our samples, there were no significant changes in the spontaneous twitching pattern of the muscles during or after optical stimulation of the neurons, nor in the amplitude of contraction of the muscle. This suggests that any NMJs that might exist are too few in number or too immature to cause the global depolarization of the tissue observed in other studies. It is worth noting that the neurons only contacted a small area on one side of the 0.8 mm^2 thick muscle tissues. The total volume of neurons measures on the order of 1 mm^3 as compared to the volume of the muscle which is around 4 mm^3. We are not able to tell whether the neurites could penetrate into the interior of these muscle tissues.

Fig. 5. Characterization of the spontaneous and evoked contractility of the muscle tissues. (A) Diagram for how the muscle contractility is measured with respect to the resting length of the muscle. (B) Comparison of the spontaneous and evoked contractility of swimmers with and without the inclusion of motor neurons. Statistics refer to t-tests assuming independent samples (*** = p-value < 0.001, n.s. = p-value > 0.05, error-bars indicate SEM). (C) Variation in contractility with increasing electrical field strength for a typical swimmer. Values refer to the mean of the contraction peaks observed when the muscle is stimulated for 4 pulses at 1 Hz for each voltage (error-bars indicate SEM of the peak values). (D) Diagram of nomenclature used to describe muscle contraction. Muscle contraction follows membrane depolarization and calcium influx. And because the refractory period for the depolarization of muscle is 2-3 ms (*54*), the

contractions of a muscle in response to membrane depolarizations can overlap. At low frequency (≤ 5 Hz), a muscle can relax between depolarizations, leading to single isolated twitches. At higher frequencies, the muscle cannot fully relax between depolarizations, leading to a constant shortening referred to as tetanic contraction. The muscle is said to exhibit unfused tetanus. At very high stimulation frequencies (> 20 Hz), the muscle contraction appears smooth and sustained, and the muscle is said to exhibit fused tetanus. (E) Variation in the muscle dynamics with increasing frequency for a typical swimmer. Muscle is subjected to electrical stimulation at each frequency in ascending order, at a field strength of 3V/cm, and with 10 second rest between stimulations. Low amplitude spontaneous twitches (~1%) can be seen interspersed with the evoked spikes. At higher frequencies, the muscle is unable to fully relax between stimulation frequencies and exhibits spontaneous twitching at increased frequency with comparable maximum contraction amplitude (~1%). High frequency and high field strength both tend to excite spontaneous twitching, which may indicate the dysregulation of the calcium cycling in the muscle fibers.

Swimming experiments:

Analyzing swimming velocities

Swimmers exhibiting strong contractility ($>2\%$) to stimulation at 3 V/cm are placed in a dish containing a mixture of coculture media and Percoll (P1644, Sigma Aldritch). The Percoll induces a density gradient, allowing the swimmer, slightly denser than water (1.06 g/mL), to float at a desired height in the media (above the floor and below the air-media interface) due to buoyancy (*55*). Of the twelve swimmers prepared following the timeline in Figure 3, eleven exhibit a response to electrical stimulation, of which six exhibit forward swimming. Swimmer displacement is extracted from videos using an ImageJ template matching plugin (*56*) (Fig. 6A). Points tracked on the body of the swimmer tend to oscillate with the muscle contractions, with the overall path of the swimmer moving along a straight trajectory (Fig 6B). The projection of the swimmer trajectory in the direction of travel is used to extract the velocity of the swimmer before and during electrical stimulation (Fig. 6C). Contraction of the muscle is calculated by tracking a point on the grip with respect to the head of the swimmer and then adding the displacement of the grip due to the tonic contraction of the muscle. At rest, the swimmers are observed to drift at speeds around 1-2 µm/s. This is attributed to convective currents in the media. In the example (Fig. 6B,C), the swimmer moves with a time averaged velocity of 63.6 µm/s, which corresponds to a *Re* of 0.33 (Supplementary Video 3). During each muscle twitch, the base of the tails are subject to an average angular displacement of $4.8\pm0.04°$ with a peak angular displacement rate of $176\pm1.6°/s$ (n = 39, mean $\pm$ SEM).

At higher frequencies, the muscle undergoes tetanus as it is unable to relax between stimulation pulses. The onset of tetanus brings the tails together, giving the swimmer a sudden high velocity kick. Similarly, when the electrical stimulation ends, the release of tetanus allows the tails to move apart, which causes a high velocity kick backwards. These transients are excluded from the calculation of time averaged swimming velocity by only fitting the swimmers position over time from one second after the start of stimulation till the end of stimulation.

443
Fig. 6. Swimming position tracking and analysis. (A) Diagram of the template tracking method employed
to extract the swimmers position and muscle contraction waveforms. (B) 2D projection of the path of a
point on the head of the swimmer before (red) and during (blue) 4Hz electrical stimulation. (C) The
corresponding stimulation, grip displacement, and position of the swimmer during the 4 Hz electrical
stimulation. The position is taken by projecting the swimmer's path onto the direction of travel. Before
stimulation, the swimmer drifts with a small velocity. This is attributed to convective currents in the dish.

Persistent motion of the swimmer

We varied actuation frequency (0.5 to 20 Hz) and measured swimmer dynamics (Fig. 7A-D)
(Supplementary Video 4). At frequencies 5 Hz and below, where the muscle experiences minimal
tetanic contraction, the swimmer appears to reach a steady time-average velocity within a few
cycles. And once the stimulation ends, the swimmer appears to continue moving forward while
decelerating (Fig. 7E*i*). At frequencies ≥ 8 Hz, the initial onset of unfused tetanus causes the
swimmer to move forward rapidly at a speed of 178 ± 16 µm/s (n = 30, mean $\pm$ SEM). Over 1-2
seconds, the swimmer appears to decelerate towards a steady, non-zero time averaged velocity,
which we attribute to the small amplitude dynamic contractions of the muscle (Fig. 7E*ii*). Once
stimulation stops, the muscle relaxes back to its baseline causing the swimmer to move backwards
at a speed of 159 ± 13 µm/s (n = 30, mean $\pm$ SEM) before decelerating (Fig.7E*iii*). Across all
samples during 0.5 Hz stimulation, the muscle length during contractions changes at a peak rate of
1.54 ± 0.10 mm/s and relaxes slower, with a peak rate of 1.31 ± 0.14 mm/s (n = 18, mean $\pm$ SEM).
This may account for some of the difference between the forward and backward velocities of the
swimmer due to tetanus.

We investigated the source of the swimmer's deceleration with a model of ballistic motion which
only accounts for the drag force. Suppose the swimmer has mass m, and experiences drag
proportional to its velocity with a constant drag coefficient γ. And suppose that the swimmer has
some initial velocity v_0 and position x_0 at time t_0. Let $x(t)$ be the position of the swimmer over
time in the lab reference where the fluid is drifting with some small velocity v_{drift}. From the force
balance, $m\ddot{x} = -\gamma(\dot{x} - v_{drift})$. Solving the initial value problem gives

$x(t) = v_0 \dfrac{m}{\gamma} e^{-\frac{t-t_0}{m/\gamma}} + v_{drift}(t - t_0) + x_0$. The characteristic time constant τ for the deceleration is mass

divided drag m/γ. We fit experimentally measured $x(t)$ of the swimmer to the above equation for

the following 3 cases: (i) soon (1 s) after low frequency (0.5 – 5 Hz) stimulation is stopped, (ii) during high frequency (8 – 20 Hz) stimulation when muscle reaches tetanus state with low amplitude contraction, and (iii) soon (1 s) after high frequency stimulation is turned off. The delay of 1 s is to avoid any transient dynamics soon after applying or removing stimulation. All the data in Fig. 7 comes from a single swimmer with a wet mass of approximately 27 mg. Based on the speed of the swimmer at the start of the experiment, the drift velocity v_{drift} is approximately 1.76 µm/s. Each curve fit for each case yields a slightly different value for the time constant τ, with an average value of 2.8 seconds. Using τ = 2.8s, we repeat the fitting to calculate values for v_0 and x_0. Using these values for v_0 and x_0, each of the curves can be nondimensionalized to isolate the first-order dynamics (Fig. 7E).

The velocities seen for this example swimmer range from 10 µm/s to 80 µm/s, which corresponds with $Re \sim O(10^{-1})$. The value of Re can be thought of in terms of a ratio of the contribution of inertial forces and viscous forces in the hydrodynamics of a body. At these intermediate values ($Re \sim 1$), we would expect both the inertial and viscous forces to be present in the propulsion generating mechanism of the swimmer. Whereas viscous forces contribute to propulsion through drag asymmetry of the tails, inertial forces would contribute by imparting momentum to the surrounding fluid. This regime of Re is not considered for flagellate swimmers (*12*, *32*).

For a wet mass of 27 mg, the average time constant of 2.8 s corresponds to a linear drag coefficient of 9.6 mg/s. This is lower than the predicted drag for the two tails, $\gamma_{tails} = 21.6$ mg/s. This is significantly lower than our full prediction of the drag of the swimmer that includes the head drag, γ = 42.6 mg/s (for a projected forward cross-sectional area of 3 mm^2). In the following section, a low *Re* model of the swimmer dynamics is provided with the tail boundary conditions from our experiments. The model is used to predict the swimming velocities. This calculation assumes that the swimmer comes to rest immediately once the propulsion force F_{prop} from the tails is removed, such that the velocity $v(t) = F_{prop} / \gamma$.

498
Fig. 7. Swimming waveforms for a high performing swimmer. (**A**) x-y coordinate plots for the
swimming trajectory of the swimmer at multiple frequencies. (**B**) Electrical stimulation waveforms (3V/cm,
10 ms pulse width). (**C**) Muscle contraction measured from motion of x_3, the junction between the grip and
the coupler. At frequencies above 5 Hz, the muscle experiences significant tetanic contraction. (**D**) swimmer
position calculated by projecting the trajectory in the direction of swimming. At frequencies ≥ 8 Hz, the
onset and relaxation of tetanus gives the position waveform a distinct sawtooth shape. (**E**)
Nondimensionalization of the swimmer dynamics with time constant $\tau = 2.8$s for each of the cases

considered. Background colors refer to time windows in (D). During these time windows, we hypothesize that the dominant force on the swimmer is drag. They include (i) when the muscle is almost motionless, so that the only force exerted on the swimmer is drag, (ii) when the initial propulsion from the onset of tetanus is large compared to the propulsion from subsequent dynamic contractions, and (iii) when the propulsion from tetanus relaxation is large compared to the subsequent, slower muscle relaxation.

Comparison between experimental swimming and low Re simulations

We plot the velocities of our six swimmers as a function of tail angle amplitude. Swimming velocities increase with increasing tail angle across aggregated data from all six swimmers (Fig. 8A). In the case of frequencies which induced tetanic contraction, the tail angle change corresponds with the dynamic contraction and excludes the tetanic contraction (Fig 5D). In some cases, the swimmer was observed to move backwards during stimulation. Across the frequencies tested, peak swimming velocity was observed at 5 Hz. In order to assess agreement with our low *Re* elasto-hydrodynamic model (*33*), swimmer velocities were calculated with drag coefficents γ = 9.6 mg/s and 42.6 mg/s, and experimental muscle contraction waveforms for frequencies in the range of 0.5 to 5 Hz (Fig. 7C) and for $\Delta\theta \in (0°, 8°]$ (see Methods and Materials). Neither drag coefficient yields velocity predictions above 40 µm/s. When considering a single swimmers performance at different velocities, we find model predictions are several times slower than experimental values (Fig. 8B). This suggests more thrust is being produced than predicted by low *Re* dynamics. This increased thrust and speed is likely contributed by inertial effects. The evidence for this comes from the deceleration of the swimmer from any arbitrary initial velocity with a single time constant in the absence of any actuation or external force.

Fig. 8. Comparison between experimental swimmer velocities and predictions from our low *Re* model. (**A**) Aggregated swimming velocities and tail angle changes across all samples (n = 6) against regions corresponding to model predictions generated with the indicated frequencies, tail angle changes, and drag coefficients. Tail angle changes correspond with the dynamic contraction (Fig. 5D) of the input waveform, excluding tetanus contraction. Simulations are run using experimental muscle contractions waveforms as the model inputs. Inputs are scaled to achieve the associated tail angle change. (**B**) Comparison of experimental and predicted swimmer velocities at multiple stimulation frequencies for a single swimmer. The predicted swimming velocities are generated using the experimental muscle contraction for this swimmer as the model input.

DISCUSSION

In this study, we fabricate and test a muscle-powered biohybrid swimmer designed to swim at low *Re* using the non-reciprocal motion of a pair of tails to generate net-thrust. Our design focuses on supporting the maturation of a muscle through mechanical and chemical cues to provide a large input displacement to a compliant mechanism which subjects the base of the tails to angular displacement. When electrically stimulated, swimmers reach velocities two orders of magnitude higher than previous biohybrid flagellate swimmer designs. When stimulation stops, the swimmers are observed to drift forward under their own inertia. Low *Re* elasto-hydrodynamic simulations made to mimic our experiments predict speed around four times slower than are observed. Taken together, our results suggest that inertial forces, expected at intermediate $Re \sim O(1)$, are playing a role in the dynamics generating thrust by our swimmer.

Adaptability of the muscle to attachment stiffness.

The tonic tension in the developing muscles grows at a similar pace irrespective of when the sacrificial supports are removed, with the only significant difference between the three groups being observed on DIVs 4 and 9 following the removal of the sacrificial support in the last group (Fig. 4E). We observed the tonic tension build-up in three groups of muscles over a 2-week period The muscle builds up tonic tension against a constant or softening stiffness. When the stiffness drops due to the removal of the sacrificial support, the muscle quickly contracts to reach the same level of tonic tension it had before the drop. We interpret this as the muscle adapting to its changing environment to reach a homeostatic tension. This tension appears to increase up to DIV 15 before leveling off. A comparable result was observed in Powell et al. (2002) with tissue-engineered human skeletal muscle. On the days between DIV 9 and 14, researchers applied a constant stretch to the muscle, increasing it by 5% every two days. And despite the perturbation, the tonic tension in the muscle stayed in the range of 400 to 600 µN. This is similar to the tonic tension found in our muscles, and by coincidence, our muscle rings and their tissues have similar cross-sectional areas of roughly 1 mm^2. In their case, applying a constant stretch has the effect of increasing the tonic force in the muscle, and the muscle is able to relax and re-establish its homeostatic tension. In our case, the muscles are able to rebuild their tonic tension after drops in tension and changes in stiffness. The drop itself is only 25-90% depending on the day of release, and in all cases, the stiffness less than 14% of the hypothesized optimal stiffness of 14 µN/um. We suspect that for a range of "soft" stiffnesses, the increase in tonic force of the muscle will follow a similar time-course which is robust to changes in the stiffness to other values within this range.

Robustness to changes in attachment stiffness within a range would allow for increased flexibility in the design of biohybrid machines. With the ability to adjust to perturbations in stiffness, muscle-powered machine can be fabricated with sacrificial supports that allow for the system to gradually reach a final configuration. Already, supporting structures are a common element in biohybrid system (*8*, *18*, *58*). Our results do not indicate how different stiffnesses will impact other aspects of the muscle aside from tonic force. A comparison between muscle development on soft and stiff pillars has been attempted before in the context of training in vitro tissue constructs with electrical stimulation (*59*). It was found that the benefits of training with electrical stimulation depended on the anchor stiffness. On a soft pillar, the training leads to increased contractility, but on a stiff pillar, training over multiple days had no improvement over stimulating the muscle for 1 hour on the last day of the test. So, although tonic forces may be comparable for different stiffnesses, the performance of the muscle and its response to other cues may vary with stiffness. In addition, it has been found that muscles cocultured with motor neurons exhibit hypertrophy from chronic electrical stimulation while muscle tissues by themselves do not (*60*). We would therefore suspect that the performance of skeletal muscle and its response to training will depend on anchor stiffness and whether it is cocultured with motor neurons. Such an investigation would benefit from granular

586   tunability of the spring stiffness and traditional measures of muscle maturity including mRNA
587   markers (*60*), sarcomere numbers, and ECM composition (*61*).

Effects of motor neurons on muscle performance

Muscles grown in coculture with motor neurons demonstrate several-fold higher contractility
compared to those grown by themselves (Fig. 5B). Although neurites are observed to grow to the
muscle (Fig. 3E), the improvement to contractility occurs within two days of adding the neurons.
This may be too soon for the formation of mature NMJs, which takes three to five days in vitro (*12,*
62, *63*). Considering the asymmetry between the volume of neurons and the volume of the muscle
(1:4), as well as restrictions on where the collagen bridge connects the neurons to the muscle in our
swimmer design, we suspect that the improvement in muscle contractility is due to chemical cues
from crosstalk between the cell types. In our samples, the neurites were able to sense and grow
towards the muscles, which may have been due to their proximity and the presence of a physical
bridge of ECM between them. Although functional improvement in muscle due to coculture with
neurons has been observed many times, the coculture parameters necessary for this improvement
are unclear, and could be studied with this platform by adjusting the proximity and intermediary
between the muscle and neurons.

Inertia in swimmer propulsion

We observed persistent motion of the swimmer following stimulation, following the onset of
tetanus, and following the release of tetanus. This is evidence of momentum which is not expected
at ultra-low Reynolds numbers. Experimental velocities are 3-4 folds higher compared to
predictions based on Stoke's flow (Fig. 8). This is not surprising since $Re \sim 10^{-1}$ found in our
experiments is much higher than that usually considered in the Stoke's flow regime, for example,
$Re \sim 10^{-3}$ for sperm dynamics (*64–66*). If inertial forces are contributing to the propulsion, this
would mean that the tails of the swimmer are imparting momentum to the fluid. Because the density
of the swimmer is almost identical to the density of the fluid, evidence of inertial drift of the
swimmer (Fig. 7E) suggests inertial drift of the fluid.

These intermediate Reynolds numbers have been examined theoretically in the literature for some
special cases (*67–70*). Their authors looked at the speed of a swimmer with respect to its flapping
Reynolds number $Re_f = \rho_{body} A \omega L / \mu$, calculated from the frequency ω and amplitude A of
actuation, and the body density ρ_{body}. Theoretical studies predict swimming speed proportional to
Re_f^{α} for dense swimmers (body density $\rho_{body} \gg$ fluid density $\rho_{fluid}, \alpha = 1$) and swimmers near
asymmetric boundaries ($\alpha \in \{1/2, 1\}$). In both cases, the introduction of inertia to the propulsion is
continuous with increasing Re. The applicable case to our swimmer is one with swimmer density
similar to the surrounding fluid ($\rho_{body} \, \rho_{fluid}$), which has not been investigated theoretically for the
general case (*69*). However, an analysis was performed for the specific case of a dimer swimmer by
linearizing the Navier-Stoke's equations around $Re \sim 1$ (*71*)

A few biological swimmers have a similar size scale to that of our swimmer, including newborn
tadpoles, however they operate at a higher Re, on the order of 10^2 to 10^4 (*72, 73*). A species of sea
slug called *Clione antarctica* exhibits both non-reciprocal low Re and reciprocal high Re
locomotion. Studies looking at the transition between the two swimming modes have found that
inertial propulsion would arise discontinuously when the amplitude and frequency of the flapping
of the slugs "wings" exceeded a threshold (*74*). They attributed it to a transition through a
hydrodynamic instability. They computed this threshold with respect to the unsteady Reynolds
number $Re_{\omega} = \rho_{body} \omega L^2 / \mu$, which is calculated based on the frequency of flapping ω and the

length scale of the body *L*. It is a measure of how quickly the sea slug flaps its wings. They found that the threshold lies between $Re_\omega \in [5, 20]$, which may be specific to their organism. A more appropriate parameter for our swimmer might be the velocity of the tails during stimulation, which is around 15.5 mm/s at the tip and depends mostly on the muscle contraction speed and less on the stimulation frequency because muscle twitches are self-similar at all frequencies up to the onset of tetanus.

Although our reasons for increasing the input angular displacement to the tails come from low *Re* theory, there are benefits to intermediate *Re* swimming (Fig. 8A). Newborn tadpoles are able to reach velocities in the mm/s to cm/s range by undulating their bodies. With further improvements in our ability to generate large amplitude angular displacements using muscle tissues, it may be possible to design a system which achieves these speeds while remaining at a mm-length scale.

In summary, we demonstrate a novel flagellate-like biohybrid swimmer capable of reaching velocities two orders of magnitude greater than previous flagellar swimmer designs of similar size. The velocities also exceed predictions based on Stokesian flow (low *Re* ~ 10^{-6}). This is attributed to inertial forces contributing to thrust in our swimmers at *Re* ~ 10^{-1}. Higher thrust was achieved by the novel design of the swimmer scaffold which transduces muscle contraction into large angular displacement at the base of the tails. Time average swimming velocity increases sharply with change in the tail angle during muscle contraction. We found that C2C12-derived muscle adjusts its tonic tension towards a homeostatic value, irrespective to the history of stiffness cues it experienced during maturation. This is a critical finding from the study that deserves further investigation to reveal how changing stiffness effects the response of tissue-engineered muscle to other supportive cues, such as electrical, chemical, and mechanical stimulation. Future iterations of the swimmer design may turn towards optimization algorithms involving Finite Element analysis to maximize tail angle change with respect to muscle contractions.

MATERIALS AND METHODS
Swimmer scaffold fabrication and calibration

The swimmer scaffold is molded from polydimethylsiloxane (PDMS, Dow Corning Sylgard 184, 10:1 base to crosslinker ratio) at 60°C for two days using a silicon wafer mold for the head and tails (⟨100⟩ orientation, 500 µm thickness, undoped) and a 3D printed resin mold for the neuron holder. The wafer is patterns with SPR220 and etched to a depth of 155 µm using deep reactive ion etching (DRIE) in an STS Pegasus. It is then coated with PTFE which acts as a release agent that helps with the demolding of PDMS. The resin mold is printed from Clear V4 resin in a Form3 SLA 3D printer with a minimum feature size of around 200 µm. The two components are manually assembled with liquid PDMS and cured at 60°C for two days. The assembled swimmer scaffold is autoclaved in distilled water to drive out monomers and then autoclaved again with a dry cycle to sterilize. The force-displacement relationship at the grips of the scaffold is calibrated in water with respect to a tungsten needle of known length and diameter (Living Systems Instrumentation, Young's modulus 411 GPa, 0.43 µN/µm stiffness). During calibration, the scaffold is adhered to a dish with double sided tape at the edge of where the neuron holder sits.

Skeletal muscle ring fabrication and mounting

Rings of C2C12 mouse myoblasts are fabricated and matured following standard protocols (Z. Li et al., 2019; Mancini et al., 2011). Briefly, P4 C2C12 mouse myoblasts are thawed from cryogenic storage and resuspended in growth media (Gibco's DMEM, 1X GultaMAX, 1X Penicillin/Streptomycin, 10% FBS) and plated at a density of 20k cells/cm^2 in a T75 treated culture flask. The growth media is changed every other day, and the cells are passaged once reaching 50-70% confluency.

Annulus shaped ring molds with inner diameter 3 mm are fabricated from PDMS using from a SLA printed resin negatives. To prevent cell adhesion, the ring molds are incubated in a 1% Pluronic solution (Sigma-Aldrich Pluronic F-127, reconstituted from powder and filtered through 0.22 µm pores) at 20ºC overnight. Afterwards, the solution is removed, and the ring molds are rinsed 3 times with PBS.

A C2C12-ECM mixture is prepared containing 2.5M cells/mL, 2 mg/mL Type I rat tail collagen, and 2 mg/mL Matrigel. The collagen is neutralized with a 7% sodium bicarbonate solution and 10X MEM. Rings are cast from 70µL of the mixture and cured at 37ºC for 45 minutes. The mold is then inundated in growth media. The time when the muscle rings are cast is used to demarcate the start of the count of days in vitro (DIV). The rings are left to compact until DIV 2. The compaction ratio is around 10:1, resulting in rings with cross section 1 mm by 0.5 mm and an inner diameter of 3 mm.

On DIV 2, the rings are mounted on the biobot scaffold as shown in Figure 2. Briefly, the biobot scaffold is fixed to a block of PDMS using insect pins, and places under a stereoscope. The scaffold is inundated with growth media, and the ring is added to the dish. Using two pairs of tweezers, the grips of the scaffold are opened, and the ring is placed inside. Then, the media is changed in all dishes to reduce the chance of infection. The rings are maintained in low serum differentiation media until DIV 18 or until motor neurons are added (Gibco's DMEM, 1X GultaMAX, 1X Penicillin/Streptomycin, 2% HS, 1X ITS). The muscles tend to start responding to electrical stimulation on DIV 6 (monophasic, 10 ms pulsewidth, 3V/cm field strength).

The sacrificial supports connecting the grips to the head of the swimmer are removed using surgical scissors under a stereomicroscope. The scissors cutting into the PDMS causes the grips to twist. The muscle rings tend to survive this step because they can flex along with the grips. Attempts are making tissues with finger-like grips, like those found in (Emon et al., 2021), fail because the adhesion of ECM to PDMS is insufficient to tolerate this torsion. Once the supports are cut, tonic tension in the muscle rings tends to cause one of the grips to twist 90º.

Preparation and seeding of the motor neuron spheroids

The procedure for preparation of motor neuron spheroids from optogenetic mouse embryonic stem cells line ChR2H134R-HBG3 Hb9-GFP is described elsewhere (Aydin et al., 2019; Uzel et al., 2016b). The procedure for adding these spheroids to the swimmer is shown in Figure 2. The swimmers are removed from their mounting pedestals and placed on a parafilm sheet with a 100 µL droplet of media. Spheroids are mixed with the same reconstituted mixture of collagen and Matrigel as the muscle rings. The droplet of media is entirely removed from around the swimmer, and the spheroid-ECM mixture is injected into the neuron holder on the head of the swimmer. An additional 20 uL of ECM is dispensed around the head of the swimmer and the muscle to protect it from dehydration and to form a continuous bridge of ECM from the muscle to the neurospheres. The ECM is cured at 37ºC and 100% humidity for 30 minutes. Next, the swimmers are pinned back onto their mounting pedestals and inundated with coculture media (47% v/v Gibco's Neurobasal Plus Medium, 47% v/v Gibco's Advanced DMEM/F-12, 2% v/v FBS, 1X GlutaMAX, 1X Penicillin/Streptomycin, 1X Gibco's B-27 Plus Supplement, 1X ITS, 0.1 Beta-mercaptoethanol). Loose ECM dislodges, but the ECM surrounding the neurospheres and which has infiltrated itself in the narrow space between the muscle and the head of the swimmer tends to remain intact, forming a bridge. This ECM bridge frequently survives reinundation when the sacrificial supports are still intact. The media is refreshed every other day.

Electric field stimulation and recordings

Typically, for voltages exceeding 1.5V, electrolysis will cause bubbles to form at the electrodes and the pH of the media to shift. However, at sufficiently short pulse-widths, bubbles do not appear to form, and the pH remains stable. In this study we use a maximum pulse-width of 10 ms. Aside from keeping the swimmer healthy, this is important because the formation of bubbles can induce flow in the media which can cause the swimmer to drift. The strength of stimulation is controlled by fixing the voltage across a pair of electrodes normalized by the distance between the electrodes. During stimulation, electrical current passes through the media, and the component which passes through the muscle initiates contraction. The actual voltage drop across the muscle can depend on many factors including the thickness of the tissue and the orientation of the muscle fibers relative to the electrodes.

The performance of the muscle is recorded (Olympus IX81, 2X lens, brightfield, 100fps) subject to electrical field stimulation (monophasic, 10 ms pulsewidth) delivered by a pair of graphite plates (20 mm by 20 mm by 3 mm) positioned on either side of the swimmer. To evaluate swimming performance, a swimmer is placed in a 100x15 mm polystyrene dish (Thermo Scientific, BioLite) containing 30 mL of coculture media and 10 mL of Percoll (Sigma-Aldritch). Using tweezers to break the surface tension, the swimmer is submerged. It is seen to float in the Percoll gradient around 3 mm above the bottom of the dish. The graphite electrodes are placed 4 cm apart to provide clearance for the swimmer. Recordings are taken at 20 or 100 fps, depending on the length of the experiment due to RAM limitations. Additional recordings are taken with a Canon Rebel Ti camera (29.97 fps), which allows for tracking the swimmer over a larger field of view.

Image processing and analysis

Tracking of the head of the swimmer is performed using the template matching plugin in ImageJ. Swimming displacement is quantified by projecting the motion of the swimmer onto its time-averaged swimming trajectory. For a given test, the trajectory may vary with time to account for rigid body rotation of the swimmer which can result from asymmetric thrust generation by the tails. Once the overall motion of the swimmer has been subtracted, the displacements of the grips are tracked from a point on the grip near the coupler.

Low Re elasto-hydrodynamic model simulations

The full details of the elasto-hydrodynamic model simulated in this paper appear in Aydin et al., (2024), and the relevant MATLAB codes are available (https://github.com/wdrennan/Biohybrid-Swimmer-Digital-Assets). A second order accurate, implicit finite difference method is used for simulating the filament dynamics. The simulation takes the heave (x_2) and twist ($\Delta\theta$) of the tails as boundary conditions. These are calculated based on the grip movement at x_3 for the test shown in Fig. 7 using the calibrations shown in Fig. 2E. When simulating the swimming speed for a wider range of angles in Fig. 8A, the $x_3(t)$ waveform for a given frequency is scaled so that the amplitude corresponds with the appropriate twist angle change using these same calibrations. The simulations are run using the experimentally derived drag coefficient ($\gamma = 9.6$ mg/s) as well as the predicted drag coefficient ($\gamma = 42.6$ mg/s). As a note, in the low *Re* model, the thrust depends on the drag asymmetry of the tails, $\zeta_\perp - \zeta_\parallel$. The experimentally derived drag coefficient ($\gamma = 9.6$ mg/s) is smaller than that calculated for the tails ($\gamma = 21.6$ mg/s). This experimental derived drag coefficient contradicts our calculated value of $\zeta_\perp$ and $\zeta_\parallel$. In the low *Re* model, we use the predicted values of $\zeta_\perp$ and $\zeta_\parallel$ to compute the thrust, even when this constitutes a contradiction with the experimental drag coefficient. We assume a PDMS stiffness of 1.9 MPa and use the dimensions of our swimmers tail cross-section of 100 µm wide and 155 µm deep (*13*).

Immunostaining of the muscle rings

For immunofluorescence imaging, samples were fixed in 4% paraformaldehyde (PFA) in phosphate-buffered saline (PBS) overnight at 4°C. The samples were then permeabilized using 0.2% Triton X-100 in PBS and blocked with a solution of 3% bovine serum albumin (BSA) and 5% normal goat serum (NGS) in PBS. Following this, the samples were incubated overnight at 4°C with a rabbit anti alpha-actinin primary antibody (1:250, Abcam #ab68167). After washing the samples five times with PBS (5 minutes each wash), they were incubated with the goat anti rabbit Alexa fluor 568 secondary antibody overnight at 4°C. The next day, samples were washed three times with PBS and incubated with 4′,6-diamidino-2-phenylindole (DAPI) (1:1000, Invitrogen) for 10 minutes, followed by another three washes in PBS. Images were acquired using a Zeiss LSM 700 confocal microscope equipped with an EC Plan-Neofluar 20X/0.5 N.A. objective (Carl Zeiss AG).

Statistical methods

A series of 3-independent sample, weighted, one-way ANOVA tests were used to compare the force and length of the aneural swimmer in each of the three sample populations on each day (Fig. 4D,E). On days where the sacrificial supports were cut, the force and length values measured after cutting were used. P-values are used to reject the null hypothesis that all the swimmer samples come from the sample population. A series of Students two-tailed t-tests assuming independent samples were used to compare the spontaneous and evoked contractility of aneural and cocultured swimmer samples (Fig. 5B). The behavior of a swimmer during inertial drift was characterized by least-square curve fitting with the given exponential function with affine offset (Fig. 7E). The value for v_{drift} is taken by fitting a linear function to the projected swimmer position over time before stimulation began. R^2-values are presented as means $\pm$ SEM for the given groupings.

Supplementary Materials

Supplementary Video 1 – Seeding and mounting C2C12 muscle rings (*3*)

Supplementary Video 2 – The cocultured swimmer samples twitching spontaneously in their petri dishes

Supplementary Video 3 – 4Hz electrical stimulation test of the swimmer sample shown in Fig. 6

Supplementary Video 4 – Frequency sweep test of the swimmer sample shown in Fig. 7 and 8

References and Notes

1. V. A. Webster-Wood, *It's Alive! From Bioinspired to Biohybrid Robots* (Springer, Cham, 2023)vol. 530.
2. R. Desatnik, Z. J. Patterson, P. I. Gorzelak, S. I. Zamora, P. LeDuc, C. Majidi, Soft robotics informs how an early echinoderm moved. doi: 10.1073/pnas.2306580120 (2023).
3. R. Mestre, T. Patiño, S. Sánchez, Biohybrid robotics: From the nanoscale to the macroscale. *Wiley Interdiscip Rev Nanomed Nanobiotechnol* **13** (2021).
4. M. Filippi, O. Yasa, J. Giachino, R. Graf, A. Balciunaite, L. Stefani, R. K. Katzschmann, Perfusable Biohybrid Designs for Bioprinted Skeletal Muscle Tissue. *Adv Healthc Mater* **12** (2023).
5. M. Filippi, M. Mekkattu, R. K. Katzschmann, Sustainable biofabrication: from bioprinting to AI-driven predictive methods. *Trends Biotechnol*, doi: 10.1016/j.tibtech.2024.07.002 (2024).
6. V. A. Webster-Wood, O. Akkus, U. A. Gurkan, H. J. Chiel, R. D. Quinn, Organismal engineering: Toward a robotic taxonomic key for devices using organic materials. *Sci. Robot* **2**, 29 (2017).
7. V. A. Webster-Wood, M. Guix, N. W. Xu, B. Behkam, H. Sato, D. Sarkar, S. Sanchez, M. Shimizu, K. K. Parker, Biohybrid robots: recent progress, challenges, and perspectives. *Bioinspir Biomim* **18** (2023).
8. M. Guix, R. Mestre, T. Patiño, M. De Corato, J. Fuentes, G. Zarpellon, S. Sánchez, Biohybrid soft robots with self-stimulating skeletons. *Sci. Robot* **6**, 7577 (2020).

9. J. C. Nawroth, H. Lee, A. W. Feinberg, C. M. Ripplinger, M. L. McCain, A. Grosberg, J. O. Dabiri, K. K. Parker, A tissue-engineered jellyfish with biomimetic propulsion. *Nat Biotechnol* **30**, 792–797 (2012).

10. A. Balciunaite, O. Yasa, M. Filippi, M. Y. Michelis, R. K. Katzschmann, "Bilayered Biofabrication Unlocks the Potential of Skeletal Muscle for Biohybrid Soft Robots" in *2024 IEEE 7th International Conference on Soft Robotics, RoboSoft 2024* (Institute of Electrical and Electronics Engineers Inc., 2024), pp. 525–530.

11. S. J. Park, M. Gazzola, K. S. Park, S. Park, V. Di Santo, E. L. Blevins, J. U. Lind, P. H. Campbell, S. Dauth, A. K. Capulli, F. S. Pasqualini, S. Ahn, A. Cho, H. Yuan, B. M. Maoz, R. Vijaykumar, J. W. Choi, K. Deisseroth, G. V. Lauder, L. Mahadevan, K. K. Parker, Phototactic guidance of a tissue-engineered soft-robotic ray. *Science (1979)* **353**, 158–162 (2016).

12. O. Aydin, X. Zhang, S. Nuethong, G. J. Pagan-Diaz, R. Bashir, M. Gazzola, M. T. A. Saif, Neuromuscular actuation of biohybrid motile bots. *Proc Natl Acad Sci U S A* **116**, 19841–19847 (2019).

13. B. J. Williams, S. V. Anand, J. Rajagopalan, M. T. A. Saif, A self-propelled biohybrid swimmer at low Reynolds number. *Nat Commun* **5** (2014).

14. G. J. Pagan-Diaz, X. Zhang, L. Grant, Y. Kim, O. Aydin, C. Cvetkovic, E. Ko, E. Solomon, J. Hollis, H. Kong, M. T. A. Saif, M. Gazzola, R. Bashir, Simulation and Fabrication of Stronger, Larger, and Faster Walking Biohybrid Machines. *Adv Funct Mater* **28** (2018).

15. R. Mestre, J. Fuentes, L. Lefaix, J. Wang, M. Guix, G. Murillo, R. Bashir, S. Sánchez, Improved Performance of Biohybrid Muscle-Based Bio-Bots Doped with Piezoelectric Boron Nitride Nanotubes. *Adv Mater Technol* **8** (2023).

16. J. Wang, X. Zhang, J. Park, I. Park, E. Kilicarslan, Y. Kim, Z. Dou, R. Bashir, M. Gazzola, Computationally Assisted Design and Selection of Maneuverable Biological Walking Machines. *Advanced Intelligent Systems* **3** (2021).

17. Y. Kim, Y. Yang, X. Zhang, Z. Li, A. Vázquez-Guardado, I. Park, J. Wang, A. I. Efimov, Z. Dou, Y. Wang, J. Park, H. Luan, X. Ni, Y. Seong Kim, J. Baek, J. Jaehyung Park, Z. Xie, H. Zhao, M. Gazzola, J. A. Rogers, R. Bashir, Remote control of muscle-driven miniature robots with battery-free wireless optoelectronics. *Sci Robot* **8** (2023).

18. Z. Li, Y. Seo, O. Aydin, M. Elhebeary, R. D. Kamm, H. Kong, M. T. A. Saif, Biohybrid valveless pump-bot powered by engineered skeletal muscle. *Proc Natl Acad Sci U S A* **116**, 1543–1548 (2019).

19. Y. Morimoto, H. Onoe, S. Takeuchi, Biohybrid robot powered by an antagonistic pair of skeletal muscle tissues. *Sci Robot* **3**, 4440 (2018).

20. Y. Morimoto, H. Onoe, S. Takeuchi, Biohybrid robot with skeletal muscle tissue covered with a collagen structure for moving in air. *APL Bioeng* **4** (2020).

21. Y. Akiyama, T. Sakuma, K. Funakoshi, T. Hoshino, K. Iwabuchi, K. Morishima, Atmospheric-operable bioactuator powered by insect muscle packaged with medium. *Lab Chip* **13**, 4870–4880 (2013).

22. O. Aydin, A. P. Passaro, R. Raman, S. E. Spellicy, R. P. Weinberg, R. D. Kamm, M. Sample, G. A. Truskey, J. Zartman, R. D. Dar, S. Palacios, J. Wang, J. Tordoff, N. Montserrat, R. Bashir, M. T. A. Saif, R. Weiss, Principles for the design of multicellular engineered living systems. *APL Bioeng* **6** (2022).

23. O. Aydin, A. P. Passaro, M. Elhebeary, G. J. Pagan-Diaz, A. Fan, S. Nuethong, R. Bashir, S. L. Stice, M. T. A. Saif, Development of 3D neuromuscular bioactuators. *APL Bioeng* **4** (2020).

24. M. A. Bakooshli, E. S. Lippmann, B. Mulcahy, N. Iyer, C. T. Nguyen, K. Tung, B. A. Stewart, H. Van Den Dorpel, T. Fuehrmann, M. Shoichet, A. Bigot, E. Pegoraro, H. Ahn, H. Ginsberg, M. Zhen, R. S. Ashton, P. M. Gilbert, A 3D culture model of innervated human skeletal muscle enables studies of the adult neuromuscular junction. *Elife*, doi: 10.7554/eLife.44530.001 (2019).

25. A. Natarajan, A. Sethumadhavan, U. M. Krishnan, Toward building the neuromuscular junction: In vitro models to study synaptogenesis and neurodegeneration. *ACS Omega* **4**, 12969–12977 (2019).

26. S. G. M. Uzel, R. J. Platt, V. Subramanian, T. M. Pearl, C. J. Rowlands, V. Chan, L. A. Boyer, P. T. C. So, R. D. Kamm, Microfluidic device for the formation of optically excitable, three-dimensional, compartmentalized motor units. *Sci Adv* **2** (2016).

27. F. B. Tian, L. Wang, Numerical modeling of sperm swimming. *Fluids* **6** (2021).

28. D. Y. Tiioe, S. Oentoeng, The Viscosity of Human Semen and the Percentage of Motile Spermatozoa. *Viscosity and Motility* **19** (1968).

29. H. M. Hübner, R. Heidl, W. Krause, Investigation of Flow Behaviour (Viscosity) from Human Seminal Fluid with a Rotational Viscosimeter. *Andrologia* **17**, 592–597 (1985).

30. J. L. Simpson, S. Humphries, J. P. Evans, L. W. Simmons, J. L. Fitzpatrick, Relationships between sperm length and speed differ among three internally and three externally fertilizing species. *Evolution (N Y)* **68**, 92–104 (2014).

31. J. L. Fitzpatrick, F. Garcia-Gonzalez, J. P. Evans, Linking sperm length and velocity: The importance of intramale variation. *Biol Lett* **6**, 797–799 (2010).

32. T. S. Yu, E. Lauga, A. E. Hosoi, Experimental investigations of elastic tail propulsion at low Reynolds number. *Physics of Fluids* **18** (2006).

33. O. Aydin, K. Hirashima, M. T. A. Saif, Incorporating Geometric Nonlinearity in Theoretical Modeling of Muscle-Powered Soft Robotic Bio-Actuators. *Journal of Applied Mechanics, Transactions ASME* **91** (2024).

34. J. Chal, O. Pourquié, Making muscle: Skeletal myogenesis in vivo and in vitro. *Development* **144**, 2104–2122 (2017).

35. M. Weitkunat, M. Brasse, A. R. Bausch, F. Schnorrer, Mechanical tension and spontaneous muscle twitching precede the formation of cross-striated muscle in vivo. *Development* **144**, 1261–1272 (2017).

36. J.-S. Kang, P. J. Mulieri, C. Miller, D. A. Sassoon, R. S. Krauss, CDO, A Robo-related Cell Surface Protein that Mediates Myogenic Differentiation. *J Cell Biol* **143**, 403–413 (1998).

37. E. N. Olson, Interplay between Proliferation and Differentiation within the Myogenic Lineage. *Dev Biol* **154**, 261–272 (1992).

38. J. Andersen, O. Revah, Y. Miura, N. Thom, N. D. Amin, K. W. Kelley, M. Singh, X. Chen, M. V. Thete, E. M. Walczak, H. Vogel, H. C. Fan, S. P. Paşca, Generation of Functional Human 3D Cortico-Motor Assembloids. *Cell* **183**, 1913-1929.e26 (2020).

39. R. G. Cox, The motion of long slender bodies in a viscous fluid Part 1. General theory. *J Fluid Mech* **44**, 791–810 (1970).

40. B. Emon, Z. Li, S. H. Joy, U. Doha, F. Kosari, M. T. A. Saif, "A novel method for sensor-based quantification of single/multicellular force dynamics and stiffening in 3D matrices" (2021); https://www.science.org.

41. G. K. Toworfe, R. J. Composto, C. S. Adams, I. M. Shapiro, P. Ducheyne, "Effect of surface activated poly(dimethylsiloxane) on fibronectin adsorption and cell function" (2003); http://repository.upenn.edu/mse_papersURL:http://www.mrs.org/members/proceedings/fall2003/f/F7_8.pdfThispa perispostedatScholarlyCommons.http://repository.upenn.edu/mse_papers/4http://repository.upenn.edu/mse_papers/4.

42. G. Agrawal, A. Aung, S. Varghese, Skeletal muscle-on-a-chip: An in vitro model to evaluate tissue formation and injury. *Lab Chip* **17**, 3447–3461 (2017).

43. M. A. Tamargo, T. R. Nash, S. Fleischer, Y. Kim, O. F. Vila, K. Yeager, M. Summers, Y. Zhao, R. Lock, M. Chavez, T. Costa, G. Vunjak-Novakovic, MilliPillar: A Platform for the Generation and Real-Time Assessment of Human Engineered Cardiac Tissues. *ACS Biomater Sci Eng* **7**, 5215–5229 (2021).

44. L. T. Feng, Z. N. Chen, H. Bian, Skeletal muscle: molecular structure, myogenesis, biological functions, and diseases. John Wiley and Sons Inc [Preprint] (2024). https://doi.org/10.1002/mco2.649.

45. J. W. Sanger, J. Wang, Y. Fan, J. White, J. M. Sanger, Assembly and dynamics of myofibrils. [Preprint] (2010). https://doi.org/10.1155/2010/858606.

46. C. D. Kaufman, S. C. Liu, C. Cvetkovic, C. A. Lee, G. Naseri Kouzehgarani, R. Gillette, R. Bashir, M. U. Gillette, Emergence of functional neuromuscular junctions in an engineered, multicellular spinal cord-muscle bioactuator. *APL Bioeng* **4** (2020).

47. O. F. Vila, S. G. M. Uzel, S. P. Ma, D. Williams, J. Pak, R. D. Kamm, G. Vunjak-Novakovic, Quantification of human neuromuscular function through optogenetics. *Theranostics* **9**, 1232–1246 (2019).

48. A. Tofangchi, A. Fan, M. T. A. Saif, Mechanism of Axonal Contractility in Embryonic Drosophila Motor Neurons In Vivo. *Biophys J* **111**, 1519–1527 (2016).

49. L. Grant, R. Raman, C. Cvetkovic, M. C. Ferrall-Fairbanks, G. J. Pagan-Diaz, P. Hadley, E. Ko, M. O. Platt, R. Bashir, Long-Term Cryopreservation and Revival of Tissue-Engineered Skeletal Muscle. *Tissue Eng Part A* **25**, 1023–1036 (2019).

50. G. Nagel, T. Szellas, W. Huhn, S. Kateriya, N. Adeishvili, P. Berthold, D. Ollig, P. Hegemann, E. Bamberg, Channelrhodopsin-2, a directly light-gated cation-selective membrane channel. *PNAS* **100** (2003).

51. G. J. Pagan-Diaz, J. Drnevich, K. P. Ramos-Cruz, R. Sam, P. Sengupta, R. Bashir, Modulating electrophysiology of motor neural networks via optogenetic stimulation during neurogenesis and synaptogenesis. *Sci Rep* **10** (2020).

52. A. Proulx, P. A. Merrifield, C. C. G. Naus, Blocking gap junctional intercellular communication in myoblasts inhibits myogenin and MRF4 expression. *Dev Genet* **20**, 133–144 (1997).

53. R. M. Mège, D. Goudou, C. Giaume, M. Nicolet, F. Rieger, Is intercellular communication via Gap junctions required for myoblast fusion?? *Cell Commun Adhes* **2**, 329–343 (1994).

54. T. W. Farmer, F. Buchthal, P. R. Rosenfalck, Refractory period of human muscle after the passage of a propagated action potential. *Electroencephalogr Clin Neurophysiol* **12** (1960).

55. H. Hocheng, C. M. Chen, Y. C. Chou, C. H. Lin, Study of novel electrical routing and integrated packaging on bio-compatible flexible substrates. *Microsystem Technologies* **16**, 423–430 (2010).

56. Q. Tseng, E. Duchemin-Pelletier, A. Deshiere, M. Balland, H. Guilloud, O. Filhol, M. Théry, Spatial organization of the extracellular matrix regulates cell-cell junction positioning. *Proc Natl Acad Sci U S A* **109**, 1506–1511 (2012).

57. C. A. Powell, B. L. Smiley, J. Mills, H. H. Vandenburgh, Mechanical stimulation improves tissue-engineered human skeletal muscle. *Am J Physiol Cell Physiol* **283** (2002).

58. V. Chan, K. Park, M. B. Collens, H. Kong, M. T. A. Saif, R. Bashir, Development of miniaturized walking biological machines. *Sci Rep* **2**, 1–8 (2012).

59. R. Mestre, T. Patiño, X. Barceló, S. Anand, A. Pérez-Jiménez, S. Sánchez, Force Modulation and Adaptability of 3D-Bioprinted Biological Actuators Based on Skeletal Muscle Tissue. *Adv Mater Technol* **4** (2019).

931   60.   A. M. Kasper, D. C. Turner, N. R. W. Martin, A. P. Sharples, Mimicking exercise in three-dimensional
932   bioengineered skeletal muscle to investigate cellular and molecular mechanisms of physiological adaptation. *J Cell*
933   *Physiol* **233**, 1985–1998 (2018).

934   61.   K. M. Wisdom, S. L. Delp, E. Kuhl, Use it or lose it: multiscale skeletal muscle adaptation to mechanical stimuli.
935   *Biomech Model Mechanobiol* **14**, 195–215 (2015).

936   62.   O. F. Vila, Y. Qu, G. Vunjak-Novakovic, In vitro models of neuromuscular junctions and their potential for novel
937   drug discovery and development. *Expert Opin Drug Discov* **15**, 307–317 (2020).

938   63.   M. J. Anderson, M. W. Cohen, E. Zorychta, Effects of innervation on the distribution of acetylcholine receptors on
939   cultured muscle cells. *J Physiol* **268**, 731–756 (1977).

940   64.   R. D. Dresdner, D. F. Katz, S. A. Berger, The propulsion by large amplitude waves of uniflagellar micro-
941   organisms of finite length. *J Fluid Mech* **97**, 591–621 (1980).

942   65.   E. A. Gillies, R. M. Cannon, R. B. Green, A. A. Pacey, Hydrodynamic propulsion of human sperm. *J Fluid Mech*
943   **625**, 445–474 (2009).

944   66.   H. M. Hubner, R. Heidl, W. Krause, Investigation of Flow Behaviour (Viscosity) from Human Seminal Fluid with
945   a Rotational Viscosimeter. *Andrologia* **17**, 592–597 (1985).

946   67.   S. Pak, E. Lauga, *Theoretical Models in Low-Reynolds-Number Locomotion* (Royal Society of Chemistry, 2014;
947   www.rsc.org).

948   68.   E. Lauga, Continuous breakdown of Purcell's scallop theorem with inertia. *Physics of Fluids* **19** (2007).

949   69.   D. Gonzalez-Rodriguez, E. Lauga, Reciprocal locomotion of dense swimmers in Stokes flow. *Journal of Physics*
950   *Condensed Matter* **21** (2009).

951   70.   E. Lauga, Life around the scallop theorem. *Soft Matter* **7**, 3060–3065 (2011).

952   71.   N. J. Derr, T. Dombrowski, C. H. Rycroft, D. Klotsa, Reciprocal swimming at intermediate Reynolds number. *J.*
953   *Fluid Mech* **952** (2022).

954   72.   H. Liu, R. Wassersug, K. Kawshi, A computational fluid dynamics study of tadpole swimming. *Journal of*
955   *Experimental Biology* **199**, 1245–1260 (1996).

956   73.   K. V. Hoff, R. J. Wassersug, Tadpole Locomotion: Axial Movement and Tail Functions in a Largely Vertebraeless
957   Vertebrate 1. *American Zoology* **40**, 62–76 (2000).

958   74.   S. Childress, R. Dudley, Transition from ciliary to flapping mode in a swimming mollusc: Flapping flight as a
959   bifurcation in Re_{ω}. *J Fluid Mech* **498**, 257–288 (2004).

Acknowledgments:

     Funding:

         National Science Foundation (NSF) Emerging Frontiers in Research and Innovation:
         Continuum, Compliant, and Configurable Soft Robotics Engineering Grant No. 1830881
         (MTAS)

         National Science Foundation Mind In-Vitro Grant No. 2123781 (MTAS)

         National Science Foundation Graduate Research Fellowship Program (WCD)

         Chan Zuckerberg Biohub Investigator grant (MTAS)

     Author contributions:

         Conceptualization: OA, MTAS, ZL, WCD

         Data curation: WCD, AB, YK, AC, MW, DD

         Formal analysis: WCD, AB, YK

         Funding acquisition: MTAS

         Investigation: WCD, AB, YK, AC, MW, DD, OA, ZL

         Methodology: WCD, BE, MTAS, OA, ZL

         Project administration: MTAS, WCD, ZL

         Resources: MTAS, OA, BE

         Software: OA, WCD, AB, YK

         Supervision: MTAS, OA, ZL

         Validation: WCD

         Visualization: WCD, AB, OA

         Writing – original draft: WCD, MTAS, MSHJ,

         Writing – review & editing: WCD, MTAS, OA, MSHJ

Competing interests: Authors declare that they have no competing interests.

Data and materials availability: Data used for the figures and analysis appearing in this paper will
be made available through the Illinois Digital Environment for Access to Learning and Scholarship
(IDEALS) repository (http://www.ideals.illinois.edu/) and is available to reviewers at the time of
the submission of this document. Raw *.tif images will be made available through the Illinois Data
Bank at the time of publication (http://databank.illinois.edu/). Backups of all digital assets are
maintained on hard drives stored in the PI's lab. Other digital assets including MATLAB codes,
CAD drawings, and vector drawings used for the figures are made available on Github
(https://github.com/wdrennan/Biohybrid-Swimmer-Digital-Assets).