In Situ Integration of Porous Polyethylene Nanomembrane with Wound Exudates for Scarless Healing

Shijie Yuan [1 2 3 4], Qiao Gu [1 2 3], Xingchen Guo [1 2 3], Xuanxuan Tang [4], Jiawen Qiu [5], Linkuo Shang [4], Julie Qiaojin Lin [4 *], Lu-Tao Weng [2 5 6**], Ping Gao [1 2 3 5 6 ***]

[1] *Multi-functional Polymeric Membranes Research Facility, The Hong Kong University of Science and Technology (Guangzhou), Guangdong, China*
[2] *Thrust of Advanced Materials, Function Hub, The Hong Kong University of Science and Technology (Guangzhou), Guangdong, China*
[3] *Green E Materials, The Hong Kong University of Science and Technology (Guangzhou), Guangdong, China*
[4] *Brain and Intelligence Research Institute, Thrust of Bioscience and Biomedical Engineering, Systems Hub, The Hong Kong University of Science and Technology (Guangzhou), Guangdong, China*
[5] *Materials Characterization and Preparation Facility (GZ), The Hong Kong University of Science and Technology (Guangzhou), Guangdong, China*
[6] *Department of Chemical and Biological Engineering, The Hong Kong University of Science and Technology, Hong Kong, China*

[*] Corresponding author; qiaojinlin@hkust-gz.edu.cn
[**] Corresponding author; mcltweng@hkust-gz.edu.cn
[***] Corresponding author; kepgao@ust.hk

Keywords: Imperceptible wound dressing, pgPE, Self-healing, Scab prevention, Scarless, Breathable, Hypoxia, Follicle regeneration

Abstract

Achieving scarless wound repair through innovative material designs, such as hydrogels infused with growth factors and cells, has been extensively explored. In this study, we introduce a scarless healing material called pgPE, which is based on a porous and biologically inert ultra-high molecular weight polyethylene (UHMWPE) nanomembrane. This highly flexible nanomembrane conforms closely to the wound site and effectively absorbs wound-associated species into its nanopores, forming pgPE *in situ*. The resulting pgPE creates an ideal environment that fosters physiological metabolism while acting as a barrier against pathogens. Our findings demonstrate that pgPE facilitates complete skin reconstruction, including the regeneration of hair follicles. Additionally, we characterized the immune microenvironment and hypoxic conditions, revealing that pgPE alleviates hypoxia and modulates immune responses, thereby promoting healing towards a scar-free outcome. The integration of wound-associated species within pgPE has been evidenced through three-dimensional Time-of-Flight Secondary Ion Mass Spectrometry (ToF-SIMS) analysis of postmortem samples. This study highlights the potential of personalized solutions that align with physiological systems for enhanced wound healing.

Introduction

The skin, the largest organ in the human body, is essential for protecting against bacterial invasion and maintaining hydration. Consequently, wound repair—especially the challenge of replacing damaged tissues without fibrosis or scarring—has become a significant research focus [1–3]. The advancement of new materials is critical for developing effective wound dressings. While traditional polyurethane materials provide effective barriers against bacterial and viral infections, their poor air permeability can hinder metabolic processes essential for healing, as insufficient oxygen supply limits cellular metabolism [4,5]. On the other hand, hydrogels excel in substance delivery and moisture retention, key features for high-quality wound dressings [6,7]; however, they too suffer from low air permeability, impeding wound recovery [8]. A promising direction involves materials that mimic the selective permeability of cell membranes, enabling physiological metabolism around the injury while preventing infections [9]. This prompts a question: is there an epidermis-like material that can create an ideal microenvironment for metabolic processes while offering mechanically imperceptible protection against pathogens?

Wound healing is a complex physiological process that involves hemostasis, inflammation, proliferation, and remodeling, with many cells playing crucial roles in regulating healing and scarring, particularly fibroblasts and immune cells at various stages [10]. Research indicates that appropriately regulating the timing of immune cell involvement and reducing the transformation of myofibroblasts can effectively minimize scarring [11]. Tissue hypoxia and pathogen invasion threaten healing, which leads to excessive vascularization and unnecessary myofibroblast transformation, potentially resulting in poorly remodel-able granulation and scar tissue [12]. Therefore, providing a breathable, pathogen-free environment may relieve the need for the

activation of the body to recruit immune cells at too early time, reducing myofibroblast transformation or scar tissues. In addition, wound exudate management can also affect wound repair outcomes significantly. Excessive fluidic exudate retention generated from impermeable dressings has been shown to trigger severe inflammatory responses [13]. On the other hand, heavily dehydrated exudates or scabs resulted commonly from bare wounds have been reported to block air exchange and serve as a breeding ground for bacteria[14–16]. Further, the interaction between the wound and the dressing is another key factor for wound repair. Studies have shown porous materials may facilitate cell adhesion and migration and enhance gas exchange with the external environment for healing enhancement [17,18]. Additionally, interfacial mechanical interactions at the wound site have been connected closely to the transformation of myofibroblasts [19], suggesting the necessity of an imperceptible material for scarless healing. In summary, effective scar-free dressing should exhibit skin-like characteristics, including breathability, pathogen resistance, humidity regulation, porosity, and mechanical imperceptibility. Unfortunately, no materials with these properties have been reported to date.

In this study, we provide an innovative solution: an epidermis-like dressing, called pgPE, which was achieved *in situ* through wound exudates impregnation inside a porous nanomembrane made from ultrahigh molecular weight polyethylene (UHMWPE) [20]. The nanomembrane possesses porosities greater than 70% and features tunable thicknesses between 20 nm to 1 μm, providing exceptional breathability and ultralow bending stiffness which can conform to the wound site imperceptibly by van der Waals attractions. Three-dimensional (3D) analysis of the nanomembrane detached from the wound using Time-of-Flight Secondary Ion Mass Spectrometry (ToF-SIMS) confirmed the infiltration of electrolytes and amphiphilic wound-associated species into the UHMWPE nanomembrane's nanopores, implicating an epidermis-like structure [21]. This personalized nanofilm transformed *in situ* (pgPE) shows high healing efficacy as demonstrated by macroscopic and histological analyses. An immunostaining analysis revealed that the pgPE maintained physiological metabolisms whilst offering protection against infections. The success of our approach may inform future wound dressing designs to harmoniously integrate with local physiological systems.

Results

Design of UHMWPE nanomembranes with pathogen prevention and tunable breathability

The UHMWPE nanomembrane features tunable microstructures that meet the wound dressing criteria, serving as a breathable barrier that allows air exchange while protecting against pathogens. Figures 1a and 1b (Supplementary Figures 1, and 2) show that these highly transparent nanomembranes are free-standing even at the monolayer level, thanks to their triangulated tessellation of interconnected nanofibrils composed of extended-chain fiber crystals [22,23]. The material's high hydrophobicity and small pore size effectively block aerosol particles in the size range of 75 ± 25 nm (Fig. 1c, 1d, Supplementary Fig. 3, 4, 5). To assess the effectiveness of UHMWPE in wound healing, we created two variants: GPNano-L, with a minimum practical thickness of 85.6 nm, and GPNano-H, with a maximum self-adhesive thickness of 821.4 nm, both demonstrating a minimum peel strength of 4.71 N/m (Supplementary Fig. 6). Characterizations using Scanning Electron Microscopy (SEM) and Atomic Force Microscopy (AFM) revealed a multilayered texture that preserved the triangulated topological porous structure observed in the monolayer membrane shown in Fig. 1b (Fig. 1e, 1f). To evaluate their filtration capabilities, we employed *E. coli* and single-stranded Adeno-Associated Virus (ssAAV) as models for permeability testing, confirming that UHMWPE nanomembrane effectively blocks bacterial and viral passages (Fig. 1g, Supplementary Fig. 7-10). Gas permeability tests showed that GPNano-L had an air permeability of 5.6×10^6 L/m²/24h, while GPNano-H demonstrated 7×10^5 L/m²/24h, making them about 250,000 to 2 million times more permeable than Tegaderm - a commercial dressing (2.74 L/m²/24h) (Fig. 1h) [24]. Finally, biocompatibility assessments using L929 cells indicated nearly 100% cell viability for the UHMWPE membranes (Supplementary Fig. 11, 12).

The breathable barrier properties of the UHMWPE are illustrated schematically in Fig. 1i-1j. In comparison, the bare wounds in the control group are expected to dehydrate rapidly forming scabs and exhibiting limited protection against pathogens. Therefore, it is important to further investigate the physical interactions between the mechanically imperceptible porous UHMWPE and the wound itself.

UHMWPE nanomembrane facilitates wound healing and reduces scarring by integrating exudates and forming pgPE *in situ*

Both variants of UHMWPE nanomembranes demonstrate a strong ability to promote Scarless wound healing and accelerate closure rates, as evidenced by macroscopic and microscopic observations along with protein-level characterizations. Figures 2a and 2b (Supplementary Fig. 13) illustrate the progression of wound healing for UHMWPE dressings compared to control and Tegaderm. The GPNano groups produced minimal scabbing and scarring. Specifically, the GPNano-H group showed no visible scabs and scars, while the GPNano-L group had a thin scab and minimal scarring. In contrast, the control group formed prominent, progressively darkening scabs from day 5 to day

9 and clear scarring by day 14. The distinctive scarring observed in the bare wound from the control group may be attributed to the rapid hydration-induced scabbing. Although Tegaderm alleviates the rapid hydration loss issue associated with the bare wound through its low air permeability, it might cause excessive wound exudates retention in the wound area, causing prolonged inflammation, and thus impede healing [25]. The apparent high performance of the UHMWPE variants, particularly their negative correlation between breathability and scab formation, indicates a balanced performance between moisture retention and air permeability. We speculate this resulted from their strong interactions with the wounding site through their high porosity and ultralow bending stiffness. The interaction might enable their integration with the wound exudates, forming an epidermis-like wound structure, called pgPE. In order to confirm this speculation, we performed a 3D ToF-SIMS analysis of GPNano-H samples detached from the wound at a cryogenic temperature (-120°C), which is necessary to maintain the sample structural integrity and prevent analyte relocation during pumping and analysis [26]. As shown in Figure 2c, the negative ion intensity of UHMWPE (represented by C_2H^-) is uniform throughout the whole GPNano-H film while the ion intensities of various electrolytes (Cl^-, PO_3^-) and amphiphilic chemical species (CNO^-) associated with the exudates continuously decrease from the surface in contact with the wounding site to the half of the GPNano-H. This suggests that the exudates penetrate the porous UHMWPE, which is fully in agreement with the 3D tomography results (Figure 2d) where the UHMWPE ion (C_2H^-) is overlayed with the exudate-associated ions (CNO^-, PO_3^- and Cl^-). Moreover, the penetration of the exudates can also be viewed from the cross-sectional analysis of CNO^-, PO_3^- ions (Supplementary Fig 14). Similarly, the infiltration of exudates into porous UHMWPE can be observed in the positive 3D ToF-SIMS analysis of the postmortem samples (supplementary Figure 15, 16). The low bending stiffness of the UHMWPE nanomembrane, approximately 10^{-13} N/mm [27], ensures its conformability, enabling effective integration with exudates, and this integrated structure helps maintain optimal moisture levels. It should be noted that the GPNano-L, which is about one-tenth of the thickness of the GPNano-H, exhibited some minute scaring, suggesting the need o sufficient thickness for the infiltration of wound exudates. The partial filling of exudates in the GPNano-H, in conjunction with its retained wound site conformability enabled it to exhibit an epidermis-like structure for scar-free healing.

The effective healing outcomes induced by pgPE dressings are further corroborated through microscopic investigations. Notably, the GPNano-H group exhibited remarkable healing efficacy, with nearly the entire wound area showing regeneration of hair follicles and sebaceous glands (Fig. 3a). Additionally, the collagen maturity and arrangement (as shown in Masson's trichrome staining panel) were nearly identical to those found in healthy skin. The GPNano-L group demonstrated slightly inferior performance, consistent with the macroscopic observations. Achieving such a high degree of healing typically requires incorporating additional signaling factors into the dressing to regulate the physiological wound-healing process [28–31]. Previous

studies have indicated that in small full-thickness cutaneous wounds (less than 1 cm $\times$ 1 cm) in mice, skin appendages such as sebaceous glands and hair follicles do not regenerate, forming scarring instead [32,33]. In contrast, the control and Tegaderm groups yielded unsatisfactory results, showing poor appendage regeneration and an immature, disorganized epidermis and dermis. Quantitatively, Fig. 3b-c showcased that both GPNano-L and GPNano-H groups exhibited significantly higher numbers of neo-hair follicles and neo-sebaceous glands. Furthermore, we also quantified the maturity of the wound by measuring the wound area. The results shown in Fig. 3d showed that the GPNano-H group exhibited no immature wound areas, while the GPNano-L group displayed lower levels of immaturity than the control and Tegaderm. Notably, the scarring index of the GPNano-H group was lower than that of the other groups (Fig. 3e). Combined with the in-vivo biocompatibility tests (Supplementary Fig. 17 - 20), these results strongly indicate that the biologically inert UHMWPE nanomembranes facilitate enhanced scarless healing, aligning well with our macroscopic observations.

At the protein level, the UHMWPE nanomembrane groups demonstrated their scarless healing capability by exhibiting significantly lower expression levels of α-smooth muscle actin (α-SMA) (Fig. 4a, 4b) compared to the control and Tegaderm groups. Previous studies suggest that α-SMA is predominantly expressed in myofibroblasts and vascular endothelial cells, showing a strong correlation with scar formation through wound fibrosis [34–36].

Having confirmed that the artificial skin characteristics of pgPE exhibit wound healing efficacy and minimize scarring at macroscopic, microscopic, and protein levels, we will further explore the key factors contributing to these healing outcomes.

pgPE regulates the wound microenvironment to enhance natural metabolism
As sufficient oxygen exchange is essential for wound healing, we first assessed the severity of hypoxic induction in the wounded tissues when covered with pgPE by immunohistochemistry of hypoxia-inducible factor 1-alpha (HIF-1α), a well-studied hypoxia indicator. HIF-1α was found at low levels in both the GPNano-L and GPNano-H groups, whereas its expression levels were significantly higher in both the control and the Tegaderm group (Fig. 4c, 4d). The elevated HIF-1α levels in the control and Tegaderm groups can be attributed to their low air permeability; Tegaderm's limited air permeability was illustrated in Fig. 1h, and the scabs formed in the control group hindered air exchange (Fig. 2a, 2b). A similar trend was observed for hypoxia-inducible factor 2-alpha HIF-2α (Fig. 4e, 4f). Thus, the high air permeability of pgPE helps alleviate hypoxic conditions in the wound, facilitating better oxygen transmission.

Various immune factors and inflammatory cells are considered next. Previous studies have shown that M2 macrophages can reduce inflammation and promote follicle regeneration [37]. Their presence in the wound area can be visualized through

immunofluorescence staining of CD206, a specific surface antigen of M2 macrophages. Figures 5a and 5b show that the pgPE groups exhibited at least 50% higher number of CD206$^+$ cells in the wound compared to both the control and Tegaderm groups. This indicates that the oxygen-rich environment provided by pgPE fosters the transformation of M2 macrophages, thereby enhancing wound healing and collagen reconstruction, which helps prevent scar formation. We also examined the expression levels of IL-4, which has been identified as a risk factor for scar formation due to its role in fibroblast proliferation and collagen density [38,39]. From days 5 to 14, we found that IL-4 levels in the pgPE groups were consistently lower than those in the Tegaderm and control groups, even in regions with similar immaturity (Fig. 5c, 5d, Supplementary Fig. 21). The expression profile of IL-13 mirrored that of IL-4, with the pgPE groups showing reduced levels of IL-13 as well (Supplementary Fig. 22). This suggests that the rapid and effective healing observed in the pgPE groups does not coincide with an increase in IL-4 and IL-13 expression, thereby reducing the risk of wound fibrosis and scar formation, consistent with our earlier observations (see Fig. 1a).

Based on these findings, we hypothesize that the changes in the downstream pathways caused by the inflammatory microenvironment are key to achieving faster healing and scarless wound repair. TGF-β1 is a well-known downstream pathway linked to wound healing and scar formation [40,41]. Although TGF-β3 also promotes cell proliferation, it is not typically associated with scarring. In wound healing, the ratio of TGF-β3 to TGF-β1 is often used as a characteristic to assess scaring risk [42,43]. Our immunohistochemical analysis revealed comparable TGF-β1 expression levels between the GPNano-L and control groups (Fig. 5e). In the GPNano-H group, where complete healing was almost achieved, TGF-β1 levels were barely detectable, whereas the Tegaderm group exhibited significantly elevated TGF-β1 levels (Fig. 5f). Conversely, TGF-β3 expression was widespread in the GPNano-L group, low in the well-healed GPNano-H group, and minimal in the control and Tegaderm groups (Fig. 5g, 5h). Quantitative analysis revealed that the GPNano-L group had a significantly higher TGF-β3/TGF-β1 ratio compared to the other groups (Supplementary Fig. 23). Notably, the expression levels and ratios in the GPNano-H group were not surprising, as the group was nearing complete healing and had entered the remodeling phase, moving beyond the primary TGF-regulated growth phase.

Through this analysis of the microenvironment, we further uncover the mechanism behind the high healing efficiency of pgPE, demonstrating how it regulates conditions that promote scarless healing

Outlook
We have demonstrated an epidermis-like platform, pgPE, for scar-free wound repair, which forms *in situ* through the integration of a nanomembrane with localized electrolytes and amphiphilic species from exudates, thus creating an ideal environment for effective skin reconstruction. The absence of scabs, low levels of

hypoxia (HIF-1α), extremely low α-SMA, and a significantly high CD206 indicate a naturally metabolic environment akin to healthy skin, facilitating humidity regulation, air exchange, mechanical imperceptibility, and pathogen protection. The successful full regeneration of skin without scarring underscores the synergistic interplay between physiological systems and the UHMWPE nanomembrane dressing. This research may also inform future designs of wound dressing that require the desirable integration with physiological systems.

Acknowledgments
We would like to express our gratitude to the MCPF(GZ) of HKUST(GZ) for their invaluable technical support and guidance. We also thank Guangdong HWT for their professional oversight of animal ethics and protocols. Additionally, we appreciate the technical assistance and support provided by Guangdong Solidgood Limited and Fumengdao Guangzhou Limited. We also appreciate the King`s Flair International (Holdings) Limited. We also thank Prof. Zhuoyi Liang for providing the HEK-293T cell line and Yaxiong Fang for technical support. This work is supported by the Tsinghua Zhujiang Research Institute of Pearl River Delta (to P.G.) and the Guangzhou Science and Technology Program City-University Joint Funding Project (Project No. 2023A03J0001) (to J.Q.L.).

Contributions
S.Y. and P.G. designed the materials and research and wrote the manuscript. S.Y. conducted most experiments without further indications. L-T. W. and J.Q.L. provided significant suggestions during manuscript preparation. Q.G. performed the aerosol permeability test and SEM. X.G. performed the physical characterizations. X.T. performed biocompatibility tests and bacterial permeability tests. J.Q. performed the ToF-SIMS. L.S. performed the virus permeability tests. All authors reviewed the manuscript and offered feedback.

Competing interests
The authors declare no competing interests.

Figure 1 a) Photograph showing the free-standing and transparent appearance of the UHMWPE nanomembrane. **b)** Representative SEM image of 20 nm UHMWPE (magnification: 20000x, scale bar: 1μm). **c)** Representative SEM image after the aerosol filtration test (magnification: 20000x, scale bar: 1μm). **d)** Filtration efficiency of 20 nm UHMWPE (n=3, error bar represents the standard deviation). **e)** Representative SEM image of GPNano-H (magnification:50000x, scale bar: 500 nm). **f)** Representative AFM image of GPNano-H (scale bar: 500 nm). **g)** Representative fluorescent images of transfection tests of ssAAV on HEK-293T. Green: transfected cells. **h)** Quantification of gas permeability (n=3 for GPNano-L and GPNano-H, error bar represents the standard error of means). **i)** Schematic illustration of conformability and breathable barrier property of UHMWPE and **j)** exudate integration. The transparent fibrous films represent UHMWPE nanomembranes. The yellow crystals represent the wound exudates, and the brown block represents a scab.

Figure 2 a) Representative appearances of wounds on day 0, 5, 9, 14. Scale bar: 7mm. **b)** Quantification of relative wound closure (n=15 (day 1-6), n=10 (day 7-9), two-way ANOVA, *** p<0.0005, **** p<0.0001, error bars represent standard error of means). **d)** Negative ToF-SIMS depth profile analysis of GPNano-H from the air site to the wound site. **d)** 3D ToF-SIMS rendering analysis of GPNano-H in which C_2H^- representing UHMWPE is overlayed with the other ions representing the wound-associated species.

Figure 3 a) Representative images of HE-staining and Masson trichrome-staining. (magnification, x25, scale bar: 1 mm; magnification, x200, scale bar: 300 μm). Black lines: wound area. Yellow dashed area: Papillary layer. Blue dashed area: subpapillary layer. Green dashed rectangle: sebaceous gland. Red dashed circle: hair follicle. Orange line: unmatured zone defined by the last two sebaceous glands from the margin of the wound. Blue line and blue dashed line: Height of scar (H) and height of skin (H_0), respectively. scar elevated index: $\frac{H}{H_0}$. **b-e)** Quantifications analysis of neo-sebaceous glands, neo-hair follicles, unmatured zone, and the Scar Elevation Index. (n=5, one-way ANOVA, *p<0.05, **p<0.001, *** p<0.005, error bars represent the standard error of means).

Figure 4 a) Representative immunofluorescence staining of α-SMA. (Green: α-SMA. Blue: DAPI Scale bar: 500 μm). **b)** Quantification analysis of the calibrated total expression (IntDen) of α-SMA. (n=3, one-way ANOVA. *p<0.05, **p<0.001, *** p<0.0005, **** p<0.0001, error bars represent the standard error of means). **c)** Representative immunofluorescence staining of HIF-1α. (Green: HIF-1α, blue: DAPI, Scale bar: 50 μm). **d)** Quantification analysis of the calibrated total expression (IntDen) of HIF-1α per cell (n=3, one-way ANOVA. *p<0.05, **p<0.001, *** p<0.0005, **** p<0.0001, error bars represent the standard error of means). **e)** Representative immunofluorescence staining of HIF-2α. (Green: HIF-1α, blue: DAPI, Scale bar: 50 μm). **f)** Quantification analysis of the calibrated total expression (IntDen) of HIF-2α per cell (n=3, one-way ANOVA. *p<0.05, **p<0.001, *** p<0.0005, **** p<0.0001, error bars represent the standard error of means).

Figure 5 a) Representative immunofluorescence staining of CD206. (Green: CD206[+] cells. Blue: DAPI Scale bar: 50 μm). **b)** Quantification analysis of CD206[+] cells per view. (n=3, one-way ANOVA. *p<0.05, error bars represent the standard error of means). **c)** Representative immunohistochemistry staining of IL-4 on day 14. (Brown: IL-4. magnification, x25, scale bar: 1 mm; magnification, x200, scale bar: 300 μm). **d)** Quantification analysis of IL-4 expression from day 5 to day 14. (n=3, one-way ANOVA. **p<0.01, error bars represent the standard error of means). **e)** Representative immunohistochemistry staining of TGF-β1. (Brown: TGF-β1. magnification, x25, scale bar: 1 mm; magnification, x200, scale bar: 300 μm). **f)** Quantification analysis of TGF-β1 expression. (n=3, one-way ANOVA. **p<0.01, error bars represent the standard error of means). **e)** Representative immunohistochemistry staining of TGF-β3. (Brown: TGF-β3. magnification, x25, scale bar: 1 mm; magnification, x200, scale bar: 300 μm). **f)** Quantification analysis of TGF-β3 expression. (n=3, one-way ANOVA. Error bars represent the standard error of means).

Methods

1. Materials

UHMWPE nanomembranes were developed and fabricated in our group, with slight modifications [44]. Briefly, a low-entanglement-density gel film was biaxially stretched by BRUCKNER KARO 5.0 in a semi-solid state at 90-130°C. The draw ratio of GPNano-H is 400-600 times, while that of GPNano-L is 100-200 times. The stretched gel films were constrained and extracted to remove the oil. The extraction system consisted of HPLC-grade n-hexane, ethyl acetate, ethanol, and water. After extraction, the gel films were vacuum-heated to remove water and other solvent residues for 72 hours. Finally, the samples were sealed in a positive-pressure room and disinfected for 24 hours using ultraviolet light.

A detailed list of the commercially available materials utilized in this study, including supplier names, catalog numbers, and CAS numbers, is available in Supplementary Data 1. All primers were purchased from Sangon Biotech.

2. Characterization methods
(a) Peel Strength test

A UHMWPE sample was cut into a 2 cm x 2 cm piece and was immediately applied to the subject's forearm. A 90° peel strength test was conducted using an Instron 68TM, with a peeling speed of 50 mm/s. The other piece was applied to adjacent skin after the test was completed, and the same tensile test was performed. Detailed schematic diagrams and images can be found in Supplementary Fig. 24.

(b) Aerosol Permeability Test

The aerosol permeability of the monolayer UHMWPE (~20 nm) was performed on TSI 8130A.

(c) Gas Permeability Test

We tested UHMWPE samples on the HBYIQI HB-TQY-01 with a pressure drop of 1.21 kPa and measured the time it took for 100 mL of gas to pass.

(d) Scanning Electron Microscopy

SEM micrographs of the thinnest UHMWPE were obtained using a hot field emission SEM instrument (JEOL 7800F) with an acceleration voltage of 2 keV. The sample film was prepared by suspending UHMWPE on a perforated bare transmission electron microscope copper grid with 200 mesh. No conductive coating was applied to the film.

The SEM micrographs of GPNano-H and GPNano-L samples were obtained using a cold field emission SEM instrument (Hitachi Regulus 8230) with an acceleration voltage of 1 keV. The GPNano samples were put on a silicon wafer and then coated with a platinum thin film using Quorum Q150T.

(e) Atomic Force Microscopy

AFM images of GPNano samples were obtained using a Bruker Dimension Icon instrument with a Scanasyst-Air probe in PeakForce mode. Samples were attached to a surface of an atomically flat mica sheet.

(f) Time-of-Flight Secondary Ion Mass Spectrometry

ToF-SIMS 3D analyses were carried out on an IONTOF M6 hybrid SIMS instrument (Ion-ToF GmbH, Mu□nster, Germany). This instrument is equipped with a 30 keV bismuth liquid-metal ion source for analysis and an argon cluster ion source for sputtering. A focused 10 keV Ar_{1302}^+ beam scanning over an area of 500 μm × 500 μm was used to sputter through the detached UHMWPE nanofilms. Sample imaging was performed over an area of 200 μm × 200 μm at the center of the sputter region using a 30 keV Bi_3^+ bunched cluster beam. The target pulsed current of the Bi_3^+ beam was ~0.3 pA. Each imaging scan contained 256 × 256 pixels. The whole profiling analysis was run in the non-interlaced mode, consisting of cycles of short pulses of Bi_3^+ primary beam for analysis followed by long pulses of Ar_{1302}^+ beam for sputtering. Charge compensation was realized using a low-energy flood gun (~21 eV). All SIMS spectra, chemical mapping, and 3D reconstruction were analyzed using SurfaceLab 7.3

To preserve structural integrity and avoid analyte relocation during pumping and analysis under ultra-high vacuum [26], GPNano-H samples were prepared and analyzed in the following way. Once detached from the wounds, the GPNano-H samples (~ 1.4 cm * 1.4 cm) were laid down on a piece of silicon wafer, with the 4 edges fixed using SEM tape in order to keep the samples as flat as possible. Samples were pre-cooled in the Loadlock chamber at -120°C for ~ 2 hours under dry N_2 and then pumped down. Once the Loadlock chamber reached a vacuum of ~10^{-6} mbar, they were transferred to the main chamber, in which the sample stage was kept also-120°C. All the SIMS analyses were performed at -120°C and a pressure of ~8.9×10^{-9} mbar.

3. Biological tests
(a) Virus Permeability Test

2.4 mL of ultrapure water was added to a 35 mm cell culture dish, and the surface was sealed with GPNano-L, ensuring that the upper surface of the membrane was in a relaxed state. Then, 0.6 mL of ultrapure water was added to apply pressure, creating a separation of only one layer of membrane between the two layers of ultrapure water. Next, 1 μL of ssAAV suspension, with a total of 10^9 GC, was added to the topside ultrapure water. The dish was placed at 4°C for 24 hours. After 24 hours, the upper liquid and GPNano-L were carefully discarded, and the lower aqueous phase was preserved for viral gene extraction, according to TIANamp Virus DNA/RNA Kit (TIANGEN, DP315).

We used a 20 μL PCR reaction system, which included 2 μL of extracted viral genomic DNA, 0.6 μL each of forward and reverse primers, 10 μL of 2X Rapid Taq Master Mix (Vazyme, P222), and 6.8 μL of nuclease-free ultrapure water. First, the mixture was pre-denatured at 95°C for 5 minutes, followed by 30 amplification cycles, each consisting of 15 seconds of denaturation at 95°C, 30 seconds of annealing at

57°C, and 30 seconds of extension at 72°C, with a final hold at 4°C. After PCR completion, the PCR products were detected by 2% agarose nucleic acid gel electrophoresis. The sequences of the GFP primers are as follows: F: GGTGAACTTCAAGATCCGCC; R: CTTGTACAGCTCGTCCATGC.

(b) Transfection Test

HEK-293T cells were seeded into a glass-bottom 6-well plate. When the confluence reached 30%, the upper culture medium was discarded, fresh medium was added, and GPNano-L was applied as described above. To the clear water above the GPNano, 10 µL of 10^{13} GC/µL ssAAV virus suspension was added, and the plate was incubated at 37°C for 72 hours. Subsequently, confocal microscopy imaging and cell RNA extraction were performed. Confocal imaging was performed by AX Confocal Microscopy (NIKON).

After washing the cells twice with PBS, 500 µL of Trizol (ThermoFisher, 15596026CN) was added to each well of a 6-well plate and incubated at room temperature for 5 minutes. Then, 100 µL of chloroform was added, and the mixture was vigorously shaken and incubated at room temperature for 3 minutes. After centrifugation, the upper aqueous phase was collected into a new RNase-free centrifuge tube. The RNA was washed sequentially with isopropanol and 75% ethanol, discarding the supernatant each time. The tube was left to dry at room temperature for 5 minutes, then DEPC water was added to dissolve the RNA, and the RNA concentration was measured for subsequent rtPCR and qPCR.

The reverse transcription program was completed according to the protocol of the PrimeScript™ RT Reagent Kit (Takara, RR047A), with an RNA input amount of 0.5 micrograms per sample. Each sample was pre-diluted to ensure consistent concentration. Subsequently, real-time quantitative PCR was performed using the TB Green Premix Ex Taq II Kit (Takara, RR820A). The primer sequences used were as follows:

GFP-F: GGTGAACTTCAAGATCCGCC;
GFP-R: CTTGTACAGCTCGTCCATGC;
GAPDH-F: ACGACCACTTTGTCAAGCTCATTTC;
GAPDH-R: GCAGTGAGGGTCTCTCTCTTCCTCT.

(c) *In-vitro* biocompatibility test

Direct contact test: L929 cells were seeded into a 96-well plate and cultured until reaching 80% confluency. A 1 cm * 1 cm of GPNano-L, GPNano-H, or nothing was added into different wells, with each material replicated three times. After 24 hours, samples were removed, and the cell viability of each group was tested according to the Cell Counting Kit-8 (Biosharp, BS350A).

Leachate test: Cells were prepared as above and after, supernatants were replaced by serum-free medium. In a sterile environment, GPNano-L and GPNano-H were cut into 7 cm x 7 cm pieces and soaked in 10 mL of serum at room temperature for 48 hours. Then, they were added to the corresponding wells at a 10% volume ratio, with normal serum used as a negative control. The remaining CCK-8 tests were performed

as described above.

(d) Animal Care

All animal experiments and procedures were approved by the ethics committee, with approval number SYXK(Yue) 2023-0249. BALB/c male mice, aged 6-8 weeks and weighing 18-22 g, were purchased from the Guangdong Medical Laboratory Animal Center (SCXK (Yue) 2022-0002)). All animals were acclimated for one week before the experiments. The animals were housed under standard conditions (temperature 23 $\pm$ 2°C, humidity 55 $\pm$ 5%), with a 12-hour light/dark cycle, and had free access to food and drinking water ad libitum. After surgery, animals were housed individually.

(e) Mouse Full-Thickness Cutaneous Wound Model

We employed a full-thickness cutaneous model in mice to demonstrate the healing efficacy of the two UHMWPE variants and the potential for natural healing. The surgery was conducted under sterile conditions, with mice anesthetized using isoflurane. Throughout the surgical process and during recovery from anesthesia, a heating pad was used to maintain body temperature. The dorsal skin was depilated using hair removal cream, followed by careful shaving of fine hairs with a razor, and then disinfected with povidone-iodine. Sterile punches (7 mm in diameter) were used to create a full-thickness excisional wound in the center of the back.

The experimental groups are as follows (n=5): 1) Control group - 5 days; 2) GPNano-L group - 5 days; 3) GPNano-H group - 5 days; 4) Tegaderm group - 5 days; 5) Control group - 9 days; 6) GPNano-L group - 9 days; 7) GPNano-H group - 9 days; 8) Tegaderm group - 9 days; 9) Control group - 14 days; 10) GPNano-L group - 14 days; 11) GPNano-H group - 14 days; 12) Tegaderm group - 14 days;

After grouping, different materials were applied, and the mice were allowed to recover from anesthesia. Daily photographs of the wound were taken and quantitatively analyzed by ImageJ. The materials were inspected twice daily for adherence, with reapplication as needed. At each time point (5, 9, and 14 days), animals were sacrificed by isoflurane anesthesia followed by the collection of blood from the retinal venous plexus for anticoagulation, and cervical dislocation. Skin tissue, heart, liver, spleen, and kidneys were collected. Except for the skin, the remaining tissues were fixed in 10% neutral formalin. The skin tissue was divided along the spinal axis into two halves: one half was preserved in liquid nitrogen, and the other half was fixed in 10% polyformaldehyde.

(f) Histological Analysis

Tissues were embedded in paraffin, sectioned into 4 µm slices, and stained with hematoxylin and eosin (H&E) as well as Masson's trichrome stain. All slides were scanned using a NanoZoomer S60 (Hamamatsu) and observed with NDP.view. The wound analysis was performed by three researchers in a double-blind manner. The wound area was defined by residual muscle tissue, and hair follicles and sebaceous glands within the wound area were counted by three researchers, with the average value taken. The immature region was determined by the distance between the most

distant mature hair follicles at both ends of the wound, while the scar elevation index was calculated as the ratio of the maximum wound thickness to the thickness at the wound edges.

(g) Immunobiological Chemistry (IHC)/ Immunofluorescence (IF) Analysis

The sections were processed by AS330 PLUS Automatic IHC (Dartmon). In brief, sections were dewaxed in xylene, rehydrated in a gradient, subjected to citrate buffer antigen retrieval, and blocked with 3% bovine serum albumin in 10% serum. For IHC, sections were incubated with H_2O_2 blocking before serum, followed by primary antibodies (IL-4 Abcam ab9811, 1:100; IL-13 Invitrogen PA5-102574, 1:100; TGF-β1 Abcam ab215715, 1:100; TGF-β3 Abcam ab15537, 1:100), secondary antibody (Dartmon 51457), and diaminobenzidine (Dartmon 51457). Sections were scanned and analyzed using the same instrument and software in the histological analysis. For IF, sections were incubated with primary antibodies (α-SMA Abclonal A7248 1:50; HIF-1α Abcam ab228649, 1:200; HIF-2α Invitrogen PA1-16510, 1:100; CD206 Abclonal A21014, 1:50), secondary antibody (Goat Anti Rabbit AF488 Abcam ab150077, 1:200), DAPI, and observed by AX Confocal Microscope (NIKON).

(h) Statistical Analysis

Statistical analysis was performed with GraphPad Prism 10. Each figure legend contains corresponding analysis methods. In brief, data are shown as the mean ± standard error of means. One-way ANOVA was used to analyze the single variable multiple groups data and two-way ANOVA was used to analyze the multiple variables data.

References

1. Mascharak, S. *et al.* Preventing Engrailed-1 activation in fibroblasts yields wound regeneration without scarring. *Science (1979)* **372**, eaba2374 (2021).

2. Yang, Y. *et al.* Sprayable biomimetic double mask with rapid autophasing and hierarchical programming for scarless wound healing. *Sci Adv* **10**, eado9479 (2024).

3. Zhang, Y. *et al.* Scarless wound healing programmed by core-shell microneedles. *Nat Commun* **14**, 3431 (2023).

4. Bishop, A. Role of oxygen in wound healing. *J Wound Care* **17**, 399–402 (2008).

5. Han, X. *et al.* Exosome-coated oxygen nanobubble-laden hydrogel augments intracellular delivery of exosomes for enhanced wound healing. *Nat Commun* **15**, (2024).

6. Griffin, D. R. *et al.* Activating an adaptive immune response from a hydrogel scaffold imparts regenerative wound healing. *Nat Mater* **20**, 560–569 (2021).

7. Lavrador, P., Moura, B. S., Almeida-Pinto, J., Gaspar, V. M. & Mano, J. F. Engineered nascent living human tissues with unit programmability. *Nat Mater* (2024) doi:10.1038/s41563-024-01958-1.

8. Nguyen, H. M., Ngoc Le, T. T., Nguyen, A. T., Thien Le, H. N. & Pham, T. T. Biomedical materials for wound dressing: recent advances and applications. *RSC Adv* **13**, 5509–5528 (2023).

9. Simões, D. *et al.* Recent advances on antimicrobial wound dressing: A review. *European Journal of Pharmaceutics and Biopharmaceutics* **127**, 130–141 (2018).

10. Peña, O. A. & Martin, P. Cellular and molecular mechanisms of skin wound healing. *Nat Rev Mol Cell Biol* **25**, 599–616 (2024).

11. Lucas, T. *et al.* Differential Roles of Macrophages in Diverse Phases of Skin Repair. *The Journal of Immunology* **184**, 3964–3977 (2010).

12. RODRIGUEZ, P. G., FELIX, F. N., WOODLEY, D. T. & SHIM, E. K. The Role of Oxygen in Wound Healing: A Review of the Literature. *Dermatologic Surgery* **34**, 1159–1169 (2008).

13. Feng, F., Zhao, Z., Li, J., Huang, Y. & Chen, W. Multifunctional dressings for wound exudate management. *Prog Mater Sci* **146**, 101328 (2024).

14. Barnett, A., Dave, B., Ksander, G. A. & Vistnes, L. M. A concentration gradient of bacteria within wound tissues and scab. *Journal of Surgical Research* **41**, 326–332 (1986).

15. Gong, Y. *et al.* Exudate Absorbing and Antimicrobial Hydrogel Integrated with Multifunctional Curcumin-Loaded Magnesium Polyphenol Network for Facilitating Burn Wound Healing. *ACS Nano* **17**, 22355–22370 (2023).

16. WINTER, G. D. Formation of the Scab and the Rate of Epithelization of Superficial Wounds in the Skin of the Young Domestic Pig. *Nature* **193**, 293–294 (1962).

17. Chung, H. H., Casillo, S. M., Perry, S. J. & Gaborski, T. R. Porous Substrates Promote Endothelial Migration at the Expense of Fibronectin Fibrillogenesis. *ACS Biomater Sci Eng* **4**, 222–230 (2018).

18. Soubhagya, A. S., Moorthi, A. & Prabaharan, M. Preparation and characterization of chitosan/pectin/ZnO porous films for wound healing. *Int J Biol Macromol* **157**, 135–145 (2020).

19. Zhou, S. *et al.* New insights into balancing wound healing and scarless skin repair. *J Tissue Eng* **14**, (2023).

20. Ping Gao, Jin Li, Runlai Li, Qinghua Zhang & Qiao Gu. US11389772B2. (2022).

21. Feng, Y. *et al.* Invisible sweat sensor: ultrathin membrane mimics skin for stress monitoring. (2024).

22. Xie, D. *et al.* 2.5 µm-Thick Ultrastrong Asymmetric Separator for Stable Lithium Metal Batteries. *ENERGY & ENVIRONMENTAL MATERIALS* **7**, e12746 (2024).

23. Feng, J. *et al.* 1 µm Thick Robust Gel Polymer Electrolyte with Excellent Interfacial Stability for High Performance Li Metal Batteries. *Adv Funct Mater* (2024) doi:10.1002/adfm.202412287.

24. Sirvio, L. M. & Grussing, D. M. The Effect of Gas Permeability of Film Dressings on Wound Environment and Healing. *J Invest Dermatol* **93**, 528–531 (1989).

25. Lee, S. M. *et al.* Physical, morphological, and wound healing properties of a polyurethane foam-film dressing. *Biomater Res* **20**, (2016).

26. Lockyer, N. P. *et al.* Secondary ion mass spectrometry. *Nature Reviews Methods Primers* **4**, 32 (2024).

27. Oktavius, A. K. *et al.* Fully-Conformable Porous Polyethylene Nanofilm Sweat Sensor for Sports Fatigue. *IEEE Sens J* **21**, 8861–8867 (2021).

28. Wang, X. *et al.* Principles and mechanisms of regeneration in the mouse model for wound induced hair follicle neogenesis. *Regeneration* **2**, 169–181 (2015).

29. Takeo, M., Lee, W. & Ito, M. Wound healing and skin regeneration. *Cold Spring Harb Perspect Med* **5**, (2015).

30. Weng, T. *et al.* Regeneration of skin appendages and nerves: current status and further challenges. *J Transl Med* **18**, 53 (2020).

31. Stoica, A. E., Grumezescu, A. M., Hermenean, A. O., Andronescu, E. & Vasile, B. S. Scar-Free Healing: Current Concepts and Future Perspectives. *Nanomaterials* **10**, 2179 (2020).

32. Guerrero-Juarez, C. F. *et al.* Single-cell analysis reveals fibroblast heterogeneity and myeloid-derived adipocyte progenitors in murine skin wounds. *Nat Commun* **10**, (2019).

33. Harn, H. I.-C. *et al.* Topological Distribution of Wound Stiffness Modulates Wound-Induced Hair Follicle Neogenesis. *Pharmaceutics* **14**, (2022).

34. Grierson, I., Joseph, J., Miller, M. & Day, J. E. Wound repair: The fibroblast and the inhibition of scar formation. *Eye (Basingstoke)* **2**, 135–148 (1988).

35. Younesi, F. S., Miller, A. E., Barker, T. H., Rossi, F. M. V. & Hinz, B. Fibroblast and myofibroblast activation in normal tissue repair and fibrosis. *Nat Rev Mol Cell Biol* **25**, 617–638 (2024).

36. Lebonvallet, N., Laverdet, B., Misery, L., Desmoulière, A. & Girard, D. New insights into the roles of myofibroblasts and innervation during skin healing and innovative therapies to improve scar innervation. *Exp Dermatol* **27**, 950–958 (2018).

37. Kasuya, A., Ito, T. & Tokura, Y. M2 macrophages promote wound-induced hair neogenesis. *J Dermatol Sci* **91**, 250–255 (2018).

38. Nguyen, J. K., Austin, E., Huang, A., Mamalis, A. & Jagdeo, J. The IL-4/IL-13 axis in skin fibrosis and scarring: mechanistic concepts and therapeutic targets. *Arch Dermatol Res* **312**, 81–92 (2020).

39. Bhogal, R. K., Stoica, C. M., McGaha, T. L. & Bona, C. A. Molecular Aspects of Regulation of Collagen Gene Expression in Fibrosis. *J Clin Immunol* **25**, 592–603 (2005).

40. Liu, Y. *et al.* TGF-β1 promotes scar fibroblasts proliferation and transdifferentiation via up-regulating MicroRNA-21. *Sci Rep* **6**, (2016).

41. Lee, J. S. *et al.* Influence of Transforming Growth Factors beta 1 and beta 3 in the Scar Formation Process. *Journal of Craniofacial Surgery* **34**, 904–909 (2023).

42. Wang, L., Tu, L., Zhang, J., Xu, K. & Qian, W. Stellate cell activation and imbalanced expression of TGF-β 1/TGF-β 3 in acute autoimmune liver lesions induced by ConA in mice. *Biomed Res Int* **2017**, (2017).

43. Wang, M., Zhao, J., Li, J., Meng, M. & Zhu, M. Insights into the role of adipose-derived stem cells and secretome: potential biology and clinical applications in hypertrophic scarring. *Stem Cell Res Ther* **15**, 137 (2024).

44. Thitisomboon, W., Gu, Q., Weng, L.-T. & Gao, P. Surface confinement induced amorphization of polyethylene oxide in high-performance porous polyethylene films. *Polymer (Guildf)* **217**, 123449 (2021).